

Finish Code	Description	Colour	Saltspray	Hex Chrome Free Y/N
1	Phosphate Plus Two Coats Olive Drab Paint	Olive Drab	96	Y
178	Zinc Nickel Plating (Sharperise)	Metallic Silver	720	Y
27	Plain - Production Oils	Self Colour	0	Y
205	Mechanical Zinc Plate, 0.0003" Min, Trivalent Chrome Topcoat	Metallic Silver	120	Y
207	Zinc Mechanical Plating Per Gm Spec.Gmw3044 8mk240/120x		240	Y
213	Zinc Electroplate (0.00015") & Trivalent Chrome Topcoat	Clear Silver To Metallic Gray Bluish Bright	32	Y
214	Mechanical Zinc Plate, Plain, No Topcoat, 0.0002" Min. Thick	Silver To Metallic Grey	48	Y
239	Type 302 Stainless Steel Material	Self Colour	N/A	Y
3B	Zinc Electroplate .00015 Minimum	Silver	24	Y
360	Phosphate Plus Two Coats Of Black Paint	Black	96	Y
374	Zinc Phosphated And Coated With 2 Coats Of Molykote 7409	Black	96	Y
375	Zinc Phosphate Plus Two Coats Of Molykote 96	Black		Y
3252	Two Coats Of Water Based Zinc Coating (Geomet) Plus Two Coats Of Geoblack 137	Black	720	Y
3255	Two Coats Of Water Base Zinc Coating (Geomet)	Silver	240	Y
3963	Two Coats Of Water Base Zinc Coating (Geomet) Plus One Coat Geomet "P" Clear Sealer	Silver	480	Y
3965	Two Coats Of Water Base Zinc Coating (Geomet) Plus One Coat Geomet "MI" Clear Sealer	Silver	720	Y
3966	Two Coats Of Water Base Zinc Coating (Geomet) Plus One Coat Plus "L" Blue Sealer	Blue	720	Y
4	Phosphate Plus One Coat Special Oil Dip	Grey/Black	72	Y
47	Zinc Phosphate Plus Zinc Rich Epoxy Resin Coating Plus A Clear Organic Top	Grey	480	Y
403	Plated Copper Coating (2.5 Micrometers Min.) Plus Lubricated Coating Per Ford Spec. S403	Copper	0	Y
434	Phosphate Plus One Coat Black Paint	Black	24	Y
440	Phosphate Plus Two Coats Of Black Paint Plus One Coat Special Oil Dip	Black	168	Y
442	Zinc Phosphate Plus Black Organic Protective Coating	Black	120	Y
449	Zinc Phosphate Pretreatment Plus A Zinc-Rich Basecoat Plus An Integrally Lubricated Aluminum- Rich Topcoat Per Ford Spec. Wss-M21p37-A1	Silver	840	Y
450	Zinc Phosphate Pretreatment Plus A Zinc-Rich Basecoat Plus An Integrally Lubricated Aluminum-Rich Topcoat	Silver	840	Y
455	Zinc Phosphate Pretreatment Plus A Zinc-Rich Basecoat Plus An Integrally Lubricated Aluminum-Rich Topcoat	Silver	240	Y
461	"Magni 594", - Zinc-Rich Basecoat, Inorganic, With Alumimum- Rich, Friction-Modified Topcoat; 12.5 Microns Minimum Coat	Metallic Silver/Grey	720	Y
4252	Two Coats Of Water Based Zinc Coating(Geomet) Plus Two Coats Of Geoblack 147.	Black	480	Y
4965	Two Coats Of Water Base Zinc Coating (Geomet) Plus One Coat "Plus L" Clear Sealer	Silver	720	Y
598	Zinc Mechanical Plate .0003 Min. Thick	Silver To Metallic Grey	56	Y
64	Dry Phosphate Only	Grey	0	Y
65	Mechanical Copper Flash	Copper	0	Y
67	Phosphate Plus Two Coats Of Aluminum Paint.	Metallic Silver	96	Y
600	Zinc Mechanical Plate .00015 Minimum.	Silver	0	Y
613	Mechanical Zinc Plate, Trivalent Chromate, Leached And Sealed, Integral Torque Control Lubricant Per Ford Spec S437m (Wss-M21p17-B4)	Silver	240	Y
619	Mechanical Zinc Plate, 0.0004", W/ Trivalent Chrome Topcoat With Black Dye Plus Sealer	Black	96	Y
620	Mechanical Zinc Plate, 0.0005" Min, Trivalent Chrome Topcoat	Clear To Bluish Metallic Silver	120	Y
79	Zinc Phosphate Treatment Plus Zinc Rich Inorganic Resin Coating And Aluminum Rich Organic Topcoat	Grey	480	Y
748	Black Oxide With Oil Coat On Stainless Steel Type 302	Black	N/A	Y
904	Mechanical Tin-Zinc Plating, 0.0004" Min Trivalent Chrome Topcoat, Hypersealed	Silvery/Dull White	250	Y
GML	Geomet, Two Basecoats With Plus MI Topcoat	Metallic Grey	720	Y
GP	Geomet, Two Basecoats With Plus Topcoat	Metallic Grey	480	Y
GPB	Geomet, Two Basecoats With Geoblack 147 Topcoat	Black	720	Y
LZA	Zinc-Rich Basecoat, W/ Alumium Rich Lubricated Organic Topcoat, Magni 511	Silver	480	Y
PG	Phosphate, Oiled (12%-15%)	Grey	72	Y
SOG	Mechanical Zinc Plate, Plain, No Topcoat, 0.0002" Min. Thick	Silver	48	Y
SOH	Mechanical Zinc Plate, Plain, No Topcoat, 0.0003" Min. Thick	Silver	56	Y
STHH	Mechanical Zinc Plate, Trivalent Chromate, Leached And Sealed, Integral Torque Control Lubricant	Silver White	240	Y
ZOL	"Magni 565", - Zinc-Rich Basecoat With Aluminum-Rich Lubricated Organic Topcoat.	Silver	1000	Y