

Stainless Steel 17-4 PH for ProX™ 200 and 300 Direct Metal Printers

General purpose metal powder with high strength, good corrosion resistance and thermal properties.



Technical Data

Chemical Composition

Stainless Steel 17-4 PH

Element	% of weight
Fe	Balance
Cr	15 - 17.5
Ni	3 - 5
Cu	3 - 5
Si	< 1.0
Mn	< 1.0
Nb	0.15 - 0.45

Mechanical Properties¹

	Condition	As-built ²	After post heat treatment ³
Ultimate Tensile Strength, MPa	ASTM E8	1100 ± 50	1300 ± 50
Yield Strength, MPa	ASTM E8	620 ± 30	1100 ± 50
Elongation at break, %	ASTM E8	16 ± 2.0	10 ± 2.0
Hardness		300 ± 20 HV5	400 ± 20 HV5
Density		approx. 100%	

¹ Parts built on a ProX 200 Direct Metal Production Printer

² As-built refers to the state of components built on the ProX 200 Direct Metal Printer before any post processing except removal from the build platform

³ Different post heat treatments might be applied for this type of alloy


Applications

Industrial grade prototypes, production parts or spare parts for:

- Aerospace
- Chemical and petrochemical industry
- Energy sector
- Surgical instruments
- High-wear components
- General metalworking

Features

- Outstanding combination of high strength and good corrosion resistance
- Excellent mechanical properties at elevated temperatures – up to 300 °C
- High hardness
- Good thermal properties



3DSYSTEMS®

UK

Tel: +44 1442 282 600
info@3dsystems-europe.com

USA

Tel: +1 803.326.3900
moreinfo@3dsystems.com

**Germany, Scandinavia,
Eastern Europe, Middle East**
Tel: +49 6151 357 0
info@3dsystems-europe.com

Asia-Pacific
Melbourne Tel: +61 3 9819 4422
Sydney Tel: +61 2 9516 5571
3dprinters.asiapac@3dsystems.com

MANUFACTURING THE FUTURE