



# CRESTAKYD<sup>®</sup> 30-5071

## Short oil alkyd

**INTRODUCTION** CRESTAKYD 30-5071 exhibits rapid drying characteristics and fast hardness development. It has very good weather resistance, excellent film build and attractive gloss.

### CHARACTERISTICS

|                                                      |                      |
|------------------------------------------------------|----------------------|
| Solids content                                       | 70±1,5%              |
| Oil type                                             | Castor Oil           |
| Oil content                                          | 45%                  |
| Solvent                                              | Xylene               |
| Acid value (base resin)                              | max. 20 mg KOH/g     |
| OH-number (base resin)                               | ~95 mg KOH/g (2,8 %) |
| Efflux time, 50% NVC in Xylene,<br>DIN cup 4, @ 20°C | 140-220 s            |
| Gardner Colour                                       | max. 8               |

**APPLICATION** CRESTAKYD 30-5071 can be used for NC finishes, acid hardening finishes and in combination with low reactivity melamine resins for industrial stoving enamels and automotive finishes.

**PACKAGING** CRESTAKYD 30-5071 can be supplied in drums, road-tankers and in containers..

**STORAGE** The resin should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 0°C and 30°C. Exposure to direct sunlight should be avoided

**HEALTH & SAFETY** Please see separate material safety data sheet.

Issue No. 2



CROATIA , 10000 ZAGREB, Radnička cesta 173i.

tel.: +385 1 2406-440

fax: +385 1 2404-573; +385 1 2404-926

e-mail: [info@scottbader.hr](mailto:info@scottbader.hr)

