



Product overview

TEXICRYL® 13-605 is a pure acrylic copolymer emulsion designed for use in a broad range of formulations requiring low VOC, low water uptake and excellent resistance to water blanching.

Characteristics (Not to be taken as a specification)	
Solids content	50%
Viscosity at 25°C (Brookfield RVT, Spindle 4, 100 rpm)	450 mPa s
pH	8.5
Minimum film formation temperature*	11°C
Glass transition temperature	15°C

*Determined by metal bar with temperature gradient

Application

TEXICRYL® 13-605 was designed for use in low / zero VOC interior and exterior coating systems. It also shows excellent scrub resistance and good water blanching resistance.

Packaging and storage

TEXICRYL® 13-605 is supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL® 13-605 should be stored in the original containers in a dry place at temperatures between 5°C and 30°C. Protect from freezing

Health and safety

Please see separate material safety data sheet.

© 2021 Scott Bader Company Limited, April 2025, Issue No. 2

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.