



Product overview

TEXICRYL[®] 13-972 is an APEO free modified styrene acrylic emulsion.

Characteristics (Not to be taken as a specification)	
Solids content	50%
Viscosity at 25°C (Brookfield RVT, Spindle 3, 50 rpm)	450 mPa s
pH	8.5
Minimum film formation temperature*	8°C
Glass transition temperature	13°C

*Determined by metal bar with temperature gradient

Application

TEXICRYL[®] 13-972 is used in high performance flexible exterior coatings..

Packaging and storage

TEXICRYL[®] 13-972 maybe supplied in drums or IBC's (please check with your local representative).

Bulk deliveries are by road tanker.

TEXICRYL[®] 13-972 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

Health and safety

Please see separate material safety data sheet.

© 2021 Scott Bader Company Limited, March 2020, Issue No. 1

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.