




## AMACO® CLAY SLIPS COMPARISON CHART

Type	Seal	Packaging	Color	Suggested Firing Temperature			Recommended Glazes	Shrinkage	Absorption
				Bisque	Glaze	Alternate			
No. 1 Porcelain		Gallons	White	Cone 04 1971°F 1077°C	Cone 5 2205°F 1207°C	None	Cone 5	Cone 5 11.75%	Cone 5 0%
15-S Earthenware		Gallons	White	Cone 04 1971°F 1077°C	Cone 05 1911°F 1044°C	Cone 06-02 1855°-2052°F 1013°-1122°C	Cone 05	Cone 05 6%	Cone 05 14.6%
67-S Earthenware		Gallons	Red	Cone 04 1971°F 1077°C	Cone 05 1911°F 1044°C	Cone 06-02 1855°-2052°F 1013°-1122°C	Cone 05	Cone 05 7%	Cone 05 12.5%