

**Prestige Carpets bvba**  
**Dhr. Dirk Santens**  
**Klein Frankrijkstraat 14**  
**9600 RONSE**

**Your notice of**  
05-03-2015

**Your reference**

**Date**  
16-03-2015

## **Analysis Report 15.01078.13**

Required tests :

**BS 4790 (1987)**

**Determination of the flammability of textile floor coverings -  
Hot metal nut method**

Identification number	Information given by the client	Date of receipt
T1504112	Hog Heaven Linkable Mats	05-03-2015

Kristina De Temmerman

Order responsible

This report runs to 2 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.

The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

---

**VAT BE 0459.218.289**  
CENTEXBEL-GENT  
Technologiepark 7  
BE-9052 Zwijnaarde  
Tel. + 32 9 220 41 51 • Fax + 32 9 220 49 55  
gent@centexbel.be

**Fin. Acc. 210-0472965-45**

---

**IBAN BE44 2100 4729 6545**  
CENTEXBEL-VERVIERS  
Avenue du Parc 38  
BE-4650 Herve (Chaineux)  
Tel. + 32 87 32 24 30 Fax + 32 87 34 05 18  
chaineux@centexbel.be

**Reference: T1504112 - Hog Heaven Linkable Mats**

**Determination of the flammability of textile floor coverings - Hot metal nut method**

Date of ending the test 10-03-2015

Standard used BS 4790 (1987)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test results relate only to the behaviour of the test specimen after application of a small source of ignition; they shall not be used as a means of assessing how the product will contribute to an established fire.

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Method of mounting test specimens Method 1 - loose-laid

Substrate Non combustible substrate: fibre cement board

	Flame time or time to reach the clamping ring (s)	Afterglow (s)	Radius affected area use-surface (mm)	Radius affected area under-surface (mm)
#1	158	0	15	0
#2	30	0	15	0
#3	178	0	15	0

Assessment and labelling in accordance with BS 5287

Radius of affected area Information to be given on the label

Up to 35 mm "When tested according to BS 4790 has a low radius of effects of ignition"

>35 mm to 75 mm "When tested according to BS 4790 has a medium radius of effects of ignition"

>75 mm "When tested according to BS 4790 has a high radius of effects of ignition"

**Conclusion "low radius of effects of ignition"**