



Volume 67, No.15

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	26	88.8	65.1	65,863	26	91.2	70.4	191,334
Corpus Christi	25	84.6	68.6	88,953	42	88.1	71.9	1,345,485
Dumas	32	63.6	33.5	107,048	33	51.8	23.0	632,209
Florence	39	90.7	79.1	116,453	39	88.1	73.7	344,970
Lamesa	22	89.4	57.8	41,372	22	87.8	58.2	84,255
Lubbock	50	86.3	67.6	204,519	50	85.5	64.7	508,105
Macon	66	89.9	75.4	192,895	66	82.6	65.6	648,815
Memphis	65	86.2	61.0	318,928	65	82.0	58.2	1,349,815
Rayville	12	73.3	48.2	29,268	16	68.6	45.8	201,932
Visalia	11	86.8	66.9	10,418	15	87.0	63.6	50,806
United States	348	85.0	64.2	1,175,717	374	80.7	60.0	5,357,726
AMERICAN PIMA								
Visalia	12			29,611	12			94,094
United States	12			29,611	12			94,094
United States all cotton	359			1,205,328	383			5,451,820

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 13, 2025

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	55.2	57.4	10.2	14.6	0.5	1.3	0.3	0.6	67.3	67.0
	3	7.9	8.7	10.1	14.3	0.8	1.0	0.2	0.3	6.7	7.2
	4	0.2	0.3	1.3	1.4	*	*	*	*	0.2	0.4
	5	*	*	*	*	*	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	63.3 66.4	21.7 30.3	1.4 2.3	0.5 0.8	74.3 74.6				
31	1 - 2	4.2	3.6	5.6	5.0	1.9	2.8	4.9	7.7	0.1	0.1
	3	5.3	8.3	24.3	22.5	17.1	18.5	21.9	24.9	0.3	0.4
	4	1.1	1.8	9.4	9.3	10.2	8.5	5.5	5.6	0.2	0.3
	5	0.1	0.1	0.9	1.0	0.6	0.5	0.3	0.2	-	*
	6	*	*	*	*	*	*	*	*	-	*
	7	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	10.8 13.8	40.1 37.8	29.8 30.4	32.6 38.3	0.6 0.9				
41	1 - 2	0.1	*	1.3	0.5	0.6	0.7	2.6	3.2	*	*
	3	0.2	0.2	5.9	4.8	17.6	19.5	31.2	29.4	*	*
	4	0.4	0.2	5.4	4.9	32.6	29.8	24.8	21.2	-	-
	5	0.2	0.1	1.1	1.2	9.2	7.5	3.4	2.9	-	-
	6	*	*	0.1	0.1	0.4	0.5	0.2	0.2	-	-
	7	-	*	*	*	*	*	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	0.9 0.5	13.7 11.6	60.4 58.0	62.2 56.9	* *				
51	1 - 2	-	-	*	*	*	*	*	0.1	-	-
	3	-	-	0.1	0.1	1.1	1.1	0.8	0.6	-	-
	4	-	-	0.1	0.4	3.7	2.8	1.6	1.0	-	-
	5	-	-	0.1	0.1	1.6	1.3	0.8	0.5	-	-
	6	-	*	*	*	0.1	0.2	0.2	0.1	-	-
	7	-	-	*	*	*	*	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- *	0.4 0.7	6.6 5.4	3.4 2.4	- -				
61	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	*	*	*	*	-	-
	4	-	-	-	*	0.1	*	*	*	-	-
	5	-	-	-	-	*	*	-	-	-	-
	6	-	-	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- *	0.1 *	* *	- -				
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- -	- -	- *	- -				
12 & 22	1 - 2	12.6	10.7	2.8	4.4	-	*	*	*	16.8	16.0
	3	3.2	3.0	3.6	3.9	*	*	-	*	4.3	4.7
	4	0.4	0.3	1.1	1.0	-	-	-	*	0.3	0.5
	5	0.1	*	0.1	0.1	-	-	-	-	-	*
	6	*	*	*	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	16.2 14.1	7.6 9.3	* *	* *	21.4 21.1				
32	1 - 2	1.0	0.5	0.6	0.7	-	*	*	*	0.2	0.3
	3	1.8	1.4	4.9	2.8	0.1	0.2	0.1	0.2	0.6	0.7
	4	0.6	0.6	4.1	2.4	0.1	0.1	0.1	0.1	0.2	0.2
	5	0.1	0.1	0.7	0.6	*	*	*	*	*	*
	6	*	*	*	*	-	*	-	-	*	*
	7	-	-	*	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	3.6 2.6	10.4 6.4	0.2 0.3	0.2 0.3	1.0 1.2				
42	1 - 2	*	*	0.1	0.1	*	*	*	*	-	*
	3	0.2	0.1	1.7	0.8	0.2	0.6	0.3	0.4	*	*
	4	0.7	0.3	1.9	1.1	0.6	1.4	0.5	0.5	-	*
	5	0.9	0.3	0.5	0.6	0.2	0.6	0.1	0.1	-	-
	6	0.2	0.1	0.1	0.1	*	0.1	*	*	-	-
	7	*	*	*	*	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	2.0 0.8	4.4 2.8	1.0 2.7	1.0 1.1	* *				

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 13, 2025

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	*	*	-	*	-	*	-	-
	3	-	-	0.1	*	0.1	0.1	*	*	-	-
	4	*	*	0.2	0.1	0.2	0.3	*	*	-	-
	5	-	-	0.1	0.1	*	0.2	*	*	-	-
	6	*	*	*	*	*	0.1	*	*	-	-
	7	-	*	*	*	*	*	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	0.4	0.2	0.4	0.7	0.1	0.1	-	-
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	*	*	*	*	-	-	-	-
	4	-	-	-	*	*	*	*	*	-	-
	5	-	-	-	*	*	*	*	*	-	-
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	*	*	-	-	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
Total	----	-	*	*	*	*	*	*	*	-	-
13 & 23	1 - 2	1.1	0.6	0.1	0.1	-	-	-	-	1.3	0.9
	3	0.4	0.3	0.2	0.1	-	-	-	-	0.7	0.5
	4	0.1	*	*	*	-	-	-	-	*	*
	5	*	*	*	*	-	-	-	-	-	*
	6	-	-	*	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.6	1.0	0.3	0.3	-	-	-	-	2.0	1.4
33	1 - 2	0.1	0.1	*	*	-	*	*	*	0.1	0.2
	3	0.5	0.3	0.2	0.1	*	*	*	*	0.3	0.3
	4	0.3	0.2	0.2	0.1	-	-	*	*	0.1	0.1
	5	*	*	*	*	-	-	*	*	*	*
	6	*	*	*	*	-	-	-	-	*	*
	7	-	*	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.0	0.6	0.5	0.3	*	*	*	*	0.5	0.5
43	1 - 2	-	*	*	*	-	-	-	*	-	-
	3	*	*	0.1	0.1	*	*	*	*	*	*
	4	*	*	0.3	0.1	0.1	*	*	*	-	-
	5	0.1	0.1	0.1	0.1	*	*	*	*	-	-
	6	*	*	*	*	*	*	*	*	-	-
	7	*	*	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	0.1	0.5	0.3	0.1	*	*	*	*	*
53	1 - 2	-	-	-	*	-	*	-	-	-	-
	3	*	*	-	*	*	*	*	*	-	-
	4	-	-	*	*	*	*	*	*	-	-
	5	*	*	*	*	*	*	-	*	-	-
	6	-	-	*	*	-	*	-	*	-	-
	7	-	-	*	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	*	*	*	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	*	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	*	*	-	*	-	-	-	-
24 - 54	1 - 8	0.3	0.2	*	*	-	-	*	*	0.3	0.2
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	*	-	-	-	-	*	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-
30		*	*	-	-	-	-	-	-	*	*
31		*	0.3	-	-	*	*	-	-	0.1	0.1
32		0.6	1.1	0.1	*	*	*	-	-	2.1	1.8
33		4.8	3.4	0.4	0.1	0.1	0.2	0.1	0.1	8.7	8.1
34		10.2	7.7	2.0	0.7	1.2	1.6	0.7	0.8	19.8	19.5
35		17.0	14.9	6.6	3.5	7.3	9.5	5.7	6.0	25.1	22.3
36		19.3	17.6	19.0	15.3	22.5	27.8	23.5	23.5	19.8	19.0
37		23.8	21.1	43.5	46.6	44.6	42.7	51.6	52.8	20.1	20.7
38		14.5	14.3	23.7	25.5	17.9	14.5	15.1	14.1	3.9	6.7
39		7.7	11.3	4.4	7.6	5.3	3.1	3.1	2.5	0.3	1.6
40 & Longer		2.1	8.3	0.3	0.7	1.0	0.5	0.3	0.2	0.1	0.1
Average Staple		36.30	36.72	36.93	37.18	36.90	36.70	36.85	36.81	35.29	35.46
Average Length		1.13	1.15	1.15	1.16	1.15	1.14	1.15	1.15	1.10	1.11

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 13, 2025

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 11 & 21	1 - 2	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
	3	68.4	64.4	1.1	2.1	0.2	0.6	3.5	4.3	28.2	35.1
	4	14.4	15.8	0.4	0.7	0.3	0.6	1.9	2.8	11.8	16.3
	5	0.7	0.9	*	*	*	*	0.1	0.2	1.4	1.1
	6	*	*	-	-	-	*	-	*	*	*
	7	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	83.5 81.2	1.5 2.8	0.6 1.2	5.6 7.3	41.5 52.6				
31	1 - 2	2.2	1.4	9.1	9.8	3.2	3.0	11.8	8.6	7.5	6.6
	3	3.7	2.7	20.4	20.1	15.2	13.3	33.6	35.1	10.8	9.1
	4	1.8	1.5	3.0	2.3	4.1	3.5	12.6	12.6	4.8	4.2
	5	0.4	0.3	0.1	0.1	0.2	0.1	1.1	0.9	1.4	1.2
	6	*	*	*	*	*	*	*	*	0.3	0.2
	7	*	*	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	8.2 6.0	32.6 32.3	22.8 19.9	59.2 57.2	24.8 21.3				
41	1 - 2	*	*	6.4	5.7	2.7	2.5	1.4	0.6	2.2	1.4
	3	*	*	35.3	35.0	30.9	30.4	12.5	10.7	6.7	2.4
	4	*	*	16.7	15.8	28.0	27.8	14.0	14.9	3.8	1.0
	5	*	*	2.3	1.6	5.0	5.4	4.8	3.7	6.9	1.6
	6	*	*	0.1	0.1	0.5	0.4	0.6	0.2	2.2	0.5
	7	*	*	*	*	*	*	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	0.1 0.1	60.8 58.2	67.1 66.5	33.3 30.1	21.8 7.0				
51	1 - 2	-	-	0.2	0.1	0.1	0.1	-	*	0.2	*
	3	-	*	1.8	1.5	2.0	1.4	*	*	2.2	0.5
	4	-	*	1.7	1.5	3.1	2.5	*	0.3	0.3	0.1
	5	*	*	0.4	0.3	1.2	1.1	*	0.3	0.1	0.1
	6	-	-	*	*	0.3	0.2	*	*	*	*
	7	-	-	*	*	0.1	*	-	-	-	-
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	* *	4.1 3.5	6.7 5.3	0.1 0.7	2.8 0.8				
61	1 - 2	-	-	*	*	-	*	-	-	-	-
	3	-	-	*	*	*	*	*	*	-	-
	4	-	-	*	*	*	*	-	*	-	-
	5	-	-	*	*	*	*	-	-	-	-
	6	-	-	-	*	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	* *	* *	* *	* *	- -	- -	- -	- -
71	1 - 2	-	-	-	-	-	*	-	-	-	-
	3	-	-	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- -	- *	- -	- -	- -	- -	- -	- -
12 & 22	1 - 2	4.1	6.2	-	0.1	*	*	-	0.1	2.6	8.9
	3	2.1	4.1	-	*	*	*	*	0.1	1.1	3.4
	4	0.2	0.5	-	*	-	*	0.1	0.1	*	0.4
	5	*	*	-	-	-	*	-	*	-	*
	6	-	*	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	6.4 10.7	- 0.1	* *	0.1 0.3	3.8 12.7				
32	1 - 2	0.2	0.1	*	0.1	*	0.1	0.1	0.1	0.5	0.5
	3	0.6	0.5	0.1	0.4	0.2	0.3	0.2	0.5	0.2	1.1
	4	0.3	0.3	0.1	0.1	0.1	0.1	0.3	0.8	0.3	1.2
	5	0.1	0.1	*	*	*	*	0.1	0.5	0.6	0.7
	6	*	*	*	*	*	*	*	0.1	0.2	0.1
	7	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	1.1 1.0	0.2 0.6	0.2 0.4	0.7 1.9	1.9 3.6				
42	1 - 2	*	*	*	0.1	*	0.3	*	*	0.1	*
	3	*	*	0.3	1.2	0.7	2.5	0.4	0.3	0.6	0.2
	4	0.1	*	0.3	0.8	0.8	1.9	0.3	1.2	0.7	0.2
	5	0.1	*	0.1	0.1	0.3	0.5	0.2	0.6	1.3	0.5
	6	*	*	*	*	*	0.1	*	0.3	0.7	0.2
	7	*	*	-	*	*	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	0.3 0.1	0.7 2.3	1.8 5.2	1.0 2.4	3.4 1.1				

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 13, 2025

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	*	*	*	*	-	-	-	-
	3	-	-	*	0.1	0.2	0.5	*	*	*	*
	4	*	*	*	0.1	0.3	0.7	*	0.1	*	*
	5	-	*	*	*	0.1	0.3	*	0.1	-	-
	6	*	*	*	*	*	*	*	*	-	*
	7	-	-	-	-	*	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	0.1	0.2	0.6	1.5	0.1	0.1	0.1	*
62	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	*	*	-	-	-	-
	4	-	-	-	*	*	*	-	-	-	-
	5	-	-	-	*	*	*	-	-	-	-
	6	-	-	-	*	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	*	*	-	-	-	-
13 & 23	1 - 2	0.1	0.1	-	-	-	-	-	-	-	0.5
	3	0.1	0.4	-	-	-	-	-	-	*	0.1
	4	*	0.1	-	-	-	-	-	-	-	0.1
	5	*	*	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	0.6	-	-	-	-	-	-	*	0.8
33	1 - 2	*	*	*	*	*	*	-	-	*	*
	3	0.1	0.1	*	*	*	*	*	*	*	0.1
	4	0.1	0.1	*	*	*	*	-	*	-	0.1
	5	*	*	-	-	-	-	-	*	-	*
	6	*	*	-	-	-	-	-	*	-	*
	7	*	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	0.3	*	*	*	*	*	*	*	0.2
43	1 - 2	*	*	*	*	*	*	-	*	-	-
	3	*	*	*	*	*	*	*	*	-	*
	4	*	*	*	*	*	*	-	*	*	*
	5	*	*	*	*	*	*	-	*	*	*
	6	*	*	*	*	-	-	-	*	*	*
	7	*	*	-	-	*	*	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
Total	----	0.1	*	*	*	*	*	*	*	*	0.1
53	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	*	*	-	-	-	-
	4	-	-	*	*	*	*	-	-	-	-
	5	-	-	-	-	*	*	-	-	-	-
	6	*	*	-	*	-	*	-	*	-	-
	7	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	*	*	-	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-
24 - 54	1 - 8	*	*	-	*	-	-	-	-	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	-	-	-	-	-	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-
30		*	*	*	*	-	-	-	-	-	-
31		0.1	0.1	*	*	-	*	-	-	-	*
32		0.4	0.7	*	*	*	*	*	*	-	*
33		2.4	3.1	0.4	0.5	0.1	0.1	0.2	0.2	*	*
34		7.4	9.3	3.7	3.9	0.6	1.1	1.8	1.8	0.3	0.4
35		15.6	17.3	14.0	14.7	3.7	4.8	11.8	12.2	1.9	2.0
36		23.5	23.6	31.4	31.7	14.2	16.7	23.3	30.0	11.8	12.8
37		31.6	29.1	36.3	36.3	49.6	48.3	35.2	39.2	29.3	42.9
38		13.1	11.8	11.0	9.8	26.3	24.3	22.5	12.6	33.0	28.4
39		4.7	4.1	2.8	2.6	4.6	4.2	4.9	3.7	21.2	12.5
40 & Longer		1.1	1.0	0.4	0.3	0.9	0.6	0.2	0.3	2.4	0.8
Average Staple		36.37	36.21	36.45	36.41	37.15	37.05	36.79	36.60	37.73	37.39
Average Length		1.13	1.13	1.14	1.13	1.16	1.16	1.15	1.14	1.18	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 13, 2025

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	2.5	1.8	0.5	0.5	*	*	1.8	1.0	1.4	2.3
Bark - Level 2	*	*	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	0.1	0.9	0.3	*	0.1	0.1	0.1	1.0	0.7
Grass - Level 2	-	-	-	*	-	-	-	-	-	-
Prep - Level 1	-	-	*	*	-	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.1	0.1	*	*	0.4	2.2	0.4	0.5	*	0.1
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	*	-	-	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	*	*	*	*	-	*	-	*	*	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	0.1	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	-	*	-	*	-	-	-	-	*	*
23	*	*	-	*	-	-	-	-	*	0.1
24	0.1	0.2	-	*	-	*	-	-	0.4	0.3
25	0.3	0.4	0.1	*	*	*	-	-	1.6	1.0
26	1.7	1.4	0.5	0.2	*	0.1	0.2	0.2	3.0	3.1
27	5.3	4.5	2.3	1.2	0.3	0.6	1.7	1.5	7.9	7.3
28	11.2	10.6	5.6	5.3	2.5	4.4	9.1	8.1	15.5	12.2
29	19.0	16.1	13.9	15.4	13.1	16.5	29.0	26.6	18.3	16.9
30	18.0	16.6	21.2	22.1	28.7	28.7	33.1	34.3	20.5	19.6
31	15.4	14.3	19.0	17.3	27.2	26.1	17.8	19.2	15.3	17.1
32	11.3	11.0	15.3	12.0	18.6	15.3	6.9	7.3	9.8	12.1
33	8.5	9.6	12.5	11.3	7.3	5.9	1.9	2.2	5.0	5.7
34	5.1	8.0	7.3	9.7	1.9	2.0	0.3	0.5	1.7	2.9
35	3.4	4.7	1.9	4.0	0.4	0.3	*	0.1	0.6	1.1
36	0.6	1.8	0.4	1.1	*	*	*	*	0.2	0.5
37	0.2	0.7	0.1	0.2	-	-	-	-	*	0.1
38	0.1	0.2	*	*	-	-	-	-	-	*
39	*	*	*	*	-	-	-	-	-	-
40 & Above	-	*	-	-	-	-	-	-	-	-
Average	30.85	31.24	31.39	31.57	31.22	31.02	30.30	30.40	30.11	30.41
Mike										
2.4 & Below	-	*	-	-	-	-	-	-	-	-
2.5	*	*	*	*	-	-	-	-	*	*
2.6	*	*	*	*	-	-	-	-	*	*
2.7	*	*	*	*	-	-	-	-	*	*
2.8	*	*	*	*	-	-	-	-	0.1	*
2.9	*	*	*	*	-	-	-	-	0.1	0.2
3.0	0.1	*	*	0.1	-	-	*	*	0.2	0.5
3.1	0.2	0.1	0.1	0.1	-	-	*	*	0.3	0.7
3.2	0.5	0.4	0.1	0.3	-	*	*	*	0.3	0.5
3.3	0.7	0.4	0.5	0.6	*	*	0.1	0.1	0.4	0.8
3.4	1.0	0.7	0.8	0.9	*	*	0.2	0.1	0.6	1.3
3.5	1.6	1.3	1.8	1.2	*	*	0.3	0.3	1.7	2.0
3.6	2.8	2.3	2.9	1.8	0.1	*	0.7	0.5	2.8	3.0
3.7	3.9	3.7	2.8	2.6	0.1	*	1.3	1.1	3.8	3.7
3.8	4.6	4.9	4.1	4.3	0.1	0.1	1.7	1.6	5.1	4.3
3.9	5.5	6.6	5.7	6.6	0.2	0.1	2.7	2.7	5.7	5.5
4.0	7.7	8.3	7.5	9.1	0.4	0.2	4.3	3.8	5.7	6.3
4.1	9.5	10.1	9.8	10.9	0.8	0.4	5.7	5.2	7.7	8.0
4.2	10.9	11.1	12.4	12.7	1.2	0.7	9.3	7.9	7.9	9.0
4.3	12.2	11.0	13.6	12.7	2.7	1.4	12.6	10.4	10.5	10.0
4.4	11.4	10.5	12.3	11.3	4.0	2.5	14.7	12.0	11.8	11.1
4.5	10.4	9.4	11.1	8.9	5.9	3.7	12.4	11.6	10.3	10.1
4.6	7.1	7.8	7.0	6.1	8.8	6.2	10.1	10.8	9.7	9.2
4.7	5.3	5.6	2.9	3.8	10.9	9.5	8.1	9.5	7.6	6.7
4.8	3.2	3.3	1.9	2.5	14.0	14.0	6.1	7.7	4.5	4.1
4.9	0.8	1.4	1.4	1.4	16.2	16.8	4.1	5.7	2.0	1.6
5.0	0.3	0.6	0.7	0.8	15.4	17.2	2.7	4.2	0.7	0.6
5.1	0.3	0.3	0.3	0.5	10.6	12.9	1.5	2.5	0.4	0.3
5.2	0.1	0.1	0.1	0.3	5.1	7.9	0.7	1.3	*	0.2
5.3	*	*	*	0.2	2.2	3.9	0.4	0.6	*	0.2
5.4	-	-	*	0.1	1.0	1.5	0.1	0.3	*	*
5.5 & Above	-	*	*	0.3	0.5	0.7	*	*	-	-
Average	4.22	4.23	4.23	4.23	4.82	4.89	4.43	4.49	4.27	4.24

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 13, 2025

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	3.8	4.9	0.2	0.4	*	*	0.9	0.3	-	*
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	*	0.1	*	*	0.2	0.1	1.0	0.8
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	-	-	*	-	-	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	0.2	0.3	0.2	0.2	0.1	3.9	0.2	0.1
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	*	*	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	0.1	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	*	*	-	-	-	*	-	-	-	-
23	*	*	-	*	-	*	-	-	-	-
24	0.1	0.1	*	*	*	*	-	-	*	*
25	0.2	0.2	*	*	*	*	*	*	*	*
26	0.6	0.6	0.1	0.1	*	*	0.1	0.2	0.3	0.1
27	1.6	1.9	0.9	0.8	0.2	0.2	0.8	2.0	1.4	0.4
28	4.8	5.1	5.3	4.8	1.9	1.8	6.2	6.3	2.9	3.1
29	10.3	11.4	16.5	15.2	12.3	11.7	19.8	19.1	8.6	11.3
30	16.3	17.0	26.0	26.5	36.0	34.3	34.6	30.2	16.9	19.2
31	20.0	19.4	23.2	24.7	32.8	33.8	18.3	18.8	15.5	20.2
32	17.7	17.0	15.0	15.2	11.6	13.2	7.0	12.5	7.1	9.5
33	13.0	12.4	7.9	7.5	3.9	3.9	2.5	6.0	11.4	7.6
34	8.7	8.5	3.4	3.5	1.1	1.0	5.7	3.0	23.5	9.8
35	4.3	4.1	1.3	1.3	0.1	0.1	4.5	1.6	8.2	10.2
36	1.9	1.7	0.4	0.4	*	*	0.4	0.2	3.6	6.4
37	0.5	0.5	0.1	0.1	*	*	*	*	0.5	1.9
38	0.2	0.2	*	*	*	*	-	*	*	0.1
39	*	*	-	*	-	-	-	-	*	*
40 & Above	-	-	-	-	-	-	-	-	*	0.1
Average	31.84	31.74	31.15	31.18	31.01	31.06	30.97	30.89	32.48	32.31
Mike										
2.4 & Below	-	-	-	-	-	-	-	-	-	-
2.5	*	*	-	-	-	-	-	-	-	-
2.6	*	*	*	*	-	-	-	-	-	-
2.7	0.1	*	*	*	-	-	-	*	-	*
2.8	0.1	0.1	*	*	-	-	-	*	-	-
2.9	0.3	0.1	*	*	-	-	-	*	-	*
3.0	0.4	0.3	*	*	-	-	*	*	*	0.1
3.1	0.7	0.5	*	*	-	-	*	*	0.2	0.2
3.2	1.1	0.8	0.1	*	-	-	0.1	*	0.3	0.2
3.3	1.7	1.3	0.1	0.1	*	*	0.1	*	0.3	0.1
3.4	2.5	1.9	0.3	0.2	0.1	*	0.1	0.1	0.2	0.3
3.5	3.3	2.6	0.5	0.3	0.1	0.1	0.3	0.1	0.2	0.6
3.6	4.2	3.3	0.8	0.5	0.2	0.2	0.3	0.2	0.9	0.9
3.7	4.8	3.9	1.2	0.9	0.3	0.3	0.7	0.3	2.1	2.2
3.8	6.1	4.8	1.8	1.3	0.6	0.6	0.4	0.5	1.7	4.1
3.9	6.7	5.8	3.3	2.1	0.9	1.0	0.7	1.2	2.0	5.1
4.0	6.8	6.3	4.9	3.2	1.4	1.5	1.3	2.1	3.1	4.5
4.1	7.0	6.8	6.8	5.0	2.6	2.4	1.8	3.7	2.3	5.6
4.2	7.9	7.8	8.7	6.6	4.0	3.7	4.2	4.5	5.8	7.4
4.3	8.0	8.9	10.1	8.2	5.6	5.3	7.3	5.0	7.7	8.1
4.4	8.7	9.5	10.3	9.5	8.2	7.9	8.0	6.1	9.8	10.1
4.5	8.3	9.4	10.4	10.4	10.2	10.7	7.7	8.1	12.8	10.3
4.6	7.3	8.5	9.9	10.5	13.7	14.1	8.0	9.3	16.0	10.5
4.7	5.6	6.7	9.5	10.3	16.0	15.6	9.9	10.4	12.8	9.6
4.8	3.7	4.4	7.6	8.9	15.3	14.5	12.8	12.0	12.3	8.4
4.9	2.3	2.6	5.6	7.5	10.2	10.6	12.7	11.0	5.9	5.4
5.0	1.0	1.4	3.7	6.0	6.1	6.5	9.2	9.0	2.4	2.8
5.1	0.6	0.9	2.4	4.2	2.8	3.1	7.7	8.0	1.2	1.8
5.2	0.3	0.5	1.0	2.4	1.3	1.2	4.5	4.7	*	1.0
5.3	0.2	0.3	0.7	1.3	0.4	0.5	1.4	2.3	*	0.3
5.4	0.1	0.2	0.3	0.5	0.1	0.1	0.8	1.0	-	0.2
5.5 & Above	0.2	0.2	0.1	0.2	*	0.1	*	0.3	-	0.2
Average	4.16	4.24	4.45	4.56	4.63	4.63	4.69	4.69	4.49	4.42

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 13, 2025

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	-	*	-	-	-	-	-	-	-	-
2.5 - 2.6	*	*	*	*	-	-	-	-	*	*
2.7 - 2.9	0.1	0.1	0.1	0.1	-	-	-	-	0.2	0.2
3.0 - 3.2	0.8	0.6	0.3	0.5	-	*	*	*	0.8	1.7
3.3 - 3.4	1.7	1.2	1.3	1.4	*	*	0.3	0.2	1.0	2.1
3.5 - 3.6	4.4	3.5	4.6	3.0	0.1	0.1	1.0	0.8	4.5	5.0
3.7 - 4.2	42.1	44.8	42.3	46.1	2.7	1.6	25.0	22.4	35.8	36.7
4.3 - 4.9	50.3	48.9	50.1	46.7	62.5	54.1	68.1	67.7	56.4	52.9
5.0 - 5.2	0.7	0.9	1.2	1.6	31.1	38.1	5.0	8.0	1.2	1.1
5.3 & Above	*	*	*	0.6	3.7	6.1	0.6	1.0	*	0.2
Average	4.22	4.23	4.23	4.23	4.82	4.89	4.43	4.49	4.27	4.24
Leaf										
1 - 2	74.4	73.1	20.7	25.5	3.0	4.9	7.8	11.6	85.8	84.5
3	19.6	22.3	51.2	49.6	37.1	40.9	54.6	55.8	13.2	13.9
4	4.0	3.7	24.0	20.7	47.6	43.1	32.6	28.5	1.0	1.5
5	1.6	0.7	3.8	3.8	11.7	10.2	4.6	3.8	*	0.1
6	0.4	0.2	0.3	0.4	0.6	0.9	0.4	0.3	*	*
7	*	*	*	*	*	*	*	*	-	-
8	*	*	-	*	-	-	-	-	-	-
Average	2.07	2.04	3.10	3.02	3.70	3.61	3.35	3.25	1.71	1.76
HVI Trash 1/										
00	*	0.1	-	*	-	-	-	-	0.8	1.0
01	42.1	41.8	4.3	5.4	0.2	0.4	0.7	1.1	60.4	56.8
02	34.6	33.4	20.9	22.8	3.6	5.7	9.8	13.3	27.2	29.0
03	12.8	13.9	28.2	27.9	14.2	16.9	25.4	27.0	8.3	9.0
04	4.6	6.0	23.2	20.2	23.6	24.2	27.1	26.0	2.3	2.8
05	2.1	2.5	13.1	11.9	22.4	21.6	19.0	17.0	0.6	0.9
06	1.2	1.1	5.9	6.4	16.3	14.6	10.2	8.8	0.2	0.3
07	0.8	0.5	2.6	3.1	10.3	8.5	4.7	4.0	0.1	0.1
08	0.6	0.3	1.2	1.4	5.3	4.3	2.0	1.7	*	*
09	0.4	0.2	0.5	0.6	2.5	2.1	0.8	0.7	*	*
10	0.3	0.1	0.2	0.2	1.0	1.0	0.3	0.3	-	*
11	0.2	0.1	0.1	0.1	0.4	0.4	0.1	0.1	*	*
12	0.1	*	*	*	0.1	0.2	*	*	-	*
13	0.1	*	*	*	*	0.1	*	*	-	*
14	*	*	*	*	*	*	*	*	*	*
15	*	*	-	*	*	*	*	*	-	-
16	*	*	*	*	-	-	*	*	-	-
17	*	*	*	*	-	-	*	*	-	-
18 & Above	*	*	*	*	-	-	*	*	-	-
Average	0.21	0.20	0.36	0.36	0.51	0.49	0.42	0.40	0.15	0.16
UNIFORMITY 2/										
74 & Below	*	*	*	*	-	-	-	-	*	*
75	0.1	0.1	*	*	-	-	-	-	*	0.1
76	0.3	0.2	*	*	*	*	-	-	0.3	0.3
77	0.9	0.6	0.3	0.1	*	*	-	-	2.2	2.2
78	3.7	2.8	1.9	0.6	0.2	0.2	0.4	0.4	10.3	11.0
79	16.1	11.7	9.9	3.4	0.8	1.1	2.6	2.5	27.4	26.8
80	32.6	28.0	24.9	12.7	6.3	7.7	12.1	11.4	35.5	32.0
81	28.9	28.3	32.5	29.9	27.9	29.2	29.6	28.9	21.3	21.4
82	11.9	16.4	21.7	31.6	40.7	38.2	38.2	37.4	2.8	4.9
83	4.6	7.8	7.5	16.6	20.3	19.1	15.3	17.3	0.3	1.3
84	0.8	3.9	1.1	4.6	3.8	4.4	1.6	2.0	*	*
85 & Above	*	0.3	0.1	0.5	0.1	0.1	0.1	0.1	-	-
Average	80.86	81.26	81.34	82.04	82.30	82.25	82.01	82.06	80.16	80.23
Tenderable 3/	88.8	91.2	84.6	88.1	63.6	51.8	90.7	88.1	89.4	87.8
SAMPLES CLASSED										
Week	65,863		88,953		107,048		116,453		41,372	
Season	191,334		1,345,485		632,209		344,970		84,255	

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 13, 2025

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	*	*	*	*	-	-	-	-	-	-
2.7 - 2.9	0.5	0.2	*	*	-	-	-	*	-	0.1
3.0 - 3.2	2.2	1.5	0.1	*	-	-	0.1	*	0.5	0.5
3.3 - 3.4	4.3	3.2	0.4	0.3	0.1	*	0.2	0.1	0.6	0.4
3.5 - 3.6	7.6	5.9	1.2	0.8	0.3	0.2	0.6	0.3	1.1	1.5
3.7 - 4.2	39.2	35.5	26.8	19.0	9.8	9.5	9.1	12.4	17.0	28.8
4.3 - 4.9	43.8	50.0	63.2	65.2	79.3	78.8	66.4	61.8	77.3	62.4
5.0 - 5.2	1.9	2.8	7.1	12.7	10.1	10.8	21.5	21.7	3.5	5.7
5.3 & Above	0.5	0.7	1.1	2.0	0.5	0.6	2.2	3.6	*	0.7
Average	4.16	4.24	4.45	4.56	4.63	4.63	4.69	4.69	4.49	4.42
Leaf										
1 - 2	74.9	72.3	16.9	18.0	6.3	6.5	16.8	13.6	41.2	53.0
3	21.0	23.6	58.3	59.0	49.4	48.8	48.8	49.5	33.6	33.2
4	3.3	3.5	21.7	20.6	36.5	36.3	27.5	30.2	11.4	8.5
5	0.7	0.6	2.9	2.2	6.9	7.4	6.3	6.0	10.3	4.2
6	0.1	0.1	0.2	0.1	0.8	0.8	0.7	0.7	3.5	1.1
7	*	*	*	*	0.2	0.1	-	-	-	-
8	*	*	-	*	-	-	-	-	-	-
Average	2.07	2.12	3.11	3.07	3.47	3.47	3.25	3.30	2.97	2.58
HVI Trash 1/										
00	*	*	-	-	-	*	-	-	-	*
01	40.1	36.2	1.9	2.2	0.5	0.7	2.2	1.7	13.0	20.0
02	38.9	40.3	21.5	22.4	7.9	7.9	17.5	14.6	35.4	40.2
03	12.9	14.5	32.2	32.4	21.9	21.6	23.9	24.4	18.7	20.3
04	4.5	5.2	22.4	22.4	26.1	26.1	22.3	23.6	10.2	8.2
05	1.8	2.1	11.8	11.5	19.9	19.9	15.5	16.5	5.2	3.8
06	0.9	0.9	5.7	5.2	11.8	11.8	9.4	9.6	4.1	2.5
07	0.4	0.4	2.6	2.3	6.2	6.3	5.0	5.0	4.7	2.0
08	0.2	0.2	1.1	0.9	2.9	3.0	2.4	2.4	3.8	1.5
09	0.1	0.1	0.5	0.4	1.5	1.5	1.1	1.2	2.5	0.9
10	0.1	0.1	0.2	0.2	0.7	0.7	0.4	0.5	1.4	0.5
11	*	*	0.1	0.1	0.4	0.3	0.2	0.3	0.7	0.2
12	*	*	*	*	0.2	0.1	0.1	0.1	0.2	0.1
13	*	*	*	*	0.1	0.1	*	*	*	*
14	*	*	*	*	0.1	*	*	*	-	*
15	*	*	*	*	*	*	-	-	-	-
16	*	*	*	*	-	-	-	-	-	-
17	*	*	*	*	-	-	-	-	-	-
18 & Above	*	*	*	*	-	-	-	-	-	-
Average	0.20	0.20	0.36	0.35	0.45	0.45	0.40	0.41	0.34	0.27
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	-	-	-	-
75	*	*	-	*	-	-	-	-	-	-
76	0.1	0.1	*	*	*	*	-	-	-	*
77	0.6	0.7	0.1	0.1	*	*	-	-	*	*
78	2.8	3.1	0.6	0.6	0.1	0.1	0.1	0.2	0.4	0.3
79	11.1	10.8	4.6	4.4	0.6	0.6	1.3	1.8	1.3	1.9
80	27.5	25.9	18.9	19.6	4.0	4.3	11.1	10.5	11.2	9.9
81	34.9	34.0	37.3	37.7	21.0	21.2	27.9	32.8	30.6	29.3
82	18.5	20.1	29.4	28.0	46.5	45.3	39.4	38.2	43.3	43.0
83	3.8	4.6	8.0	8.1	24.8	26.0	18.2	14.8	12.4	13.4
84	0.5	0.6	1.1	1.3	2.7	2.4	2.0	1.7	0.6	2.1
85 & Above	0.1	0.1	0.1	0.1	0.2	0.2	*	0.1	0.2	0.1
Average	81.12	81.16	81.64	81.63	82.44	82.44	82.14	82.03	82.01	82.06
Tenderable 3/	86.3	85.5	89.9	82.6	86.2	82.0	73.3	68.6	86.8	87.0
SAMPLES CLASSED										
Week	204,519		192,895		318,928		29,268		10,418	
Season		508,105		648,815		1,349,815		201,932		50,806

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 13, 2025

Color Grade	Leaf	VISALIA			Quality Designation	VISALIA	
		Week	Season			Week	Season
01	1	7.0	10.2		MIKE	-	-
	2	7.1	9.4		2.4 & Below	-	-
	3	0.1	0.1		2.5 - 2.6	-	-
	4	-	-		2.7 - 2.9	0.1	*
	5	-	-		3.0 - 3.2	0.9	0.4
	6	-	-		3.3 - 3.4	2.3	1.9
	7	-	-		3.5 - 3.6	9.9	9.8
Total -----		14.2	19.8		3.7 - 4.2	84.4	86.2
02	1	5.8	6.6		4.3 - 4.9	2.4	1.6
	2	30.5	36.0		5.0 - 5.2	-	-
	3	5.8	7.3		5.3 & Above	-	-
	4	*	0.1		Average	3.88	3.87
	5	-	*		ALL RANGE MIKE		
	6	-	-		2.4 & Below	-	-
	7	-	-		2.5	-	-
Total -----		42.0	50.0		2.6	-	-
03	1	0.6	0.3		2.7	*	*
	2	11.3	9.3		2.8	*	*
	3	21.2	14.9		2.9	0.1	*
	4	2.1	1.8		3.0	*	*
	5	*	*		3.1	0.4	0.1
	6	-	-		3.2	0.5	0.3
	7	-	-		3.3	0.8	0.7
Total -----		35.1	26.3		3.4	1.6	1.2
04	1	*	*		3.5	3.4	3.2
	2	0.7	0.3		3.6	6.6	6.7
	3	5.0	2.2		3.7	8.7	10.5
	4	2.3	1.1		3.8	18.0	17.8
	5	0.1	0.1		3.9	21.9	23.5
	6	*	*		4.0	18.4	20.7
	7	-	-		4.1	11.2	9.6
Total -----		8.1	3.7		4.2	6.2	4.1
05	1	*	*		4.3	2.0	1.1
	2	*	*		4.4	0.3	0.3
	3	0.2	0.1		4.5	*	0.1
	4	0.3	0.1		4.6	*	*
	5	*	*		4.7	-	*
	6	*	*		4.8	*	*
	7	-	-		4.9	-	*
Total -----		0.5	0.2		5.0	-	-
06	1	-	-		5.1	-	-
	2	-	-		5.2	-	-
	3	*	*		5.3 & Above	-	-
	4	*	*		Average	3.88	3.87
	5	-	-		STRENGTH 1/		
	6	-	-		36 & Below	2.9	2.6
	7	-	-		37	6.2	7.0
Total -----		*	*		38	4.0	4.3
07	1	-	-		39	1.3	1.3
	2	-	-		40	1.8	2.3
	3	-	-		41	7.0	7.3
	4	-	-		42	14.3	13.4
	5	-	-		43	18.6	19.8
	6	-	-		44	19.3	21.0
	7	-	-		45	17.3	14.3
Total -----		-	-		46	5.8	5.5
STAPLE	44 & Shorter	2.2	3.4		47	1.4	1.0
	46	13.0	12.1		48 & Above	0.3	0.2
	48	41.2	49.5		Average	43.05	42.94
	50	43.1	34.4		UNIFORMITY		
	52 & Longer	0.6	0.6		83 & Below	1.6	1.0
Average Staple		48.54	48.33		84	11.8	12.8
Average Length		1.41	1.41		85	26.9	31.4
EXTRANEEOUS MATTER	Bark	*	*		86	53.1	49.1
	Grass	*	0.2		87	6.2	5.3
	Spindle Twist	*	*		88 & Above	0.4	0.4
	Preparation	-	*		Average	85.97	85.91
	All Other	*	*		Samples Classed		
					Week	29,611	
					Season		94,094

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.