Quality of Cotton Classed by State for the week ending - 11/20/2025

Agricultural Marketing Service
Cotton Market News

November 21, 2025

Volume 27, No.16

State	Week Gins	Week Tenderable (%)	Week Eligible (%)	Week Bales	Season Gins	Season Tenderable (%)	Season Eligible (%)	Season Bales
				UPLAND				
AL	21	90.5	77.2	63,984	21	88.5	74.7	296,421
AR	24	69.1	41.6	140,285	26	69.4	40.9	910,193
AZ	7	88.8	61.1	6,747	7	89.4	57.6	33,680
CA	3	95.9	82.0	4,055	6	86.0	73.3	27,384
FL	4	95.6	83.4	10,954	4	88.3	70.0	44,444
GA	52	91.8	75.9	177,625	52	84.3	67.4	664,975
KS	2	45.7	31.7	5,697	2	54.1	41.5	10,911
LA	10	78.4	50.3	22,902	14	71.1	46.6	189,705
MO	16	86.7	63.0	72,487	16	84.4	61.5	401,457
MS	29	67.8	42.5	80,004	30	62.5	34.9	611,237
NC	26	91.0	79.6	87,487	26	88.9	74.5	327,234
NM	-	-	-	-	-	-	-	-
OK	10	94.7	83.8	30,941	10	95.3	82.3	130,388
SC	10	85.8	70.1	25,453	10	81.1	62.8	78,522
TN	17	89.6	70.0	39,075	17	82.1	63.0	301,195
TX	116	86.0	65.5	371,619	139	86.9	68.2	2,416,705
VA	4	97.7	95.2	20,908	4	97.2	93.6	73,062
United States	**351**	**84.6**	**65.2**	**1,160,223**	**385**	**81.4**	**60.9**	**6,517,850**
				AMERICAN PIMA				
AZ	2			783	2			1,447
CA	8			21,814	8			111,373
NM*	-			-	-			-
TX	3			4,592	3			7,076
United States	14			31,039	14			125,133
United States all cotton	**364**			**1,191,262**	**395**			**6,642,983**

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

MP CN100

Source: USDA AMS Cotton and Tobacco Market News
Memphis, Tennessee | 901-384-3016 |cottonmn@ams.usda.gov
https://www.ams.usda.gov/market-news/cotton
https://mymarketnews.ams.usda.govcottonmn@ams.usda.gov

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 20, 2025

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	2.7	2.7	0.1	0.2	11.9	35.2	15.9	26.1	0.1	2.9	0.5	1.1
	3	1.0	1.3	*	0.1	0.7	10.5	8.5	18.8	*	0.6	0.2	0.4
	4	*	*	*	*	0.3	0.9	0.2	1.2	-	*	*	*
	5	-	-	-	-	0.1	*	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***3.8***	***4.0***	***0.1***	***0.3***	***12.9***	***46.5***	***24.6***	***46.0***	***0.1***	***3.5***	***0.6***	***1.5***
31	1 - 2	11.6	10.9	1.4	1.1	39.2	10.5	2.1	9.3	2.1	4.7	7.7	8.6
	3	31.3	32.9	9.3	9.6	11.4	6.3	20.5	14.7	10.1	14.9	20.4	18.9
	4	7.9	8.0	3.7	3.4	1.8	1.7	17.7	8.6	1.6	2.6	3.1	2.2
	5	0.5	0.5	0.1	0.1	0.7	0.4	0.6	2.0	*	*	0.1	*
	6	*	*	*	*	*	0.1	-	0.3	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***51.4***	***52.3***	***14.6***	***14.3***	***53.0***	***19.0***	***40.9***	***34.8***	***13.8***	***22.2***	***31.3***	***29.8***
41	1 - 2	2.4	2.3	0.6	0.7	11.8	3.1	4.7	2.2	3.5	3.9	6.1	6.3
	3	21.9	19.9	25.2	26.4	13.0	4.5	2.9	2.6	41.5	37.9	36.8	37.5
	4	15.6	15.4	33.2	36.7	3.8	1.2	14.0	3.5	34.4	24.1	17.2	16.1
	5	2.9	2.7	6.9	8.5	0.2	0.1	8.7	4.3	4.0	2.8	2.1	1.6
	6	0.2	0.2	0.6	0.7	*	*	0.4	1.0	0.1	0.1	0.1	0.1
	7	*	*	*	*	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***43.0***	***40.4***	***66.5***	***73.0***	***28.8***	***8.9***	***30.7***	***13.6***	***83.5***	***68.7***	***62.3***	***61.6***
51	1 - 2	0.1	0.1	*	*	0.5	0.2	0.7	0.1	*	*	0.2	0.2
	3	0.4	0.3	3.2	1.4	0.9	0.8	0.5	0.1	0.7	0.9	2.3	1.9
	4	0.4	0.3	7.8	3.4	0.2	0.1	-	0.1	1.3	1.4	1.8	1.7
	5	0.1	0.1	3.6	1.9	-	0.2	-	*	0.2	0.4	0.5	0.4
	6	*	*	0.8	0.4	-	0.1	-	*	0.1	*	0.1	*
	7	*	*	0.1	0.1	-	-	-	-	*	*	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	*
Total	**----**	***1.0***	***0.8***	***15.4***	***7.3***	***1.6***	***1.4***	***1.2***	***0.3***	***2.4***	***2.8***	***4.7***	***4.3***
61	1 - 2	-	-	-	*	-	-	-	-	-	-	*	*
	3	-	-	*	*	-	-	-	-	-	-	*	*
	4	-	*	*	*	-	-	-	-	-	*	*	*
	5	-	*	*	*	-	-	-	-	-	*	*	*
	6	-	-	*	*	-	-	-	-	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***-***	*******	*******	*******	***-***	***-***	***-***	***-***	***-***	*******	*******	*******
71	1 - 2	-	-	-	*	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***-***	***-***	***-***	*******	***-***	***-***	***-***	***-***	***-***	***-***	***-***	***-***
12 & 22	1 - 2	-	0.2	-	*	1.0	13.4	-	0.1	-	*	-	*
	3	*	*	-	*	0.6	5.0	*	0.3	-	*	-	*
	4	-	*	-	*	0.1	0.5	-	0.1	-	-	-	*
	5	-	-	-	*	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	*******	***0.2***	***-***	*******	***1.8***	***19.0***	*******	***0.5***	***-***	*******	***-***	*******
32	1 - 2	*	0.1	*	*	*	0.5	-	0.1	-	0.1	*	0.1
	3	0.2	0.5	0.1	0.1	0.6	1.5	0.1	0.3	-	0.4	0.3	0.4
	4	0.1	0.1	*	0.1	0.8	1.0	0.5	1.3	-	0.1	0.2	0.1
	5	*	*	*	*	-	0.3	0.1	1.0	-	-	*	*
	6	*	*	-	*	-	0.1	-	0.1	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***0.4***	***0.8***	***0.1***	***0.2***	***1.4***	***3.3***	***0.8***	***2.9***	***-***	***0.6***	***0.5***	***0.5***
42	1 - 2	*	*	*	*	*	*	0.2	*	-	0.1	*	0.1
	3	0.1	0.6	0.8	1.1	0.1	0.2	0.6	0.2	*	1.3	0.3	1.1
	4	0.2	0.6	0.9	1.7	0.1	0.1	0.2	0.3	*	0.6	0.2	0.7
	5	0.1	0.2	0.2	0.7	-	0.1	0.1	0.8	*	*	*	0.1
	6	*	*	*	0.1	-	*	-	0.4	-	-	*	*
	7	-	*	-	*	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***0.4***	***1.5***	***1.9***	***3.6***	***0.2***	***0.4***	***1.0***	***1.7***	***0.1***	***2.1***	***0.5***	***2.0***

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 20, 2025

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	*	*	-	-	0.1	*	-	-	-	*
	3	*	*	0.2	0.2	-	*	0.2	*	*	*	*	0.1
	4	*	*	0.6	0.6	*	*	0.1	*	*	*	0.1	0.1
	5	*	*	0.2	0.3	-	-	-	-	*	*	*	0.1
	6	-	*	*	0.1	-	*	-	-	*	*	*	*
	7	-	-	*	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	*****	*****	***1.1***	***1.2***	*****	*****	***0.4***	***0.1***	***0.1***	***0.1***	***0.1***	***0.2***
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	*	*	-	-	-	-	-	-	-	-
	4	-	-	*	*	-	-	-	-	-	-	*	*
	5	-	-	*	*	-	-	-	-	*	*	-	*
	6	-	-	*	*	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	**-**	**-**	*****	*****	**-**	**-**	**-**	**-**	*****	*****	*****	*****
13 & 23	1 - 2	-	-	-	-	-	0.8	-	-	-	-	-	-
	3	-	-	-	-	*	0.2	-	-	-	-	-	-
	4	-	-	-	-	-	0.1	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	**-**	**-**	**-**	**-**	*****	***1.1***	**-**	**-**	**-**	**-**	**-**	**-**
33	1 - 2	-	*	-	-	-	*	-	*	-	-	-	*
	3	*	*	-	*	0.2	0.2	*	*	-	-	*	*
	4	*	*	*	*	0.1	0.1	*	*	-	-	*	*
	5	-	-	-	-	-	*	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	*****	*****	*****	*****	***0.3***	***0.3***	*****	*****	**-**	**-**	*****	*****
43	1 - 2	-	-	-	-	-	-	-	-	-	-	-	*
	3	*	*	*	*	-	*	0.1	*	-	*	*	*
	4	-	*	*	*	-	*	-	*	-	-	*	*
	5	*	*	*	*	-	*	-	*	-	-	-	*
	6	-	-	*	*	-	*	-	*	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	*****	*****	***0.1***	*****	**-**	***0.1***	***0.1***	*****	**-**	*****	*****	*****
53	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	*	*	*	*	-	-	0.1	*	-	*	-	-
	4	-	-	*	*	-	-	*	*	-	-	-	*
	5	-	*	*	*	-	-	-	-	-	-	-	-
	6	-	*	*	*	-	-	-	-	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	*****	*****	*****	*****	**-**	**-**	***0.1***	*****	**-**	*****	**-**	*****
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	**-**	**-**	**-**	**-**	**-**	**-**	**-**	**-**	**-**	**-**	**-**	**-**
24 - 54	1 - 8	-	-	-	-	-	*	-	-	-	-	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	*	*
31		-	*	-	*	-	*	-	-	*	*	*	*
32		0.1	*	*	*	-	*	-	-	-	-	0.3	0.1
33		0.6	0.3	*	0.1	0.1	0.1	-	*	0.3	0.2	1.2	0.7
34		4.1	2.8	0.3	0.3	3.2	1.2	-	*	2.9	1.7	5.3	4.6
35		11.9	10.8	2.2	2.7	13.0	4.5	0.5	1.0	12.3	10.8	17.2	16.4
36		22.7	23.8	12.8	14.6	26.0	16.3	7.9	10.6	33.3	34.7	32.1	32.8
37		44.7	43.2	50.0	52.9	36.7	46.6	10.4	32.9	40.6	40.0	31.1	33.3
38		13.1	15.0	29.1	24.9	15.2	25.0	19.9	28.7	5.9	9.4	10.1	9.2
39		2.4	3.4	5.1	4.2	5.2	6.1	43.6	23.4	3.6	2.7	2.4	2.5
40 & Longer		0.5	0.7	0.5	0.4	0.4	0.3	17.7	3.4	1.1	0.4	0.3	0.3
Average Staple		***36.58***	***36.69***	***37.23***	***37.13***	***36.65***	***37.09***	***38.52***	***37.73***	***36.48***	***36.54***	***36.28***	***36.32***
Average Length		***1.14***	***1.14***	***1.16***	***1.16***	***1.14***	***1.16***	***1.20***	***1.18***	***1.14***	***1.14***	***1.13***	***1.13***

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 20, 2025

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	8.7	13.3	2.0	4.6	*	*	0.6	2.3	0.1	0.5	-	-
	3	0.5	4.7	1.8	2.6	*	*	0.8	2.0	0.1	0.3	-	-
	4	-	0.4	*	*	-	-	*	*	-	*	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***9.3***	***18.4***	***3.8***	***7.3***	*******	*******	***1.5***	***4.3***	***0.3***	***0.8***	***-***	***-***
31	1 - 2	2.3	2.9	8.3	9.4	1.2	1.2	1.9	3.7	4.6	7.4	-	-
	3	11.6	15.8	36.8	37.9	9.3	8.8	13.6	21.2	14.3	22.5	-	-
	4	5.0	6.3	8.2	12.5	1.6	1.8	6.0	8.8	4.4	5.4	-	-
	5	1.1	0.7	0.4	0.8	*	*	0.3	0.6	0.2	0.3	-	-
	6	*	*	*	*	*	*	*	*	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***19.9***	***25.7***	***53.7***	***60.6***	***12.1***	***11.8***	***21.8***	***34.4***	***23.6***	***35.5***	***-***	***-***
41	1 - 2	*	*	0.9	0.5	2.9	2.2	0.7	0.9	4.2	3.7	-	-
	3	2.8	1.9	12.7	9.8	41.0	38.6	17.3	18.2	33.9	30.4	-	-
	4	6.4	4.4	20.3	15.2	23.4	29.5	34.2	24.9	26.4	21.6	-	-
	5	6.8	4.1	6.4	4.3	3.1	3.7	10.9	6.9	5.7	3.6	-	-
	6	2.0	1.2	0.5	0.3	0.1	0.1	0.9	0.5	0.5	0.3	-	-
	7	0.1	0.1	-	-	-	*	*	*	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***18.3***	***11.7***	***40.8***	***30.0***	***70.4***	***74.2***	***64.0***	***51.4***	***70.6***	***59.5***	***-***	***-***
51	1 - 2	-	-	*	*	0.1	*	*	*	0.1	0.1	-	-
	3	-	-	*	*	4.9	2.3	0.9	1.1	1.0	0.6	-	-
	4	-	-	0.4	0.4	7.7	4.0	5.5	3.2	2.4	1.2	-	-
	5	*	*	0.5	0.3	2.2	1.0	2.8	1.5	1.2	0.7	-	-
	6	*	*	0.2	*	0.1	0.1	0.2	0.2	0.2	0.2	-	-
	7	*	*	-	-	-	*	*	*	*	*	-	-
	8	0.1	0.1	-	-	-	-	-	-	-	-	-	-
Total	***----***	***0.2***	***0.1***	***1.1***	***0.8***	***14.9***	***7.4***	***9.4***	***6.1***	***4.9***	***2.8***	***-***	***-***
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	*	-	-	-	-
	4	-	-	-	*	*	*	*	*	*	*	-	-
	5	-	-	-	-	*	*	*	*	*	*	-	-
	6	-	-	-	-	*	*	-	*	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***-***	***-***	***-***	*******	*******	*******	*******	*******	*******	*******	***-***	***-***
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***-***	***-***	***-***	***-***	***-***	***-***	***-***	***-***	***-***	*******	***-***	***-***
12 & 22	1 - 2	3.5	2.8	*	0.1	-	-	-	*	*	*	-	-
	3	2.7	2.2	-	*	-	-	*	*	-	*	-	-
	4	0.1	0.1	-	-	-	-	*	*	-	*	-	-
	5	-	-	*	*	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***6.3***	***5.1***	*******	***0.1***	***-***	***-***	*******	*******	*******	*******	***-***	***-***
32	1 - 2	0.2	0.3	*	0.1	*	*	*	*	*	*	-	-
	3	2.7	3.0	*	0.3	*	0.1	*	0.2	0.1	0.2	-	-
	4	4.4	3.8	0.1	0.2	*	*	*	0.1	0.1	0.1	-	-
	5	1.3	0.9	-	*	-	*	-	*	*	*	-	-
	6	*	*	-	*	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***8.6***	***7.9***	***0.1***	***0.5***	***0.1***	***0.2***	***0.1***	***0.3***	***0.1***	***0.4***	***-***	***-***
42	1 - 2	0.1	0.2	*	*	*	0.2	*	*	*	*	-	-
	3	2.2	2.1	*	0.2	0.8	1.9	0.2	0.7	0.1	0.4	-	-
	4	7.1	7.4	0.2	0.4	0.7	1.8	1.5	1.3	0.2	0.4	-	-
	5	10.7	10.5	0.1	0.1	0.1	0.4	0.7	0.5	0.1	0.1	-	-
	6	8.2	5.6	-	*	*	*	0.1	0.1	*	*	-	-
	7	2.0	1.1	-	-	-	*	-	*	-	-	-	-
	8	0.1	0.1	-	-	-	-	-	-	-	-	-	-
Total	***----***	***30.4***	***27.0***	***0.4***	***0.7***	***1.6***	***4.3***	***2.5***	***2.6***	***0.4***	***0.9***	***-***	***-***

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 20, 2025

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	-	*	*	-	*	-	*	-	-
	3	-	-	*	*	0.1	0.6	*	0.1	*	*	-	-
	4	-	-	*	*	0.5	0.9	0.1	0.3	*	*	-	-
	5	0.1	*	*	*	0.2	0.3	0.4	0.3	*	*	-	-
	6	0.7	0.4	*	*	*	*	0.1	0.2	*	*	-	-
	7	1.8	0.9	-	-	-	*	-	*	-	*	-	-
	8	0.8	0.4	-	-	-	-	-	-	-	-	-	-
Total	***----***	***3.4***	***1.8***	***0.1***	*******	***0.8***	***2.0***	***0.7***	***0.8***	***0.1***	***0.1***	***-***	***-***
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	-	-	*	*	*	-	*	-	-
	5	-	-	-	-	*	*	*	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***-***	***-***	***-***	***-***	*******	*******	*******	*******	***-***	*******	***-***	***-***
13 & 23	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	0.1	*	-	-	-	-	-	-	-	-	-	-
	4	*	*	-	-	-	-	-	-	*	*	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***0.1***	*******	***-***	***-***	***-***	***-***	***-***	***-***	*******	*******	***-***	***-***
33	1 - 2	*	*	-	-	-	-	-	*	-	*	-	-
	3	0.4	0.2	-	*	-	-	*	*	*	*	-	-
	4	0.4	0.2	-	-	*	*	*	*	*	*	-	-
	5	0.1	*	-	-	-	-	-	-	-	*	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***0.8***	***0.5***	***-***	*******	*******	*******	*******	*******	*******	*******	***-***	***-***
43	1 - 2	-	-	-	*	-	-	-	-	*	*	-	-
	3	-	*	-	*	*	*	*	*	*	*	-	-
	4	0.1	0.1	*	*	*	*	*	*	*	*	-	-
	5	0.4	0.4	*	*	*	*	*	*	*	*	-	-
	6	1.2	0.7	-	-	-	-	*	*	-	*	-	-
	7	0.4	0.2	-	-	-	-	-	-	-	-	-	-
	8	0.1	*	-	-	-	-	-	-	-	-	-	-
Total	***----***	***2.2***	***1.5***	*******	*******	*******	*******	*******	*******	***0.1***	*******	***-***	***-***
53	1 - 2	-	-	-	-	-	-	-	*	-	-	-	-
	3	-	-	-	-	*	*	-	*	-	*	-	-
	4	-	-	-	-	*	*	*	*	*	*	-	-
	5	-	*	-	-	*	*	-	*	-	-	-	-
	6	0.1	*	-	-	*	*	*	*	-	*	-	-
	7	0.1	0.1	-	-	-	-	*	*	-	-	-	-
	8	0.2	0.1	-	-	-	-	-	-	-	-	-	-
Total	***----***	***0.4***	***0.2***	***-***	***-***	*******	*******	*******	*******	*******	*******	***-***	***-***
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***-***	***-***	***-***	***-***	***-***	***-***	***-***	*******	***-***	***-***	***-***	***-***
24 - 54	1 - 8	0.1	0.1	-	-	-	-	-	-	*	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		-	-	-	-	-	-	-	*	-	-	-	-
32		-	-	-	-	-	*	-	*	-	-	-	-
33		*	*	*	0.1	*	*	0.1	0.3	*	0.1	-	-
34		0.6	0.3	0.9	1.2	0.1	0.3	1.0	2.2	1.1	1.0	-	-
35		5.5	3.0	11.5	10.6	1.3	1.8	7.5	11.9	7.8	6.8	-	-
36		9.8	9.2	17.8	27.4	8.5	10.2	23.5	28.0	24.2	22.7	-	-
37		23.0	27.1	51.3	41.8	47.0	49.0	40.0	36.7	48.8	51.2	-	-
38		36.0	39.1	14.5	14.3	35.9	33.6	18.3	14.9	14.9	15.2	-	-
39		21.0	19.0	3.5	4.3	6.9	4.7	7.3	4.7	3.0	2.8	-	-
40 & Longer		4.1	2.3	0.4	0.3	0.3	0.3	2.4	1.3	0.3	0.3	-	-
Average Staple		***37.68***	***37.68***	***36.79***	***36.72***	***37.39***	***37.29***	***36.99***	***36.69***	***36.79***	***36.82***	***-***	***-***
Average Length		***1.18***	***1.18***	***1.15***	***1.15***	***1.17***	***1.17***	***1.15***	***1.14***	***1.15***	***1.15***	***-***	***-***

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 20, 2025

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	51.3	57.6	-	0.3	0.1	0.4	56.5	34.8	0.1	0.2
	3	7.4	9.7	-	0.2	0.1	0.1	14.0	14.0	0.1	0.1
	4	0.3	0.3	*	*	-	*	1.2	1.2	-	*
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	***----***	***59.1***	***67.5***	*******	***0.4***	***0.2***	***0.6***	***71.7***	***49.9***	***0.2***	***0.3***
31	1 - 2	8.2	5.7	1.7	2.1	4.9	7.0	2.2	3.5	5.1	8.5
	3	16.9	14.2	7.7	9.9	14.5	13.9	5.3	14.1	32.2	35.2
	4	3.5	3.0	1.6	2.1	3.3	2.7	2.7	6.0	7.9	7.7
	5	0.3	0.2	0.1	0.1	0.1	0.1	0.5	0.7	0.5	0.3
	6	*	*	-	-	*	*	*	*	*	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	***----***	***28.8***	***23.1***	***11.0***	***14.2***	***22.9***	***23.8***	***10.8***	***24.4***	***45.7***	***51.7***
41	1 - 2	0.2	0.1	3.0	3.1	9.1	8.0	0.4	0.4	2.2	1.8
	3	1.9	0.6	36.4	37.3	38.2	36.8	1.5	3.0	31.0	24.7
	4	1.5	0.6	33.5	31.3	14.8	13.7	0.8	3.0	17.8	18.3
	5	0.5	0.2	5.7	4.4	1.4	1.2	0.4	0.8	2.8	2.6
	6	0.1	*	0.2	0.1	*	0.1	0.1	0.1	0.3	0.1
	7	*	*	-	-	-	*	*	*	*	*
	8	-	-	-	-	-	-	-	*	-	-
Total	***----***	***4.3***	***1.6***	***78.9***	***76.2***	***63.5***	***59.8***	***3.3***	***7.2***	***54.0***	***47.5***
51	1 - 2	-	-	0.3	0.2	0.7	0.2	0.1	*	-	-
	3	*	*	3.5	2.5	6.4	2.4	0.2	0.1	*	*
	4	-	-	4.5	3.4	4.1	2.2	0.1	0.3	*	0.2
	5	-	-	1.3	1.1	0.5	0.5	*	0.1	*	0.1
	6	-	*	0.1	0.1	*	*	*	*	-	*
	7	-	-	-	*	-	*	-	*	-	*
	8	-	-	-	-	-	-	-	-	-	-
Total	***----***	*******	*******	***9.7***	***7.2***	***11.6***	***5.3***	***0.4***	***0.4***	*******	***0.3***
61	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	*	*	-	-	-	-
	4	-	-	-	*	*	*	-	*	-	-
	5	-	-	-	-	*	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	***----***	***-***	***-***	***-***	*******	*******	*******	***-***	*******	***-***	***-***
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	***----***	***-***	***-***	***-***	***-***	***-***	***-***	***-***	***-***	***-***	***-***
12 & 22	1 - 2	2.3	2.7	-	-	-	*	6.9	6.1	-	-
	3	1.4	1.4	-	-	-	*	3.0	3.8	*	*
	4	0.2	0.2	-	-	-	*	0.5	0.7	-	-
	5	*	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	***----***	***3.9***	***4.3***	***-***	***-***	***-***	*******	***10.3***	***10.7***	*******	*******
32	1 - 2	0.3	0.2	-	*	0.1	0.3	0.2	0.5	-	*
	3	1.3	1.3	*	0.1	0.1	0.6	0.8	1.9	*	*
	4	0.6	0.6	*	0.1	*	0.1	0.6	1.5	*	*
	5	0.1	0.1	*	*	-	*	0.2	0.4	-	*
	6	*	*	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	***----***	***2.2***	***2.2***	***0.1***	***0.1***	***0.2***	***0.9***	***1.8***	***4.3***	***0.1***	***0.1***
42	1 - 2	*	*	-	*	0.1	1.0	*	0.1	-	*
	3	0.2	0.1	0.1	0.5	0.8	5.4	0.2	0.5	-	*
	4	0.3	0.1	0.1	0.9	0.3	1.7	0.2	0.7	-	0.1
	5	0.2	0.1	*	0.1	*	0.1	0.1	0.4	*	*
	6	0.1	*	*	*	-	*	0.1	0.1	-	*
	7	*	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	***----***	***0.8***	***0.3***	***0.2***	***1.5***	***1.2***	***8.3***	***0.6***	***1.8***	*******	***0.1***

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 20, 2025

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	*	0.1	*	*	-	-
	3	-	-	*	*	0.2	0.7	*	*	-	-
	4	-	-	*	0.1	0.1	0.5	*	0.1	-	-
	5	-	-	*	*	*	0.1	*	*	-	*
	6	-	*	-	*	-	*	*	*	-	-
	7	*	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	**----**	*****	*****	***0.1***	***0.2***	***0.3***	***1.4***	*****	***0.2***	**-**	*****
62	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	*	*	*	-	-
	4	-	-	-	-	*	*	*	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
Total	**----**	**-**	*****	**-**	**-**	*****	*****	*****	*****	**-**	**-**
13 & 23	1 - 2	0.1	0.1	-	-	-	-	0.4	0.2	-	-
	3	0.2	0.1	-	-	-	-	0.2	0.2	-	-
	4	*	*	-	-	-	-	*	*	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	**----**	***0.3***	***0.2***	**-**	**-**	**-**	**-**	***0.7***	***0.5***	**-**	**-**
33	1 - 2	*	*	-	-	-	*	*	*	-	-
	3	0.2	0.2	*	*	*	*	0.1	0.1	-	*
	4	0.1	0.1	*	*	-	*	0.1	0.1	-	*
	5	*	0.1	-	*	-	-	*	*	*	*
	6	-	*	-	-	-	-	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	**----**	***0.4***	***0.4***	*****	*****	*****	*****	***0.3***	***0.3***	*****	*****
43	1 - 2	*	*	-	*	*	*	*	*	-	-
	3	*	*	*	*	0.1	*	*	*	-	-
	4	*	*	*	*	*	*	*	0.1	-	-
	5	*	0.1	*	*	-	*	*	*	-	-
	6	*	*	-	-	-	-	*	*	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	**----**	***0.1***	***0.2***	*****	***0.1***	***0.1***	*****	***0.1***	***0.2***	**-**	*****
53	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	*	*	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	*	*	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	**----**	**-**	**-**	*****	*****	*****	*****	*****	*****	**-**	**-**
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	**----**	**-**	**-**	**-**	**-**	**-**	**-**	**-**	*****	**-**	**-**
24 - 54	1 - 8	0.1	0.2	*	*	-	-	0.1	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	-	-	-	*	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	*	*	-	-
30		-	-	-	-	-	-	*	*	-	-
31		*	*	-	-	-	-	0.1	0.1	-	-
32		0.1	*	-	-	*	*	0.6	0.4	-	-
33		0.7	0.6	*	*	0.1	0.1	3.1	1.7	*	*
34		2.4	2.7	1.3	0.9	0.9	2.6	9.0	4.9	0.6	0.4
35		6.6	7.9	10.4	7.7	8.5	9.6	16.6	9.8	6.8	4.9
36		11.4	12.8	33.7	33.2	27.5	31.4	23.5	18.9	23.4	20.8
37		25.1	22.9	35.0	43.5	50.2	43.9	29.4	38.4	51.6	58.5
38		18.8	19.0	14.1	11.5	11.9	11.1	12.9	19.2	14.1	13.0
39		20.5	19.0	5.3	2.9	0.8	1.2	3.4	5.8	3.2	2.3
40 & Longer		14.4	15.1	0.2	0.2	*	0.1	1.4	0.8	0.1	0.1
Average Staple		***37.71***	***37.66***	***36.67***	***36.66***	***36.66***	***36.55***	***36.26***	***36.71***	***36.82***	***36.86***
Average Length		***1.18***	***1.18***	***1.14***	***1.14***	***1.14***	***1.14***	***1.13***	***1.15***	***1.15***	***1.15***

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 20, 2025

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	0.1	0.1	*	*	0.8	0.2	0.1	*	0.3	0.3	0.5	0.4
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	*	*	0.1	0.3	0.1	0.2	1.5	0.1	0.1	*	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	-	-	-	-	-	-	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	0.1	0.3	1.5	0.1	0.1	-	-	*	0.2	0.1	0.3
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	*	*	-	-	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	*	*	-	-	-	-	-	-	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	0.1	-	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/												
22 & Below	*	*	-	-	-	-	-	-	-	-	-	-
23	-	-	-	*	-	-	-	-	-	-	*	*
24	*	*	*	*	*	*	-	-	-	-	*	*
25	*	*	*	*	0.4	0.1	-	-	-	-	*	*
26	*	*	*	*	2.9	0.7	-	*	*	*	0.2	0.2
27	0.8	0.3	0.1	0.2	6.2	1.8	-	0.1	0.1	0.1	2.0	1.3
28	7.6	4.0	1.6	2.0	24.3	8.7	0.4	1.0	3.4	2.1	10.3	6.8
29	24.5	18.6	14.3	11.5	30.3	17.2	0.5	6.8	13.0	11.0	21.8	18.0
30	31.3	29.8	39.3	34.3	19.0	22.7	3.6	12.5	27.0	24.8	24.2	26.4
31	21.2	24.7	30.8	34.0	7.2	21.2	3.9	13.8	27.9	27.9	19.6	22.4
32	9.4	13.3	10.8	13.4	2.3	11.0	5.5	5.4	17.0	19.3	11.8	13.4
33	3.7	6.1	2.4	3.6	3.6	9.2	12.2	5.3	7.0	8.5	6.2	6.8
34	1.1	2.3	0.6	0.8	3.2	6.4	27.9	15.0	3.7	5.0	2.6	3.0
35	0.1	0.7	0.2	0.1	0.6	1.0	33.8	22.7	0.8	1.1	0.9	1.1
36	*	0.1	*	*	*	*	11.2	13.5	0.1	0.1	0.3	0.4
37	*	*	*	*	-	*	0.8	3.6	*	*	0.1	0.1
38	*	*	*	*	-	-	*	0.2	-	-	*	*
39	-	-	-	-	-	-	*	0.1	-	-	-	*
40 & Above	-	-	-	-	-	-	*	0.1	-	-	-	-
Average	***30.59***	***31.00***	***30.90***	***31.04***	***29.73***	***31.03***	***34.49***	***33.58***	***31.27***	***31.48***	***30.74***	***30.99***
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-	-	-	-	*
2.7	-	-	-	-	-	-	-	*	-	-	-	*
2.8	-	*	-	-	-	-	-	-	-	-	*	*
2.9	-	*	-	-	-	-	-	0.1	-	-	*	*
3.0	-	*	-	-	-	-	-	0.1	-	-	*	*
3.1	-	*	-	-	-	-	0.4	0.4	*	*	*	*
3.2	*	*	-	*	-	-	-	0.2	*	0.1	*	*
3.3	0.2	0.1	*	*	-	*	*	0.1	-	0.1	0.1	0.1
3.4	0.5	0.3	*	*	-	-	1.0	0.6	0.2	0.1	0.2	0.2
3.5	0.9	0.4	0.1	*	0.3	0.1	2.7	1.3	1.5	0.7	0.4	0.3
3.6	1.0	0.7	*	*	0.8	0.4	3.5	1.9	1.7	0.8	1.0	0.6
3.7	1.8	1.4	0.1	0.1	0.4	1.0	2.5	3.2	1.4	0.8	1.5	1.0
3.8	2.6	2.2	0.1	0.1	0.6	1.0	0.4	6.2	1.1	0.8	2.3	1.6
3.9	3.4	3.4	0.3	0.3	0.1	1.2	0.4	7.4	2.3	1.3	3.2	2.4
4.0	4.6	4.6	0.8	0.5	1.1	2.6	2.2	5.7	2.4	1.9	5.2	3.7
4.1	7.4	6.7	1.1	0.8	3.4	4.8	6.4	6.1	3.1	3.0	7.9	5.7
4.2	10.5	9.0	1.8	1.5	3.6	7.2	4.6	6.1	6.2	5.3	9.9	7.4
4.3	10.1	10.3	3.2	2.8	3.7	7.6	7.5	7.7	13.3	8.7	10.1	8.4
4.4	9.2	10.1	5.2	4.9	9.8	11.4	9.4	8.4	14.7	11.9	10.1	9.5
4.5	9.6	10.5	8.8	7.7	17.9	14.2	14.5	8.2	15.4	14.1	10.1	10.1
4.6	9.8	9.8	10.8	11.5	14.0	14.1	17.1	8.0	12.5	11.4	9.0	10.1
4.7	9.1	8.6	13.7	14.7	12.0	10.3	19.3	11.1	11.8	12.3	8.7	10.0
4.8	6.8	7.1	13.9	16.0	12.4	10.4	7.3	7.0	6.6	9.8	8.3	8.8
4.9	4.6	5.6	13.2	14.3	11.2	7.2	0.9	4.0	2.3	7.4	5.7	7.1
5.0	3.4	3.9	11.9	11.4	7.6	4.0	-	2.2	1.4	5.0	3.2	5.6
5.1	1.8	2.5	7.7	7.0	0.5	1.4	-	1.6	0.7	3.0	1.8	3.7
5.2	1.3	1.5	4.5	3.9	0.2	0.7	-	1.1	*	0.8	0.9	2.1
5.3	0.8	0.9	2.0	1.8	0.3	0.2	-	0.4	0.2	0.2	0.3	1.0
5.4	0.4	0.3	0.7	0.6	*	0.1	-	0.3	0.7	0.3	0.1	0.4
5.5 & Above	0.1	0.2	0.1	0.3	-	-	-	0.3	0.4	0.1	*	0.1
Average	***4.42***	***4.46***	***4.76***	***4.77***	***4.60***	***4.52***	***4.41***	***4.35***	***4.44***	***4.54***	***4.43***	***4.53***

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 20, 2025

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	25.1	20.0	0.3	*	*	*	*	*	1.8	1.0	-	-
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	*	*	*	*	*	*	*	0.1	0.1	-	-
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	-	*	*	*	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.5	0.4	0.5	0.4	0.2	0.3	0.5	0.4	0.2	0.3	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	-	*	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	-	-	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	-	*	*	*	*	*	*	*	*	-	-
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/												
22 & Below	-	-	-	-	*	*	-	-	-	-	-	-
23	-	-	-	-	*	*	-	-	-	-	-	-
24	-	-	-	-	*	*	-	*	-	-	-	-
25	-	-	*	*	*	*	*	*	-	-	-	-
26	*	*	*	*	*	*	*	0.1	0.3	0.2	-	-
27	0.1	*	0.9	0.6	0.1	*	0.3	1.0	2.1	1.4	-	-
28	0.3	0.2	4.4	4.8	0.4	0.5	3.7	4.6	10.7	7.9	-	-
29	1.4	1.4	10.8	19.9	10.8	6.6	14.6	15.5	30.5	26.1	-	-
30	8.1	9.3	38.6	33.8	42.0	33.3	29.2	27.3	32.4	34.3	-	-
31	20.8	27.5	25.3	20.4	30.9	38.5	28.2	26.3	16.7	19.8	-	-
32	32.7	28.6	14.2	11.7	10.8	15.1	16.6	16.1	5.4	7.5	-	-
33	22.8	20.0	3.0	4.4	4.3	4.8	5.6	6.4	1.6	2.2	-	-
34	10.6	9.8	1.5	2.6	0.7	1.0	1.3	2.3	0.4	0.5	-	-
35	2.1	2.7	1.1	1.7	*	0.1	0.3	0.4	*	0.1	-	-
36	0.8	0.4	0.1	0.2	*	*	*	*	*	*	-	-
37	0.2	0.1	-	*	-	*	-	*	-	-	-	-
38	0.1	0.1	-	*	-	*	-	*	-	-	-	-
39	-	*	-	-	-	-	-	-	-	-	-	-
40 & Above	-	-	-	-	-	-	-	-	-	-	-	-
Average	***32.59***	***32.45***	***30.97***	***30.90***	***31.02***	***31.25***	***31.07***	***31.06***	***30.19***	***30.42***	**-**	**-**
Mike												
2.4 & Below	0.4	0.2	-	-	-	-	-	-	-	-	-	-
2.5	1.0	0.5	-	-	-	-	-	-	-	-	-	-
2.6	0.6	0.3	-	-	-	-	-	-	-	-	-	-
2.7	0.4	0.2	-	*	-	-	-	-	-	-	-	-
2.8	0.1	0.1	-	-	-	-	-	-	-	-	-	-
2.9	0.1	*	*	*	-	-	-	-	-	-	-	-
3.0	0.1	*	*	*	-	-	-	-	*	*	-	-
3.1	0.2	0.2	*	*	-	-	-	-	*	*	-	-
3.2	1.9	1.2	0.1	*	-	-	-	*	0.1	*	-	-
3.3	1.8	1.1	*	*	-	*	*	*	0.2	0.1	-	-
3.4	3.3	2.0	*	0.1	*	*	*	*	0.2	0.2	-	-
3.5	5.7	3.5	*	0.1	*	*	*	*	0.4	0.4	-	-
3.6	7.1	5.5	0.3	0.1	0.1	0.1	0.3	0.1	0.9	0.6	-	-
3.7	6.4	5.2	0.4	0.3	0.2	0.1	0.3	0.1	1.5	1.1	-	-
3.8	5.3	4.5	1.1	0.4	0.2	0.3	0.5	0.2	2.8	1.9	-	-
3.9	9.5	6.8	1.2	0.6	0.3	0.6	0.6	0.4	3.7	2.7	-	-
4.0	8.8	7.0	1.4	1.4	1.0	1.2	1.1	0.7	4.7	3.8	-	-
4.1	8.9	11.6	4.3	2.5	1.8	2.0	1.8	1.2	7.0	5.6	-	-
4.2	8.2	9.4	5.2	3.5	3.9	3.4	2.9	1.9	9.1	8.0	-	-
4.3	7.8	11.0	7.6	4.8	6.5	5.7	3.9	2.9	12.0	10.6	-	-
4.4	7.5	8.8	6.8	6.1	8.2	8.6	5.8	4.2	12.6	11.7	-	-
4.5	3.7	6.1	5.3	7.8	12.8	12.1	7.1	5.8	11.6	11.6	-	-
4.6	2.4	4.2	6.7	9.1	14.2	15.4	9.7	8.5	9.8	10.7	-	-
4.7	1.9	5.2	11.2	11.0	17.1	16.7	12.4	11.2	8.3	9.5	-	-
4.8	1.9	2.6	13.9	12.8	13.4	14.2	12.4	13.8	5.6	7.5	-	-
4.9	2.8	1.7	14.4	12.0	9.2	9.7	13.6	14.9	4.1	5.6	-	-
5.0	2.1	1.1	10.3	10.0	6.4	5.6	11.2	13.9	2.7	4.0	-	-
5.1	0.1	*	3.9	8.4	3.1	2.6	8.2	10.1	1.6	2.3	-	-
5.2	*	*	2.4	4.9	0.9	1.0	5.6	5.9	0.8	1.2	-	-
5.3	-	-	2.0	2.6	0.3	0.4	2.1	2.7	0.1	0.4	-	-
5.4	-	-	1.1	1.2	0.1	0.2	0.5	1.1	*	0.2	-	-
5.5 & Above	-	-	0.2	0.3	*	0.1	0.1	0.4	*	*	-	-
Average	***4.00***	***4.12***	***4.66***	***4.73***	***4.63***	***4.63***	***4.74***	***4.81***	***4.40***	***4.47***	**-**	**-**

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 20, 2025

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	0.9	1.2	2.9	2.5	*	*	2.0	1.8	1.6	1.2
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	*	0.1	0.1	-	*	0.2	0.3	*	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	-	-	-	*	-	-	*	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	2.5	1.1	-	*	*	0.3	*	0.8
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	-	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	*	-	-
Other - Level 1	-	*	-	-	-	-	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	-	-	-	-	-	-	*	*	-	-
23	*	*	-	-	-	-	*	*	-	-
24	*	*	-	-	-	*	0.1	*	-	-
25	*	0.1	-	-	-	*	0.3	0.2	-	-
26	0.1	0.3	0.1	0.1	-	*	1.0	0.6	0.8	0.7
27	0.6	1.2	1.1	0.8	0.1	0.3	3.2	2.1	5.8	4.4
28	3.8	4.8	7.7	6.8	3.8	3.5	8.0	6.3	19.3	16.4
29	9.9	11.1	35.1	31.2	23.5	20.7	14.5	14.6	31.7	33.2
30	14.1	15.5	35.9	35.6	33.8	39.0	20.1	20.4	26.2	29.0
31	16.0	15.2	13.3	16.9	24.2	24.7	20.1	18.0	11.5	11.8
32	18.1	14.2	5.4	6.3	12.4	8.5	14.1	13.4	3.6	3.2
33	19.5	14.8	1.2	2.0	2.0	2.5	9.4	10.9	0.9	0.9
34	12.5	12.4	0.1	0.3	0.2	0.7	5.5	8.3	0.1	0.2
35	4.6	6.9	*	*	*	0.1	2.3	3.6	*	*
36	0.6	2.3	-	*	*	*	0.9	1.1	-	*
37	0.2	0.8	-	-	*	*	0.5	0.3	-	-
38	*	0.2	-	-	-	-	0.2	0.1	-	-
39	*	*	-	-	-	-	*	*	-	-
40 & Above	-	*	-	-	-	-	*	*	-	-
Average	***32.14***	***32.13***	***30.19***	***30.35***	***30.70***	***30.69***	***31.19***	***31.46***	***29.76***	***29.85***
Mike										
2.4 & Below	-	-	-	-	-	-	-	*	-	-
2.5	-	*	-	-	-	-	*	*	-	-
2.6	-	*	-	-	-	-	0.1	*	-	-
2.7	-	*	-	-	-	-	0.1	*	-	-
2.8	-	*	-	-	-	-	0.2	0.1	-	-
2.9	*	*	-	-	-	-	0.3	0.1	-	-
3.0	0.1	*	-	*	-	-	0.5	0.2	-	*
3.1	0.2	0.1	*	*	-	-	0.8	0.3	*	*
3.2	0.3	0.2	*	*	-	-	1.3	0.6	*	*
3.3	0.3	0.2	0.2	0.1	*	*	1.9	0.9	*	*
3.4	0.7	0.6	0.2	0.1	0.1	*	2.3	1.3	*	*
3.5	0.7	1.0	0.1	0.1	0.3	0.2	3.0	1.8	0.1	0.2
3.6	1.4	1.9	0.2	0.2	0.5	0.3	3.9	2.5	0.4	0.6
3.7	3.0	3.5	1.2	0.7	0.6	0.7	4.6	3.2	1.5	2.1
3.8	5.1	5.4	1.3	1.0	1.0	1.0	5.4	4.6	2.8	2.9
3.9	8.6	7.1	2.9	2.1	1.7	1.4	6.5	6.4	6.5	5.6
4.0	11.4	8.8	5.2	3.3	2.0	2.1	7.4	8.1	9.1	7.2
4.1	11.1	10.1	6.0	4.6	2.6	3.5	9.0	9.7	13.3	8.7
4.2	9.8	9.8	7.9	6.8	4.9	5.1	9.7	11.1	16.4	12.5
4.3	9.8	9.7	7.8	7.4	8.5	6.8	9.7	11.3	15.0	15.2
4.4	9.7	9.3	9.3	9.4	11.5	9.8	8.8	10.5	13.9	16.4
4.5	9.5	9.5	11.1	10.2	12.9	12.2	7.7	8.8	10.0	12.2
4.6	7.9	9.1	12.0	11.0	12.9	13.9	6.0	6.7	6.2	9.1
4.7	5.2	6.9	10.9	11.3	12.6	13.8	4.3	4.6	2.9	4.7
4.8	3.2	4.2	9.6	10.5	11.1	12.2	3.1	3.0	1.2	1.8
4.9	1.4	1.6	5.7	7.7	7.9	8.2	1.7	1.7	0.4	0.6
5.0	0.4	0.5	3.6	5.8	5.7	5.2	0.8	0.9	0.1	0.2
5.1	0.1	0.2	2.8	3.9	2.5	2.5	0.4	0.5	0.1	0.1
5.2	*	0.1	1.0	2.0	0.5	1.0	0.2	0.3	*	*
5.3	-	*	0.2	1.1	0.1	0.3	0.1	0.2	-	*
5.4	-	-	0.2	0.5	*	*	0.1	0.1	-	*
5.5 & Above	-	*	0.2	0.1	*	*	0.1	0.2	-	*
Average	***4.23***	***4.25***	***4.49***	***4.57***	***4.56***	***4.57***	***4.14***	***4.22***	***4.25***	***4.29***

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 20, 2025

Quality Designation	ALABAMA Week	ALABAMA Season	ARKANSAS Week	ARKANSAS Season	ARIZONA Week	ARIZONA Season	CALIFORNIA Week	CALIFORNIA Season	FLORIDA Week	FLORIDA Season	GEORGIA Week	GEORGIA Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	-	-	-	-	*
2.7 - 2.9	-	*	-	-	-	-	-	0.1	-	-	*	*
3.0 - 3.2	*	*	-	*	-	-	0.4	0.7	*	0.1	*	*
3.3 - 3.4	0.7	0.4	*	*	-	*	1.0	0.7	0.2	0.2	0.2	0.3
3.5 - 3.6	1.9	1.1	0.1	0.1	1.1	0.5	6.1	3.3	3.3	1.5	1.4	0.9
3.7 - 4.2	30.3	27.3	4.3	3.2	9.2	17.8	16.4	34.8	16.5	13.2	30.0	21.8
4.3 - 4.9	59.3	61.9	68.7	71.8	81.0	75.2	76.1	54.4	76.6	75.6	61.9	64.0
5.0 - 5.2	6.5	7.9	24.1	22.3	8.3	6.1	-	4.9	2.1	8.8	5.9	11.4
5.3 & Above	1.3	1.4	2.8	2.7	0.4	0.3	-	1.1	1.4	0.6	0.5	1.6
Average	***4.42***	***4.46***	***4.76***	***4.77***	***4.60***	***4.52***	***4.41***	***4.35***	***4.44***	***4.54***	***4.43***	***4.53***
Leaf												
1 - 2	16.9	16.4	2.1	2.0	64.4	63.7	23.7	38.0	5.7	11.8	14.4	16.3
3	55.0	55.6	38.9	39.1	27.4	29.2	33.5	37.1	52.4	56.0	60.1	60.3
4	24.2	24.4	46.4	45.9	7.2	5.7	32.8	15.1	37.4	28.8	22.6	21.0
5	3.7	3.4	11.1	11.6	0.9	1.1	9.5	8.0	4.3	3.3	2.7	2.2
6	0.3	0.3	1.4	1.3	*	0.3	0.4	1.8	0.2	0.1	0.2	0.1
7	*	*	0.1	0.1	-	-	-	-	*	*	*	*
8	-	-	-	-	-	-	-	-	-	-	-	*
Average	***3.15***	***3.15***	***3.71***	***3.71***	***2.35***	***2.33***	***3.28***	***2.95***	***3.41***	***3.24***	***3.14***	***3.09***
HVI Trash 1/												
00	-	-	-	-	-	*	-	-	-	-	-	-
01	2.2	2.3	0.1	0.1	26.3	27.0	6.9	10.4	0.2	1.6	1.5	1.7
02	18.1	18.2	3.2	3.1	44.8	44.9	23.7	33.3	7.0	13.5	19.6	21.4
03	27.6	28.2	14.5	14.8	15.5	16.8	15.3	22.8	21.7	26.6	33.1	33.3
04	23.2	23.7	24.7	24.6	7.9	6.5	17.4	11.5	29.6	26.5	24.0	23.0
05	14.5	14.3	23.3	23.0	3.2	2.5	15.0	6.8	21.6	16.7	12.2	11.6
06	7.7	7.3	15.8	15.9	1.4	1.1	11.2	5.2	12.1	8.6	5.6	5.2
07	3.8	3.4	9.0	9.3	0.4	0.5	6.2	4.1	4.5	3.7	2.3	2.2
08	1.6	1.5	4.6	4.8	0.4	0.3	3.1	2.9	1.8	1.6	1.0	0.9
09	0.8	0.6	2.4	2.4	0.1	0.2	1.0	1.7	0.7	0.6	0.4	0.4
10	0.4	0.3	1.2	1.1	0.1	0.1	0.3	0.8	0.4	0.3	0.2	0.2
11	0.1	0.1	0.6	0.5	*	*	-	0.3	0.2	0.1	0.1	0.1
12	0.1	0.1	0.3	0.2	-	*	-	0.1	*	*	*	*
13	*	*	0.2	0.1	-	-	-	*	*	*	*	*
14	*	*	0.1	*	-	-	-	*	0.1	*	*	*
15	-	*	*	*	-	-	-	-	*	*	*	*
16	*	*	-	-	-	-	-	-	*	*	*	*
17	*	*	-	-	-	-	-	-	*	*	*	*
18 & Above	*	*	-	-	-	-	-	-	*	*	*	*
Average	***0.38***	***0.38***	***0.51***	***0.51***	***0.23***	***0.22***	***0.39***	***0.34***	***0.44***	***0.40***	***0.36***	***0.35***
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	-	-	-	-	-	-	-	-	-	*	*
76	*	*	*	*	*	*	-	*	-	*	*	*
77	*	*	*	*	0.2	0.1	-	*	*	*	0.2	0.1
78	0.4	0.2	0.1	0.1	1.0	0.3	0.4	0.4	0.1	0.1	1.2	0.9
79	3.3	2.2	0.4	0.5	6.7	1.9	1.2	3.1	1.4	1.3	7.0	5.7
80	14.2	12.1	4.1	4.0	29.6	15.0	7.9	8.1	10.8	9.2	25.0	22.4
81	31.2	32.9	23.3	20.5	38.0	34.6	19.1	23.0	50.6	40.8	36.2	36.5
82	34.6	35.9	46.7	43.6	19.2	40.9	47.5	40.9	32.7	38.9	23.3	25.6
83	14.4	14.7	22.5	27.4	5.1	6.9	23.6	21.0	4.2	9.4	6.1	7.5
84	1.8	1.7	2.6	3.8	0.1	0.2	0.2	3.4	0.1	0.2	0.9	1.4
85 & Above	0.2	0.2	0.2	0.2	-	*	0.2	0.1	*	*	0.1	0.1
Average	***81.92***	***81.99***	***82.40***	***82.50***	***81.27***	***81.79***	***82.30***	***82.22***	***81.73***	***81.91***	***81.40***	***81.53***
Tenderable 3/	**90.5**	**88.5**	**69.1**	**69.4**	**88.8**	**89.4**	**95.9**	**86.0**	**95.6**	**88.3**	**91.8**	**84.3**
SAMPLES CLASSED	**63,984**	**296,421**	**140,285**	**910,193**	**6,747**	**33,680**	**4,055**	**27,384**	**10,954**	**44,444**	**177,625**	**664,975**

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 20, 2025

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	0.4	0.2	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	1.5	0.8	-	-	-	-	-	-	-	-	-	-
2.7 - 2.9	0.6	0.3	*	*	-	-	-	-	-	-	-	-
3.0 - 3.2	2.2	1.4	0.1	*	-	-	-	*	0.2	0.1	-	-
3.3 - 3.4	5.1	3.1	0.1	0.1	*	*	*	*	0.4	0.3	-	-
3.5 - 3.6	12.8	9.0	0.3	0.2	0.1	0.1	0.3	0.2	1.3	1.0	-	-
3.7 - 4.2	47.3	44.5	13.6	8.6	7.6	7.6	7.2	4.5	28.8	23.3	-	-
4.3 - 4.9	28.0	39.7	66.0	63.7	81.5	82.6	64.8	61.3	64.0	67.2	-	-
5.0 - 5.2	2.1	1.1	16.6	23.3	10.4	9.1	25.0	29.9	5.1	7.5	-	-
5.3 & Above	-	-	3.3	4.1	0.4	0.6	2.7	4.2	0.2	0.7	-	-
Average	***4.00***	***4.12***	***4.66***	***4.73***	***4.63***	***4.63***	***4.74***	***4.81***	***4.40***	***4.47***	**-**	**-**
Leaf												
1 - 2	14.8	19.6	11.2	14.7	4.2	3.6	3.2	7.0	9.0	11.8	-	-
3	23.1	30.0	51.4	50.8	56.2	52.5	32.9	43.5	49.6	54.4	-	-
4	23.4	22.6	29.2	28.7	33.8	38.2	47.4	38.8	33.5	28.7	-	-
5	20.4	16.7	7.4	5.5	5.6	5.4	15.2	9.7	7.2	4.6	-	-
6	12.3	8.0	0.7	0.3	0.2	0.3	1.3	1.0	0.7	0.4	-	-
7	4.6	2.4	-	-	-	*	*	*	*	*	-	-
8	1.3	0.7	-	-	-	-	-	-	-	-	-	-
Average	***4.09***	***3.71***	***3.35***	***3.26***	***3.41***	***3.46***	***3.79***	***3.54***	***3.41***	***3.27***	**-**	**-**
HVI Trash 1/												
00	-	-	-	-	-	-	-	-	-	-	-	-
01	5.7	6.3	0.8	1.9	0.1	0.1	0.2	0.6	0.7	1.2	-	-
02	9.7	14.0	13.4	15.6	6.6	5.5	4.0	8.3	11.2	13.7	-	-
03	10.2	13.9	25.1	25.1	24.2	22.2	12.9	19.7	23.9	26.6	-	-
04	11.6	13.5	23.0	23.4	28.9	29.1	19.2	23.8	24.0	25.2	-	-
05	10.0	10.5	16.1	16.0	19.5	21.7	20.6	19.6	18.0	16.6	-	-
06	8.5	8.3	9.8	9.3	10.9	11.8	17.5	12.8	11.3	9.0	-	-
07	7.7	7.0	6.3	4.9	5.5	5.5	12.1	7.5	6.0	4.4	-	-
08	6.6	5.8	3.1	2.3	2.6	2.4	7.0	4.0	2.8	1.9	-	-
09	6.9	5.5	1.5	1.0	1.1	1.0	3.6	2.0	1.2	0.8	-	-
10	5.7	4.2	0.6	0.4	0.5	0.4	1.8	1.0	0.5	0.3	-	-
11	4.1	3.2	0.2	0.2	0.2	0.2	0.8	0.4	0.2	0.2	-	-
12	3.2	2.2	0.1	*	0.1	0.1	0.3	0.2	0.1	0.1	-	-
13	2.9	1.8	*	*	*	*	0.1	0.1	*	*	-	-
14	2.0	1.2	*	*	*	*	*	*	*	*	-	-
15	1.4	0.8	-	-	*	*	*	*	*	*	-	-
16	1.0	0.6	-	-	-	-	-	-	*	*	-	-
17	0.8	0.4	-	-	-	-	-	-	*	*	-	-
18 & Above	2.0	1.0	-	-	-	-	-	-	*	*	-	-
Average	***0.67***	***0.57***	***0.43***	***0.41***	***0.44***	***0.45***	***0.54***	***0.47***	***0.43***	***0.41***	**-**	**-**
UNIFORMITY 2/												
74 & Below	*	*	-	-	-	-	-	-	-	-	-	-
75	0.1	*	-	-	-	-	-	-	-	-	-	-
76	0.3	0.2	-	-	*	*	-	*	-	-	-	-
77	0.8	0.4	-	-	*	*	*	*	-	-	-	-
78	1.3	0.7	0.2	0.1	0.1	0.1	0.1	0.2	0.9	0.6	-	-
79	3.1	1.9	1.8	1.3	0.2	0.3	0.8	1.3	4.5	3.2	-	-
80	14.3	13.0	6.3	7.5	2.5	2.2	7.4	9.0	13.5	11.4	-	-
81	32.7	32.4	28.4	32.2	20.5	15.9	29.2	30.4	31.8	28.3	-	-
82	29.0	33.3	46.0	40.9	51.2	50.3	38.5	38.1	34.5	36.8	-	-
83	15.7	16.1	15.0	16.1	23.1	28.8	21.3	17.7	13.5	17.6	-	-
84	2.5	1.8	2.3	2.0	2.1	2.3	2.6	3.1	1.2	2.0	-	-
85 & Above	0.2	0.1	0.1	0.1	0.2	0.2	0.1	0.1	0.1	0.1	-	-
Average	***81.83***	***81.93***	***82.18***	***82.14***	***82.47***	***82.57***	***82.25***	***82.16***	***81.86***	***82.04***	**-**	**-**
Tenderable 3/	**45.7**	**54.1**	**78.4**	**71.1**	**86.7**	**84.4**	**67.8**	**62.5**	**91.0**	**88.9**	**-**	**-**
SAMPLES CLASSED	**5,697**	**10,911**	**22,902**	**189,705**	**72,487**	**401,457**	**80,004**	**611,237**	**87,487**	**327,234**	**-**	**-**

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 20, 2025

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	-	-	-	-	-	-	*	-	-
2.5 - 2.6	-	*	-	-	-	-	0.1	*	-	-
2.7 - 2.9	*	*	-	-	-	-	0.6	0.2	-	-
3.0 - 3.2	0.5	0.4	*	*	-	-	2.6	1.1	*	*
3.3 - 3.4	1.0	0.8	0.4	0.2	0.1	0.1	4.2	2.3	0.1	0.1
3.5 - 3.6	2.1	2.8	0.4	0.3	0.8	0.5	6.9	4.3	0.5	0.8
3.7 - 4.2	49.1	44.7	24.5	18.5	12.8	13.6	42.7	43.2	49.7	38.9
4.3 - 4.9	46.8	50.5	66.6	67.6	77.4	76.8	41.2	46.6	49.5	59.9
5.0 - 5.2	0.5	0.8	7.4	11.7	8.8	8.7	1.4	1.8	0.2	0.3
5.3 & Above	-	*	0.6	1.7	0.1	0.4	0.3	0.5	-	*
Average	***4.23***	***4.25***	***4.49***	***4.57***	***4.56***	***4.57***	***4.14***	***4.22***	***4.25***	***4.29***
Leaf										
1 - 2	62.6	66.4	5.0	5.7	15.0	17.0	66.7	45.6	7.3	10.5
3	29.6	27.7	47.7	50.5	60.4	60.0	25.4	37.8	63.4	60.1
4	6.5	5.0	39.8	37.9	22.5	21.0	6.3	13.7	25.8	26.3
5	1.1	0.7	7.2	5.7	2.1	2.0	1.4	2.6	3.3	3.0
6	0.2	0.1	0.3	0.2	0.1	0.1	0.2	0.3	0.3	0.1
7	0.1	*	*	*	-	*	*	*	*	*
8	*	*	-	-	-	-	*	*	-	-
Average	***2.24***	***2.12***	***3.50***	***3.44***	***3.12***	***3.08***	***2.20***	***2.63***	***3.26***	***3.22***
HVI Trash 1/										
00	*	0.1	-	-	-	*	0.2	0.1	-	-
01	34.9	38.2	0.2	0.2	1.0	2.2	37.4	20.0	0.2	0.6
02	29.8	30.4	6.9	7.5	15.6	17.7	33.9	28.8	8.6	11.7
03	17.8	16.8	22.2	23.4	29.3	30.5	14.9	21.7	28.6	28.0
04	9.1	8.3	26.5	27.2	26.1	24.9	6.7	13.7	30.1	27.0
05	4.4	3.6	21.1	20.8	15.5	13.9	3.4	7.8	17.3	17.0
06	2.2	1.5	12.3	11.5	7.2	6.4	1.7	4.2	8.7	9.0
07	0.9	0.6	6.4	5.6	3.1	2.7	0.9	2.0	3.8	4.1
08	0.4	0.3	2.7	2.3	1.3	1.0	0.4	0.9	1.5	1.7
09	0.2	0.1	1.1	0.9	0.4	0.4	0.2	0.4	0.7	0.7
10	0.1	0.1	0.4	0.4	0.2	0.2	0.1	0.2	0.3	0.2
11	0.1	0.1	0.2	0.1	0.1	0.1	0.1	0.1	0.1	0.1
12	*	*	*	*	*	*	0.1	*	*	*
13	*	*	*	*	*	*	*	*	*	*
14	*	*	*	*	*	*	*	*	*	*
15	*	*	-	*	*	*	*	*	-	-
16	-	*	*	*	-	-	*	*	-	*
17	-	*	-	-	-	-	*	*	-	-
18 & Above	*	*	*	*	-	-	*	*	-	-
Average	***0.23***	***0.22***	***0.45***	***0.44***	***0.39***	***0.37***	***0.22***	***0.29***	***0.41***	***0.41***
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	*	*	-	-
75	*	*	-	-	-	-	0.1	*	-	-
76	*	*	-	-	-	*	0.3	0.1	-	-
77	0.1	0.2	-	-	*	*	1.1	0.5	-	-
78	1.0	1.0	0.6	0.4	0.1	0.1	4.5	2.3	0.4	0.3
79	5.0	5.3	6.5	3.8	0.4	0.7	14.6	8.1	2.2	1.9
80	17.1	17.6	20.0	15.9	6.4	7.3	30.5	19.9	10.3	11.7
81	31.1	30.5	35.2	31.7	31.8	33.2	29.7	30.3	33.2	35.5
82	23.8	23.9	29.9	36.8	44.9	42.9	14.4	24.7	38.5	34.9
83	17.7	14.4	7.3	10.5	15.8	15.0	4.1	11.0	13.9	14.5
84	3.9	6.5	0.4	0.9	0.5	0.7	0.7	2.8	1.5	1.3
85 & Above	0.2	0.6	*	0.1	0.1	0.1	0.1	0.3	0.1	0.1
Average	***81.87***	***81.88***	***81.56***	***81.81***	***82.16***	***82.11***	***80.91***	***81.56***	***82.00***	***81.97***
Tenderable 3/	**94.7**	**95.3**	**85.8**	**81.1**	**89.6**	**82.1**	**86.0**	**86.9**	**97.7**	**97.2**
SAMPLES CLASSED	**30,941**	**130,388**	**25,453**	**78,522**	**39,075**	**301,195**	**371,619**	**2,416,705**	**20,908**	**73,062**

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 20, 2025

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
01	1	0.1	0.1	2.3	8.6	-	-	7.3	10.0
	2	0.1	0.1	5.4	8.4	-	-	11.8	16.0
	3	-	-	0.2	0.1	-	-	0.3	0.7
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total ----------		***0.3***	***0.1***	***7.9***	***17.1***	***-***	***-***	***19.4***	***26.7***
02	1	44.1	31.6	3.1	5.5	-	-	10.6	11.8
	2	18.9	12.4	33.3	35.4	-	-	54.7	48.0
	3	0.1	0.1	9.8	7.9	-	-	4.2	5.6
	4	-	-	0.1	0.1	-	-	0.1	0.3
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total ----------		***63.1***	***44.0***	***46.3***	***48.9***	***-***	***-***	***69.6***	***65.6***
03	1	13.4	19.4	0.2	0.1	-	-	0.2	0.1
	2	21.3	32.8	16.9	10.9	-	-	8.7	5.8
	3	0.6	1.0	20.6	16.6	-	-	2.1	1.5
	4	-	-	2.3	2.0	-	-	*	0.2
	5	-	-	*	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total ----------		***35.4***	***53.1***	***40.0***	***29.5***	***-***	***-***	***11.0***	***7.6***
04	1	0.1	0.3	*	*	-	-	-	-
	2	1.0	2.2	0.6	0.3	-	-	-	*
	3	0.1	0.3	2.9	2.4	-	-	*	*
	4	-	-	1.1	1.2	-	-	-	*
	5	-	-	0.1	0.1	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total ----------		***1.3***	***2.8***	***4.7***	***4.0***	***-***	***-***	*******	***0.1***
05	1	-	-	-	*	-	-	-	-
	2	-	-	*	*	-	-	-	-
	3	-	-	0.4	0.1	-	-	-	-
	4	-	-	0.4	0.2	-	-	-	-
	5	-	-	0.1	*	-	-	-	-
	6	-	-	0.1	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total ----------		***-***	***-***	***1.1***	***0.4***	***-***	***-***	***-***	***-***
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	*	*	-	-	-	-
	4	-	-	*	*	-	-	-	-
	5	-	-	*	*	-	-	-	-
	6	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total ----------		***-***	***-***	***0.1***	*******	***-***	***-***	***-***	***-***
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total ----------		***-***	***-***	***-***	***-***	***-***	***-***	***-***	***-***
STAPLE									
44 & Shorter		0.1	0.1	3.7	2.9	-	-	12.8	19.9
46		25.9	20.2	12.5	11.0	-	-	46.2	52.7
48		73.7	78.6	33.0	46.8	-	-	39.9	26.8
50		0.3	1.1	49.6	38.6	-	-	1.0	0.7
52 & Longer		-	-	1.2	0.7	-	-	*	*
Average Staple		***47.48***	***47.62***	***48.64***	***48.47***	***-***	***-***	***46.58***	***46.17***
Average Length		***1.38***	***1.38***	***1.41***	***1.41***	***-***	***-***	***1.36***	***1.35***
EXTRANEOUS MATTER									
Bark		-	-	-	-	-	-	-	0.1
Grass		-	-	0.3	0.2	-	-	1.3	1.3
Spindle Twist		-	-	0.1	*	-	-	-	-
Preparation		-	-	-	*	-	-	-	-
All Other		-	-	*	*	-	-	-	*

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Nov 20, 2025

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	-
2.7 - 2.9	-	-	*	*	-	-	*	*
3.0 - 3.2	-	-	0.1	0.2	-	-	7.6	7.7
3.3 - 3.4	-	-	1.0	1.2	-	-	18.6	20.5
3.5 - 3.6	0.1	0.1	7.9	8.7	-	-	14.1	18.3
3.7 - 4.2	93.7	95.5	85.8	87.5	-	-	59.2	53.2
4.3 - 4.9	6.1	4.4	5.2	2.3	-	-	0.4	0.3
5.0 - 5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	***4.01***	***4.00***	***3.92***	***3.89***	**-**	**-**	***3.69***	***3.65***
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-
2.7	-	-	-	*	-	-	-	-
2.8	-	-	*	*	-	-	-	-
2.9	-	-	*	*	-	-	*	*
3.0	-	-	*	*	-	-	1.5	1.0
3.1	-	-	*	*	-	-	1.5	2.2
3.2	-	-	0.1	0.2	-	-	4.7	4.5
3.3	-	-	0.1	0.5	-	-	8.5	8.1
3.4	-	-	0.9	0.8	-	-	10.1	12.4
3.5	-	-	2.8	2.6	-	-	8.6	12.4
3.6	0.1	0.1	5.1	6.1	-	-	5.5	5.9
3.7	9.2	5.5	9.8	10.2	-	-	9.4	9.5
3.8	14.4	12.7	14.7	17.4	-	-	10.6	12.5
3.9	12.1	20.1	21.3	23.5	-	-	17.2	15.6
4.0	12.8	19.4	20.0	21.1	-	-	13.8	10.3
4.1	32.3	25.8	13.4	10.6	-	-	7.8	5.1
4.2	12.9	12.1	6.6	4.6	-	-	0.5	0.3
4.3	5.9	4.2	3.4	1.6	-	-	0.3	0.2
4.4	0.3	0.2	1.2	0.5	-	-	*	*
4.5	-	-	0.5	0.2	-	-	-	-
4.6	-	-	0.1	*	-	-	-	-
4.7	-	-	*	*	-	-	-	-
4.8	-	-	*	*	-	-	-	-
4.9	-	-	*	*	-	-	-	-
5.0	-	-	-	-	-	-	-	-
5.1	-	-	-	-	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	***4.01***	***4.00***	***3.92***	***3.89***	**-**	**-**	***3.69***	***3.65***
STRENGTH 1/								
36 & Below	-	-	2.8	2.5	-	-	8.6	8.1
37	-	-	8.8	7.0	-	-	18.8	21.5
38	-	0.1	4.0	3.4	-	-	20.3	28.4
39	-	-	1.2	0.8	-	-	8.8	13.4
40	13.0	11.7	1.6	2.2	-	-	0.8	0.7
41	27.2	32.6	6.2	7.1	-	-	2.7	1.8
42	38.6	35.8	11.4	13.1	-	-	10.0	6.5
43	16.2	15.4	19.8	20.1	-	-	12.9	8.4
44	4.9	4.1	22.3	21.9	-	-	11.6	7.5
45	-	0.1	16.1	15.2	-	-	4.6	3.0
46	-	-	4.8	5.6	-	-	0.7	0.5
47	0.1	0.1	0.9	1.0	-	-	0.2	0.1
48 & Above	-	-	0.2	0.2	-	-	0.2	0.1
Average	***42.23***	***42.16***	***42.94***	***43.06***	**-**	**-**	***40.36***	***39.62***
UNIFORMITY								
83 & Below	0.1	0.1	1.4	1.1	-	-	1.7	1.2
84	3.3	4.8	16.7	13.4	-	-	16.3	18.4
85	43.0	32.5	26.1	29.3	-	-	45.5	55.1
86	50.7	57.2	50.2	50.3	-	-	35.6	24.6
87	2.7	5.5	5.2	5.4	-	-	0.7	0.5
88 & Above	0.1	0.1	0.4	0.4	-	-	0.2	0.1
Average	***85.98***	***86.11***	***85.87***	***85.91***	**-**	**-**	***85.63***	***85.49***
Samples Classed	**783**	**1,447**	**21,814**	**111,373**	**-**	**-**	**4,592**	**7,076**

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.