



Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	31	84.6	65.1	89,422	31	88.0	65.4	441,427
Corpus Christi	13	91.0	85.9	20,857	42	88.0	72.2	1,457,967
Dumas	25	57.1	28.8	47,968	33	53.4	25.2	850,756
Florence	40	93.6	83.6	131,143	40	90.3	78.1	719,152
Lamesa	24	83.2	56.5	66,680	24	86.5	59.5	247,443
Lubbock	52	81.2	62.8	276,369	53	84.5	65.4	1,262,393
Macon	67	92.2	80.3	241,815	67	87.6	72.7	1,326,301
Memphis	41	89.8	68.1	154,434	65	83.1	59.3	1,994,198
Rayville	7	73.2	47.1	12,342	16	70.3	47.4	262,224
Visalia	16	82.9	65.8	22,525	19	86.4	65.2	100,504
United States	316	85.9	68.7	1,063,555	390	82.5	62.6	8,662,365
AMERICAN PIMA								
Visalia	17			39,007	17			193,596
United States	17			39,007	17			193,596
United States all cotton	328			1,102,562	400			8,855,961

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed. MP_CN100

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 04, 2025

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	44.4	48.4	17.2	14.4	0.2	1.0	0.7	0.4	75.7	73.0
	3	7.2	8.3	21.9	14.5	0.2	0.9	0.9	0.3	4.1	5.7
	4	0.3	0.3	1.4	1.4	*	*	0.1	*	0.2	0.3
	5	*	*	*	*	-	*	*	*	*	*
	6	-	-	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	51.9 57.0	40.5 30.3	0.4 1.9	1.7 0.8	80.0 79.0	80.0 79.0	80.0 79.0	80.0 79.0	80.0 79.0
31	1 - 2	8.4	5.2	3.4	5.0	0.9	2.4	5.2	5.9	0.5	0.4
	3	10.0	9.3	25.0	22.2	13.0	16.6	23.6	21.7	0.7	0.6
	4	4.0	2.7	10.8	9.3	7.6	8.1	6.9	5.6	0.2	0.3
	5	0.8	0.3	0.4	1.0	0.5	0.5	0.5	0.3	*	*
	6	0.1	*	*	*	*	*	*	*	*	*
	7	*	*	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	23.4 17.4	39.7 37.5	22.1 27.7	36.2 33.5	1.4 1.3	1.4 1.3	1.4 1.3	1.4 1.3	1.4 1.3
41	1 - 2	0.3	0.2	0.2	0.6	0.7	0.7	2.1	2.9	-	*
	3	0.6	0.6	4.1	5.1	24.7	19.5	26.7	29.3	*	*
	4	0.9	0.7	5.5	5.0	38.7	32.0	24.1	24.4	-	*
	5	0.9	0.5	1.3	1.3	8.8	8.4	4.5	4.1	-	*
	6	0.4	0.2	0.2	0.1	0.4	0.6	0.3	0.3	-	*
	7	0.1	*	*	*	*	*	*	*	-	*
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	3.3 2.3	11.3 12.1	73.4 61.0	57.6 61.0	* *	* *	* *	* *	* *
51	1 - 2	*	*	-	*	*	*	0.1	0.1	-	-
	3	-	*	0.3	0.2	0.4	1.2	1.3	0.9	-	-
	4	*	*	0.1	0.4	1.5	3.1	1.8	1.7	-	-
	5	*	*	0.4	0.1	0.7	1.4	0.7	0.8	-	-
	6	*	*	0.4	*	0.1	0.2	0.1	0.2	-	-
	7	*	*	0.1	*	-	*	*	*	-	-
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	0.1 *	1.2 0.8	2.7 6.0	4.0 3.6	- -	- -	- -	- -	- -
61	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	*	*	-	*	-	-
	4	-	-	*	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	*	*	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	* *	* *	* *	* *	- -	* *	- -	- -
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- -	- -	- -	- -	- *	- *	- -	- -
12 & 22	1 - 2	9.8	12.3	*	4.1	-	*	-	*	13.9	13.9
	3	3.1	3.5	0.8	3.8	*	*	*	*	2.4	3.0
	4	0.3	0.4	0.4	1.0	-	*	-	*	0.2	0.3
	5	*	*	*	0.1	-	-	-	-	*	*
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	13.1 16.2	1.2 9.0	* *	* *	* *	* *	* *	16.5 17.2	16.5 17.2
32	1 - 2	0.5	0.5	*	0.6	*	*	*	*	0.2	0.2
	3	1.0	1.4	0.7	2.7	0.1	0.1	*	0.1	0.2	0.4
	4	0.9	0.9	1.4	2.4	0.1	0.1	*	0.1	0.1	0.1
	5	0.5	0.3	0.2	0.6	*	*	*	*	*	*
	6	0.1	0.1	-	*	-	*	-	-	*	*
	7	*	*	-	*	-	-	-	-	*	*
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	3.0 3.1	2.3 6.4	0.2 0.3	0.1 0.2	0.1 0.2	0.1 0.2	0.1 0.2	0.5 0.7	0.5 0.7
42	1 - 2	*	*	*	0.1	*	*	*	*	-	*
	3	0.3	0.2	1.0	0.9	0.2	0.5	0.1	0.3	-	*
	4	0.7	0.5	0.8	1.1	0.5	1.3	0.1	0.3	-	*
	5	1.1	0.6	0.6	0.6	0.2	0.5	0.1	0.1	*	*
	6	0.7	0.4	0.3	0.1	*	0.1	*	*	-	*
	7	0.2	0.1	*	*	-	*	-	*	-	-
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	3.1 1.8	2.7 2.8	0.9 2.4	0.3 0.7	0.3 0.7	0.3 0.7	0.3 0.7	* *	* *

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 04, 2025

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	*	-	*	-	-
	3	-	-	0.1	*	*	0.1	*	*	-	-
	4	*	*	0.1	0.1	0.1	0.2	*	*	-	-
	5	*	*	0.1	0.1	*	0.2	*	*	-	-
	6	*	*	0.1	*	*	0.1	*	*	-	-
	7	0.1	0.1	*	*	-	*	-	*	-	-
	8	0.1	*	-	-	-	-	-	-	-	-
Total	----	0.2	0.1	0.4	0.2	0.2	0.6	*	0.1	-	-
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	-	*	*	-	*	*	*	-	-
	5	-	-	-	*	-	*	*	*	-	-
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
Total	----	-	*	*	*	-	*	*	*	-	-
13 & 23	1 - 2	0.5	0.6	*	0.1	-	-	-	-	0.9	0.8
	3	0.2	0.3	*	0.1	-	-	-	-	0.3	0.4
	4	*	0.1	0.1	*	-	-	-	*	*	*
	5	*	*	*	*	-	-	-	-	-	*
	6	-	*	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.8	1.1	0.1	0.3	-	-	-	*	1.2	1.2
33	1 - 2	0.1	0.1	*	*	*	*	*	*	*	0.1
	3	0.2	0.3	0.1	0.1	*	*	*	*	0.2	0.2
	4	0.1	0.2	0.1	0.1	*	*	*	*	*	0.1
	5	*	0.1	*	*	-	-	*	*	-	*
	6	*	*	-	*	-	-	-	-	*	*
	7	-	*	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.4	0.6	0.2	0.3	*	*	*	*	0.3	0.4
43	1 - 2	-	*	-	*	-	-	-	*	-	-
	3	*	*	*	0.1	*	*	*	*	*	*
	4	0.1	0.1	*	0.1	*	*	*	*	-	-
	5	0.1	0.1	*	0.1	*	*	*	*	*	*
	6	0.1	0.1	*	*	*	*	*	*	-	-
	7	*	*	-	*	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
Total	----	0.5	0.2	0.1	0.3	*	*	*	*	*	*
53	1 - 2	-	-	-	*	-	*	-	-	-	-
	3	*	*	-	*	-	*	-	*	-	-
	4	*	*	*	*	-	*	*	*	-	-
	5	*	*	*	*	-	*	*	*	-	-
	6	*	*	*	*	-	*	*	*	-	-
	7	*	*	0.1	*	-	*	-	*	-	-
	8	*	*	-	-	-	-	-	-	-	-
Total	----	0.1	*	0.1	*	-	*	*	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	*	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	*	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	-	*	-	-	-	-
24 - 54	1 - 8	0.1	0.1	0.1	*	-	-	*	*	0.1	0.2
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	*	*	-	-	-	-	-	*
STAPLE											
28 & Shorter		-	*	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	*	*
31		*	0.2	-	*	-	*	-	-	0.2	0.2
32		0.2	0.6	-	*	-	*	-	-	1.5	1.8
33		1.2	2.8	0.1	0.1	*	0.2	0.1	0.1	6.1	6.9
34		5.7	7.3	0.9	0.7	0.5	1.4	1.0	1.0	20.1	19.3
35		13.6	14.1	5.9	3.7	5.9	8.7	7.3	7.0	25.3	24.6
36		19.7	18.2	14.6	15.6	20.3	26.2	26.5	24.9	20.0	20.8
37		25.6	23.1	31.4	46.1	45.8	42.5	49.2	50.2	20.2	19.2
38		16.1	14.7	25.3	25.4	18.2	15.6	13.0	13.8	5.4	5.9
39		12.7	11.6	18.8	7.7	8.0	4.4	2.8	2.8	1.1	1.1
40 & Longer		5.4	7.4	3.1	0.7	1.2	1.0	0.2	0.2	0.1	0.1
Average Staple		36.88	36.77	37.43	37.17	37.04	36.79	36.75	36.78	35.44	35.43
Average Length		1.15	1.15	1.17	1.16	1.16	1.15	1.15	1.15	1.10	1.10

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 04, 2025

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 11 & 21	1 - 2	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
	3	66.4	66.6	1.7	1.6	0.2	0.5	3.4	4.0	29.7	28.6
	4	15.7	15.8	1.1	0.7	0.1	0.4	2.6	2.7	5.0	10.9
	5	0.8	0.9	*	*	*	*	0.3	0.2	0.1	0.7
	6	*	*	*	*	-	*	*	*	-	*
	7	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
Total	----	82.9	83.3	2.8	2.3	0.3	0.9	6.2	6.8	34.8	40.2
31	1 - 2	1.7	1.6	7.9	8.9	2.7	2.8	7.4	8.2	15.3	12.0
	3	3.7	3.1	23.6	21.4	10.4	12.8	23.1	33.9	18.5	13.4
	4	1.8	1.5	4.7	3.3	3.5	3.6	8.9	11.8	4.1	4.7
	5	0.3	0.3	0.2	0.1	0.4	0.2	1.2	0.9	0.2	0.8
	6	*	*	*	*	*	*	0.1	*	*	0.1
	7	*	*	-	-	*	*	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	7.6	6.4	36.4	33.6	17.0	19.5	40.6	54.8	38.1	31.0
41	1 - 2	*	*	5.1	5.4	1.8	2.3	1.0	0.7	1.2	2.3
	3	0.1	*	31.0	33.7	29.8	30.0	18.1	11.9	8.4	6.3
	4	0.1	*	17.8	17.2	27.4	27.3	18.4	16.2	6.0	4.2
	5	0.1	*	2.4	2.1	5.4	5.4	8.1	4.4	0.8	1.7
	6	0.1	*	0.2	0.1	0.4	0.4	1.0	0.4	0.1	0.3
	7	*	*	*	*	*	*	-	-	*	*
	8	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.4	0.1	56.5	58.5	64.8	65.6	46.6	33.6	16.5	14.7
51	1 - 2	-	*	0.2	0.1	0.1	0.1	-	*	0.1	0.1
	3	-	*	1.5	1.5	5.2	2.2	*	*	0.5	0.5
	4	*	*	1.4	1.4	7.7	4.0	0.1	0.3	0.9	0.3
	5	-	*	0.4	0.4	1.9	1.6	0.2	0.3	0.5	0.2
	6	-	-	*	*	0.3	0.3	0.1	*	0.1	0.1
	7	-	-	*	*	*	*	-	-	*	*
	8	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	3.6	3.5	15.1	8.1	0.4	0.7	2.0	1.2
61	1 - 2	-	-	-	*	-	*	-	-	-	-
	3	-	-	*	*	*	*	-	*	-	-
	4	-	-	*	*	*	*	-	*	-	-
	5	-	-	*	*	*	*	-	-	-	-
	6	-	-	*	*	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	*	*	-	*	-	-
71	1 - 2	-	-	-	-	-	*	-	-	-	-
	3	-	-	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	*	-	-	-	-
12 & 22	1 - 2	4.6	5.1	*	*	-	*	1.0	0.1	0.5	4.9
	3	2.3	2.9	*	*	*	*	1.3	0.1	0.3	2.1
	4	0.4	0.4	*	*	-	*	*	0.1	*	0.2
	5	*	*	-	-	-	*	-	*	-	*
	6	*	*	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	7.3	8.3	*	0.1	*	*	2.3	0.4	0.9	7.2
32	1 - 2	0.1	0.1	*	0.1	*	0.1	*	0.1	0.1	0.4
	3	0.4	0.4	0.1	0.3	0.1	0.2	0.2	0.4	0.6	0.9
	4	0.2	0.2	0.1	0.1	0.1	0.1	0.7	0.7	0.3	0.8
	5	0.1	0.1	*	*	*	*	0.7	0.4	*	0.4
	6	*	*	-	*	*	*	0.1	0.1	*	0.1
	7	*	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.9	0.8	0.2	0.5	0.1	0.4	1.8	1.6	1.1	2.5
42	1 - 2	*	*	*	0.1	*	0.2	-	*	*	*
	3	*	*	0.2	0.7	0.5	1.9	0.6	0.3	2.1	0.6
	4	*	*	0.2	0.5	0.7	1.5	0.3	1.0	1.3	0.6
	5	*	*	*	0.1	0.1	0.4	0.3	0.5	0.3	0.5
	6	*	*	*	*	*	0.1	0.6	0.2	*	0.2
	7	*	*	-	*	-	*	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	0.1	0.5	1.3	1.3	4.1	1.8	2.1	3.7	1.9

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 04, 2025

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 52	1 - 2	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
	3	-	-	*	*	*	*	-	-	*	*
	4	-	-	*	*	0.3	0.4	*	*	0.3	0.1
	5	-	*	*	0.1	0.4	0.6	*	0.1	0.6	0.2
	6	-	*	*	*	0.2	0.3	-	0.1	0.9	0.3
	7	*	*	*	*	0.1	0.1	-	*	0.7	0.2
	8	-	*	-	*	*	*	-	-	0.2	0.1
	8	-	-	*	*	-	-	-	-	-	-
Total	----	*	*	*	0.2	1.0	1.4	*	0.1	2.7	0.7
62	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	*	*	-	-	-	-
	4	-	-	-	*	*	*	-	-	-	-
	5	-	-	-	*	*	*	-	-	-	-
	6	-	-	-	*	*	*	-	-	-	-
	7	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	*	*	-	-	-	-
13 & 23	1 - 2	0.3	0.2	-	-	-	-	-	-	-	0.3
	3	0.3	0.3	*	*	-	-	-	-	*	0.1
	4	0.1	0.1	-	-	-	-	-	-	-	*
	5	*	*	-	-	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.6	0.5	*	*	-	-	-	-	*	0.4
33	1 - 2	*	*	-	*	*	*	-	-	-	*
	3	0.1	0.1	*	*	*	*	*	*	*	0.1
	4	0.1	0.1	*	*	*	*	*	*	-	*
	5	*	*	-	-	*	*	*	*	-	*
	6	*	*	-	-	-	*	*	*	-	*
	7	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	0.2	*	*	0.1	*	0.1	*	*	0.1
43	1 - 2	-	*	-	*	*	*	-	*	-	-
	3	*	*	*	*	0.1	*	-	*	*	*
	4	*	*	*	*	0.1	*	*	*	*	*
	5	*	*	*	*	*	*	*	*	*	*
	6	*	*	*	*	*	*	*	*	-	*
	7	*	*	*	*	-	*	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	0.1	0.1	0.1	*	*	*
53	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	*	*	-	-	-	*
	4	-	-	-	*	*	*	-	-	-	*
	5	-	-	-	*	*	*	-	-	-	-
	6	-	*	-	*	-	*	-	*	-	-
	7	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	*	*	-	*	-	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-
24 - 54	1 - 8	*	*	-	*	-	-	-	-	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	-	-	-	-	-	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-
30		*	*	-	*	-	-	-	-	-	-
31		0.1	0.1	*	*	-	*	-	-	-	*
32		0.6	0.6	0.1	0.1	*	*	-	*	0.1	*
33		2.5	2.8	0.5	0.7	0.1	0.1	0.3	0.2	0.1	0.1
34		8.2	8.5	3.3	4.1	0.4	0.9	2.3	1.7	0.4	0.6
35		17.1	16.9	14.2	14.7	2.9	4.3	9.9	11.8	1.5	2.9
36		25.8	24.7	29.6	30.6	12.3	15.5	31.3	28.6	11.6	13.4
37		29.6	29.7	38.4	36.6	47.0	47.6	39.4	39.9	47.1	41.9
38		11.5	11.8	11.6	10.5	31.2	26.4	14.7	13.6	27.1	26.8
39		3.6	3.8	2.1	2.4	5.5	4.7	2.0	3.8	5.4	10.1
40 & Longer		1.0	1.2	0.2	0.3	0.5	0.6	0.2	0.4	6.7	4.3
Average Staple		36.24	36.25	36.46	36.41	37.24	37.11	36.60	36.64	37.66	37.51
Average Length		1.13	1.13	1.14	1.13	1.16	1.16	1.14	1.14	1.18	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 04, 2025

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	4.5	2.6	0.8	0.6	*	*	1.8	1.5	0.9	1.4
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	0.1	0.2	0.3	*	0.1	*	0.1	0.2	0.5
Grass - Level 2	-	-	-	*	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	*	*	*	*	-	-
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	-	*	*	1.7	0.5	0.5	0.1	0.1
Seed Coat - Level 2	*	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	*	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	*	*	-	*	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	0.1	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	-	*	-	*	-	-	-	-	*	*
23	*	*	-	*	-	-	-	-	*	*
24	*	0.1	-	*	-	*	*	*	0.1	0.2
25	0.1	0.2	*	*	*	*	*	*	0.4	0.8
26	0.3	0.8	0.2	0.2	*	0.1	0.8	0.3	1.2	2.1
27	2.4	3.2	1.7	1.2	0.5	0.5	3.9	2.3	2.9	5.6
28	7.5	8.8	6.7	5.3	3.8	4.1	15.5	10.7	8.5	11.1
29	14.0	14.8	12.2	15.0	13.6	15.9	33.3	28.9	18.9	18.3
30	16.3	16.4	15.4	21.8	25.9	28.9	26.8	32.0	25.2	22.5
31	15.3	15.1	18.2	17.6	27.3	26.7	12.5	16.8	22.8	19.7
32	15.6	13.5	16.8	12.3	17.3	15.5	5.7	6.6	12.3	11.9
33	12.2	11.3	14.4	11.5	8.2	6.0	1.3	1.9	5.2	4.9
34	8.6	8.4	9.1	9.7	2.8	1.9	0.2	0.4	1.6	1.9
35	4.6	4.7	4.2	4.0	0.6	0.3	*	0.1	0.7	0.7
36	1.7	1.7	0.9	1.1	*	*	-	*	0.2	0.3
37	1.0	0.8	0.2	0.2	-	-	*	*	*	0.1
38	0.4	0.3	*	*	-	-	-	-	*	*
39	*	*	*	*	-	-	-	-	-	-
40 & Above	*	*	-	-	-	-	-	-	-	-
Average	31.68	31.49	31.73	31.59	31.23	31.04	29.95	30.24	30.66	30.45
Mike										
2.4 & Below	*	*	-	-	-	-	-	-	-	-
2.5	*	*	-	*	-	-	-	-	*	*
2.6	0.1	*	-	*	-	-	-	-	*	0.1
2.7	0.3	0.1	-	*	-	-	-	-	0.1	0.1
2.8	0.4	0.2	-	*	-	-	*	*	0.4	0.2
2.9	0.5	0.2	-	*	-	-	*	*	0.7	0.5
3.0	0.5	0.3	*	0.1	-	-	*	*	0.8	0.6
3.1	0.7	0.5	0.3	0.1	-	-	0.1	*	1.0	0.7
3.2	1.0	0.7	0.2	0.3	*	*	0.2	0.1	1.8	0.9
3.3	1.5	0.9	0.4	0.5	*	*	0.3	0.2	2.0	1.2
3.4	1.8	1.3	0.4	0.8	0.1	*	0.5	0.2	2.6	1.8
3.5	2.5	1.9	0.1	1.2	0.2	*	0.7	0.4	2.2	2.2
3.6	3.2	2.7	0.5	1.8	0.1	0.1	1.1	0.7	2.4	2.9
3.7	4.4	3.9	1.5	2.6	0.2	0.1	2.1	1.5	2.8	3.6
3.8	5.3	5.2	3.5	4.3	0.2	0.1	3.1	2.3	4.0	4.2
3.9	6.9	7.2	7.1	6.7	0.5	0.2	4.7	3.5	4.2	5.0
4.0	8.5	8.9	10.3	9.1	1.0	0.4	6.4	4.8	5.0	5.8
4.1	10.0	10.3	13.8	11.1	1.7	0.6	8.5	6.6	5.4	7.1
4.2	11.0	11.1	13.8	12.8	2.2	1.1	11.2	9.3	7.0	8.3
4.3	10.2	10.9	13.1	12.8	2.6	1.7	12.7	11.6	8.5	9.6
4.4	9.3	9.9	11.7	11.2	3.5	2.8	12.1	12.2	9.3	10.0
4.5	7.7	8.2	9.6	8.8	4.4	4.0	10.6	11.3	9.3	9.6
4.6	6.3	6.4	6.3	6.1	5.7	6.4	8.9	10.0	9.4	8.7
4.7	3.7	4.3	3.6	3.7	7.7	9.5	7.0	8.4	8.3	7.2
4.8	2.4	2.7	2.1	2.4	12.7	13.6	4.7	6.2	5.8	5.0
4.9	1.2	1.3	1.3	1.3	15.7	16.2	2.7	4.4	3.4	2.6
5.0	0.5	0.6	0.4	0.8	15.0	16.5	1.3	3.0	2.2	1.4
5.1	0.2	0.2	0.1	0.4	11.8	12.7	0.5	1.7	1.0	0.5
5.2	0.2	0.1	*	0.3	8.6	8.0	0.4	0.9	0.4	0.2
5.3	*	*	*	0.2	4.7	3.9	0.1	0.4	0.1	0.1
5.4	-	-	-	0.1	1.1	1.5	*	0.2	*	*
5.5 & Above	-	*	-	0.2	0.2	0.5	*	*	-	-
Average	4.13	4.17	4.24	4.23	4.84	4.88	4.33	4.42	4.24	4.23

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 04, 2025

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	3.5	3.5	0.9	0.6	*	*	1.6	0.7	0.4	0.2
Bark - Level 2	*	*	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	0.1	0.1	0.1	*	*	*	0.1	0.6	0.6
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	*	*	*	*	-	*	-	-	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.1	*	0.2	0.2	*	0.1	-	3.1	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	*	-	-	-	-	-	-	-	-
Other - Level 1	*	*	*	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	*	*	-	-	-	*	-	-	-	-
23	*	*	-	*	-	*	-	-	-	-
24	*	0.1	*	*	-	*	-	-	*	*
25	0.1	0.2	*	*	*	*	-	*	*	*
26	0.6	0.6	0.3	0.2	*	*	*	0.2	0.2	0.3
27	2.4	2.2	2.5	1.4	0.5	0.2	1.1	1.8	1.0	1.2
28	6.6	5.9	10.8	7.2	2.4	1.9	11.8	6.5	5.0	5.5
29	14.0	12.8	23.8	18.9	13.2	12.3	17.5	18.0	13.9	13.6
30	19.3	18.6	26.6	26.4	41.2	35.4	24.3	30.7	22.4	19.7
31	20.0	20.0	18.1	22.3	30.3	32.9	19.4	19.9	19.8	18.0
32	16.0	16.3	10.7	13.2	9.2	12.5	13.2	12.6	14.9	10.7
33	10.2	11.1	4.9	6.4	2.5	3.7	8.5	5.8	11.2	7.8
34	6.3	6.9	1.7	2.7	0.5	0.9	4.0	2.9	7.1	8.9
35	2.8	3.2	0.5	1.0	0.1	0.1	0.3	1.5	3.1	8.3
36	1.0	1.3	0.1	0.3	*	*	*	0.2	1.1	4.4
37	0.4	0.5	*	0.1	*	*	-	*	0.3	1.3
38	0.2	0.2	*	*	-	*	-	*	0.1	0.1
39	*	*	-	*	-	-	-	-	*	*
40 & Above	-	-	-	-	-	-	-	-	*	*
Average	31.39	31.53	30.55	30.92	30.84	31.02	30.91	30.91	31.54	31.91
Mike										
2.4 & Below	*	*	-	-	-	-	-	-	-	-
2.5	*	*	-	*	-	-	-	-	-	-
2.6	0.1	*	-	*	-	-	-	-	-	-
2.7	0.2	0.1	-	*	-	-	-	*	-	*
2.8	0.6	0.3	*	*	*	*	-	*	*	*
2.9	0.9	0.4	*	*	*	*	-	*	0.1	0.1
3.0	1.1	0.6	*	*	*	*	-	*	0.2	0.2
3.1	1.3	0.9	*	*	*	*	*	*	0.9	0.4
3.2	2.0	1.4	*	*	*	*	*	*	0.6	0.4
3.3	2.7	2.0	0.1	0.1	*	*	0.7	0.1	0.5	0.3
3.4	3.5	2.7	0.1	0.2	0.2	0.1	1.0	0.1	0.2	0.4
3.5	4.0	3.4	0.5	0.4	0.4	0.1	1.5	0.2	1.3	0.9
3.6	4.7	4.1	1.0	0.7	0.4	0.2	2.5	0.3	1.2	1.4
3.7	5.2	4.8	1.9	1.3	0.5	0.4	1.1	0.4	2.9	2.6
3.8	5.7	5.6	3.2	2.0	0.9	0.7	0.8	0.6	2.1	3.3
3.9	6.3	6.2	4.5	3.0	1.4	1.0	0.6	1.1	3.2	3.7
4.0	6.6	6.6	5.9	4.5	2.5	1.7	0.2	1.9	4.2	4.1
4.1	6.9	7.1	9.2	6.7	3.8	2.5	1.3	3.5	6.0	5.5
4.2	7.2	7.7	10.2	8.5	5.8	3.9	3.0	4.4	5.7	7.0
4.3	7.1	8.3	10.5	9.6	6.9	5.5	7.0	5.5	7.2	7.6
4.4	7.2	8.5	10.1	10.1	7.6	7.9	5.8	6.3	9.4	9.4
4.5	6.9	8.0	9.9	10.4	11.1	10.8	9.4	8.3	10.4	11.2
4.6	6.6	7.1	9.2	9.8	14.8	14.0	11.8	9.6	11.2	11.1
4.7	5.3	5.6	7.7	9.1	15.4	15.4	9.9	10.7	10.6	9.7
4.8	3.4	3.7	5.8	7.7	12.5	14.1	12.9	11.9	8.6	8.6
4.9	2.1	2.2	4.4	6.0	8.6	10.4	10.0	10.9	6.4	5.8
5.0	1.2	1.1	2.6	4.3	4.2	6.4	8.2	8.8	5.0	3.6
5.1	0.5	0.6	1.6	2.8	2.1	3.1	4.7	7.2	1.7	1.7
5.2	0.3	0.3	0.9	1.6	0.5	1.1	2.5	4.3	0.3	0.7
5.3	0.1	0.2	0.4	0.8	0.1	0.4	1.3	2.3	*	0.2
5.4	*	0.1	0.1	0.3	*	0.1	0.7	1.0	*	0.1
5.5 & Above	*	0.1	*	0.1	*	*	3.3	0.5	-	0.1
Average	4.08	4.15	4.38	4.47	4.56	4.62	4.64	4.69	4.42	4.42

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 04, 2025

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	*	*	-	-	-	-	-	-	-	-
2.5 - 2.6	0.1	0.1	-	*	-	-	-	-	*	0.1
2.7 - 2.9	1.1	0.5	-	0.1	-	-	*	*	1.2	0.8
3.0 - 3.2	2.2	1.5	0.5	0.5	*	*	0.3	0.1	3.7	2.3
3.3 - 3.4	3.3	2.2	0.8	1.4	0.1	*	0.8	0.4	4.5	2.9
3.5 - 3.6	5.7	4.6	0.6	3.0	0.3	0.1	1.8	1.1	4.7	5.1
3.7 - 4.2	45.9	46.6	50.0	46.6	5.9	2.5	36.0	28.0	28.4	34.1
4.3 - 4.9	40.7	43.7	47.6	46.4	52.3	54.3	58.7	64.2	54.0	52.5
5.0 - 5.2	0.9	0.9	0.5	1.5	35.4	37.1	2.2	5.6	3.5	2.1
5.3 & Above	*	*	*	0.5	6.1	5.9	0.2	0.5	0.1	0.1
Average	4.13	4.17	4.24	4.23	4.84	4.88	4.33	4.42	4.24	4.23
Leaf										
1 - 2	64.1	67.3	21.0	25.0	1.9	4.1	8.1	9.3	91.2	88.4
3	22.8	23.9	54.0	49.7	38.8	38.9	52.6	52.7	8.0	10.4
4	7.5	5.7	20.8	21.0	48.6	44.9	33.0	32.2	0.7	1.1
5	3.4	1.9	3.0	3.9	10.2	11.1	5.8	5.3	0.1	0.1
6	1.6	0.8	1.1	0.4	0.6	1.0	0.5	0.5	*	*
7	0.5	0.2	0.2	*	*	*	*	*	*	*
8	0.2	0.1	-	*	-	-	-	-	-	-
Average	2.39	2.24	3.09	3.03	3.69	3.66	3.38	3.35	1.59	1.66
HVI Trash 1/										
00	*	*	-	*	-	-	-	-	1.0	1.0
01	33.5	35.9	4.0	5.2	*	0.3	0.5	0.7	69.1	63.5
02	34.3	34.3	22.4	22.6	2.7	4.9	10.1	11.0	23.3	26.2
03	13.4	14.5	28.3	27.9	13.9	15.5	24.8	24.9	4.8	6.5
04	6.3	6.6	23.4	20.2	24.7	23.4	26.0	25.8	1.2	1.9
05	3.5	3.2	12.2	12.0	24.3	22.0	18.5	18.3	0.4	0.6
06	2.5	1.8	4.7	6.4	16.8	15.5	10.6	10.4	0.1	0.2
07	1.7	1.1	1.8	3.1	9.5	9.3	5.3	5.1	*	0.1
08	1.3	0.7	1.0	1.4	4.5	4.8	2.4	2.2	*	*
09	0.9	0.5	0.7	0.6	2.1	2.4	1.1	1.0	*	*
10	0.7	0.4	0.5	0.3	0.8	1.1	0.4	0.4	*	*
11	0.5	0.3	0.4	0.1	0.4	0.5	0.2	0.2	*	*
12	0.4	0.2	0.2	0.1	0.1	0.2	0.1	0.1	*	*
13	0.3	0.2	0.1	*	0.1	0.1	*	*	-	*
14	0.2	0.1	0.1	*	*	*	*	*	*	*
15	0.1	0.1	*	*	*	*	*	*	-	-
16	0.1	0.1	*	*	-	-	*	*	-	-
17	0.1	*	*	*	-	-	-	*	-	-
18 & Above	0.2	0.1	*	*	-	-	*	*	-	-
Average	0.26	0.24	0.36	0.36	0.50	0.50	0.43	0.42	0.14	0.15
UNIFORMITY 2/										
74 & Below	*	*	-	*	-	-	-	-	*	*
75	*	*	-	*	-	-	-	-	*	0.1
76	0.1	0.2	*	*	*	*	*	*	0.4	0.4
77	0.7	0.7	0.3	0.1	*	*	*	*	1.7	2.0
78	2.8	2.8	2.1	0.7	0.1	0.2	0.3	0.5	6.7	9.2
79	11.7	11.8	6.5	3.7	0.8	1.0	2.0	2.8	22.4	24.4
80	25.9	27.4	17.6	13.3	6.8	7.2	10.2	11.5	37.7	35.0
81	29.2	28.7	27.0	29.9	26.8	28.4	24.8	28.5	26.8	23.5
82	20.8	17.3	25.4	31.2	37.5	38.4	35.7	36.3	4.0	4.8
83	7.7	8.4	15.8	16.3	21.4	20.1	22.7	18.1	0.3	0.7
84	1.0	2.5	4.5	4.4	6.3	4.7	4.0	2.2	*	*
85 & Above	0.1	0.2	0.7	0.5	0.2	0.1	0.3	0.2	*	*
Average	81.23	81.24	81.80	82.01	82.37	82.28	82.24	82.06	80.39	80.30
Tenderable 3/	84.6	88.0	91.0	88.0	57.1	53.4	93.6	90.3	83.2	86.5
SAMPLES CLASSED										
Week	89,422		20,857		47,968		131,143		66,680	
Season	441,427		1,457,967		850,756		719,152		247,443	

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 04, 2025

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	*	*	-	-	-	-	-	-	-	-
2.5 - 2.6	0.1	0.1	-	*	-	-	-	-	-	-
2.7 - 2.9	1.7	0.8	*	*	*	*	-	*	0.1	0.1
3.0 - 3.2	4.5	2.9	0.1	0.1	*	*	*	0.1	1.7	0.9
3.3 - 3.4	6.2	4.8	0.2	0.3	0.3	0.1	1.7	0.2	0.7	0.6
3.5 - 3.6	8.7	7.5	1.4	1.1	0.8	0.4	3.9	0.5	2.5	2.2
3.7 - 4.2	38.1	38.0	34.9	25.9	15.0	10.2	7.0	11.8	24.1	26.2
4.3 - 4.9	38.6	43.4	57.8	62.6	76.9	78.2	66.7	63.3	63.8	63.5
5.0 - 5.2	1.9	2.1	5.0	8.7	6.8	10.6	15.4	20.4	7.0	6.0
5.3 & Above	0.2	0.4	0.6	1.3	0.2	0.6	5.3	3.8	*	0.4
Average	4.08	4.15	4.38	4.47	4.56	4.62	4.64	4.69	4.42	4.42
Leaf										
1 - 2	73.1	73.6	15.0	16.2	4.8	5.9	12.8	13.0	47.0	48.6
3	22.7	22.5	57.5	58.3	46.4	48.1	45.9	49.4	35.8	34.9
4	3.6	3.3	24.3	22.7	39.8	37.2	28.7	30.3	13.3	11.7
5	0.6	0.5	3.0	2.7	8.1	7.9	10.7	6.5	2.8	3.9
6	0.1	0.1	0.2	0.2	0.8	0.9	1.9	0.8	1.0	0.9
7	*	*	*	*	0.1	0.1	-	-	0.3	0.1
8	*	*	*	*	-	-	-	-	-	-
Average	2.11	2.09	3.16	3.12	3.54	3.50	3.43	3.32	2.67	2.66
HVI Trash 1/										
00	*	*	-	-	-	*	-	-	-	*
01	38.6	38.6	1.7	1.9	0.3	0.5	1.8	1.6	18.7	18.3
02	40.8	40.3	20.0	20.6	6.1	7.3	15.1	14.2	33.7	37.1
03	13.6	13.6	31.3	31.8	19.4	20.8	24.7	24.3	20.9	20.7
04	4.3	4.5	23.6	23.2	26.2	25.9	19.3	23.4	12.8	10.5
05	1.6	1.7	13.0	12.4	21.5	20.3	12.8	16.4	6.7	5.6
06	0.6	0.7	6.0	5.8	13.4	12.3	9.6	9.7	3.6	3.3
07	0.3	0.3	2.6	2.5	7.1	6.7	6.0	5.2	1.7	1.9
08	0.1	0.1	1.1	1.1	3.4	3.3	4.3	2.6	0.8	1.3
09	0.1	0.1	0.4	0.4	1.6	1.6	2.9	1.3	0.6	0.7
10	*	*	0.2	0.2	0.7	0.8	1.7	0.6	0.2	0.4
11	*	*	0.1	0.1	0.3	0.3	1.2	0.4	0.2	0.2
12	*	*	*	*	0.1	0.2	0.5	0.2	0.1	0.1
13	*	*	*	*	*	0.1	0.2	0.1	*	*
14	*	*	*	*	*	*	0.1	*	*	*
15	*	*	*	*	*	*	-	-	*	*
16	*	*	*	*	-	-	-	-	-	-
17	*	*	*	*	-	-	-	-	-	-
18 & Above	*	*	*	*	-	-	-	-	-	-
Average	0.19	0.20	0.37	0.36	0.47	0.46	0.45	0.42	0.29	0.28
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	-	-	-	-
75	*	*	-	*	-	-	-	-	-	-
76	0.2	0.2	*	*	*	*	-	-	*	*
77	1.0	0.9	0.1	0.1	*	*	-	-	*	*
78	4.1	3.7	0.5	0.7	0.1	0.1	0.2	0.2	0.4	0.7
79	13.6	12.5	3.8	4.6	0.3	0.5	3.0	1.8	4.9	3.6
80	30.7	28.7	18.0	19.8	2.6	4.0	13.3	10.0	14.7	12.7
81	33.7	33.4	37.6	37.2	18.1	21.0	32.3	31.7	31.2	30.6
82	13.6	16.5	30.1	28.0	48.2	45.5	33.3	38.5	30.6	36.6
83	2.8	3.6	8.6	8.1	27.8	26.1	15.5	15.8	14.3	12.9
84	0.4	0.5	1.3	1.2	2.7	2.6	2.5	2.0	3.4	2.6
85 & Above	0.1	0.1	0.1	0.1	0.2	0.2	0.1	0.1	0.4	0.2
Average	80.90	81.01	81.69	81.62	82.55	82.46	81.97	82.08	81.90	81.94
Tenderable 3/	81.2	84.5	92.2	87.6	89.8	83.1	73.2	70.3	82.9	86.4
SAMPLES CLASSED										
Week	276,369		241,815		154,434		12,342		22,525	
Season		1,262,393		1,326,301		1,994,198		262,224		100,504

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 04, 2025

Color Grade	Leaf	VISALIA			Quality Designation	VISALIA	
		Week	Season			Week	Season
01	1	4.9	7.5		MIKE	-	-
	2	6.2	7.6		2.4 & Below	-	-
	3	0.3	0.2		2.5 - 2.6	-	-
	4	-	-		2.7 - 2.9	0.1	0.1
	5	-	-		3.0 - 3.2	3.4	1.7
	6	-	-		3.3 - 3.4	4.4	3.1
	7	-	-		3.5 - 3.6	8.0	9.2
Total -----		11.5	15.3		3.7 - 4.2	81.4	83.8
02	1	7.0	6.9		4.3 - 4.9	2.6	2.2
	2	38.4	37.4		5.0 - 5.2	-	-
	3	10.9	8.2		5.3 & Above	-	-
	4	0.3	0.1		Average	3.86	3.87
	5	*	*		ALL RANGE MIKE		
	6	-	-		2.4 & Below	-	-
	7	-	-		2.5	-	-
Total -----		56.6	52.7		2.6	-	-
03	1	0.8	0.4		2.7	*	*
	2	13.1	11.2		2.8	*	*
	3	13.3	15.0		2.9	0.1	*
	4	1.6	1.6		3.0	0.6	0.2
	5	0.1	*		3.1	1.2	0.5
	6	*	*		3.2	1.6	0.9
	7	-	-		3.3	1.8	1.2
Total -----		28.8	28.3		3.4	2.6	1.9
04	1	*	*		3.5	3.1	3.2
	2	0.8	0.4		3.6	4.9	6.0
	3	1.5	2.0		3.7	9.0	10.1
	4	0.4	0.8		3.8	14.1	16.2
	5	*	0.1		3.9	22.2	21.7
	6	-	*		4.0	19.2	19.9
	7	-	-		4.1	12.4	10.9
Total -----		2.7	3.4		4.2	4.6	4.8
05	1	-	*		4.3	1.6	1.5
	2	0.1	*		4.4	0.8	0.5
	3	0.2	0.1		4.5	0.2	0.2
	4	0.1	0.1		4.6	*	*
	5	*	*		4.7	*	*
	6	-	*		4.8	*	*
	7	-	-		4.9	-	*
Total -----		0.4	0.3		5.0	-	-
06	1	-	-		5.1	-	-
	2	*	*		5.2	-	-
	3	*	*		5.3 & Above	-	-
	4	-	*		Average	3.86	3.87
	5	-	*		STRENGTH 1/		
	6	-	*		36 & Below	3.8	3.3
	7	-	-		37	2.9	6.5
Total -----		*	*		38	3.4	4.1
07	1	-	-		39	1.6	1.4
	2	-	-		40	1.3	2.0
	3	-	-		41	5.1	6.4
	4	-	-		42	11.8	12.8
	5	-	-		43	15.7	18.6
	6	-	-		44	19.0	20.7
	7	-	-		45	19.7	15.4
Total -----		-	-		46	10.7	6.5
STAPLE	44 & Shorter	1.0	3.0		47	3.4	1.7
	46	11.8	12.9		48 & Above	1.5	0.6
	48	48.3	48.0		Average	43.60	43.05
	50	36.7	35.0		UNIFORMITY		
	52 & Longer	2.2	1.2		83 & Below	0.6	1.1
Average Staple		48.55	48.37		84	11.9	12.9
Average Length		1.41	1.41		85	35.9	33.2
EXTRANEIOUS MATTER	Bark	*	*		86	44.5	47.0
	Grass	0.4	0.3		87	6.4	5.3
	Spindle Twist	*	*		88 & Above	0.7	0.5
	Preparation	*	*		Average	85.91	85.89
	All Other	*	*		Samples Classed		
					Week	39,007	
					Season		193,596

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.