



State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	20	94.6	84.1	57,179	21	90.2	77.3	416,346
AR	18	79.1	52.8	97,647	26	70.5	41.9	1,137,684
AZ	7	84.5	69.2	15,004	7	88.3	63.7	58,919
CA	4	78.2	57.3	4,103	7	85.2	68.7	35,091
FL	4	95.1	85.0	13,657	4	90.6	74.1	67,306
GA	52	91.2	78.6	184,098	52	87.1	71.7	1,014,678
KS	3	39.5	27.3	14,013	3	44.9	33.2	34,603
LA	5	73.2	42.9	8,079	14	72.0	47.5	215,077
MO	14	91.4	72.1	56,553	16	85.4	62.9	529,209
MS	21	66.4	39.7	26,018	30	63.7	36.2	691,787
NC	26	93.2	83.1	78,161	26	90.1	77.1	468,347
NM	2	94.8	83.7	1,574	2	96.5	86.9	2,639
OK	10	95.0	84.5	33,288	10	94.9	83.2	192,608
SC	10	92.4	83.7	29,772	10	84.9	69.8	135,379
TN	5	85.9	67.1	11,537	17	82.1	63.2	336,413
TX	111	83.0	62.7	409,662	141	86.3	67.1	3,210,853
VA	4	96.2	85.4	23,210	4	97.1	92.1	115,426
United States	316	85.9	68.7	1,063,555	390	82.5	62.6	8,662,365
AMERICAN PIMA								
AZ	2			2,096	2			4,356
CA	9			29,869	9			164,450
NM*	-			-	-			-
TX	5			3,614	5			13,155
United States	17			39,007	17			193,596
United States all cotton	328			1,102,562	400			8,855,961

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 04, 2025

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	3.1	2.6	*	0.1	22.7	28.0	51.0	29.3	0.7	2.1	1.4	1.1
	3	1.6	1.3	*	0.1	4.2	7.6	1.2	15.6	0.8	0.6	0.9	0.5
	4	0.1	*	-	*	0.1	0.5	-	1.0	-	*	*	*
	5	-	-	-	-	-	*	-	*	-	-	*	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	4.8	3.9	0.1	0.2	27.0	36.2	52.2	45.9	1.5	2.6	2.3	1.5
31	1 - 2	11.4	10.6	1.4	1.1	11.9	11.5	33.7	13.7	2.6	3.7	7.3	8.0
	3	27.0	31.0	8.9	9.4	19.8	11.7	6.5	13.4	15.1	13.6	23.5	20.4
	4	6.9	7.8	3.8	3.5	3.7	2.4	0.3	7.4	3.3	2.8	4.8	3.1
	5	0.7	0.6	0.3	0.1	0.1	0.3	*	1.6	0.1	0.1	0.2	0.1
	6	0.1	*	*	*	-	*	*	0.2	-	-	*	*
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	46.0	50.1	14.3	14.2	35.5	26.0	40.6	36.3	21.0	20.2	35.8	31.7
41	1 - 2	6.0	2.9	0.8	0.7	1.7	2.7	0.4	1.9	1.6	3.0	4.8	5.7
	3	25.1	21.2	25.9	26.0	11.6	9.2	2.8	2.4	38.0	36.8	31.3	35.6
	4	12.5	15.7	35.8	36.2	8.8	5.2	0.2	3.1	31.1	27.9	18.4	17.2
	5	2.4	2.9	7.4	8.4	1.2	0.7	-	3.4	4.2	3.8	2.5	2.0
	6	0.4	0.3	0.5	0.7	0.1	*	-	0.8	0.3	0.2	0.1	0.1
	7	*	*	*	*	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	46.4	43.0	70.4	72.0	23.4	17.9	3.4	11.6	75.1	71.7	57.1	60.6
51	1 - 2	0.1	0.1	*	*	0.1	0.1	-	0.1	*	0.1	0.2	0.1
	3	1.2	0.4	2.7	1.9	0.7	0.7	-	0.1	0.8	1.2	1.5	1.7
	4	0.6	0.3	6.5	4.2	1.4	0.5	*	0.1	1.0	1.7	1.7	1.7
	5	0.2	0.1	2.4	2.2	0.7	0.4	-	*	0.3	0.5	0.5	0.4
	6	*	*	0.4	0.5	0.1	0.1	-	*	0.1	*	*	*
	7	*	*	*	0.1	*	*	-	-	*	*	*	*
	8	-	*	-	-	-	-	-	-	-	-	-	*
Total	----	2.2	1.0	12.1	8.8	3.1	1.8	*	0.3	2.2	3.6	3.9	4.0
61	1 - 2	-	-	-	*	-	-	-	-	-	-	-	*
	3	*	*	*	*	-	-	-	-	-	-	*	*
	4	*	*	0.1	*	-	-	-	-	-	*	*	*
	5	*	*	*	*	-	-	-	-	-	*	*	*
	6	-	-	-	*	-	-	-	-	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	0.1	*	-	-	-	-	-	*	*	*
71	1 - 2	-	-	-	*	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	-	-	-	-	-
12 & 22	1 - 2	*	0.1	-	*	0.7	8.1	*	0.3	-	*	*	*
	3	*	*	*	*	0.2	3.1	-	0.5	*	*	*	*
	4	-	*	-	*	*	0.3	-	0.1	-	-	*	*
	5	-	-	-	*	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	0.2	*	*	0.9	11.5	*	0.9	*	*	*	*
32	1 - 2	*	0.1	*	*	*	0.3	0.5	0.3	-	0.1	*	0.1
	3	0.2	0.4	0.1	0.1	0.7	1.1	0.7	0.7	*	0.3	0.1	0.3
	4	0.1	0.1	0.1	0.1	0.3	0.6	*	1.1	*	0.1	0.1	0.1
	5	*	*	*	*	*	0.2	*	0.9	-	-	*	*
	6	-	*	*	*	-	*	*	0.1	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.4	0.7	0.1	0.2	1.0	2.2	1.3	3.1	0.1	0.4	0.2	0.4
42	1 - 2	*	*	*	*	0.1	*	-	*	*	0.1	*	0.1
	3	0.1	0.5	0.5	1.0	2.6	0.9	1.8	0.4	0.1	0.9	0.2	0.8
	4	*	0.4	0.8	1.6	1.7	0.8	0.6	0.4	-	0.4	0.3	0.5
	5	*	0.1	0.1	0.6	0.5	0.5	-	0.6	-	*	*	0.1
	6	*	*	*	0.1	0.1	0.1	-	0.3	-	*	*	*
	7	-	*	-	*	*	*	-	-	-	*	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	1.1	1.5	3.2	4.9	2.3	2.4	1.8	0.1	1.4	0.6	1.5

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 04, 2025

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	*	*	*	*	-	*	-	-	*	*
	3	*	*	0.3	0.2	0.4	0.1	-	*	-	*	*	*
	4	*	*	0.5	0.6	0.9	0.3	-	*	*	*	*	0.1
	5	-	*	0.3	0.3	1.4	0.4	-	-	-	*	*	*
	6	-	*	0.1	0.1	1.0	0.3	-	-	-	*	*	*
	7	-	*	*	*	0.3	0.1	-	-	-	*	-	*
	8	-	-	-	-	-	-	-	-	-	-	*	*
Total	----	*	*	1.2	1.2	4.1	1.2	-	0.1	*	0.1	*	0.2
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	*	-	-	-	-	-	-	-	-
	4	-	-	*	*	-	-	-	-	-	-	-	*
	5	-	-	*	*	-	-	-	-	-	*	-	*
	6	-	-	*	*	-	-	-	-	-	-	-	*
	7	-	-	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	*	*	-	-	-	-	-	*	-	*
13 & 23	1 - 2	-	-	-	-	-	0.5	-	-	-	-	-	-
	3	*	*	-	-	-	0.1	-	*	-	-	-	-
	4	-	-	-	-	-	0.1	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	-	-	0.7	-	*	-	-	-	-
33	1 - 2	-	*	-	-	-	*	-	*	-	-	-	*
	3	*	*	*	*	-	0.1	-	*	-	-	*	*
	4	*	*	*	*	-	0.1	-	*	-	-	-	*
	5	-	-	*	*	-	*	-	*	-	-	-	-
	6	-	*	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	-	0.2	-	*	-	-	*	*
43	1 - 2	-	-	*	*	-	-	-	-	-	-	-	*
	3	*	*	*	*	-	*	*	*	-	*	*	*
	4	*	*	0.1	*	*	*	0.1	*	-	-	*	*
	5	*	*	*	*	*	*	-	*	-	-	*	*
	6	-	*	*	*	-	*	-	*	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	0.1	0.1	*	0.1	0.1	0.1	-	*	*	*
53	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	*	*	-	-	-	*	-	*	-	-
	4	-	-	*	*	-	-	-	*	-	-	-	*
	5	-	*	*	*	-	-	-	-	-	-	-	*
	6	-	*	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	0.1	*	-	-	-	*	-	*	-	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
24 - 54	1 - 8	-	-	-	-	*	*	-	-	-	-	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	*
31		-	*	-	*	-	*	-	-	-	*	*	*
32		*	*	*	*	-	*	-	-	-	-	0.1	0.1
33		0.4	0.4	0.1	0.1	0.1	0.1	-	*	0.1	0.2	0.6	0.8
34		2.8	2.9	0.2	0.2	0.5	0.8	-	*	1.9	2.1	3.5	4.4
35		13.1	10.9	1.5	2.4	0.9	3.7	0.1	0.9	19.5	12.7	13.9	15.6
36		23.2	23.7	9.4	13.8	10.5	14.2	18.5	12.9	25.8	31.5	31.1	31.9
37		42.5	42.7	48.5	51.5	51.2	48.7	56.1	35.9	25.5	36.3	38.0	34.7
38		15.7	15.4	32.7	26.7	30.3	26.9	18.8	28.0	19.5	12.7	10.8	10.0
39		2.1	3.3	6.9	4.9	6.1	5.3	6.2	19.6	6.4	3.8	1.9	2.3
40 & Longer		0.1	0.6	0.7	0.4	0.4	0.3	0.3	2.7	1.3	0.8	0.1	0.3
Average Staple		36.61	36.68	37.35	37.18	37.30	37.14	37.13	37.61	36.65	36.59	36.43	36.36
Average Length		1.14	1.14	1.17	1.16	1.17	1.16	1.16	1.17	1.14	1.14	1.14	1.13

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE													
For The Week Ending Dec 04, 2025													
Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	5.7	9.9	3.9	4.4	*	*	0.4	2.0	0.4	0.5	57.4	53.8
	3	8.9	7.3	1.7	2.6	*	*	0.3	1.8	0.6	0.3	14.5	13.5
	4	1.0	0.8	*	*	*	*	*	*	*	*	-	0.1
	5	*	*	-	-	-	-	-	*	*	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	15.6	18.0	5.6	7.1	*	*	0.7	3.9	1.0	0.8	71.9	67.3
31	1 - 2	0.5	1.2	10.0	9.2	1.8	1.3	1.6	3.4	4.4	6.2	12.0	8.4
	3	8.0	9.6	27.2	37.0	6.7	8.7	15.5	20.3	18.9	20.6	11.6	13.2
	4	12.5	9.7	9.1	12.3	2.2	1.9	6.2	8.6	6.2	5.7	1.7	3.7
	5	4.0	2.4	0.5	0.8	0.1	*	0.4	0.6	0.5	0.3	0.1	0.3
	6	0.4	0.2	-	*	*	*	*	*	*	*	-	-
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	25.4	23.1	46.8	59.3	10.7	11.9	23.8	32.9	30.0	32.8	25.3	25.7
41	1 - 2	*	*	0.4	0.5	2.5	2.2	1.0	0.9	2.5	3.3	-	-
	3	0.7	1.1	10.2	9.9	37.5	37.9	30.2	18.5	28.8	29.4	0.5	0.3
	4	3.7	3.7	23.4	16.1	24.0	28.7	31.6	26.1	25.9	24.1	0.5	0.7
	5	4.4	4.2	11.6	4.8	3.3	3.6	6.5	7.4	5.7	4.5	0.3	1.3
	6	2.6	2.0	1.1	0.3	0.1	0.1	0.4	0.6	0.5	0.4	1.0	0.9
	7	0.7	0.4	-	-	-	*	*	*	*	*	0.4	0.3
	8	*	*	-	-	-	-	-	-	-	-	-	-
Total	----	12.2	11.4	46.6	31.6	67.4	72.5	69.6	53.5	63.5	61.6	2.7	3.5
51	1 - 2	-	-	-	*	0.2	0.1	-	*	0.1	0.1	-	-
	3	-	-	*	*	8.7	3.3	0.5	1.1	1.3	0.8	-	-
	4	-	-	0.1	0.4	9.9	5.3	2.0	3.3	2.2	1.7	-	-
	5	*	*	0.4	0.3	1.3	1.2	0.5	1.5	1.1	0.9	-	-
	6	0.1	0.1	0.1	0.1	*	0.1	0.1	0.2	0.2	0.2	0.1	*
	7	0.1	0.1	-	-	-	*	-	*	*	*	-	-
	8	0.1	0.1	-	-	-	-	-	-	-	-	-	-
Total	----	0.3	0.3	0.6	0.8	20.1	9.8	3.1	6.1	4.9	3.7	0.1	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	*	*	*	*	-	-	-	-
	4	-	-	-	*	*	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	*	*	*	*	*	-	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	*	-	-
12 & 22	1 - 2	3.5	3.6	*	0.1	-	-	-	*	-	*	-	0.6
	3	6.6	5.2	*	*	-	*	-	*	*	*	-	*
	4	1.3	1.5	*	*	-	-	-	*	-	*	-	-
	5	*	0.1	-	*	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	11.4	10.4	0.1	0.1	-	*	-	*	*	*	-	0.7
32	1 - 2	0.1	0.1	-	0.1	*	*	*	*	*	*	0.1	2.4
	3	2.0	2.4	0.2	0.3	*	0.1	0.2	0.2	*	0.2	-	0.3
	4	4.8	5.3	*	0.2	*	*	0.2	0.1	*	0.1	-	-
	5	2.7	2.6	-	*	-	*	*	*	*	*	-	-
	6	0.5	0.6	-	*	-	-	-	*	-	-	-	-
	7	0.1	0.1	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-	-	-
Total	----	10.2	11.1	0.2	0.5	*	0.2	0.4	0.3	0.1	0.3	0.1	2.7
42	1 - 2	*	0.1	-	*	*	0.1	*	*	*	*	-	-
	3	1.1	1.4	-	0.2	0.3	1.6	0.7	0.6	0.1	0.3	-	-
	4	4.3	5.1	*	0.4	0.4	1.6	1.0	1.2	0.2	0.3	-	-
	5	6.8	7.3	*	0.1	0.2	0.4	0.2	0.5	0.1	0.1	-	-
	6	4.7	4.9	-	*	*	0.1	*	0.1	*	*	-	-
	7	1.2	1.4	-	-	-	*	-	*	-	*	-	-
	8	0.1	0.2	-	-	-	-	-	-	-	-	-	-
Total	----	18.2	20.4	*	0.6	0.8	3.7	2.0	2.4	0.4	0.7	-	-

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 04, 2025

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	-	*	*	-	*	-	*	-	-
	3	-	-	*	*	0.3	0.5	*	0.1	*	*	-	-
	4	0.1	*	-	*	0.3	0.8	0.2	0.2	*	*	-	-
	5	0.1	*	-	*	0.1	0.3	0.1	0.3	*	*	-	-
	6	0.3	0.3	-	*	*	*	*	0.1	*	*	-	-
	7	0.5	0.6	-	-	-	*	-	*	-	*	-	-
	8	0.4	0.4	-	-	-	-	-	-	-	-	-	-
Total		----	1.41.5	**		0.71.7		0.30.7		*0.1		-	-
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	*	*	-	*	-	-	-	-
	4	-	-	-	-	-	*	-	*	*	*	-	-
	5	-	-	-	-	-	*	-	*	*	*	-	-
	6	-	-	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	-	-	-	**		-*		**		-	-
13 & 23	1 - 2	0.4	0.2	-	-	-	-	-	-	-	-	-	-
	3	0.3	0.2	-	-	-	-	-	-	-	-	-	-
	4	0.1	0.1	-	-	-	-	-	-	-	*	-	-
	5	*	0.1	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	0.80.5	-	-	-	-	-	-	-	*	-	-
33	1 - 2	-	*	-	-	*	*	*	*	*	*	-	-
	3	*	0.1	-	*	*	*	*	*	*	*	-	-
	4	0.2	0.2	-	*	*	*	*	*	*	*	-	-
	5	0.2	0.3	-	*	-	-	-	-	*	*	-	-
	6	0.1	0.1	-	-	-	-	-	-	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	0.60.8	-	*	0.1*		0.1*		**		-	-
43	1 - 2	-	-	-	*	*	*	-	-	-	*	-	-
	3	0.3	0.1	-	*	0.1	*	*	*	*	*	-	-
	4	0.9	0.4	-	*	*	*	*	*	*	*	-	-
	5	0.9	0.6	-	*	*	*	*	*	*	*	-	-
	6	0.9	0.8	-	-	-	*	*	*	*	*	-	-
	7	0.3	0.2	-	-	-	-	-	-	-	-	-	-
	8	0.1	0.1	-	-	-	-	-	-	-	-	-	-
Total		----	3.32.2	-	*	0.2*		0.1*		0.1*		-	-
53	1 - 2	-	-	-	-	-	-	-	*	-	-	-	-
	3	*	*	-	-	*	*	-	*	-	*	-	-
	4	*	*	-	-	*	*	-	*	*	*	-	-
	5	0.1	*	-	-	-	*	-	*	*	*	-	-
	6	0.1	*	-	-	-	*	-	*	*	*	-	-
	7	0.1	0.1	-	-	-	-	-	*	-	-	-	-
	8	0.1	0.1	-	-	-	-	-	-	-	-	-	-
Total		----	0.30.2	-	-	**		-*		**		-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-	-	-
Total		----	**	-	-	-	-	-	*	-	-	-	-
24 - 54	1 - 8	0.3	0.2	-	-	-	-	-	-	*	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		-	-	-	-	-	-	-	*	-	-	-	-
32		-	*	-	-	-	*	-	*	-	-	-	-
33		0.5	0.4	-	0.1	*	*	0.2	0.2	0.1	0.1	-	-
34		2.1	2.0	0.1	1.1	0.2	0.2	1.7	2.2	1.2	1.1	-	1.6
35		6.1	5.4	7.6	10.1	2.2	1.8	10.5	11.6	8.3	7.2	1.8	5.6
36		12.7	11.2	26.0	26.8	13.9	10.1	24.7	27.6	25.7	23.4	9.7	13.6
37		27.0	26.3	50.3	41.7	50.9	48.6	35.5	36.5	47.6	50.2	38.1	30.2
38		29.3	34.3	14.2	15.1	27.9	33.8	17.1	15.0	13.9	14.8	47.1	44.4
39		18.9	17.3	1.5	4.5	4.3	5.1	8.9	5.4	3.0	2.9	1.5	3.4
40 & Longer		3.3	3.1	0.3	0.5	0.6	0.4	1.4	1.5	0.2	0.3	1.8	1.1
Average Staple		37.44	37.48	36.77	36.75	37.19	37.31	36.88	36.72	36.74	36.80	37.42	37.25
Average Length		1.17	1.17	1.15	1.15	1.16	1.17	1.15	1.15	1.15	1.15	1.17	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE For The Week Ending Dec 04, 2025											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	39.3	51.1	1.0	0.4	*	0.4	64.4	41.9	1.4	0.4
	3	6.1	8.7	1.0	0.3	*	0.1	13.3	13.8	1.9	0.5
	4	0.2	0.3	0.1	*	-	*	0.7	1.1	0.1	*
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	45.6	60.1	2.1	0.7	0.1	0.5	78.3	56.8	3.4	1.0
31	1 - 2	20.7	9.4	3.1	2.4	5.9	7.0	1.6	3.1	10.6	8.4
	3	21.1	17.0	20.5	12.8	22.8	14.3	4.3	11.6	43.4	36.9
	4	4.9	3.8	7.0	3.4	6.1	3.2	2.0	5.0	9.3	8.1
	5	0.4	0.2	0.3	0.1	0.5	0.2	0.3	0.6	0.8	0.4
	6	*	*	-	-	*	*	*	*	*	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	47.2	30.4	30.9	18.6	35.4	24.6	8.2	20.3	64.1	53.9
41	1 - 2	0.9	0.3	1.6	2.4	4.7	7.8	*	0.3	1.1	1.7
	3	1.4	1.2	28.3	34.2	22.5	36.0	0.3	2.4	17.2	23.3
	4	0.9	1.0	28.9	31.9	19.0	14.0	0.4	2.4	11.8	17.1
	5	0.4	0.4	3.2	4.4	10.5	1.8	0.1	0.6	2.0	2.6
	6	0.1	*	*	0.1	1.1	0.1	0.1	0.1	0.1	0.1
	7	*	*	-	-	-	*	*	*	*	*
	8	-	-	-	-	-	-	-	*	-	-
Total	----	3.7	2.9	62.1	73.1	57.9	59.7	0.9	5.7	32.2	44.7
51	1 - 2	*	*	0.2	0.1	0.2	0.2	-	*	*	*
	3	-	*	2.2	2.1	3.8	2.4	*	0.1	*	*
	4	*	*	2.0	3.0	0.9	2.2	*	0.2	*	0.1
	5	-	*	0.3	0.9	0.2	0.5	*	0.1	-	*
	6	-	*	*	0.1	0.1	*	*	*	-	*
	7	*	*	-	*	-	*	*	*	-	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	*	*	4.7	6.3	5.2	5.3	0.1	0.4	*	0.2
61	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	*	-	*	*	*	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	-	-	-	*	-	*	*	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-
12 & 22	1 - 2	0.9	2.1	-	-	-	*	7.3	6.5	-	-
	3	0.6	1.1	-	-	-	*	2.4	3.5	*	*
	4	*	0.1	-	-	-	*	0.3	0.6	-	-
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.5	3.4	-	-	-	*	10.1	10.6	*	*
32	1 - 2	0.5	0.3	-	*	*	0.2	0.2	0.4	*	*
	3	0.8	1.1	*	*	*	0.6	0.5	1.5	0.1	*
	4	0.2	0.5	*	*	-	0.1	0.3	1.3	*	0.1
	5	0.1	0.1	-	*	-	*	0.1	0.4	*	*
	6	*	*	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	1.5	2.0	*	0.1	*	0.9	1.1	3.6	0.1	0.1
42	1 - 2	*	*	-	*	0.2	0.9	*	*	-	*
	3	0.1	0.1	0.1	0.3	1.0	5.0	0.1	0.4	*	*
	4	0.1	0.1	0.1	0.6	0.2	1.5	0.1	0.6	*	0.1
	5	*	0.1	*	0.1	*	0.1	0.1	0.3	*	*
	6	*	*	-	*	-	*	*	0.1	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	0.4	0.2	1.0	1.4	7.6	0.3	1.5	*	0.1

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Dec 04, 2025											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	*	0.1	-	*	-	-
	3	-	-	*	*	0.1	0.7	*	*	-	-
	4	*	*	*	0.1	*	0.5	*	0.1	-	-
	5	-	-	*	*	-	0.1	*	*	-	*
	6	-	*	-	*	-	*	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	*	*	*	0.1	0.1	1.3	*	0.1	-
62	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	-	-	*	*	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
	Total	----	-	*	-	-	-	*	*	*	-
13 & 23	1 - 2	*	0.1	-	-	-	-	0.4	0.3	-	-
	3	*	0.1	-	-	-	-	0.3	0.2	-	-
	4	-	*	-	-	-	-	*	*	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	*	0.1	-	-	-	-	0.8	0.6	-
33	1 - 2	*	*	-	-	-	*	*	*	-	-
	3	*	0.2	-	*	-	*	0.1	0.1	-	*
	4	0.1	0.1	*	*	-	*	0.1	0.1	*	*
	5	*	*	-	*	-	-	*	*	-	*
	6	-	*	-	-	-	-	*	*	-	-
	7	-	*	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	0.1	0.4	*	*	-	*	0.2	0.3	*
43	1 - 2	-	*	-	*	*	*	-	*	-	-
	3	*	*	-	*	*	*	*	*	-	-
	4	*	*	-	*	-	*	*	0.1	-	-
	5	*	0.1	-	*	-	*	*	*	-	-
	6	*	*	-	-	-	*	*	*	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
	Total	----	0.1	0.1	-	*	*	*	*	0.1	-
53	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	*	-	*	-	*	-	-
	4	-	*	-	*	-	*	*	*	-	-
	5	-	*	-	*	-	*	*	*	-	-
	6	-	*	-	-	-	-	*	*	-	-
	7	*	*	-	*	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	*	*	-	*	-	*	*	*	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	*	*	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	-	-	-	-	-	-	*	*	-
24 - 54	1 - 8	*	0.2	-	*	-	-	*	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	*	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	*	-	-
29		-	-	-	-	-	-	-	*	-	-
30		-	-	-	-	-	-	-	*	-	-
31		-	*	-	-	-	-	0.1	0.1	-	-
32		*	*	-	-	-	*	0.7	0.5	-	-
33		*	0.4	0.1	0.1	*	0.1	2.9	2.0	*	*
34		0.9	2.3	1.1	1.1	0.6	2.6	10.0	6.0	0.3	0.5
35		4.4	6.8	7.8	7.8	10.7	9.6	18.4	11.7	3.4	5.1
36		11.8	11.9	30.6	32.2	36.9	31.0	24.4	20.3	23.7	22.5
37		27.8	24.5	47.9	44.5	37.7	44.0	27.4	35.9	56.4	56.7
38		22.2	18.9	10.3	11.2	10.8	11.3	10.8	17.2	13.2	12.7
39		22.6	20.3	2.1	2.8	3.0	1.3	3.9	5.3	2.9	2.3
40 & Longer		10.3	14.9	0.2	0.3	0.3	0.1	1.4	1.0	0.1	0.1
Average Staple		37.76	37.73	36.65	36.66	36.58	36.56	36.18	36.59	36.88	36.83
Average Length		1.18	1.18	1.14	1.14	1.14	1.14	1.13	1.14	1.15	1.15

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 04, 2025

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	0.3	0.1	*	*	0.6	0.3	-	*	1.3	0.6	1.1	0.6
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	*	*	0.1	0.3	0.1	2.4	1.4	0.2	0.1	0.1	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	-	-	-	-	-	-	*	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	0.1	*	1.2	-	0.1	-	-	0.1	0.2	0.3	0.3
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	-	-	-	-	*	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	-	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	-	-	-	-	-	-	-
23	-	-	-	*	-	-	-	-	-	-	-	*
24	*	*	-	*	*	*	*	*	-	-	*	*
25	*	*	*	*	*	0.1	*	*	-	-	*	*
26	0.1	*	*	*	*	0.5	0.2	*	*	*	0.4	0.2
27	1.0	0.6	0.1	0.2	0.9	2.0	0.5	0.1	0.2	0.2	3.0	1.7
28	11.1	5.6	1.4	1.9	5.7	7.6	4.3	2.7	2.7	2.4	11.1	7.8
29	30.2	20.8	11.7	11.3	13.6	16.2	22.0	9.7	17.3	12.9	23.2	19.5
30	30.1	30.3	39.8	34.8	18.0	22.5	42.1	16.1	30.9	26.5	25.9	26.4
31	15.5	22.9	31.4	33.9	18.4	20.5	27.9	14.8	22.2	27.0	18.2	21.5
32	8.2	11.9	10.7	13.3	19.3	13.8	1.1	5.7	13.9	17.3	10.6	12.7
33	2.7	5.3	3.7	3.6	13.4	9.5	0.5	4.2	7.4	8.0	5.2	6.2
34	0.9	2.0	1.0	0.8	7.1	5.8	0.4	12.4	4.1	4.5	1.7	2.6
35	0.1	0.5	0.2	0.1	2.5	1.4	0.3	18.9	1.1	1.0	0.5	1.0
36	*	0.1	*	*	0.7	0.2	*	11.5	0.2	0.1	0.1	0.3
37	*	*	*	*	0.3	0.1	0.2	3.4	*	*	*	0.1
38	-	*	-	*	*	*	0.3	0.2	-	-	*	*
39	-	-	-	-	-	-	-	0.1	-	-	-	*
40 & Above	-	-	-	-	-	-	-	0.1	-	-	-	-
Average	30.32	30.85	30.99	31.05	31.60	31.13	30.52	33.08	31.18	31.36	30.54	30.87
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	-	*	-	-	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-	-	-	-	*
2.7	-	*	-	-	-	-	-	*	-	-	-	*
2.8	*	*	-	-	-	-	-	-	-	-	-	*
2.9	*	*	-	-	-	-	-	*	-	-	*	*
3.0	*	*	-	-	-	-	-	0.1	-	-	*	*
3.1	0.1	*	-	-	*	*	-	0.3	-	*	*	*
3.2	*	*	*	*	*	*	-	0.2	-	0.1	*	*
3.3	0.1	0.1	*	*	*	*	-	0.1	-	0.1	0.1	0.1
3.4	0.4	0.3	0.1	*	*	*	-	0.5	*	0.1	0.1	0.2
3.5	1.3	0.7	0.1	*	0.2	0.1	-	1.2	0.1	0.6	0.4	0.3
3.6	1.3	0.9	0.1	0.1	0.4	0.4	0.7	2.2	0.4	0.7	1.0	0.7
3.7	2.2	1.7	0.2	0.1	2.0	1.3	0.5	3.0	1.1	1.2	1.9	1.2
3.8	3.4	2.6	0.2	0.1	1.1	1.1	2.5	6.0	1.7	1.2	3.3	2.0
3.9	5.3	3.8	0.5	0.3	2.0	1.4	3.0	6.6	2.8	1.8	4.5	3.0
4.0	6.6	5.2	1.1	0.5	3.6	2.9	2.8	5.4	5.5	3.2	5.8	4.5
4.1	11.0	7.5	1.5	0.9	6.8	5.6	3.4	5.4	11.8	5.2	8.5	6.6
4.2	11.1	9.6	2.7	1.6	6.0	7.7	6.5	6.3	10.8	6.6	9.8	8.3
4.3	11.2	10.5	4.2	2.9	8.1	8.3	6.3	6.9	11.7	9.1	10.1	9.3
4.4	11.0	10.4	5.2	4.8	10.3	11.0	10.7	8.0	8.9	11.2	9.8	9.9
4.5	8.7	10.3	9.3	7.7	12.4	14.1	7.6	7.9	10.3	12.9	10.1	10.2
4.6	8.5	9.5	15.2	11.8	13.9	13.7	7.7	8.4	10.2	10.7	9.2	9.8
4.7	6.2	7.8	15.8	14.8	12.9	10.3	7.2	10.1	12.2	12.7	7.8	9.3
4.8	4.4	6.4	14.6	15.9	9.3	9.7	9.4	7.8	6.8	9.2	6.2	7.9
4.9	3.7	4.9	11.7	14.1	5.4	6.3	13.4	5.9	2.7	6.2	4.7	6.3
5.0	1.7	3.2	7.8	10.9	4.6	4.2	10.7	3.2	1.2	4.0	3.0	4.6
5.1	1.0	2.0	4.7	6.8	0.9	1.2	5.7	2.6	1.1	2.2	1.8	3.0
5.2	0.6	1.2	2.9	3.8	*	0.4	1.7	1.1	0.5	0.6	1.0	1.6
5.3	0.3	0.7	1.5	1.8	-	0.1	*	0.3	0.1	0.2	0.5	0.8
5.4	*	0.3	0.5	0.6	-	0.1	*	0.3	-	0.2	0.2	0.3
5.5 & Above	*	0.2	0.1	0.2	-	-	-	0.2	-	0.1	*	0.1
Average	4.32	4.42	4.70	4.76	4.49	4.50	4.59	4.38	4.40	4.50	4.40	4.48

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 04, 2025

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	24.4	20.2	0.1	*	*	*	*	*	2.1	1.2	0.2	0.1
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	*	*	*	*	*	-	*	*	0.1	-	-
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	-	-	*	*	*	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.1	0.2	-	0.4	*	0.3	*	0.3	0.2	0.3	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	-	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	*	*	*	*	*	*	0.1	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	-	-	-	-	*	-	-	-	-	-	-
23	*	*	-	-	-	*	-	-	-	-	-	-
24	-	-	-	-	-	*	-	*	*	*	-	-
25	*	*	-	*	-	*	-	*	*	*	-	-
26	0.2	0.1	*	*	*	*	*	0.1	0.4	0.2	-	-
27	1.0	0.5	0.1	0.5	*	*	1.1	1.0	2.7	1.8	2.7	1.7
28	2.3	1.2	4.3	4.5	0.8	0.6	8.3	4.7	14.0	9.4	5.6	6.0
29	4.2	2.9	16.5	19.2	8.6	6.9	14.4	15.5	31.8	27.0	6.5	22.7
30	7.1	7.8	32.2	33.6	41.4	34.6	19.7	27.0	27.8	32.7	33.7	30.9
31	13.2	19.3	22.4	21.1	34.4	37.7	24.0	26.4	14.5	18.6	29.1	23.1
32	19.6	25.4	12.6	11.8	11.9	14.4	18.7	16.1	6.8	7.5	19.5	13.9
33	21.7	22.6	8.7	4.8	2.5	4.8	9.7	6.5	1.8	2.2	0.8	0.5
34	18.0	13.3	2.8	2.7	0.3	1.0	3.3	2.3	0.3	0.5	2.0	1.2
35	10.3	5.7	0.3	1.7	*	0.1	0.7	0.4	*	0.1	0.1	*
36	1.8	1.0	-	0.2	*	*	*	*	-	*	-	-
37	0.3	0.2	-	*	-	*	-	*	-	-	-	-
38	0.1	0.1	-	*	-	*	-	*	-	-	-	-
39	*	*	-	-	-	-	-	-	-	-	-	-
40 & Above	*	*	-	-	-	-	-	-	-	-	-	-
Average	32.87	32.66	31.08	30.94	31.01	31.22	31.18	31.06	30.10	30.36	30.94	30.61
Mike												
2.4 & Below	-	0.1	-	-	-	-	-	-	-	-	-	-
2.5	*	0.2	-	-	-	-	-	-	-	-	-	-
2.6	0.4	0.4	-	-	-	-	-	-	-	-	-	-
2.7	1.6	0.9	-	*	-	-	-	-	-	-	-	-
2.8	2.3	1.7	-	-	-	-	-	-	*	*	-	-
2.9	2.4	1.9	-	*	-	-	-	-	*	*	0.1	*
3.0	2.5	2.3	-	*	-	-	-	-	*	*	0.1	*
3.1	3.0	2.6	*	*	-	-	-	-	0.1	*	-	-
3.2	2.8	2.7	-	*	-	-	*	*	0.3	0.1	0.3	0.2
3.3	4.4	3.3	*	*	-	*	*	*	0.4	0.2	1.8	1.1
3.4	5.5	4.0	*	0.1	*	*	0.1	*	0.6	0.3	0.8	0.5
3.5	6.3	5.0	-	0.1	*	*	0.3	0.1	0.9	0.5	3.4	2.0
3.6	6.8	6.0	-	0.1	0.1	0.1	0.2	0.1	1.2	0.8	1.5	0.9
3.7	7.4	6.1	*	0.2	0.3	0.2	0.4	0.2	2.0	1.4	10.4	6.3
3.8	7.0	5.9	*	0.3	0.6	0.3	0.3	0.3	3.0	2.2	4.6	8.5
3.9	6.2	6.3	0.2	0.6	1.0	0.6	0.7	0.4	4.4	3.2	12.1	14.2
4.0	5.4	6.5	0.3	1.2	2.1	1.3	1.3	0.8	5.7	4.3	11.6	13.8
4.1	5.8	8.3	1.0	2.3	4.0	2.1	2.3	1.3	7.9	6.3	8.1	11.3
4.2	4.7	6.9	2.2	3.4	7.3	3.8	2.8	2.0	10.6	8.8	6.3	8.8
4.3	5.3	7.6	4.8	4.9	9.0	6.0	3.8	3.0	12.6	11.3	8.6	11.0
4.4	6.8	6.8	5.6	6.2	9.6	8.9	5.0	4.5	11.8	12.0	8.2	6.7
4.5	4.8	4.6	7.3	8.2	12.8	12.5	6.7	6.0	11.0	11.5	10.2	6.9
4.6	3.8	3.3	11.0	9.6	13.2	15.4	8.4	8.6	9.7	10.4	2.6	2.3
4.7	1.8	2.7	11.1	11.3	13.6	16.1	9.6	11.2	8.5	9.1	1.2	0.8
4.8	2.0	2.3	17.3	12.9	10.9	13.7	12.9	13.7	5.1	6.7	4.1	2.4
4.9	0.6	1.0	13.5	11.9	8.2	9.4	13.9	14.7	2.4	4.7	3.5	2.1
5.0	0.2	0.5	11.1	9.8	3.8	5.5	11.9	13.4	1.2	3.2	-	-
5.1	*	*	5.5	7.8	2.5	2.6	9.0	9.9	0.5	1.8	-	-
5.2	*	*	1.9	4.5	0.7	0.9	6.3	5.7	0.2	0.9	0.4	0.2
5.3	-	-	2.0	2.7	0.1	0.3	3.4	2.6	0.1	0.3	0.1	0.1
5.4	-	-	0.8	1.1	*	0.1	0.5	1.0	*	0.1	-	-
5.5 & Above	-	-	4.4	0.6	*	*	0.3	0.4	*	*	-	-
Average	3.82	3.90	4.78	4.73	4.56	4.62	4.76	4.80	4.34	4.43	4.13	4.11

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Dec 04, 2025										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	0.9	1.1	1.6	2.5	-	*	2.7	1.9	1.1	1.1
Bark - Level 2	-	*	-	-	-	-	*	*	-	-
Grass - Level 1	0.1	0.1	*	0.1	-	*	0.1	0.2	*	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	-	-	-	*	-	-	*	*	-	*
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	1.5	1.1	-	*	0.1	0.3	0.5	0.7
Seed Coat - Level 2	-	-	-	-	-	-	*	*	-	-
Oil - Level 1	-	-	-	-	-	-	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	*	-	-
Other - Level 1	-	*	-	-	-	-	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	-	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	-	-	-	-	-	-	*	*	-	-
23	-	*	-	-	-	-	*	*	-	-
24	-	*	*	*	-	*	*	*	-	-
25	*	*	*	*	*	*	0.2	0.2	-	-
26	*	0.2	0.3	0.2	*	*	0.7	0.6	2.7	1.1
27	0.2	0.9	2.1	1.3	5.0	0.5	2.7	2.2	10.0	5.6
28	2.5	3.9	14.1	9.1	13.6	3.8	7.5	6.6	22.4	18.0
29	9.6	9.9	38.6	33.0	25.9	20.9	15.3	14.7	31.4	32.1
30	15.0	14.3	29.9	33.9	37.0	38.7	20.0	20.4	19.6	26.8
31	17.7	15.3	9.9	14.9	16.4	24.7	19.8	18.5	9.1	11.6
32	19.1	15.4	4.3	5.7	1.8	8.3	15.0	13.8	3.7	3.7
33	15.2	15.3	0.5	1.6	0.2	2.4	9.3	10.5	1.0	0.9
34	11.3	13.0	0.1	0.3	0.1	0.7	5.5	7.6	0.1	0.2
35	5.6	7.7	*	*	-	0.1	2.5	3.3	*	*
36	2.5	2.7	-	*	-	*	0.9	1.1	-	*
37	1.0	1.0	*	*	-	*	0.4	0.3	-	-
38	0.3	0.3	-	-	-	-	0.2	0.1	-	-
39	*	*	-	-	-	-	*	*	-	-
40 & Above	*	*	-	-	-	-	*	*	-	-
Average	32.30	32.33	29.90	30.21	29.98	30.67	31.24	31.41	29.48	29.79
Mike										
2.4 & Below	*	*	-	-	-	-	*	*	-	-
2.5	*	*	-	-	-	-	*	*	-	-
2.6	*	*	-	-	-	-	0.1	*	-	-
2.7	*	*	-	-	-	-	0.2	0.1	-	-
2.8	0.1	*	*	*	*	*	0.5	0.1	-	-
2.9	0.2	0.1	*	*	0.1	*	0.7	0.2	*	*
3.0	0.2	0.1	*	*	0.1	*	0.9	0.3	0.1	*
3.1	0.3	0.2	*	*	0.1	*	1.2	0.5	0.1	*
3.2	0.4	0.3	0.1	*	0.2	*	1.8	0.8	0.1	*
3.3	0.8	0.5	0.2	0.1	0.2	*	2.3	1.2	0.2	0.1
3.4	0.6	0.7	0.2	0.2	1.6	0.1	3.0	1.7	0.2	0.1
3.5	1.2	1.0	0.5	0.3	2.2	0.2	3.4	2.2	0.4	0.3
3.6	2.3	1.9	1.0	0.5	1.3	0.3	4.0	2.9	0.9	0.8
3.7	3.1	3.3	2.9	1.3	1.1	0.7	4.6	3.7	1.8	2.1
3.8	4.9	5.2	3.2	1.6	3.0	1.0	5.3	4.9	3.6	3.1
3.9	7.0	7.3	4.7	2.7	4.1	1.6	6.1	6.4	5.7	5.8
4.0	9.5	9.0	5.9	4.0	7.0	2.4	6.7	7.9	9.6	7.9
4.1	10.3	10.2	6.1	4.9	9.4	3.8	7.4	9.2	13.3	10.3
4.2	10.5	10.1	8.9	7.5	10.8	5.2	8.1	10.4	16.3	13.8
4.3	10.4	10.5	11.4	9.1	6.6	6.7	8.1	10.7	14.9	15.7
4.4	9.6	9.7	13.2	10.8	5.9	9.5	8.0	10.0	11.7	14.9
4.5	9.2	9.4	12.5	11.3	5.3	11.9	7.5	8.5	6.9	10.6
4.6	8.1	8.5	11.2	11.1	5.6	13.5	6.9	6.6	3.5	7.3
4.7	4.9	6.1	7.1	10.1	9.5	13.5	5.5	4.7	2.1	3.7
4.8	3.0	3.7	4.3	8.2	10.6	11.9	3.5	3.1	4.0	2.0
4.9	2.3	1.6	2.9	6.2	6.1	8.1	2.1	1.7	3.4	1.1
5.0	0.8	0.6	1.6	4.4	5.0	5.4	1.2	1.0	1.2	0.4
5.1	0.1	0.2	0.8	2.8	3.5	2.7	0.5	0.5	0.2	0.1
5.2	*	*	1.1	1.6	0.8	1.0	0.3	0.3	-	*
5.3	-	*	0.2	0.8	-	0.3	0.1	0.2	*	*
5.4	-	-	0.1	0.3	-	*	*	0.1	-	*
5.5 & Above	-	*	*	0.1	-	*	*	0.1	-	*
Average	4.22	4.24	4.36	4.50	4.39	4.57	4.12	4.19	4.25	4.27

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE												
For The Week Ending Dec 04, 2025												
Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	*	-	-	-	-	-	-	-	-	-	*
2.7 - 2.9	*	*	-	-	-	-	-	0.1	-	-	*	*
3.0 - 3.2	0.1	*	*	*	*	*	-	0.6	-	0.1	0.1	0.1
3.3 - 3.4	0.5	0.5	0.1	*	*	*	-	0.6	*	0.1	0.2	0.2
3.5 - 3.6	2.6	1.6	0.2	0.1	0.6	0.5	0.7	3.4	0.5	1.3	1.4	1.1
3.7 - 4.2	39.6	30.4	6.1	3.6	21.5	20.1	18.8	32.6	33.7	19.2	33.8	25.7
4.3 - 4.9	53.7	59.8	76.1	72.1	72.2	73.4	62.4	55.0	62.8	72.0	58.1	62.6
5.0 - 5.2	3.3	6.4	15.4	21.5	5.6	5.8	18.0	6.9	2.8	6.8	5.8	9.2
5.3 & Above	0.3	1.3	2.1	2.7	-	0.2	0.1	0.8	0.1	0.5	0.7	1.2
Average	4.32	4.42	4.70	4.76	4.49	4.50	4.59	4.38	4.40	4.50	4.40	4.48
Leaf												
1 - 2	20.7	16.4	2.3	2.0	37.1	51.3	85.6	45.6	4.9	9.0	13.7	15.1
3	55.2	54.9	38.5	38.8	40.2	34.6	13.0	33.2	54.7	53.4	57.6	59.3
4	20.2	24.5	47.6	46.2	17.0	10.9	1.2	13.1	35.4	32.9	25.3	22.7
5	3.3	3.7	10.5	11.6	4.0	2.5	0.1	6.6	4.6	4.4	3.2	2.7
6	0.5	0.3	1.0	1.3	1.3	0.6	*	1.5	0.3	0.2	0.2	0.1
7	0.1	*	0.1	0.1	0.4	0.1	-	-	*	*	*	*
8	-	*	-	-	-	-	-	-	-	-	*	*
Average	3.07	3.16	3.70	3.72	2.87	2.58	1.96	2.79	3.41	3.33	3.18	3.13
HVI Trash 1/												
00	-	-	-	-	-	*	-	-	-	-	-	-
01	2.8	2.2	0.1	0.1	13.6	20.5	41.9	15.3	0.2	1.1	1.4	1.5
02	23.3	18.3	3.3	3.0	29.9	38.7	45.4	35.4	7.2	10.7	19.4	20.3
03	29.9	28.0	14.2	14.5	22.9	19.9	8.9	20.5	24.0	24.4	31.7	32.6
04	21.8	23.4	24.6	24.5	15.3	10.4	2.5	10.1	30.9	27.5	23.6	23.4
05	11.9	14.3	24.2	23.1	8.4	5.2	0.6	5.9	19.3	18.5	13.2	12.3
06	5.5	7.4	16.3	16.0	4.7	2.6	0.4	4.6	9.9	9.8	6.2	5.7
07	2.7	3.6	9.1	9.4	2.4	1.2	0.2	3.4	4.9	4.5	2.7	2.4
08	1.2	1.6	4.5	4.9	1.1	0.7	0.1	2.4	2.0	2.0	1.1	1.0
09	0.6	0.7	2.2	2.5	0.8	0.4	-	1.4	0.8	0.8	0.4	0.4
10	0.2	0.3	0.9	1.2	0.3	0.2	*	0.7	0.5	0.4	0.2	0.2
11	0.1	0.1	0.4	0.5	0.3	0.1	-	0.3	0.2	0.2	0.1	0.1
12	*	0.1	0.2	0.3	0.2	*	-	0.1	0.1	0.1	*	*
13	*	*	0.1	0.1	*	*	-	*	*	*	*	*
14	*	*	*	0.1	*	*	-	*	*	*	*	*
15	*	*	*	*	*	*	-	-	*	*	*	*
16	*	*	-	-	-	-	-	-	-	*	*	*
17	*	*	-	-	-	-	-	-	*	*	*	*
18 & Above	*	*	-	-	-	-	-	-	*	*	*	*
Average	0.36	0.38	0.50	0.51	0.32	0.26	0.18	0.31	0.43	0.42	0.37	0.36
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	-	-	-	-	-	-	-	-	-	-	*
76	*	*	*	*	-	*	*	*	-	*	*	*
77	*	*	*	*	*	*	*	*	-	*	0.1	0.1
78	0.1	0.3	0.1	0.1	0.1	0.2	1.3	1.4	*	0.1	0.6	0.9
79	1.4	2.2	0.5	0.5	0.7	1.7	22.6	7.2	0.3	1.2	4.5	5.3
80	10.4	11.7	3.0	3.7	7.9	13.3	39.7	12.2	5.2	8.6	20.4	21.7
81	31.1	31.9	18.7	19.8	39.2	38.1	7.8	20.0	37.4	39.9	38.3	36.7
82	39.0	36.3	46.0	43.5	37.7	38.3	9.6	35.1	43.1	39.7	27.0	26.0
83	15.4	15.4	27.8	28.1	13.3	8.0	9.8	18.9	10.4	9.4	7.9	7.9
84	2.4	2.0	3.9	4.1	1.0	0.4	8.9	4.9	3.4	1.0	1.1	1.3
85 & Above	0.1	0.2	0.2	0.2	*	*	0.2	0.1	0.1	*	0.1	0.1
Average	82.09	82.01	82.55	82.53	82.03	81.82	81.13	82.01	82.14	81.96	81.60	81.56
Tenderable 3/	94.6	90.2	79.1	70.5	84.5	88.3	78.2	85.2	95.1	90.6	91.2	87.1
SAMPLES CLASSED	57,179	416,346	97,647	1,137,684	15,004	58,919	4,103	35,091	13,657	67,306	184,098	1,014,678

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 04, 2025

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	0.1	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	0.5	0.6	-	-	-	-	-	-	-	-	-	-
2.7 - 2.9	6.4	4.6	-	*	-	-	-	-	*	*	0.1	*
3.0 - 3.2	8.3	7.6	*	*	-	-	*	*	0.4	0.1	0.3	0.2
3.3 - 3.4	9.9	7.4	*	0.1	*	*	0.1	*	1.0	0.5	2.7	1.6
3.5 - 3.6	13.2	11.0	-	0.2	0.1	0.1	0.5	0.2	2.0	1.3	4.9	2.9
3.7 - 4.2	36.5	39.9	3.7	8.1	15.4	8.3	7.8	5.0	33.5	26.1	53.1	62.8
4.3 - 4.9	25.0	28.4	70.5	65.1	77.4	82.0	60.2	61.7	61.0	65.6	38.4	32.1
5.0 - 5.2	0.2	0.5	18.6	22.1	7.0	9.0	27.2	29.0	2.0	5.9	0.4	0.2
5.3 & Above	-	-	7.2	4.4	0.1	0.5	4.2	4.0	0.1	0.5	0.1	0.1
Average	3.82	3.90	4.78	4.73	4.56	4.62	4.76	4.80	4.34	4.43	4.13	4.11
Leaf												
1 - 2	10.2	15.1	14.3	14.2	4.4	3.7	3.0	6.4	7.4	10.1	69.4	65.2
3	27.9	27.4	39.4	50.0	53.7	52.1	47.5	42.6	49.8	51.6	26.6	27.4
4	28.8	26.8	32.7	29.4	36.9	38.3	41.2	39.8	34.6	31.9	2.2	4.5
5	19.3	17.6	12.5	6.0	4.9	5.5	7.7	10.2	7.4	5.8	0.4	1.7
6	9.7	9.0	1.2	0.4	0.1	0.3	0.5	1.0	0.7	0.6	1.0	1.0
7	3.0	3.0	-	-	-	*	*	*	*	*	0.4	0.3
8	1.0	1.0	-	-	-	-	-	-	-	-	-	-
Average	4.02	3.90	3.46	3.28	3.43	3.47	3.55	3.57	3.44	3.35	2.26	2.31
HVI Trash 1/												
00	-	-	-	-	-	*	-	-	-	-	-	-
01	2.7	4.8	2.5	1.9	0.2	0.1	0.1	0.5	0.5	0.9	24.4	28.5
02	10.5	12.6	14.2	15.0	6.5	5.5	4.8	7.7	9.5	11.9	49.4	41.5
03	13.2	12.5	19.7	24.5	23.6	22.0	19.0	18.9	23.0	24.6	18.4	18.4
04	12.9	12.4	18.3	23.2	29.2	28.9	26.2	23.5	25.1	25.0	4.4	5.3
05	11.9	11.6	14.2	16.2	20.6	21.6	22.0	20.0	18.7	17.9	1.0	2.6
06	11.1	10.2	11.3	9.5	11.7	11.9	14.1	13.3	11.7	10.4	0.7	1.4
07	8.9	8.1	7.5	5.2	5.1	5.6	7.6	8.0	6.1	5.2	0.1	0.9
08	7.3	6.5	5.0	2.5	2.0	2.5	3.5	4.2	3.1	2.4	0.4	0.5
09	5.3	5.2	3.2	1.2	0.7	1.1	1.6	2.1	1.5	1.1	0.6	0.5
10	4.0	4.0	1.7	0.5	0.2	0.4	0.7	1.0	0.5	0.4	0.2	0.1
11	3.2	3.1	1.4	0.2	0.1	0.2	0.3	0.5	0.2	0.2	0.1	0.1
12	2.5	2.5	0.6	0.1	*	0.1	0.1	0.2	0.1	0.1	0.1	0.1
13	1.7	1.9	0.2	*	*	*	0.1	0.1	*	*	-	-
14	1.5	1.3	0.1	*	*	*	*	*	*	*	-	-
15	0.9	0.9	-	-	-	*	*	*	*	*	-	-
16	0.7	0.7	-	-	-	-	-	-	*	*	-	-
17	0.5	0.5	-	-	-	-	-	-	-	*	-	-
18 & Above	1.2	1.3	-	-	-	-	-	-	*	*	-	-
Average	0.61	0.60	0.47	0.41	0.44	0.45	0.47	0.47	0.44	0.42	0.22	0.23
UNIFORMITY 2/												
74 & Below	*	*	-	-	-	-	-	-	-	-	-	-
75	0.1	0.1	-	-	-	-	-	-	-	-	-	-
76	0.5	0.3	-	-	*	*	*	*	*	*	-	-
77	1.8	1.1	-	-	*	*	*	*	*	*	0.1	0.1
78	4.6	3.0	0.1	0.1	0.1	0.1	0.1	0.2	0.4	0.5	0.5	0.3
79	8.8	6.9	1.5	1.2	0.3	0.3	1.4	1.3	2.3	2.9	2.7	1.9
80	15.9	16.4	6.4	7.0	2.6	2.2	9.9	8.8	9.9	11.0	22.3	16.7
81	29.4	31.1	26.4	30.6	18.9	16.2	26.0	30.0	23.9	27.2	39.1	37.6
82	24.2	26.8	39.7	40.8	48.1	49.6	39.7	38.2	34.6	36.1	27.8	35.5
83	11.6	12.3	22.1	17.8	27.4	28.9	18.5	18.0	23.9	19.4	7.4	7.7
84	3.0	2.0	3.6	2.4	2.6	2.6	4.2	3.3	4.7	2.6	0.1	0.2
85 & Above	0.1	0.1	0.1	0.1	0.1	0.2	0.2	0.1	0.3	0.2	-	-
Average	81.44	81.57	82.28	82.19	82.53	82.58	82.23	82.17	82.27	82.10	81.58	81.73
Tenderable 3/	39.5	44.9	73.2	72.0	91.4	85.4	66.4	63.7	93.2	90.1	94.8	96.5
SAMPLES CLASSED	14,013	34,603	8,079	215,077	56,553	529,209	26,018	691,787	78,161	468,347	1,574	2,639

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Dec 04, 2025										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	*	*	-	-	-	-	*	*	-	-
2.5 - 2.6	*	*	-	-	-	-	0.1	*	-	-
2.7 - 2.9	0.4	0.1	*	*	0.1	*	1.4	0.4	*	*
3.0 - 3.2	0.9	0.5	0.1	0.1	0.3	*	3.8	1.7	0.3	0.1
3.3 - 3.4	1.4	1.2	0.4	0.3	1.8	0.1	5.3	2.9	0.4	0.2
3.5 - 3.6	3.5	2.9	1.5	0.7	3.5	0.6	7.4	5.1	1.3	1.1
3.7 - 4.2	45.3	45.0	31.6	22.0	35.4	14.7	38.2	42.4	50.3	42.9
4.3 - 4.9	47.6	49.4	62.4	66.9	49.6	75.1	41.6	45.2	46.3	55.2
5.0 - 5.2	0.9	0.8	3.4	8.9	9.3	9.1	2.0	1.8	1.3	0.6
5.3 & Above	-	*	0.4	1.2	-	0.3	0.1	0.4	*	*
Average	4.22	4.24	4.36	4.50	4.39	4.57	4.12	4.19	4.25	4.27
Leaf										
1 - 2	62.3	63.4	6.0	5.3	11.1	16.5	74.0	52.5	13.1	10.5
3	30.1	29.5	52.2	49.9	50.2	59.2	21.3	33.7	62.6	60.8
4	6.5	6.1	38.0	39.0	26.2	21.5	3.9	11.4	21.3	25.5
5	1.0	0.9	3.8	5.6	11.3	2.6	0.7	2.1	2.8	3.1
6	0.1	0.1	0.1	0.2	1.2	0.2	0.2	0.3	0.1	0.1
7	*	*	-	*	-	*	*	*	*	*
8	-	*	-	-	-	-	*	*	-	-
Average	2.25	2.20	3.40	3.45	3.41	3.10	2.07	2.49	3.14	3.21
HVI Trash 1/										
00	*	0.1	-	-	-	*	0.2	0.1	-	-
01	32.9	34.8	0.4	0.2	0.5	2.0	42.0	25.2	0.5	0.5
02	33.2	31.0	8.4	7.3	12.1	17.2	37.0	30.9	14.3	11.8
03	19.0	17.9	24.5	23.0	24.8	29.9	12.6	19.5	31.2	28.7
04	8.6	9.1	28.9	27.5	21.1	24.6	4.7	11.5	25.5	26.9
05	3.4	4.0	20.5	21.1	15.1	14.1	1.9	6.4	15.3	16.7
06	1.6	1.7	10.5	11.7	10.0	6.7	0.8	3.4	7.4	8.7
07	0.7	0.8	4.3	5.6	7.4	3.1	0.3	1.6	3.6	4.0
08	0.3	0.3	1.6	2.3	4.7	1.3	0.2	0.8	1.4	1.6
09	0.1	0.1	0.6	0.9	2.5	0.6	0.1	0.3	0.6	0.7
10	0.1	0.1	0.1	0.3	1.2	0.2	0.1	0.2	0.2	0.2
11	*	*	*	0.1	0.4	0.1	*	0.1	0.1	0.1
12	*	*	*	*	0.2	*	*	*	*	*
13	*	*	*	*	*	*	*	*	*	*
14	-	*	-	*	*	*	*	*	*	*
15	*	*	*	*	-	*	*	*	-	-
16	*	*	-	*	-	-	*	*	-	*
17	-	*	-	-	-	-	*	*	-	-
18 & Above	*	*	-	*	-	-	*	*	*	*
Average	0.23	0.23	0.42	0.44	0.45	0.38	0.19	0.27	0.39	0.40
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	*	*	-	-
75	*	*	-	-	-	-	*	*	-	-
76	*	*	-	-	-	*	0.2	0.1	-	-
77	0.2	0.2	*	*	-	*	1.0	0.6	-	-
78	0.7	0.9	0.3	0.4	*	0.1	4.4	2.8	0.1	0.2
79	5.5	5.1	2.2	3.3	0.1	0.6	14.9	9.7	0.8	1.6
80	16.8	16.6	15.6	14.7	6.8	6.9	31.5	22.7	4.5	9.6
81	31.3	30.0	33.6	31.2	30.8	32.8	31.6	30.6	16.7	30.6
82	30.6	25.6	32.4	36.4	44.4	43.2	12.5	21.9	43.7	36.7
83	13.4	15.8	14.7	13.0	15.8	15.5	3.1	9.1	28.7	18.7
84	1.3	5.3	1.1	0.9	1.8	0.8	0.5	2.2	5.2	2.4
85 & Above	0.1	0.4	0.1	0.1	0.1	0.1	0.1	0.2	0.4	0.2
Average	81.77	81.90	81.89	81.88	82.22	82.13	80.86	81.39	82.57	82.14
Tenderable 3/	95.0	94.9	92.4	84.9	85.9	82.1	83.0	86.3	96.2	97.1
SAMPLES CLASSED	33,288	192,608	29,772	135,379	11,537	336,413	409,662	3,210,853	23,210	115,426

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE									
For The Week Ending Dec 04, 2025									
Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	3.0	1.6	3.0	7.0	-	-	24.8	16.8
	2	0.2	0.1	4.9	7.2	-	-	19.4	16.2
	3	-	-	0.2	0.1	-	-	0.5	0.5
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		3.1	1.7	8.1	14.4	-	-	44.7	33.6
02	1	41.2	36.1	3.7	5.2	-	-	16.4	14.8
	2	17.1	16.8	38.4	35.9	-	-	33.7	42.5
	3	0.1	0.2	11.3	8.7	-	-	2.4	3.7
	4	-	-	0.2	0.1	-	-	0.1	0.2
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		58.4	53.1	53.6	49.9	-	-	52.6	61.2
03	1	10.8	13.2	0.2	0.1	-	-	0.1	0.1
	2	22.4	27.8	15.1	12.0	-	-	2.1	4.0
	3	0.8	1.1	17.1	17.4	-	-	0.4	0.9
	4	-	-	2.0	1.9	-	-	0.1	0.1
	5	-	-	0.1	*	-	-	-	-
	6	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		33.9	42.0	34.5	31.5	-	-	2.6	5.2
04	1	0.3	0.3	*	*	-	-	-	-
	2	3.8	2.7	0.8	0.4	-	-	0.1	*
	3	0.4	0.3	1.9	2.4	-	-	-	*
	4	-	-	0.5	1.0	-	-	-	*
	5	-	-	*	0.1	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		4.5	3.2	3.3	3.9	-	-	0.1	*
05	1	-	-	-	*	-	-	-	-
	2	-	-	0.1	*	-	-	-	-
	3	-	-	0.3	0.2	-	-	-	-
	4	-	-	0.1	0.1	-	-	-	-
	5	-	-	*	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	0.5	0.3	-	-	-	-
06	1	-	-	-	-	-	-	-	-
	2	-	-	*	*	-	-	-	-
	3	-	-	*	*	-	-	-	-
	4	-	-	-	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	*	*	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	-
STAPLE									
44 & Shorter		-	*	0.6	2.2	-	-	5.6	16.1
46		25.4	20.9	5.5	9.6	-	-	63.9	54.8
48		72.1	74.4	49.0	47.6	-	-	26.7	27.7
50		2.5	4.6	42.2	39.3	-	-	3.5	1.4
52 & Longer		-	*	2.7	1.3	-	-	0.2	0.1
Average Staple		47.54	47.67	48.82	48.56	-	-	46.58	46.29
Average Length		1.38	1.38	1.42	1.41	-	-	1.36	1.35
EXTRANEIOUS MATTER									
Bark		-	-	*	*	-	-	*	*
Grass		-	-	0.5	0.3	-	-	0.1	0.7
Spindle Twist		-	-	*	*	-	-	-	-
Preparation		0.1	*	-	*	-	-	-	-
All Other		-	-	*	*	-	-	*	*

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE For The Week Ending Dec 04, 2025								
Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	-
2.7 - 2.9	*	*	*	*	-	-	1.2	0.3
3.0 - 3.2	-	-	0.2	0.4	-	-	24.5	16.6
3.3 - 3.4	1.1	0.5	2.9	1.6	-	-	12.6	18.8
3.5 - 3.6	1.4	1.0	6.1	7.8	-	-	19.4	16.2
3.7 - 4.2	93.0	94.6	88.2	88.0	-	-	41.2	47.6
4.3 - 4.9	4.5	3.9	2.7	2.2	-	-	1.1	0.5
5.0 - 5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	3.97	3.99	3.90	3.90	-	-	3.55	3.61
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-
2.7	*	*	*	*	-	-	-	-
2.8	-	-	*	*	-	-	-	-
2.9	-	-	*	*	-	-	1.2	0.3
3.0	-	-	*	*	-	-	6.2	3.3
3.1	-	-	0.1	0.1	-	-	8.9	5.6
3.2	-	-	0.1	0.3	-	-	9.5	7.8
3.3	0.5	0.3	1.0	0.6	-	-	7.7	8.2
3.4	0.6	0.3	1.9	1.0	-	-	4.8	10.5
3.5	0.1	*	2.0	2.3	-	-	9.8	10.2
3.6	1.3	0.9	4.1	5.5	-	-	9.6	6.0
3.7	4.9	5.0	9.2	9.9	-	-	7.5	7.5
3.8	15.3	13.0	14.7	17.0	-	-	12.3	10.9
3.9	17.6	18.9	25.1	23.2	-	-	10.3	12.9
4.0	30.6	26.8	21.3	21.4	-	-	5.1	9.3
4.1	15.9	20.7	13.2	11.4	-	-	5.0	5.9
4.2	8.7	10.3	4.8	5.1	-	-	0.9	1.1
4.3	3.6	3.2	1.6	1.5	-	-	1.1	0.4
4.4	0.8	0.6	0.8	0.5	-	-	-	0.1
4.5	0.1	*	0.2	0.2	-	-	-	-
4.6	-	-	*	*	-	-	*	*
4.7	-	*	*	*	-	-	-	-
4.8	-	-	*	*	-	-	-	-
4.9	-	-	-	*	-	-	-	-
5.0	-	-	-	-	-	-	-	-
5.1	-	-	-	-	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	3.97	3.99	3.90	3.90	-	-	3.55	3.61
STRENGTH 1/								
36 & Below	-	-	0.1	1.9	-	-	22.4	15.8
37	*	*	1.0	5.7	-	-	23.7	23.0
38	0.1	0.2	3.2	3.2	-	-	10.3	19.1
39	0.1	0.1	1.7	1.0	-	-	2.5	8.8
40	4.3	8.5	1.1	1.9	-	-	1.7	0.9
41	19.5	25.9	4.3	6.1	-	-	2.4	1.6
42	41.4	38.8	10.7	12.3	-	-	2.2	4.6
43	28.1	20.6	16.1	19.3	-	-	3.3	6.7
44	5.3	5.1	21.8	22.1	-	-	4.8	8.4
45	0.8	0.5	23.7	17.2	-	-	5.4	4.1
46	0.2	0.1	11.9	7.1	-	-	10.7	3.8
47	0.1	0.2	3.2	1.6	-	-	7.7	2.3
48 & Above	*	*	1.5	0.5	-	-	2.8	0.8
Average	42.59	42.35	44.19	43.34	-	-	40.54	39.90
UNIFORMITY								
83 & Below	0.2	0.1	0.5	1.1	-	-	2.7	2.1
84	2.8	3.1	9.2	12.4	-	-	35.7	27.6
85	49.5	41.3	37.2	32.1	-	-	35.2	44.3
86	45.2	51.6	45.7	48.4	-	-	23.1	24.7
87	2.1	3.7	6.7	5.5	-	-	2.9	1.1
88 & Above	0.2	0.1	0.9	0.5	-	-	0.3	0.2
Average	85.92	86.02	85.96	85.91	-	-	85.36	85.41
Samples Classed	2,096	4,356	29,869	164,450	-	-	3,614	13,155

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.