



Weekly Quality of Cotton Classed by Classing Office: Week Ending - 12/18/2025

Agricultural Marketing Service
Cotton Market News

Volume 67, No.20

December 19, 2025

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	31	82.4	60.3	82,996	31	86.7	64.3	611,733
Corpus Christi	9	93.5	90.7	17,478	42	88.1	72.6	1,490,480
Dumas	13	48.3	22.0	25,387	33	53.1	25.0	904,115
Florence	38	91.2	81.0	126,943	40	90.6	79.1	972,728
Lamesa	23	85.6	64.6	61,768	24	86.4	61.7	369,175
Lubbock	52	76.7	54.8	228,404	54	82.4	62.9	1,740,669
Macon	68	92.2	80.2	195,389	68	88.6	74.3	1,736,307
Memphis	26	79.0	54.8	80,488	65	83.0	59.3	2,182,477
Rayville	4	72.2	60.3	5,711	16	70.3	48.2	275,521
Visalia	19	87.3	74.1	28,375	25	86.3	67.4	151,261
United States	283	83.7	66.2	852,939	398	82.7	63.4	10,434,466
AMERICAN PIMA								
Visalia	14			25,980	17			255,060
United States	14			25,980	17			255,060
United States all cotton	294			878,919	406			10,689,526

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

MP_CN100

Source: USDA AMS Cotton and Tobacco Market News

Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov

<https://www.ams.usda.gov/market-news/cotton>

<https://mymarketnews.ams.usda.govcottonmn@ams.usda.gov>

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 18, 2025

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	38.8	46.2	18.5	14.4	*	1.0	0.6	0.5	72.7	74.3
	3	6.6	7.8	14.5	14.5	*	0.8	1.0	0.5	8.2	6.4
	4	0.5	0.3	2.1	1.4	-	*	*	*	0.3	0.3
	5	*	*	*	*	-	*	-	*	*	*
	6	-	*	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	45.8 54.4	35.1 30.3	35.1 30.3	* 1.8	1.8	1.7 1.0	1.0	81.2 80.9	80.9
31	1 - 2	7.5	6.1	6.3	5.0	0.7	2.3	5.0	5.5	2.2	0.8
	3	11.5	9.8	20.6	22.2	14.2	16.6	25.8	22.3	2.3	1.0
	4	5.4	3.2	7.5	9.3	6.5	8.0	6.9	6.0	0.6	0.3
	5	1.2	0.5	1.8	1.0	0.5	0.5	0.2	0.3	0.1	*
	6	0.2	*	0.1	*	-	*	*	*	*	*
	7	*	*	*	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	25.8 19.7	36.3 37.5	36.3 37.5	21.9 27.4	27.4	37.9 34.1	34.1	5.2 2.1	2.1
41	1 - 2	0.1	0.1	1.4	0.6	0.2	0.7	2.0	2.7	*	*
	3	0.8	0.6	13.0	5.3	23.3	19.6	27.9	29.1	*	*
	4	1.6	0.9	4.1	5.0	38.6	32.3	22.8	24.4	*	*
	5	1.8	0.7	2.6	1.3	10.7	8.5	3.7	4.1	0.1	*
	6	0.7	0.3	0.3	0.1	0.3	0.6	0.2	0.3	*	*
	7	0.1	*	0.2	*	*	*	*	*	*	*
	8	*	*	-	-	-	-	*	*	-	-
	Total	----	5.1 2.7	21.6 12.3	21.6 12.3	73.2 61.7	61.7	56.6 60.5	60.5	0.1 *	*
51	1 - 2	-	*	0.1	*	-	*	0.1	0.1	-	-
	3	-	*	0.6	0.2	0.2	1.2	0.9	0.9	-	-
	4	*	*	0.2	0.4	2.2	3.1	1.4	1.6	-	-
	5	*	*	*	0.1	1.8	1.4	0.4	0.7	-	-
	6	*	*	0.1	*	0.1	0.2	*	0.1	-	-
	7	*	*	0.2	*	-	*	*	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
	Total	----	* *	1.1 0.8	1.1 0.8	4.3 5.8	5.8	2.8 3.4	3.4	- -	-
61	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	*	*	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- *	- *	* *	* *	- *	* *	- -	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- -	- -	- -	- -	- *	* *	- -	-
12 & 22	1 - 2	9.8	11.6	*	4.0	-	*	-	*	7.5	11.5
	3	2.4	3.3	0.5	3.8	-	*	*	*	2.1	2.6
	4	0.3	0.3	0.5	1.0	-	*	*	*	0.1	0.2
	5	*	*	0.1	0.1	-	-	-	-	*	*
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	12.7 15.3	1.2 8.9	8.9	- *	* *	* *	* *	9.7 14.4	14.4
32	1 - 2	1.0	0.7	0.1	0.6	-	*	*	*	0.4	0.2
	3	2.2	1.6	0.5	2.7	*	0.1	0.1	0.1	0.6	0.4
	4	1.6	1.0	0.9	2.4	*	0.1	0.1	0.1	0.4	0.2
	5	0.8	0.3	0.7	0.6	*	*	*	*	*	*
	6	0.2	0.1	0.3	*	-	*	-	-	*	*
	7	*	*	*	*	-	-	-	-	-	*
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	5.9 3.7	2.6 6.3	6.3	* 0.3	0.3	0.2 0.2	0.2	1.3 0.8	0.8
42	1 - 2	*	*	*	0.1	*	*	*	*	*	*
	3	0.4	0.3	0.4	0.9	0.1	0.5	0.2	0.2	*	*
	4	0.6	0.6	0.2	1.1	0.2	1.2	0.2	0.3	*	*
	5	0.6	0.6	0.4	0.6	0.1	0.5	*	0.1	-	*
	6	0.5	0.4	0.3	0.1	*	0.1	*	*	-	*
	7	0.2	0.1	0.1	*	-	*	*	*	-	-
	8	0.1	*	-	-	-	-	0.1	*	-	-
	Total	----	2.5 2.1	1.4 2.8	2.8	0.4 2.3	2.3	0.5 0.6	0.6	* *	*

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 18, 2025

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	*	*	-	*	-	*	*	*
	3	-	-	*	*	-	0.1	*	*	-	-
	4	*	*	*	0.1	*	0.2	*	*	-	-
	5	*	*	*	0.1	0.1	0.2	*	*	-	-
	6	*	*	-	*	*	0.1	-	*	-	-
	7	*	*	0.1	*	-	*	*	*	-	-
	8	*	*	-	-	-	-	0.1	*	-	-
Total	----	0.1	0.1	0.1	0.2	0.1	0.6	0.2	0.1	*	*
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	*	*	-	-	-	-	-	-
	8	*	*	-	*	-	-	-	-	-	-
Total	----	*	*	*	*	-	*	-	*	-	-
13 & 23	1 - 2	0.6	0.6	-	0.1	-	-	-	-	0.9	0.7
	3	0.5	0.4	*	0.1	-	-	*	*	0.5	0.4
	4	0.2	0.1	*	*	-	-	-	*	*	*
	5	*	*	-	*	-	-	-	-	*	*
	6	*	*	-	*	-	-	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.4	1.1	*	0.3	-	-	*	*	1.4	1.1
33	1 - 2	0.1	0.1	-	*	-	*	*	*	0.1	0.1
	3	0.2	0.3	*	0.1	-	*	*	*	0.3	0.2
	4	0.1	0.2	0.1	0.1	-	*	*	*	0.2	0.1
	5	0.1	0.1	0.1	*	-	-	*	*	*	*
	6	*	*	*	*	-	-	*	*	*	*
	7	*	*	*	*	-	-	-	-	-	*
	8	*	*	-	-	-	-	-	-	-	-
Total	----	0.5	0.6	0.2	0.3	-	*	*	*	0.7	0.4
43	1 - 2	-	*	-	*	-	-	-	*	-	*
	3	*	*	-	0.1	*	*	*	*	*	*
	4	*	0.1	*	0.1	-	*	*	*	*	*
	5	*	0.1	0.1	0.1	-	*	*	*	*	*
	6	*	0.1	0.1	*	-	*	*	*	*	*
	7	*	*	0.1	*	-	-	*	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
Total	----	0.1	0.2	0.3	0.3	*	*	0.1	*	*	*
53	1 - 2	-	-	-	*	-	*	-	-	-	-
	3	-	*	-	*	-	*	*	*	-	-
	4	*	*	-	*	*	*	*	*	-	-
	5	*	*	-	*	-	*	*	*	-	-
	6	-	*	-	*	-	*	-	*	-	-
	7	*	*	-	*	-	*	*	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
Total	----	*	*	-	*	*	*	*	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	-	-	-	-
24 - 54	1 - 8	0.1	0.1	*	*	-	-	*	*	0.3	0.2
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	*	-	-	-	-	*	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	*	*
31		*	0.1	-	*	-	*	*	*	0.1	0.2
32		0.3	0.5	*	*	-	*	*	*	1.5	1.8
33		3.3	2.8	0.2	0.1	-	0.2	0.2	0.1	8.4	7.2
34		8.7	7.5	1.6	0.7	0.1	1.3	1.7	1.1	22.2	20.2
35		13.1	14.0	5.6	3.7	2.7	8.4	9.2	7.4	31.6	26.4
36		16.8	18.1	15.7	15.5	15.8	25.6	29.5	25.6	23.5	21.3
37		23.1	23.6	45.8	45.9	48.2	42.9	46.0	49.4	10.7	17.4
38		19.9	15.5	20.0	25.4	24.7	16.1	10.7	13.3	1.5	4.6
39		11.4	11.6	9.5	7.9	7.2	4.5	2.4	2.8	0.3	0.8
40 & Longer		3.5	6.3	1.6	0.7	1.3	1.0	0.3	0.3	*	0.1
Average Staple		36.69	36.76	37.11	37.18	37.21	36.81	36.63	36.76	35.07	35.33
Average Length		1.15	1.15	1.16	1.16	1.16	1.15	1.14	1.15	1.09	1.10

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 18, 2025

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	52.3	64.0	1.7	1.7	*	0.4	3.6	4.0	19.2	27.0
	3	15.3	15.5	1.9	0.9	*	0.4	0.9	2.6	3.2	8.8
	4	0.7	0.9	0.1	*	-	*	-	0.2	0.1	0.5
	5	*	*	*	*	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	68.3 80.4	3.6 2.6	0.1 0.9	4.4 6.7	22.5 36.3	22.5 36.3	22.5 36.3	22.5 36.3	22.5 36.3
31	1 - 2	4.0	2.0	7.8	8.5	1.7	2.7	7.1	8.1	17.8	13.5
	3	7.0	3.9	22.7	21.9	6.9	12.4	27.1	33.6	17.0	15.4
	4	2.8	1.7	5.5	3.8	1.7	3.5	8.3	11.8	2.0	4.0
	5	0.5	0.3	0.2	0.1	0.1	0.2	0.6	0.9	0.1	0.6
	6	*	*	*	*	-	*	0.1	*	-	0.1
	7	*	*	-	-	-	*	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	14.3 7.9	36.3 34.4	10.4 18.9	43.1 54.4	36.9 33.5	36.9 33.5	36.9 33.5	36.9 33.5	36.9 33.5
41	1 - 2	*	*	6.7	5.4	3.2	2.3	0.8	0.7	2.2	2.0
	3	0.1	*	31.7	33.2	34.7	30.3	21.0	12.3	13.1	7.4
	4	0.2	0.1	14.8	17.0	19.1	26.8	20.2	16.3	11.1	5.7
	5	0.2	0.1	2.0	2.1	1.7	5.2	8.4	4.5	3.4	2.0
	6	0.1	*	0.1	0.1	0.1	0.4	0.8	0.4	0.5	0.4
	7	*	*	*	*	*	*	-	-	*	*
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	0.6 0.3	55.3 57.7	58.7 65.1	51.2 34.2	30.3 17.5	30.3 17.5	30.3 17.5	30.3 17.5	30.3 17.5
51	1 - 2	*	*	0.2	0.1	0.6	0.1	*	*	*	0.1
	3	*	*	1.8	1.5	9.2	2.7	0.1	*	0.9	0.5
	4	*	*	1.5	1.4	11.3	4.5	0.5	0.3	2.2	0.7
	5	*	*	0.4	0.4	2.9	1.6	0.1	0.3	1.5	0.6
	6	-	-	*	*	0.2	0.3	-	*	0.3	0.2
	7	-	-	*	*	*	*	-	-	0.2	0.1
	8	*	*	-	*	-	-	-	-	*	*
	Total	----	* *	3.9 3.5	24.2 9.3	0.6 0.7	5.1 2.2	5.1 2.2	5.1 2.2	5.1 2.2	5.1 2.2
61	1 - 2	0.1	*	-	*	-	*	-	-	-	-
	3	*	*	*	*	*	*	-	*	-	-
	4	*	*	*	*	*	*	-	*	-	-
	5	-	-	*	*	*	*	-	-	-	*
	6	-	-	*	*	0.1	*	-	-	-	-
	7	-	-	-	*	*	*	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	0.1 *	* *	0.2 *	- *	- *	- *	- *	- *	- *
71	1 - 2	*	*	-	-	-	*	-	-	-	-
	3	*	*	-	-	-	*	-	-	-	-
	4	-	-	-	-	*	*	-	-	-	-
	5	-	-	-	-	*	*	-	-	-	-
	6	-	-	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	* *	- -	* *	- -	- -	- -	- -	- -	- -
12 & 22	1 - 2	6.7	5.3	*	*	-	*	-	0.1	0.1	3.4
	3	3.9	3.1	*	*	-	*	-	0.1	0.2	1.8
	4	0.4	0.4	*	*	-	*	-	0.1	-	0.2
	5	*	*	-	-	-	*	-	*	-	*
	6	*	*	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	11.0 8.7	0.1 0.1	- *	- 0.3	0.3 5.4	0.3 5.4	0.3 5.4	0.3 5.4	0.3 5.4
32	1 - 2	0.4	0.2	*	0.1	*	*	-	0.1	0.3	0.3
	3	1.4	0.6	0.2	0.3	0.1	0.2	-	0.4	0.8	0.8
	4	1.1	0.4	0.1	0.1	0.1	0.1	0.1	0.6	0.3	0.6
	5	0.3	0.1	*	*	*	*	*	0.4	*	0.3
	6	*	*	-	*	-	*	-	0.1	-	*
	7	*	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	3.2 1.3	0.3 0.4	0.2 0.3	0.1 1.5	1.4 2.0	1.4 2.0	1.4 2.0	1.4 2.0	1.4 2.0
42	1 - 2	*	*	*	*	*	0.2	-	*	0.1	*
	3	*	*	0.2	0.6	1.5	1.8	0.1	0.3	0.7	0.6
	4	*	0.1	0.2	0.4	1.8	1.5	0.2	1.0	0.5	0.6
	5	0.1	0.1	*	0.1	0.4	0.4	0.2	0.5	0.3	0.4
	6	*	*	*	*	*	0.1	-	0.2	0.2	0.2
	7	*	*	*	*	*	*	-	-	*	*
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	0.1 0.2	0.4 1.1	3.8 4.0	0.5 2.0	1.8 1.7	1.8 1.7	1.8 1.7	1.8 1.7	1.8 1.7

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 18, 2025

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	*	*	*	*	-	-	*	*
	3	-	-	*	*	0.5	0.4	-	*	0.3	0.1
	4	*	*	*	0.1	0.8	0.7	-	*	0.5	0.2
	5	-	*	*	*	0.4	0.3	-	*	0.3	0.2
	6	-	*	*	*	0.1	0.1	-	*	0.1	0.1
	7	-	*	*	*	*	*	-	-	*	*
	8	-	-	-	*	-	-	-	-	*	*
	Total	----	*	*	0.1	0.1	1.7	1.4	-	0.1	1.2
62	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	-	*	*	*	*	-	-	-	-
	5	-	-	-	*	*	*	-	-	*	*
	6	-	-	-	*	*	*	-	-	-	-
	7	-	-	-	*	*	*	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	-	*	*	*	0.1	*	-	-	*
13 & 23	1 - 2	0.7	0.3	*	*	-	-	-	-	*	0.2
	3	0.4	0.3	*	*	-	-	-	-	*	0.1
	4	0.1	0.1	*	*	-	-	-	-	-	*
	5	*	*	-	-	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	1.2	0.7	*	*	-	-	-	-	*
33	1 - 2	0.3	0.1	*	*	-	*	-	-	-	*
	3	0.4	0.2	*	*	-	*	-	*	*	*
	4	0.3	0.1	*	*	*	*	-	*	*	*
	5	0.1	*	*	*	-	*	-	*	-	*
	6	*	*	-	-	-	*	-	*	-	*
	7	*	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	1.0	0.4	*	*	*	*	-	*	*
43	1 - 2	*	*	-	*	-	*	-	*	*	*
	3	*	*	*	*	0.1	*	-	*	0.1	*
	4	*	*	*	*	0.2	*	-	*	0.1	0.1
	5	*	*	*	*	*	*	-	*	0.1	*
	6	*	*	*	*	*	*	-	*	*	*
	7	*	*	-	*	-	*	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	*	*	*	*	0.3	0.1	-	*	0.3
53	1 - 2	-	-	-	-	*	*	-	-	-	-
	3	-	-	*	*	0.1	*	-	-	-	*
	4	-	-	*	*	0.1	*	-	-	*	*
	5	-	-	*	*	*	*	-	-	0.1	*
	6	-	*	-	*	*	*	-	*	*	*
	7	-	-	-	-	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	-	*	*	*	0.3	*	-	*	0.2
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	-	-	-	-	-	-	-	-	-
24 - 54	1 - 8	0.1	0.1	*	*	*	*	-	-	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	*	*	*	*	-	-	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		*	*	-	-	-	-	-	-	-	-
30		*	*	-	*	-	-	-	-	-	-
31		0.1	0.1	*	*	-	*	-	-	-	*
32		0.5	0.5	0.1	0.1	-	*	-	*	*	*
33		2.8	2.7	1.1	0.7	*	0.1	-	0.2	0.1	0.1
34		8.6	8.3	5.1	4.2	0.5	0.9	*	1.6	1.3	0.9
35		17.0	16.9	17.8	14.9	5.0	4.2	1.4	11.5	5.2	3.7
36		24.7	25.0	31.3	30.4	13.1	15.2	35.9	29.2	10.3	12.9
37		31.5	30.2	33.8	36.8	47.3	47.7	53.5	39.9	39.7	39.9
38		10.9	11.5	9.0	10.3	28.3	26.6	8.1	13.4	26.3	27.0
39		3.0	3.6	1.8	2.4	5.5	4.8	1.2	3.7	8.4	9.7
40 & Longer		0.9	1.2	0.2	0.3	0.2	0.6	-	0.4	8.7	5.8
Average Staple		36.22	36.25	36.26	36.40	37.15	37.11	36.72	36.64	37.73	37.57
Average Length		1.13	1.13	1.13	1.13	1.16	1.16	1.14	1.14	1.18	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 18, 2025

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	6.5	3.4	0.9	0.6	*	*	2.8	1.8	2.6	1.6
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	0.4	0.3	*	0.1	*	*	0.3	0.4
Grass - Level 2	-	-	-	*	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	*	*	-	-
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	-	*	*	1.6	1.0	0.6	*	0.1
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	*	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	*	*	-	*	-	*	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	0.1	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	-	*	-	*	-	-	-	-	*	*
23	*	*	-	*	-	-	-	-	*	*
24	*	0.1	-	*	-	*	*	*	*	0.1
25	*	0.2	*	*	*	*	0.1	*	0.2	0.6
26	0.3	0.7	0.3	0.2	*	0.1	0.5	0.4	1.1	1.8
27	1.3	2.7	0.9	1.2	0.3	0.5	3.4	2.5	4.4	5.2
28	6.2	7.9	4.3	5.2	2.1	4.0	16.4	11.9	11.9	11.3
29	14.8	14.6	15.1	14.9	13.4	15.8	36.1	30.4	19.6	18.8
30	18.5	16.8	24.3	21.8	30.0	28.9	26.1	31.0	22.9	23.1
31	17.8	15.9	21.3	17.7	32.0	26.9	11.9	15.7	20.4	20.1
32	14.5	13.8	14.6	12.4	14.6	15.5	4.3	6.0	10.9	11.4
33	12.1	11.6	9.1	11.5	5.4	6.0	1.0	1.7	5.0	4.6
34	8.3	8.6	6.1	9.7	1.6	1.9	0.1	0.3	2.2	1.8
35	3.5	4.6	3.0	4.0	0.5	0.4	*	0.1	0.9	0.7
36	1.5	1.6	0.7	1.1	*	*	*	*	0.3	0.2
37	1.0	0.8	0.2	0.2	-	-	-	*	0.1	0.1
38	0.1	0.2	*	*	-	-	-	-	*	*
39	*	*	*	*	-	-	-	-	-	-
40 & Above	*	*	-	-	-	-	-	-	-	-
Average	31.63	31.56	31.40	31.59	31.13	31.05	29.88	30.16	30.56	30.46
Mike										
2.4 & Below	-	*	-	-	-	-	-	-	*	*
2.5	0.1	*	-	*	-	-	*	*	0.1	*
2.6	0.1	0.1	-	*	-	-	-	-	0.2	0.1
2.7	0.2	0.1	-	*	-	-	*	*	0.2	0.1
2.8	0.6	0.3	-	*	-	-	*	*	0.2	0.2
2.9	0.8	0.3	-	*	-	-	*	*	0.2	0.4
3.0	0.9	0.4	-	0.1	-	-	*	*	0.3	0.6
3.1	1.0	0.6	*	0.1	-	-	0.1	*	0.6	0.7
3.2	1.2	0.8	-	0.3	-	*	0.1	0.1	1.2	1.0
3.3	1.8	1.1	*	0.5	-	*	0.3	0.2	1.8	1.3
3.4	2.5	1.5	*	0.8	*	*	0.5	0.3	1.8	1.7
3.5	3.2	2.1	0.1	1.2	*	*	0.9	0.5	2.3	2.2
3.6	5.4	3.1	0.3	1.8	0.1	0.1	1.5	0.9	3.0	2.8
3.7	6.0	4.3	0.9	2.6	0.3	0.1	2.6	1.6	4.2	3.4
3.8	6.1	5.3	2.7	4.3	*	0.1	3.8	2.5	5.2	4.4
3.9	7.3	7.2	3.7	6.7	0.1	0.2	5.7	3.9	5.3	5.2
4.0	8.4	8.7	5.5	9.1	0.1	0.4	8.3	5.5	6.1	6.1
4.1	8.9	10.1	8.9	11.1	0.2	0.6	9.9	7.5	7.2	7.2
4.2	9.9	10.9	12.7	12.8	0.5	1.0	10.9	9.8	8.8	8.4
4.3	10.3	10.9	16.9	12.8	0.9	1.7	10.8	11.6	8.5	9.1
4.4	8.7	9.7	18.6	11.3	1.9	2.8	10.1	11.9	8.5	9.6
4.5	6.9	8.0	15.4	8.9	3.3	4.0	8.8	10.9	8.8	9.5
4.6	4.6	6.1	9.2	6.1	6.2	6.4	8.1	9.5	9.0	8.7
4.7	2.4	3.9	3.3	3.7	9.2	9.5	6.5	7.9	6.9	7.2
4.8	1.2	2.4	1.3	2.4	11.9	13.5	4.8	5.8	4.2	4.9
4.9	1.0	1.2	0.3	1.3	14.4	16.1	3.0	4.1	3.0	2.8
5.0	0.4	0.5	0.1	0.8	14.1	16.3	1.7	2.7	1.2	1.4
5.1	*	0.3	*	0.4	14.5	12.9	1.0	1.5	0.5	0.6
5.2	*	0.1	-	0.3	13.0	8.2	0.4	0.8	0.3	0.3
5.3	-	*	-	0.2	6.6	4.0	0.1	0.3	0.2	0.1
5.4	-	-	-	0.1	2.2	1.5	0.1	0.1	*	*
5.5 & Above	-	*	-	0.2	0.7	0.5	*	*	*	*
Average	4.04	4.15	4.32	4.23	4.94	4.88	4.30	4.39	4.21	4.23

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 18, 2025

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	7.5	4.4	1.4	0.7	*	*	0.9	0.7	*	0.1
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	0.2	0.1	0.2	0.1	*	*	-	0.1	-	0.4
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	*	*	*	*	*	*	-	-	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.2	0.1	0.4	0.2	0.1	0.1	-	2.9	*	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	*	-	-	-	-	-	-	-	-
Other - Level 1	*	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	*	*	-	-	-	*	-	-	-	-
23	*	*	*	*	-	*	-	-	-	-
24	*	0.1	*	*	-	*	-	-	-	*
25	0.2	0.2	0.2	*	*	*	-	*	0.1	0.1
26	0.8	0.7	1.2	0.3	*	*	*	0.2	0.6	0.3
27	3.6	2.5	6.1	2.1	0.2	0.2	1.7	1.7	2.4	1.4
28	8.5	6.5	16.9	8.6	1.9	1.9	9.5	6.7	5.2	5.4
29	15.5	13.6	23.9	19.8	13.8	12.3	18.0	18.2	9.4	12.6
30	21.7	19.3	22.4	25.9	38.1	35.6	33.2	30.2	21.2	19.6
31	20.1	19.9	15.7	21.3	32.7	32.9	24.8	19.7	20.5	18.0
32	13.8	15.7	9.0	12.5	9.5	12.4	6.7	12.4	13.3	12.3
33	8.6	10.6	3.4	5.8	3.2	3.7	2.5	5.9	7.9	9.1
34	4.2	6.2	1.0	2.4	0.5	0.9	0.8	3.1	8.6	9.0
35	1.7	2.9	0.2	0.8	0.1	0.1	1.6	1.6	5.2	7.1
36	0.7	1.2	0.1	0.2	*	*	1.2	0.2	3.4	3.7
37	0.3	0.5	*	0.1	-	*	*	*	1.7	1.2
38	0.1	0.2	*	*	-	*	-	*	0.2	0.1
39	*	*	*	*	-	-	-	-	0.1	0.1
40 & Above	-	-	-	-	-	-	-	-	0.1	*
Average	31.03	31.41	30.13	30.79	30.91	31.02	30.66	30.91	31.81	31.89
Mike										
2.4 & Below	*	*	-	-	-	-	-	-	-	-
2.5	*	*	-	*	-	-	-	-	-	-
2.6	0.1	0.1	*	*	-	-	-	*	-	-
2.7	0.2	0.2	*	*	-	*	-	*	-	*
2.8	0.4	0.3	*	*	*	*	-	*	-	*
2.9	0.7	0.5	*	*	-	*	-	*		0.1
3.0	1.0	0.7	*	*	*	*	-	*	*	0.1
3.1	1.6	1.1	*	*	*	*	-	*	0.2	0.4
3.2	2.0	1.6	0.1	*	*	*	0.1	*	1.1	0.6
3.3	2.5	2.2	0.2	0.1	*	*	-	0.1	0.6	0.5
3.4	3.5	2.9	0.4	0.2	*	0.1	0.1	0.1	0.2	0.4
3.5	4.3	3.7	0.7	0.5	*	0.1	0.3	0.2	0.8	0.9
3.6	5.0	4.4	1.3	0.9	*	0.2	0.1	0.3	1.6	1.4
3.7	5.1	5.0	2.3	1.5	0.1	0.4	0.1	0.4	2.2	2.4
3.8	5.3	5.7	3.6	2.3	0.3	0.7	0.3	0.6	3.3	3.3
3.9	5.9	6.2	5.7	3.5	0.6	1.1	0.1	1.1	4.5	3.9
4.0	6.6	6.6	7.8	5.0	1.5	1.7	0.7	1.8	6.2	4.7
4.1	6.6	7.0	8.1	7.0	2.5	2.6	2.4	3.4	6.2	6.1
4.2	6.8	7.6	9.3	8.7	4.3	3.9	5.1	4.4	10.3	8.0
4.3	7.1	7.9	10.5	9.8	5.8	5.6	6.0	5.5	9.6	8.3
4.4	7.2	8.0	10.3	10.2	8.5	7.9	9.6	6.6	9.8	9.1
4.5	6.8	7.6	9.7	10.3	9.6	10.8	14.7	8.7	10.1	10.9
4.6	6.3	6.8	8.9	9.6	12.5	13.9	12.8	9.7	10.5	10.8
4.7	5.4	5.4	7.7	8.8	13.9	15.3	9.6	10.6	7.9	8.9
4.8	4.1	3.7	5.2	7.2	15.1	14.1	5.2	11.6	4.6	7.4
4.9	2.7	2.2	3.7	5.5	9.0	10.3	7.5	10.6	4.4	5.3
5.0	1.6	1.2	2.2	3.9	7.3	6.4	5.6	8.5	3.0	3.5
5.1	0.7	0.7	1.3	2.5	5.6	3.2	6.9	7.1	0.9	1.6
5.2	0.4	0.3	0.5	1.4	2.6	1.2	3.4	4.1	0.7	0.8
5.3	0.2	0.2	0.3	0.7	0.4	0.4	0.1	2.2	0.6	0.5
5.4	0.1	0.1	0.1	0.3	0.1	0.1	4.1	1.1	0.3	0.2
5.5 & Above	*	0.1	*	0.1	*	*	5.4	1.1	0.1	0.1
Average	4.10	4.13	4.34	4.45	4.66	4.62	4.70	4.69	4.36	4.40

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 18, 2025

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	-	*	-	-	-	-	-	-	*	*
2.5 - 2.6	0.2	0.1	-	*	-	-	*	*	0.2	0.1
2.7 - 2.9	1.7	0.7	-	0.1	-	-	*	*	0.6	0.7
3.0 - 3.2	3.1	1.8	*	0.5	-	*	0.2	0.1	2.1	2.4
3.3 - 3.4	4.2	2.6	*	1.4	*	*	0.8	0.5	3.6	2.9
3.5 - 3.6	8.5	5.3	0.4	3.0	0.1	0.1	2.4	1.3	5.4	5.0
3.7 - 4.2	46.6	46.4	34.3	46.6	1.2	2.5	41.3	30.9	36.9	34.6
4.3 - 4.9	35.2	42.1	65.1	46.6	47.7	53.9	52.0	61.7	48.9	51.9
5.0 - 5.2	0.4	0.9	0.2	1.5	41.6	37.4	3.1	5.0	2.1	2.2
5.3 & Above	-	*	-	0.5	9.5	6.1	0.2	0.5	0.2	0.2
Average	4.04	4.15	4.32	4.23	4.94	4.88	4.30	4.39	4.21	4.23
Leaf										
1 - 2	57.9	65.5	26.4	24.9	0.9	4.0	7.7	8.8	83.9	87.7
3	24.7	24.2	50.2	49.7	37.9	38.9	56.0	53.2	14.1	11.0
4	10.5	6.7	15.5	20.9	47.6	45.1	31.4	32.4	1.8	1.2
5	4.7	2.4	5.9	3.9	13.1	11.1	4.4	5.2	0.2	0.1
6	1.7	0.9	1.3	0.5	0.5	0.9	0.2	0.4	*	*
7	0.4	0.2	0.6	0.1	*	*	0.1	*	*	*
8	0.1	0.1	-	*	-	-	0.2	*	-	-
Average	2.52	2.29	3.06	3.03	3.74	3.66	3.34	3.35	1.82	1.69
HVI Trash 1/										
00	*	*	-	*	-	-	-	-	0.4	0.8
01	31.0	34.6	5.4	5.2	*	0.3	0.5	0.6	56.0	62.4
02	30.6	34.0	24.0	22.5	2.2	4.8	10.2	10.6	31.8	27.4
03	14.0	14.4	28.7	27.9	15.0	15.5	26.9	25.1	8.0	6.6
04	8.2	6.9	18.9	20.3	24.7	23.5	27.1	26.1	2.3	1.9
05	5.0	3.6	10.2	12.0	22.2	22.1	18.1	18.4	0.9	0.6
06	3.3	2.1	5.6	6.4	15.3	15.5	9.6	10.4	0.4	0.2
07	2.3	1.3	3.3	3.1	10.3	9.3	4.5	5.0	0.1	0.1
08	1.8	0.9	1.8	1.4	5.6	4.9	1.8	2.2	0.1	*
09	1.2	0.6	0.9	0.6	2.8	2.4	0.7	0.9	*	*
10	1.0	0.4	0.4	0.3	1.1	1.1	0.3	0.4	*	*
11	0.6	0.3	0.3	0.1	0.5	0.5	0.1	0.1	*	*
12	0.4	0.2	0.1	0.1	0.2	0.2	*	0.1	*	*
13	0.2	0.2	0.2	*	0.1	0.1	*	*	*	*
14	0.2	0.1	0.1	*	*	*	*	*	-	*
15	0.1	0.1	*	*	*	*	*	*	-	-
16	0.1	0.1	*	*	-	-	*	*	*	*
17	*	*	-	*	-	-	*	*	-	-
18 & Above	0.1	0.1	*	*	-	-	0.1	*	-	-
Average	0.28	0.24	0.36	0.36	0.51	0.50	0.42	0.42	0.16	0.15
UNIFORMITY 2/										
74 & Below	*	*	-	*	-	-	*	*	*	*
75	0.3	0.1	*	*	-	-	*	*	0.1	0.1
76	0.4	0.2	*	*	-	*	0.1	*	0.3	0.4
77	0.6	0.7	0.2	0.1	*	*	0.1	*	2.0	2.0
78	2.8	2.8	1.0	0.7	0.2	0.2	0.6	0.5	11.1	9.9
79	13.9	12.2	4.9	3.7	0.9	1.0	2.7	2.7	27.4	25.7
80	27.7	27.3	17.7	13.3	5.3	7.1	12.8	11.3	35.9	35.7
81	30.0	28.8	34.9	29.9	27.7	28.4	29.0	28.2	18.6	21.5
82	15.9	17.6	29.4	31.2	34.6	38.2	32.6	35.8	4.2	4.3
83	6.7	8.0	10.4	16.3	23.1	20.2	19.0	19.0	0.4	0.5
84	1.7	2.2	1.3	4.4	7.8	4.8	3.1	2.5	*	*
85 & Above	0.1	0.2	0.1	0.5	0.3	0.1	0.2	0.2	-	*
Average	81.10	81.22	81.68	82.01	82.43	82.29	82.05	82.09	80.16	80.23
Tenderable 3/	82.4	86.7	93.5	88.1	48.3	53.1	91.2	90.6	85.6	86.4
SAMPLES CLASSED										
Week	82,996		17,478		25,387		126,943		61,768	
Season	611,733		1,490,480		904,115		972,728		369,175	

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 18, 2025

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	*	*	-	-	-	-	-	-	-	-
2.5 - 2.6	0.1	0.1	*	*	-	-	-	*	-	-
2.7 - 2.9	1.2	1.0	*	*	*	*	-	*	*	0.1
3.0 - 3.2	4.6	3.5	0.1	0.1	*	*	0.1	0.1	1.3	1.0
3.3 - 3.4	6.0	5.2	0.6	0.3	*	0.1	0.1	0.2	0.9	0.9
3.5 - 3.6	9.3	8.1	2.0	1.3	0.1	0.4	0.4	0.5	2.4	2.3
3.7 - 4.2	36.4	38.1	36.9	27.9	9.4	10.3	8.6	11.7	32.7	28.4
4.3 - 4.9	39.6	41.5	55.9	61.4	74.4	77.8	65.3	63.3	57.0	60.7
5.0 - 5.2	2.6	2.2	4.0	7.8	15.5	10.8	15.8	19.8	4.6	5.8
5.3 & Above	0.3	0.4	0.4	1.1	0.6	0.6	9.6	4.4	1.0	0.7
Average	4.10	4.13	4.34	4.45	4.66	4.62	4.70	4.69	4.36	4.40
Leaf										
1 - 2	64.5	72.0	16.5	15.8	5.6	5.9	11.5	12.9	39.8	46.5
3	28.6	23.6	58.5	58.4	53.2	48.4	49.1	49.5	36.2	35.6
4	5.5	3.7	22.2	22.9	35.2	37.1	29.2	30.3	16.9	12.6
5	1.1	0.6	2.7	2.7	5.6	7.7	9.4	6.5	5.8	4.1
6	0.2	0.1	0.1	0.2	0.5	0.8	0.9	0.8	1.0	1.0
7	*	*	*	*	*	0.1	-	-	0.3	0.2
8	*	*	-	*	-	-	-	-	0.1	*
Average	2.31	2.13	3.11	3.13	3.42	3.49	3.39	3.32	2.86	2.71
HVI Trash 1/										
00	*	*	-	-	-	*	-	-	-	*
01	28.7	36.8	1.6	1.7	0.3	0.5	1.2	1.6	15.3	17.3
02	43.3	40.9	21.6	20.4	8.3	7.3	14.0	14.2	29.5	35.8
03	16.9	14.2	32.3	31.9	24.1	21.0	26.4	24.5	20.5	20.8
04	6.1	4.8	23.1	23.4	27.4	26.1	22.9	23.5	13.1	11.1
05	2.6	1.8	11.9	12.5	19.8	20.3	13.6	16.3	8.5	6.1
06	1.2	0.8	5.4	5.7	11.1	12.3	8.0	9.6	5.6	3.7
07	0.6	0.4	2.3	2.5	5.3	6.6	5.5	5.2	3.5	2.2
08	0.3	0.2	0.9	1.0	2.3	3.2	3.5	2.6	1.8	1.3
09	0.1	0.1	0.4	0.4	0.9	1.6	2.3	1.3	1.1	0.8
10	0.1	*	0.2	0.2	0.3	0.7	1.5	0.7	0.5	0.4
11	*	*	0.1	0.1	0.1	0.3	0.6	0.4	0.3	0.2
12	*	*	*	*	0.1	0.2	0.3	0.2	0.2	0.1
13	*	*	*	*	*	0.1	0.1	0.1	0.1	*
14	*	*	*	*	*	*	0.1	*	*	*
15	*	*	*	*	*	*	-	-	*	*
16	-	*	*	*	-	-	-	-	*	*
17	*	*	*	*	-	-	-	-	-	*
18 & Above	*	*	*	*	-	-	-	-	-	*
Average	0.22	0.20	0.36	0.36	0.43	0.46	0.43	0.42	0.32	0.29
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	-	-	-	-
75	*	*	-	*	-	-	-	-	-	-
76	0.1	0.2	*	*	*	*	-	-	*	*
77	0.7	0.9	0.1	0.1	*	*	-	-	*	*
78	3.4	3.8	0.9	0.7	*	0.1	0.1	0.2	0.2	0.5
79	12.1	12.9	6.2	4.7	0.2	0.5	0.5	1.7	2.9	3.6
80	27.6	29.0	21.7	19.6	4.5	3.9	5.8	10.2	13.7	13.1
81	34.3	33.1	34.8	36.7	22.8	20.8	35.9	31.6	32.0	30.7
82	17.4	16.0	27.2	28.4	45.9	45.6	40.3	37.9	33.4	36.0
83	3.8	3.5	8.2	8.5	23.2	26.2	13.6	16.2	14.3	13.3
84	0.5	0.4	0.9	1.3	3.1	2.7	3.7	2.1	3.2	2.6
85 & Above	*	0.1	0.1	0.1	0.2	0.2	0.1	0.1	0.3	0.2
Average	81.05	80.98	81.54	81.63	82.42	82.47	82.17	82.08	81.98	81.94
Tenderable 3/	76.7	82.4	92.2	88.6	79.0	83.0	72.2	70.3	87.3	86.3
SAMPLES CLASSED										
Week	228,404		195,389		80,488		5,711		28,375	
Season		1,740,669		1,736,307		2,182,477		275,521		151,261

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Dec 18, 2025

Color Grade	Leaf	VISALIA			Quality Designation	VISALIA	
		Week	Season			Week	Season
01	1	4.5	6.7		MIKE	-	-
	2	6.5	7.4		2.4 & Below	-	-
	3	0.3	0.2		2.5 - 2.6	-	-
	4	-	-		2.7 - 2.9	0.1	0.1
	5	-	-		3.0 - 3.2	2.3	1.7
	6	-	-		3.3 - 3.4	5.4	3.2
	7	-	-		3.5 - 3.6	12.0	9.2
Total -----		11.4	14.2		3.7 - 4.2	76.2	83.2
02	1	7.2	7.1		4.3 - 4.9	4.0	2.6
	2	34.5	36.7		5.0 - 5.2	-	-
	3	8.4	8.2		5.3 & Above	-	-
	4	0.4	0.2		Average	3.85	3.87
	5	-	*		ALL RANGE MIKE		
	6	-	-		2.4 & Below	-	-
	7	-	-		2.5	-	-
Total -----		50.4	52.2		2.6	-	-
03	1	0.5	0.5		2.7	-	*
	2	14.1	12.2		2.8	0.1	*
	3	16.0	15.2		2.9	*	0.1
	4	2.4	1.8		3.0	0.1	0.2
	5	0.1	*		3.1	1.1	0.5
	6	*	*		3.2	1.1	0.9
	7	-	-		3.3	1.5	1.2
Total -----		33.1	29.7		3.4	3.9	2.0
04	1	*	*		3.5	5.0	3.4
	2	0.7	0.5		3.6	7.0	5.8
	3	2.4	2.0		3.7	10.2	9.9
	4	1.1	0.8		3.8	14.3	15.9
	5	0.1	0.1		3.9	19.8	21.3
	6	*	*		4.0	16.9	19.7
	7	-	-		4.1	10.5	11.3
Total -----		4.4	3.4		4.2	4.5	5.1
05	1	-	*		4.3	1.9	1.7
	2	0.2	*		4.4	1.4	0.6
	3	0.3	0.2		4.5	0.5	0.2
	4	0.1	0.1		4.6	0.2	*
	5	*	*		4.7	*	*
	6	*	*		4.8	*	*
	7	-	-		4.9	*	*
Total -----		0.8	0.4		5.0	-	-
06	1	-	-		5.1	-	-
	2	*	*		5.2	-	-
	3	*	*		5.3 & Above	-	-
	4	*	*		Average	3.85	3.87
	5	-	*		STRENGTH 1/		
	6	-	*		36 & Below	3.4	3.1
	7	-	-		37	4.4	5.7
Total -----		0.1	*		38	3.6	3.9
07	1	-	-		39	1.9	1.6
	2	-	-		40	2.3	2.0
	3	-	-		41	6.0	6.4
	4	-	-		42	10.4	12.5
	5	-	-		43	17.2	18.2
	6	-	-		44	19.9	20.5
	7	-	-		45	17.0	15.8
Total -----		-	-		46	9.1	7.3
STAPLE					47	3.8	2.3
44 & Shorter		1.7	2.6		48 & Above	0.9	0.7
46		11.8	12.2		Average	43.39	43.17
48		40.9	47.3		UNIFORMITY		
50		42.2	36.3		83 & Below	0.8	1.1
52 & Longer		3.4	1.6		84	11.4	12.0
Average Staple		48.67	48.44		85	35.3	33.9
Average Length		1.41	1.41		86	47.2	47.1
EXTRANEIOUS MATTER					87	5.0	5.6
Bark		*	*		88 & Above	0.3	0.5
Grass		1.0	0.4		Average	85.89	85.90
Spindle Twist		*	*		Samples Classed		
Preparation		-	*		Week	25,980	
All Other		*	*		Season		255,060

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.