



State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	16	93.0	84.6	38,546	21	90.6	78.4	488,104
AR	12	64.5	39.2	73,084	26	70.2	42.0	1,289,999
AZ	9	89.4	78.1	17,996	9	87.6	66.8	91,728
CA	4	82.9	71.2	5,940	9	85.0	70.0	43,478
FL	4	95.9	86.7	7,610	4	91.8	76.8	82,716
GA	53	91.8	78.8	150,596	53	88.1	73.2	1,345,362
KS	3	50.1	39.7	16,601	3	47.1	34.8	65,049
LA	2	53.9	38.3	3,365	14	71.5	47.6	223,278
MO	10	89.7	64.7	29,414	16	85.7	63.3	598,007
MS	12	78.7	67.6	3,982	30	63.7	36.5	705,258
NC	24	92.2	83.0	64,783	26	90.5	78.3	598,282
NM	2	96.8	75.5	964	2	97.2	87.1	6,068
OK	10	94.1	79.5	24,624	10	95.0	83.0	247,050
SC	10	88.7	75.2	42,692	10	86.3	71.8	211,656
TN*	-	-	-	-	17	82.3	63.4	340,307
TX	107	80.5	58.6	352,939	144	85.2	65.7	3,935,334
VA	4	93.6	87.1	19,468	4	96.7	91.2	162,790
United States	283	83.7	66.2	852,939	398	82.7	63.4	10,434,466
AMERICAN PIMA								
AZ	2			849	2			6,883
CA	8			18,870	9			211,998
NM*	-			-	-			-
TX	3			4,833	5			20,863
United States	14			25,980	17			255,060
United States all cotton	294			878,919	406			10,689,526

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 18, 2025

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	1.0	2.4	-	0.1	12.2	24.0	27.6	30.2	1.6	1.8	1.8	1.3
	3	1.9	1.4	*	0.1	2.6	6.4	2.5	13.3	0.6	0.5	1.9	0.8
	4	0.1	*	-	*	0.1	0.4	0.1	0.8	-	*	0.1	*
	5	*	*	-	-	-	*	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	3.0	3.8	*	0.2	14.8	30.8	30.1	44.3	2.2	2.4	3.8	2.0
31	1 - 2	7.0	10.1	0.7	1.1	18.0	13.5	17.8	14.5	0.9	3.3	8.4	7.9
	3	17.8	29.8	7.4	9.2	16.2	13.8	6.3	12.9	5.7	13.0	24.7	21.5
	4	4.9	7.7	2.8	3.4	2.6	2.6	0.2	6.0	2.0	2.9	5.9	3.8
	5	0.2	0.6	0.2	0.1	0.1	0.2	-	1.3	0.2	0.1	0.3	0.1
	6	*	*	-	*	-	*	-	0.2	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	29.9	48.1	11.1	13.9	36.9	30.1	24.3	34.9	8.7	19.2	39.3	33.2
41	1 - 2	6.5	3.3	1.9	0.8	1.4	2.2	5.9	2.4	3.2	3.0	6.9	5.7
	3	33.2	22.6	31.0	26.4	13.2	9.7	21.7	4.9	46.7	38.0	30.4	34.4
	4	16.4	15.6	27.5	35.2	15.7	7.8	5.4	3.2	29.7	28.4	13.7	16.9
	5	2.5	2.9	4.9	8.0	5.2	1.9	0.3	2.8	3.1	3.8	1.9	2.0
	6	0.1	0.3	0.2	0.6	0.7	0.3	-	0.6	0.1	0.2	0.1	0.1
	7	-	*	*	*	0.1	*	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	58.8	44.6	65.5	71.2	36.3	21.9	33.1	14.0	82.7	73.3	53.0	59.1
51	1 - 2	0.4	0.1	0.2	*	*	0.1	0.1	0.1	*	0.1	0.2	0.1
	3	3.0	0.7	4.9	2.3	1.3	0.8	0.3	0.1	3.1	1.3	1.4	1.6
	4	2.8	0.6	9.5	4.8	3.4	1.2	0.3	0.1	1.7	1.6	1.2	1.6
	5	0.6	0.2	2.7	2.2	2.4	0.9	0.1	*	0.4	0.5	0.3	0.4
	6	*	*	0.1	0.4	0.4	0.3	-	*	0.1	*	*	*
	7	*	*	-	0.1	0.3	0.2	-	-	-	*	*	*
	8	-	*	-	-	0.1	*	-	-	-	-	-	*
Total	----	6.8	1.6	17.4	9.8	7.8	3.5	0.8	0.3	5.3	3.5	3.1	3.8
61	1 - 2	-	-	-	*	-	-	-	-	-	-	-	*
	3	*	*	-	*	-	-	-	-	-	-	-	*
	4	0.1	*	*	*	-	-	-	-	*	*	-	*
	5	*	*	*	*	-	*	-	-	-	*	*	*
	6	*	*	*	*	-	-	-	-	-	-	*	*
	7	-	-	-	-	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	*	0.1	*	-	*	-	-	*	*	*	*
71	1 - 2	-	-	-	*	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	*	*	-	-	-	-	-	-	-	-
	6	-	-	*	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	*	*	-	-	-	-	-	-	-	-
12 & 22	1 - 2	-	0.1	-	*	0.1	5.4	0.2	0.3	-	*	*	*
	3	*	*	-	*	0.2	2.7	*	0.5	-	*	*	*
	4	-	*	-	*	-	0.3	-	0.1	-	-	*	*
	5	-	-	-	*	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	0.1	-	*	0.3	8.4	0.2	0.8	-	*	0.1	*
32	1 - 2	*	0.1	*	*	*	0.2	1.5	0.5	-	*	*	*
	3	0.2	0.4	*	0.1	0.2	0.8	2.9	1.0	0.1	0.2	0.2	0.2
	4	0.1	0.1	0.1	0.1	0.1	0.5	1.1	1.0	-	0.1	0.1	0.1
	5	*	*	*	*	*	0.1	0.1	0.7	-	-	*	*
	6	-	*	-	*	-	*	-	0.1	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.4	0.6	0.1	0.2	0.3	1.6	5.6	3.3	0.1	0.3	0.3	0.4
42	1 - 2	*	*	*	*	*	*	0.5	0.1	*	0.1	*	*
	3	0.5	0.4	1.4	1.0	0.2	0.6	3.0	0.7	0.6	0.8	0.1	0.6
	4	0.3	0.4	1.8	1.6	0.3	0.7	1.2	0.5	0.2	0.3	0.1	0.4
	5	*	0.1	0.4	0.5	0.4	0.4	*	0.5	*	*	*	0.1
	6	-	*	*	0.1	0.3	0.1	-	0.3	-	*	*	*
	7	-	*	*	*	0.1	*	-	-	-	*	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.8	1.0	3.7	3.2	1.3	1.9	4.7	2.1	0.9	1.2	0.3	1.2

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 18, 2025

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	*	*	*	*	*	*	-	-	-	*
	3	0.1	*	0.4	0.3	0.5	0.2	*	*	*	*	*	*
	4	0.1	*	0.8	0.6	0.7	0.3	-	*	*	*	*	0.1
	5	-	*	0.4	0.3	0.5	0.4	-	-	-	*	*	*
	6	*	*	*	0.1	0.1	0.2	-	-	-	*	*	*
	7	-	*	-	*	*	0.1	-	-	-	*	*	*
	8	-	-	-	-	*	*	-	-	-	-	-	*
Total	----	0.1	*	1.6	1.3	1.9	1.2	*	0.1	0.1	0.1	*	0.2
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	*	-	-	-	-	-	-	-	-
	4	*	*	*	*	-	-	-	-	-	-	-	*
	5	-	-	-	*	*	*	-	-	-	*	-	*
	6	-	*	-	*	-	-	-	-	-	-	-	*
	7	-	-	-	*	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	*	*	*	*	-	-	-	*	-	*
13 & 23	1 - 2	-	*	-	-	-	0.3	*	*	-	-	*	*
	3	-	*	-	-	*	0.1	-	*	-	-	*	*
	4	*	*	-	-	-	*	-	-	-	-	*	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	-	*	0.4	*	*	-	-	*	*
33	1 - 2	*	*	-	-	-	*	-	*	-	-	*	*
	3	*	*	-	*	-	0.1	0.1	*	-	-	*	*
	4	*	*	-	*	-	*	0.1	*	-	-	*	*
	5	*	*	-	*	-	*	-	*	-	-	-	-
	6	-	*	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	-	0.1	0.1	0.1	-	-	*	*
43	1 - 2	-	-	-	*	-	-	*	*	-	-	-	*
	3	*	*	0.1	*	*	*	0.2	*	-	*	*	*
	4	*	*	0.1	0.1	*	*	0.5	0.1	*	*	*	*
	5	*	*	*	*	0.1	*	0.1	*	-	-	*	*
	6	*	*	*	*	*	*	-	*	-	-	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	*	0.2	0.1	0.2	0.1	0.9	0.2	*	*	*	*
53	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	0.1	*	-	-	-	*	-	*	*	*
	4	*	*	0.1	*	0.1	*	-	*	-	-	*	*
	5	-	*	*	*	0.2	*	-	-	-	-	*	*
	6	-	*	*	*	*	*	-	-	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	0.2	*	0.3	0.1	-	*	-	*	*	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
24 - 54	1 - 8	*	*	*	*	-	*	-	-	-	-	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	*
31		*	*	-	*	-	*	-	-	-	*	*	*
32		*	*	-	*	-	*	-	-	-	-	0.1	0.1
33		0.9	0.5	*	0.1	*	*	*	*	0.3	0.2	1.1	0.8
34		4.6	3.1	0.2	0.2	0.2	0.6	3.1	0.4	5.8	2.3	5.2	4.4
35		15.4	11.2	3.7	2.5	1.9	2.9	9.9	3.1	18.6	13.1	18.3	15.6
36		28.0	24.0	14.3	13.6	6.9	12.5	18.7	14.4	12.9	30.3	32.8	31.5
37		38.3	42.3	48.0	51.2	43.3	46.2	49.5	36.9	39.4	35.5	32.4	35.2
38		10.8	15.1	28.0	27.0	35.0	29.1	15.7	26.6	20.6	14.2	8.1	9.7
39		1.8	3.2	5.3	4.9	11.2	7.5	2.7	16.4	2.3	3.7	1.8	2.3
40 & Longer		0.1	0.5	0.5	0.4	1.6	1.3	0.2	2.2	0.1	0.6	0.2	0.3
Average Staple		36.38	36.66	37.18	37.18	37.51	37.28	36.74	37.45	36.57	36.59	36.22	36.36
Average Length		1.13	1.14	1.16	1.16	1.17	1.16	1.15	1.17	1.14	1.14	1.13	1.13

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 18, 2025

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	3.2	8.7	6.1	4.5	*	*	*	2.0	0.2	0.4	66.4	55.9
	3	8.2	7.6	1.5	2.6	0.1	*	0.1	1.8	0.3	0.3	2.9	8.0
	4	1.3	1.1	-	*	-	*	-	*	*	*	-	*
	5	*	*	-	-	-	-	-	*	-	*	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	12.7	17.4	7.5	7.1	0.2	*	0.1	3.9	0.5	0.8	69.3	64.0
31	1 - 2	0.9	1.7	9.5	9.2	3.4	1.4	2.3	3.4	4.6	5.7	20.7	11.8
	3	14.3	11.6	21.9	36.6	11.4	8.8	24.1	20.3	21.2	20.1	9.9	15.9
	4	20.1	13.2	8.2	12.3	2.2	1.8	7.5	8.6	6.7	5.8	0.1	2.9
	5	5.5	3.5	0.6	0.8	*	*	0.3	0.6	0.3	0.3	-	0.2
	6	1.1	0.4	-	*	-	*	-	*	*	*	-	-
	7	0.1	*	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	41.9	30.4	40.1	58.9	17.0	12.1	34.3	32.9	32.7	31.9	30.7	30.8
41	1 - 2	-	*	0.7	0.5	4.0	2.3	1.0	0.9	2.1	3.2	-	*
	3	0.2	0.8	14.1	10.1	35.2	37.8	32.9	18.8	29.0	29.9	-	0.8
	4	4.9	3.9	21.2	16.2	13.5	27.4	24.2	26.1	26.1	24.7	-	0.9
	5	8.8	5.1	13.3	4.9	0.9	3.3	2.6	7.3	4.5	4.5	-	1.1
	6	3.4	2.3	1.3	0.3	*	0.1	0.1	0.6	0.3	0.3	-	0.7
	7	0.5	0.4	-	-	-	*	-	*	*	*	-	0.1
	8	*	*	-	-	-	-	-	-	*	*	-	-
Total	----	17.8	12.6	50.6	32.0	53.6	71.0	60.7	53.6	62.0	62.6	-	3.7
51	1 - 2	-	-	-	*	1.2	0.1	*	*	0.1	0.1	-	-
	3	-	-	0.1	*	13.1	4.1	0.4	1.1	0.7	0.8	-	-
	4	-	-	0.4	0.4	8.9	5.7	1.9	3.3	1.7	1.7	-	-
	5	*	*	0.1	0.3	2.7	1.3	0.4	1.5	0.6	0.9	-	-
	6	*	*	-	0.1	0.4	0.1	0.1	0.2	0.1	0.2	-	*
	7	*	0.1	-	-	*	*	-	*	*	*	-	-
	8	*	0.1	-	-	-	-	-	-	*	*	-	-
Total	----	0.1	0.2	0.7	0.7	26.3	11.4	2.7	6.1	3.2	3.6	-	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	*	*	-	*	-	*	-	-
	4	-	-	-	*	*	*	*	*	-	*	-	-
	5	-	-	-	-	0.1	*	-	*	-	*	-	-
	6	-	-	-	-	0.2	*	-	*	-	*	-	-
	7	-	-	-	-	*	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	0.3	*	*	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	*	*	-	-	-	-	-	-
	5	-	-	-	-	*	*	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	*	*	-	-	-	*	-	-
12 & 22	1 - 2	0.2	2.3	-	0.1	-	-	-	*	-	*	-	0.3
	3	1.6	3.9	-	*	-	*	-	*	*	*	-	*
	4	1.2	1.4	-	*	-	-	-	*	*	*	-	-
	5	0.2	0.1	-	*	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	3.2	7.7	-	0.1	-	*	-	*	*	*	-	0.3
32	1 - 2	0.1	0.2	-	0.1	-	*	-	*	*	*	-	1.0
	3	2.5	2.9	-	0.3	0.1	0.1	0.1	0.2	0.1	0.1	-	0.1
	4	5.5	5.1	0.2	0.2	*	*	-	0.1	0.1	0.1	-	-
	5	3.7	2.6	*	*	*	*	-	*	*	*	-	-
	6	0.9	0.6	-	*	-	-	-	*	-	-	-	-
	7	0.1	0.1	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-	-	-
Total	----	12.8	11.4	0.2	0.5	0.1	0.2	0.1	0.3	0.2	0.3	-	1.2
42	1 - 2	-	*	-	*	*	0.1	*	*	*	*	-	-
	3	0.1	1.1	0.1	0.1	0.4	1.4	0.6	0.6	0.3	0.3	-	-
	4	0.7	4.0	0.4	0.4	0.4	1.5	0.8	1.2	0.3	0.3	-	-
	5	2.0	5.4	0.4	0.1	0.1	0.4	0.1	0.5	*	0.1	-	-
	6	2.4	3.6	-	*	*	0.1	-	0.1	*	*	-	-
	7	0.8	1.0	-	-	-	*	-	*	0.1	*	-	-
	8	0.5	0.2	-	-	-	-	-	-	0.2	*	-	-
Total	----	6.5	15.5	0.8	0.6	0.9	3.6	1.5	2.4	0.9	0.7	-	-

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 18, 2025

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	-	*	*	-	*	-	*	-	-
	3	-	-	-	*	0.3	0.5	-	0.1	*	*	-	-
	4	*	*	-	*	0.3	0.8	0.1	0.3	0.1	*	-	-
	5	*	*	-	*	0.1	0.3	0.3	0.3	*	*	-	-
	6	0.1	0.2	-	*	0.1	0.1	0.1	0.1	-	*	-	-
	7	0.1	0.4	-	-	*	*	-	*	*	*	-	-
	8	0.1	0.3	-	-	-	-	-	-	0.2	*	-	-
Total	----	0.4	0.9	-	*	0.8	1.7	0.5	0.7	0.3	0.1	-	-
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	-	*	*	-	*	-	*	-	-
	5	-	-	-	-	0.1	*	-	*	-	*	-	-
	6	-	-	-	-	*	*	-	*	-	-	-	-
	7	-	-	-	-	*	*	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	-	0.1	*	-	*	-	*	-	-
13 & 23	1 - 2	0.4	0.2	-	-	-	-	-	-	-	-	-	-
	3	1.5	0.7	-	-	-	-	-	-	*	*	-	-
	4	0.9	0.3	-	-	-	-	-	-	-	*	-	-
	5	0.2	0.1	-	-	-	-	-	-	-	-	-	-
	6	*	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	3.0	1.4	-	-	-	-	-	-	*	*	-	-
33	1 - 2	-	*	-	-	-	*	-	*	*	*	-	-
	3	*	0.1	-	*	-	*	-	*	*	*	-	-
	4	0.3	0.3	-	*	-	*	-	*	*	*	-	-
	5	0.5	0.3	-	*	-	-	-	-	-	*	-	-
	6	0.1	0.1	-	-	-	-	-	-	*	*	-	-
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-	-	-
Total	----	1.0	0.7	-	*	-	*	-	*	*	*	-	-
43	1 - 2	-	-	-	*	-	*	-	-	-	*	-	-
	3	-	0.1	-	*	0.1	*	*	*	*	*	-	-
	4	*	0.3	-	*	0.2	*	-	*	0.1	*	-	-
	5	0.1	0.4	-	*	*	*	-	*	*	*	-	-
	6	0.1	0.5	-	-	*	*	-	*	*	*	-	-
	7	0.1	0.2	-	-	-	-	-	-	*	*	-	-
	8	0.1	0.1	-	-	-	-	-	-	*	*	-	-
Total	----	0.4	1.5	-	*	0.3	0.1	*	*	0.1	*	-	-
53	1 - 2	-	-	-	-	*	*	-	*	-	-	-	-
	3	-	*	-	-	0.2	*	-	*	*	*	-	-
	4	-	*	-	-	0.2	*	*	*	*	*	-	-
	5	-	*	-	-	*	*	-	*	*	*	-	-
	6	-	*	-	-	*	*	-	*	-	*	-	-
	7	*	*	-	-	-	-	-	*	*	*	-	-
	8	*	*	-	-	-	-	-	-	*	*	-	-
Total	----	0.1	0.1	-	-	0.5	*	*	*	*	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	-	-	*	-	-	-	-
24 - 54	1 - 8	0.1	0.1	-	-	-	-	-	-	*	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	-	*	*	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		-	*	-	-	-	-	-	*	*	*	-	-
32		-	*	-	-	-	*	-	*	*	*	-	-
33		-	0.2	-	0.1	0.1	*	-	0.2	0.3	0.1	-	-
34		*	1.2	-	1.1	0.5	0.2	0.4	2.1	1.9	1.3	4.3	2.4
35		1.6	3.9	1.7	10.0	5.3	1.9	7.0	11.6	9.0	7.6	26.2	9.5
36		8.2	10.1	16.3	26.9	11.8	10.4	50.5	27.7	26.3	23.7	5.3	11.1
37		27.7	26.2	68.5	42.1	47.8	48.8	30.8	36.4	48.0	49.9	32.5	27.3
38		40.8	35.9	11.9	15.0	27.4	33.2	6.0	15.0	11.6	14.3	12.6	40.0
39		19.0	19.5	1.7	4.4	6.9	5.1	4.8	5.4	2.5	2.8	17.0	8.5
40 & Longer		2.7	2.8	-	0.4	0.2	0.4	0.7	1.5	0.4	0.3	2.2	1.3
Average Staple		37.76	37.61	36.96	36.75	37.18	37.30	36.52	36.72	36.66	36.77	36.83	37.24
Average Length		1.18	1.18	1.15	1.15	1.16	1.17	1.14	1.15	1.14	1.15	1.15	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE For The Week Ending Dec 18, 2025											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	44.7	49.1	0.5	0.4	-	0.4	53.6	44.8	2.2	0.9
	3	7.4	8.2	1.1	0.5	-	0.1	12.8	13.6	3.2	1.2
	4	0.3	0.3	0.1	*	-	*	0.6	1.0	0.1	*
	5	*	*	-	-	-	*	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	52.4	57.5	1.7	0.9	-	0.5	67.0	59.4	5.5	2.2
31	1 - 2	17.3	11.4	3.2	2.5	-	6.9	4.0	3.1	10.7	8.8
	3	20.7	17.8	21.8	15.6	-	14.5	6.9	10.6	49.6	39.1
	4	3.0	3.7	6.9	4.7	-	3.2	2.4	4.5	7.4	8.4
	5	0.1	0.2	0.2	0.2	-	0.2	0.4	0.5	0.2	0.4
	6	-	*	*	*	-	*	*	*	-	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	41.2	33.2	32.1	23.0	-	24.8	13.8	18.7	67.9	56.8
41	1 - 2	0.2	0.3	2.1	2.2	-	7.7	0.1	0.3	1.4	1.5
	3	0.8	1.1	31.9	33.3	-	35.8	0.8	2.1	15.6	21.0
	4	0.8	1.0	24.6	30.3	-	14.2	0.4	2.0	7.7	15.5
	5	0.1	0.3	3.6	4.2	-	1.8	0.3	0.6	1.2	2.5
	6	-	*	0.1	0.1	-	0.1	0.1	0.1	0.1	0.1
	7	-	*	*	*	-	*	*	*	-	*
	8	-	-	-	-	-	-	*	*	-	-
Total	----	1.8	2.8	62.2	70.1	-	59.6	1.8	5.0	26.1	40.6
51	1 - 2	-	*	0.1	0.1	-	0.2	*	*	-	*
	3	-	*	1.7	1.8	-	2.4	*	0.1	*	*
	4	*	*	1.4	2.5	-	2.2	*	0.2	0.1	0.1
	5	*	*	0.2	0.7	-	0.5	*	*	*	*
	6	-	*	*	0.1	-	*	*	*	-	*
	7	-	*	-	*	-	*	*	*	-	*
	8	-	*	-	-	-	-	*	*	-	-
Total	----	*	*	3.5	5.1	-	5.3	0.1	0.3	0.1	0.1
61	1 - 2	-	-	-	-	-	-	*	*	-	-
	3	-	-	-	*	-	*	*	*	-	-
	4	-	-	-	*	-	*	*	*	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	*	0.1	*	-	-
71	1 - 2	-	-	-	-	-	-	*	*	-	-
	3	-	-	-	-	-	-	*	*	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	*	*	-	-
12 & 22	1 - 2	1.8	2.3	-	-	-	*	7.8	6.6	-	-
	3	0.4	1.0	*	*	-	*	3.4	3.4	*	*
	4	*	0.1	-	-	-	*	0.3	0.6	*	*
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	2.3	3.4	*	*	-	*	11.6	10.6	0.1	*
32	1 - 2	0.2	0.3	*	*	-	0.2	0.5	0.4	*	*
	3	0.8	1.1	0.1	*	-	0.5	1.4	1.5	0.1	*
	4	0.3	0.5	*	*	-	0.1	0.9	1.2	0.1	*
	5	0.1	0.1	*	*	-	*	0.3	0.3	*	*
	6	*	*	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.5	1.9	0.2	0.1	-	0.8	3.1	3.4	0.2	0.1
42	1 - 2	*	*	-	*	-	0.9	*	*	-	*
	3	0.2	0.1	*	0.2	-	5.0	0.1	0.4	-	*
	4	0.3	0.1	0.1	0.4	-	1.5	0.1	0.5	*	*
	5	0.1	0.1	*	0.1	-	0.1	0.1	0.3	*	*
	6	*	*	*	*	-	*	*	0.1	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	0.6	0.4	0.2	0.7	-	7.5	0.4	1.3	*	0.1

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Dec 18, 2025											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	*	*	*	-	-
	3	-	-	*	*	-	0.7	*	*	-	-
	4	-	*	0.1	0.1	-	0.5	*	*	-	*
	5	-	-	*	*	-	0.1	*	*	-	*
	6	-	*	-	*	-	*	-	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	0.1	0.1	-	1.3	*	0.1	-	*
62	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	-	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
Total	----	-	*	-	-	-	*	*	*	-	-
13 & 23	1 - 2	0.1	0.1	-	-	-	-	0.7	0.3	-	-
	3	*	0.1	-	-	-	-	0.4	0.3	*	*
	4	*	*	-	-	-	-	0.1	0.1	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	0.1	0.2	-	-	-	-	1.2	0.7	*	*
33	1 - 2	*	*	-	-	-	*	0.2	0.1	-	-
	3	*	0.2	-	*	-	*	0.3	0.2	0.1	*
	4	*	0.1	*	*	-	*	0.2	0.1	*	*
	5	-	*	-	*	-	-	*	*	*	*
	6	-	*	-	-	-	-	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	0.4	*	*	-	*	0.8	0.4	0.1	*
43	1 - 2	-	*	-	*	-	*	*	*	-	-
	3	-	*	-	*	-	*	*	*	*	*
	4	*	*	-	*	-	*	*	*	*	*
	5	*	*	*	*	-	*	*	*	*	*
	6	-	*	-	-	-	*	*	*	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	*	0.1	*	*	-	*	0.1	0.1	0.1	*
53	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	*	-	*	-	*	-	*	-	-
	4	-	*	-	*	-	*	*	*	-	-
	5	-	*	-	*	-	*	*	*	-	-
	6	-	*	-	-	-	-	-	*	-	-
	7	-	*	-	*	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	*	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	*	-	-
24 - 54	1 - 8	*	0.1	-	*	-	-	0.2	0.1	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	*	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	*	*	-	-
30		-	-	-	-	-	-	*	*	-	-
31		-	*	-	-	-	-	0.1	0.1	-	-
32		*	*	*	*	-	*	0.7	0.5	*	*
33		0.2	0.4	0.1	0.1	-	0.1	4.1	2.3	*	*
34		0.5	1.9	1.6	1.1	-	2.6	11.6	6.9	1.0	0.6
35		3.3	6.3	10.7	8.5	-	9.5	19.7	13.2	6.3	5.4
36		10.5	11.9	39.8	33.6	-	30.9	23.8	21.1	17.7	22.0
37		25.4	25.1	38.4	43.0	-	44.3	27.0	34.4	56.3	55.9
38		27.6	20.1	7.3	10.4	-	11.3	9.2	15.8	15.0	13.3
39		22.8	20.6	2.1	3.0	-	1.3	2.7	4.8	3.1	2.6
40 & Longer		9.6	13.7	*	0.4	-	0.1	1.3	1.0	0.6	0.1
Average Staple		37.83	37.73	36.45	36.63	-	36.56	36.03	36.49	36.90	36.84
Average Length		1.18	1.18	1.14	1.14	-	1.14	1.12	1.14	1.15	1.15

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 18, 2025

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	1.1	0.2	*	*	*	0.2	-	*	1.6	0.7	1.4	0.8
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.2	0.1	*	0.1	-	0.1	-	1.2	0.4	0.1	0.2	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	*	*	-	-	-	-	-	-	*	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.2	0.1	*	1.0	-	*	-	-	0.8	0.2	0.4	0.3
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	-	-	-	-	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	-	-	-	-	-	-	-
23	-	-	-	*	-	-	-	-	-	-	*	*
24	-	*	-	*	-	*	-	*	-	-	*	*
25	0.1	*	*	*	*	*	0.3	*	*	*	0.2	*
26	0.7	0.1	*	*	0.1	0.3	2.2	0.3	0.2	*	1.3	0.4
27	5.3	1.1	0.1	0.2	0.9	1.5	7.7	1.1	1.8	0.3	6.5	2.3
28	17.2	6.8	2.0	1.9	2.7	6.2	15.5	4.3	8.3	3.1	17.1	9.1
29	24.5	21.3	14.0	11.6	7.7	13.9	15.9	10.0	18.5	13.4	23.9	20.3
30	25.7	30.0	32.8	34.7	21.8	21.6	20.3	16.4	22.4	26.4	21.7	25.7
31	16.7	22.2	33.2	33.7	25.5	20.8	7.5	13.3	21.7	26.8	15.3	20.6
32	8.3	11.4	12.6	13.2	17.6	15.5	0.5	6.1	19.2	16.9	8.7	12.1
33	1.2	4.8	4.2	3.6	9.5	10.2	0.6	5.9	6.7	7.8	3.7	5.8
34	0.2	1.8	0.9	0.8	8.9	7.1	8.8	11.8	0.9	4.1	1.1	2.4
35	*	0.5	0.2	0.1	2.4	2.1	8.8	16.6	0.2	1.0	0.3	0.9
36	*	0.1	*	*	1.6	0.5	7.5	10.5	*	0.1	0.1	0.3
37	-	*	-	*	1.3	0.3	3.5	3.3	-	*	*	0.1
38	-	*	-	*	0.1	*	0.6	0.2	-	-	*	*
39	-	-	-	-	*	*	0.1	0.1	-	-	*	*
40 & Above	-	-	-	-	*	*	0.2	0.1	-	-	-	-
Average	30.05	30.76	31.02	31.04	31.84	31.39	31.31	32.83	30.88	31.30	30.12	30.75
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	-	*	-	-	-	-	-	-	-	-	-	-
2.6	*	*	-	-	-	-	-	-	-	-	*	*
2.7	*	*	-	-	-	-	-	*	-	-	-	*
2.8	*	*	*	*	-	-	-	-	-	-	*	*
2.9	*	*	-	-	-	-	0.2	0.1	-	-	*	*
3.0	*	*	*	*	-	-	*	0.1	-	-	*	*
3.1	*	*	*	*	*	*	0.1	0.4	-	*	0.1	*
3.2	0.1	*	-	*	-	*	-	0.3	-	0.1	0.1	*
3.3	0.2	0.1	*	*	*	0.1	0.1	0.2	0.1	0.1	0.2	0.1
3.4	0.7	0.4	*	*	*	0.1	*	0.4	0.1	0.1	0.4	0.2
3.5	1.2	0.7	*	*	*	0.1	-	1.0	0.2	0.5	0.6	0.4
3.6	2.1	1.0	*	0.1	0.2	0.4	*	1.8	0.6	0.8	1.1	0.9
3.7	3.0	1.9	0.1	0.1	0.6	1.3	2.0	2.7	1.1	1.2	2.2	1.4
3.8	3.5	2.8	0.2	0.2	1.2	1.4	5.1	5.5	2.6	1.4	3.6	2.3
3.9	7.8	4.3	0.3	0.3	3.5	2.3	7.6	6.7	5.7	2.2	5.3	3.5
4.0	9.8	5.8	0.8	0.6	4.8	3.8	11.6	6.4	9.4	3.7	7.2	5.0
4.1	10.8	7.8	1.4	1.0	5.5	6.1	8.8	6.2	11.2	6.0	7.4	6.8
4.2	11.8	9.8	2.5	1.7	8.9	8.1	18.2	8.6	10.9	7.4	8.6	8.5
4.3	12.5	10.7	3.5	3.0	10.1	8.7	10.2	8.1	8.8	9.9	10.1	9.4
4.4	10.1	10.5	5.1	4.9	12.1	10.4	5.5	7.8	11.1	12.1	10.3	9.9
4.5	7.8	10.2	6.8	7.6	13.9	13.4	4.4	7.4	10.5	12.7	10.1	10.2
4.6	6.5	9.1	10.0	11.7	13.9	13.2	5.5	7.6	8.6	10.4	9.5	9.8
4.7	4.8	7.4	12.2	14.7	9.7	9.7	4.7	8.8	10.7	11.8	8.2	9.0
4.8	2.6	5.9	14.2	15.7	5.5	8.3	2.1	6.6	6.7	8.5	5.8	7.4
4.9	1.4	4.5	11.5	13.8	4.9	5.8	4.1	5.4	1.6	5.3	4.3	5.8
5.0	1.5	3.0	11.2	10.9	3.5	4.1	2.9	3.3	-	3.3	2.5	4.2
5.1	1.1	1.9	9.9	7.0	1.1	1.4	1.0	2.3	*	1.8	1.4	2.7
5.2	0.5	1.1	6.6	4.0	0.6	0.7	1.4	1.1	*	0.5	0.6	1.4
5.3	0.2	0.7	2.7	1.9	0.1	0.4	2.4	0.6	-	0.1	0.3	0.7
5.4	*	0.3	0.8	0.6	-	0.1	1.6	0.4	-	0.2	0.1	0.3
5.5 & Above	*	0.2	0.3	0.2	-	*	0.3	0.2	-	0.1	*	0.1
Average	4.25	4.40	4.78	4.76	4.46	4.48	4.33	4.36	4.33	4.47	4.37	4.46

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 18, 2025

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	26.1	21.4	0.8	0.1	*	*	-	*	2.8	1.5	-	*
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	*	-	*	-	*	*	*	*	*	-	*
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	-	*	*	-	*	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	0.1	-	0.4	0.2	0.2	0.1	0.3	1.0	0.4	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	-	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	*	*	*	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	*	-	-	-	-	-	-
23	-	*	-	-	-	*	-	-	-	-	-	-
24	-	-	-	-	-	*	-	*	-	*	-	-
25	*	*	-	*	*	*	-	*	0.1	*	-	-
26	0.1	0.1	-	*	0.1	*	*	0.1	0.5	0.3	-	-
27	0.2	0.4	0.5	0.5	0.3	0.1	2.1	1.0	3.1	2.0	0.2	1.6
28	0.6	1.0	3.0	4.4	1.9	0.6	12.0	4.8	15.5	10.4	5.1	5.6
29	1.9	2.5	8.2	19.0	12.8	7.1	28.4	15.6	32.8	28.2	26.6	24.3
30	5.9	7.0	32.6	33.2	44.7	35.2	33.6	26.9	26.8	32.0	47.4	33.5
31	12.0	15.9	34.9	21.1	31.1	37.1	16.2	26.3	14.0	17.6	17.0	19.9
32	22.5	22.8	10.9	11.7	5.9	13.9	4.4	16.1	5.5	7.0	3.4	11.2
33	27.3	23.1	4.1	5.1	2.7	4.8	2.2	6.5	1.5	2.1	-	1.9
34	20.3	17.4	1.2	2.9	0.5	1.1	0.9	2.3	0.2	0.4	0.3	2.0
35	7.2	7.9	2.6	1.8	0.1	0.1	0.3	0.4	*	0.1	-	0.1
36	1.5	1.4	2.0	0.2	*	*	0.1	*	*	*	-	-
37	0.2	0.2	*	*	-	*	-	*	-	-	-	-
38	0.1	0.1	-	*	-	*	-	*	-	-	-	-
39	*	*	-	-	-	-	-	-	-	-	-	-
40 & Above	-	*	-	-	-	-	-	-	-	-	-	-
Average	33.09	32.90	31.29	30.97	30.81	31.21	30.19	31.06	29.99	30.29	30.30	30.60
Mike												
2.4 & Below	-	0.1	-	-	-	-	-	-	-	-	-	-
2.5	0.4	0.3	-	-	-	-	-	-	*	*	-	-
2.6	0.7	0.5	-	*	-	-	-	-	-	-	-	-
2.7	1.1	1.1	-	*	-	-	-	-	*	*	-	-
2.8	2.6	1.9	-	-	-	-	-	-	*	*	-	-
2.9	3.4	2.3	-	*	-	-	-	-	*	*	-	*
3.0	3.4	2.5	-	*	-	-	-	-	*	*	-	*
3.1	3.6	3.0	-	*	-	*	-	-	*	*	-	-
3.2	3.5	3.1	0.1	*	*	*	-	*	0.1	0.1	-	0.1
3.3	5.1	4.1	-	*	*	*	*	*	0.2	0.2	-	0.5
3.4	5.6	4.8	-	0.1	*	*	*	*	0.4	0.3	0.1	0.3
3.5	6.7	5.9	-	0.1	*	*	0.1	0.1	0.7	0.5	0.1	1.0
3.6	7.2	6.3	-	0.1	*	0.1	0.1	0.1	1.4	0.8	3.9	1.1
3.7	6.6	6.6	*	0.2	*	0.1	0.2	0.2	2.5	1.5	5.4	3.7
3.8	6.5	6.2	0.4	0.3	0.1	0.3	0.3	0.3	3.2	2.3	8.3	5.4
3.9	6.5	6.4	0.1	0.6	0.1	0.6	0.6	0.4	4.7	3.4	3.7	7.9
4.0	7.2	6.6	1.0	1.3	1.3	1.3	0.5	0.8	7.0	4.7	2.9	7.7
4.1	5.6	7.7	0.7	2.2	2.5	2.2	3.3	1.3	9.3	6.8	1.8	9.3
4.2	4.5	6.3	3.7	3.4	5.3	4.0	5.3	2.0	11.5	9.1	5.4	9.2
4.3	4.8	6.7	2.4	4.9	7.2	6.3	8.1	3.0	11.5	11.5	4.7	11.0
4.4	5.5	5.7	7.0	6.3	11.5	9.2	10.8	4.5	11.9	12.1	6.6	9.1
4.5	5.1	4.3	8.8	8.2	11.5	12.5	15.8	6.2	10.0	11.4	6.0	10.3
4.6	2.2	2.7	6.2	9.7	14.1	15.2	14.9	8.7	9.6	10.3	12.9	8.8
4.7	1.1	2.0	9.6	11.2	15.4	16.0	8.6	11.2	7.0	8.7	17.8	6.2
4.8	0.9	1.8	4.4	12.6	15.9	13.7	6.9	13.6	4.3	6.2	11.3	4.4
4.9	0.2	0.9	12.6	11.7	7.8	9.1	4.4	14.6	2.6	4.3	5.9	3.0
5.0	0.1	0.3	9.5	9.6	3.6	5.3	6.0	13.3	1.0	2.9	3.1	0.6
5.1	-	*	11.7	7.7	2.3	2.6	6.3	9.9	0.6	1.6	-	0.2
5.2	-	*	5.7	4.4	1.0	1.0	6.7	5.7	0.3	0.8	-	0.1
5.3	-	-	0.1	2.6	0.2	0.4	0.9	2.6	0.1	0.3	-	*
5.4	-	-	6.9	1.3	0.1	0.1	0.2	1.0	0.1	0.1	-	-
5.5 & Above	-	-	9.2	1.4	*	*	*	0.4	*	*	-	-
Average	3.74	3.84	4.87	4.74	4.61	4.62	4.63	4.80	4.32	4.41	4.41	4.27

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Dec 18, 2025										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	1.1	1.1	3.2	2.9	-	*	5.6	2.4	1.9	1.2
Bark - Level 2	-	*	-	-	-	-	-	*	-	-
Grass - Level 1	*	0.1	0.1	0.1	-	*	0.2	0.2	-	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	-	-	*	*	-	-	*	*	-	*
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	1.4	1.1	-	*	0.1	0.2	*	0.5
Seed Coat - Level 2	-	-	-	-	-	-	-	*	-	-
Oil - Level 1	-	-	-	-	-	-	*	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	*	-	-
Other - Level 1	-	*	-	-	-	-	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	-	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	-	-	-	-	-	-	*	*	-	-
23	*	*	-	-	-	-	*	*	-	-
24	-	*	*	*	-	*	*	*	*	*
25	*	*	*	*	-	*	0.2	0.2	0.1	*
26	*	0.1	0.3	0.2	-	*	0.8	0.6	0.8	1.0
27	0.3	0.7	3.0	1.7	-	0.5	3.5	2.4	5.4	5.6
28	2.3	3.4	16.0	11.1	-	3.8	9.0	6.9	20.3	18.7
29	6.5	9.0	41.3	35.2	-	21.0	17.2	15.1	35.7	32.3
30	13.8	14.0	26.2	31.9	-	38.7	22.5	20.7	23.5	26.2
31	22.9	16.6	9.5	13.5	-	24.7	19.8	18.7	9.9	11.4
32	17.4	16.1	2.8	4.9	-	8.2	12.9	13.7	3.6	3.6
33	14.9	15.6	0.7	1.3	-	2.4	7.6	10.1	0.4	0.8
34	10.6	12.9	0.1	0.2	-	0.7	3.8	6.9	0.1	0.2
35	5.2	7.4	*	*	-	0.1	1.7	3.0	*	*
36	2.9	2.7	*	*	-	*	0.7	1.0	*	*
37	2.7	1.2	-	*	-	*	0.2	0.3	-	-
38	0.3	0.3	-	-	-	-	0.1	0.1	-	-
39	*	*	-	-	-	-	*	*	-	-
40 & Above	*	*	-	-	-	-	*	*	-	-
Average	32.43	32.37	29.78	30.09	-	30.66	30.93	31.34	29.68	29.77
Mike										
2.4 & Below	-	*	-	-	-	-	*	*	-	-
2.5	-	*	-	-	-	-	*	*	-	-
2.6	*	*	-	-	-	-	0.1	*	-	-
2.7	*	*	-	-	-	*	0.1	0.1	-	*
2.8	*	*	*	*	-	*	0.3	0.2	*	*
2.9	0.1	0.1	*	*	-	*	0.5	0.3	*	*
3.0	*	0.1	*	*	-	*	0.8	0.4	0.2	*
3.1	*	0.1	*	*	-	*	1.2	0.6	0.2	0.1
3.2	0.4	0.3	0.2	0.1	-	*	1.7	1.0	0.3	0.1
3.3	0.9	0.5	0.2	0.1	-	*	2.1	1.4	0.8	0.2
3.4	1.7	0.8	0.4	0.2	-	0.1	2.8	1.9	1.1	0.3
3.5	2.0	1.1	0.6	0.3	-	0.3	3.6	2.5	2.1	0.6
3.6	5.8	2.3	1.1	0.6	-	0.3	4.4	3.1	3.1	1.2
3.7	6.8	3.6	2.0	1.4	-	0.8	4.8	3.9	4.6	2.6
3.8	7.0	5.4	3.7	2.2	-	1.1	5.2	5.0	6.1	3.9
3.9	7.6	7.4	5.4	3.3	-	1.7	5.9	6.4	9.6	6.5
4.0	7.2	8.8	7.7	5.1	-	2.5	6.8	7.7	13.8	9.2
4.1	8.8	10.1	8.9	6.3	-	3.9	7.3	8.9	14.5	11.7
4.2	9.7	10.0	8.9	8.1	-	5.3	8.1	10.0	13.6	14.2
4.3	12.1	10.8	9.8	9.4	-	6.7	8.3	10.2	10.4	14.7
4.4	9.3	9.9	8.9	10.5	-	9.5	8.2	9.6	6.9	12.8
4.5	7.8	9.6	8.5	10.9	-	11.8	7.6	8.2	5.4	9.0
4.6	5.1	8.0	7.6	10.1	-	13.4	6.8	6.6	3.9	6.0
4.7	2.9	5.6	8.2	9.2	-	13.4	5.2	4.7	1.1	3.2
4.8	1.5	3.4	7.5	7.8	-	11.8	3.6	3.1	0.1	1.8
4.9	2.2	1.5	4.7	5.9	-	8.1	2.4	1.8	0.5	1.0
5.0	0.8	0.5	3.0	4.0	-	5.4	1.3	1.0	1.2	0.5
5.1	*	0.1	1.8	2.4	-	2.7	0.6	0.6	0.5	0.2
5.2	*	*	0.7	1.2	-	1.0	0.3	0.3	*	*
5.3	-	*	0.2	0.5	-	0.3	0.1	0.2	-	*
5.4	-	-	0.1	0.3	-	*	*	0.1	-	*
5.5 & Above	-	*	*	0.1	-	*	*	0.1	-	*
Average	4.14	4.23	4.37	4.46	-	4.56	4.13	4.18	4.11	4.24

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 18, 2025

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	*	*	-	-	-	-	-	-	-	-	*	*
2.7 - 2.9	*	*	*	*	-	-	0.2	0.1	-	-	*	*
3.0 - 3.2	0.1	0.1	*	*	*	*	0.1	0.8	-	0.1	0.1	0.1
3.3 - 3.4	0.9	0.5	*	*	*	0.2	0.1	0.6	0.2	0.2	0.6	0.3
3.5 - 3.6	3.3	1.7	0.1	0.1	0.2	0.5	*	2.8	0.8	1.3	1.7	1.3
3.7 - 4.2	46.6	32.3	5.3	3.9	24.5	23.0	53.3	36.2	40.9	21.9	34.4	27.5
4.3 - 4.9	45.7	58.3	63.1	71.4	70.0	69.5	36.6	51.8	58.1	70.6	58.2	61.5
5.0 - 5.2	3.1	6.0	27.7	21.8	5.2	6.2	5.3	6.6	*	5.6	4.4	8.3
5.3 & Above	0.2	1.1	3.8	2.7	0.1	0.6	4.4	1.3	-	0.4	0.5	1.0
Average	4.25	4.40	4.78	4.76	4.46	4.48	4.33	4.36	4.33	4.47	4.37	4.46
Leaf												
1 - 2	14.9	16.1	2.9	2.1	31.7	45.6	53.7	48.1	5.6	8.3	17.3	15.1
3	56.7	55.3	45.4	39.5	34.4	35.2	36.9	33.5	56.8	53.9	58.9	59.2
4	24.8	24.5	42.7	45.8	23.0	13.8	8.9	11.9	33.6	33.2	21.2	22.8
5	3.4	3.7	8.7	11.3	8.8	4.1	0.5	5.4	3.7	4.4	2.5	2.7
6	0.2	0.3	0.4	1.2	1.6	1.0	-	1.2	0.2	0.2	0.1	0.1
7	*	*	*	0.1	0.4	0.2	-	-	-	*	*	*
8	-	*	-	-	0.1	*	-	-	-	-	-	*
Average	3.17	3.17	3.58	3.70	3.11	2.73	2.42	2.71	3.36	3.34	3.09	3.13
HVI Trash 1/												
00	-	-	-	-	-	*	-	-	-	-	-	-
01	1.8	2.1	0.1	0.1	11.4	17.4	25.7	17.5	0.3	0.9	1.6	1.5
02	18.1	18.2	4.3	3.1	25.2	35.7	31.1	35.7	7.6	10.0	23.1	20.3
03	29.5	28.3	18.2	14.9	18.7	19.9	20.1	20.3	24.9	24.2	33.2	32.6
04	25.2	23.6	27.0	24.8	14.6	11.5	13.5	10.2	31.3	28.5	22.2	23.5
05	13.7	14.2	22.5	23.0	11.0	6.6	6.2	5.7	19.9	18.8	11.2	12.3
06	6.6	7.3	14.0	15.8	7.9	3.9	2.4	4.0	9.3	9.7	5.0	5.6
07	3.1	3.6	7.6	9.2	5.2	2.2	0.8	2.8	3.8	4.4	2.1	2.4
08	1.3	1.5	3.7	4.7	2.7	1.2	0.2	1.9	1.6	2.0	0.9	1.0
09	0.4	0.7	1.7	2.4	1.6	0.8	0.1	1.1	0.8	0.8	0.4	0.4
10	0.2	0.3	0.6	1.1	0.8	0.4	-	0.5	0.3	0.4	0.2	0.2
11	0.1	0.1	0.2	0.5	0.4	0.2	-	0.2	0.1	0.1	0.1	0.1
12	*	0.1	0.1	0.2	0.2	0.1	-	0.1	0.1	0.1	*	*
13	*	*	*	0.1	0.2	0.1	-	*	-	*	*	*
14	*	*	*	*	0.1	*	-	*	-	*	*	*
15	*	*	*	*	*	*	-	-	*	*	*	*
16	*	*	-	-	*	*	-	-	-	*	*	*
17	*	*	-	-	-	*	-	-	-	*	*	*
18 & Above	*	*	-	-	-	*	-	-	-	*	*	*
Average	0.37	0.38	0.48	0.51	0.37	0.29	0.26	0.30	0.42	0.42	0.35	0.36
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	-	-	-	-	-	-	-	-	-	-	*
76	*	*	*	*	*	*	-	*	-	*	*	*
77	*	*	*	*	0.1	*	*	*	*	*	0.1	0.1
78	0.6	0.3	0.1	0.1	0.1	0.2	0.3	1.2	*	0.1	1.0	0.8
79	5.2	2.5	0.5	0.5	1.5	1.6	2.1	7.5	1.5	1.1	6.6	5.2
80	21.2	12.7	4.8	3.8	10.3	12.3	24.8	15.1	9.9	8.3	22.2	21.1
81	31.0	31.3	26.1	20.3	32.1	35.6	40.3	23.4	30.3	37.6	35.9	36.6
82	30.9	35.8	40.0	43.3	42.8	39.8	10.7	30.2	38.6	40.8	25.6	26.5
83	9.9	15.2	23.7	27.7	12.0	9.7	13.6	17.2	19.2	10.8	7.5	8.1
84	1.2	2.0	4.6	4.1	1.0	0.7	7.8	5.1	0.4	1.1	0.9	1.3
85 & Above	*	0.2	0.2	0.2	0.1	*	0.3	0.2	*	0.1	0.1	0.1
Average	81.66	82.00	82.41	82.52	82.02	81.90	81.76	81.91	82.10	82.01	81.49	81.58
Tenderable 3/	93.0	90.6	64.5	70.2	89.4	87.6	82.9	85.0	95.9	91.8	91.8	88.1
SAMPLES CLASSED	38,546	488,104	73,084	1,289,999	17,996	91,728	5,940	43,478	7,610	82,716	150,596	1,345,362

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 18, 2025

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	0.1	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	1.0	0.9	-	*	-	-	-	-	*	*	-	-
2.7 - 2.9	7.1	5.2	-	*	-	-	-	-	*	*	-	*
3.0 - 3.2	10.5	8.6	0.1	*	*	*	-	*	0.2	0.2	-	0.1
3.3 - 3.4	10.7	8.9	-	0.1	*	*	0.1	*	0.6	0.5	0.1	0.8
3.5 - 3.6	13.9	12.2	-	0.2	*	0.1	0.2	0.2	2.0	1.4	4.0	2.0
3.7 - 4.2	36.9	39.8	5.9	8.1	9.2	8.5	10.2	5.0	38.1	27.8	27.5	43.3
4.3 - 4.9	19.8	24.0	51.0	64.6	83.5	82.0	69.5	61.8	57.0	64.5	65.2	52.8
5.0 - 5.2	0.1	0.3	26.8	21.7	6.9	8.8	18.9	29.0	1.9	5.2	3.1	1.0
5.3 & Above	-	-	16.2	5.2	0.3	0.5	1.1	4.0	0.2	0.4	-	*
Average	3.74	3.84	4.87	4.74	4.61	4.62	4.63	4.80	4.32	4.41	4.41	4.27
Leaf												
1 - 2	4.8	13.1	16.3	14.2	8.7	4.0	3.4	6.3	6.9	9.4	87.1	69.0
3	28.5	28.9	37.6	49.8	60.8	52.8	58.2	42.8	51.7	51.6	12.8	24.9
4	35.0	29.5	30.4	29.5	25.6	37.3	34.5	39.7	35.0	32.6	0.1	3.9
5	21.1	17.7	14.4	6.1	4.0	5.5	3.8	10.1	5.5	5.8	-	1.4
6	8.1	7.8	1.3	0.4	0.7	0.4	0.2	1.0	0.4	0.5	-	0.7
7	1.8	2.3	-	-	0.1	*	-	*	0.2	0.1	-	0.1
8	0.7	0.8	-	-	-	-	-	-	0.4	*	-	-
Average	4.07	3.87	3.47	3.28	3.27	3.45	3.39	3.57	3.43	3.37	1.94	2.23
HVI Trash 1/												
00	-	-	-	-	-	*	-	-	-	-	-	-
01	0.5	3.3	2.0	1.9	0.5	0.2	0.1	0.5	0.6	0.8	40.1	30.6
02	6.5	12.1	15.5	15.0	13.5	6.1	8.2	7.7	9.2	11.2	48.8	41.4
03	14.1	13.7	16.5	24.4	31.9	22.8	30.8	19.1	23.6	24.3	9.4	17.0
04	16.0	13.8	17.4	23.2	26.4	28.8	28.5	23.6	26.7	25.3	1.3	5.4
05	14.8	13.0	15.4	16.2	14.4	21.0	17.7	19.9	19.2	18.3	0.1	2.6
06	12.0	10.7	11.2	9.6	6.9	11.5	8.3	13.3	11.1	10.6	0.2	1.2
07	9.7	8.4	8.6	5.2	3.5	5.5	3.8	7.9	5.3	5.3	-	0.8
08	8.1	6.7	5.5	2.5	1.5	2.4	1.7	4.2	2.3	2.4	-	0.5
09	5.9	5.0	3.7	1.2	0.8	1.0	0.6	2.1	0.9	1.0	-	0.2
10	4.6	3.8	2.5	0.5	0.3	0.4	0.2	1.0	0.4	0.4	-	0.1
11	3.1	2.8	0.9	0.2	0.2	0.2	0.1	0.5	0.1	0.2	-	*
12	1.9	2.1	0.5	0.1	0.1	0.1	0.1	0.2	0.1	0.1	-	0.1
13	1.1	1.5	0.2	*	0.1	*	-	0.1	*	*	-	*
14	0.8	1.0	0.1	*	*	*	-	*	0.1	*	-	-
15	0.3	0.6	-	-	*	*	*	*	0.1	*	-	-
16	0.3	0.5	-	-	-	-	-	-	0.1	*	-	-
17	0.1	0.3	-	-	-	-	-	-	0.1	*	-	-
18 & Above	0.3	0.7	-	-	-	-	-	-	0.2	*	-	-
Average	0.60	0.57	0.48	0.41	0.39	0.44	0.41	0.47	0.44	0.43	0.17	0.22
UNIFORMITY 2/												
74 & Below	-	*	-	-	-	-	-	-	*	*	-	-
75	*	0.1	-	-	-	-	-	-	*	*	-	-
76	0.2	0.3	-	-	-	*	-	*	0.1	*	-	-
77	1.0	1.1	-	-	*	*	-	*	0.2	*	-	*
78	2.9	3.1	0.1	0.1	*	0.1	0.1	0.2	0.7	0.6	0.1	0.2
79	7.2	7.6	0.7	1.2	0.1	0.2	0.3	1.3	2.6	2.9	0.2	1.1
80	17.9	16.8	2.4	7.1	4.5	2.2	7.7	8.8	10.6	10.7	7.8	13.1
81	33.2	30.4	25.0	30.1	18.6	16.0	42.6	30.0	27.8	27.1	57.2	38.5
82	25.9	26.8	44.5	40.4	52.4	49.9	36.2	38.1	30.7	35.5	21.0	36.0
83	9.9	11.7	21.0	18.5	21.2	28.8	11.4	18.1	22.7	20.2	13.5	10.8
84	1.7	1.9	6.2	2.6	3.0	2.6	1.6	3.3	4.2	2.8	0.3	0.2
85 & Above	*	0.1	0.1	0.1	0.2	0.2	0.1	0.1	0.3	0.2	-	*
Average	81.50	81.53	82.45	82.21	82.44	82.58	82.01	82.18	82.15	82.12	81.90	81.87
Tenderable 3/	50.1	47.1	53.9	71.5	89.7	85.7	78.7	63.7	92.2	90.5	96.8	97.2
SAMPLES CLASSED	16,601	65,049	3,365	223,278	29,414	598,007	3,982	705,258	64,783	598,282	964	6,068

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Dec 18, 2025										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	*	-	-	-	-	*	*	-	-
2.5 - 2.6	*	*	-	-	-	-	0.1	0.1	-	-
2.7 - 2.9	0.2	0.1	*	*	-	*	0.9	0.6	*	*
3.0 - 3.2	0.5	0.5	0.2	0.1	-	*	3.6	2.1	0.7	0.2
3.3 - 3.4	2.6	1.3	0.6	0.3	-	0.2	4.9	3.3	1.9	0.5
3.5 - 3.6	7.8	3.4	1.7	0.9	-	0.6	8.0	5.6	5.1	1.9
3.7 - 4.2	47.1	45.3	36.5	26.3	-	15.1	38.1	41.9	62.1	48.1
4.3 - 4.9	41.0	48.8	55.1	63.8	-	74.7	42.1	44.3	28.4	48.6
5.0 - 5.2	0.9	0.7	5.6	7.6	-	9.0	2.1	1.9	1.8	0.7
5.3 & Above	-	*	0.2	0.9	-	0.3	0.2	0.4	-	*
Average	4.14	4.23	4.37	4.46	-	4.56	4.13	4.18	4.11	4.24
Leaf										
1 - 2	64.4	63.5	5.9	5.2	-	16.4	67.1	55.6	14.3	11.3
3	30.3	29.6	56.7	51.5	-	59.0	26.4	32.1	68.7	61.4
4	4.8	5.9	33.3	38.0	-	21.8	5.2	10.1	15.4	24.1
5	0.4	0.8	4.0	5.2	-	2.7	1.1	1.9	1.4	3.1
6	*	0.1	0.1	0.2	-	0.2	0.2	0.3	0.1	0.1
7	-	*	*	*	-	*	0.1	*	-	*
8	-	*	-	-	-	-	*	*	-	-
Average	2.22	2.21	3.36	3.44	-	3.11	2.24	2.44	3.04	3.19
HVI Trash 1/										
00	*	0.1	-	-	-	*	0.1	0.1	-	-
01	33.1	34.3	0.2	0.2	-	2.0	33.7	27.3	0.6	0.5
02	35.3	31.9	9.0	7.4	-	17.1	39.6	32.4	15.7	12.6
03	18.1	18.0	27.8	23.9	-	29.7	15.5	18.5	36.0	29.7
04	8.6	9.0	27.8	27.8	-	24.7	6.0	10.4	27.1	26.6
05	3.3	3.9	18.9	20.7	-	14.2	2.6	5.7	12.4	16.0
06	1.1	1.6	9.8	11.4	-	6.8	1.3	3.0	4.7	8.2
07	0.4	0.7	4.3	5.2	-	3.1	0.7	1.4	1.9	3.8
08	0.1	0.3	1.4	2.1	-	1.3	0.3	0.7	0.9	1.6
09	*	0.1	0.5	0.8	-	0.6	0.2	0.3	0.4	0.6
10	*	0.1	0.2	0.3	-	0.2	0.1	0.1	0.1	0.2
11	*	*	0.1	0.1	-	0.1	*	0.1	0.1	0.1
12	-	*	*	*	-	*	*	*	*	*
13	-	*	*	*	-	*	*	*	*	*
14	-	*	*	*	-	*	*	*	*	*
15	-	*	-	*	-	*	*	*	-	*
16	-	*	-	*	-	-	*	*	-	*
17	-	*	-	-	-	-	*	*	-	*
18 & Above	-	*	-	*	-	-	*	*	-	*
Average	0.22	0.23	0.41	0.44	-	0.38	0.21	0.26	0.37	0.40
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	*	*	-	-
75	*	*	*	*	-	-	0.1	*	-	-
76	*	*	*	*	-	*	0.2	0.2	*	*
77	0.2	0.2	*	*	-	*	0.9	0.7	*	*
78	1.2	1.0	0.5	0.4	-	0.1	4.7	3.2	0.2	0.2
79	4.7	5.0	3.3	3.1	-	0.6	15.6	11.0	1.2	1.4
80	16.3	16.2	18.8	15.0	-	6.9	29.7	24.3	6.7	8.4
81	34.7	30.6	34.0	31.7	-	32.7	30.3	30.3	21.9	27.6
82	23.9	26.5	31.0	35.0	-	43.1	14.6	20.2	42.3	38.2
83	14.2	15.4	11.1	13.6	-	15.6	3.4	8.0	23.8	21.2
84	4.4	4.8	1.0	1.2	-	0.9	0.4	1.9	3.7	2.9
85 & Above	0.4	0.4	0.1	0.1	-	0.1	*	0.2	0.2	0.2
Average	81.82	81.88	81.75	81.88	-	82.14	80.88	81.28	82.37	82.24
Tenderable 3/	94.1	95.0	88.7	86.3	-	82.3	80.5	85.2	93.6	96.7
SAMPLES CLASSED	24,624	247,050	42,692	211,656	-	340,307	352,939	3,935,334	19,468	162,790

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE									
For The Week Ending Dec 18, 2025									
Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	2.9	2.5	1.7	5.9	-	-	16.7	17.4
	2	0.5	0.2	3.2	6.5	-	-	14.2	16.6
	3	0.1	*	0.1	0.1	-	-	0.2	0.4
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		3.5	2.7	5.0	12.5	-	-	31.1	34.5
02	1	44.6	40.1	3.5	5.0	-	-	16.5	15.7
	2	19.0	17.0	33.0	35.5	-	-	42.9	41.4
	3	0.2	0.1	9.0	8.6	-	-	2.7	3.1
	4	-	-	0.2	0.1	-	-	-	0.1
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		63.8	57.3	45.7	49.2	-	-	62.1	60.3
03	1	9.2	12.7	0.1	0.2	-	-	0.7	0.3
	2	21.4	23.8	17.0	13.3	-	-	5.3	4.1
	3	0.8	0.9	21.7	18.1	-	-	0.9	0.8
	4	-	-	3.1	2.1	-	-	-	0.1
	5	-	-	0.2	0.1	-	-	-	-
	6	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		31.4	37.4	42.2	33.7	-	-	6.8	5.2
04	1	0.5	0.3	-	*	-	-	-	-
	2	0.7	2.1	0.9	0.5	-	-	*	*
	3	-	0.3	3.3	2.4	-	-	-	*
	4	-	-	1.6	1.0	-	-	-	*
	5	-	-	0.1	0.1	-	-	-	-
	6	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		1.2	2.6	5.9	4.0	-	-	*	*
05	1	-	-	-	*	-	-	-	-
	2	-	-	0.3	0.1	-	-	-	-
	3	-	-	0.5	0.2	-	-	-	-
	4	-	-	0.2	0.2	-	-	-	-
	5	-	-	0.1	*	-	-	-	-
	6	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	1.1	0.5	-	-	-	-
06	1	-	-	-	-	-	-	-	-
	2	-	-	*	*	-	-	-	-
	3	-	-	*	*	-	-	-	-
	4	-	-	*	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	0.1	*	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	-
STAPLE									
44 & Shorter		0.1	*	0.8	2.0	-	-	6.0	12.0
46		39.2	21.8	4.3	8.4	-	-	38.6	50.8
48		56.7	74.0	38.1	46.4	-	-	41.9	33.1
50		3.4	4.0	52.9	41.4	-	-	12.1	3.7
52 & Longer		0.6	0.2	3.8	1.8	-	-	1.4	0.4
Average Staple		47.30	47.65	49.09	48.65	-	-	47.28	46.59
Average Length		1.38	1.38	1.43	1.41	-	-	1.37	1.36
EXTRANEIOUS MATTER									
Bark		-	-	*	*	-	-	-	*
Grass		-	-	0.5	0.3	-	-	3.2	1.2
Spindle Twist		-	-	*	*	-	-	-	-
Preparation		-	*	-	*	-	-	-	-
All Other		-	*	*	*	-	-	*	*

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE								
For The Week Ending Dec 18, 2025								
Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	-
2.7 - 2.9	-	*	0.2	0.1	-	-	*	0.2
3.0 - 3.2	0.1	*	0.3	0.4	-	-	8.3	12.4
3.3 - 3.4	0.1	0.3	1.0	1.4	-	-	15.6	17.3
3.5 - 3.6	-	1.0	9.1	7.3	-	-	21.4	21.4
3.7 - 4.2	86.8	93.1	85.2	88.2	-	-	52.2	47.7
4.3 - 4.9	13.0	5.5	4.2	2.6	-	-	2.5	0.9
5.0 - 5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	4.04	4.00	3.90	3.90	-	-	3.71	3.64
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-
2.7	-	*	-	*	-	-	-	-
2.8	-	-	0.2	*	-	-	-	-
2.9	-	-	-	*	-	-	*	0.2
3.0	0.1	*	*	*	-	-	0.3	2.1
3.1	-	-	0.1	0.1	-	-	5.3	4.7
3.2	-	-	0.2	0.2	-	-	2.8	5.6
3.3	-	0.2	0.1	0.5	-	-	4.1	6.7
3.4	0.1	0.2	0.9	0.9	-	-	11.5	10.6
3.5	-	*	2.4	2.1	-	-	12.9	13.1
3.6	-	0.9	6.7	5.2	-	-	8.4	8.3
3.7	1.8	4.2	11.6	9.9	-	-	7.2	7.7
3.8	4.8	11.0	17.4	17.0	-	-	5.2	9.9
3.9	24.6	18.9	22.1	22.9	-	-	13.7	12.4
4.0	33.9	27.6	17.9	21.2	-	-	14.3	10.0
4.1	17.6	21.8	11.3	11.8	-	-	8.7	6.3
4.2	4.1	9.6	5.0	5.5	-	-	3.1	1.5
4.3	0.9	2.9	2.1	1.7	-	-	1.4	0.6
4.4	11.9	2.4	1.3	0.6	-	-	0.4	0.1
4.5	-	0.2	0.6	0.3	-	-	0.7	0.2
4.6	0.1	*	0.2	0.1	-	-	-	*
4.7	-	*	*	*	-	-	*	*
4.8	-	-	*	*	-	-	-	-
4.9	-	-	-	*	-	-	*	*
5.0	-	-	-	-	-	-	-	-
5.1	-	-	-	-	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	4.04	4.00	3.90	3.90	-	-	3.71	3.64
STRENGTH 1/ 36 & Below	-	-	0.8	1.6	-	-	7.8	12.3
37	0.1	*	2.0	4.6	-	-	14.8	20.8
38	0.1	0.1	2.2	2.8	-	-	10.2	18.6
39	0.4	0.4	1.6	1.2	-	-	3.7	7.5
40	5.9	7.1	1.7	1.8	-	-	1.7	2.3
41	17.2	26.1	4.9	6.0	-	-	5.3	2.3
42	36.2	36.0	9.9	12.1	-	-	9.3	5.2
43	28.6	22.3	18.4	19.0	-	-	10.2	6.8
44	10.4	6.9	23.4	22.0	-	-	10.7	9.0
45	-	0.6	19.1	17.6	-	-	15.5	7.3
46	0.5	0.2	10.2	8.0	-	-	8.7	5.1
47	0.4	0.2	4.7	2.5	-	-	1.9	2.0
48 & Above	0.4	0.1	1.2	0.7	-	-	0.3	0.7
Average	42.65	42.42	44.02	43.52	-	-	41.85	40.40
UNIFORMITY								
83 & Below	0.4	0.1	0.8	1.2	-	-	1.2	1.6
84	4.8	3.1	10.1	11.4	-	-	16.5	22.4
85	49.0	41.7	34.1	32.5	-	-	36.4	46.2
86	43.5	50.3	50.3	48.8	-	-	38.1	26.8
87	2.4	4.7	4.4	5.7	-	-	7.7	2.9
88 & Above	-	0.1	0.3	0.5	-	-	0.2	0.1
Average	85.83	86.02	85.93	85.92	-	-	85.78	85.52
Samples Classed	849	6,883	18,870	211,998	-	-	4,833	20,863

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.