



State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	14	87.4	78.1	16,789	21	90.5	78.4	504,893
AR	8	60.8	37.4	27,431	26	70.0	41.9	1,317,430
AZ	7	85.7	70.2	11,784	9	87.4	67.2	103,512
CA	5	75.1	73.3	5,229	10	84.0	70.3	48,707
FL	4	86.1	74.8	2,697	4	91.6	76.7	85,413
GA	52	91.0	78.8	111,744	53	88.3	73.7	1,457,106
KS	3	44.4	38.8	7,086	3	46.8	35.2	72,078
LA	-	-	-	-	14	71.5	47.6	223,278
MO	8	96.5	78.7	29,297	16	86.2	64.1	627,304
MS	2	42.7	27.8	1,138	30	63.7	36.5	706,396
NC	19	93.6	82.2	17,935	26	90.6	78.4	616,217
NM	2	77.0	67.4	1,294	2	93.6	83.6	7,362
OK	10	90.6	79.8	26,645	10	94.6	82.7	273,695
SC	10	86.8	76.9	22,616	10	86.3	72.3	234,272
TN	-	-	-	-	17	82.3	63.4	340,307
TX	103	77.5	55.5	262,150	144	84.7	65.1	4,197,483
VA	4	90.3	83.3	5,558	4	96.4	90.9	168,348
United States	251	82.1	64.8	549,393	399	82.7	63.4	10,983,801
AMERICAN PIMA								
AZ	2			1,054	2			7,937
CA	8			16,900	10			228,893
NM*	-			-	-			-
TX	3			906	5			21,769
United States	14			20,237	18			275,292
United States all cotton	263			569,630	408			11,259,093

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 25, 2025

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	0.2	2.3	-	0.1	13.3	22.8	9.4	28.0	-	1.8	1.9	1.3
	3	0.9	1.3	*	0.1	0.8	5.7	0.2	11.9	*	0.5	2.2	0.9
	4	0.1	*	-	*	*	0.3	-	0.7	-	*	0.1	*
	5	-	*	-	-	-	*	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.2	3.7	*	0.2	14.1	28.9	9.7	40.6	*	2.3	4.2	2.2
31	1 - 2	2.9	9.9	0.5	1.1	4.1	12.4	26.7	15.8	1.0	3.2	7.8	7.9
	3	12.9	29.2	6.5	9.2	6.1	12.9	5.2	12.0	3.7	12.7	23.5	21.7
	4	3.0	7.5	5.2	3.4	1.3	2.4	0.1	5.4	1.6	2.9	5.6	3.9
	5	0.2	0.5	0.5	0.1	0.1	0.2	-	1.2	*	0.1	0.3	0.1
	6	-	*	-	*	-	*	-	0.1	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	19.1	47.2	12.7	13.9	11.7	28.0	32.0	34.6	6.3	18.8	37.4	33.6
41	1 - 2	3.1	3.3	0.6	0.8	0.4	2.0	11.3	3.3	2.2	2.9	4.3	5.6
	3	27.6	22.7	19.4	26.3	14.7	10.3	36.9	8.4	38.0	38.0	27.7	33.9
	4	19.6	15.8	37.3	35.3	23.8	9.6	5.8	3.5	38.3	28.7	15.2	16.8
	5	3.1	2.9	13.3	8.2	9.4	2.8	0.1	2.5	5.0	3.8	2.0	2.0
	6	0.2	0.3	0.9	0.7	0.9	0.3	-	0.6	0.1	0.2	0.1	0.1
	7	-	*	*	*	*	*	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	53.5	44.9	71.5	71.2	49.2	25.0	54.0	18.3	83.5	73.6	49.3	58.4
51	1 - 2	0.7	0.1	0.1	*	*	0.1	*	0.1	-	0.1	0.2	0.2
	3	8.8	1.0	2.7	2.3	0.7	0.8	0.9	0.2	2.9	1.4	3.6	1.8
	4	10.6	0.9	5.7	4.8	6.4	1.8	0.4	0.1	3.8	1.6	3.5	1.7
	5	1.7	0.2	4.3	2.2	8.4	1.8	*	*	0.9	0.5	0.6	0.4
	6	0.2	*	0.6	0.4	3.8	0.7	-	*	0.1	*	0.1	*
	7	*	*	*	0.1	0.6	0.2	-	-	-	*	*	*
	8	-	*	-	-	*	*	-	-	-	-	-	*
Total	----	21.9	2.3	13.3	9.9	20.0	5.4	1.4	0.4	7.7	3.6	7.9	4.1
61	1 - 2	-	-	-	*	-	-	-	-	-	-	-	*
	3	0.2	*	*	*	-	-	-	-	-	-	*	*
	4	0.5	*	*	*	-	-	-	-	-	*	*	*
	5	0.1	*	0.1	*	*	*	-	-	-	*	*	*
	6	*	*	*	*	*	*	-	-	*	*	*	*
	7	-	-	-	-	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	*	*
Total	----	0.8	*	0.1	*	*	*	-	-	*	*	*	*
71	1 - 2	-	-	-	*	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	*	-	-	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	-	-	-	-	-
12 & 22	1 - 2	-	0.1	-	*	1.8	5.0	-	0.3	-	*	*	*
	3	*	*	-	*	0.9	2.5	-	0.4	-	*	0.1	*
	4	-	*	-	*	0.1	0.3	-	0.1	-	-	*	*
	5	-	-	-	*	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	0.1	-	*	2.8	7.7	-	0.8	-	*	0.1	*
32	1 - 2	*	0.1	-	*	*	0.2	0.2	0.5	-	*	*	*
	3	0.3	0.4	-	0.1	*	0.7	0.6	0.9	*	0.2	0.2	0.2
	4	0.4	0.1	*	0.1	*	0.4	0.1	0.9	*	0.1	0.1	0.1
	5	*	*	*	*	-	0.1	-	0.6	-	-	*	*
	6	-	*	*	*	-	*	-	0.1	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.8	0.6	*	0.2	0.1	1.4	0.8	3.0	0.1	0.3	0.4	0.4
42	1 - 2	-	*	-	*	*	*	0.2	0.1	-	0.1	*	*
	3	0.4	0.4	*	1.0	0.2	0.6	0.8	0.7	0.2	0.8	0.2	0.6
	4	0.9	0.4	0.7	1.5	0.2	0.6	0.2	0.4	1.1	0.4	0.2	0.4
	5	0.2	0.1	0.8	0.5	0.2	0.4	*	0.5	0.3	*	0.1	0.1
	6	*	*	0.2	0.1	0.2	0.1	-	0.2	0.1	*	*	*
	7	-	*	*	*	0.1	*	-	-	-	*	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.5	1.0	1.7	3.2	0.7	1.7	1.2	2.0	1.7	1.2	0.5	1.1

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 25, 2025

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	-	*	*	*	-	*	-	-	*	*
	3	0.3	*	*	0.3	0.4	0.2	*	*	0.4	*	*	*
	4	0.4	*	0.2	0.6	0.3	0.3	0.1	*	0.1	*	*	0.1
	5	0.2	*	0.3	0.3	0.1	0.4	*	*	*	*	*	*
	6	*	*	0.1	0.1	0.1	0.2	-	-	*	*	*	*
	7	-	*	*	*	0.2	0.1	-	-	-	*	-	*
	8	-	-	-	-	*	*	-	-	-	-	-	*
Total	----	0.9	0.1	0.6	1.3	1.2	1.2	0.2	0.1	0.6	0.1	0.1	0.1
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	*	*	-	*	-	-	-	-	-	-	-	-
	4	-	*	-	*	*	*	*	*	-	-	-	*
	5	*	*	-	*	-	*	-	-	-	*	-	*
	6	-	*	-	*	*	*	-	-	-	-	-	*
	7	-	-	-	*	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	*	*	*	*	-	*	-	*
13 & 23	1 - 2	-	*	-	-	*	0.3	-	*	-	-	*	*
	3	-	*	-	-	*	0.1	-	*	-	-	*	*
	4	-	*	-	-	-	*	-	-	-	-	-	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	0.1	0.4	-	*	-	-	*	*
33	1 - 2	-	*	-	-	-	*	*	*	-	-	*	*
	3	-	*	-	*	*	0.1	0.1	*	-	-	*	*
	4	-	*	-	*	-	*	0.1	*	-	-	*	*
	5	-	*	-	*	-	*	-	*	-	-	-	-
	6	-	*	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	*	0.1	0.2	0.1	-	-	*	*
43	1 - 2	-	-	-	*	-	-	-	*	-	-	*	*
	3	*	*	*	*	-	*	0.2	0.1	*	*	*	*
	4	0.1	*	*	*	-	*	0.2	0.1	-	*	*	*
	5	*	*	*	*	-	*	*	*	-	-	*	*
	6	-	*	*	*	-	*	-	*	-	-	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	*	*	0.1	-	0.1	0.4	0.2	*	*	0.1	*
53	1 - 2	*	*	-	-	-	-	-	-	-	-	-	-
	3	*	*	-	*	-	-	-	*	*	*	*	*
	4	0.1	*	-	*	0.1	*	-	*	-	-	*	*
	5	-	*	*	*	0.1	*	-	-	-	-	*	*
	6	-	*	-	*	-	*	-	-	-	-	*	*
	7	-	-	-	*	*	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	*	*	*	0.1	0.1	-	*	*	*	*	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
24 - 54	1 - 8	-	*	*	*	-	*	0.1	*	-	-	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	*
31		-	*	-	*	-	*	-	-	-	*	*	*
32		*	*	-	*	-	*	-	-	0.6	*	0.1	0.1
33		0.7	0.5	*	0.1	*	*	-	*	0.5	0.2	0.7	0.8
34		5.3	3.1	0.3	0.2	0.1	0.5	0.3	0.4	3.9	2.3	5.0	4.5
35		16.8	11.4	4.8	2.5	0.9	2.6	0.6	2.8	7.7	12.9	16.7	15.7
36		26.6	24.1	19.2	13.8	10.7	12.3	28.9	15.9	11.3	29.7	31.1	31.5
37		35.8	42.1	40.4	51.0	39.2	45.4	60.4	39.4	34.9	35.5	33.5	35.1
38		12.7	15.0	24.3	26.9	29.8	29.1	7.0	24.5	38.3	15.0	10.0	9.7
39		2.0	3.2	9.1	5.0	17.0	8.6	2.8	15.0	2.7	3.7	2.5	2.3
40 & Longer		*	0.5	1.9	0.5	2.3	1.4	0.1	2.0	0.1	0.6	0.5	0.3
Average Staple		36.38	36.65	37.18	37.18	37.58	37.31	36.82	37.38	37.01	36.61	36.34	36.36
Average Length		1.13	1.14	1.16	1.16	1.17	1.17	1.15	1.17	1.16	1.14	1.13	1.13

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 25, 2025

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	1.0	7.9	-	4.5	-	*	-	2.0	0.1	0.4	27.7	51.0
	3	4.4	7.3	-	2.6	-	*	-	1.8	0.2	0.3	9.0	8.2
	4	1.5	1.1	-	*	-	*	-	*	*	*	0.2	0.1
	5	*	*	-	-	-	-	-	*	-	*	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	6.9	16.4	-	7.1	-	*	-	3.8	0.3	0.7	36.9	59.2
31	1 - 2	1.7	1.7	-	9.2	1.4	1.4	1.1	3.4	4.1	5.6	11.0	11.6
	3	8.8	11.3	-	36.6	10.2	8.8	19.2	20.3	20.1	20.1	29.3	18.2
	4	14.4	13.3	-	12.3	2.2	1.9	6.2	8.6	4.7	5.8	8.0	3.8
	5	4.7	3.6	-	0.8	*	*	-	0.6	0.3	0.3	0.2	0.2
	6	0.4	0.4	-	*	-	*	-	*	-	*	-	-
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-	-	-
Total	----	29.9	30.4	-	58.9	13.8	12.2	26.4	32.9	29.1	31.8	48.5	33.9
41	1 - 2	-	*	-	0.5	2.8	2.3	0.4	0.9	2.1	3.1	-	*
	3	0.2	0.8	-	10.1	38.6	37.9	32.9	18.8	32.2	29.9	1.0	0.9
	4	4.5	3.9	-	16.2	23.7	27.2	36.1	26.1	27.4	24.8	2.1	1.1
	5	9.1	5.5	-	4.9	2.2	3.3	2.7	7.3	3.9	4.5	0.8	1.1
	6	6.8	2.7	-	0.3	*	0.1	0.2	0.6	0.2	0.3	0.1	0.6
	7	1.4	0.5	-	-	-	*	-	*	-	*	-	0.1
	8	0.1	*	-	-	-	-	-	-	-	*	-	-
Total	----	22.2	13.6	-	32.0	67.2	70.8	72.2	53.6	65.7	62.7	3.9	3.7
51	1 - 2	-	-	-	*	0.2	0.1	-	*	-	0.1	-	-
	3	-	-	-	*	7.3	4.2	-	1.1	0.9	0.8	-	-
	4	-	-	-	0.4	8.2	5.8	-	3.3	2.8	1.7	-	-
	5	*	*	-	0.3	2.0	1.4	-	1.5	0.5	0.8	0.1	*
	6	0.7	0.1	-	0.1	0.1	0.1	-	0.2	*	0.2	-	*
	7	1.4	0.2	-	-	-	*	-	*	-	*	-	-
	8	0.4	0.1	-	-	-	-	-	-	-	*	-	-
Total	----	2.5	0.4	-	0.7	17.8	11.7	-	6.1	4.2	3.7	0.1	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	*	-	*	-	-
	4	-	-	-	*	*	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	*	*	-	*	-	*	-	-
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	*	*	-	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	*	-	-	-	*	-	-
12 & 22	1 - 2	0.4	2.1	-	0.1	-	-	-	*	-	*	-	0.2
	3	5.7	4.1	-	*	-	*	-	*	*	*	0.1	*
	4	3.1	1.5	-	*	-	-	-	*	-	*	0.2	*
	5	0.3	0.2	-	*	-	-	-	-	-	-	-	-
	6	*	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	9.6	7.9	-	0.1	-	*	-	*	*	*	0.3	0.3
32	1 - 2	*	0.1	-	0.1	-	*	-	*	*	*	-	0.9
	3	1.2	2.8	-	0.3	*	0.1	0.1	0.2	0.1	0.1	0.6	0.2
	4	4.4	5.0	-	0.2	*	*	0.1	0.1	0.1	0.1	2.9	0.5
	5	4.9	2.8	-	*	-	*	-	*	*	*	1.1	0.2
	6	0.6	0.6	-	*	-	-	-	*	-	-	0.1	*
	7	*	0.1	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	11.2	11.4	-	0.5	*	0.2	0.2	0.3	0.2	0.3	4.7	1.8
42	1 - 2	-	*	-	*	*	0.1	-	*	-	*	-	-
	3	*	1.0	-	0.1	0.2	1.4	0.4	0.6	0.1	0.3	0.3	0.1
	4	1.4	3.8	-	0.4	0.4	1.4	0.8	1.2	0.1	0.3	0.5	0.1
	5	4.4	5.3	-	0.1	0.1	0.4	-	0.5	*	0.1	-	-
	6	4.3	3.7	-	*	*	0.1	-	0.1	*	*	-	-
	7	1.9	1.1	-	-	-	*	-	*	*	*	-	-
	8	0.4	0.2	-	-	-	-	-	-	-	*	-	-
Total	----	12.3	15.1	-	0.6	0.7	3.4	1.1	2.4	0.3	0.7	0.9	0.1

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 25, 2025

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	-	*	*	-	*	-	*	-	-
	3	-	-	-	*	*	0.5	-	0.1	*	*	-	-
	4	-	*	-	*	0.2	0.7	-	0.2	*	*	-	-
	5	0.1	*	-	*	0.1	0.3	-	0.3	*	*	-	-
	6	0.4	0.2	-	*	*	0.1	-	0.1	*	*	-	-
	7	0.8	0.4	-	-	-	*	-	*	-	*	-	-
	8	0.8	0.3	-	-	-	-	-	-	*	*	-	-
Total	----	2.1	1.0	-	*	0.3	1.6	-	0.7	0.1	0.1	-	-
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	*	*	-	*	-	-	-	-
	4	-	-	-	-	*	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	*	*	-	*	-	*	-	-
13 & 23	1 - 2	*	0.2	-	-	-	-	-	-	-	-	-	-
	3	0.3	0.7	-	-	-	-	-	-	-	*	-	-
	4	0.7	0.4	-	-	-	-	-	-	-	*	-	-
	5	0.4	0.1	-	-	-	-	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.4	1.4	-	-	-	-	-	-	-	*	-	-
33	1 - 2	-	*	-	-	-	*	-	*	-	*	-	-
	3	-	0.1	-	*	-	*	-	*	*	*	0.9	0.1
	4	0.1	0.2	-	*	-	*	-	*	*	*	2.1	0.4
	5	0.2	0.3	-	*	-	-	-	-	-	*	1.5	0.3
	6	*	0.1	-	-	-	-	-	-	-	*	0.1	*
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	0.3	0.7	-	*	-	*	-	*	*	*	4.6	0.8
43	1 - 2	-	-	-	*	-	*	-	-	-	*	-	-
	3	-	0.1	-	*	*	*	-	*	*	*	-	-
	4	0.1	0.3	-	*	*	*	-	*	0.1	*	-	-
	5	0.3	0.4	-	*	*	*	-	*	*	*	0.1	*
	6	0.6	0.5	-	-	-	*	-	*	*	*	0.1	*
	7	0.4	0.2	-	-	-	-	-	-	-	*	-	-
	8	0.1	0.1	-	-	-	-	-	-	-	*	-	-
Total	----	1.4	1.5	-	*	*	0.1	-	*	0.1	*	0.2	*
53	1 - 2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	*	-	-	*	*	-	*	-	*	-	-
	4	-	*	-	-	-	*	-	*	*	*	-	-
	5	-	*	-	-	*	*	-	*	-	*	-	-
	6	-	*	-	-	-	*	-	*	-	*	-	-
	7	*	*	-	-	-	-	-	*	-	*	-	-
	8	0.1	*	-	-	-	-	-	-	-	*	-	-
Total	----	0.1	0.1	-	-	*	*	-	*	*	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	-	-	*	-	-	-	-
24 - 54	1 - 8	*	0.1	-	-	*	*	-	-	-	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	-	-	-	*	*	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		-	*	-	-	-	-	-	*	-	*	-	-
32		-	*	-	-	-	*	-	*	*	*	-	-
33		*	0.2	-	0.1	-	*	-	0.2	0.1	0.1	-	-
34		0.4	1.2	-	1.1	*	0.2	0.2	2.1	1.0	1.3	5.1	2.8
35		2.4	3.8	-	10.0	0.6	1.8	0.8	11.5	8.5	7.6	10.8	9.7
36		8.3	10.0	-	26.9	5.8	10.1	31.1	27.7	25.4	23.8	9.7	10.9
37		28.9	26.5	-	42.1	48.0	48.7	50.2	36.4	44.4	49.7	43.5	30.2
38		43.5	36.7	-	15.0	41.4	33.6	16.2	15.0	18.0	14.4	27.3	37.8
39		14.7	19.0	-	4.4	4.1	5.1	1.2	5.4	2.3	2.8	2.6	7.5
40 & Longer		1.8	2.7	-	0.4	0.1	0.4	0.4	1.5	0.4	0.3	1.0	1.2
Average Staple		37.64	37.61	-	36.75	37.43	37.30	36.86	36.72	36.78	36.77	36.89	37.18
Average Length		1.18	1.18	-	1.15	1.17	1.17	1.15	1.15	1.15	1.15	1.15	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE For The Week Ending Dec 25, 2025											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	38.4	48.0	0.2	0.4	-	0.4	49.5	45.1	1.0	0.9
	3	6.9	8.1	0.5	0.5	-	0.1	12.8	13.5	3.8	1.3
	4	0.3	0.3	*	*	-	*	0.6	1.0	0.3	0.1
	5	-	*	-	-	-	*	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	45.6	56.3	0.8	0.9	-	0.5	62.8	59.6	5.0	2.3
31	1 - 2	18.3	12.1	1.9	2.5	-	6.9	5.0	3.2	7.5	8.8
	3	20.9	18.1	13.1	15.4	-	14.5	8.1	10.5	34.5	39.0
	4	3.9	3.8	6.3	4.8	-	3.2	3.1	4.4	6.3	8.3
	5	0.3	0.2	0.4	0.2	-	0.2	0.4	0.5	0.8	0.5
	6	*	*	-	*	-	*	*	*	*	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	43.4	34.2	21.8	22.8	-	24.8	16.7	18.6	49.1	56.6
41	1 - 2	0.2	0.3	1.1	2.1	-	7.7	0.1	0.2	3.4	1.6
	3	1.1	1.1	30.5	33.0	-	35.8	0.4	2.0	28.1	21.2
	4	1.6	1.0	35.4	30.8	-	14.2	0.7	1.9	11.7	15.3
	5	1.0	0.4	5.2	4.3	-	1.8	0.3	0.5	2.4	2.5
	6	0.1	0.1	0.1	0.1	-	0.1	0.1	0.1	0.2	0.1
	7	*	*	*	*	-	*	*	*	-	*
	8	-	-	-	-	-	-	*	*	-	-
Total	----	4.0	2.9	72.3	70.3	-	59.6	1.6	4.8	45.8	40.8
51	1 - 2	-	*	*	0.1	-	0.2	*	*	-	*
	3	-	*	1.7	1.8	-	2.4	*	0.1	*	*
	4	*	*	2.1	2.4	-	2.2	*	0.2	*	0.1
	5	*	*	0.5	0.7	-	0.5	*	*	-	*
	6	*	*	*	0.1	-	*	*	*	-	*
	7	-	*	*	*	-	*	*	*	-	*
	8	*	*	-	-	-	-	-	*	-	-
Total	----	*	*	4.4	5.1	-	5.3	*	0.3	*	0.1
61	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	*	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	*	-	-
12 & 22	1 - 2	2.5	2.3	-	-	-	*	6.4	6.6	-	-
	3	1.0	1.0	-	*	-	*	3.7	3.4	-	*
	4	0.1	0.1	-	-	-	*	0.5	0.6	-	*
	5	*	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	3.6	3.4	-	*	-	*	10.6	10.6	-	*
32	1 - 2	0.3	0.3	-	*	-	0.2	1.0	0.5	-	*
	3	1.0	1.1	0.2	0.1	-	0.5	2.1	1.5	-	*
	4	0.3	0.4	0.2	0.1	-	0.1	1.1	1.2	-	*
	5	0.1	0.1	-	*	-	*	0.3	0.3	-	*
	6	-	*	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	1.8	1.9	0.3	0.1	-	0.8	4.5	3.4	-	0.1
42	1 - 2	*	*	-	*	-	0.9	*	*	-	*
	3	0.1	0.1	0.1	0.2	-	5.0	0.1	0.4	-	*
	4	0.2	0.1	0.2	0.4	-	1.5	0.3	0.5	-	*
	5	0.1	0.1	*	0.1	-	0.1	0.1	0.3	-	*
	6	*	*	-	*	-	*	*	0.1	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	0.4	0.4	0.3	0.7	-	7.5	0.6	1.2	-	0.1

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Dec 25, 2025											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	*	-	*	-	-
	3	-	-	-	*	-	0.7	*	*	-	-
	4	-	*	*	0.1	-	0.5	*	*	-	*
	5	-	-	*	*	-	0.1	-	*	-	*
	6	-	*	-	*	-	*	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	*	0.1	-	1.3	*	0.1	-	*
62	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	-	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
Total	----	-	*	-	-	-	*	*	*	-	-
13 & 23	1 - 2	0.4	0.1	-	-	-	-	1.1	0.4	-	-
	3	0.1	0.1	-	-	-	-	0.6	0.3	-	*
	4	-	*	-	-	-	-	0.1	0.1	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	0.5	0.2	-	-	-	-	1.8	0.7	-	*
33	1 - 2	0.2	0.1	-	-	-	*	0.2	0.1	-	-
	3	0.4	0.2	*	*	-	*	0.5	0.2	*	*
	4	0.1	0.1	-	*	-	*	0.3	0.1	-	*
	5	*	*	-	*	-	-	0.1	*	-	*
	6	-	*	-	-	-	-	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.6	0.4	*	*	-	*	1.1	0.4	*	*
43	1 - 2	-	*	-	*	-	*	*	*	-	-
	3	*	*	*	*	-	*	*	*	-	*
	4	*	*	0.1	*	-	*	*	*	-	*
	5	-	*	*	*	-	*	*	*	-	*
	6	*	*	-	-	-	*	*	*	-	*
	7	*	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	*	0.1	0.1	*	-	*	0.1	0.1	-	*
53	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	*	-	*	-	*	-	*	-	-
	4	-	*	-	*	-	*	-	*	-	-
	5	*	*	-	*	-	*	*	*	-	-
	6	*	*	-	-	-	-	*	*	-	-
	7	*	*	-	*	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	-	*	*	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	*	-	-
24 - 54	1 - 8	*	0.1	-	*	-	-	0.1	0.1	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	*	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	*	*	-	-
30		-	-	-	-	-	-	*	*	-	-
31		-	*	-	-	-	-	*	0.1	-	-
32		*	*	-	*	-	*	0.6	0.5	-	*
33		0.2	0.4	0.5	0.1	-	0.1	3.8	2.4	*	*
34		1.8	1.9	2.8	1.3	-	2.6	11.7	7.2	0.4	0.6
35		7.5	6.4	12.3	8.9	-	9.5	22.0	13.7	5.3	5.4
36		16.8	12.3	36.1	33.8	-	30.9	23.2	21.2	38.8	22.5
37		30.5	25.7	38.3	42.5	-	44.3	24.9	33.8	49.0	55.7
38		19.4	20.0	9.3	10.3	-	11.3	9.9	15.4	4.8	13.0
39		13.6	19.9	0.7	2.8	-	1.3	2.6	4.7	1.6	2.6
40 & Longer		10.1	13.4	*	0.4	-	0.1	1.3	1.1	-	0.1
Average Staple		37.41	37.70	36.40	36.61	-	36.56	36.00	36.46	36.57	36.84
Average Length		1.17	1.18	1.13	1.14	-	1.14	1.12	1.14	1.14	1.15

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 25, 2025

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	2.0	0.3	0.3	*	*	0.2	*	*	3.0	0.8	2.3	0.9
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.3	0.1	*	0.1	*	0.1	0.3	1.1	0.1	0.1	0.1	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	-	-	-	-	-	-	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.2	0.1	*	1.0	-	*	-	-	0.8	0.2	0.5	0.3
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	-	-	-	-	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	-	-	-	-	-	-	-
23	-	-	-	*	-	-	-	-	-	-	*	*
24	-	*	-	*	-	*	-	*	-	-	*	*
25	*	*	-	*	*	*	*	*	-	*	0.2	0.1
26	0.2	0.1	*	*	*	0.3	0.6	0.4	0.2	*	1.4	0.5
27	4.3	1.2	0.1	0.2	0.9	1.5	4.4	1.5	2.5	0.4	7.5	2.7
28	17.3	7.1	2.3	1.9	7.2	6.3	25.4	6.5	7.3	3.3	19.5	9.9
29	24.6	21.4	16.3	11.7	8.1	13.2	28.2	12.0	12.3	13.3	24.3	20.6
30	23.1	29.7	31.9	34.7	16.8	21.0	26.1	17.4	33.6	26.6	22.1	25.4
31	18.9	22.1	26.9	33.6	28.8	21.7	8.9	12.8	23.5	26.7	14.2	20.1
32	8.0	11.3	15.0	13.2	15.0	15.4	0.2	5.4	18.9	17.0	6.4	11.7
33	3.3	4.8	5.4	3.6	7.2	9.8	0.6	5.4	1.3	7.6	3.1	5.6
34	0.3	1.7	1.6	0.8	6.9	7.0	1.1	10.6	0.2	4.0	1.0	2.3
35	0.1	0.5	0.4	0.1	5.2	2.5	2.1	15.0	0.1	0.9	0.3	0.8
36	*	0.1	*	*	2.6	0.7	0.8	9.5	-	0.1	0.1	0.2
37	*	*	*	*	1.2	0.4	0.9	3.0	-	*	*	0.1
38	-	*	-	*	*	*	0.7	0.3	-	-	-	*
39	-	-	-	-	*	*	0.1	0.1	-	-	-	*
40 & Above	-	-	-	-	*	*	*	0.1	-	-	-	-
Average	30.18	30.74	31.05	31.04	31.78	31.43	29.94	32.52	30.75	31.28	29.96	30.69
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	-	*	-	-	-	-	-	-	-	-	-	-
2.6	-	*	-	-	-	-	-	-	-	-	*	*
2.7	-	*	-	-	-	-	-	*	-	-	*	*
2.8	-	*	-	*	-	-	-	-	-	-	*	*
2.9	-	*	-	-	-	-	-	0.1	-	-	*	*
3.0	-	*	-	*	-	-	-	0.1	-	-	*	*
3.1	-	*	-	*	-	*	-	0.4	-	*	0.1	*
3.2	*	*	*	*	*	*	-	0.2	-	0.1	0.2	*
3.3	0.2	0.1	-	*	*	0.1	-	0.2	-	0.1	0.1	0.1
3.4	0.7	0.4	-	*	*	0.1	0.1	0.4	-	0.1	0.3	0.2
3.5	1.3	0.7	*	*	0.4	0.2	*	0.9	0.1	0.5	0.7	0.5
3.6	1.8	1.1	*	0.1	0.3	0.4	0.1	1.6	0.5	0.8	1.4	0.9
3.7	2.1	1.9	*	0.1	1.0	1.3	-	2.4	0.3	1.2	2.8	1.5
3.8	3.5	2.9	0.1	0.1	4.0	1.7	0.9	5.1	0.7	1.4	3.8	2.4
3.9	6.1	4.3	0.2	0.3	5.1	2.6	7.5	6.8	0.7	2.2	4.5	3.6
4.0	6.8	5.8	0.5	0.6	7.0	4.2	13.6	7.1	1.8	3.6	6.2	5.1
4.1	11.3	7.9	1.2	1.0	7.1	6.2	16.7	7.4	4.8	5.9	8.3	6.9
4.2	11.5	9.8	1.8	1.7	6.8	7.9	19.4	9.8	7.7	7.4	10.2	8.6
4.3	11.3	10.7	4.4	3.0	7.7	8.6	11.4	8.5	9.3	9.9	12.4	9.7
4.4	12.8	10.6	5.7	4.9	7.5	10.1	2.4	7.2	11.9	12.1	11.8	10.1
4.5	11.2	10.2	5.3	7.6	9.2	12.9	2.3	6.9	12.1	12.6	9.5	10.1
4.6	5.8	8.9	8.7	11.6	14.1	13.3	1.8	7.0	11.1	10.4	8.0	9.6
4.7	3.4	7.3	10.9	14.6	13.9	10.2	1.1	8.0	19.8	12.0	6.5	8.8
4.8	2.8	5.8	12.2	15.6	7.5	8.3	0.1	5.9	8.0	8.4	5.1	7.2
4.9	2.3	4.4	12.6	13.8	1.9	5.4	0.3	4.8	3.1	5.3	3.5	5.6
5.0	1.4	2.9	12.8	10.9	2.1	3.9	4.6	3.4	6.2	3.4	2.4	4.0
5.1	1.2	1.9	9.4	7.0	1.0	1.3	7.8	2.9	1.7	1.8	1.3	2.6
5.2	1.4	1.1	8.0	4.1	0.7	0.7	4.9	1.5	0.1	0.5	0.5	1.4
5.3	0.5	0.7	4.5	1.9	0.5	0.5	4.3	1.0	*	0.1	0.2	0.7
5.4	0.3	0.3	1.3	0.7	*	0.1	0.7	0.5	-	0.2	*	0.3
5.5 & Above	0.3	0.2	0.2	0.2	2.1	0.2	-	0.2	-	0.1	*	0.1
Average	4.30	4.40	4.81	4.76	4.44	4.48	4.38	4.36	4.53	4.47	4.34	4.45

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 25, 2025

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	19.2	21.2	-	0.1	-	*	-	*	2.5	1.5	0.1	0.1
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	1.1	0.1	-	*	-	*	-	*	*	*	3.4	0.6
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	-	-	*	-	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	0.1	-	0.4	-	0.2	-	0.3	0.2	0.4	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	-	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	*	*	0.2	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	*	-	-	-	-	-	-
23	-	*	-	-	-	*	-	-	-	-	-	-
24	-	-	-	-	-	*	-	*	*	*	-	-
25	*	*	-	*	-	*	-	*	0.1	*	0.2	*
26	0.3	0.1	-	*	*	*	-	0.1	0.6	0.3	1.4	0.2
27	0.8	0.4	-	0.5	*	0.1	-	1.0	3.0	2.0	2.1	1.7
28	2.4	1.2	-	4.4	1.0	0.6	2.2	4.8	14.7	10.5	17.6	7.7
29	4.9	2.8	-	19.0	14.0	7.4	14.1	15.6	27.2	28.2	19.3	23.4
30	8.3	7.1	-	33.2	49.0	35.9	33.5	26.9	29.1	31.9	16.8	30.6
31	15.3	15.9	-	21.1	26.7	36.7	26.1	26.3	17.4	17.6	13.4	18.7
32	27.9	23.3	-	11.7	6.1	13.6	14.5	16.1	6.0	6.9	14.6	11.8
33	27.8	23.6	-	5.1	2.5	4.7	9.4	6.5	1.4	2.1	12.1	3.7
34	10.8	16.8	-	2.9	0.4	1.0	0.1	2.3	0.4	0.4	2.4	2.0
35	1.4	7.3	-	1.8	0.1	0.1	0.1	0.4	0.1	0.1	0.1	0.1
36	0.2	1.3	-	0.2	*	*	-	*	-	*	-	-
37	*	0.2	-	*	-	*	-	*	-	-	0.1	*
38	*	0.1	-	*	-	*	-	*	-	-	-	-
39	-	*	-	-	-	-	-	-	-	-	-	-
40 & Above	-	*	-	-	-	-	-	-	-	-	-	-
Average	32.38	32.85	-	30.97	30.77	31.19	31.07	31.06	30.13	30.28	30.71	30.62
Mike												
2.4 & Below	-	0.1	-	-	-	-	-	-	-	-	-	-
2.5	0.8	0.4	-	-	-	-	-	-	-	*	-	-
2.6	2.0	0.7	-	*	-	-	-	-	-	-	-	-
2.7	2.6	1.2	-	*	-	-	-	-	*	*	-	-
2.8	2.8	2.0	-	-	-	-	-	-	*	*	0.1	*
2.9	1.4	2.2	-	*	-	-	-	-	*	*	0.9	0.2
3.0	2.0	2.5	-	*	-	-	-	-	0.1	*	1.0	0.2
3.1	3.3	3.0	-	*	-	*	-	-	0.1	*	0.2	*
3.2	3.0	3.1	-	*	-	*	-	*	0.1	0.1	4.3	0.8
3.3	3.6	4.0	-	*	-	*	-	*	0.3	0.2	1.7	0.7
3.4	5.4	4.9	-	0.1	-	*	0.1	*	0.4	0.3	-	0.3
3.5	5.1	5.8	-	0.1	-	*	0.3	0.1	1.3	0.5	1.9	1.1
3.6	8.2	6.5	-	0.1	-	0.1	0.1	0.1	1.8	0.9	1.7	1.2
3.7	8.0	6.7	-	0.2	-	0.1	1.0	0.2	1.8	1.5	5.5	4.0
3.8	8.8	6.5	-	0.3	*	0.3	0.9	0.3	3.5	2.3	12.7	6.7
3.9	7.8	6.5	-	0.6	0.1	0.5	0.2	0.4	5.0	3.4	20.1	10.1
4.0	9.4	6.9	-	1.3	0.6	1.2	0.4	0.8	8.2	4.8	13.1	8.7
4.1	9.2	7.8	-	2.2	1.4	2.2	0.4	1.3	10.1	6.9	1.2	7.9
4.2	6.1	6.3	-	3.4	4.9	4.0	1.3	2.0	9.9	9.2	1.7	7.9
4.3	5.5	6.5	-	4.9	11.4	6.5	0.1	3.0	10.6	11.5	8.3	10.5
4.4	3.2	5.4	-	6.3	17.2	9.6	1.0	4.5	11.4	12.1	2.5	8.0
4.5	1.5	4.0	-	8.2	18.1	12.8	8.9	6.2	9.3	11.3	6.3	9.6
4.6	0.3	2.5	-	9.7	14.7	15.2	7.6	8.7	8.1	10.2	1.2	7.5
4.7	*	1.8	-	11.2	12.3	15.8	6.7	11.2	8.1	8.6	4.4	5.9
4.8	-	1.6	-	12.6	10.5	13.5	10.6	13.6	5.7	6.2	2.3	4.0
4.9	-	0.8	-	11.7	6.2	9.0	4.7	14.6	2.0	4.3	4.0	3.2
5.0	-	0.3	-	9.6	2.0	5.1	9.0	13.3	1.1	2.8	4.9	1.4
5.1	-	*	-	7.7	0.3	2.5	6.2	9.9	0.6	1.6	-	0.2
5.2	-	*	-	4.4	*	0.9	14.9	5.7	0.3	0.8	-	0.1
5.3	-	-	-	2.6	*	0.4	21.7	2.6	*	0.3	-	*
5.4	-	-	-	1.3	*	0.1	4.4	1.0	*	0.1	-	-
5.5 & Above	-	-	-	1.4	*	*	-	0.4	-	*	-	-
Average	3.70	3.82	-	4.74	4.54	4.62	4.94	4.80	4.30	4.41	4.07	4.24

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Dec 25, 2025										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	3.4	1.3	3.7	3.0	-	*	7.1	2.7	1.5	1.2
Bark - Level 2	-	*	-	-	-	-	-	*	-	-
Grass - Level 1	0.2	0.1	0.1	0.1	-	*	0.2	0.2	*	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	-	-	-	*	-	-	*	*	-	*
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	3.4	1.4	-	*	0.1	0.2	0.4	0.5
Seed Coat - Level 2	-	-	-	-	-	-	-	*	-	-
Oil - Level 1	-	-	-	-	-	-	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	*	-	-
Other - Level 1	-	*	-	-	-	-	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	-	*	*	*	0.1	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	-	-	-	-	-	-	*	*	-	-
23	-	*	-	-	-	-	0.1	*	-	-
24	-	*	-	*	-	*	0.1	*	*	*
25	*	*	*	*	-	*	0.2	0.2	0.3	*
26	0.1	0.1	0.2	0.2	-	*	1.0	0.7	1.2	1.0
27	0.6	0.7	2.8	1.8	-	0.5	3.2	2.5	10.9	5.8
28	2.2	3.3	15.3	11.5	-	3.8	9.0	7.1	24.9	18.9
29	7.8	8.9	41.4	35.8	-	21.0	15.9	15.2	32.9	32.4
30	14.2	14.0	25.1	31.2	-	38.7	20.6	20.7	18.4	25.9
31	21.1	17.0	11.4	13.3	-	24.7	19.6	18.8	6.1	11.3
32	17.6	16.2	3.1	4.7	-	8.2	14.0	13.7	4.7	3.7
33	17.1	15.8	0.6	1.2	-	2.4	8.5	10.0	0.6	0.8
34	11.2	12.7	0.1	0.2	-	0.7	4.4	6.8	*	0.2
35	5.3	7.2	*	*	-	0.1	2.0	3.0	*	*
36	1.9	2.6	-	*	-	*	0.9	1.0	-	*
37	0.7	1.2	-	*	-	*	0.3	0.3	-	-
38	0.2	0.3	-	-	-	-	0.1	0.1	-	-
39	*	*	-	-	-	-	*	*	-	-
40 & Above	*	*	-	-	-	-	*	*	-	-
Average	32.28	32.36	29.84	30.07	-	30.66	31.05	31.32	29.39	29.76
Mike										
2.4 & Below	-	*	-	-	-	-	*	*	-	-
2.5	*	*	-	-	-	-	0.1	*	-	-
2.6	*	*	-	-	-	-	0.3	0.1	-	-
2.7	0.1	*	-	-	-	*	0.4	0.1	-	*
2.8	0.1	*	-	*	-	*	0.4	0.2	-	*
2.9	0.2	0.1	-	*	-	*	0.6	0.3	-	*
3.0	0.3	0.1	0.1	*	-	*	1.0	0.5	1.0	0.1
3.1	0.5	0.2	0.2	*	-	*	1.3	0.7	0.6	0.1
3.2	0.4	0.3	0.4	0.1	-	*	1.8	1.0	1.6	0.1
3.3	1.0	0.5	0.8	0.2	-	*	2.1	1.4	2.1	0.2
3.4	1.5	0.8	1.3	0.3	-	0.1	2.6	1.9	2.3	0.4
3.5	1.6	1.2	1.1	0.4	-	0.3	3.6	2.5	2.3	0.7
3.6	2.0	2.3	1.2	0.7	-	0.3	4.3	3.2	2.1	1.2
3.7	3.2	3.5	1.2	1.4	-	0.8	4.9	3.9	2.9	2.6
3.8	5.0	5.4	2.0	2.1	-	1.1	5.6	5.0	4.8	3.9
3.9	6.7	7.4	3.1	3.3	-	1.7	6.1	6.3	9.4	6.6
4.0	6.5	8.6	5.9	5.1	-	2.5	6.7	7.6	6.8	9.1
4.1	8.2	9.9	7.7	6.5	-	3.9	7.4	8.8	8.8	11.6
4.2	10.1	10.0	9.7	8.3	-	5.3	7.9	9.9	10.9	14.1
4.3	12.2	10.9	10.6	9.5	-	6.7	7.7	10.0	10.3	14.6
4.4	12.2	10.1	9.7	10.4	-	9.5	8.0	9.5	15.8	12.9
4.5	11.1	9.7	12.9	11.1	-	11.8	7.3	8.2	8.2	9.0
4.6	8.2	8.0	12.5	10.3	-	13.4	6.1	6.5	4.6	6.0
4.7	4.6	5.5	8.8	9.2	-	13.4	5.1	4.7	3.2	3.2
4.8	2.5	3.3	5.1	7.5	-	11.8	3.9	3.2	1.2	1.8
4.9	1.1	1.5	2.6	5.6	-	8.1	2.2	1.9	0.8	1.0
5.0	0.6	0.5	1.9	3.8	-	5.4	1.2	1.0	*	0.5
5.1	0.1	0.1	1.0	2.3	-	2.7	0.8	0.6	0.3	0.2
5.2	*	*	0.1	1.1	-	1.0	0.3	0.3	-	*
5.3	-	*	0.2	0.5	-	0.3	0.1	0.2	-	*
5.4	-	-	*	0.2	-	*	*	0.1	-	*
5.5 & Above	-	*	-	0.1	-	*	*	0.1	-	*
Average	4.21	4.23	4.36	4.45	-	4.56	4.11	4.17	4.13	4.23

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE												
For The Week Ending Dec 25, 2025												
Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	*	-	-	-	-	-	-	-	-	*	*
2.7 - 2.9	-	*	-	*	-	-	-	0.1	-	-	0.1	*
3.0 - 3.2	*	0.1	*	*	*	*	-	0.7	-	0.1	0.3	0.1
3.3 - 3.4	0.9	0.5	-	*	*	0.2	0.1	0.5	-	0.1	0.5	0.3
3.5 - 3.6	3.1	1.8	*	0.1	0.7	0.5	0.1	2.5	0.6	1.3	2.1	1.3
3.7 - 4.2	41.3	32.6	3.9	3.9	30.9	23.9	58.1	38.5	16.0	21.7	35.8	28.1
4.3 - 4.9	49.5	58.0	59.8	71.2	61.8	68.6	19.3	48.3	75.3	70.8	56.8	61.2
5.0 - 5.2	4.0	5.9	30.2	22.0	3.9	5.9	17.3	7.7	8.0	5.7	4.3	8.0
5.3 & Above	1.2	1.1	6.0	2.8	2.6	0.8	5.0	1.7	*	0.4	0.2	1.0
Average	4.30	4.40	4.81	4.76	4.44	4.48	4.38	4.36	4.53	4.47	4.34	4.45
Leaf												
1 - 2	6.9	15.8	1.2	2.1	19.8	42.7	47.8	48.1	3.1	8.1	14.4	15.0
3	51.6	55.2	28.6	39.3	23.8	33.9	44.9	34.7	45.3	53.6	57.5	59.1
4	35.6	24.9	49.0	45.9	32.2	15.9	7.0	11.3	44.9	33.6	24.9	23.0
5	5.6	3.8	19.3	11.4	18.3	5.7	0.2	4.8	6.3	4.5	3.0	2.7
6	0.4	0.3	1.8	1.2	5.1	1.5	-	1.1	0.3	0.2	0.2	0.2
7	*	*	*	0.1	0.9	0.3	-	-	-	*	*	*
8	-	*	-	-	*	*	-	-	-	-	*	*
Average	3.41	3.17	3.92	3.71	3.65	2.83	2.47	2.68	3.55	3.35	3.17	3.14
HVI Trash 1/												
00	-	-	-	-	-	*	0.1	*	-	-	-	-
01	0.4	2.1	*	0.1	8.1	16.4	20.9	17.8	0.1	0.9	1.4	1.5
02	11.1	17.9	1.7	3.1	13.3	33.1	30.9	35.1	3.8	9.8	18.6	20.2
03	26.2	28.2	9.5	14.8	11.0	18.9	27.0	21.0	16.4	24.0	30.9	32.5
04	25.9	23.7	19.6	24.7	16.6	12.1	14.0	10.6	27.0	28.4	24.2	23.5
05	18.1	14.3	23.4	23.0	15.6	7.7	5.1	5.6	25.5	19.0	13.8	12.4
06	10.0	7.4	19.9	15.9	12.5	4.9	1.5	3.7	15.4	9.9	6.4	5.7
07	4.8	3.6	13.2	9.3	9.2	3.0	0.3	2.6	6.9	4.5	2.8	2.4
08	2.0	1.6	7.4	4.8	5.7	1.7	0.2	1.7	2.6	2.0	1.1	1.0
09	0.9	0.7	3.4	2.4	3.4	1.1	-	1.0	1.5	0.8	0.4	0.4
10	0.3	0.3	1.3	1.1	2.0	0.6	-	0.5	0.5	0.4	0.2	0.2
11	0.1	0.1	0.5	0.5	1.3	0.3	-	0.2	0.3	0.2	0.1	0.1
12	0.1	0.1	0.1	0.2	0.5	0.2	*	0.1	0.1	0.1	*	*
13	*	*	0.1	0.1	0.3	0.1	-	*	-	*	*	*
14	*	*	*	*	0.2	0.1	-	*	-	*	*	*
15	-	*	-	*	0.1	*	-	-	-	*	*	*
16	*	*	-	-	*	*	-	-	*	*	*	*
17	-	*	-	-	*	*	-	-	*	*	*	*
18 & Above	*	*	-	-	-	*	-	-	-	*	*	*
Average	0.42	0.38	0.55	0.51	0.48	0.31	0.26	0.29	0.48	0.42	0.37	0.36
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	-	-	-	-	-	-	-	-	-	-	*
76	-	*	-	*	-	*	-	*	-	*	*	*
77	*	*	*	*	*	*	-	*	-	*	0.1	0.1
78	0.4	0.3	0.1	0.1	0.1	0.2	-	1.1	*	0.1	0.9	0.8
79	4.7	2.5	0.4	0.5	0.4	1.5	-	6.7	0.5	1.1	5.2	5.2
80	20.7	12.9	3.9	3.8	9.0	12.0	28.2	16.5	2.5	8.1	22.6	21.2
81	38.2	31.5	27.4	20.5	29.2	34.9	33.0	24.4	31.5	37.4	36.8	36.6
82	24.1	35.4	34.4	43.1	46.3	40.5	29.4	30.2	54.3	41.2	25.8	26.5
83	9.6	15.1	25.0	27.7	14.5	10.3	6.0	16.0	10.6	10.8	7.5	8.1
84	2.1	2.0	8.3	4.1	0.5	0.6	3.3	4.9	0.6	1.1	1.0	1.3
85 & Above	0.1	0.2	0.5	0.2	*	*	0.1	0.1	-	0.1	0.1	0.1
Average	81.63	81.98	82.51	82.52	82.12	81.92	81.68	81.88	82.18	82.01	81.53	81.57
Tenderable 3/	87.4	90.5	60.8	70.0	85.7	87.4	75.1	84.0	86.1	91.6	91.0	88.3
SAMPLES CLASSED	16,789	504,893	27,431	1,317,430	11,784	103,512	5,229	48,707	2,697	85,413	111,744	1,457,106

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Dec 25, 2025

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	0.1	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	2.7	1.0	-	*	-	-	-	-	-	*	-	-
2.7 - 2.9	6.7	5.4	-	*	-	-	-	-	0.1	*	1.0	0.2
3.0 - 3.2	8.2	8.6	-	*	-	*	-	*	0.3	0.2	5.5	1.0
3.3 - 3.4	9.0	8.9	-	0.1	-	*	0.1	*	0.7	0.5	1.7	1.0
3.5 - 3.6	13.3	12.4	-	0.2	-	0.1	0.4	0.2	3.2	1.4	3.6	2.3
3.7 - 4.2	49.4	40.7	-	8.1	7.0	8.4	4.0	5.0	38.6	28.1	54.3	45.2
4.3 - 4.9	10.6	22.7	-	64.6	90.5	82.4	39.5	61.8	55.1	64.2	29.1	48.6
5.0 - 5.2	-	0.3	-	21.7	2.4	8.5	30.0	29.0	2.0	5.2	4.9	1.7
5.3 & Above	-	-	-	5.2	*	0.5	26.1	4.0	*	0.4	-	*
Average	3.70	3.82	-	4.74	4.54	4.62	4.94	4.80	4.30	4.41	4.07	4.24
Leaf												
1 - 2	3.1	12.1	-	14.2	4.4	4.0	1.4	6.3	6.3	9.3	38.7	63.7
3	20.6	28.1	-	49.8	56.4	53.0	52.5	42.8	53.7	51.6	41.1	27.8
4	30.2	29.6	-	29.5	34.7	37.2	43.1	39.7	35.1	32.7	16.1	6.0
5	24.5	18.4	-	6.1	4.5	5.4	2.7	10.1	4.7	5.7	3.8	1.8
6	13.8	8.4	-	0.4	0.1	0.4	0.2	1.0	0.2	0.5	0.3	0.6
7	5.9	2.6	-	-	-	*	-	*	*	0.1	-	0.1
8	1.9	0.8	-	-	-	-	-	-	*	*	-	-
Average	4.51	3.93	-	3.28	3.39	3.45	3.48	3.57	3.39	3.37	2.81	2.33
HVI Trash 1/												
00	-	-	-	-	-	*	-	-	-	-	-	-
01	0.3	3.0	-	1.9	0.1	0.2	-	0.5	0.1	0.8	10.6	27.1
02	4.7	11.4	-	15.0	8.6	6.2	2.6	7.7	8.2	11.1	30.4	39.5
03	9.7	13.3	-	24.4	28.4	23.1	13.9	19.0	25.3	24.3	23.0	18.1
04	11.3	13.6	-	23.2	27.5	28.7	31.5	23.6	27.8	25.4	19.3	7.8
05	12.5	13.0	-	16.2	18.7	20.9	30.1	19.9	18.9	18.3	9.0	3.7
06	11.9	10.9	-	9.6	10.1	11.4	14.1	13.3	11.2	10.6	4.5	1.8
07	10.7	8.6	-	5.2	4.3	5.4	5.1	7.9	4.8	5.3	2.1	1.0
08	9.1	6.9	-	2.5	1.5	2.3	2.1	4.2	2.3	2.4	0.9	0.6
09	6.8	5.2	-	1.2	0.6	1.0	0.4	2.1	0.8	1.0	0.2	0.2
10	5.3	4.0	-	0.5	0.2	0.4	0.2	1.0	0.3	0.4	0.1	0.1
11	4.7	3.0	-	0.2	*	0.2	-	0.5	0.1	0.2	0.1	*
12	3.6	2.2	-	0.1	*	0.1	-	0.2	0.1	0.1	-	0.1
13	2.6	1.6	-	*	*	*	-	0.1	*	*	-	*
14	2.1	1.1	-	*	-	*	-	*	-	*	-	-
15	1.0	0.6	-	-	-	*	-	*	*	*	-	-
16	1.2	0.5	-	-	-	-	-	-	*	*	-	-
17	0.9	0.4	-	-	-	-	-	-	-	*	-	-
18 & Above	1.7	0.8	-	-	-	-	-	-	*	*	-	-
Average	0.72	0.59	-	0.41	0.42	0.44	0.47	0.47	0.43	0.43	0.31	0.24
UNIFORMITY 2/												
74 & Below	-	*	-	-	-	-	-	-	-	*	-	-
75	0.1	0.1	-	-	-	-	-	-	*	*	-	-
76	0.5	0.3	-	-	-	*	-	*	-	*	-	-
77	2.1	1.2	-	-	-	*	-	*	*	*	-	*
78	5.2	3.3	-	0.1	*	0.1	0.4	0.2	0.4	0.6	0.3	0.3
79	10.3	7.9	-	1.2	0.1	0.2	0.4	1.3	3.4	2.9	3.3	1.5
80	18.1	17.0	-	7.1	0.5	2.1	5.5	8.8	10.1	10.7	9.3	12.4
81	37.1	31.1	-	30.1	15.8	16.0	44.6	30.1	25.1	27.0	56.2	41.6
82	22.3	26.4	-	40.4	54.1	50.1	48.2	38.1	33.9	35.4	24.3	33.9
83	3.8	10.9	-	18.5	26.2	28.6	0.7	18.1	24.0	20.4	5.6	9.9
84	0.3	1.8	-	2.6	2.7	2.6	0.2	3.3	3.0	2.8	1.0	0.4
85 & Above	*	0.1	-	0.1	0.7	0.2	-	0.1	0.1	0.2	-	*
Average	81.11	81.49	-	82.21	82.63	82.58	81.90	82.18	82.18	82.12	81.65	81.83
Tenderable 3/	44.4	46.8	-	71.5	96.5	86.2	42.7	63.7	93.6	90.6	77.0	93.6
SAMPLES CLASSED	7,086	72,078	-	223,278	29,297	627,304	1,138	706,396	17,935	616,217	1,294	7,362

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Dec 25, 2025										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	*	-	-	-	-	*	*	-	-
2.5 - 2.6	*	*	-	-	-	-	0.4	0.1	-	-
2.7 - 2.9	0.4	0.1	-	*	-	*	1.4	0.6	-	*
3.0 - 3.2	1.2	0.6	0.6	0.1	-	*	4.2	2.2	3.1	0.3
3.3 - 3.4	2.5	1.4	2.1	0.5	-	0.2	4.7	3.4	4.4	0.6
3.5 - 3.6	3.6	3.4	2.3	1.1	-	0.6	7.9	5.8	4.4	1.9
3.7 - 4.2	39.6	44.7	29.7	26.7	-	15.1	38.7	41.7	43.7	48.0
4.3 - 4.9	52.0	49.1	62.1	63.6	-	74.7	40.2	44.0	44.1	48.5
5.0 - 5.2	0.6	0.7	3.0	7.2	-	9.0	2.4	1.9	0.3	0.7
5.3 & Above	-	*	0.2	0.8	-	0.3	0.2	0.4	-	*
Average	4.21	4.23	4.36	4.45	-	4.56	4.11	4.17	4.13	4.23
Leaf										
1 - 2	60.3	63.2	3.3	5.0	-	16.4	63.3	56.1	11.9	11.3
3	31.5	29.8	46.2	51.0	-	59.0	28.5	31.8	66.4	61.6
4	6.4	5.9	44.3	38.6	-	21.8	6.6	9.9	18.2	23.9
5	1.5	0.9	6.0	5.3	-	2.7	1.3	1.9	3.3	3.1
6	0.2	0.1	0.1	0.2	-	0.2	0.2	0.3	0.2	0.1
7	*	*	*	*	-	*	0.1	*	-	*
8	*	*	-	-	-	-	*	*	-	-
Average	2.34	2.22	3.54	3.45	-	3.11	2.31	2.43	3.13	3.19
HVI Trash 1/										
00	*	0.1	-	-	-	*	0.1	0.1	-	-
01	27.6	33.6	0.1	0.2	-	2.0	31.3	27.5	0.3	0.5
02	36.5	32.4	4.6	7.1	-	17.1	38.7	32.8	12.4	12.6
03	19.4	18.1	19.9	23.5	-	29.7	16.5	18.4	33.8	29.9
04	9.2	9.0	28.6	27.9	-	24.7	7.1	10.2	26.9	26.6
05	3.7	3.8	23.5	21.0	-	14.2	3.3	5.5	13.5	15.9
06	1.6	1.6	13.6	11.6	-	6.8	1.5	2.9	6.6	8.1
07	0.9	0.7	6.1	5.3	-	3.1	0.7	1.4	3.6	3.8
08	0.6	0.3	2.3	2.1	-	1.3	0.4	0.6	1.8	1.6
09	0.2	0.1	0.8	0.8	-	0.6	0.2	0.3	0.8	0.6
10	0.1	0.1	0.3	0.3	-	0.2	0.1	0.1	0.2	0.2
11	0.1	*	0.1	0.1	-	0.1	*	0.1	0.1	0.1
12	*	*	*	*	-	*	*	*	*	*
13	*	*	*	*	-	*	*	*	*	*
14	-	*	-	*	-	*	*	*	-	*
15	-	*	*	*	-	*	*	*	*	*
16	-	*	-	*	-	-	*	*	-	*
17	*	*	-	-	-	-	*	*	-	*
18 & Above	-	*	-	*	-	-	*	*	-	*
Average	0.24	0.23	0.46	0.44	-	0.38	0.22	0.25	0.39	0.40
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	*	*	-	-
75	-	*	-	*	-	-	0.1	*	-	-
76	*	*	*	*	-	*	0.4	0.2	-	*
77	0.2	0.2	0.1	*	-	*	1.6	0.8	-	*
78	1.0	1.0	0.7	0.4	-	0.1	6.4	3.4	0.1	0.2
79	5.5	5.0	4.5	3.2	-	0.6	17.5	11.4	1.2	1.4
80	18.9	16.5	20.3	15.5	-	6.9	31.0	24.7	6.6	8.3
81	34.9	31.0	33.9	31.9	-	32.7	28.2	30.2	33.3	27.7
82	25.7	26.4	29.9	34.5	-	43.1	11.9	19.7	36.6	38.1
83	11.9	15.1	10.2	13.2	-	15.6	2.5	7.6	20.2	21.2
84	1.8	4.5	0.4	1.1	-	0.9	0.4	1.8	2.0	2.9
85 & Above	0.1	0.4	*	0.1	-	0.1	0.1	0.2	0.1	0.2
Average	81.67	81.86	81.66	81.86	-	82.14	80.69	81.24	82.20	82.23
Tenderable 3/	90.6	94.6	86.8	86.3	-	82.3	77.5	84.7	90.3	96.4
SAMPLES CLASSED	26,645	273,695	22,616	234,272	-	340,307	262,150	4,197,483	5,558	168,348

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE									
For The Week Ending Dec 25, 2025									
Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	2.4	2.5	0.8	5.5	-	-	9.7	17.1
	2	1.1	0.3	3.3	6.3	-	-	10.8	16.4
	3	-	*	0.1	0.1	-	-	-	0.4
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		3.5	2.8	4.3	11.9	-	-	20.5	33.9
02	1	43.3	40.5	1.7	4.8	-	-	14.0	15.6
	2	28.1	18.5	23.7	34.6	-	-	42.6	41.4
	3	0.4	0.2	9.7	8.7	-	-	1.7	3.0
	4	-	-	0.2	0.1	-	-	-	0.1
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		71.7	59.2	35.3	48.2	-	-	58.3	60.2
03	1	11.6	12.6	0.2	0.2	-	-	2.2	0.3
	2	11.5	22.1	19.8	13.8	-	-	16.4	4.6
	3	-	0.8	27.0	18.7	-	-	2.1	0.9
	4	-	-	3.0	2.1	-	-	-	0.1
	5	-	-	0.1	0.1	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		23.1	35.5	50.1	34.9	-	-	20.8	5.9
04	1	0.6	0.3	-	*	-	-	-	-
	2	1.0	1.9	1.4	0.6	-	-	0.3	*
	3	-	0.2	4.4	2.5	-	-	0.1	*
	4	-	-	2.0	1.1	-	-	-	*
	5	-	-	0.2	0.1	-	-	-	-
	6	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		1.6	2.5	8.0	4.2	-	-	0.4	0.1
05	1	-	-	-	*	-	-	-	-
	2	0.1	*	0.1	0.1	-	-	-	-
	3	-	-	0.8	0.3	-	-	-	-
	4	-	-	1.3	0.3	-	-	-	-
	5	-	-	0.1	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		0.1	*	2.3	0.6	-	-	-	-
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	*	-	-	-	-
	3	-	-	*	*	-	-	-	-
	4	-	-	0.1	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	0.1	*	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	-	-	-	-	-
STAPLE									
44 & Shorter		0.3	0.1	2.8	2.1	-	-	6.8	11.8
46		10.7	20.3	8.3	8.4	-	-	54.7	51.0
48		74.6	74.1	33.0	45.4	-	-	22.8	32.7
50		14.0	5.3	50.4	42.1	-	-	9.8	3.9
52 & Longer		0.4	0.2	5.5	2.1	-	-	5.7	0.6
Average Staple		48.07	47.71	48.95	48.68	-	-	47.06	46.61
Average Length		1.40	1.39	1.42	1.41	-	-	1.37	1.36
EXTRANEIOUS MATTER									
Bark		-	-	-	*	-	-	-	*
Grass		-	-	0.4	0.3	-	-	-	1.2
Spindle Twist		-	-	0.2	0.1	-	-	-	-
Preparation		-	*	-	*	-	-	-	-
All Other		-	*	*	*	-	-	-	*

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE								
For The Week Ending Dec 25, 2025								
Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	-
2.7 - 2.9	-	*	0.3	0.1	-	-	0.2	0.2
3.0 - 3.2	-	*	1.5	0.4	-	-	6.4	12.2
3.3 - 3.4	0.6	0.4	1.6	1.4	-	-	16.0	17.3
3.5 - 3.6	3.3	1.3	5.9	7.2	-	-	6.1	20.8
3.7 - 4.2	93.5	93.2	88.6	88.3	-	-	54.4	48.0
4.3 - 4.9	2.7	5.1	2.1	2.6	-	-	16.9	1.5
5.0 - 5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	3.92	3.99	3.89	3.90	-	-	3.83	3.64
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-
2.7	-	*	-	*	-	-	0.1	*
2.8	-	-	*	*	-	-	0.1	*
2.9	-	-	0.3	0.1	-	-	-	0.2
3.0	-	*	0.7	0.1	-	-	0.1	2.0
3.1	-	-	0.3	0.1	-	-	5.0	4.7
3.2	-	-	0.6	0.3	-	-	1.3	5.4
3.3	0.1	0.2	0.8	0.5	-	-	-	6.4
3.4	0.5	0.2	0.8	0.9	-	-	16.0	10.8
3.5	1.6	0.2	1.6	2.1	-	-	0.1	12.6
3.6	1.7	1.0	4.3	5.1	-	-	6.0	8.2
3.7	6.5	4.5	12.7	10.1	-	-	18.0	8.1
3.8	22.8	12.6	17.1	17.0	-	-	8.6	9.8
3.9	30.7	20.5	22.2	22.8	-	-	3.6	12.0
4.0	16.9	26.2	17.5	20.9	-	-	5.3	9.8
4.1	12.2	20.5	13.7	11.9	-	-	15.1	6.7
4.2	4.3	8.9	5.5	5.5	-	-	3.8	1.6
4.3	1.9	2.8	1.3	1.7	-	-	10.6	1.0
4.4	0.5	2.1	0.4	0.6	-	-	5.8	0.4
4.5	0.3	0.2	0.2	0.3	-	-	0.2	0.2
4.6	-	*	0.1	0.1	-	-	0.2	*
4.7	-	*	*	*	-	-	-	*
4.8	-	-	-	*	-	-	-	-
4.9	-	-	-	*	-	-	-	*
5.0	-	-	-	-	-	-	-	-
5.1	-	-	-	-	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	3.92	3.99	3.89	3.90	-	-	3.83	3.64
STRENGTH 1/ 36 & Below	-	-	1.7	1.6	-	-	1.7	11.9
37	0.6	0.1	3.8	4.6	-	-	18.1	20.7
38	0.7	0.2	3.1	2.9	-	-	15.0	18.5
39	3.9	0.9	2.8	1.3	-	-	3.8	7.3
40	7.4	7.1	2.5	1.9	-	-	6.8	2.5
41	16.9	24.9	5.4	6.0	-	-	16.4	2.9
42	31.7	35.5	7.9	11.8	-	-	2.3	5.1
43	22.5	22.4	13.5	18.6	-	-	27.9	7.7
44	7.3	6.9	22.8	22.1	-	-	7.2	8.9
45	6.3	1.3	20.3	17.8	-	-	0.2	7.0
46	2.3	0.5	12.0	8.3	-	-	-	4.9
47	0.3	0.2	3.4	2.6	-	-	0.4	2.0
48 & Above	0.3	0.1	0.8	0.8	-	-	0.1	0.7
Average	42.66	42.45	43.75	43.54	-	-	40.87	40.42
UNIFORMITY								
83 & Below	0.6	0.2	1.8	1.2	-	-	5.4	1.7
84	5.3	3.4	12.7	11.5	-	-	7.8	21.8
85	33.0	40.5	32.0	32.4	-	-	51.1	46.4
86	52.2	50.6	48.3	48.8	-	-	27.6	26.8
87	8.5	5.2	4.7	5.6	-	-	7.9	3.1
88 & Above	0.4	0.1	0.3	0.5	-	-	0.1	0.1
Average	86.08	86.03	85.86	85.92	-	-	85.66	85.52
Samples Classed	1,054	7,937	16,900	228,893	-	-	906	21,769

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.