



Weekly Quality of Cotton Classed by Classing Office: Week Ending - 1/1/2026

Agricultural Marketing Service
Cotton Market News

Volume 67, No.22

January 05, 2026

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	31	70.0	53.0	74,746	31	84.9	63.2	758,413
Corpus Christi	5	76.5	53.1	6,458	42	88.1	72.4	1,506,023
Dumas	4	57.6	31.8	15,446	33	53.1	25.2	935,931
Florence	28	89.7	81.0	30,154	40	90.6	79.2	1,048,991
Lamesa	21	86.8	59.4	34,556	24	85.5	61.0	456,096
Lubbock	50	69.3	46.9	161,319	54	80.8	60.9	2,060,752
Macon	63	88.7	76.1	102,861	68	88.7	74.7	1,970,013
Memphis	10	91.6	73.3	19,719	65	83.2	59.6	2,244,077
Rayville*	-	-	-	-	16	69.8	47.8	277,992
Visalia	19	84.6	71.7	28,141	26	85.6	68.1	201,116
United States	232	77.5	59.2	475,871	399	82.5	63.3	11,459,404
AMERICAN PIMA								
Visalia	13			26,824	18			302,116
United States	13			26,824	18			302,116
United States all cotton	241			502,695	408			11,761,520

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

MP_CN100

Source: USDA AMS Cotton and Tobacco Market News

Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov

<https://www.ams.usda.gov/market-news/cotton>

<https://mymarketnews.ams.usda.govcottonmn@ams.usda.gov>

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 01, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	27.1	43.3	3.8	14.3	*	0.9	0.2	0.5	65.1	73.1
	3	8.2	7.8	7.5	14.4	*	0.8	0.7	0.5	8.7	6.8
	4	0.9	0.4	6.0	1.4	-	*	*	*	0.3	0.3
	5	0.1	*	0.6	*	-	*	-	*	-	*
	6	*	*	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	36.3 51.5	17.9 30.2	*	1.7	0.9 1.0	74.1 80.2			
31	1 - 2	8.9	6.8	4.0	5.0	*	2.2	1.7	5.3	4.7	1.4
	3	12.4	10.5	18.3	22.2	6.4	16.3	13.5	21.9	4.2	1.5
	4	5.4	3.5	13.5	9.4	7.7	8.0	8.3	6.0	1.0	0.4
	5	1.3	0.6	2.3	1.0	0.2	0.5	0.6	0.3	*	*
	6	0.2	0.1	*	*	-	*	*	*	*	*
	7	*	*	-	*	-	-	-	-	*	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	28.3 21.5	38.2 37.5	14.3 27.0	24.0 33.6	9.9 3.4				
41	1 - 2	0.4	0.2	0.1	0.6	-	0.6	1.2	2.6	*	*
	3	1.3	0.7	1.1	5.3	7.1	19.3	26.6	29.1	*	*
	4	1.7	1.0	7.2	5.0	43.7	32.8	35.0	24.9	*	*
	5	2.7	1.0	3.9	1.3	20.3	8.8	6.6	4.2	*	*
	6	1.7	0.4	0.1	0.1	1.3	0.6	0.6	0.3	-	*
	7	0.4	0.1	-	*	*	*	*	*	-	*
	8	*	*	-	-	-	-	-	*	-	-
	Total	----	8.1 3.4	12.5 12.4	72.4 62.1	70.0 61.1	* *				
51	1 - 2	-	*	-	*	-	*	*	0.1	-	-
	3	*	*	-	0.2	0.1	1.1	1.5	0.9	-	-
	4	*	*	-	0.4	3.1	3.0	2.3	1.6	-	-
	5	0.1	*	0.1	0.1	5.1	1.5	0.7	0.7	-	-
	6	0.4	*	0.1	*	1.2	0.2	0.1	0.1	-	-
	7	0.4	0.1	*	*	*	*	*	*	-	-
	8	0.1	*	-	-	-	-	-	*	-	-
	Total	----	1.0 0.1	0.2 0.8	9.6 5.9	4.6 3.4	- -				
61	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	*	-	*	*	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- *	- *	* *	- -				
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- -	- -	- *	- -				
12 & 22	1 - 2	4.9	10.5	0.2	4.0	-	*	-	*	9.6	10.8
	3	3.6	3.3	8.9	3.8	-	*	*	*	2.6	2.6
	4	0.9	0.4	10.2	1.0	-	*	*	*	0.1	0.2
	5	0.1	*	1.2	0.1	-	-	-	-	*	*
	6	*	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	9.5 14.2	20.6 8.9	- *	* *	12.2 13.6				
32	1 - 2	1.2	0.9	0.1	0.6	-	*	-	*	0.2	0.2
	3	3.9	2.0	2.4	2.6	*	0.1	*	0.1	0.8	0.4
	4	2.9	1.2	5.3	2.4	0.1	0.1	0.1	0.1	0.6	0.2
	5	1.0	0.4	1.5	0.6	*	*	*	*	0.1	0.1
	6	0.1	0.1	*	*	-	*	*	*	*	*
	7	*	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	9.1 4.6	9.4 6.3	0.1 0.3	0.1 0.2	1.7 0.9				
42	1 - 2	0.1	*	0.1	0.1	-	*	-	*	-	*
	3	0.4	0.3	0.2	0.9	*	0.5	0.1	0.2	-	*
	4	0.7	0.6	0.1	1.1	0.4	1.2	0.2	0.3	*	*
	5	1.2	0.7	0.1	0.6	1.5	0.5	0.1	0.1	*	*
	6	0.7	0.4	*	0.1	0.5	0.1	*	*	*	*
	7	0.3	0.1	-	*	-	*	-	*	-	*
	8	0.1	*	-	-	-	-	-	*	-	-
	Total	----	3.4 2.2	0.5 2.8	2.4 2.3	0.3 0.6	* *				

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 01, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	*	*	-	*	-	*	-	*
	3	-	-	-	*	-	0.1	-	*	-	-
	4	*	*	-	0.1	0.1	0.2	*	*	-	-
	5	*	*	-	0.1	0.7	0.2	-	*	*	*
	6	0.1	*	-	*	0.4	0.1	-	*	-	-
	7	0.1	0.1	-	*	*	*	-	*	-	-
	8	0.2	*	-	-	-	-	-	*	-	-
Total	----	0.4	0.1	*	0.2	1.2	0.6	*	0.1	*	*
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	-	*	-	-
13 & 23	1 - 2	0.5	0.6	-	0.1	-	-	-	-	1.1	0.8
	3	0.6	0.4	-	0.1	-	-	-	*	0.4	0.4
	4	0.3	0.1	*	*	-	-	-	*	*	*
	5	*	*	-	*	-	-	-	-	-	*
	6	-	*	-	*	-	-	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.4	1.2	*	0.3	-	-	-	*	1.6	1.2
33	1 - 2	0.2	0.1	-	*	-	*	-	*	*	0.1
	3	0.7	0.4	*	0.1	-	*	-	*	0.1	0.2
	4	0.5	0.2	0.4	0.1	*	*	*	*	0.1	0.1
	5	0.1	0.1	0.2	*	-	-	-	*	*	*
	6	*	*	*	*	-	-	-	*	*	*
	7	*	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	1.6	0.8	0.6	0.3	*	*	*	*	0.3	0.4
43	1 - 2	*	*	-	*	-	-	-	*	-	*
	3	*	*	-	0.1	*	*	*	*	-	*
	4	0.1	0.1	*	0.1	-	*	0.1	*	-	*
	5	0.2	0.1	*	0.1	*	*	*	*	*	*
	6	0.2	0.1	-	*	-	*	-	*	-	*
	7	0.1	*	-	*	-	-	-	*	-	*
	8	*	*	-	-	-	-	-	*	-	-
Total	----	0.7	0.3	*	0.3	*	*	0.1	*	*	*
53	1 - 2	-	-	-	*	-	*	-	-	-	-
	3	-	*	-	*	-	*	-	*	-	-
	4	-	*	-	*	-	*	-	*	-	-
	5	-	*	-	*	-	*	*	*	-	-
	6	*	*	-	*	-	*	-	*	-	*
	7	*	*	-	*	-	*	-	*	-	-
	8	0.1	*	-	-	-	-	-	*	-	-
Total	----	0.1	*	-	*	-	*	*	*	-	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	-	-	-	-
24 - 54	1 - 8	0.1	0.1	*	*	-	-	*	*	0.1	0.1
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	*	-	-	-	-	*	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	*	*
31		*	0.1	-	*	-	*	-	*	0.1	0.2
32		0.4	0.5	-	*	*	*	-	*	1.5	1.8
33		2.4	2.8	0.1	0.1	*	0.2	0.4	0.1	5.6	7.2
34		7.6	7.7	0.9	0.7	0.8	1.3	3.7	1.2	17.2	20.1
35		15.0	14.4	3.5	3.7	5.7	8.2	14.1	7.7	33.7	27.4
36		21.7	18.8	15.8	15.5	16.7	25.3	30.4	26.0	25.7	21.7
37		25.6	23.8	44.5	45.9	37.4	42.8	38.2	48.8	13.8	16.4
38		14.0	15.2	25.4	25.4	25.9	16.4	11.8	13.2	2.4	4.4
39		9.3	10.9	8.3	7.8	12.1	4.8	1.2	2.7	0.1	0.7
40 & Longer		4.1	5.9	1.5	0.7	1.3	1.1	0.1	0.3	-	*
Average Staple		36.59	36.71	37.21	37.18	37.23	36.83	36.43	36.74	35.28	35.30
Average Length		1.14	1.15	1.16	1.16	1.16	1.15	1.14	1.15	1.10	1.10

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 01, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	37.8	60.7	1.8	1.7	*	0.4	-	3.9	21.1	25.2
	3	17.2	15.7	1.6	1.0	-	0.4	-	2.6	3.1	7.3
	4	1.1	0.9	0.1	*	-	*	-	0.1	0.2	0.4
	5	*	*	*	*	-	*	-	*	*	*
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	56.1 77.3	3.4 2.7	* 0.8	-	6.7	24.4 32.9			
31	1 - 2	4.8	2.4	6.1	8.2	0.5	2.7	-	8.0	9.8	12.7
	3	9.2	4.6	20.5	21.9	5.9	12.3	-	33.3	10.9	14.2
	4	4.0	2.0	5.8	4.0	0.3	3.5	-	11.7	3.5	3.7
	5	0.6	0.3	0.4	0.2	*	0.2	-	0.9	0.2	0.5
	6	0.1	*	*	*	-	*	-	*	-	*
	7	*	*	-	*	-	*	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	18.7 9.4	32.8 34.3	6.7 18.6	-	54.0	24.4 31.1			
41	1 - 2	*	*	3.5	5.2	1.3	2.3	-	0.7	3.0	2.3
	3	0.1	0.1	26.7	32.5	36.8	30.5	-	12.2	16.1	9.7
	4	0.1	0.1	16.8	16.9	33.5	26.8	-	16.2	13.3	7.7
	5	0.2	0.1	2.5	2.1	5.9	5.1	-	4.5	5.1	2.8
	6	0.1	*	0.1	0.1	0.4	0.4	-	0.4	0.7	0.4
	7	*	*	*	*	*	*	-	-	0.1	*
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	0.5 0.3	49.6 56.8	77.9 65.2	-	34.2	38.3 22.9			
51	1 - 2	*	*	0.4	0.2	*	0.1	-	*	0.2	0.1
	3	*	*	4.7	1.8	4.0	2.8	-	*	1.6	0.7
	4	*	*	5.3	1.8	8.3	4.7	-	0.3	3.5	1.4
	5	*	*	1.2	0.5	1.2	1.7	-	0.3	2.3	1.2
	6	*	*	0.1	*	*	0.3	-	0.1	0.9	0.5
	7	-	*	*	*	-	*	-	-	0.2	0.1
	8	-	*	-	*	-	-	-	-	*	*
	Total	----	* *	11.6 4.4	13.5 9.5	-	0.7	8.8 4.1			
61	1 - 2	-	*	*	*	-	*	-	-	-	-
	3	-	*	0.1	*	-	*	-	*	-	-
	4	-	*	*	*	*	*	-	*	*	*
	5	-	-	*	*	-	*	-	-	*	*
	6	-	-	*	*	-	*	-	-	*	*
	7	-	-	-	*	-	*	-	-	-	*
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	- *	0.1 *	* *	-	*	* *			
71	1 - 2	-	*	-	-	-	*	-	-	-	-
	3	-	*	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- *	- -	- *	-	-	- -			
12 & 22	1 - 2	7.5	5.5	*	*	-	*	-	0.1	1.7	2.9
	3	7.4	3.5	0.1	*	-	*	-	0.1	0.4	1.5
	4	0.7	0.4	*	*	-	*	-	0.1	*	0.2
	5	*	*	-	-	-	*	-	*	-	*
	6	-	*	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	15.7 9.4	0.1 0.1	- *	-	0.3	2.2 4.6			
32	1 - 2	0.4	0.2	*	0.1	-	*	-	0.1	*	0.2
	3	1.8	0.8	0.2	0.3	*	0.2	-	0.4	0.1	0.6
	4	1.3	0.5	0.1	0.1	-	0.1	-	0.7	0.2	0.5
	5	0.3	0.1	*	*	-	*	-	0.4	*	0.2
	6	0.1	*	-	*	-	*	-	0.1	-	*
	7	*	*	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	4.0 1.7	0.4 0.4	* 0.3	-	1.6	0.4 1.6			
42	1 - 2	*	*	*	*	-	0.2	-	*	*	*
	3	0.1	*	0.3	0.5	0.3	1.8	-	0.3	0.3	0.5
	4	0.1	0.1	0.4	0.4	0.5	1.5	-	1.1	0.5	0.5
	5	0.1	0.1	0.1	0.1	0.4	0.4	-	0.7	0.2	0.3
	6	0.1	*	*	*	0.1	0.1	-	0.3	*	0.1
	7	0.1	*	*	*	*	*	-	-	-	*
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	0.4 0.2	0.9 1.1	1.3 3.9	-	2.4	1.0 1.5			

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 01, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	*	*	-	*	-	-	*	*
	3	-	-	0.1	*	0.1	0.4	-	*	0.3	0.1
	4	-	*	0.3	0.1	0.2	0.6	-	*	0.1	0.2
	5	-	*	0.2	*	0.1	0.3	-	0.1	*	0.2
	6	*	*	*	*	0.1	0.1	-	*	*	0.1
	7	-	*	-	*	*	*	-	-	*	*
	8	-	-	-	*	-	-	-	-	*	*
Total	----	*	*	0.6	0.2	0.4	1.4	-	0.1	0.4	0.7
62	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	*	*
	4	-	-	*	*	*	*	-	-	-	*
	5	-	-	*	*	-	*	-	-	-	*
	6	-	-	*	*	-	*	-	-	-	*
	7	-	-	-	*	-	*	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	*	*	*	*	-	-	*	*
13 & 23	1 - 2	1.5	0.5	*	*	-	-	-	-	0.1	0.2
	3	1.6	0.4	*	*	-	-	-	-	*	0.1
	4	0.3	0.1	*	*	-	-	-	-	-	*
	5	*	*	-	-	-	-	-	-	-	-
	6	*	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	3.4	1.0	*	*	-	-	-	-	0.1	0.3
33	1 - 2	0.2	0.1	*	*	-	*	-	-	-	*
	3	0.6	0.2	*	*	-	*	-	*	*	*
	4	0.3	0.1	*	*	*	*	-	*	*	*
	5	0.1	*	*	*	-	*	-	*	-	*
	6	*	*	-	-	-	*	-	*	-	*
	7	*	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.2	0.5	0.1	*	*	*	-	*	*	0.1
43	1 - 2	-	*	*	*	-	*	-	*	-	*
	3	*	*	*	*	*	*	-	*	-	*
	4	*	*	*	*	*	*	-	*	*	*
	5	*	*	*	*	*	*	-	*	-	*
	6	*	*	*	*	-	*	-	*	-	*
	7	*	*	*	*	-	*	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
Total	----	0.1	*	0.1	*	*	0.1	-	*	*	0.1
53	1 - 2	-	-	-	*	-	*	-	-	-	-
	3	-	-	*	*	-	*	-	-	-	*
	4	-	-	*	*	*	*	-	-	*	*
	5	-	-	*	*	*	*	-	-	*	*
	6	*	*	*	*	-	*	-	*	-	*
	7	-	-	*	*	-	*	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	0.1	*	*	*	-	*	*	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-
24 - 54	1 - 8	0.1	0.1	*	*	-	*	-	-	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	*	-	*	-	-	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		*	*	-	-	-	-	-	-	-	-
30		*	*	-	*	-	-	-	-	-	-
31		*	0.1	*	*	-	*	-	-	-	*
32		0.3	0.5	0.1	0.1	-	*	-	*	-	*
33		1.5	2.5	1.5	0.8	0.1	0.1	-	0.2	0.1	0.1
34		7.6	8.2	6.8	4.4	0.7	0.8	-	1.6	0.3	0.9
35		18.7	17.2	16.5	15.0	4.6	4.2	-	11.4	4.9	3.8
36		28.4	25.2	27.2	30.2	5.1	15.1	-	29.0	16.4	13.7
37		29.7	30.1	33.0	36.4	39.1	47.5	-	40.0	40.5	40.2
38		9.8	11.4	10.8	10.4	42.8	27.0	-	13.7	21.3	25.4
39		2.8	3.5	3.7	2.5	7.4	4.8	-	3.7	8.0	9.5
40 & Longer		1.1	1.2	0.5	0.3	0.1	0.5	-	0.4	8.5	6.2
Average Staple		36.22	36.25	36.33	36.39	37.41	37.12	-	36.65	37.63	37.57
Average Length		1.13	1.13	1.13	1.13	1.17	1.16	-	1.14	1.18	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 01, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	17.4	4.9	*	0.6	*	*	4.1	1.9	1.0	1.5
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	-	0.3	-	0.1	*	*	0.3	0.4
Grass - Level 2	-	-	-	*	-	-	-	-	-	-
Prep - Level 1	*	*	-	*	-	*	*	*	-	-
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	0.5	1.5	3.1	0.7	0.1	0.1
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	*	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	0.1	0.1	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	-	*	-	*	-	-	-	-	*	*
23	*	*	-	*	-	-	-	-	0.1	*
24	*	*	-	*	-	*	*	*	0.3	0.2
25	0.1	0.1	*	*	-	*	0.2	*	1.7	0.7
26	0.6	0.7	0.1	0.2	*	0.1	1.0	0.4	4.2	2.0
27	2.4	2.7	0.6	1.2	0.1	0.5	5.7	2.7	10.0	5.8
28	7.4	8.0	5.0	5.2	1.6	3.9	15.6	12.2	17.5	12.1
29	13.7	14.5	19.8	14.9	8.1	15.6	26.1	30.5	18.8	19.0
30	19.6	17.0	29.3	21.8	20.9	28.8	27.1	30.7	20.2	23.0
31	20.9	16.5	20.4	17.7	25.6	26.9	15.8	15.5	15.7	19.6
32	16.8	14.2	11.4	12.4	22.4	15.6	6.2	5.9	8.1	10.9
33	11.5	11.7	7.4	11.5	12.4	6.1	1.7	1.7	2.1	4.3
34	4.8	8.1	3.9	9.7	5.9	2.0	0.4	0.3	0.7	1.6
35	1.7	4.1	1.7	4.0	2.6	0.4	0.1	0.1	0.2	0.6
36	0.3	1.4	0.3	1.1	0.4	*	*	*	0.1	0.2
37	0.1	0.6	0.1	0.2	0.1	*	-	*	*	0.1
38	*	0.2	-	*	*	*	-	-	-	*
39	*	*	-	*	*	*	-	-	-	-
40 & Above	-	*	-	-	-	-	-	-	-	-
Average	31.26	31.51	31.05	31.59	31.81	31.06	30.00	30.14	29.76	30.37
Mike										
2.4 & Below	*	*	-	-	-	-	-	-	*	*
2.5	0.2	0.1	-	*	-	-	-	*	0.1	0.1
2.6	0.3	0.1	-	*	-	-	-	-	0.1	0.2
2.7	0.4	0.2	-	*	-	-	-	*	*	0.2
2.8	0.5	0.3	-	*	-	-	0.1	*	0.1	0.3
2.9	0.7	0.4	-	*	-	-	*	*	0.3	0.5
3.0	0.9	0.5	-	0.1	-	-	*	*	0.6	0.7
3.1	1.0	0.6	-	0.1	-	-	*	*	0.8	0.8
3.2	1.6	0.9	*	0.3	-	*	*	0.1	0.8	1.1
3.3	2.0	1.2	0.4	0.5	-	*	0.1	0.2	1.5	1.4
3.4	2.6	1.6	2.6	0.9	-	*	0.3	0.3	1.6	1.7
3.5	3.2	2.2	8.8	1.3	-	*	0.7	0.5	2.9	2.3
3.6	4.4	3.3	17.8	1.9	*	0.1	1.4	0.9	3.9	3.0
3.7	5.3	4.3	15.9	2.7	*	0.1	2.6	1.7	4.8	3.7
3.8	6.7	5.4	9.4	4.3	*	0.1	3.9	2.6	4.4	4.6
3.9	7.6	7.2	5.0	6.7	-	0.2	6.3	4.0	5.9	5.4
4.0	8.0	8.6	3.2	9.1	0.1	0.4	6.9	5.6	6.1	6.2
4.1	9.4	10.2	3.8	11.1	0.3	0.6	9.0	7.6	6.3	7.0
4.2	9.1	10.8	5.9	12.7	0.7	1.0	9.8	9.8	7.8	8.1
4.3	9.6	10.8	7.3	12.8	1.9	1.7	12.7	11.6	9.4	8.8
4.4	7.8	9.6	7.0	11.3	3.9	2.8	13.2	11.9	10.2	9.3
4.5	6.2	7.9	6.8	8.9	6.9	4.0	11.4	10.9	8.4	9.1
4.6	5.1	6.0	2.0	6.0	10.4	6.5	8.3	9.5	7.5	8.5
4.7	3.4	3.8	1.0	3.7	10.8	9.6	5.5	7.8	5.6	6.8
4.8	2.0	2.3	0.9	2.4	12.4	13.4	3.6	5.7	5.1	4.9
4.9	0.8	1.1	0.7	1.3	14.2	16.0	2.4	4.0	3.5	2.8
5.0	0.7	0.5	0.7	0.8	15.1	16.2	1.0	2.6	1.6	1.4
5.1	0.1	0.2	0.5	0.4	13.1	12.8	0.3	1.5	0.6	0.6
5.2	*	0.1	0.2	0.3	6.7	8.2	0.2	0.7	*	0.3
5.3	-	*	-	0.2	2.8	4.1	0.1	0.3	*	0.1
5.4	-	-	-	0.1	0.5	1.5	*	0.1	-	*
5.5 & Above	-	*	-	0.2	0.1	0.5	-	*	-	*
Average	4.05	4.14	3.94	4.23	4.84	4.88	4.30	4.39	4.21	4.21

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE

For The Week Ending Jan 01, 2026

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	15.6	5.7	3.6	0.9	-	*	-	1.2	0.3	0.1
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	0.1	0.2	0.1	*	*	-	0.1	0.3	0.4
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	*	*	*	*	-	*	-	-	-	-
Prep - Level 2	*	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.3	0.1	0.7	0.3	*	0.1	-	2.9	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	*	*	-	-	-	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	*	*
Spindle Twist - Level 2	-	*	-	-	-	-	-	-	-	-
Other - Level 1	*	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	-	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	*	*	-	-	-	*	-	-	-	-
23	*	*	*	*	-	*	-	-	-	-
24	0.1	0.1	*	*	-	*	-	-	*	*
25	0.2	0.2	0.1	*	-	*	-	*	*	0.1
26	0.6	0.7	0.9	0.4	*	*	-	0.2	0.2	0.3
27	2.4	2.4	4.9	2.6	*	0.2	-	1.7	3.1	1.7
28	7.1	6.5	15.6	9.6	0.6	1.9	-	6.6	10.5	6.7
29	14.3	13.7	22.7	20.3	11.6	12.3	-	18.1	14.4	13.0
30	20.7	19.5	24.6	25.6	44.1	35.8	-	30.0	17.1	19.2
31	21.0	20.1	16.7	20.7	33.6	32.8	-	19.8	19.0	18.6
32	14.9	15.7	8.7	11.9	8.0	12.2	-	12.5	14.9	12.7
33	9.4	10.4	3.9	5.6	1.9	3.7	-	6.1	10.0	8.9
34	4.9	6.1	1.5	2.3	0.1	0.9	-	3.1	4.8	7.9
35	2.5	2.8	0.3	0.8	*	0.1	-	1.6	2.7	6.1
36	1.1	1.2	*	0.2	-	*	-	0.2	2.5	3.4
37	0.5	0.5	*	*	-	*	-	*	0.7	1.1
38	0.2	0.2	-	*	-	*	-	*	0.1	0.1
39	*	*	-	*	-	-	-	-	*	0.1
40 & Above	-	-	-	-	-	-	-	-	*	*
Average	31.29	31.40	30.26	30.71	30.88	31.01	-	30.93	31.32	31.74
Mike										
2.4 & Below	0.1	*	-	-	-	-	-	-	-	-
2.5	0.1	*	-	*	-	-	-	-	-	-
2.6	0.3	0.1	*	*	-	-	-	*	*	*
2.7	0.4	0.2	*	*	-	*	-	*	*	*
2.8	0.7	0.3	-	*	-	*	-	*	0.1	*
2.9	1.0	0.6	*	*	-	*	-	*	0.1	0.1
3.0	1.5	0.8	*	*	-	*	-	*	0.1	0.1
3.1	1.9	1.2	0.1	*	-	*	-	*	0.5	0.4
3.2	2.0	1.7	0.3	0.1	-	*	-	*	1.3	0.7
3.3	2.4	2.3	0.4	0.1	-	*	-	0.1	0.7	0.5
3.4	3.0	2.9	0.4	0.2	*	0.1	-	0.1	1.2	0.6
3.5	3.9	3.7	1.2	0.5	*	0.1	-	0.2	1.8	1.2
3.6	4.3	4.4	2.2	1.0	-	0.2	-	0.4	1.6	1.5
3.7	4.8	5.0	2.7	1.6	*	0.4	-	0.5	2.6	2.4
3.8	5.8	5.6	3.5	2.5	0.1	0.6	-	0.7	3.4	3.4
3.9	6.0	6.2	5.7	3.7	0.2	1.0	-	1.1	4.8	4.4
4.0	6.5	6.6	7.3	5.2	1.0	1.7	-	1.8	5.0	5.2
4.1	6.6	6.9	9.3	7.2	1.9	2.6	-	3.4	7.0	6.5
4.2	6.8	7.4	11.2	8.9	2.3	3.9	-	4.4	8.1	8.1
4.3	6.8	7.7	11.9	10.0	5.4	5.7	-	5.5	7.9	8.2
4.4	6.4	7.8	10.2	10.3	11.5	8.1	-	6.6	9.0	8.8
4.5	6.5	7.5	7.5	10.1	16.8	10.9	-	8.7	12.0	10.6
4.6	6.0	6.7	7.7	9.4	15.3	13.9	-	9.7	10.2	10.5
4.7	5.5	5.4	6.4	8.5	20.5	15.3	-	10.6	8.0	8.7
4.8	4.0	3.8	4.9	6.9	13.6	14.0	-	11.6	4.3	6.6
4.9	3.1	2.3	3.4	5.2	4.9	10.2	-	10.7	2.8	4.6
5.0	1.9	1.3	1.9	3.7	4.0	6.4	-	8.5	1.6	3.1
5.1	1.0	0.7	0.9	2.4	1.8	3.1	-	7.1	1.8	1.7
5.2	0.4	0.4	0.5	1.3	0.5	1.2	-	4.1	1.3	1.0
5.3	0.2	0.2	0.3	0.7	0.1	0.4	-	2.2	0.8	0.6
5.4	0.1	0.1	0.1	0.3	-	0.1	-	1.1	1.1	0.3
5.5 & Above	*	0.1	*	0.1	-	*	-	1.1	0.7	0.3
Average	4.09	4.12	4.30	4.43	4.61	4.62	-	4.68	4.34	4.38

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 01, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	*	*	-	-	-	-	-	-	*	*
2.5 - 2.6	0.4	0.2	-	*	-	-	-	*	0.2	0.2
2.7 - 2.9	1.6	0.8	-	0.1	-	-	0.1	*	0.4	1.0
3.0 - 3.2	3.6	2.0	*	0.5	-	*	0.1	0.2	2.2	2.6
3.3 - 3.4	4.6	2.8	3.0	1.4	-	*	0.4	0.5	3.1	3.1
3.5 - 3.6	7.7	5.5	26.6	3.1	*	0.1	2.1	1.4	6.8	5.3
3.7 - 4.2	46.1	46.4	43.3	46.5	1.1	2.5	38.5	31.3	35.3	35.1
4.3 - 4.9	35.0	41.4	25.6	46.4	60.6	54.0	57.2	61.4	49.7	50.1
5.0 - 5.2	0.9	0.9	1.4	1.5	35.0	37.3	1.4	4.8	2.2	2.3
5.3 & Above	-	*	-	0.5	3.3	6.1	0.1	0.4	*	0.2
Average	4.05	4.14	3.94	4.23	4.84	4.88	4.30	4.39	4.21	4.21
Leaf										
1 - 2	43.4	62.5	8.3	24.8	*	3.8	3.1	8.5	80.7	86.5
3	31.2	25.4	38.5	49.6	13.8	38.1	42.3	52.8	16.9	11.9
4	13.4	7.5	42.8	21.1	55.0	45.5	45.9	33.0	2.1	1.4
5	6.8	2.9	10.0	4.0	27.7	11.6	8.0	5.3	0.3	0.2
6	3.4	1.2	0.4	0.5	3.4	1.0	0.6	0.4	*	*
7	1.3	0.4	*	0.1	*	*	*	*	*	*
8	0.5	0.1	-	*	-	-	-	*	-	-
Average	2.92	2.37	3.56	3.04	4.21	3.68	3.61	3.36	1.93	1.73
HVI Trash 1/										
00	*	*	-	*	-	-	-	-	0.3	0.7
01	17.8	32.2	0.9	5.2	-	0.3	0.1	0.6	48.9	60.4
02	29.1	33.5	8.8	22.4	0.1	4.6	4.1	10.3	36.6	28.7
03	18.1	15.1	20.4	27.9	2.9	15.1	16.8	24.8	9.6	7.0
04	10.5	7.4	24.9	20.4	13.3	23.2	27.2	26.2	3.0	2.0
05	6.7	4.0	20.2	12.1	23.0	22.1	24.1	18.7	1.1	0.7
06	4.3	2.3	14.3	6.5	23.4	15.7	14.8	10.6	0.3	0.3
07	3.1	1.5	7.0	3.1	17.4	9.5	7.5	5.1	0.1	0.1
08	2.6	1.1	2.5	1.4	10.4	5.0	3.2	2.2	*	0.1
09	1.9	0.8	0.7	0.6	5.8	2.5	1.4	0.9	*	*
10	1.4	0.6	0.2	0.3	2.4	1.1	0.4	0.4	*	*
11	1.1	0.4	0.1	0.1	0.8	0.5	0.2	0.1	*	*
12	0.8	0.3	*	0.1	0.4	0.2	0.1	0.1	*	*
13	0.7	0.2	*	*	0.1	0.1	*	*	-	*
14	0.5	0.2	-	*	*	*	*	*	*	*
15	0.4	0.1	-	*	*	*	-	*	-	-
16	0.3	0.1	-	*	-	-	-	*	-	*
17	0.2	0.1	-	*	-	-	-	*	*	*
18 & Above	0.5	0.1	-	*	-	-	-	*	-	-
Average	0.37	0.26	0.44	0.36	0.61	0.50	0.48	0.43	0.17	0.15
UNIFORMITY 2/										
74 & Below	*	*	*	*	-	-	-	*	-	*
75	*	0.1	-	*	-	-	-	*	0.1	0.1
76	0.2	0.2	-	*	-	*	*	*	0.7	0.5
77	0.9	0.7	*	0.1	*	*	*	*	2.4	2.4
78	3.0	2.9	0.6	0.7	0.2	0.2	0.5	0.5	6.1	10.2
79	12.2	12.3	3.6	3.7	1.1	1.0	2.9	2.7	17.2	25.3
80	27.6	27.4	18.3	13.3	6.3	7.0	16.0	11.5	36.4	34.9
81	32.3	29.3	40.3	30.0	22.9	28.3	31.6	28.4	29.1	21.6
82	18.4	17.7	29.1	31.1	34.1	38.0	30.1	35.5	7.3	4.4
83	4.9	7.5	7.3	16.2	24.5	20.3	16.5	18.8	0.7	0.5
84	0.4	1.9	0.7	4.4	9.3	5.0	2.3	2.4	*	*
85 & Above	*	0.1	*	0.4	1.5	0.2	0.1	0.2	-	*
Average	81.08	81.19	81.64	82.00	82.54	82.30	81.92	82.07	80.50	80.21
Tenderable 3/	70.0	84.9	76.5	88.1	57.6	53.1	89.7	90.6	86.8	85.5
SAMPLES CLASSED										
Week	74,746		6,458		15,446		30,154		34,556	
Season	758,413		1,506,023		935,931		1,048,991		456,096	

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 01, 2026

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	0.1	*	-	-	-	-	-	-	-	-
2.5 - 2.6	0.4	0.1	*	*	-	-	-	*	*	*
2.7 - 2.9	2.0	1.1	*	*	-	*	-	*	0.2	0.1
3.0 - 3.2	5.4	3.7	0.4	0.1	-	*	-	0.1	1.9	1.2
3.3 - 3.4	5.5	5.2	0.8	0.4	*	0.1	-	0.2	1.9	1.1
3.5 - 3.6	8.2	8.1	3.4	1.5	*	0.3	-	0.5	3.4	2.6
3.7 - 4.2	36.5	37.7	39.7	29.1	5.5	10.2	-	11.8	30.9	30.0
4.3 - 4.9	38.3	41.2	52.0	60.6	88.0	78.0	-	63.3	54.4	58.0
5.0 - 5.2	3.3	2.4	3.3	7.3	6.3	10.7	-	19.7	4.7	5.8
5.3 & Above	0.3	0.3	0.4	1.0	0.1	0.6	-	4.4	2.6	1.2
Average	4.09	4.12	4.30	4.43	4.61	4.62	-	4.68	4.34	4.38
Leaf										
1 - 2	52.2	69.5	11.9	15.4	1.9	5.8	-	12.8	35.9	43.7
3	38.0	25.3	54.3	58.1	47.1	48.4	-	49.1	32.8	34.8
4	8.1	4.3	29.0	23.4	42.8	37.2	-	30.3	21.4	14.7
5	1.3	0.7	4.6	2.9	7.6	7.7	-	6.8	7.9	5.3
6	0.3	0.1	0.3	0.2	0.6	0.8	-	1.0	1.7	1.3
7	0.1	*	*	*	*	0.1	-	-	0.3	0.2
8	*	*	-	*	-	-	-	-	*	*
Average	2.52	2.18	3.27	3.14	3.58	3.49	-	3.34	2.97	2.79
HVI Trash 1/										
00	*	*	-	-	-	*	-	-	*	*
01	19.4	34.6	1.2	1.7	*	0.5	-	1.6	17.8	17.0
02	41.9	41.1	15.4	20.0	3.5	7.2	-	14.1	21.4	32.6
03	22.3	15.2	28.2	31.6	19.5	21.0	-	24.3	17.5	20.0
04	9.2	5.3	24.4	23.6	28.1	26.1	-	23.3	15.2	12.0
05	3.9	2.1	15.5	12.7	22.6	20.3	-	16.3	10.9	7.3
06	1.7	0.9	8.2	6.0	14.9	12.3	-	9.6	7.1	4.6
07	0.7	0.4	4.0	2.6	7.3	6.6	-	5.3	4.5	2.8
08	0.4	0.2	1.8	1.1	2.8	3.2	-	2.7	2.7	1.7
09	0.2	0.1	0.8	0.5	0.9	1.5	-	1.4	1.5	1.0
10	0.1	0.1	0.3	0.2	0.3	0.7	-	0.8	0.7	0.5
11	0.1	*	0.1	0.1	0.1	0.3	-	0.4	0.4	0.3
12	0.1	*	0.1	*	*	0.1	-	0.2	0.2	0.1
13	*	*	*	*	*	0.1	-	0.1	0.1	0.1
14	*	*	*	*	*	*	-	*	*	*
15	*	*	*	*	-	*	-	-	*	*
16	*	*	*	*	-	-	-	-	-	*
17	*	*	*	*	-	-	-	-	*	*
18 & Above	*	*	*	*	-	-	-	-	*	*
Average	0.25	0.21	0.40	0.37	0.47	0.46	-	0.42	0.35	0.31
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	-	-	-	-
75	0.1	*	-	*	-	-	-	-	-	-
76	0.3	0.2	*	*	-	*	-	-	*	*
77	1.2	0.9	0.1	0.1	-	*	-	-	*	*
78	5.5	4.0	0.9	0.7	*	0.1	-	0.2	1.0	0.6
79	16.1	13.3	5.4	4.7	0.1	0.5	-	1.7	2.4	3.1
80	32.7	29.5	20.0	19.8	3.6	3.9	-	10.2	14.3	13.5
81	29.0	32.7	34.7	36.6	12.6	20.7	-	31.9	34.1	31.2
82	12.0	15.5	27.8	28.2	47.6	45.7	-	37.8	33.6	35.9
83	2.7	3.3	9.5	8.5	32.1	26.3	-	16.0	11.7	12.9
84	0.4	0.4	1.4	1.3	4.0	2.7	-	2.1	2.6	2.5
85 & Above	0.1	0.1	0.1	0.1	0.1	0.2	-	0.1	0.2	0.2
Average	80.76	80.96	81.63	81.62	82.66	82.47	-	82.08	81.88	81.93
Tenderable 3/	69.3	80.8	88.7	88.7	91.6	83.2	-	69.8	84.6	85.6
SAMPLES CLASSED										
Week	161,319		102,861		19,719		-		28,141	
Season		2,060,752		1,970,013		2,244,077		277,992		201,116

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE

For The Week Ending Jan 01, 2026

Color Grade	Leaf	VISALIA			Quality Designation	VISALIA	
		Week	Season			Week	Season
01	1	4.4	6.1		MIKE	-	-
	2	8.6	7.3		2.4 & Below	-	-
	3	0.5	0.2		2.5 - 2.6	-	-
	4	-	-		2.7 - 2.9	0.8	0.2
	5	-	-		3.0 - 3.2	1.9	1.7
	6	-	-		3.3 - 3.4	2.2	3.1
	7	-	-		3.5 - 3.6	8.6	9.0
Total -----		13.4	13.6		3.7 - 4.2	77.1	82.8
02	1	4.1	6.7		4.3 - 4.9	9.3	3.2
	2	29.3	35.3		5.0 - 5.2	-	-
	3	10.9	8.6		5.3 & Above	-	-
	4	0.4	0.2		Average	3.92	3.88
	5	*	*		ALL RANGE MIKE		
	6	-	-		2.4 & Below	-	-
	7	-	-		2.5	-	-
Total -----		44.6	50.8		2.6	-	-
03	1	0.4	0.5		2.7	-	*
	2	15.5	12.9		2.8	*	*
	3	19.1	16.1		2.9	0.8	0.1
	4	1.3	1.8		3.0	0.8	0.3
	5	*	*		3.1	0.8	0.6
	6	-	*		3.2	0.3	0.9
	7	-	-		3.3	0.7	1.1
Total -----		36.4	31.3		3.4	1.5	2.0
04	1	0.1	*		3.5	2.9	3.3
	2	1.5	0.6		3.6	5.7	5.8
	3	2.5	2.1		3.7	9.9	10.1
	4	0.6	0.9		3.8	12.3	15.7
	5	*	0.1		3.9	16.7	20.8
	6	-	*		4.0	15.6	19.1
	7	-	-		4.1	12.6	11.5
Total -----		4.7	3.7		4.2	10.0	5.6
05	1	-	*		4.3	6.5	2.1
	2	0.1	0.1		4.4	1.9	0.7
	3	0.1	0.2		4.5	0.6	0.3
	4	0.1	0.2		4.6	0.2	0.1
	5	*	*		4.7	0.1	*
	6	-	*		4.8	*	*
	7	-	-		4.9	*	*
Total -----		0.3	0.5		5.0	-	-
06	1	-	-		5.1	-	-
	2	*	*		5.2	-	-
	3	*	*		5.3 & Above	-	-
	4	*	*		Average	3.92	3.88
	5	*	*		STRENGTH 1/		
	6	*	*		36 & Below	2.4	3.1
	7	-	-		37	3.1	5.4
Total -----		0.1	*		38	5.0	4.0
07	1	-	-		39	1.9	1.7
	2	-	-		40	2.0	2.1
	3	0.1	*		41	4.5	6.2
	4	0.2	*		42	8.1	11.8
	5	0.1	*		43	12.4	17.4
	6	*	*		44	17.1	20.2
	7	-	-		45	14.8	15.8
Total -----		0.4	*		46	13.3	8.0
STAPLE					47	10.3	3.1
44 & Shorter		4.4	2.8		48 & Above	5.1	1.1
46		10.0	11.9		Average	44.07	43.26
48		42.9	46.2		UNIFORMITY		
50		40.8	37.2		83 & Below	4.3	1.4
52 & Longer		1.8	1.9		84	13.4	12.1
Average Staple		48.49	48.47		85	39.8	34.4
Average Length		1.41	1.41		86	36.7	46.1
EXTRANEIOUS MATTER					87	5.3	5.5
Bark		0.1	*		88 & Above	0.5	0.4
Grass		0.4	0.4		Average	85.71	85.88
Spindle Twist		0.6	0.1		Samples Classed		
Preparation		-	*		Week	26,824	
All Other		*	*		Season		302,116

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.