Weekly Quality of Cotton Classed by State: Week Ending - 1/1/2026

Agricultural Marketing Service
Cotton Market News

Volume 27, No.22 January 05, 2026

State	Week Gins	Week Tenderable (%)	Week Eligible (%)	Week Bales	Season Gins	Season Tenderable (%)	Season Eligible (%)	Season Bales
			UPLAND					
AL	11	81.2	71.5	9,587	21	90.4	78.3	514,480
AR	6	65.1	42.4	22,446	26	69.9	41.9	1,339,876
AZ	8	87.2	74.5	18,232	9	87.3	68.3	121,744
CA	6	76.3	64.0	5,353	10	83.2	69.7	54,060
FL	3	79.0	73.2	2,421	4	91.2	76.6	87,834
GA	50	89.8	76.7	90,858	53	88.4	73.8	1,547,964
KS	3	24.7	22.5	14,073	3	43.3	33.2	85,943
LA	-	-	-	-	14	71.5	47.6	223,278
MO	6	97.0	77.3	12,679	16	86.4	64.3	639,983
MS*	-	-	-	-	30	63.7	36.5	706,431
NC	16	93.4	83.6	11,704	26	90.7	78.5	627,921
NM	2	92.9	90.6	911	2	93.5	84.4	8,273
OK	10	85.1	69.8	26,130	10	93.7	81.6	299,825
SC	9	87.0	79.0	16,334	10	86.4	72.8	250,606
TN	-	-	-	-	17	82.3	63.4	340,307
TX	98	72.8	49.6	242,992	144	84.1	64.2	4,440,415
VA	3	90.5	81.9	2,116	4	96.4	90.8	170,464
United States	**232**	**77.5**	**59.2**	**475,871**	**399**	**82.5**	**63.3**	**11,459,404**
			AMERICAN PIMA					
AZ*	-			-	2			8,389
CA	7			21,507	10			250,400
NM*	-			-	-			-
TX	3			2,548	5			24,317
United States	13			26,824	18			302,116
United States all cotton	**241**			**502,695**	**408**			**11,761,520**

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

MP CN100

Source: USDA AMS Cotton and Tobacco Market News
Memphis, Tennessee | 901-384-3016 |cottonmn@ams.usda.gov
https://www.ams.usda.gov/market-news/cotton
https://mymarketnews.ams.usda.govcottonmn@ams.usda.gov

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 01, 2026

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	0.7	2.3	*	0.1	19.1	22.2	16.1	26.8	-	1.7	1.9	1.3
	3	0.7	1.3	*	0.1	1.5	5.1	0.2	10.7	*	0.5	1.7	0.9
	4	*	*	-	*	*	0.3	-	0.7	-	*	0.1	*
	5	-	*	-	-	-	*	-	*	-	-	*	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***1.4***	***3.7***	*******	***0.2***	***20.7***	***27.6***	***16.3***	***38.2***	*******	***2.2***	***3.8***	***2.3***
31	1 - 2	2.1	9.7	0.1	1.1	6.7	11.6	19.6	16.2	1.1	3.2	6.7	7.8
	3	15.6	29.0	4.9	9.1	4.1	11.6	15.9	12.4	13.1	12.7	21.2	21.6
	4	4.4	7.4	5.3	3.5	1.7	2.3	7.5	5.6	3.3	2.9	6.0	4.0
	5	0.1	0.5	0.1	0.1	0.1	0.2	0.4	1.1	0.1	0.1	0.4	0.2
	6	-	*	-	*	-	*	-	0.1	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***22.3***	***46.7***	***10.4***	***13.8***	***12.6***	***25.7***	***43.5***	***35.5***	***17.6***	***18.8***	***34.3***	***33.6***
41	1 - 2	1.7	3.2	0.5	0.8	2.7	2.1	6.8	3.7	0.4	2.9	3.8	5.5
	3	19.9	22.7	16.3	26.1	18.2	11.5	22.5	9.8	22.9	37.6	27.5	33.5
	4	18.6	15.8	44.1	35.4	18.9	11.0	5.6	3.7	30.2	28.7	16.2	16.7
	5	2.0	2.9	17.4	8.3	7.7	3.5	0.3	2.3	3.6	3.8	2.5	2.1
	6	*	0.2	1.0	0.7	1.0	0.4	-	0.5	*	0.2	0.1	0.1
	7	-	*	*	*	0.1	*	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***42.2***	***44.9***	***79.2***	***71.3***	***48.5***	***28.5***	***35.1***	***19.9***	***57.1***	***73.1***	***50.2***	***57.9***
51	1 - 2	1.6	0.2	-	*	*	0.1	0.9	0.2	-	*	0.2	0.2
	3	11.5	1.2	0.4	2.2	1.9	1.0	2.0	0.4	6.3	1.5	3.9	1.9
	4	11.1	1.1	2.4	4.8	5.4	2.3	0.1	0.1	14.0	2.0	4.4	1.9
	5	2.5	0.3	3.6	2.2	3.5	2.0	-	*	3.3	0.6	1.0	0.5
	6	0.1	*	0.8	0.4	1.4	0.8	-	*	0.4	0.1	0.1	*
	7	-	*	*	0.1	0.4	0.2	-	-	-	*	*	*
	8	-	*	-	-	*	*	-	-	-	-	-	*
Total	***----***	***26.8***	***2.8***	***7.2***	***9.8***	***12.7***	***6.5***	***3.0***	***0.7***	***24.0***	***4.2***	***9.6***	***4.4***
61	1 - 2	*	*	-	*	-	-	-	-	-	-	*	*
	3	0.5	*	-	*	-	-	-	-	-	-	*	*
	4	0.2	*	-	*	*	*	-	-	*	*	*	*
	5	0.2	*	-	*	*	*	-	-	-	*	*	*
	6	*	*	-	*	*	*	-	-	0.1	*	-	*
	7	-	-	-	-	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	*
Total	***----***	***0.9***	***0.1***	***-***	*******	*******	*******	***-***	***-***	***0.1***	*******	*******	*******
71	1 - 2	-	-	-	*	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	*	-	-	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***-***	***-***	***-***	*******	***-***	***-***	***-***	***-***	***-***	***-***	***-***	***-***
12 & 22	1 - 2	-	0.1	-	*	2.6	4.6	-	0.2	-	*	*	*
	3	*	*	-	*	0.6	2.2	-	0.4	-	*	0.1	*
	4	*	*	-	*	0.1	0.3	*	*	-	-	*	*
	5	-	-	-	*	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	*******	***0.1***	***-***	*******	***3.3***	***7.1***	*******	***0.7***	***-***	*******	***0.1***	***0.1***
32	1 - 2	-	0.1	-	*	*	0.2	-	0.4	-	*	*	*
	3	0.1	0.4	*	0.1	0.2	0.6	0.1	0.8	-	0.2	0.3	0.2
	4	0.1	0.1	0.1	0.1	0.3	0.4	*	0.8	-	*	0.2	0.1
	5	-	*	*	*	*	0.1	-	0.6	-	-	*	*
	6	-	*	-	*	-	*	-	0.1	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***0.2***	***0.6***	***0.1***	***0.2***	***0.5***	***1.3***	***0.1***	***2.7***	***-***	***0.3***	***0.5***	***0.4***
42	1 - 2	*	*	-	*	*	*	-	0.1	-	0.1	*	*
	3	0.2	0.4	*	1.0	0.3	0.5	0.2	0.7	*	0.7	0.3	0.6
	4	1.9	0.5	0.4	1.5	0.8	0.7	0.1	0.4	0.1	0.4	0.3	0.4
	5	0.7	0.1	1.3	0.6	0.2	0.4	-	0.4	-	*	0.1	0.1
	6	0.1	*	0.4	0.1	*	0.1	-	0.2	-	*	*	*
	7	-	*	*	*	-	*	-	-	-	*	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	***----***	***2.8***	***1.1***	***2.1***	***3.2***	***1.4***	***1.7***	***0.2***	***1.8***	***0.2***	***1.2***	***0.8***	***1.1***

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 01, 2026

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	-	*	-	*	0.1	*	-	-	*	*
	3	0.1	*	*	0.3	-	0.2	1.3	0.2	0.2	*	0.1	*
	4	1.4	0.1	0.1	0.6	0.1	0.3	0.2	*	0.6	*	0.1	0.1
	5	1.2	*	0.5	0.3	*	0.3	*	*	0.1	*	0.1	*
	6	0.1	*	0.3	0.1	*	0.2	-	-	-	*	*	*
	7	-	*	*	*	*	0.1	-	-	-	*	-	*
	8	-	-	-	-	*	*	-	-	-	-	-	*
Total	**----**	***2.8***	***0.1***	***0.9***	***1.3***	***0.1***	***1.0***	***1.6***	***0.2***	***0.9***	***0.1***	***0.4***	***0.2***
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	*	-	-	*	*	-	-	-	-
	4	*	*	-	*	-	*	-	*	-	-	*	*
	5	*	*	-	*	-	*	-	-	-	*	*	*
	6	*	*	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	*	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***0.1***	*****	***-***	*****	***-***	*****	*****	*****	***-***	*****	*****	*****
13 & 23	1 - 2	-	*	-	-	0.1	0.3	-	*	-	-	*	*
	3	-	*	-	-	*	0.1	-	*	-	-	*	*
	4	-	*	-	-	-	*	-	-	-	-	*	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***-***	*****	***-***	***-***	***0.1***	***0.4***	***-***	*****	***-***	***-***	*****	*****
33	1 - 2	-	*	-	-	-	*	-	*	-	-	*	*
	3	-	*	-	*	-	*	-	*	-	-	*	*
	4	-	*	*	*	*	*	-	*	-	-	*	*
	5	-	*	-	*	-	*	-	*	-	-	*	*
	6	-	*	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***-***	*****	*****	*****	*****	***0.1***	***-***	***0.1***	***-***	***-***	***0.1***	*****
43	1 - 2	-	-	-	*	-	-	-	*	-	-	*	*
	3	-	*	*	*	-	*	-	0.1	0.1	*	*	*
	4	0.1	*	-	*	-	*	*	0.1	-	*	*	*
	5	-	*	*	*	-	*	-	*	-	-	*	*
	6	-	*	-	*	-	*	-	*	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***0.1***	*****	*****	***0.1***	***-***	***0.1***	*****	***0.2***	***0.1***	*****	***0.1***	*****
53	1 - 2	-	*	-	-	-	-	-	-	-	-	-	-
	3	*	*	-	*	-	-	-	*	-	*	*	*
	4	0.2	*	-	*	*	*	-	*	-	-	*	*
	5	0.1	*	-	*	*	*	0.1	*	*	*	*	*
	6	-	*	-	*	-	*	-	-	-	-	*	*
	7	-	-	-	*	-	*	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***0.3***	*****	***-***	*****	*****	***0.1***	***0.1***	*****	*****	*****	***0.1***	*****
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***-***	***-***	***-***	***-***	***-***	***-***	***-***	***-***	***-***	***-***	***-***	***-***
24 - 54	1 - 8	-	*	-	*	*	*	-	*	-	-	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	*
31		-	*	-	*	-	*	-	-	-	*	*	*
32		0.1	*	*	*	-	*	-	-	-	*	0.1	0.1
33		1.1	0.5	0.1	0.1	*	*	-	*	-	0.2	1.5	0.8
34		5.1	3.2	1.2	0.3	0.2	0.5	-	0.4	*	2.3	7.1	4.6
35		17.9	11.5	7.9	2.6	3.6	2.8	4.2	2.9	*	12.6	16.8	15.8
36		28.8	24.1	14.5	13.8	12.8	12.4	20.9	16.4	0.5	28.9	27.7	31.3
37		34.2	41.9	36.6	50.8	46.7	45.6	41.8	39.7	25.5	35.2	33.1	35.0
38		9.7	14.9	28.4	26.9	25.2	28.6	22.2	24.2	38.1	15.6	10.2	9.7
39		2.7	3.2	10.4	5.1	9.1	8.7	10.7	14.5	33.7	4.5	3.0	2.4
40 & Longer		0.5	0.5	0.9	0.5	2.4	1.5	0.1	1.8	2.1	0.7	0.4	0.3
Average Staple		***36.32***	***36.64***	***37.18***	***37.18***	***37.30***	***37.31***	***37.14***	***37.36***	***38.11***	***36.65***	***36.28***	***36.35***
Average Length		***1.13***	***1.14***	***1.16***	***1.16***	***1.16***	***1.17***	***1.16***	***1.17***	***1.19***	***1.14***	***1.13***	***1.13***

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 01, 2026

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	0.6	6.7	-	4.5	-	*	-	2.0	0.3	0.4	30.2	48.7
	3	3.4	6.7	-	2.6	-	*	-	1.8	1.3	0.3	13.3	8.8
	4	1.7	1.2	-	*	-	*	-	*	*	*	3.7	0.5
	5	0.2	0.1	-	-	-	-	-	*	-	*	0.2	*
	6	*	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***6.0***	***14.7***	***-***	***7.1***	***-***	*******	***-***	***3.8***	***1.6***	***0.8***	***47.4***	***57.9***
31	1 - 2	0.1	1.5	-	9.2	0.7	1.4	-	3.4	2.2	5.6	3.0	10.7
	3	5.6	10.4	-	36.6	8.4	8.8	-	20.3	17.0	20.0	22.0	18.7
	4	10.1	12.8	-	12.3	0.4	1.8	-	8.6	7.1	5.8	18.4	5.4
	5	4.3	3.7	-	0.8	-	*	-	0.6	0.2	0.3	2.7	0.5
	6	0.8	0.5	-	*	-	*	-	*	-	*	-	-
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	**----**	***21.0***	***28.9***	***-***	***58.9***	***9.5***	***12.1***	***-***	***32.9***	***26.5***	***31.7***	***46.1***	***35.2***
41	1 - 2	-	*	-	0.5	1.2	2.3	-	0.9	0.9	3.1	-	*
	3	0.5	0.7	-	10.1	37.1	37.9	-	18.8	29.3	29.9	0.1	0.8
	4	4.0	4.0	-	16.2	27.1	27.2	-	26.1	31.3	24.9	0.5	1.1
	5	11.2	6.5	-	4.9	3.1	3.3	-	7.3	5.8	4.5	2.1	1.2
	6	8.2	3.6	-	0.3	0.3	0.1	-	0.6	0.7	0.3	1.9	0.7
	7	1.8	0.7	-	-	*	*	-	*	0.1	*	0.3	0.1
	8	0.2	0.1	-	-	-	-	-	-	-	*	-	-
Total	**----**	***25.9***	***15.6***	***-***	***32.0***	***68.9***	***70.8***	***-***	***53.6***	***68.0***	***62.8***	***4.9***	***3.9***
51	1 - 2	-	-	-	*	0.1	0.1	-	*	-	0.1	-	-
	3	-	-	-	*	5.8	4.3	-	1.1	1.2	0.8	-	-
	4	*	*	-	0.4	12.3	6.0	-	3.3	1.4	1.7	-	-
	5	0.4	0.1	-	0.3	1.7	1.4	-	1.5	0.5	0.8	-	*
	6	1.8	0.4	-	0.1	0.1	0.1	-	0.2	*	0.2	-	*
	7	1.8	0.5	-	-	-	*	-	*	-	*	-	-
	8	0.7	0.2	-	-	-	-	-	-	-	*	-	-
Total	**----**	***4.8***	***1.1***	***-***	***0.7***	***19.9***	***11.9***	***-***	***6.1***	***3.1***	***3.6***	***-***	*******
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	*	-	*	-	-
	4	-	-	-	*	*	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***-***	***-***	***-***	*******	*******	*******	***-***	*******	***-***	*******	***-***	***-***
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***-***	***-***	***-***	***-***	***-***	*******	***-***	***-***	***-***	*******	***-***	***-***
12 & 22	1 - 2	0.1	1.8	-	0.1	-	-	-	*	-	*	-	0.2
	3	5.1	4.2	-	*	-	*	-	*	*	*	-	*
	4	3.4	1.9	-	*	-	-	-	*	*	*	-	*
	5	0.5	0.2	-	*	-	-	-	-	-	-	-	-
	6	*	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***9.1***	***8.1***	***-***	***0.1***	***-***	*******	***-***	*******	*******	*******	***-***	***0.3***
32	1 - 2	*	0.1	-	0.1	-	*	-	*	-	*	-	0.8
	3	2.0	2.6	-	0.3	*	0.1	-	0.2	0.1	0.1	0.1	0.2
	4	6.2	5.2	-	0.2	-	*	-	0.1	0.1	0.1	0.4	0.5
	5	3.8	3.0	-	*	-	*	-	*	0.1	*	0.4	0.2
	6	0.5	0.6	-	*	-	-	-	*	-	-	-	*
	7	*	0.1	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	**----**	***12.5***	***11.6***	***-***	***0.5***	*******	***0.2***	***-***	***0.3***	***0.3***	***0.3***	***1.0***	***1.7***
42	1 - 2	-	*	-	*	-	0.1	-	*	-	*	-	-
	3	0.1	0.9	-	0.1	0.4	1.4	-	0.6	0.1	0.3	-	*
	4	1.8	3.4	-	0.4	0.6	1.4	-	1.2	0.2	0.3	-	0.1
	5	4.6	5.2	-	0.1	0.1	0.4	-	0.5	0.1	0.1	0.2	*
	6	3.5	3.7	-	*	-	0.1	-	0.1	-	*	0.3	*
	7	1.4	1.2	-	-	-	*	-	*	-	*	-	-
	8	0.4	0.2	-	-	-	-	-	-	-	*	-	-
Total	**----**	***11.8***	***14.6***	***-***	***0.6***	***1.1***	***3.4***	***-***	***2.4***	***0.3***	***0.7***	***0.5***	***0.2***

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 01, 2026

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	-	-	*	-	*	-	*	-	-
	3	-	-	-	*	0.1	0.5	-	0.1	-	*	-	-
	4	*	*	-	*	0.3	0.7	-	0.2	*	*	-	-
	5	*	*	-	*	0.1	0.3	-	0.3	-	*	-	-
	6	0.3	0.3	-	*	-	*	-	0.1	-	*	-	-
	7	0.6	0.5	-	-	-	*	-	*	-	*	-	-
	8	0.9	0.3	-	-	-	-	-	-	-	*	-	-
Total	**----**	***1.9***	***1.0***	***-***	*******	***0.4***	***1.6***	***-***	***0.7***	*******	***0.1***	***-***	***-***
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	-	*	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	**----**	***-***	*******	***-***	***-***	*******	*******	***-***	*******	***-***	*******	***-***	***-***
13 & 23	1 - 2	*	0.2	-	-	-	-	-	-	-	-	-	-
	3	1.1	0.8	-	-	-	-	-	-	-	*	-	-
	4	1.2	0.5	-	-	-	-	-	-	-	*	-	-
	5	0.1	0.1	-	-	-	-	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	**----**	***2.4***	***1.6***	***-***	***-***	***-***	***-***	***-***	***-***	***-***	*******	***-***	***-***
33	1 - 2	-	*	-	-	-	*	-	*	-	*	-	-
	3	0.1	0.1	-	*	-	*	-	*	-	*	-	0.1
	4	0.6	0.3	-	*	*	*	-	*	*	*	-	0.3
	5	0.4	0.3	-	*	-	-	-	-	-	*	-	0.2
	6	0.1	0.1	-	-	-	-	-	-	-	*	-	*
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	**----**	***1.2***	***0.8***	***-***	*******	*******	*******	***-***	*******	*******	*******	***-***	***0.7***
43	1 - 2	-	-	-	*	-	*	-	-	-	*	-	-
	3	*	0.1	-	*	*	*	-	*	*	*	-	-
	4	0.3	0.3	-	*	*	*	-	*	0.1	*	-	-
	5	0.9	0.5	-	*	*	*	-	*	*	*	-	*
	6	0.8	0.5	-	-	-	*	-	*	-	*	-	*
	7	0.6	0.2	-	-	-	-	-	-	-	*	-	-
	8	0.2	0.1	-	-	-	-	-	-	-	*	-	-
Total	**----**	***2.8***	***1.7***	***-***	*******	*******	***0.1***	***-***	*******	***0.1***	*******	***-***	*******
53	1 - 2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	*	-	-	-	*	-	*	-	*	-	-
	4	-	*	-	-	*	*	-	*	-	*	-	-
	5	-	*	-	-	*	*	-	*	*	*	-	-
	6	*	*	-	-	-	*	-	*	-	*	-	-
	7	0.2	0.1	-	-	-	-	-	*	-	*	-	-
	8	0.3	0.1	-	-	-	-	-	-	-	*	-	-
Total	**----**	***0.5***	***0.2***	***-***	***-***	*******	*******	***-***	*******	*******	*******	***-***	***-***
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	**----**	***-***	*******	***-***	***-***	***-***	***-***	***-***	*******	***-***	***-***	***-***	***-***
24 - 54	1 - 8	0.1	0.1	-	-	-	*	-	-	*	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	-	-	*	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		-	*	-	-	-	-	-	*	-	*	-	-
32		-	*	-	-	-	*	-	*	-	*	-	-
33		0.1	0.2	-	0.1	-	*	-	0.2	0.2	0.1	-	-
34		1.0	1.1	-	1.1	-	0.2	-	2.1	2.4	1.3	0.2	2.6
35		5.3	4.0	-	10.0	*	1.8	-	11.5	14.0	7.8	19.8	10.8
36		14.2	10.7	-	26.9	2.7	10.0	-	27.7	26.0	23.8	29.9	12.9
37		29.1	26.9	-	42.1	41.3	48.6	-	36.4	38.3	49.5	26.5	29.7
38		33.4	36.1	-	15.0	48.0	33.9	-	15.0	17.3	14.5	19.8	35.8
39		15.3	18.4	-	4.4	7.9	5.1	-	5.4	1.7	2.8	3.8	7.1
40 & Longer		1.6	2.5	-	0.4	*	0.4	-	1.5	0.1	0.3	0.1	1.1
Average Staple		***37.41***	***37.57***	***-***	***36.75***	***37.61***	***37.31***	***-***	***36.72***	***36.59***	***36.77***	***36.58***	***37.11***
Average Length		***1.17***	***1.17***	***-***	***1.15***	***1.18***	***1.17***	***-***	***1.15***	***1.14***	***1.15***	***1.14***	***1.16***

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 01, 2026

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	38.1	47.2	*	0.3	-	0.4	39.2	44.8	0.8	0.9
	3	7.1	8.0	0.2	0.5	-	0.1	14.6	13.6	0.8	1.3
	4	0.3	0.3	*	*	-	*	1.1	1.0	-	0.1
	5	*	*	-	-	-	*	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	***----***	***45.5***	***55.4***	***0.3***	***0.8***	***-***	***0.5***	***54.9***	***59.3***	***1.6***	***2.3***
31	1 - 2	17.1	12.5	0.6	2.3	-	6.9	5.0	3.3	6.7	8.8
	3	16.4	17.9	10.6	15.1	-	14.5	9.5	10.4	16.0	38.7
	4	4.2	3.8	9.8	5.1	-	3.2	3.9	4.4	2.7	8.3
	5	0.6	0.3	0.9	0.2	-	0.2	0.6	0.5	0.4	0.5
	6	*	*	*	*	-	*	0.1	*	0.2	*
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	***----***	***38.2***	***34.6***	***22.0***	***22.8***	***-***	***24.8***	***19.0***	***18.6***	***26.1***	***56.2***
41	1 - 2	0.8	0.3	0.8	2.0	-	7.7	0.1	0.2	6.0	1.7
	3	1.7	1.2	24.4	32.4	-	35.8	0.3	1.9	27.7	21.3
	4	1.3	1.1	38.8	31.3	-	14.2	0.5	1.9	26.7	15.5
	5	1.0	0.5	6.9	4.5	-	1.8	0.4	0.5	9.6	2.6
	6	0.2	0.1	0.3	0.1	-	0.1	0.1	0.1	2.0	0.1
	7	*	*	-	*	-	*	*	*	*	*
	8	-	-	-	-	-	-	*	*	-	-
Total	***----***	***5.0***	***3.1***	***71.1***	***70.3***	***-***	***59.6***	***1.4***	***4.6***	***72.1***	***41.2***
51	1 - 2	-	*	*	0.1	-	0.2	*	*	-	*
	3	*	*	1.9	1.8	-	2.4	*	0.1	-	*
	4	-	*	3.3	2.5	-	2.2	*	0.1	0.1	0.1
	5	*	*	0.9	0.7	-	0.5	*	*	0.1	*
	6	0.1	*	0.1	0.1	-	*	*	*	-	*
	7	0.1	*	*	*	-	*	*	*	-	*
	8	*	*	-	-	-	-	-	*	-	-
Total	***----***	***0.2***	*******	***6.2***	***5.1***	***-***	***5.3***	*******	***0.3***	***0.3***	***0.1***
61	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	*	-	*	-	*	-	-
	4	-	-	*	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	***----***	***-***	***-***	*******	*******	***-***	*******	***-***	*******	***-***	***-***
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	***----***	***-***	***-***	***-***	***-***	***-***	***-***	***-***	*******	***-***	***-***
12 & 22	1 - 2	3.2	2.4	-	-	-	*	7.5	6.6	-	-
	3	1.8	1.1	-	*	-	*	6.1	3.6	-	*
	4	0.1	0.1	-	-	-	*	0.8	0.6	-	*
	5	-	*	-	-	-	-	0.1	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	***----***	***5.0***	***3.6***	***-***	*******	***-***	*******	***14.5***	***10.8***	***-***	*******
32	1 - 2	0.2	0.3	-	*	-	0.2	0.7	0.5	-	*
	3	1.8	1.1	*	0.1	-	0.5	2.3	1.5	-	*
	4	1.0	0.5	*	0.1	-	0.1	1.6	1.2	-	*
	5	0.2	0.1	*	*	-	*	0.4	0.3	-	*
	6	*	*	*	*	-	-	0.1	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	***----***	***3.2***	***2.0***	***0.1***	***0.1***	***-***	***0.8***	***5.0***	***3.5***	***-***	***0.1***
42	1 - 2	*	*	-	*	-	0.9	*	*	-	*
	3	0.2	0.1	*	0.2	-	5.0	0.1	0.3	-	*
	4	0.4	0.2	0.2	0.4	-	1.5	0.3	0.5	-	*
	5	0.4	0.1	0.1	0.1	-	0.1	0.3	0.3	-	*
	6	0.1	*	*	*	-	*	0.2	0.1	-	*
	7	*	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	***----***	***1.1***	***0.4***	***0.3***	***0.7***	***-***	***7.5***	***1.0***	***1.2***	***-***	***0.1***

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 01, 2026

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	*	*	*	-	-
	3	-	-	-	*	-	0.7	-	*	-	-
	4	-	*	*	0.1	-	0.5	*	*	-	*
	5	*	*	-	*	-	0.1	*	*	-	*
	6	*	*	-	*	-	*	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	**----**	*****	*****	*****	***0.1***	**-**	***1.3***	*****	***0.1***	**-**	*****
62	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	-	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
Total	**----**	**-**	*****	**-**	**-**	**-**	*****	**-**	*****	**-**	**-**
13 & 23	1 - 2	0.1	0.1	-	-	-	-	1.3	0.4	-	-
	3	0.2	0.1	-	-	-	-	1.2	0.3	-	*
	4	*	*	-	-	-	-	0.2	0.1	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	**----**	***0.3***	***0.2***	**-**	**-**	**-**	**-**	***2.7***	***0.8***	**-**	*****
33	1 - 2	0.1	0.1	-	-	-	*	0.2	0.1	-	-
	3	0.6	0.3	-	*	-	*	0.6	0.2	-	*
	4	0.5	0.1	-	*	-	*	0.3	0.1	-	*
	5	*	*	-	*	-	-	0.1	*	-	*
	6	*	*	-	-	-	-	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	**----**	***1.2***	***0.5***	**-**	*****	**-**	*****	***1.2***	***0.5***	**-**	*****
43	1 - 2	-	*	-	*	-	*	*	*	-	-
	3	*	*	*	*	-	*	*	*	-	*
	4	*	*	0.1	*	-	*	*	*	-	*
	5	*	*	*	*	-	*	*	*	-	*
	6	*	*	-	-	-	*	*	*	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	**----**	***0.1***	***0.1***	***0.1***	*****	**-**	*****	***0.1***	***0.1***	**-**	*****
53	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	*	-	*	-	*	-	*	-	-
	4	-	*	-	*	-	*	-	*	-	-
	5	-	*	-	*	-	*	-	*	-	-
	6	-	*	-	-	-	-	*	*	-	-
	7	-	*	-	*	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	**----**	**-**	*****	**-**	*****	**-**	*****	*****	*****	**-**	**-**
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	**----**	**-**	**-**	**-**	**-**	**-**	**-**	**-**	*****	**-**	**-**
24 - 54	1 - 8	0.1	0.1	-	*	-	-	0.1	0.1	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	*	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	*	*	-	-
30		-	-	-	-	-	-	*	*	-	-
31		-	*	-	-	-	-	*	0.1	-	-
32		-	*	-	*	-	*	0.5	0.5	-	*
33		*	0.3	0.5	0.1	-	0.1	2.5	2.4	0.6	*
34		1.5	1.9	4.4	1.5	-	2.6	9.7	7.3	5.3	0.6
35		6.7	6.5	14.0	9.2	-	9.5	21.0	14.1	15.1	5.5
36		19.0	12.9	33.9	33.8	-	30.9	27.1	21.5	27.7	22.6
37		31.6	26.2	37.6	42.2	-	44.3	26.4	33.4	43.1	55.5
38		15.4	19.6	8.5	10.1	-	11.3	8.7	15.0	7.7	13.0
39		15.6	19.5	1.0	2.6	-	1.3	2.4	4.6	0.4	2.6
40 & Longer		10.2	13.1	0.1	0.4	-	0.1	1.6	1.1	-	0.1
Average Staple		***37.41***	***37.67***	***36.33***	***36.59***	**-**	***36.56***	***36.10***	***36.44***	***36.32***	***36.83***
Average Length		***1.17***	***1.18***	***1.13***	***1.14***	**-**	***1.14***	***1.13***	***1.14***	***1.13***	***1.15***

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 01, 2026

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	4.6	0.4	*	*	*	0.1	0.8	0.1	15.5	1.2	3.1	1.0
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.3	0.1	*	0.1	-	0.1	1.2	1.1	0.2	0.1	0.2	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	-	-	-	-	-	-	*	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.8	0.1	0.4	1.0	-	*	-	-	4.0	0.3	0.6	0.3
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	0.1	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	-	-	-	-	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	*	*	-	*	*	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/												
22 & Below	-	*	-	-	-	-	-	-	-	-	-	-
23	-	-	-	*	-	-	-	-	-	-	*	*
24	-	*	-	*	*	*	-	*	-	-	*	*
25	-	*	-	*	0.1	*	*	*	-	*	0.1	0.1
26	0.2	0.1	*	*	0.3	0.3	-	0.3	*	*	1.0	0.5
27	3.5	1.2	0.1	0.2	4.4	1.9	0.7	1.4	-	0.4	5.2	2.9
28	17.5	7.3	1.4	1.9	11.7	7.1	11.3	7.0	0.9	3.2	15.8	10.3
29	24.0	21.5	11.1	11.7	14.1	13.4	18.3	12.6	6.2	13.1	23.0	20.8
30	21.1	29.6	27.6	34.5	18.8	20.7	14.0	17.1	45.0	27.1	24.5	25.4
31	19.7	22.0	25.3	33.5	21.0	21.6	19.9	13.5	34.9	27.0	15.9	19.9
32	8.8	11.3	19.2	13.3	14.3	15.3	6.3	5.5	7.7	16.7	8.7	11.5
33	3.8	4.7	9.1	3.7	8.8	9.7	5.8	5.4	3.2	7.5	3.9	5.5
34	0.8	1.7	4.1	0.9	2.3	6.3	8.6	10.4	1.5	3.9	1.6	2.2
35	0.2	0.4	1.8	0.2	2.2	2.4	5.0	14.0	0.5	0.9	0.2	0.8
36	0.1	0.1	0.2	*	1.6	0.9	7.3	9.2	-	0.1	*	0.2
37	*	*	0.1	*	0.3	0.4	2.3	2.9	*	*	*	0.1
38	-	*	*	*	0.1	*	0.4	0.3	-	-	-	*
39	-	-	*	*	*	*	*	0.1	-	-	-	*
40 & Above	-	-	-	-	*	*	*	0.1	-	-	-	-
Average	***30.28***	***30.73***	***31.49***	***31.05***	***31.02***	***31.37***	***31.74***	***32.45***	***31.09***	***31.28***	***30.24***	***30.67***
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	-	*	-	-	-	-	-	-	-	-	-	-
2.6	-	*	-	-	*	*	-	-	-	-	*	*
2.7	-	*	-	-	*	*	-	*	-	-	*	*
2.8	-	*	-	*	0.1	*	-	-	-	-	-	*
2.9	-	*	-	-	0.2	*	-	*	-	-	*	*
3.0	-	*	-	*	0.1	*	-	0.1	-	-	*	*
3.1	*	*	-	*	0.3	*	-	0.4	-	*	0.1	*
3.2	0.4	*	-	*	0.5	0.1	-	0.2	-	0.1	0.3	0.1
3.3	0.3	0.1	-	*	0.5	0.1	-	0.2	-	0.1	0.4	0.1
3.4	0.3	0.4	*	*	0.9	0.2	*	0.3	-	0.1	0.4	0.2
3.5	1.1	0.7	-	*	1.0	0.3	*	0.8	-	0.5	1.2	0.5
3.6	2.1	1.1	*	0.1	0.9	0.4	0.3	1.5	-	0.7	2.2	1.0
3.7	2.0	1.9	*	0.1	1.5	1.3	-	2.1	-	1.2	2.9	1.6
3.8	2.8	2.9	*	0.1	1.7	1.7	3.7	4.9	-	1.4	3.6	2.5
3.9	4.9	4.4	0.1	0.3	4.5	2.9	5.9	6.7	-	2.1	5.9	3.7
4.0	6.9	5.8	0.1	0.6	4.6	4.2	8.5	7.3	0.1	3.5	7.6	5.2
4.1	6.9	7.9	0.3	1.0	6.1	6.2	11.3	7.8	0.5	5.8	9.7	7.1
4.2	9.8	9.8	0.6	1.7	7.3	7.8	9.8	9.8	1.9	7.2	11.6	8.8
4.3	15.7	10.8	1.9	3.0	8.6	8.6	5.7	8.2	11.0	9.9	11.5	9.8
4.4	10.6	10.6	5.8	4.9	10.2	10.1	4.8	7.0	28.9	12.6	9.7	10.0
4.5	7.2	10.2	10.0	7.6	15.8	13.3	5.2	6.7	33.0	13.2	6.9	9.9
4.6	12.1	9.0	12.9	11.6	13.2	13.3	5.6	6.8	17.0	10.6	6.9	9.5
4.7	5.3	7.3	13.0	14.6	9.8	10.1	6.3	7.8	2.9	11.8	6.6	8.7
4.8	2.8	5.8	11.9	15.6	4.1	7.6	7.8	6.1	2.1	8.3	5.1	7.1
4.9	2.3	4.4	12.0	13.8	3.1	5.0	4.2	4.8	2.6	5.2	3.5	5.5
5.0	2.3	2.9	13.4	11.0	1.6	3.5	2.9	3.3	*	3.3	1.9	3.9
5.1	1.8	1.9	10.5	7.1	0.7	1.2	7.1	3.3	*	1.7	0.9	2.5
5.2	1.2	1.1	5.1	4.1	1.3	0.8	2.4	1.6	-	0.5	0.5	1.3
5.3	0.6	0.7	2.0	1.9	0.3	0.4	3.2	1.2	-	0.1	0.2	0.6
5.4	0.1	0.3	0.4	0.6	0.5	0.2	4.0	0.8	-	0.2	0.1	0.2
5.5 & Above	*	0.2	*	0.2	0.8	0.3	1.2	0.3	-	0.1	*	0.1
Average	***4.34***	***4.39***	***4.79***	***4.76***	***4.39***	***4.47***	***4.51***	***4.38***	***4.48***	***4.47***	***4.29***	***4.44***

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 01, 2026

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	52.2	26.2	-	0.1	-	*	-	*	1.8	1.5	3.5	0.4
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	-	*	-	*	-	*	-	*	1.2	0.7
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	-	-	*	-	*	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	0.1	-	0.4	-	0.2	-	0.3	1.5	0.4	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	-	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	-	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/												
22 & Below	-	*	-	-	-	*	-	-	-	-	-	-
23	*	*	-	-	-	*	-	-	-	-	-	-
24	0.1	*	-	-	-	*	-	*	*	*	-	-
25	0.3	0.1	-	*	-	*	-	*	0.3	*	-	*
26	1.0	0.3	-	*	*	*	-	0.1	0.8	0.3	-	0.2
27	2.0	0.7	-	0.5	*	0.1	-	1.0	4.4	2.0	5.3	2.1
28	3.3	1.5	-	4.4	0.2	0.6	-	4.8	13.1	10.6	7.1	7.6
29	4.9	3.1	-	19.0	8.1	7.4	-	15.6	22.9	28.1	10.6	22.0
30	7.6	7.2	-	33.2	45.1	36.0	-	26.9	27.4	31.8	25.2	30.0
31	18.0	16.2	-	21.1	38.6	36.7	-	26.3	18.1	17.6	13.3	18.1
32	29.1	24.3	-	11.7	5.8	13.4	-	16.1	9.1	7.0	23.7	13.1
33	22.9	23.5	-	5.1	2.0	4.6	-	6.5	2.8	2.1	14.7	4.9
34	8.3	15.4	-	2.9	0.2	1.0	-	2.3	1.0	0.4	-	1.8
35	2.2	6.4	-	1.8	*	0.1	-	0.4	0.2	0.1	-	0.1
36	0.2	1.1	-	0.2	-	*	-	*	*	*	-	-
37	*	0.2	-	*	-	*	-	*	-	-	-	*
38	*	0.1	-	*	-	*	-	*	-	-	-	-
39	*	*	-	-	-	-	-	-	-	-	-	-
40 & Above	-	*	-	-	-	-	-	-	-	-	-	-
Average	***32.12***	***32.73***	***-***	***30.97***	***30.93***	***31.18***	***-***	***31.06***	***30.26***	***30.28***	***31.09***	***30.67***
Mike												
2.4 & Below	0.1	0.1	-	-	-	-	-	-	-	-	-	-
2.5	0.9	0.5	-	-	-	-	-	-	-	*	-	-
2.6	1.3	0.8	-	*	-	-	-	-	-	-	-	-
2.7	1.8	1.3	-	*	-	-	-	-	-	*	-	-
2.8	2.2	2.0	-	-	-	-	-	-	-	*	-	*
2.9	2.4	2.3	-	*	-	-	-	-	*	*	-	0.2
3.0	2.9	2.5	-	*	-	-	-	-	*	*	-	0.2
3.1	3.2	3.0	-	*	-	*	-	-	0.1	*	-	*
3.2	5.6	3.5	-	*	-	*	-	*	0.1	0.1	-	0.7
3.3	5.4	4.2	-	*	-	*	-	*	0.2	0.2	0.1	0.6
3.4	6.5	5.1	-	0.1	-	*	-	*	0.5	0.3	0.3	0.3
3.5	4.8	5.6	-	0.1	*	*	-	0.1	1.0	0.5	-	1.0
3.6	6.0	6.4	-	0.1	-	0.1	-	0.1	1.3	0.9	-	1.1
3.7	6.7	6.7	-	0.2	0.1	0.1	-	0.2	1.8	1.5	1.3	3.7
3.8	7.1	6.6	-	0.3	0.1	0.3	-	0.3	2.6	2.3	2.2	6.2
3.9	6.4	6.5	-	0.6	0.2	0.5	-	0.4	3.2	3.4	5.5	9.5
4.0	7.4	7.0	-	1.3	1.4	1.2	-	0.8	5.4	4.8	6.0	8.4
4.1	7.3	7.7	-	2.2	2.7	2.2	-	1.3	7.2	6.9	10.3	8.2
4.2	4.7	6.1	-	3.4	3.4	4.0	-	2.0	11.5	9.2	13.1	8.4
4.3	4.7	6.3	-	4.9	7.2	6.5	-	3.0	15.2	11.6	15.3	11.0
4.4	5.6	5.5	-	6.3	12.5	9.6	-	4.5	15.9	12.2	19.0	9.2
4.5	3.6	3.9	-	8.2	16.6	12.9	-	6.2	13.1	11.3	10.1	9.6
4.6	1.5	2.4	-	9.7	13.7	15.2	-	8.7	7.9	10.2	5.4	7.2
4.7	0.5	1.6	-	11.2	22.0	15.9	-	11.2	4.8	8.6	7.8	6.1
4.8	0.3	1.4	-	12.6	15.2	13.6	-	13.6	4.0	6.1	2.6	3.9
4.9	0.6	0.7	-	11.7	3.8	8.9	-	14.6	3.1	4.2	1.0	2.9
5.0	0.5	0.3	-	9.6	1.1	5.0	-	13.3	1.0	2.8	-	1.2
5.1	0.1	*	-	7.7	0.1	2.4	-	9.9	*	1.5	-	0.2
5.2	*	*	-	4.4	*	0.9	-	5.7	*	0.8	-	0.1
5.3	-	-	-	2.6	-	0.3	-	2.6	-	0.3	-	*
5.4	-	-	-	1.3	-	0.1	-	1.0	-	0.1	-	-
5.5 & Above	-	-	-	1.4	-	*	-	0.4	-	*	-	-
Average	***3.72***	***3.81***	***-***	***4.74***	***4.57***	***4.62***	***-***	***4.80***	***4.33***	***4.41***	***4.31***	***4.24***

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 01, 2026

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	5.8	1.7	5.9	3.2	-	*	12.7	3.3	3.4	1.2
Bark - Level 2	-	*	-	-	-	-	-	*	-	-
Grass - Level 1	-	0.1	*	0.1	-	*	0.1	0.2	-	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	-	-	-	*	-	-	*	*	-	*
Prep - Level 2	-	*	-	-	-	-	*	*	-	-
Seed Coat - Level 1	-	*	4.3	1.6	-	*	0.2	0.2	3.2	0.6
Seed Coat - Level 2	-	-	-	-	-	-	-	*	-	-
Oil - Level 1	-	-	-	-	-	-	*	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	*	-	-
Other - Level 1	-	*	-	-	-	-	*	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	-	-	-	-	-	-	*	*	-	-
23	-	*	-	-	-	-	*	*	-	-
24	-	*	*	*	-	*	0.1	0.1	0.1	*
25	*	*	0.1	*	-	*	0.4	0.2	0.9	*
26	0.2	0.1	0.7	0.3	-	*	1.1	0.7	4.4	1.0
27	0.9	0.7	5.2	2.0	-	0.5	3.5	2.5	16.6	5.9
28	2.6	3.2	16.7	11.9	-	3.8	9.3	7.2	21.0	18.9
29	7.9	8.8	28.4	35.3	-	21.0	15.9	15.2	25.9	32.3
30	19.7	14.5	27.7	31.0	-	38.7	21.1	20.7	20.7	25.9
31	26.1	17.8	15.2	13.4	-	24.7	19.7	18.8	7.3	11.2
32	18.7	16.4	4.7	4.7	-	8.2	13.6	13.7	1.9	3.7
33	14.4	15.7	1.1	1.2	-	2.4	7.9	9.9	0.9	0.8
34	6.6	12.2	0.1	0.2	-	0.7	4.0	6.6	0.2	0.2
35	2.3	6.7	*	*	-	0.1	1.9	2.9	0.1	*
36	0.4	2.4	-	*	-	*	0.8	1.0	-	*
37	0.1	1.1	-	*	-	*	0.4	0.3	-	-
38	*	0.2	-	-	-	-	0.2	0.1	-	-
39	*	*	-	-	-	-	*	*	-	-
40 & Above	-	*	-	-	-	-	*	*	-	-
Average	***31.77***	***32.31***	***29.92***	***30.06***	***-***	***30.66***	***30.98***	***31.30***	***29.19***	***29.75***
Mike										
2.4 & Below	*	*	-	-	-	-	*	*	-	-
2.5	*	*	-	-	-	-	0.1	*	-	-
2.6	*	*	-	-	-	-	0.2	0.1	-	-
2.7	*	*	-	-	-	*	0.3	0.1	-	*
2.8	*	*	-	*	-	*	0.5	0.2	1.6	*
2.9	0.1	0.1	-	*	-	*	0.7	0.3	0.5	*
3.0	0.2	0.1	-	*	-	*	1.2	0.5	0.1	0.1
3.1	0.4	0.2	-	*	-	*	1.5	0.7	0.1	0.1
3.2	0.9	0.4	*	0.1	-	*	1.6	1.1	*	0.1
3.3	1.5	0.6	*	0.2	-	*	2.0	1.5	0.3	0.2
3.4	2.2	1.0	0.1	0.3	-	0.1	2.6	2.0	0.2	0.4
3.5	3.6	1.4	0.4	0.4	-	0.3	3.7	2.6	1.0	0.7
3.6	4.8	2.5	1.4	0.7	-	0.3	4.5	3.3	2.8	1.3
3.7	5.8	3.7	3.1	1.5	-	0.8	5.2	4.0	3.1	2.6
3.8	6.0	5.4	4.5	2.3	-	1.1	6.0	5.1	6.9	3.9
3.9	5.9	7.2	7.6	3.6	-	1.7	6.4	6.3	13.2	6.7
4.0	7.9	8.5	6.7	5.2	-	2.5	6.5	7.6	17.7	9.2
4.1	9.5	9.9	9.8	6.7	-	3.9	6.9	8.7	12.4	11.6
4.2	8.7	9.9	8.4	8.3	-	5.3	7.5	9.8	11.6	14.1
4.3	9.3	10.8	11.1	9.6	-	6.7	7.9	9.9	11.3	14.5
4.4	9.4	10.0	12.1	10.6	-	9.5	7.1	9.3	6.5	12.8
4.5	7.2	9.5	10.9	11.1	-	11.8	6.7	8.1	6.0	9.0
4.6	6.3	7.9	9.3	10.3	-	13.4	6.1	6.5	3.1	6.0
4.7	5.1	5.5	6.6	9.0	-	13.4	5.1	4.8	1.1	3.2
4.8	2.3	3.2	3.8	7.3	-	11.8	3.9	3.2	0.3	1.7
4.9	0.9	1.4	2.2	5.3	-	8.1	2.9	1.9	-	1.0
5.0	1.7	0.6	1.1	3.6	-	5.4	1.5	1.1	-	0.5
5.1	0.1	0.1	0.5	2.1	-	2.7	0.8	0.6	-	0.2
5.2	*	*	0.3	1.1	-	1.0	0.3	0.3	-	*
5.3	-	*	0.1	0.5	-	0.3	0.1	0.2	-	*
5.4	-	-	*	0.2	-	*	*	0.1	-	*
5.5 & Above	-	*	-	0.1	-	*	*	0.1	-	*
Average	***4.14***	***4.22***	***4.30***	***4.44***	***-***	***4.56***	***4.11***	***4.17***	***4.07***	***4.23***

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 01, 2026

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	*	-	-	*	*	-	-	-	-	*	*
2.7 - 2.9	-	*	-	*	0.3	*	-	0.1	-	-	*	*
3.0 - 3.2	0.4	0.1	-	*	0.9	0.1	-	0.6	-	0.1	0.4	0.1
3.3 - 3.4	0.6	0.5	*	*	1.4	0.3	*	0.5	-	0.1	0.9	0.4
3.5 - 3.6	3.2	1.8	*	0.1	1.9	0.7	0.3	2.3	-	1.3	3.5	1.5
3.7 - 4.2	33.4	32.7	1.1	3.9	25.6	24.2	39.3	38.6	2.5	21.2	41.3	28.9
4.3 - 4.9	56.2	58.0	67.5	71.1	64.8	68.1	39.6	47.4	97.4	71.5	50.3	60.5
5.0 - 5.2	5.4	5.9	29.0	22.1	3.5	5.6	12.4	8.2	0.1	5.5	3.2	7.7
5.3 & Above	0.8	1.1	2.4	2.8	1.6	0.9	8.4	2.3	-	0.4	0.4	0.9
Average	***4.34***	***4.39***	***4.79***	***4.76***	***4.39***	***4.47***	***4.51***	***4.38***	***4.48***	***4.47***	***4.29***	***4.44***
Leaf												
1 - 2	6.1	15.6	0.5	2.1	31.2	41.0	43.4	47.6	1.5	7.9	12.7	14.9
3	48.5	55.0	21.6	39.0	27.0	32.8	42.3	35.5	42.7	53.3	55.2	58.9
4	38.1	25.1	52.4	46.0	27.3	17.6	13.5	11.6	48.2	34.0	27.6	23.3
5	6.9	3.8	22.9	11.6	11.6	6.6	0.8	4.4	7.1	4.5	4.3	2.8
6	0.3	0.3	2.6	1.3	2.5	1.6	-	1.0	0.5	0.2	0.3	0.2
7	-	*	*	0.1	0.5	0.3	-	-	-	*	*	*
8	-	*	-	-	*	*	-	-	-	-	-	*
Average	***3.47***	***3.18***	***4.06***	***3.71***	***3.19***	***2.89***	***2.56***	***2.67***	***3.62***	***3.36***	***3.24***	***3.14***
HVI Trash 1/												
00	-	-	-	-	-	*	0.1	*	-	-	-	-
01	0.5	2.0	*	0.1	16.8	16.4	21.7	18.2	-	0.9	1.3	1.5
02	8.0	17.8	0.8	3.1	16.2	30.6	25.2	34.2	2.0	9.6	16.5	20.0
03	22.3	28.1	6.3	14.6	12.4	18.0	25.1	21.4	13.3	23.7	29.2	32.3
04	25.6	23.8	17.0	24.5	15.7	12.6	18.1	11.3	23.3	28.3	24.3	23.6
05	19.2	14.4	23.0	23.0	13.8	8.6	7.1	5.8	24.6	19.1	14.8	12.5
06	12.4	7.5	22.2	16.0	10.1	5.6	1.9	3.6	16.5	10.1	7.6	5.8
07	6.5	3.6	15.2	9.4	6.6	3.5	0.5	2.4	10.5	4.7	3.5	2.5
08	2.8	1.6	8.4	4.8	4.0	2.1	0.2	1.6	5.4	2.1	1.6	1.1
09	1.5	0.7	4.4	2.4	2.2	1.2	*	0.9	2.3	0.9	0.7	0.4
10	0.6	0.3	1.8	1.1	1.1	0.7	-	0.4	1.1	0.4	0.2	0.2
11	0.3	0.1	0.6	0.5	0.6	0.4	*	0.2	0.5	0.2	0.1	0.1
12	0.1	0.1	0.3	0.2	0.2	0.2	0.1	0.1	0.3	0.1	0.1	*
13	0.1	*	*	0.1	0.1	0.1	-	*	0.1	*	*	*
14	*	*	*	*	0.1	0.1	-	*	0.1	*	*	*
15	*	*	*	*	*	*	-	-	-	*	*	*
16	*	*	-	-	-	*	-	-	-	*	*	*
17	*	*	-	-	*	*	-	-	*	*	*	*
18 & Above	*	*	-	-	*	*	-	-	0.1	*	*	*
Average	***0.45***	***0.38***	***0.58***	***0.51***	***0.40***	***0.33***	***0.27***	***0.29***	***0.52***	***0.43***	***0.39***	***0.36***
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	-	-	-	-	-	-	-	-	-	-	*
76	-	*	-	*	*	*	-	*	-	*	*	*
77	*	*	*	*	0.1	*	-	*	-	*	0.1	0.1
78	0.2	0.3	0.1	0.1	0.1	0.2	-	1.0	-	0.1	1.0	0.8
79	2.4	2.5	0.8	0.5	1.6	1.5	1.6	6.2	0.2	1.1	5.8	5.3
80	19.6	13.1	7.1	3.9	12.0	12.0	21.1	17.0	2.2	8.0	20.6	21.2
81	34.4	31.6	20.3	20.5	37.7	35.3	27.7	24.8	38.0	37.5	34.6	36.5
82	27.7	35.3	32.3	42.9	38.7	40.2	26.3	29.8	54.0	41.6	27.1	26.5
83	12.5	15.0	29.6	27.7	7.9	9.9	19.8	16.4	4.8	10.7	9.4	8.2
84	2.7	2.1	8.7	4.2	1.8	0.8	3.4	4.7	0.7	1.1	1.3	1.3
85 & Above	0.5	0.2	1.1	0.2	*	*	*	0.1	*	0.1	0.1	0.1
Average	***81.83***	***81.98***	***82.58***	***82.52***	***81.89***	***81.92***	***81.96***	***81.89***	***82.09***	***82.01***	***81.59***	***81.57***
Tenderable 3/	**81.2**	**90.4**	**65.1**	**69.9**	**87.2**	**87.3**	**76.3**	**83.2**	**79.0**	**91.2**	**89.8**	**88.4**
SAMPLES CLASSED	**9,587**	**514,480**	**22,446**	**1,339,876**	**18,232**	**121,744**	**5,353**	**54,060**	**2,421**	**87,834**	**90,858**	**1,547,964**

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 01, 2026

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	0.1	0.1	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	2.2	1.2	-	*	-	-	-	-	-	*	-	-
2.7 - 2.9	6.4	5.5	-	*	-	-	-	-	*	*	-	0.2
3.0 - 3.2	11.7	9.0	-	*	-	*	-	*	0.2	0.2	-	0.9
3.3 - 3.4	11.9	9.4	-	0.1	-	*	-	*	0.7	0.5	0.4	0.9
3.5 - 3.6	10.7	12.1	-	0.2	*	0.1	-	0.2	2.3	1.4	-	2.1
3.7 - 4.2	39.6	40.6	-	8.1	7.8	8.4	-	5.0	31.7	28.2	38.4	44.4
4.3 - 4.9	16.8	21.8	-	64.6	91.0	82.6	-	61.8	64.1	64.2	61.1	50.0
5.0 - 5.2	0.7	0.4	-	21.7	1.1	8.4	-	29.0	1.1	5.1	-	1.5
5.3 & Above	-	-	-	5.2	-	0.5	-	4.0	-	0.4	-	*
Average	***3.72***	***3.81***	***-***	***4.74***	***4.57***	***4.62***	***-***	***4.80***	***4.33***	***4.41***	***4.31***	***4.24***
Leaf												
1 - 2	0.8	10.3	-	14.2	2.0	4.0	-	6.3	3.4	9.2	33.2	60.3
3	18.0	26.5	-	49.8	51.9	53.0	-	42.8	49.1	51.6	35.5	28.6
4	29.3	29.6	-	29.5	40.7	37.2	-	39.7	40.1	32.8	23.2	7.9
5	26.6	19.8	-	6.1	5.1	5.4	-	10.1	6.6	5.8	5.7	2.2
6	16.0	9.7	-	0.4	0.4	0.4	-	1.0	0.8	0.5	2.2	0.8
7	6.6	3.3	-	-	*	*	-	*	0.1	0.1	0.3	0.1
8	2.7	0.9	-	-	-	-	-	-	-	*	-	-
Average	***4.69***	***4.05***	***-***	***3.28***	***3.50***	***3.45***	***-***	***3.57***	***3.52***	***3.37***	***3.05***	***2.41***
HVI Trash 1/												
00	-	-	-	-	-	*	-	-	-	-	-	-
01	*	2.5	-	1.9	*	0.2	-	0.5	0.1	0.8	8.3	25.0
02	1.2	9.8	-	15.0	4.1	6.1	-	7.7	5.0	11.0	29.4	38.4
03	6.9	12.3	-	24.4	22.7	23.1	-	19.0	20.4	24.3	22.6	18.6
04	11.6	13.3	-	23.2	29.7	28.7	-	23.6	28.7	25.5	17.1	8.8
05	12.4	12.9	-	16.2	22.3	21.0	-	19.9	22.9	18.4	12.1	4.6
06	10.7	10.9	-	9.6	12.4	11.4	-	13.3	12.8	10.6	4.3	2.0
07	10.2	8.9	-	5.2	5.6	5.4	-	7.9	6.1	5.3	2.0	1.1
08	9.6	7.4	-	2.5	2.2	2.3	-	4.2	2.5	2.4	1.8	0.7
09	8.1	5.7	-	1.2	0.6	1.0	-	2.1	1.1	1.0	1.6	0.4
10	6.3	4.4	-	0.5	0.3	0.4	-	1.0	0.2	0.4	0.1	0.1
11	5.4	3.4	-	0.2	*	0.2	-	0.5	0.1	0.2	0.3	0.1
12	4.1	2.5	-	0.1	*	0.1	-	0.2	*	0.1	0.3	0.1
13	3.7	1.9	-	*	-	*	-	0.1	*	*	-	*
14	2.7	1.4	-	*	*	*	-	*	*	*	-	-
15	2.0	0.8	-	-	-	*	-	*	-	*	-	-
16	1.5	0.7	-	-	-	-	-	-	-	*	-	-
17	1.2	0.5	-	-	-	-	-	-	-	*	-	-
18 & Above	2.5	0.9	-	-	-	-	-	-	-	*	-	-
Average	***0.80***	***0.62***	***-***	***0.41***	***0.45***	***0.44***	***-***	***0.47***	***0.45***	***0.43***	***0.34***	***0.25***
UNIFORMITY 2/												
74 & Below	*	*	-	-	-	-	-	-	-	*	-	-
75	0.2	0.1	-	-	-	-	-	-	-	*	-	-
76	0.8	0.4	-	-	-	*	-	*	*	*	-	-
77	2.6	1.5	-	-	-	*	-	*	*	*	0.1	*
78	4.8	3.6	-	0.1	*	0.1	-	0.2	0.4	0.6	0.2	0.3
79	7.1	7.7	-	1.2	*	0.2	-	1.3	2.3	2.9	4.1	1.8
80	16.2	16.9	-	7.1	0.7	2.1	-	8.8	9.5	10.7	41.8	15.7
81	34.8	31.6	-	30.1	11.4	15.9	-	30.1	25.6	27.0	34.2	40.8
82	22.8	25.8	-	40.4	58.2	50.3	-	38.1	39.4	35.5	12.6	31.6
83	9.2	10.6	-	18.5	27.2	28.6	-	18.1	20.1	20.3	6.8	9.5
84	1.5	1.7	-	2.6	2.3	2.6	-	3.3	2.6	2.8	0.1	0.3
85 & Above	*	0.1	-	0.1	0.2	0.2	-	0.1	0.1	0.2	-	*
Average	***81.30***	***81.46***	***-***	***82.21***	***82.65***	***82.58***	***-***	***82.18***	***82.17***	***82.12***	***81.16***	***81.75***
Tenderable 3/	**24.7**	**43.3**	**-**	**71.5**	**97.0**	**86.4**	**-**	**63.7**	**93.4**	**90.7**	**92.9**	**93.5**
SAMPLES CLASSED	**14,073**	**85,943**	**-**	**223,278**	**12,679**	**639,983**	**-**	**706,431**	**11,704**	**627,921**	**911**	**8,273**

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 01, 2026

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	*	*	-	-	-	-	*	*	-	-
2.5 - 2.6	0.1	*	-	-	-	-	0.3	0.1	-	-
2.7 - 2.9	0.1	0.1	-	*	-	*	1.5	0.7	2.1	*
3.0 - 3.2	1.5	0.7	*	0.1	-	*	4.3	2.3	0.3	0.3
3.3 - 3.4	3.7	1.6	0.1	0.5	-	0.2	4.6	3.5	0.6	0.6
3.5 - 3.6	8.4	3.9	1.8	1.1	-	0.6	8.2	5.9	3.9	2.0
3.7 - 4.2	43.9	44.6	40.0	27.5	-	15.1	38.5	41.5	65.0	48.2
4.3 - 4.9	40.5	48.3	56.0	63.2	-	74.7	39.6	43.8	28.2	48.2
5.0 - 5.2	1.9	0.8	1.9	6.8	-	9.0	2.6	1.9	-	0.7
5.3 & Above	-	*	0.1	0.8	-	0.3	0.2	0.3	-	*
Average	***4.14***	***4.22***	***4.30***	***4.44***	***-***	***4.56***	***4.11***	***4.17***	***4.07***	***4.23***
Leaf										
1 - 2	59.5	62.9	1.5	4.8	-	16.4	54.0	56.0	13.4	11.4
3	29.8	29.8	37.2	50.1	-	59.0	34.7	32.0	44.6	61.4
4	7.9	6.1	52.2	39.5	-	21.8	8.8	9.9	29.6	24.0
5	2.2	1.0	8.8	5.5	-	2.7	1.9	1.9	10.2	3.1
6	0.5	0.2	0.4	0.2	-	0.2	0.5	0.3	2.2	0.1
7	0.1	*	*	*	-	*	0.1	*	*	*
8	*	*	-	-	-	-	*	*	-	-
Average	***2.39***	***2.24***	***3.69***	***3.46***	***-***	***3.11***	***2.49***	***2.43***	***3.43***	***3.19***
HVI Trash 1/										
00	*	*	-	-	-	*	0.1	0.1	-	-
01	26.9	33.0	*	0.2	-	2.0	22.7	27.3	1.1	0.5
02	36.4	32.7	2.3	6.8	-	17.1	38.8	33.1	13.2	12.6
03	18.2	18.1	13.5	22.9	-	29.7	20.4	18.5	22.6	29.8
04	8.6	9.0	27.0	27.8	-	24.7	9.0	10.2	20.1	26.5
05	4.3	3.9	26.2	21.3	-	14.2	4.3	5.5	15.2	15.9
06	2.1	1.7	16.8	11.9	-	6.8	2.1	2.8	10.5	8.2
07	1.3	0.8	8.5	5.5	-	3.1	1.1	1.4	7.6	3.9
08	0.9	0.4	3.7	2.2	-	1.3	0.6	0.6	4.0	1.6
09	0.5	0.2	1.4	0.8	-	0.6	0.4	0.3	2.7	0.7
10	0.3	0.1	0.4	0.3	-	0.2	0.2	0.1	1.6	0.2
11	0.1	*	0.1	0.1	-	0.1	0.1	0.1	0.5	0.1
12	0.1	*	*	*	-	*	0.1	*	0.8	*
13	*	*	*	*	-	*	*	*	-	*
14	*	*	-	*	-	*	*	*	0.1	*
15	*	*	-	*	-	*	*	*	-	*
16	*	*	-	*	-	-	*	*	-	*
17	*	*	-	-	-	-	*	*	-	*
18 & Above	*	*	-	*	-	-	*	*	-	*
Average	***0.25***	***0.23***	***0.49***	***0.44***	***-***	***0.38***	***0.25***	***0.25***	***0.46***	***0.40***
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	*	*	-	-
75	-	*	-	*	-	-	0.1	*	-	-
76	*	*	-	*	-	*	0.3	0.2	-	*
77	0.2	0.2	*	*	-	*	1.2	0.8	0.1	*
78	0.7	0.9	0.6	0.4	-	0.1	5.2	3.5	0.1	0.2
79	5.8	5.1	3.6	3.2	-	0.6	16.1	11.7	1.2	1.4
80	19.9	16.8	22.0	15.9	-	6.9	33.0	25.1	5.8	8.3
81	35.5	31.4	36.1	32.2	-	32.7	29.6	30.2	30.2	27.8
82	29.9	26.7	22.3	33.7	-	43.1	11.5	19.3	39.7	38.1
83	7.8	14.4	13.4	13.3	-	15.6	2.5	7.4	19.9	21.2
84	0.3	4.1	1.9	1.2	-	0.9	0.4	1.7	2.8	2.9
85 & Above	*	0.3	*	0.1	-	0.1	0.1	0.2	0.2	0.2
Average	***81.57***	***81.84***	***81.69***	***81.85***	***-***	***82.14***	***80.75***	***81.22***	***82.26***	***82.24***
Tenderable 3/	**85.1**	**93.7**	**87.0**	**86.4**	**-**	**82.3**	**72.8**	**84.1**	**90.5**	**96.4**
SAMPLES CLASSED	**26,130**	**299,825**	**16,334**	**250,606**	**-**	**340,307**	**242,992**	**4,440,415**	**2,116**	**170,464**

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 01, 2026

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
01	1	-	2.4	3.4	5.3	-	-	16.5	17.0
	2	-	0.3	7.0	6.4	-	-	16.8	16.4
	3	-	*	0.1	0.1	-	-	0.2	0.4
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total	----------	**-**	***2.7***	***10.5***	***11.8***	**-**	**-**	***33.5***	***33.8***
02	1	-	39.9	3.3	4.6	-	-	9.4	15.0
	2	-	18.3	27.2	34.0	-	-	44.2	41.7
	3	-	0.2	9.8	8.8	-	-	2.7	3.0
	4	-	-	0.1	0.1	-	-	-	0.1
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total	----------	**-**	***58.4***	***40.4***	***47.5***	**-**	**-**	***56.4***	***59.8***
03	1	-	12.6	0.2	0.2	-	-	0.8	0.4
	2	-	22.5	17.6	14.1	-	-	8.4	5.0
	3	-	0.8	23.2	19.1	-	-	0.8	0.9
	4	-	-	1.4	2.1	-	-	-	0.1
	5	-	-	*	0.1	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total	----------	**-**	***35.9***	***42.4***	***35.6***	**-**	**-**	***10.0***	***6.3***
04	7	-	-	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-
	5	-	-	*	0.1	-	-	-	-
	4	-	-	0.8	1.0	-	-	-	*
	3	-	0.3	3.1	2.6	-	-	*	*
	2	-	2.4	1.7	0.7	-	-	*	*
	1	-	0.3	0.1	*	-	-	-	-
Total	----------	**-**	***3.0***	***5.6***	***4.4***	**-**	**-**	***0.1***	***0.1***
05	1	-	-	-	*	-	-	-	-
	2	-	*	0.1	0.1	-	-	-	-
	3	-	*	0.2	0.3	-	-	*	*
	4	-	-	0.1	0.2	-	-	-	-
	5	-	-	*	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total	----------	**-**	*******	***0.3***	***0.6***	**-**	**-**	*******	*******
06	1	-	-	-	-	-	-	-	-
	2	-	-	*	*	-	-	-	-
	3	-	-	*	*	-	-	-	-
	4	-	-	0.1	*	-	-	-	-
	5	-	-	*	*	-	-	-	-
	6	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total	----------	**-**	**-**	***0.2***	***0.1***	**-**	**-**	**-**	**-**
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	0.1	*	-	-	-	-
	4	-	-	0.3	*	-	-	-	-
	5	-	-	0.1	*	-	-	-	-
	6	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total	----------	**-**	**-**	***0.5***	*******	**-**	**-**	**-**	**-**
STAPLE									
44 & Shorter		-	0.1	4.2	2.2	-	-	10.8	11.7
46		-	19.6	4.5	8.0	-	-	48.9	50.8
48		-	74.9	41.2	45.1	-	-	36.4	33.1
50		-	5.1	48.4	42.6	-	-	3.8	3.9
52 & Longer		-	0.2	1.7	2.1	-	-	0.1	0.5
Average Staple		**-**	***47.71***	***48.75***	***48.68***	**-**	**-**	***46.67***	***46.62***
Average Length		**-**	***1.39***	***1.42***	***1.41***	**-**	**-**	***1.36***	***1.36***
EXTRANEOUS MATTER									
Bark		-	-	0.1	*	-	-	-	*
Grass		-	-	-	0.3	-	-	0.5	1.1
Spindle Twist		-	-	0.7	0.1	-	-	-	-
Preparation		-	*	-	*	-	-	-	-
All Other		-	*	*	*	-	-	*	*

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 01, 2026

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	*Season*	*Week*	*Season*	*Week*	*Season*	*Week*	*Season*
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	-
2.7 - 2.9	-	*	0.6	0.1	-	-	-	0.2
3.0 - 3.2	-	*	0.9	0.5	-	-	*	10.9
3.3 - 3.4	-	0.4	1.8	1.5	-	-	0.3	15.5
3.5 - 3.6	-	1.3	6.1	7.1	-	-	19.5	20.7
3.7 - 4.2	-	93.5	80.9	87.6	-	-	71.9	50.5
4.3 - 4.9	-	4.9	9.7	3.2	-	-	8.3	2.3
5.0 - 5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	**-**	***3.99***	***3.94***	***3.90***	**-**	**-**	***3.90***	***3.67***
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-
2.7	-	*	-	*	-	-	-	*
2.8	-	-	*	*	-	-	-	*
2.9	-	-	0.5	0.1	-	-	-	0.2
3.0	-	*	0.3	0.1	-	-	*	1.8
3.1	-	-	0.4	0.1	-	-	-	4.2
3.2	-	-	0.2	0.3	-	-	-	4.9
3.3	-	0.1	0.5	0.5	-	-	*	5.7
3.4	-	0.2	1.3	0.9	-	-	0.2	9.7
3.5	-	0.2	2.2	2.1	-	-	3.1	11.6
3.6	-	1.0	3.9	5.0	-	-	16.4	9.1
3.7	-	4.5	8.7	10.0	-	-	20.1	9.4
3.8	-	12.5	13.1	16.7	-	-	6.7	9.5
3.9	-	21.2	18.7	22.5	-	-	6.7	11.5
4.0	-	26.3	17.0	20.5	-	-	12.1	10.0
4.1	-	20.6	12.8	12.0	-	-	17.4	7.8
4.2	-	8.5	10.6	6.0	-	-	8.9	2.3
4.3	-	2.7	6.7	2.1	-	-	6.0	1.5
4.4	-	2.0	2.0	0.7	-	-	0.9	0.4
4.5	-	0.2	0.7	0.3	-	-	0.1	0.1
4.6	-	*	0.1	0.1	-	-	1.2	0.1
4.7	-	*	0.1	*	-	-	*	*
4.8	-	-	*	*	-	-	*	*
4.9	-	-	*	*	-	-	-	*
5.0	-	-	-	-	-	-	-	-
5.1	-	-	-	-	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	**-**	***3.99***	***3.94***	***3.90***	**-**	**-**	***3.90***	***3.67***
STRENGTH 1/								
36 & Below	-	-	1.0	1.6	-	-	0.3	10.6
37	-	0.1	2.2	4.4	-	-	7.2	19.3
38	-	0.2	2.7	2.9	-	-	25.3	19.2
39	-	0.8	1.2	1.3	-	-	4.3	7.0
40	-	6.8	1.4	1.8	-	-	2.4	2.5
41	-	24.3	3.1	5.7	-	-	6.8	3.3
42	-	35.7	6.5	11.3	-	-	8.6	5.4
43	-	22.5	12.8	18.1	-	-	5.9	7.5
44	-	7.3	19.1	21.8	-	-	10.1	9.0
45	-	1.3	16.8	17.7	-	-	10.2	7.4
46	-	0.5	15.8	8.9	-	-	4.7	4.9
47	-	0.2	11.8	3.4	-	-	7.3	2.5
48 & Above	-	0.1	5.5	1.2	-	-	6.9	1.3
Average	**-**	***42.48***	***44.67***	***43.64***	**-**	**-**	***42.36***	***40.62***
UNIFORMITY								
83 & Below	-	0.2	5.0	1.5	-	-	1.2	1.7
84	-	3.2	10.1	11.4	-	-	31.4	22.8
85	-	40.3	40.3	33.1	-	-	33.2	45.0
86	-	51.0	38.7	47.9	-	-	28.3	27.0
87	-	5.1	5.4	5.6	-	-	5.5	3.4
88 & Above	-	0.1	0.5	0.5	-	-	0.4	0.2
Average	**-**	***86.03***	***85.75***	***85.90***	**-**	**-**	***85.52***	***85.52***
Samples Classed	**-**	**8,389**	**21,507**	**250,400**	**-**	**-**	**2,548**	**24,317**

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.