



Weekly Quality of Cotton Classed by Classing Office: Week Ending - 1/8/2026

Agricultural Marketing Service
Cotton Market News

Volume 67, No.23

January 09, 2026

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	30	74.5	55.6	92,244	31	83.8	62.4	850,586
Corpus Christi	4	92.4	88.1	4,688	42	88.1	72.5	1,510,711
Dumas	7	45.5	27.0	7,257	33	53.1	25.2	943,188
Florence	27	87.5	79.9	29,323	40	90.5	79.2	1,078,314
Lamesa	19	77.4	52.0	34,042	24	84.9	60.4	490,119
Lubbock	46	67.5	45.4	139,949	54	80.0	59.9	2,200,651
Macon	56	86.3	75.6	94,106	68	88.6	74.8	2,064,118
Memphis	8	86.1	70.5	27,963	65	83.2	59.7	2,272,040
Rayville*	-	-	-	-	16	69.8	47.8	278,491
Visalia	15	84.9	69.8	27,345	26	85.5	68.3	228,461
United States	214	76.8	59.5	457,416	399	82.3	63.1	11,916,679
AMERICAN PIMA								
Visalia	12			19,468	18			321,583
United States	12			19,468	18			321,583
United States all cotton	224			476,884	408			12,238,262

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

MP_CN100

Source: USDA AMS Cotton and Tobacco Market News

Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov

<https://www.ams.usda.gov/market-news/cotton>

<https://mymarketnews.ams.usda.govcottonmn@ams.usda.gov>

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 08, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	29.1	41.8	33.4	14.4	-	0.9	0.1	0.5	66.7	72.7
	3	5.3	7.5	2.4	14.3	-	0.8	0.2	0.5	7.0	6.8
	4	0.6	0.4	*	1.4	-	*	*	*	0.1	0.3
	5	*	*	-	*	-	*	-	*	*	*
	6	-	*	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	35.0 49.7	35.9 30.2	1.7	0.3	1.0	73.8	79.8		
31	1 - 2	13.3	7.5	21.5	5.0	*	2.2	3.4	5.3	4.6	1.7
	3	14.0	10.9	17.0	22.1	0.9	16.2	15.2	21.7	1.3	1.4
	4	3.2	3.5	2.9	9.4	2.9	8.0	6.7	6.1	0.2	0.4
	5	0.4	0.6	0.9	1.0	0.6	0.5	0.4	0.3	0.1	*
	6	*	0.1	-	*	-	*	-	*	*	*
	7	-	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	30.9 22.5	42.2 37.6	4.5 26.9	25.7	33.3	6.3	3.6		
41	1 - 2	0.5	0.2	2.4	0.6	-	0.6	1.9	2.6	-	*
	3	1.8	0.8	4.0	5.3	3.2	19.2	30.8	29.2	-	*
	4	2.4	1.2	3.5	5.0	38.3	32.8	29.0	25.0	*	*
	5	1.6	1.0	2.0	1.3	31.2	9.0	6.1	4.2	*	*
	6	0.7	0.5	0.3	0.1	2.2	0.6	0.3	0.3	*	*
	7	0.1	0.1	-	*	-	*	-	*	-	*
	8	*	*	-	-	-	-	-	*	-	-
	Total	----	7.2 3.8	12.1 12.4	74.8 62.2	68.2	61.3	*	*		
51	1 - 2	-	*	-	*	-	*	0.1	0.1	-	-
	3	*	*	0.1	0.2	-	1.1	1.3	1.0	-	-
	4	*	*	0.1	0.4	0.9	3.0	1.9	1.6	-	-
	5	0.1	*	1.0	0.1	2.2	1.5	0.9	0.7	-	-
	6	0.1	0.1	0.7	*	0.3	0.2	0.2	0.1	-	-
	7	0.1	0.1	0.3	*	-	*	*	*	-	-
	8	*	*	-	-	-	-	-	*	-	-
	Total	----	0.3 0.2	2.1 0.8	3.4 5.8	4.4	3.5	-	-		
61	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	*	-	-
	7	-	-	*	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	* *	- *	- *	- *	- *	- *		
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- -	- -	- -	- *	- *	- *		
12 & 22	1 - 2	5.8	10.0	*	4.0	-	*	-	*	11.4	10.9
	3	2.4	3.2	*	3.8	-	*	*	*	2.4	2.5
	4	0.7	0.4	-	1.0	-	*	-	*	0.1	0.2
	5	*	*	-	0.1	-	-	-	-	*	*
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	8.9 13.7	0.1 8.9	- *	*	*	13.9	13.6		
32	1 - 2	3.0	1.1	0.4	0.6	-	*	*	*	0.4	0.2
	3	4.5	2.3	2.6	2.6	-	0.1	0.1	0.1	0.5	0.4
	4	1.8	1.3	0.9	2.4	0.1	0.1	0.3	0.1	0.5	0.3
	5	0.5	0.4	0.4	0.6	0.1	*	*	*	0.2	0.1
	6	0.1	0.1	0.1	*	-	*	-	*	*	*
	7	*	*	-	*	-	-	-	-	*	*
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	10.0 5.2	4.3 6.3	0.1 0.3	0.5	0.2	1.7	1.0		
42	1 - 2	0.1	*	0.1	0.1	-	*	*	*	-	*
	3	0.6	0.3	0.5	0.9	-	0.5	0.1	0.2	*	*
	4	1.0	0.6	0.7	1.1	2.5	1.2	0.5	0.3	-	*
	5	1.0	0.7	0.9	0.6	10.4	0.6	0.2	0.1	-	*
	6	0.8	0.5	0.4	0.1	1.9	0.1	*	*	*	*
	7	0.5	0.2	*	*	*	*	-	*	-	*
	8	0.1	*	-	-	-	-	-	*	-	-
	Total	----	4.1 2.4	2.6 2.8	14.8 2.4	0.8	0.6	*	*		

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 08, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	*	-	*	-	*
	3	-	-	-	*	-	0.1	-	*	-	-
	4	-	*	*	0.1	0.1	0.2	*	*	-	-
	5	*	*	-	0.1	1.1	0.2	-	*	-	*
	6	*	*	-	*	1.0	0.1	-	*	-	-
	7	0.1	0.1	*	*	*	*	-	*	-	-
	8	0.1	*	-	-	-	-	-	*	-	-
Total	----	0.3	0.1	*	0.2	2.3	0.6	*	0.1	-	*
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	-	*	-	-
13 & 23	1 - 2	0.7	0.6	-	0.1	-	-	*	*	2.0	0.9
	3	0.5	0.4	-	0.1	-	-	*	*	0.2	0.4
	4	0.1	0.1	*	*	-	-	-	*	*	*
	5	*	*	-	*	-	-	-	-	-	*
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.2	1.2	*	0.2	-	-	*	*	2.2	1.3
33	1 - 2	0.2	0.1	-	*	-	*	*	*	0.1	0.1
	3	0.6	0.4	0.1	0.1	-	*	*	*	0.3	0.2
	4	0.3	0.2	-	0.1	-	*	*	*	0.7	0.2
	5	0.1	0.1	-	*	-	-	-	*	0.5	0.1
	6	*	*	-	*	-	-	-	*	0.1	*
	7	*	*	-	*	-	-	-	-	*	*
	8	*	*	-	-	-	-	-	-	-	-
Total	----	1.2	0.8	0.1	0.3	-	*	0.1	*	1.7	0.5
43	1 - 2	*	*	-	*	-	-	-	*	-	*
	3	*	*	*	0.1	-	*	*	*	*	*
	4	0.1	0.1	0.1	0.1	-	*	0.1	*	*	*
	5	0.2	0.1	0.2	0.1	*	*	*	*	0.1	*
	6	0.2	0.1	0.1	*	*	*	-	*	0.1	*
	7	0.1	*	*	*	-	-	-	*	*	*
	8	*	*	-	-	-	-	-	*	-	-
Total	----	0.8	0.3	0.4	0.3	*	*	0.1	*	0.2	*
53	1 - 2	-	-	-	*	-	*	-	-	-	-
	3	-	*	-	*	-	*	-	*	-	-
	4	-	*	*	*	*	*	-	*	-	-
	5	-	*	-	*	-	*	*	*	-	-
	6	-	*	-	*	-	*	-	*	-	*
	7	*	*	*	*	-	*	-	*	-	-
	8	*	*	-	-	-	-	-	*	-	-
Total	----	*	*	*	*	*	*	*	*	-	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	-	-	-	-
24 - 54	1 - 8	0.1	0.1	-	*	-	-	*	*	0.1	0.1
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	*	-	-	-	-	*	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-
30		*	*	-	-	-	-	-	-	*	*
31		*	0.1	-	*	-	*	-	*	0.2	0.2
32		0.3	0.5	-	*	-	*	*	*	2.1	1.8
33		2.5	2.8	0.6	0.1	*	0.2	1.3	0.1	9.6	7.3
34		10.1	8.0	1.7	0.7	0.6	1.3	7.9	1.4	26.8	20.6
35		18.2	14.8	1.7	3.7	3.9	8.2	17.8	8.0	31.8	27.7
36		19.9	18.9	2.9	15.5	16.8	25.2	37.7	26.3	18.7	21.5
37		25.9	24.0	49.1	45.9	30.0	42.7	28.6	48.2	9.0	15.9
38		12.8	14.9	39.9	25.4	26.0	16.5	5.1	13.0	1.8	4.2
39		6.4	10.4	3.9	7.8	14.9	4.9	1.4	2.7	0.1	0.7
40 & Longer		3.8	5.7	0.1	0.7	7.7	1.1	0.1	0.3	*	*
Average Staple		36.42	36.68	37.34	37.18	37.53	36.83	36.06	36.72	34.90	35.28
Average Length		1.14	1.14	1.17	1.16	1.17	1.15	1.12	1.15	1.09	1.10

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 08, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	43.7	59.6	2.4	1.7	-	0.4	-	3.9	9.9	23.4
	3	14.3	15.6	2.1	1.1	-	0.4	-	2.6	2.0	6.7
	4	0.7	0.9	0.1	*	-	*	-	0.1	0.3	0.4
	5	*	*	*	*	-	*	-	*	*	*
	6	*	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	58.7	76.1	4.6	2.8	-	0.8	-	6.6	12.2	30.4
31	1 - 2	4.9	2.6	6.8	8.2	2.3	2.7	-	8.0	8.3	12.2
	3	6.5	4.7	20.5	21.8	8.3	12.2	-	33.3	11.7	13.9
	4	2.2	2.0	6.5	4.1	0.7	3.4	-	11.7	1.7	3.4
	5	0.4	0.3	0.5	0.2	*	0.2	-	0.9	0.2	0.4
	6	*	*	*	*	-	*	-	*	*	*
	7	-	*	-	*	-	*	-	-	*	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	14.1	9.7	34.2	34.3	11.3	18.5	-	53.9	21.9	30.0
41	1 - 2	*	*	3.1	5.1	2.7	2.3	-	0.7	5.1	2.6
	3	0.1	0.1	20.5	31.9	37.6	30.6	-	12.3	28.2	11.9
	4	0.2	0.1	14.9	16.8	19.4	26.7	-	16.2	15.7	8.7
	5	0.3	0.1	2.8	2.2	2.6	5.1	-	4.5	2.3	2.7
	6	0.2	*	0.2	0.1	0.1	0.4	-	0.4	0.2	0.4
	7	*	*	*	*	*	*	-	-	*	*
	8	*	*	-	-	-	-	-	-	-	-
Total	----	0.8	0.4	41.5	56.1	62.3	65.2	-	34.2	51.5	26.3
51	1 - 2	-	*	0.4	0.2	0.6	0.1	-	*	*	0.1
	3	-	*	6.0	2.0	8.7	2.9	-	*	1.4	0.8
	4	-	*	7.2	2.1	9.9	4.7	-	0.3	3.8	1.7
	5	*	*	1.7	0.5	2.4	1.7	-	0.3	3.0	1.4
	6	0.1	*	0.2	0.1	0.2	0.3	-	0.1	1.9	0.7
	7	*	*	*	*	*	*	-	-	0.5	0.2
	8	*	*	*	*	-	-	-	-	*	*
Total	----	0.2	*	15.5	4.9	21.7	9.7	-	0.7	10.5	4.9
61	1 - 2	-	*	*	*	-	*	-	-	-	-
	3	-	*	0.1	*	*	*	-	*	-	-
	4	-	*	0.1	*	*	*	-	*	*	*
	5	-	-	*	*	-	*	-	-	*	*
	6	-	-	*	*	-	*	-	-	*	*
	7	-	-	*	*	-	*	-	-	*	*
	8	-	-	-	*	-	-	-	-	-	-
Total	----	-	*	0.3	*	*	*	-	*	0.1	*
71	1 - 2	-	*	-	-	-	*	-	-	-	-
	3	-	*	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	*	-	-	-	-
12 & 22	1 - 2	8.2	5.7	0.1	*	-	*	-	0.1	1.0	2.7
	3	6.6	3.7	0.4	*	-	*	-	0.1	0.4	1.4
	4	0.8	0.4	0.1	*	-	*	-	0.1	0.3	0.2
	5	*	*	-	-	-	*	-	*	-	*
	6	*	*	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	15.6	9.8	0.5	0.1	-	*	-	0.3	1.6	4.2
32	1 - 2	0.5	0.3	*	0.1	-	*	-	0.1	0.2	0.2
	3	1.8	0.9	0.3	0.3	*	0.2	-	0.4	0.2	0.6
	4	1.3	0.6	0.4	0.1	*	0.1	-	0.7	0.1	0.5
	5	0.7	0.2	0.1	*	-	*	-	0.4	0.1	0.2
	6	0.2	*	*	*	-	*	-	0.1	*	*
	7	*	*	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
Total	----	4.6	1.9	0.9	0.4	*	0.3	-	1.7	0.6	1.5
42	1 - 2	*	*	*	*	*	0.2	-	*	*	*
	3	*	*	0.4	0.5	0.6	1.8	-	0.3	0.5	0.5
	4	0.1	0.1	0.5	0.4	1.8	1.5	-	1.1	0.2	0.5
	5	0.2	0.1	0.2	0.1	0.4	0.4	-	0.7	0.1	0.3
	6	0.1	*	*	*	*	0.1	-	0.3	*	0.1
	7	*	*	*	*	-	*	-	-	*	*
	8	*	*	-	-	-	-	-	-	-	-
Total	----	0.5	0.2	1.2	1.1	2.9	3.9	-	2.4	0.9	1.4

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 08, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	*	*	-	*	-	-	-	*
	3	-	-	0.2	*	0.3	0.4	-	*	*	0.1
	4	-	*	0.3	0.1	1.1	0.7	-	*	0.3	0.2
	5	*	*	0.2	*	0.2	0.3	-	0.1	0.3	0.2
	6	*	*	*	*	*	0.1	-	*	0.1	0.1
	7	*	*	*	*	-	*	-	-	*	*
	8	-	-	*	*	-	-	-	-	*	*
Total	----	*	*	0.7	0.2	1.6	1.4	-	0.1	0.7	0.7
62	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	*	*	-	*	-	-	-	*
	4	-	-	*	*	*	*	-	-	-	*
	5	-	-	*	*	-	*	-	-	*	*
	6	-	-	*	*	-	*	-	-	*	*
	7	-	-	*	*	-	*	-	-	*	*
	8	-	-	*	*	-	-	-	-	*	*
Total	----	-	-	*	*	*	*	-	-	*	*
13 & 23	1 - 2	1.5	0.6	*	*	-	-	-	-	*	0.2
	3	1.8	0.5	*	*	-	-	-	-	*	*
	4	0.2	0.1	*	*	-	-	-	-	*	*
	5	*	*	-	-	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	3.5	1.2	*	*	-	-	-	-	*	0.2
33	1 - 2	0.3	0.1	*	*	-	*	-	*	*	*
	3	0.7	0.3	*	*	-	*	-	*	-	*
	4	0.4	0.2	*	*	*	*	-	*	*	*
	5	0.2	0.1	*	*	-	*	-	*	*	*
	6	0.1	*	-	-	-	*	-	*	-	*
	7	*	*	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
Total	----	1.7	0.6	0.1	*	*	*	-	*	*	0.1
43	1 - 2	-	*	*	*	-	*	-	*	-	*
	3	*	*	0.1	*	-	*	-	*	*	*
	4	*	*	0.1	*	*	*	-	*	*	*
	5	*	*	0.1	*	*	*	-	*	*	*
	6	*	*	*	*	-	*	-	*	-	*
	7	*	*	-	*	-	*	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
Total	----	*	*	0.3	*	*	0.1	-	*	*	0.1
53	1 - 2	-	-	-	*	-	*	-	-	*	*
	3	-	-	*	*	*	*	-	-	-	*
	4	-	-	*	*	*	*	-	-	-	*
	5	-	-	*	*	*	*	-	-	-	*
	6	-	*	*	*	*	*	-	*	-	*
	7	-	-	*	*	-	*	-	-	-	*
	8	*	*	-	-	-	-	-	-	-	-
Total	----	*	*	0.1	*	0.1	*	-	*	*	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-
24 - 54	1 - 8	0.3	0.1	*	*	-	*	-	-	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	*	-	*	-	-	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-
30		*	*	-	*	-	-	-	-	-	-
31		0.1	0.1	*	*	-	*	-	-	-	*
32		0.4	0.5	0.1	0.1	-	*	-	*	*	*
33		2.5	2.5	1.5	0.8	0.1	0.1	-	0.2	*	0.1
34		9.3	8.3	7.2	4.5	1.8	0.8	-	1.6	0.6	0.8
35		22.2	17.6	18.4	15.2	5.6	4.2	-	11.4	2.6	3.7
36		29.9	25.5	29.6	30.2	21.7	15.1	-	29.0	15.2	13.9
37		26.2	29.9	29.8	36.1	51.6	47.6	-	40.1	46.0	40.9
38		7.3	11.1	9.2	10.4	18.7	26.9	-	13.7	21.5	25.0
39		1.5	3.4	3.7	2.5	0.6	4.7	-	3.7	6.4	9.1
40 & Longer		0.7	1.1	0.5	0.3	*	0.5	-	0.4	7.7	6.4
Average Staple		35.99	36.23	36.23	36.39	36.81	37.11	-	36.65	37.60	37.57
Average Length		1.12	1.13	1.13	1.13	1.15	1.16	-	1.14	1.18	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE

For The Week Ending Jan 08, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	13.2	5.8	1.2	0.6	*	*	4.9	2.0	1.1	1.4
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	1.5	0.3	-	0.1	-	*	*	0.4
Grass - Level 2	-	-	-	*	-	-	-	-	-	-
Prep - Level 1	*	*	-	*	-	*	-	*	-	-
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	-	*	1.2	1.5	3.9	0.8	*	0.1
Seed Coat - Level 2	*	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	*	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	*	*	-	*	-	*	-	*	-	*
Other - Level 2	*	*	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	0.1	-	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	*	*	-	*	-	-	-	-	*	*
23	*	*	-	*	-	-	-	-	0.1	*
24	*	*	-	*	-	*	*	*	0.3	0.2
25	0.1	0.1	-	*	-	*	0.1	*	1.4	0.7
26	0.7	0.7	-	0.2	-	0.1	2.2	0.4	5.9	2.3
27	2.6	2.7	0.5	1.2	-	0.5	11.1	2.9	16.7	6.5
28	8.3	8.0	2.6	5.2	*	3.9	22.7	12.5	23.9	12.9
29	16.7	14.8	11.3	14.8	1.5	15.5	28.8	30.5	23.7	19.3
30	20.9	17.4	13.8	21.8	9.4	28.7	20.5	30.4	14.1	22.3
31	19.9	16.9	13.0	17.7	20.3	26.9	9.5	15.4	8.1	18.8
32	14.9	14.3	22.2	12.4	22.7	15.7	3.6	5.8	3.4	10.3
33	8.4	11.3	22.1	11.5	17.5	6.2	1.0	1.6	1.7	4.1
34	3.8	7.6	9.9	9.7	13.8	2.1	0.3	0.3	0.4	1.5
35	1.5	3.9	3.5	4.0	9.4	0.5	0.1	0.1	0.1	0.6
36	0.8	1.3	0.9	1.1	3.9	0.1	*	*	*	0.2
37	1.1	0.7	0.2	0.2	1.2	*	-	*	*	*
38	0.1	0.2	*	*	0.2	*	-	-	-	*
39	*	*	-	*	*	*	-	-	-	-
40 & Above	0.1	*	-	-	*	*	-	-	-	-
Average	31.13	31.47	32.14	31.59	32.97	31.08	29.48	30.12	29.12	30.28
Mike										
2.4 & Below	*	*	-	-	-	-	-	-	*	*
2.5	0.4	0.1	-	*	-	-	-	*	0.3	0.1
2.6	0.5	0.2	-	*	-	-	-	-	0.5	0.2
2.7	0.6	0.2	-	*	-	-	-	*	0.6	0.2
2.8	0.4	0.3	-	*	-	-	-	*	0.9	0.3
2.9	0.4	0.4	-	*	-	-	-	*	1.0	0.5
3.0	0.5	0.5	-	0.1	-	-	*	*	1.4	0.8
3.1	0.9	0.7	-	0.1	-	-	*	*	1.6	0.9
3.2	1.2	0.9	-	0.3	-	*	*	0.1	1.9	1.1
3.3	1.8	1.3	-	0.5	-	*	0.2	0.2	2.8	1.5
3.4	2.7	1.7	-	0.9	-	*	0.3	0.3	3.9	1.9
3.5	3.2	2.3	0.1	1.3	-	*	0.6	0.5	3.6	2.4
3.6	4.5	3.4	0.3	1.8	*	0.1	1.6	0.9	3.1	3.0
3.7	5.0	4.4	0.4	2.7	0.3	0.1	3.1	1.7	3.8	3.7
3.8	5.9	5.5	1.3	4.3	0.5	0.1	4.4	2.6	5.0	4.6
3.9	6.8	7.1	2.6	6.7	0.7	0.2	7.7	4.1	6.4	5.5
4.0	9.0	8.6	2.6	9.0	0.8	0.4	8.3	5.7	5.7	6.2
4.1	11.1	10.3	5.9	11.0	1.1	0.6	9.6	7.7	6.6	7.0
4.2	10.4	10.8	13.7	12.7	1.6	1.0	10.9	9.8	7.7	8.1
4.3	10.1	10.7	26.4	12.9	2.5	1.7	13.2	11.6	8.5	8.7
4.4	9.0	9.6	26.6	11.3	5.1	2.8	12.8	11.9	7.9	9.2
4.5	6.8	7.8	14.1	8.9	5.6	4.0	9.0	10.8	7.1	9.0
4.6	4.2	5.8	4.2	6.0	6.9	6.5	7.5	9.4	6.0	8.3
4.7	2.6	3.6	0.7	3.7	8.1	9.6	5.0	7.7	5.2	6.7
4.8	1.3	2.2	0.7	2.3	9.5	13.4	2.5	5.6	2.7	4.7
4.9	0.5	1.0	0.2	1.3	13.5	16.0	1.3	3.9	2.8	2.8
5.0	0.1	0.5	0.2	0.8	15.8	16.2	1.1	2.6	1.9	1.4
5.1	*	0.2	-	0.4	13.1	12.9	0.7	1.4	1.0	0.6
5.2	-	0.1	*	0.3	9.9	8.3	0.2	0.7	0.1	0.3
5.3	-	*	-	0.2	3.7	4.1	*	0.3	*	0.1
5.4	-	-	-	0.1	0.9	1.5	-	0.1	*	*
5.5 & Above	-	*	-	0.2	0.2	0.5	-	*	-	*
Average	4.04	4.13	4.32	4.23	4.84	4.88	4.26	4.38	4.08	4.20

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE

For The Week Ending Jan 08, 2026

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	16.3	6.4	6.1	1.2	*	*	-	1.2	0.3	0.2
Bark - Level 2	*	*	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	0.1	0.1	0.1	*	*	-	0.1	1.2	0.5
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	*	*	*	*	-	*	-	-	*	*
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	1.2	0.2	0.3	0.3	-	0.1	-	2.9	-	*
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	*
Spindle Twist - Level 2	-	*	-	-	-	-	-	-	-	-
Other - Level 1	*	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	0.1	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	*	*	-	-	-	*	-	-	-	-
23	*	*	*	*	-	*	-	-	-	-
24	0.1	0.1	*	*	*	*	-	-	*	*
25	0.3	0.2	0.2	0.1	*	*	-	*	0.2	0.1
26	1.1	0.7	1.6	0.5	*	*	-	0.1	0.8	0.4
27	3.6	2.5	7.4	2.8	0.1	0.2	-	1.7	2.2	1.7
28	10.2	6.8	17.6	10.0	1.6	1.8	-	6.6	10.1	7.1
29	19.4	14.0	22.7	20.4	19.1	12.4	-	18.0	25.0	14.4
30	23.7	19.8	21.0	25.4	47.7	36.0	-	30.0	24.7	19.9
31	17.9	20.0	15.6	20.4	22.2	32.6	-	19.9	17.0	18.5
32	11.9	15.5	9.6	11.8	7.5	12.2	-	12.6	10.4	12.4
33	6.7	10.2	3.2	5.5	1.8	3.7	-	6.1	5.0	8.4
34	3.0	5.9	0.9	2.2	0.1	0.9	-	3.1	1.7	7.2
35	1.2	2.7	0.2	0.7	*	0.1	-	1.6	1.6	5.6
36	0.5	1.1	0.1	0.2	-	*	-	0.2	0.9	3.1
37	0.2	0.4	*	*	-	*	-	*	0.2	1.0
38	0.1	0.2	*	*	-	*	-	*	0.1	0.1
39	*	*	-	*	-	-	-	-	*	*
40 & Above	-	-	*	*	-	-	-	-	*	*
Average	30.72	31.36	30.07	30.68	30.65	31.01	-	30.93	30.65	31.61
Mike										
2.4 & Below	0.1	*	-	-	-	-	-	-	-	-
2.5	0.1	*	-	*	-	-	-	-	-	-
2.6	0.2	0.1	*	*	-	-	-	*	*	*
2.7	0.4	0.2	*	*	-	*	-	*	*	*
2.8	0.4	0.3	*	*	-	*	-	*	0.6	0.1
2.9	0.6	0.6	0.1	*	-	*	-	*	0.7	0.2
3.0	1.2	0.9	0.1	*	*	*	-	*	0.7	0.2
3.1	1.9	1.2	0.1	*	0.1	*	-	*	0.8	0.5
3.2	2.6	1.8	0.3	0.1	*	*	-	*	0.6	0.7
3.3	2.8	2.3	0.5	0.1	0.1	*	-	0.1	0.3	0.5
3.4	3.6	3.0	1.1	0.3	0.1	0.1	-	0.1	0.3	0.6
3.5	4.0	3.7	1.6	0.6	0.1	0.1	-	0.2	0.8	1.1
3.6	4.5	4.4	2.5	1.1	0.1	0.2	-	0.4	2.0	1.5
3.7	5.0	5.0	4.3	1.8	0.4	0.4	-	0.5	2.3	2.4
3.8	4.7	5.6	5.4	2.6	1.0	0.6	-	0.7	2.7	3.3
3.9	5.4	6.1	6.6	3.8	1.6	1.0	-	1.1	4.0	4.3
4.0	5.9	6.6	8.9	5.4	2.9	1.7	-	1.8	7.9	5.5
4.1	6.1	6.9	9.5	7.3	5.1	2.6	-	3.4	11.7	7.1
4.2	6.3	7.4	9.3	8.9	8.2	4.0	-	4.4	13.9	8.8
4.3	7.1	7.7	10.3	10.0	7.7	5.7	-	5.5	12.0	8.7
4.4	7.3	7.8	10.5	10.3	9.2	8.1	-	6.6	7.2	8.6
4.5	6.9	7.5	8.1	10.0	12.6	10.9	-	8.7	7.2	10.2
4.6	6.7	6.7	7.5	9.3	13.7	13.9	-	9.7	4.7	9.8
4.7	5.1	5.4	6.1	8.4	13.3	15.3	-	10.6	4.0	8.2
4.8	4.4	3.8	3.2	6.7	8.4	13.9	-	11.5	3.8	6.3
4.9	3.2	2.4	1.8	5.1	6.4	10.1	-	10.7	5.5	4.7
5.0	2.0	1.3	1.1	3.6	4.6	6.4	-	8.5	3.2	3.1
5.1	0.9	0.7	0.5	2.3	2.9	3.1	-	7.1	1.4	1.7
5.2	0.3	0.4	0.2	1.3	1.2	1.2	-	4.1	0.9	1.0
5.3	0.2	0.2	0.2	0.6	0.3	0.4	-	2.2	0.6	0.6
5.4	0.1	0.1	0.1	0.3	*	0.1	-	1.1	*	0.3
5.5 & Above	0.1	0.1	*	0.1	*	*	-	1.1	*	0.2
Average	4.10	4.12	4.23	4.43	4.53	4.62	-	4.68	4.28	4.37

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE

For The Week Ending Jan 08, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	*	*	-	-	-	-	-	-	*	*
2.5 - 2.6	0.9	0.3	-	*	-	-	-	*	0.7	0.3
2.7 - 2.9	1.4	0.9	-	0.1	-	-	-	*	2.4	1.1
3.0 - 3.2	2.6	2.1	-	0.5	-	*	0.1	0.2	4.9	2.8
3.3 - 3.4	4.5	3.0	-	1.4	-	*	0.5	0.5	6.7	3.4
3.5 - 3.6	7.6	5.7	0.4	3.1	*	0.1	2.2	1.5	6.6	5.4
3.7 - 4.2	48.3	46.6	26.6	46.5	5.1	2.5	44.0	31.6	35.3	35.1
4.3 - 4.9	34.6	40.6	72.9	46.5	51.1	54.0	51.2	61.1	40.2	49.5
5.0 - 5.2	0.2	0.8	0.2	1.5	38.9	37.3	2.0	4.7	3.0	2.3
5.3 & Above	-	*	-	0.5	4.9	6.1	*	0.4	*	0.2
Average	4.04	4.13	4.32	4.23	4.84	4.88	4.26	4.38	4.08	4.20
Leaf										
1 - 2	52.6	61.4	57.8	24.9	*	3.8	5.7	8.4	85.1	86.4
3	29.9	25.9	26.7	49.6	4.1	37.9	47.8	52.7	11.8	11.9
4	10.3	7.8	8.2	21.1	44.8	45.4	38.4	33.1	1.8	1.4
5	3.9	3.0	5.4	4.0	45.6	11.8	7.7	5.3	1.0	0.3
6	2.0	1.3	1.4	0.5	5.5	1.0	0.5	0.4	0.2	0.1
7	1.0	0.4	0.5	0.1	0.1	*	*	*	*	*
8	0.3	0.1	-	*	-	-	-	*	-	-
Average	2.63	2.40	2.62	3.03	4.53	3.68	3.50	3.37	1.86	1.74
HVI Trash 1/										
00	*	*	-	*	-	-	-	-	0.6	0.7
01	24.3	31.3	14.2	5.2	-	0.3	0.2	0.6	55.9	60.1
02	31.9	33.4	42.8	22.5	0.1	4.6	7.7	10.2	33.4	29.0
03	17.4	15.4	19.7	27.8	0.9	15.0	21.8	24.7	6.2	7.0
04	9.6	7.7	9.2	20.3	6.1	23.1	25.9	26.2	1.7	2.0
05	5.4	4.2	5.7	12.1	16.3	22.1	20.3	18.7	0.9	0.7
06	3.2	2.4	3.4	6.5	25.3	15.8	12.8	10.6	0.6	0.3
07	2.1	1.6	1.8	3.1	23.6	9.7	6.4	5.1	0.5	0.1
08	1.4	1.1	1.2	1.4	14.9	5.1	3.1	2.2	0.2	0.1
09	1.1	0.8	0.6	0.6	7.6	2.5	1.2	0.9	0.1	*
10	0.8	0.6	0.4	0.3	3.7	1.1	0.4	0.4	*	*
11	0.7	0.4	0.4	0.1	1.1	0.5	0.2	0.1	*	*
12	0.6	0.3	0.2	0.1	0.4	0.2	0.1	0.1	*	*
13	0.5	0.3	0.2	*	0.1	0.1	*	*	-	*
14	0.3	0.2	0.1	*	-	*	-	*	-	*
15	0.2	0.1	0.1	*	-	*	*	*	-	-
16	0.2	0.1	-	*	-	-	-	*	-	*
17	0.1	0.1	-	*	-	-	-	*	-	*
18 & Above	0.2	0.1	-	*	-	-	-	*	-	-
Average	0.31	0.26	0.29	0.36	0.67	0.50	0.45	0.43	0.16	0.15
UNIFORMITY 2/										
74 & Below	*	*	-	*	-	-	-	*	*	*
75	*	0.1	-	*	-	-	-	*	0.1	0.1
76	0.2	0.2	-	*	-	*	*	*	0.4	0.5
77	0.7	0.7	0.1	0.1	-	*	0.2	*	2.2	2.4
78	2.7	2.9	0.5	0.7	*	0.2	1.5	0.5	10.4	10.2
79	13.0	12.3	1.9	3.7	0.5	1.0	8.3	2.9	23.7	25.2
80	29.4	27.6	8.1	13.3	4.4	7.0	21.8	11.8	39.7	35.3
81	32.5	29.7	34.8	30.0	18.2	28.3	35.5	28.6	17.8	21.4
82	15.8	17.5	43.7	31.2	32.4	37.9	26.1	35.3	5.1	4.4
83	4.9	7.2	10.3	16.2	28.0	20.4	5.9	18.4	0.5	0.5
84	0.7	1.7	0.5	4.3	13.0	5.0	0.6	2.4	*	*
85 & Above	0.1	0.1	-	0.4	3.6	0.2	*	0.2	-	*
Average	81.05	81.18	81.98	82.00	82.81	82.30	81.42	82.06	80.21	80.21
Tenderable 3/	74.5	83.8	92.4	88.1	45.5	53.1	87.5	90.5	77.4	84.9
SAMPLES CLASSED										
Week	92,244		4,688		7,257		29,323		34,042	
Season	850,586		1,510,711		943,188		1,078,314		490,119	

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 08, 2026

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	0.1	*	-	-	-	-	-	-	-	-
2.5 - 2.6	0.4	0.2	*	*	-	-	-	*	*	*
2.7 - 2.9	1.4	1.1	0.1	*	-	*	-	*	1.4	0.3
3.0 - 3.2	5.7	3.8	0.6	0.1	0.1	*	-	0.1	2.1	1.3
3.3 - 3.4	6.4	5.3	1.5	0.4	0.1	0.1	-	0.2	0.7	1.1
3.5 - 3.6	8.5	8.1	4.1	1.6	0.2	0.3	-	0.5	2.9	2.7
3.7 - 4.2	33.4	37.5	44.1	29.8	19.3	10.3	-	11.9	42.4	31.5
4.3 - 4.9	40.6	41.2	47.4	60.0	71.2	78.0	-	63.3	44.5	56.4
5.0 - 5.2	3.2	2.4	1.8	7.1	8.7	10.7	-	19.6	5.5	5.7
5.3 & Above	0.4	0.3	0.4	1.0	0.4	0.6	-	4.4	0.7	1.1
Average	4.10	4.12	4.23	4.43	4.53	4.62	-	4.68	4.28	4.37
Leaf										
1 - 2	59.3	68.9	12.8	15.3	5.5	5.8	-	12.8	24.5	41.4
3	32.1	25.8	50.6	57.8	55.5	48.5	-	49.1	44.4	36.0
4	6.0	4.4	30.4	23.7	33.0	37.1	-	30.4	22.4	15.6
5	1.9	0.8	5.7	3.0	5.6	7.7	-	6.8	5.9	5.4
6	0.6	0.2	0.5	0.2	0.3	0.8	-	1.0	2.2	1.4
7	0.1	*	*	*	*	0.1	-	-	0.5	0.2
8	*	*	*	*	-	-	-	-	*	*
Average	2.44	2.20	3.30	3.15	3.40	3.49	-	3.34	3.15	2.83
HVI Trash 1/										
00	*	*	-	-	-	*	-	-	-	*
01	23.8	33.9	1.1	1.7	0.1	0.5	-	1.6	7.6	15.8
02	44.0	41.2	16.4	19.8	7.8	7.2	-	14.1	21.4	31.2
03	18.7	15.4	26.2	31.3	26.1	21.1	-	24.2	23.7	20.4
04	6.7	5.4	23.7	23.6	29.1	26.2	-	23.3	19.0	12.9
05	2.8	2.1	15.9	12.9	19.7	20.3	-	16.3	12.0	7.8
06	1.5	0.9	8.7	6.1	10.6	12.2	-	9.7	6.7	4.8
07	0.9	0.4	4.2	2.7	4.5	6.5	-	5.3	3.9	3.0
08	0.6	0.2	2.0	1.1	1.5	3.2	-	2.7	2.4	1.8
09	0.4	0.1	0.9	0.5	0.5	1.5	-	1.4	1.5	1.1
10	0.2	0.1	0.4	0.2	0.1	0.7	-	0.8	0.8	0.6
11	0.1	*	0.2	0.1	0.1	0.3	-	0.4	0.5	0.3
12	0.1	*	0.1	*	*	0.1	-	0.2	0.2	0.1
13	*	*	*	*	*	0.1	-	0.1	0.1	0.1
14	*	*	*	*	-	*	-	*	0.1	*
15	*	*	*	*	*	*	-	-	*	*
16	*	*	*	*	-	-	-	-	*	*
17	*	*	*	*	-	-	-	-	*	*
18 & Above	*	*	*	*	-	-	-	-	*	*
Average	0.24	0.21	0.40	0.37	0.42	0.46	-	0.42	0.38	0.32
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	-	-	-	-
75	0.1	*	-	*	-	-	-	-	-	-
76	0.4	0.2	*	*	-	*	-	-	-	*
77	1.7	1.0	0.2	0.1	*	*	-	-	0.1	*
78	6.5	4.2	1.1	0.7	0.1	0.1	-	0.2	0.4	0.5
79	20.5	13.7	7.0	4.8	0.3	0.5	-	1.7	3.8	3.2
80	33.6	29.8	21.5	19.9	6.5	3.9	-	10.3	24.3	14.8
81	26.0	32.3	35.0	36.5	33.2	20.8	-	31.9	33.9	31.6
82	9.4	15.1	26.9	28.2	44.5	45.6	-	37.8	27.7	34.9
83	1.6	3.2	7.6	8.4	14.4	26.2	-	16.0	8.5	12.4
84	0.2	0.4	0.8	1.2	0.9	2.7	-	2.1	1.2	2.3
85 & Above	0.1	0.1	0.1	0.1	*	0.2	-	0.1	0.2	0.2
Average	80.55	80.93	81.50	81.62	82.13	82.47	-	82.07	81.61	81.89
Tenderable 3/	67.5	80.0	86.3	88.6	86.1	83.2	-	69.8	84.9	85.5
SAMPLES CLASSED										
Week	139,949		94,106		27,963		-		27,345	
Season		2,200,651		2,064,118		2,272,040		278,491		228,461

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE

For The Week Ending Jan 08, 2026

Color Grade	Leaf	VISALIA			Quality Designation	VISALIA	
		Week	Season			Week	Season
01	1	6.5	6.1		MIKE	-	-
	2	10.0	7.5		2.4 & Below	-	-
	3	0.1	0.2		2.5 - 2.6	-	-
	4	-	-		2.7 - 2.9	0.4	0.2
	5	-	-		3.0 - 3.2	0.9	1.7
	6	-	-		3.3 - 3.4	1.0	2.9
	7	-	-		3.5 - 3.6	3.6	8.7
Total -----		16.6	13.8		3.7 - 4.2	83.2	82.8
02	1	4.2	6.5		4.3 - 4.9	11.0	3.7
	2	29.7	35.0		5.0 - 5.2	*	*
	3	7.4	8.5		5.3 & Above	-	-
	4	0.1	0.2		Average	3.97	3.88
	5	-	*		ALL RANGE MIKE		
	6	-	-		2.4 & Below	-	-
	7	-	-		2.5	-	-
Total -----		41.4	50.2		2.6	-	-
03	1	0.5	0.5		2.7	-	*
	2	15.4	13.0		2.8	*	*
	3	18.6	16.2		2.9	0.3	0.1
	4	1.8	1.8		3.0	0.1	0.3
	5	*	*		3.1	0.4	0.6
	6	-	*		3.2	0.4	0.8
	7	-	-		3.3	0.3	1.1
Total -----		36.3	31.6		3.4	0.6	1.9
04	1	*	*		3.5	0.8	3.1
	2	0.8	0.6		3.6	2.8	5.6
	3	1.8	2.1		3.7	6.7	9.9
	4	0.8	0.9		3.8	15.0	15.6
	5	*	0.1		3.9	18.9	20.7
	6	-	*		4.0	17.9	19.0
	7	-	-		4.1	14.1	11.7
Total -----		3.5	3.7		4.2	10.6	5.9
05	1	-	*		4.3	6.3	2.4
	2	0.2	0.1		4.4	3.2	0.9
	3	0.6	0.2		4.5	1.2	0.3
	4	0.3	0.2		4.6	0.2	0.1
	5	*	*		4.7	*	*
	6	*	*		4.8	*	*
	7	-	-		4.9	*	*
Total -----		1.2	0.6		5.0	-	-
06	1	-	-		5.1	*	*
	2	0.1	*		5.2	-	-
	3	0.5	*		5.3 & Above	-	-
	4	0.2	*		Average	3.97	3.88
	5	*	*		STRENGTH 1/		
	6	*	*		36 & Below	0.4	2.9
	7	-	-		37	4.4	5.3
Total -----		0.8	0.1		38	5.4	4.1
07	1	-	-		39	2.2	1.7
	2	-	-		40	1.1	2.0
	3	*	*		41	1.6	6.0
	4	0.1	*		42	4.9	11.4
	5	*	*		43	8.8	16.9
	6	-	*		44	13.2	19.8
	7	-	-		45	21.0	16.1
Total -----		0.1	*		46	19.6	8.7
STAPLE					47	10.0	3.5
44 & Shorter		4.6	2.9		48 & Above	7.5	1.5
46		10.2	11.8		Average	44.64	43.35
48		49.1	46.4		UNIFORMITY		
50		35.5	37.1		83 & Below	4.6	1.6
52 & Longer		0.7	1.8		84	18.0	12.4
Average Staple		48.35	48.46		85	40.6	34.8
Average Length		1.41	1.41		86	33.1	45.3
EXTRANEIOUS MATTER					87	3.5	5.4
Bark		*	*		88 & Above	0.2	0.4
Grass		0.1	0.4		Average	85.58	85.86
Spindle Twist		0.4	0.1		Samples Classed		
Preparation		-	*		Week	19,468	
All Other		*	*		Season		321,583

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.