



State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	11	82.5	72.3	9,925	21	90.2	78.2	524,405
AR	6	67.7	45.9	19,036	26	69.9	42.0	1,358,912
AZ	8	84.0	64.3	16,444	9	87.0	67.8	138,188
CA	3	92.4	87.7	8,354	10	84.4	72.1	62,414
FL	2	81.3	62.9	2,233	4	91.0	76.3	90,067
GA	44	86.8	76.3	82,279	53	88.3	74.0	1,630,242
KS	3	28.6	20.5	12,749	3	41.4	31.6	98,639
LA*	-	-	-	-	14	71.5	47.6	223,299
MO	4	90.0	80.3	15,774	16	86.5	64.7	655,757
MS*	-	-	-	-	30	63.7	36.5	706,510
NC	14	91.2	85.8	13,526	26	90.7	78.7	641,447
NM	2	48.2	39.8	794	2	89.6	80.5	9,067
OK	10	90.0	79.2	35,495	10	93.4	81.3	335,320
SC	10	85.0	76.7	14,124	10	86.3	73.0	264,730
TN	-	-	-	-	17	82.3	63.4	340,307
TX	89	71.0	47.6	224,910	144	83.4	63.4	4,665,238
VA	3	77.9	59.5	1,673	4	96.2	90.5	172,137
United States	214	76.8	59.5	457,416	399	82.3	63.1	11,916,679
AMERICAN PIMA								
AZ	2			1,025	2			9,414
CA	5			16,450	10			266,849
NM*	-			-	-			-
TX	4			1,765	5			26,082
United States	12			19,468	18			321,583
United States all cotton	224			476,884	408			12,238,262

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 08, 2026

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	1.5	2.3	-	0.1	13.7	21.2	1.1	23.4	-	1.7	2.5	1.4
	3	0.7	1.3	-	0.1	1.2	4.6	*	9.3	-	0.5	2.3	1.0
	4	*	*	-	*	0.1	0.3	-	0.6	-	*	0.1	*
	5	-	*	-	-	-	*	-	*	-	-	*	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	2.2	3.6	-	0.2	15.0	26.1	1.1	33.2	-	2.2	4.9	2.4
31	1 - 2	3.2	9.6	0.6	1.1	3.5	10.6	16.1	16.2	0.5	3.1	7.4	7.8
	3	8.0	28.6	2.8	9.0	5.4	10.9	15.3	12.8	3.5	12.5	22.4	21.7
	4	1.1	7.3	1.2	3.4	0.9	2.2	0.9	5.0	0.5	2.8	7.2	4.2
	5	*	0.5	0.2	0.1	0.1	0.2	-	1.0	-	0.1	0.5	0.2
	6	-	*	-	*	-	*	-	0.1	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	12.3	46.0	4.8	13.7	9.9	23.8	32.3	35.0	4.5	18.4	37.6	33.8
41	1 - 2	3.5	3.2	1.5	0.8	3.4	2.2	10.0	4.5	0.9	2.8	3.1	5.4
	3	18.9	22.6	30.1	26.2	26.4	13.3	40.3	13.8	13.4	37.0	20.8	32.9
	4	12.7	15.8	25.8	35.3	20.4	12.1	11.0	4.7	35.6	28.9	14.7	16.6
	5	1.6	2.8	13.9	8.4	3.5	3.5	0.7	2.1	11.2	4.0	2.7	2.1
	6	0.1	0.2	0.9	0.7	0.3	0.4	-	0.5	0.7	0.2	0.2	0.1
	7	-	*	*	*	-	*	-	-	*	*	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	36.8	44.7	72.2	71.3	53.9	31.6	62.0	25.6	61.8	72.9	41.5	57.0
51	1 - 2	1.1	0.2	0.3	*	0.1	0.1	*	0.1	0.4	0.1	0.4	0.2
	3	17.6	1.5	5.4	2.3	2.0	1.1	0.6	0.4	10.5	1.7	4.6	2.0
	4	19.7	1.5	6.3	4.8	6.1	2.8	0.5	0.2	16.3	2.3	5.5	2.1
	5	3.5	0.3	3.1	2.3	4.8	2.4	0.2	*	2.6	0.6	1.4	0.5
	6	0.2	*	0.3	0.4	3.1	1.1	*	*	0.6	0.1	0.2	0.1
	7	-	*	*	0.1	0.8	0.3	-	-	0.1	*	*	*
	8	-	*	-	-	0.1	*	-	-	-	-	*	*
Total	----	42.0	3.5	15.3	9.9	16.8	7.7	1.3	0.8	30.4	4.8	12.1	4.8
61	1 - 2	*	*	-	*	-	-	-	-	-	-	-	*
	3	0.6	*	-	*	-	-	-	-	0.2	*	*	*
	4	0.5	*	-	*	*	*	-	-	0.3	*	0.1	*
	5	0.1	*	-	*	*	*	-	-	0.1	*	*	*
	6	-	*	-	*	*	*	-	-	*	*	*	*
	7	-	-	-	-	*	*	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	*
Total	----	1.2	0.1	-	*	0.1	*	-	-	0.6	*	0.2	*
71	1 - 2	-	-	-	*	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	*	-	-	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	-	-	-	-	-
12 & 22	1 - 2	-	0.1	-	*	1.6	4.2	-	0.2	-	*	0.1	*
	3	*	*	-	*	0.6	2.0	-	0.3	-	*	0.4	*
	4	-	*	-	*	0.3	0.3	-	*	-	-	0.1	*
	5	-	-	-	*	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	0.1	-	*	2.5	6.5	-	0.6	-	*	0.6	0.1
32	1 - 2	*	0.1	-	*	*	0.1	0.6	0.4	-	*	*	*
	3	0.1	0.4	-	0.1	0.1	0.5	0.6	0.8	-	0.2	0.3	0.2
	4	0.1	0.1	*	0.1	*	0.4	*	0.7	-	*	0.5	0.1
	5	*	*	*	*	*	0.1	-	0.5	-	-	0.2	*
	6	-	*	-	*	-	*	-	0.1	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.2	0.6	*	0.2	0.1	1.1	1.1	2.5	-	0.3	1.0	0.4
42	1 - 2	0.1	*	-	*	*	*	0.1	0.1	-	0.1	*	*
	3	0.2	0.4	0.2	1.0	0.1	0.5	1.4	0.8	0.2	0.7	0.4	0.6
	4	0.7	0.5	1.3	1.5	0.2	0.6	0.4	0.4	0.1	0.4	0.5	0.4
	5	0.2	0.1	4.3	0.6	0.1	0.3	*	0.4	-	*	0.2	0.1
	6	*	*	0.8	0.1	*	0.1	-	0.2	-	*	*	*
	7	-	*	*	*	*	*	-	-	-	*	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.1	1.1	6.6	3.2	0.4	1.5	1.9	1.8	0.3	1.2	1.2	1.1

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 08, 2026

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	*	-	*	-	*	*	*	*	*
	3	0.8	*	*	0.3	0.1	0.1	*	0.1	1.2	0.1	0.1	*
	4	1.7	0.1	0.1	0.6	0.4	0.3	0.1	*	0.9	0.1	0.1	0.1
	5	1.0	0.1	0.5	0.3	0.5	0.3	*	*	*	*	0.1	*
	6	*	*	0.4	0.1	0.1	0.2	-	-	-	*	*	*
	7	-	*	*	*	*	0.1	-	-	-	*	*	*
	8	-	-	-	-	*	*	-	-	-	-	*	*
Total	----	3.6	0.2	1.0	1.3	1.1	1.0	0.1	0.2	2.1	0.2	0.3	0.2
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	*	-	-	-	*	0.1	*	*	*
	4	-	*	-	*	-	*	-	*	*	*	*	*
	5	*	*	-	*	*	*	-	-	-	*	*	*
	6	*	*	-	*	*	*	-	-	-	-	-	*
	7	-	-	-	*	*	*	-	-	-	-	*	*
	8	-	-	-	-	*	*	-	-	-	-	*	*
Total	----	*	*	-	*	*	*	-	*	0.1	*	*	*
13 & 23	1 - 2	-	*	-	-	*	0.2	-	*	-	-	*	*
	3	-	*	-	-	*	0.1	-	*	-	-	*	*
	4	-	*	-	-	-	*	-	-	-	-	*	*
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	*	0.3	-	*	-	-	*	*
33	1 - 2	-	*	-	-	-	*	*	*	-	-	*	*
	3	*	*	-	*	-	*	-	*	-	-	*	*
	4	0.1	*	-	*	*	*	-	*	-	-	*	*
	5	-	*	-	*	-	*	-	*	-	-	*	*
	6	-	*	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	*	-	*	*	0.1	*	0.1	-	-	0.1	*
43	1 - 2	-	-	-	*	-	-	-	*	-	-	*	*
	3	*	*	-	*	*	*	*	0.1	-	*	0.1	*
	4	*	*	-	*	-	*	*	0.1	-	*	0.2	*
	5	*	*	*	*	-	*	*	*	-	-	0.1	*
	6	-	*	*	*	-	*	-	*	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	*	*	0.1	*	0.1	0.1	0.2	-	*	0.3	0.1
53	1 - 2	-	*	-	-	*	*	-	-	-	-	-	-
	3	0.1	*	-	*	-	-	-	*	-	*	*	*
	4	0.1	*	*	*	-	*	-	*	*	*	*	*
	5	*	*	-	*	-	*	-	*	-	*	*	*
	6	-	*	-	*	-	*	-	-	-	-	*	*
	7	-	-	-	*	-	*	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.3	*	*	*	*	*	-	*	*	*	0.1	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	-	-	-	-	-
24 - 54	1 - 8	-	*	-	*	*	*	-	*	-	-	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	*
31		-	*	-	*	-	*	-	-	-	*	*	*
32		*	*	-	*	*	*	-	-	0.1	*	0.2	0.1
33		1.1	0.5	*	0.1	0.1	*	-	*	1.6	0.2	1.5	0.8
34		13.6	3.4	2.3	0.3	1.0	0.5	*	0.3	6.5	2.4	6.5	4.7
35		22.9	11.7	6.4	2.7	3.4	2.9	1.6	2.7	3.4	12.4	18.3	15.9
36		29.7	24.3	16.3	13.8	14.7	12.7	18.4	16.7	41.5	29.2	29.3	31.2
37		22.0	41.6	46.8	50.7	42.8	45.2	60.1	42.4	44.2	35.5	30.3	34.8
38		8.2	14.8	19.5	26.8	26.8	28.3	16.6	23.2	2.4	15.3	9.5	9.7
39		2.3	3.2	5.7	5.1	9.1	8.7	3.0	13.0	0.2	4.4	3.9	2.4
40 & Longer		0.1	0.5	2.9	0.5	2.2	1.6	0.2	1.6	-	0.6	0.6	0.3
Average Staple		35.92	36.63	37.04	37.18	37.27	37.31	37.02	37.31	36.28	36.64	36.27	36.35
Average Length		1.12	1.14	1.16	1.16	1.16	1.17	1.15	1.16	1.13	1.14	1.13	1.13

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 08, 2026

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	0.8	6.0	-	4.5	-	*	-	2.0	0.2	0.4	28.3	46.9
	3	5.7	6.6	-	2.6	-	*	-	1.8	0.2	0.3	23.9	10.1
	4	2.8	1.4	-	*	-	*	-	*	-	*	6.4	1.0
	5	0.1	0.1	-	-	-	-	-	*	-	*	0.1	*
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	9.4	14.0	-	7.1	-	*	-	3.8	0.4	0.8	58.8	58.0
31	1 - 2	*	1.3	-	9.2	3.5	1.5	-	3.4	6.2	5.6	1.8	9.9
	3	3.6	9.5	-	36.6	11.6	8.9	-	20.3	19.6	20.0	11.0	18.0
	4	8.7	12.3	-	12.3	1.1	1.8	-	8.6	5.0	5.8	12.3	6.0
	5	2.6	3.6	-	0.8	*	*	-	0.6	0.4	0.3	4.3	0.8
	6	0.1	0.4	-	*	-	*	-	*	-	*	0.3	*
	7	-	*	-	-	-	-	-	-	-	-	0.1	*
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	15.0	27.1	-	58.9	16.1	12.2	-	32.9	31.3	31.7	29.7	34.8
41	1 - 2	*	*	-	0.5	2.9	2.3	-	0.9	2.2	3.1	-	*
	3	2.1	0.9	-	10.1	31.5	37.7	-	18.8	31.8	30.0	-	0.7
	4	7.0	4.4	-	16.2	20.3	27.0	-	26.1	22.8	24.8	0.3	1.0
	5	9.1	6.8	-	4.9	2.1	3.2	-	7.3	5.9	4.5	0.8	1.1
	6	4.7	3.8	-	0.3	0.1	0.1	-	0.6	0.5	0.3	0.4	0.7
	7	1.0	0.8	-	-	-	*	-	*	-	*	0.4	0.2
	8	0.1	0.1	-	-	-	-	-	-	-	*	-	-
Total	----	23.9	16.7	-	32.0	56.8	70.4	-	53.6	63.1	62.8	1.8	3.7
51	1 - 2	-	-	-	*	0.5	0.1	-	*	*	0.1	-	-
	3	-	-	-	*	7.8	4.4	-	1.1	1.0	0.8	-	-
	4	*	*	-	0.4	10.1	6.1	-	3.3	1.6	1.7	-	-
	5	0.4	0.1	-	0.3	1.6	1.4	-	1.5	1.2	0.8	-	*
	6	0.8	0.4	-	0.1	0.1	0.1	-	0.2	0.3	0.2	-	*
	7	0.7	0.5	-	-	*	*	-	*	*	*	-	-
	8	0.2	0.1	-	-	-	-	-	-	-	*	-	-
Total	----	2.2	1.2	-	0.7	20.1	12.1	-	6.1	4.1	3.7	-	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	*	*	-	*	-	*	-	-
	4	-	-	-	*	*	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	*	*	-	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	*	-	-	-	*	-	-
12 & 22	1 - 2	0.8	1.7	-	0.1	-	-	-	*	-	*	0.1	0.2
	3	5.6	4.4	-	*	-	*	-	*	*	*	0.4	0.1
	4	4.4	2.2	-	*	-	-	-	*	-	*	2.1	0.2
	5	0.2	0.2	-	*	-	-	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	11.0	8.5	-	0.1	-	*	-	*	*	*	2.6	0.5
32	1 - 2	0.1	0.1	-	0.1	-	*	-	*	0.1	*	0.4	0.7
	3	1.9	2.6	-	0.3	0.1	0.1	-	0.2	0.1	0.1	0.9	0.3
	4	4.9	5.2	-	0.2	*	*	-	0.1	0.2	0.1	1.4	0.6
	5	2.6	2.9	-	*	-	*	-	*	*	*	2.1	0.4
	6	0.8	0.6	-	*	-	-	-	*	-	-	1.1	0.1
	7	0.1	0.1	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-	-	-
Total	----	10.5	11.5	-	0.5	0.1	0.1	-	0.3	0.4	0.3	5.9	2.1
42	1 - 2	-	*	-	*	*	0.1	-	*	*	*	-	-
	3	0.1	0.8	-	0.1	0.9	1.4	-	0.6	0.2	0.3	-	*
	4	2.1	3.3	-	0.4	2.8	1.5	-	1.2	0.3	0.3	-	0.1
	5	5.5	5.2	-	0.1	0.3	0.4	-	0.5	0.1	0.1	0.1	*
	6	5.8	4.0	-	*	-	0.1	-	0.1	-	*	0.1	*
	7	3.3	1.4	-	-	-	*	-	*	-	*	-	-
	8	0.7	0.2	-	-	-	-	-	-	-	*	-	-
Total	----	17.6	15.0	-	0.6	4.0	3.4	-	2.4	0.6	0.7	0.3	0.2

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 08, 2026

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	-	-	*	-	*	-	*	-	-
	3	-	-	-	*	0.5	0.5	-	0.1	-	*	-	-
	4	-	*	-	*	1.9	0.8	-	0.2	*	*	-	-
	5	0.1	0.1	-	*	0.3	0.3	-	0.3	-	*	-	-
	6	0.3	0.3	-	*	*	*	-	0.1	-	*	-	-
	7	0.7	0.5	-	-	-	*	-	*	-	*	-	-
	8	0.7	0.3	-	-	-	-	-	-	-	*	-	-
Total	----	1.8	1.1	-	*	2.7	1.6	-	0.7	*	0.1	-	-
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	-	*	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	*	*	-	*	-	*	-	-
13 & 23	1 - 2	0.1	0.2	-	-	-	-	-	-	*	*	-	-
	3	1.7	0.9	-	-	-	-	-	-	*	*	0.1	*
	4	0.8	0.5	-	-	-	-	-	-	-	*	0.1	*
	5	*	0.1	-	-	-	-	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	2.7	1.7	-	-	-	-	-	-	*	*	0.3	*
33	1 - 2	-	*	-	-	-	*	-	*	*	*	0.1	*
	3	0.4	0.1	-	*	-	*	-	*	0.1	*	-	0.1
	4	1.4	0.4	-	*	*	*	-	*	*	*	0.3	0.3
	5	0.3	0.3	-	*	-	-	-	-	-	*	0.1	0.2
	6	0.1	0.1	-	-	-	-	-	-	-	*	-	*
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-	-	-
Total	----	2.2	1.0	-	*	*	*	-	*	0.1	*	0.5	0.7
43	1 - 2	-	-	-	*	-	*	-	-	-	*	-	-
	3	-	0.1	-	*	-	*	-	*	*	*	0.1	*
	4	0.1	0.3	-	*	*	*	-	*	*	*	-	-
	5	0.7	0.5	-	*	*	*	-	*	-	*	-	*
	6	1.4	0.6	-	-	-	*	-	*	-	*	-	*
	7	0.9	0.3	-	-	-	-	-	-	-	*	-	-
	8	0.4	0.1	-	-	-	-	-	-	-	*	-	-
Total	----	3.4	1.9	-	*	0.1	0.1	-	*	*	*	0.1	*
53	1 - 2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	*	-	-	*	*	-	*	-	*	-	-
	4	-	*	-	-	0.1	*	-	*	-	*	-	-
	5	-	*	-	-	0.1	*	-	*	*	*	-	-
	6	-	*	-	-	*	*	-	*	-	*	-	-
	7	0.1	0.1	-	-	-	-	-	*	-	*	-	-
	8	0.3	0.1	-	-	-	-	-	-	-	*	-	-
Total	----	0.3	0.2	-	-	0.1	*	-	*	*	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	-	-	*	-	-	-	-
24 - 54	1 - 8	*	0.1	-	-	-	*	-	-	*	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	*	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		-	*	-	-	-	-	-	*	-	*	-	-
32		-	*	-	-	-	*	-	*	*	*	-	-
33		*	0.2	-	0.1	*	*	-	0.2	1.1	0.1	-	-
34		0.7	1.1	-	1.1	0.1	0.2	-	2.1	6.7	1.4	0.1	2.3
35		5.6	4.3	-	10.0	3.4	1.8	-	11.5	21.9	8.1	3.7	10.2
36		24.3	12.5	-	26.9	25.8	10.4	-	27.7	35.9	24.1	23.7	13.9
37		41.9	28.9	-	42.1	48.2	48.6	-	36.4	28.4	49.1	62.1	32.6
38		19.9	34.0	-	15.0	21.5	33.6	-	15.0	5.2	14.3	10.1	33.6
39		6.7	16.9	-	4.4	1.0	5.0	-	5.4	0.7	2.7	0.3	6.5
40 & Longer		0.9	2.3	-	0.4	*	0.4	-	1.5	*	0.3	0.1	1.0
Average Staple		36.98	37.50	-	36.75	36.90	37.30	-	36.72	36.02	36.76	36.80	37.08
Average Length		1.15	1.17	-	1.15	1.15	1.17	-	1.15	1.12	1.15	1.15	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE For The Week Ending Jan 08, 2026											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	46.8	47.1	*	0.3	-	0.4	42.5	44.7	-	0.9
	3	5.8	7.7	0.3	0.4	-	0.1	11.1	13.5	-	1.3
	4	0.1	0.3	*	*	-	*	0.5	0.9	-	0.1
	5	-	*	-	-	-	*	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	52.7	55.1	0.3	0.8	-	0.5	54.1	59.1	-	2.2
31	1 - 2	20.7	13.4	1.1	2.3	-	6.9	6.5	3.5	1.0	8.7
	3	18.2	18.0	12.3	14.9	-	14.5	7.7	10.3	3.4	38.4
	4	2.0	3.6	8.3	5.3	-	3.2	2.1	4.2	6.4	8.2
	5	0.1	0.2	0.4	0.2	-	0.2	0.3	0.5	0.4	0.5
	6	*	*	-	*	-	*	*	*	-	*
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	41.0	35.2	22.1	22.7	-	24.8	16.6	18.5	11.2	55.7
41	1 - 2	*	0.3	1.4	2.0	-	7.7	0.3	0.2	4.6	1.7
	3	0.6	1.1	27.5	32.2	-	35.8	0.7	1.8	51.0	21.6
	4	1.2	1.1	35.3	31.5	-	14.2	0.6	1.8	26.6	15.6
	5	0.4	0.5	6.9	4.6	-	1.8	0.3	0.5	1.3	2.6
	6	*	0.1	0.2	0.1	-	0.1	0.1	0.1	-	0.1
	7	*	*	-	*	-	*	*	*	-	*
	8	-	-	-	-	-	-	*	*	-	-
Total	----	2.3	3.0	71.3	70.4	-	59.6	2.0	4.5	83.5	41.6
51	1 - 2	-	*	0.3	0.1	-	0.2	-	*	-	*
	3	-	*	1.7	1.8	-	2.4	*	0.1	0.8	*
	4	*	*	1.9	2.4	-	2.2	*	0.1	4.3	0.1
	5	*	*	0.7	0.7	-	0.5	*	*	0.2	*
	6	*	*	*	0.1	-	*	0.1	*	-	*
	7	-	*	-	*	-	*	*	*	-	*
	8	-	*	-	-	-	-	*	*	-	-
Total	----	*	*	4.5	5.1	-	5.3	0.1	0.3	5.3	0.2
61	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	*	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	*	*	*	-	-
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	*	-	-
12 & 22	1 - 2	1.3	2.3	-	-	-	*	8.9	6.7	-	-
	3	0.5	1.0	-	*	-	*	5.1	3.7	-	*
	4	*	0.1	-	-	-	*	0.5	0.6	-	*
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	1.8	3.4	-	*	-	*	14.6	11.0	-	*
32	1 - 2	0.3	0.3	-	*	-	0.2	1.6	0.5	-	*
	3	0.9	1.1	0.2	0.1	-	0.5	2.9	1.6	-	*
	4	0.3	0.5	0.4	0.1	-	0.1	1.3	1.2	-	*
	5	*	0.1	*	*	-	*	0.5	0.3	-	*
	6	*	*	-	*	-	-	0.1	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	1.6	2.0	0.6	0.1	-	0.8	6.5	3.7	-	0.1
42	1 - 2	*	*	-	*	-	0.9	*	*	-	*
	3	0.1	0.1	0.1	0.2	-	5.0	0.3	0.3	-	*
	4	0.1	0.2	0.7	0.4	-	1.5	0.4	0.5	-	*
	5	0.1	0.1	0.3	0.1	-	0.1	0.2	0.3	-	*
	6	*	*	*	*	-	*	0.1	0.1	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	0.3	0.4	1.0	0.7	-	7.5	1.1	1.2	-	0.1

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Jan 08, 2026											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	*	-	*	-	-
	3	-	-	-	*	-	0.7	-	*	-	-
	4	-	*	*	0.1	-	0.5	*	*	-	*
	5	-	*	-	*	-	0.1	*	*	-	*
	6	-	*	-	*	-	*	*	*	-	-
	7	*	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	*	*	*	0.1	-	1.3	*	0.1	-	*
62	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	-	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
Total	----	-	*	-	-	-	*	-	*	-	-
13 & 23	1 - 2	0.1	0.1	-	-	-	-	1.5	0.5	-	-
	3	*	0.1	-	-	-	-	1.2	0.4	-	*
	4	-	*	-	-	-	-	0.1	0.1	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	0.1	0.2	-	-	-	-	2.8	0.9	-	*
33	1 - 2	0.1	0.1	-	-	-	*	0.3	0.1	-	-
	3	0.1	0.2	-	*	-	*	0.7	0.2	-	*
	4	*	0.1	*	*	-	*	0.4	0.2	-	*
	5	*	*	-	*	-	-	0.2	*	-	*
	6	-	*	-	-	-	-	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	0.2	0.5	*	*	-	*	1.6	0.5	-	*
43	1 - 2	-	*	-	*	-	*	*	*	-	-
	3	*	*	*	*	-	*	*	*	-	*
	4	*	*	0.1	*	-	*	0.1	*	-	*
	5	*	*	*	*	-	*	0.1	*	-	*
	6	-	*	-	-	-	*	*	*	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	*	0.1	0.1	*	-	*	0.2	0.1	-	*
53	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	*	-	*	-	*	-	*	-	-
	4	-	*	-	*	-	*	*	*	-	-
	5	-	*	-	*	-	*	-	*	-	-
	6	-	*	-	-	-	-	-	*	-	-
	7	-	*	-	*	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
Total	----	-	*	-	*	-	*	*	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	*	-	-
24 - 54	1 - 8	*	0.1	-	*	-	-	0.2	0.1	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	*	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	*	-	-
30		-	-	-	-	-	-	-	*	-	-
31		-	*	-	-	-	-	0.1	0.1	-	-
32		-	*	*	*	-	*	0.7	0.5	-	*
33		0.1	0.3	1.7	0.2	-	0.1	4.0	2.5	-	*
34		0.8	1.8	10.0	1.9	-	2.6	13.8	7.6	0.2	0.6
35		5.8	6.4	15.9	9.6	-	9.5	24.9	14.6	2.0	5.5
36		15.8	13.2	37.0	34.0	-	30.9	25.8	21.7	57.6	22.9
37		33.5	26.9	27.9	41.4	-	44.3	21.8	32.8	35.8	55.3
38		21.2	19.8	5.3	9.9	-	11.3	6.5	14.6	2.6	12.9
39		13.5	18.9	2.1	2.6	-	1.3	1.2	4.4	1.8	2.6
40 & Longer		9.3	12.7	0.2	0.3	-	0.1	1.3	1.1	-	0.1
Average Staple		37.52	37.66	36.05	36.56	-	36.56	35.79	36.41	36.44	36.82
Average Length		1.17	1.18	1.12	1.14	-	1.14	1.12	1.14	1.14	1.15

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 08, 2026

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	6.8	0.5	*	*	0.1	0.1	0.3	0.1	11.7	1.5	5.9	1.3
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	0.1	*	0.1	0.5	0.1	2.8	1.3	0.3	0.1	0.1	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	*	-	-	*	*	-	-	*	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.2	0.1	0.5	1.0	-	*	-	-	0.6	0.3	0.3	0.3
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	-	-	-	-	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	-	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	-	-	-	-	-	-	-
23	-	-	-	*	-	-	-	-	-	-	*	*
24	-	*	*	*	*	*	-	*	-	-	*	*
25	-	*	*	*	0.3	0.1	*	*	-	*	0.2	0.1
26	0.1	0.1	-	*	1.1	0.4	0.6	0.4	*	*	1.8	0.6
27	2.9	1.2	*	0.2	2.0	1.9	3.1	1.6	0.9	0.4	8.1	3.2
28	24.5	7.7	0.4	1.9	6.4	7.0	19.4	8.7	8.2	3.3	17.1	10.6
29	27.6	21.6	13.8	11.7	18.6	14.0	43.2	16.7	10.4	13.1	22.5	20.9
30	20.4	29.4	32.2	34.5	27.9	21.5	20.5	17.5	12.8	26.8	21.3	25.1
31	11.7	21.8	24.7	33.3	22.0	21.7	10.1	13.1	42.9	27.4	15.3	19.6
32	10.4	11.3	11.2	13.3	13.6	15.1	1.9	5.0	23.1	16.9	9.1	11.4
33	2.0	4.7	6.8	3.8	4.9	9.1	*	4.7	1.6	7.3	3.4	5.4
34	0.2	1.7	5.3	1.0	1.3	5.7	*	9.0	0.1	3.8	1.0	2.2
35	0.1	0.4	3.6	0.2	0.9	2.2	0.9	12.3	*	0.9	0.2	0.8
36	*	0.1	1.5	*	0.9	0.9	0.1	8.0	-	0.1	0.1	0.2
37	-	*	0.5	*	0.1	0.4	-	2.5	-	*	*	0.1
38	-	*	0.1	*	0.1	*	-	0.3	-	-	*	*
39	-	-	*	*	*	*	-	0.1	-	-	-	*
40 & Above	-	-	-	-	*	*	-	0.1	-	-	*	*
Average	30.00	30.71	31.49	31.05	30.82	31.30	29.70	32.08	31.05	31.27	30.05	30.64
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	-	*	-	-	-	-	-	-	-	-	-	-
2.6	-	*	-	-	*	*	-	-	-	-	*	*
2.7	-	*	-	-	*	*	-	*	-	-	*	*
2.8	-	*	-	*	*	*	-	-	-	-	*	*
2.9	-	*	-	-	-	*	0.3	0.1	-	-	0.1	*
3.0	*	*	*	*	0.1	*	*	*	-	-	0.1	*
3.1	0.2	*	-	*	0.2	0.1	0.1	0.3	-	*	0.1	*
3.2	0.1	*	-	*	*	0.1	0.3	0.2	-	0.1	0.4	0.1
3.3	0.3	0.1	*	*	0.1	0.1	0.7	0.2	*	0.1	0.5	0.1
3.4	0.8	0.4	-	*	0.2	0.2	0.5	0.3	-	0.1	1.1	0.3
3.5	1.1	0.7	-	*	0.5	0.3	0.2	0.7	-	0.5	1.7	0.6
3.6	1.1	1.1	*	0.1	1.4	0.6	*	1.3	-	0.7	2.8	1.1
3.7	2.9	1.9	0.1	0.1	0.9	1.3	0.7	2.0	-	1.2	4.6	1.8
3.8	4.6	2.9	0.2	0.1	0.7	1.6	4.4	4.9	-	1.3	5.7	2.7
3.9	4.2	4.4	0.3	0.3	1.2	2.7	9.0	7.0	0.4	2.1	7.1	3.9
4.0	6.6	5.8	0.3	0.6	3.8	4.2	17.0	8.6	0.4	3.4	9.4	5.4
4.1	6.9	7.9	0.6	1.0	8.6	6.5	20.8	9.5	0.2	5.6	10.1	7.2
4.2	9.3	9.8	1.4	1.7	13.9	8.5	17.4	10.8	0.5	7.1	9.6	8.8
4.3	12.1	10.8	2.2	3.0	14.9	9.3	9.0	8.3	1.6	9.7	10.3	9.8
4.4	12.2	10.6	5.8	4.9	10.3	10.1	2.7	6.4	2.2	12.3	10.5	10.1
4.5	9.5	10.1	9.3	7.7	9.8	12.9	4.0	6.4	6.0	13.0	8.0	9.8
4.6	11.2	9.0	13.7	11.7	6.4	12.5	2.6	6.3	33.6	11.2	6.3	9.3
4.7	7.0	7.3	14.9	14.6	5.6	9.6	1.8	7.0	35.8	12.4	5.1	8.5
4.8	4.7	5.7	12.1	15.5	4.8	7.3	2.7	5.6	12.3	8.4	2.8	6.9
4.9	2.0	4.3	11.7	13.7	7.7	5.3	3.0	4.5	5.3	5.2	1.6	5.3
5.0	1.1	2.9	10.8	10.9	4.3	3.6	1.9	3.2	1.6	3.2	1.0	3.8
5.1	0.9	1.8	8.8	7.1	2.1	1.3	0.5	2.9	0.1	1.7	0.5	2.4
5.2	0.9	1.1	5.4	4.1	1.5	0.9	-	1.4	-	0.5	0.2	1.3
5.3	0.4	0.7	1.9	1.9	0.8	0.5	0.3	1.1	-	0.1	0.2	0.6
5.4	0.1	0.3	0.4	0.6	0.1	0.2	-	0.7	*	0.1	0.2	0.2
5.5 & Above	-	0.2	0.1	0.2	*	0.3	-	0.3	-	0.1	*	0.1
Average	4.33	4.39	4.77	4.76	4.44	4.46	4.18	4.35	4.66	4.48	4.21	4.43

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending Jan 08, 2026

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	39.2	27.8	-	0.1	-	*	-	*	3.4	1.6	4.4	0.8
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	0.1	-	*	-	*	-	*	-	*	0.3	0.6
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	-	-	*	-	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	0.1	-	0.4	-	0.2	-	0.3	3.6	0.5	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	-	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	-	*	0.1	*	-	*	*	*	0.1	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	*	*	-	-	-	*	-	-	-	-	-	-
23	*	*	-	-	-	*	-	-	-	-	-	-
24	0.1	*	-	-	-	*	-	*	*	*	-	-
25	0.4	0.1	-	*	-	*	-	*	0.1	*	-	*
26	1.2	0.4	-	*	*	*	-	0.1	1.3	0.3	-	0.2
27	2.7	0.9	-	0.5	*	0.1	-	1.0	8.2	2.2	1.3	2.0
28	4.3	1.9	-	4.4	2.1	0.6	-	4.8	21.3	10.8	10.8	7.9
29	7.2	3.6	-	19.0	17.2	7.7	-	15.6	28.9	28.1	21.3	22.0
30	16.5	8.4	-	33.2	49.2	36.4	-	26.9	24.0	31.7	53.3	32.0
31	24.1	17.2	-	21.1	18.4	36.3	-	26.3	9.6	17.4	9.2	17.3
32	25.0	24.4	-	11.7	10.0	13.3	-	16.1	4.0	6.9	2.5	12.2
33	14.5	22.3	-	5.1	2.9	4.6	-	6.5	1.6	2.1	1.6	4.6
34	3.1	13.8	-	2.9	0.1	1.0	-	2.3	0.6	0.4	-	1.7
35	0.7	5.7	-	1.8	-	0.1	-	0.4	0.2	0.1	-	0.1
36	0.2	1.0	-	0.2	-	*	-	*	*	*	-	-
37	*	0.2	-	*	-	*	-	*	-	-	-	*
38	-	0.1	-	*	-	*	-	*	-	-	-	-
39	-	*	-	-	-	-	-	-	-	-	-	-
40 & Above	-	*	-	-	-	-	-	*	-	-	-	-
Average	31.47	32.57	-	30.97	30.70	31.17	-	31.06	29.69	30.27	30.19	30.63
Mike												
2.4 & Below	0.1	0.1	-	-	-	-	-	-	-	-	-	-
2.5	1.9	0.7	-	-	-	-	-	-	-	*	-	-
2.6	3.2	1.1	-	*	-	-	-	-	-	-	-	-
2.7	2.9	1.5	-	*	-	-	-	-	-	*	-	-
2.8	1.9	2.0	-	-	-	-	-	-	-	*	19.6	1.7
2.9	1.3	2.1	-	*	-	-	-	-	-	*	17.5	1.7
3.0	1.1	2.3	-	*	-	-	-	-	*	*	8.7	0.9
3.1	2.2	2.9	-	*	-	*	-	-	*	*	3.8	0.4
3.2	3.2	3.5	-	*	*	*	-	*	0.1	0.1	1.5	0.8
3.3	4.6	4.3	-	*	*	*	-	*	0.3	0.2	0.1	0.6
3.4	7.2	5.4	-	0.1	*	*	-	*	0.2	0.3	0.1	0.3
3.5	6.6	5.8	-	0.1	0.1	*	-	0.1	0.4	0.5	1.8	1.1
3.6	7.9	6.6	-	0.1	0.2	0.1	-	0.1	1.0	0.9	4.9	1.4
3.7	8.7	7.0	-	0.2	0.7	0.2	-	0.2	1.5	1.5	1.5	3.5
3.8	8.9	6.9	-	0.3	1.7	0.3	-	0.3	2.7	2.4	3.0	5.9
3.9	8.3	6.7	-	0.6	2.7	0.6	-	0.4	4.6	3.5	2.6	8.9
4.0	7.1	7.0	-	1.3	4.9	1.3	-	0.8	6.6	4.9	3.3	7.9
4.1	6.1	7.5	-	2.2	8.5	2.4	-	1.3	9.2	7.0	2.0	7.6
4.2	4.2	5.8	-	3.4	13.4	4.2	-	2.0	11.2	9.2	6.8	8.3
4.3	2.9	5.8	-	4.9	11.8	6.7	-	3.0	14.7	11.6	8.3	10.8
4.4	2.4	5.1	-	6.3	11.3	9.7	-	4.5	15.4	12.3	5.5	8.9
4.5	2.7	3.8	-	8.2	13.4	12.9	-	6.2	12.2	11.4	2.9	9.1
4.6	1.6	2.3	-	9.7	10.9	15.1	-	8.7	9.9	10.2	1.8	6.8
4.7	1.9	1.6	-	11.2	9.2	15.8	-	11.2	7.2	8.5	3.0	5.8
4.8	0.6	1.3	-	12.6	4.6	13.3	-	13.6	2.0	6.0	1.1	3.6
4.9	0.1	0.7	-	11.7	3.4	8.7	-	14.6	0.7	4.2	-	2.7
5.0	0.1	0.3	-	9.6	2.3	5.0	-	13.3	0.1	2.7	-	1.1
5.1	0.1	*	-	7.7	0.5	2.4	-	9.9	0.1	1.5	-	0.1
5.2	-	*	-	4.4	*	0.9	-	5.7	*	0.7	-	0.1
5.3	-	-	-	2.6	*	0.3	-	2.6	*	0.3	-	*
5.4	-	-	-	1.3	*	0.1	-	1.0	-	0.1	-	-
5.5 & Above	-	-	-	1.4	*	*	-	0.4	-	*	-	-
Average	3.68	3.79	-	4.74	4.40	4.61	-	4.80	4.31	4.41	3.51	4.18

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Jan 08, 2026										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	4.2	2.0	5.7	3.3	-	*	12.9	3.7	9.6	1.3
Bark - Level 2	-	*	-	-	-	-	*	*	-	-
Grass - Level 1	0.1	0.1	-	0.1	-	*	0.1	0.2	-	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	-	-	-	*	-	-	*	*	-	*
Prep - Level 2	-	*	-	-	-	-	-	*	-	-
Seed Coat - Level 1	*	*	4.5	1.7	-	*	0.8	0.3	1.3	0.6
Seed Coat - Level 2	*	*	-	-	-	-	*	*	-	-
Oil - Level 1	-	-	*	*	-	-	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	*	-	-
Other - Level 1	-	*	-	-	-	-	*	*	-	-
Other - Level 2	*	*	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	-	*	*	*	0.1	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	-	-	-	-	-	-	*	*	-	-
23	*	*	-	-	-	-	*	*	-	-
24	*	*	*	*	-	*	0.1	0.1	0.1	*
25	0.1	*	0.2	*	-	*	0.4	0.2	0.1	*
26	0.3	0.2	2.2	0.4	-	*	1.7	0.7	9.6	1.1
27	1.0	0.8	10.7	2.5	-	0.5	5.6	2.7	37.0	6.2
28	2.5	3.2	24.1	12.5	-	3.8	12.8	7.5	23.1	19.0
29	8.4	8.8	29.7	35.0	-	21.0	21.0	15.5	20.5	32.2
30	18.3	14.9	18.7	30.3	-	38.7	21.9	20.8	6.9	25.7
31	22.7	18.3	10.4	13.2	-	24.7	16.0	18.7	0.8	11.1
32	20.3	16.8	3.4	4.7	-	8.2	10.2	13.5	1.9	3.6
33	12.2	15.3	0.5	1.2	-	2.4	5.8	9.7	0.1	0.8
34	6.3	11.5	0.1	0.2	-	0.7	2.6	6.4	-	0.2
35	2.8	6.3	-	*	-	0.1	1.1	2.8	-	*
36	1.8	2.3	-	*	-	*	0.4	1.0	-	*
37	2.9	1.3	-	*	-	*	0.1	0.3	-	-
38	0.3	0.2	-	-	-	-	0.1	0.1	-	-
39	*	*	-	-	-	-	*	*	-	-
40 & Above	*	*	-	-	-	-	0.1	*	-	-
Average	31.99	32.27	29.42	30.02	-	30.66	30.46	31.26	28.32	29.73
Mike										
2.4 & Below	*	*	-	-	-	-	0.1	*	-	-
2.5	0.1	*	-	-	-	-	0.2	*	-	-
2.6	*	*	-	-	-	-	0.2	0.1	-	-
2.7	-	*	-	-	-	*	0.4	0.1	-	*
2.8	*	*	-	*	-	*	0.5	0.2	-	*
2.9	*	0.1	-	*	-	*	0.6	0.4	-	*
3.0	0.3	0.1	*	*	-	*	1.1	0.5	-	0.1
3.1	0.7	0.2	*	*	-	*	1.6	0.8	-	0.1
3.2	1.0	0.4	*	0.1	-	*	2.1	1.1	0.1	0.1
3.3	1.4	0.7	*	0.2	-	*	2.5	1.5	1.0	0.2
3.4	1.7	1.0	0.3	0.3	-	0.1	3.2	2.0	0.8	0.4
3.5	2.3	1.5	0.5	0.4	-	0.3	3.7	2.7	2.0	0.7
3.6	4.2	2.7	2.0	0.8	-	0.3	4.1	3.3	3.4	1.3
3.7	5.1	3.9	4.8	1.7	-	0.8	4.6	4.0	1.9	2.6
3.8	4.8	5.4	6.5	2.5	-	1.1	4.9	5.1	0.4	3.9
3.9	6.1	7.1	11.4	4.0	-	1.7	5.8	6.3	2.0	6.7
4.0	10.6	8.7	10.3	5.5	-	2.5	6.3	7.5	4.4	9.2
4.1	12.4	10.1	10.2	6.9	-	3.9	7.2	8.6	7.5	11.6
4.2	10.1	9.9	9.9	8.4	-	5.3	7.9	9.7	16.4	14.1
4.3	10.6	10.8	12.0	9.7	-	6.7	8.6	9.9	11.3	14.5
4.4	9.9	10.0	10.3	10.5	-	9.5	8.3	9.3	12.0	12.8
4.5	7.3	9.3	5.0	10.7	-	11.8	7.2	8.1	18.1	9.1
4.6	4.7	7.5	6.0	10.0	-	13.4	6.1	6.5	0.9	5.9
4.7	3.3	5.3	3.4	8.7	-	13.4	4.5	4.8	0.8	3.2
4.8	2.0	3.1	2.9	7.1	-	11.8	3.3	3.2	2.8	1.7
4.9	0.9	1.4	1.7	5.2	-	8.1	2.5	1.9	3.7	1.0
5.0	0.3	0.6	1.4	3.5	-	5.4	1.5	1.1	6.6	0.5
5.1	*	0.1	1.0	2.1	-	2.7	0.7	0.6	2.9	0.2
5.2	-	*	0.3	1.0	-	1.0	0.2	0.3	1.1	*
5.3	-	*	*	0.5	-	0.3	0.2	0.2	0.1	*
5.4	-	-	-	0.2	-	*	*	0.1	-	*
5.5 & Above	-	*	-	0.1	-	*	*	0.1	-	*
Average	4.12	4.21	4.21	4.43	-	4.56	4.10	4.17	4.35	4.23

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE												
For The Week Ending Jan 08, 2026												
Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	*	-	-	*	*	-	-	-	-	*	*
2.7 - 2.9	-	*	-	*	*	*	0.3	0.1	-	-	0.1	*
3.0 - 3.2	0.4	0.1	*	*	0.3	0.2	0.4	0.6	-	0.1	0.7	0.1
3.3 - 3.4	1.0	0.5	*	*	0.2	0.3	1.2	0.6	*	0.1	1.6	0.4
3.5 - 3.6	2.2	1.8	*	0.1	1.9	0.9	0.2	2.0	-	1.2	4.4	1.6
3.7 - 4.2	34.5	32.7	2.9	3.9	29.1	24.7	69.4	42.7	1.5	20.7	46.4	29.8
4.3 - 4.9	58.6	58.0	69.7	71.1	59.5	67.0	25.7	44.5	96.8	72.1	44.7	59.7
5.0 - 5.2	2.9	5.8	25.0	22.2	7.9	5.9	2.4	7.4	1.7	5.4	1.7	7.4
5.3 & Above	0.5	1.1	2.4	2.8	1.0	0.9	0.3	2.1	*	0.3	0.4	0.9
Average	4.33	4.39	4.77	4.76	4.44	4.46	4.18	4.35	4.66	4.48	4.21	4.43
Leaf												
1 - 2	9.2	15.5	2.3	2.1	22.3	38.7	27.9	45.0	1.8	7.8	13.5	14.8
3	47.3	54.9	38.5	39.0	35.7	33.2	58.2	38.5	29.1	52.7	51.6	58.5
4	36.7	25.4	34.7	45.8	28.6	18.9	13.0	11.7	53.7	34.5	29.0	23.6
5	6.6	3.9	22.0	11.8	8.9	6.9	0.9	4.0	13.9	4.8	5.3	2.9
6	0.3	0.3	2.4	1.3	3.6	1.8	*	0.8	1.3	0.3	0.5	0.2
7	-	*	*	0.1	0.8	0.4	-	-	0.1	*	*	*
8	-	*	-	-	0.1	*	-	-	-	-	*	*
Average	3.41	3.18	3.84	3.71	3.34	2.94	2.86	2.70	3.84	3.37	3.28	3.15
HVI Trash 1/												
00	-	-	-	-	-	*	-	*	-	-	-	-
01	0.9	2.0	*	0.1	9.9	15.6	3.7	16.3	*	0.9	1.2	1.5
02	11.7	17.6	3.2	3.1	15.2	28.7	30.9	33.7	2.1	9.4	17.4	19.9
03	22.8	28.0	15.6	14.6	16.7	17.8	33.4	23.0	10.1	23.4	27.1	32.0
04	25.2	23.8	20.9	24.5	19.3	13.4	18.9	12.3	22.5	28.1	23.6	23.6
05	19.0	14.5	18.8	23.0	14.8	9.3	8.3	6.1	24.5	19.3	15.3	12.7
06	11.3	7.6	16.7	16.0	9.2	6.1	3.2	3.5	19.5	10.3	8.1	5.9
07	5.6	3.7	12.3	9.4	5.8	3.8	1.1	2.2	10.9	4.8	3.9	2.6
08	2.3	1.6	7.0	4.9	3.8	2.3	0.3	1.4	5.6	2.2	1.9	1.1
09	0.7	0.7	3.3	2.4	2.4	1.4	0.1	0.8	1.9	0.9	0.9	0.5
10	0.2	0.3	1.5	1.1	1.3	0.7	*	0.4	1.6	0.5	0.4	0.2
11	0.1	0.1	0.5	0.5	0.8	0.4	-	0.2	0.5	0.2	0.2	0.1
12	0.1	0.1	0.2	0.2	0.4	0.2	-	0.1	0.3	0.1	0.1	*
13	*	*	0.1	0.1	0.2	0.1	*	*	0.2	*	*	*
14	*	*	-	*	0.1	0.1	-	*	*	*	*	*
15	*	*	-	*	0.1	*	-	-	*	*	*	*
16	*	*	-	-	*	*	-	-	*	*	*	*
17	-	*	-	-	*	*	-	-	0.1	*	*	*
18 & Above	*	*	-	-	*	*	-	-	0.1	*	*	*
Average	0.43	0.38	0.53	0.51	0.42	0.34	0.31	0.29	0.54	0.43	0.40	0.37
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	-	-	-	-	-	-	-	-	-	-	*
76	-	*	-	*	-	*	-	*	-	*	*	*
77	*	*	*	*	0.1	*	*	*	-	*	0.2	0.1
78	0.2	0.3	0.1	0.1	0.2	0.2	0.7	1.0	-	0.1	1.2	0.8
79	2.6	2.5	0.3	0.5	3.8	1.8	2.5	5.7	0.1	1.1	7.7	5.4
80	21.0	13.2	6.5	3.9	13.7	12.2	48.2	21.2	3.7	7.8	22.1	21.2
81	42.7	31.8	24.7	20.5	34.5	35.2	37.7	26.5	22.6	37.1	34.4	36.4
82	26.3	35.1	36.1	42.8	37.0	39.9	9.6	27.1	55.1	41.9	26.1	26.5
83	6.9	14.9	24.8	27.6	9.7	9.9	1.1	14.3	18.4	10.9	7.3	8.1
84	0.3	2.0	6.2	4.2	0.9	0.8	0.1	4.1	0.2	1.1	0.9	1.3
85 & Above	*	0.2	1.4	0.3	*	*	-	0.1	-	0.1	0.1	0.1
Average	81.59	81.97	82.47	82.52	81.81	81.90	81.03	81.77	82.32	82.02	81.47	81.57
Tenderable 3/	82.5	90.2	67.7	69.9	84.0	87.0	92.4	84.4	81.3	91.0	86.8	88.3
SAMPLES CLASSED	9,925	524,405	19,036	1,358,912	16,444	138,188	8,354	62,414	2,233	90,067	82,279	1,630,242

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 08, 2026

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	0.1	0.1	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	5.1	1.7	-	*	-	-	-	-	-	*	-	-
2.7 - 2.9	6.2	5.6	-	*	-	-	-	-	-	*	37.2	3.4
3.0 - 3.2	6.5	8.7	-	*	*	*	-	*	0.1	0.2	14.0	2.1
3.3 - 3.4	11.8	9.7	-	0.1	*	*	-	*	0.5	0.5	0.3	0.9
3.5 - 3.6	14.5	12.4	-	0.2	0.3	0.1	-	0.2	1.4	1.4	6.7	2.5
3.7 - 4.2	43.4	41.0	-	8.1	32.0	9.0	-	5.0	35.8	28.3	19.3	42.2
4.3 - 4.9	12.3	20.5	-	64.6	64.7	82.1	-	61.8	61.9	64.2	22.7	47.6
5.0 - 5.2	0.2	0.3	-	21.7	2.9	8.2	-	29.0	0.2	5.0	-	1.3
5.3 & Above	-	-	-	5.2	*	0.5	-	4.0	*	0.4	-	*
Average	3.68	3.79	-	4.74	4.40	4.61	-	4.80	4.31	4.41	3.51	4.18
Leaf												
1 - 2	1.8	9.2	-	14.2	6.9	4.1	-	6.3	8.7	9.1	30.7	57.7
3	21.2	25.8	-	49.8	52.4	53.0	-	42.8	53.0	51.6	36.4	29.3
4	32.3	30.0	-	29.5	36.2	37.2	-	39.7	29.9	32.8	22.9	9.2
5	21.6	20.0	-	6.1	4.3	5.4	-	10.1	7.6	5.8	7.6	2.7
6	13.9	10.2	-	0.4	0.2	0.4	-	1.0	0.8	0.5	1.9	0.9
7	6.8	3.7	-	-	*	*	-	*	*	0.1	0.5	0.2
8	2.3	1.0	-	-	-	-	-	-	-	*	-	-
Average	4.54	4.11	-	3.28	3.38	3.45	-	3.57	3.39	3.37	3.13	2.48
HVI Trash 1/												
00	-	-	-	-	-	*	-	-	-	-	-	-
01	0.2	2.2	-	1.9	0.1	0.2	-	0.5	0.4	0.8	6.9	23.5
02	3.0	8.9	-	15.0	9.9	6.2	-	7.7	10.8	11.0	27.0	37.4
03	9.2	11.9	-	24.4	27.2	23.2	-	19.0	25.3	24.3	25.4	19.2
04	14.1	13.4	-	23.2	28.3	28.7	-	23.6	25.7	25.5	18.6	9.7
05	13.4	13.0	-	16.2	19.2	20.9	-	19.9	17.9	18.3	9.6	5.1
06	11.3	10.9	-	9.6	10.0	11.4	-	13.3	9.5	10.6	4.3	2.2
07	9.2	9.0	-	5.2	3.8	5.4	-	7.9	5.4	5.3	3.9	1.3
08	7.9	7.4	-	2.5	1.1	2.3	-	4.2	2.8	2.4	2.1	0.8
09	6.8	5.8	-	1.2	0.3	1.0	-	2.1	1.2	1.0	1.1	0.4
10	5.7	4.5	-	0.5	0.1	0.4	-	1.0	0.5	0.4	0.3	0.1
11	4.9	3.6	-	0.2	*	0.2	-	0.5	0.3	0.2	0.3	0.1
12	4.1	2.7	-	0.1	*	0.1	-	0.2	0.1	0.1	0.4	0.1
13	3.3	2.1	-	*	-	*	-	0.1	0.1	*	0.1	*
14	2.1	1.5	-	*	-	*	-	*	-	*	-	-
15	1.7	0.9	-	-	*	*	-	*	*	*	-	-
16	1.2	0.8	-	-	-	-	-	-	-	*	-	-
17	0.8	0.5	-	-	-	-	-	-	-	*	-	-
18 & Above	1.4	0.9	-	-	-	-	-	-	-	*	-	-
Average	0.73	0.63	-	0.41	0.41	0.44	-	0.47	0.43	0.43	0.35	0.26
UNIFORMITY 2/												
74 & Below	*	*	-	-	-	-	-	-	-	*	-	-
75	0.2	0.1	-	-	-	-	-	-	-	*	-	-
76	0.8	0.5	-	-	-	*	-	*	0.1	*	-	-
77	2.3	1.6	-	-	*	*	-	*	0.2	*	0.3	0.1
78	4.6	3.7	-	0.1	*	0.1	-	0.2	1.8	0.6	2.3	0.4
79	7.5	7.7	-	1.2	0.3	0.2	-	1.3	6.4	2.9	23.8	3.7
80	18.4	17.1	-	7.1	4.9	2.1	-	8.8	16.5	10.8	38.0	17.6
81	37.4	32.4	-	30.1	36.4	16.4	-	30.1	34.8	27.2	27.7	39.6
82	22.9	25.5	-	40.4	49.8	50.3	-	38.1	29.7	35.4	7.9	29.5
83	5.4	10.0	-	18.5	8.5	28.1	-	18.1	9.3	20.1	-	8.7
84	0.4	1.6	-	2.6	0.1	2.5	-	3.3	1.1	2.8	-	0.3
85 & Above	*	*	-	0.1	*	0.2	-	0.1	0.1	0.2	-	*
Average	81.18	81.42	-	82.20	82.06	82.57	-	82.18	81.61	82.11	80.61	81.65
Tenderable 3/	28.6	41.4	-	71.5	90.0	86.5	-	63.7	91.2	90.7	48.2	89.6
SAMPLES CLASSED	12,749	98,639	-	223,299	15,774	655,757	-	706,510	13,526	641,447	794	9,067

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Jan 08, 2026										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	*	*	-	-	-	-	0.1	*	-	-
2.5 - 2.6	0.1	*	-	-	-	-	0.4	0.1	-	-
2.7 - 2.9	*	0.1	-	*	-	*	1.5	0.7	-	*
3.0 - 3.2	2.0	0.8	*	0.1	-	*	4.8	2.4	0.1	0.3
3.3 - 3.4	3.1	1.7	0.3	0.5	-	0.2	5.7	3.6	1.7	0.6
3.5 - 3.6	6.5	4.1	2.5	1.2	-	0.6	7.8	6.0	5.4	2.0
3.7 - 4.2	49.1	45.1	53.2	28.9	-	15.1	36.7	41.3	32.6	48.0
4.3 - 4.9	38.8	47.3	41.2	62.0	-	74.7	40.4	43.6	49.6	48.2
5.0 - 5.2	0.3	0.7	2.7	6.6	-	9.0	2.5	2.0	10.6	0.8
5.3 & Above	-	*	*	0.7	-	0.3	0.2	0.3	0.1	*
Average	4.12	4.21	4.21	4.43	-	4.56	4.10	4.17	4.35	4.23
Leaf										
1 - 2	69.3	63.6	2.8	4.7	-	16.4	61.7	56.3	5.6	11.3
3	26.2	29.4	41.9	49.6	-	59.0	29.8	31.9	55.2	61.3
4	3.8	5.9	46.7	39.8	-	21.8	6.1	9.7	37.3	24.1
5	0.6	1.0	8.4	5.6	-	2.7	1.8	1.9	1.9	3.1
6	*	0.1	0.2	0.2	-	0.2	0.5	0.3	-	0.1
7	*	*	-	*	-	*	0.1	*	-	*
8	*	*	-	-	-	-	*	*	-	-
Average	2.14	2.23	3.61	3.47	-	3.11	2.37	2.43	3.35	3.19
HVI Trash 1/										
00	0.1	*	-	-	-	*	0.1	0.1	-	-
01	35.5	33.3	0.1	0.2	-	2.0	28.0	27.3	-	0.5
02	37.6	33.2	4.7	6.7	-	17.1	40.6	33.5	7.1	12.5
03	16.4	18.0	18.2	22.6	-	29.7	17.4	18.5	23.7	29.7
04	6.1	8.7	26.0	27.7	-	24.7	7.0	10.0	27.0	26.5
05	2.5	3.7	22.6	21.4	-	14.2	3.1	5.3	19.3	16.0
06	1.0	1.6	15.7	12.1	-	6.8	1.6	2.8	15.3	8.2
07	0.5	0.7	7.5	5.6	-	3.1	1.0	1.3	5.0	3.9
08	0.2	0.4	3.4	2.3	-	1.3	0.5	0.6	2.3	1.7
09	0.1	0.2	1.2	0.8	-	0.6	0.3	0.3	0.2	0.7
10	*	0.1	0.4	0.3	-	0.2	0.2	0.1	-	0.2
11	*	*	0.1	0.1	-	0.1	0.1	0.1	-	0.1
12	*	*	0.1	*	-	*	0.1	*	-	*
13	*	*	*	*	-	*	*	*	-	*
14	-	*	-	*	-	*	*	*	-	*
15	-	*	-	*	-	*	*	*	-	*
16	*	*	-	*	-	-	*	*	-	*
17	-	*	-	-	-	-	*	*	-	*
18 & Above	*	*	-	*	-	-	*	*	-	*
Average	0.21	0.23	0.47	0.44	-	0.38	0.23	0.25	0.44	0.40
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	*	*	-	-
75	*	*	-	*	-	-	*	*	-	-
76	*	*	*	*	-	*	0.3	0.2	-	*
77	0.1	0.2	0.3	*	-	*	1.6	0.8	-	*
78	1.0	1.0	1.3	0.5	-	0.1	6.3	3.7	0.1	0.2
79	5.7	5.2	11.1	3.6	-	0.6	20.4	12.1	0.6	1.3
80	23.3	17.5	28.9	16.6	-	6.9	34.5	25.6	4.1	8.2
81	36.3	31.9	35.7	32.4	-	32.7	25.2	29.9	39.9	27.9
82	22.8	26.3	20.2	33.0	-	43.1	9.4	18.8	46.4	38.2
83	9.3	13.9	2.4	12.7	-	15.6	1.8	7.1	7.9	21.0
84	1.4	3.8	0.1	1.1	-	0.9	0.3	1.7	1.0	2.9
85 & Above	0.2	0.3	-	0.1	-	0.1	0.1	0.2	-	0.2
Average	81.54	81.80	81.15	81.81	-	82.14	80.56	81.19	82.07	82.23
Tenderable 3/	90.0	93.4	85.0	86.3	-	82.3	71.0	83.4	77.9	96.2
SAMPLES CLASSED	35,495	335,320	14,124	264,730	-	340,307	224,910	4,665,238	1,673	172,137

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE									
For The Week Ending Jan 08, 2026									
Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	0.9	2.2	5.8	5.4	-	-	16.7	17.0
	2	-	0.3	9.5	6.6	-	-	20.3	16.7
	3	-	*	0.1	0.1	-	-	0.3	0.4
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		0.9	2.5	15.4	12.0	-	-	37.3	34.1
02	1	33.3	39.2	2.2	4.5	-	-	6.8	14.4
	2	17.9	18.3	28.9	33.7	-	-	45.4	42.0
	3	-	0.1	8.3	8.8	-	-	3.3	3.0
	4	-	-	0.1	0.1	-	-	-	0.1
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		51.1	57.6	39.5	47.0	-	-	55.5	59.5
03	1	7.0	12.0	0.1	0.2	-	-	0.5	0.4
	2	27.8	23.1	16.0	14.3	-	-	4.9	5.0
	3	1.2	0.8	21.5	19.3	-	-	0.8	0.9
	4	-	-	1.9	2.1	-	-	-	0.1
	5	-	-	*	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		36.0	35.9	39.5	35.8	-	-	6.2	6.3
04	1	0.2	0.3	*	*	-	-	-	-
	2	8.7	3.1	0.4	0.6	-	-	0.3	0.1
	3	1.2	0.4	1.9	2.5	-	-	0.5	*
	4	-	-	0.9	1.0	-	-	-	*
	5	-	-	*	0.1	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		10.0	3.8	3.2	4.3	-	-	0.8	0.1
05	1	-	-	-	*	-	-	-	-
	2	1.5	0.2	0.1	0.1	-	-	-	-
	3	0.5	0.1	0.7	0.3	-	-	0.1	*
	4	-	-	0.4	0.3	-	-	-	-
	5	-	-	0.1	*	-	-	-	-
	6	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		2.0	0.2	1.3	0.7	-	-	0.1	*
06	1	-	-	-	-	-	-	-	-
	2	-	-	0.1	*	-	-	-	-
	3	-	-	0.6	*	-	-	-	-
	4	-	-	0.2	*	-	-	-	-
	5	-	-	*	*	-	-	-	-
	6	-	-	*	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	1.0	0.1	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	*	*	-	-	-	-
	4	-	-	0.1	*	-	-	-	-
	5	-	-	*	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	0.2	0.1	-	-	-	-
STAPLE									
44 & Shorter		-	0.1	3.8	2.3	-	-	15.5	12.0
46		10.7	18.7	8.6	8.1	-	-	25.2	49.0
48		88.6	76.4	45.1	45.1	-	-	59.0	34.8
50		0.7	4.7	41.8	42.6	-	-	0.3	3.7
52 & Longer		-	0.2	0.8	2.0	-	-	-	0.5
Average Staple		47.80	47.72	48.54	48.67	-	-	46.88	46.63
Average Length		1.38	1.39	1.41	1.41	-	-	1.36	1.36
EXTRANEIOUS MATTER									
Bark		-	-	-	*	-	-	0.1	*
Grass		-	-	*	0.3	-	-	0.3	1.1
Spindle Twist		-	-	0.5	0.1	-	-	-	-
Preparation		-	*	-	*	-	-	-	-
All Other		-	*	*	*	-	-	0.1	*

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE								
For The Week Ending Jan 08, 2026								
Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	-
2.7 - 2.9	0.3	*	0.4	0.1	-	-	-	0.2
3.0 - 3.2	-	*	1.0	0.5	-	-	-	10.2
3.3 - 3.4	0.7	0.4	0.9	1.4	-	-	1.2	14.5
3.5 - 3.6	1.7	1.3	3.2	6.9	-	-	8.7	19.9
3.7 - 4.2	85.7	92.6	83.6	87.4	-	-	76.9	52.3
4.3 - 4.9	11.7	5.6	10.8	3.6	-	-	13.2	3.0
5.0 - 5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	3.98	3.99	3.97	3.91	-	-	3.98	3.69
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-
2.7	-	*	-	*	-	-	-	*
2.8	0.2	*	*	*	-	-	-	*
2.9	0.1	*	0.4	0.1	-	-	-	0.2
3.0	-	*	0.2	0.1	-	-	-	1.7
3.1	-	-	0.5	0.1	-	-	-	4.0
3.2	-	-	0.4	0.3	-	-	-	4.5
3.3	-	0.1	0.3	0.5	-	-	0.7	5.4
3.4	0.7	0.3	0.6	0.9	-	-	0.5	9.1
3.5	-	0.2	0.8	2.0	-	-	0.9	10.8
3.6	1.7	1.1	2.4	4.9	-	-	7.8	9.0
3.7	2.8	4.3	6.5	9.8	-	-	11.4	9.5
3.8	15.1	12.8	15.4	16.6	-	-	12.5	9.7
3.9	24.7	21.5	19.6	22.3	-	-	8.9	11.3
4.0	26.6	26.3	17.6	20.4	-	-	12.7	10.2
4.1	10.2	19.4	13.8	12.1	-	-	17.8	8.5
4.2	6.1	8.3	10.7	6.2	-	-	13.6	3.1
4.3	10.0	3.5	6.1	2.4	-	-	6.6	1.9
4.4	1.7	2.0	3.1	0.8	-	-	4.4	0.7
4.5	0.1	0.2	1.2	0.4	-	-	2.1	0.3
4.6	-	*	0.3	0.1	-	-	0.1	0.1
4.7	-	*	0.1	*	-	-	-	*
4.8	-	-	*	*	-	-	-	*
4.9	-	-	*	*	-	-	-	*
5.0	-	-	-	-	-	-	-	-
5.1	-	-	*	*	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	3.98	3.99	3.97	3.91	-	-	3.98	3.69
STRENGTH 1/								
36 & Below	-	-	0.4	1.5	-	-	0.4	9.9
37	-	0.1	5.1	4.4	-	-	1.1	18.1
38	-	0.2	5.4	3.0	-	-	9.6	18.5
39	0.2	0.8	1.3	1.3	-	-	11.7	7.3
40	0.2	6.1	1.0	1.8	-	-	2.1	2.5
41	1.9	21.9	1.6	5.5	-	-	0.2	3.1
42	31.4	35.3	3.6	10.8	-	-	2.3	5.2
43	43.8	24.9	6.8	17.4	-	-	2.8	7.2
44	16.6	8.3	13.2	21.3	-	-	10.8	9.1
45	3.7	1.6	22.5	18.0	-	-	18.7	8.1
46	1.7	0.6	19.6	9.6	-	-	30.8	6.6
47	0.2	0.2	11.0	3.8	-	-	7.3	2.9
48 & Above	0.4	0.1	8.5	1.6	-	-	2.2	1.4
Average	43.42	42.58	44.78	43.71	-	-	44.15	40.86
UNIFORMITY								
83 & Below	0.5	0.2	5.2	1.8	-	-	1.6	1.7
84	1.7	3.0	18.7	11.9	-	-	21.3	22.7
85	58.1	42.3	39.7	33.5	-	-	36.8	44.4
86	39.0	49.7	32.2	46.9	-	-	39.5	27.8
87	0.6	4.6	3.9	5.5	-	-	0.7	3.2
88 & Above	0.1	0.1	0.3	0.5	-	-	0.1	0.2
Average	85.83	86.00	85.57	85.88	-	-	85.57	85.53
Samples Classed	1,025	9,414	16,450	266,849	-	-	1,765	26,082

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.