



State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	11	83.9	72.1	7,106	21	90.1	78.1	531,511
AR	2	71.8	55.5	17,694	26	69.9	42.1	1,376,606
AZ	9	83.3	72.3	16,876	9	86.6	68.3	155,064
CA	2	96.8	92.4	4,507	10	85.3	73.5	66,921
FL	-	-	-	-	4	91.0	76.3	90,067
GA	33	89.7	79.8	46,937	53	88.3	74.1	1,677,176
KS	3	17.7	14.0	17,630	3	37.9	28.9	116,158
LA	-	-	-	-	14	71.5	47.6	223,299
MO	3	94.4	78.7	15,399	16	86.7	65.0	671,156
MS	-	-	-	-	30	63.7	36.5	706,510
NC	6	94.8	75.6	4,444	26	90.7	78.7	645,891
NM*	-	-	-	-	2	87.3	78.5	9,488
OK	10	89.0	81.7	29,770	10	93.0	81.3	365,090
SC	5	93.6	84.7	5,286	10	86.5	73.2	270,016
TN	-	-	-	-	17	82.3	63.4	340,307
TX	80	71.9	50.0	217,066	144	82.9	62.8	4,882,198
VA*	-	-	-	-	4	96.1	90.5	172,426
United States	167	75.4	58.5	383,425	399	82.1	63.0	12,299,884
AMERICAN PIMA								
AZ	2			2,291	2			11,705
CA	4			10,296	10			277,145
NM*	-			-	-			-
TX	3			2,808	5			28,890
United States	10			15,404	18			336,987
United States all cotton	177			398,829	408			12,636,871

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 15, 2026

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	0.5	2.2	0.1	0.1	13.4	20.4	15.8	22.9	-	1.7	2.9	1.4
	3	1.4	1.3	0.7	0.1	2.3	4.4	5.8	9.1	-	0.5	3.6	1.1
	4	*	*	-	*	0.1	0.2	0.2	0.5	-	*	0.2	*
	5	-	*	-	-	-	*	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.9	3.6	0.7	0.2	15.8	25.0	21.8	32.5	-	2.2	6.7	2.6
31	1 - 2	3.4	9.5	0.6	1.1	5.4	10.0	5.1	15.5	-	3.1	6.4	7.7
	3	15.6	28.4	12.3	9.1	14.7	11.3	9.2	12.6	-	12.5	24.5	21.7
	4	4.9	7.3	3.1	3.4	4.2	2.4	0.9	4.7	-	2.8	6.2	4.2
	5	0.2	0.5	0.3	0.1	0.6	0.2	-	0.9	-	0.1	0.4	0.2
	6	-	*	*	*	*	*	-	0.1	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	24.1	45.7	16.3	13.7	24.9	23.9	15.3	33.7	-	18.4	37.5	33.9
41	1 - 2	1.1	3.2	0.4	0.8	1.2	2.1	6.3	4.6	-	2.8	3.0	5.3
	3	14.0	22.5	17.8	26.1	12.6	13.2	37.6	15.4	-	37.0	23.1	32.6
	4	10.7	15.7	29.2	35.2	19.0	12.9	14.1	5.3	-	28.9	13.3	16.5
	5	0.8	2.8	15.3	8.5	7.7	4.0	0.5	1.9	-	4.0	1.8	2.1
	6	0.1	0.2	1.8	0.7	1.1	0.5	*	0.4	-	0.2	0.1	0.1
	7	*	*	*	*	0.1	*	-	-	-	*	*	*
	8	-	-	-	-	*	*	-	-	-	-	-	-
Total	----	26.7	44.5	64.5	71.2	41.8	32.7	58.6	27.8	-	72.9	41.2	56.6
51	1 - 2	4.7	0.2	0.1	*	*	0.1	*	0.1	-	0.1	0.5	0.2
	3	21.6	1.8	4.0	2.3	1.4	1.1	0.3	0.4	-	1.7	5.4	2.1
	4	10.8	1.6	4.9	4.8	4.7	3.0	1.0	0.2	-	2.3	5.0	2.1
	5	0.9	0.3	1.8	2.3	3.0	2.4	0.2	0.1	-	0.6	1.0	0.5
	6	0.1	*	0.7	0.4	0.8	1.1	-	*	-	0.1	*	0.1
	7	-	*	*	0.1	0.1	0.3	-	-	-	*	-	*
	8	-	*	-	-	*	*	-	-	-	-	-	*
Total	----	38.1	4.0	11.6	9.9	10.0	8.0	1.5	0.8	-	4.8	11.9	5.0
61	1 - 2	0.3	*	-	*	*	*	-	-	-	-	*	*
	3	1.2	*	-	*	*	*	-	-	-	*	0.1	*
	4	0.4	*	-	*	0.1	*	-	-	-	*	0.1	*
	5	0.1	*	-	*	-	*	-	-	-	*	*	*
	6	-	*	-	*	-	*	-	-	-	*	*	*
	7	-	-	-	-	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	*
Total	----	2.0	0.1	-	*	0.1	*	-	-	-	*	0.3	*
71	1 - 2	-	-	-	*	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	*	-	-	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	-	-	-	-	-	-	-
12 & 22	1 - 2	-	0.1	-	*	0.1	3.8	0.1	0.2	-	*	*	*
	3	*	*	-	*	0.1	1.8	0.4	0.3	-	*	0.3	0.1
	4	-	*	-	*	*	0.2	-	*	-	-	0.1	*
	5	-	-	-	*	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	0.1	-	*	0.2	5.8	0.5	0.6	-	*	0.4	0.1
32	1 - 2	*	0.1	-	*	0.2	0.1	-	0.4	-	*	*	*
	3	0.7	0.4	*	0.1	0.7	0.6	0.9	0.8	-	0.2	0.2	0.2
	4	0.7	0.1	*	0.1	0.3	0.4	0.5	0.7	-	*	0.3	0.1
	5	0.1	*	-	*	*	0.1	*	0.5	-	-	*	*
	6	-	*	-	*	-	*	-	0.1	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.5	0.6	*	0.2	1.2	1.1	1.4	2.4	-	0.3	0.6	0.4
42	1 - 2	*	*	*	*	*	*	0.1	0.1	-	0.1	*	*
	3	0.8	0.4	0.3	1.0	0.7	0.5	0.4	0.8	-	0.7	0.1	0.6
	4	1.5	0.5	1.1	1.5	1.8	0.7	0.1	0.4	-	0.4	0.3	0.4
	5	0.3	0.1	2.4	0.6	1.2	0.4	0.1	0.4	-	*	0.1	0.1
	6	-	*	1.1	0.1	0.2	0.1	-	0.2	-	*	*	*
	7	*	*	0.1	*	*	*	-	-	-	*	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	2.6	1.1	4.9	3.2	3.9	1.8	0.6	1.8	-	1.2	0.5	1.1

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 15, 2026

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	0.2	*	-	*	-	*	-	*	-	*	*	*
	3	0.8	*	0.1	0.2	*	0.1	0.1	0.1	-	0.1	0.1	*
	4	0.3	0.1	0.1	0.6	0.4	0.3	0.1	*	-	0.1	*	0.1
	5	0.2	0.1	0.8	0.3	0.8	0.4	-	*	-	*	*	*
	6	0.1	*	0.8	0.1	0.4	0.2	-	-	-	*	-	*
	7	-	*	*	*	*	0.1	-	-	-	*	-	*
	8	-	-	-	-	-	*	-	-	-	-	-	*
Total	----	1.6	0.2	1.8	1.3	1.7	1.1	0.2	0.2	-	0.2	0.1	0.2
62	1 - 2	*	*	-	-	-	-	-	-	-	-	-	-
	3	0.2	*	-	*	-	-	-	*	-	*	*	*
	4	*	*	-	*	-	*	-	*	-	*	*	*
	5	-	*	-	*	-	*	-	-	-	*	*	*
	6	-	*	-	*	-	*	-	-	-	-	*	*
	7	-	-	-	*	*	*	-	-	-	-	-	*
	8	-	-	-	-	-	*	-	-	-	-	-	*
Total	----	0.2	*	-	*	*	*	-	*	-	*	*	*
13 & 23	1 - 2	-	*	-	-	-	0.2	-	*	-	-	*	*
	3	-	*	-	-	-	0.1	-	*	-	-	*	*
	4	-	*	-	-	-	*	-	-	-	-	*	*
	5	-	-	-	-	-	-	-	-	-	-	*	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	0.3	-	*	-	-	*	*
33	1 - 2	-	*	-	-	*	*	-	*	-	-	-	*
	3	*	*	-	*	*	*	*	*	-	-	*	*
	4	*	*	*	*	-	*	*	*	-	-	*	*
	5	-	*	*	*	-	*	-	*	-	-	*	*
	6	-	*	-	-	-	*	-	-	-	-	*	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	*	*	*	*	0.1	0.1	0.1	-	-	0.1	*
43	1 - 2	-	-	-	*	-	-	-	*	-	-	*	*
	3	0.2	*	-	*	*	*	-	*	-	*	*	*
	4	0.2	*	*	*	0.1	*	*	0.1	-	*	0.2	*
	5	*	*	*	*	*	*	-	*	-	-	0.2	*
	6	-	*	-	*	*	*	-	*	-	-	0.1	*
	7	-	*	-	-	-	-	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.4	*	0.1	0.1	0.2	0.1	*	0.2	-	*	0.5	0.1
53	1 - 2	*	*	-	-	-	*	-	-	-	-	-	-
	3	0.3	*	-	*	*	*	-	*	-	*	*	*
	4	0.3	*	-	*	*	*	-	*	-	*	*	*
	5	0.1	*	-	*	-	*	-	*	-	*	*	*
	6	-	*	-	*	-	*	-	-	-	-	*	*
	7	-	-	-	*	*	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.6	*	-	*	*	*	-	*	-	*	0.1	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	0.1	*	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.1	*	-	-	-	-	-	-	-	-	-	-
24 - 54	1 - 8	0.1	*	-	*	-	*	-	*	-	-	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	*
31		0.1	*	-	*	-	*	-	-	-	*	*	*
32		0.7	*	-	*	-	*	-	-	-	*	0.1	0.1
33		7.0	0.6	*	0.1	*	*	*	*	-	0.2	1.3	0.9
34		11.5	3.5	0.1	0.3	0.2	0.5	-	0.3	-	2.4	7.6	4.8
35		15.9	11.8	2.0	2.7	2.0	2.8	1.3	2.7	-	12.4	18.1	16.0
36		26.3	24.3	17.4	13.9	7.8	12.1	20.9	17.0	-	29.2	29.9	31.1
37		32.0	41.4	42.0	50.6	41.4	44.8	61.1	43.7	-	35.5	30.3	34.6
38		4.1	14.7	26.7	26.8	31.9	28.7	15.4	22.7	-	15.3	8.9	9.7
39		2.3	3.2	8.6	5.1	12.1	9.1	1.3	12.2	-	4.4	3.0	2.5
40 & Longer		0.1	0.5	3.1	0.6	4.6	1.9	*	1.5	-	0.6	0.7	0.3
Average Staple		35.84	36.62	37.32	37.18	37.58	37.34	36.95	37.29	-	36.64	36.22	36.34
Average Length		1.12	1.14	1.17	1.16	1.18	1.17	1.15	1.16	-	1.14	1.13	1.13

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 15, 2026

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	0.6	5.2	-	4.5	-	*	-	2.0	0.2	0.4	-	45.9
	3	0.5	5.7	-	2.6	*	*	-	1.8	0.7	0.3	-	10.0
	4	0.3	1.3	-	*	-	*	-	*	-	*	-	1.0
	5	*	0.1	-	-	-	-	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.4	12.1	-	7.1	*	*	-	3.8	0.9	0.8	-	56.9
31	1 - 2	0.3	1.1	-	9.2	2.3	1.5	-	3.4	5.2	5.6	-	9.6
	3	3.4	8.6	-	36.6	11.5	9.0	-	20.3	33.9	20.1	-	18.1
	4	4.3	11.1	-	12.3	1.9	1.8	-	8.6	8.4	5.8	-	6.7
	5	1.7	3.3	-	0.8	*	*	-	0.6	0.3	0.3	-	1.1
	6	0.2	0.4	-	*	-	*	-	*	-	*	-	0.1
	7	*	*	-	-	-	-	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	9.9	24.6	-	58.9	15.7	12.3	-	32.9	47.7	31.8	-	35.6
41	1 - 2	0.1	*	-	0.5	6.8	2.4	-	0.9	1.9	3.1	-	*
	3	2.0	1.1	-	10.1	44.5	37.9	-	18.8	30.9	30.0	-	0.7
	4	9.8	5.2	-	16.2	11.4	26.7	-	26.1	16.0	24.8	-	1.0
	5	16.7	8.3	-	4.9	1.2	3.2	-	7.3	1.5	4.5	-	1.2
	6	8.0	4.4	-	0.3	*	0.1	-	0.6	*	0.3	-	0.7
	7	1.8	0.9	-	-	-	*	-	*	-	*	-	0.1
	8	0.2	0.1	-	-	-	-	-	-	-	*	-	-
Total	----	38.5	20.0	-	32.0	63.9	70.3	-	53.6	50.3	62.7	-	3.7
51	1 - 2	-	-	-	*	0.5	0.2	-	*	*	0.1	-	-
	3	-	-	-	*	10.7	4.5	-	1.1	*	0.8	-	-
	4	*	*	-	0.4	5.1	6.0	-	3.3	0.1	1.7	-	*
	5	1.1	0.3	-	0.3	0.4	1.4	-	1.5	*	0.8	-	*
	6	4.9	1.1	-	0.1	*	0.1	-	0.2	-	0.2	-	*
	7	3.2	0.9	-	-	-	*	-	*	-	*	-	-
	8	0.9	0.2	-	-	-	-	-	-	-	*	-	-
Total	----	10.1	2.5	-	0.7	16.7	12.2	-	6.1	0.2	3.6	-	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	*	*	-	*	-	*	-	-
	4	-	-	-	*	*	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	*	*	-	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	*	-	-	-	*	-	-
12 & 22	1 - 2	0.2	1.4	-	0.1	-	-	-	*	-	*	-	0.2
	3	2.3	4.1	-	*	-	*	-	*	-	*	-	0.1
	4	1.5	2.1	-	*	-	-	-	*	-	*	-	0.2
	5	0.2	0.2	-	*	-	-	-	-	-	-	-	-
	6	*	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	4.2	7.8	-	0.1	-	*	-	*	-	*	-	0.5
32	1 - 2	0.1	0.1	-	0.1	-	*	-	*	*	*	-	0.7
	3	3.0	2.6	-	0.3	*	0.1	-	0.2	0.1	0.1	-	0.3
	4	3.9	5.0	-	0.2	*	*	-	0.1	0.1	0.1	-	0.7
	5	2.4	2.9	-	*	-	*	-	*	0.1	*	-	0.6
	6	0.6	0.6	-	*	-	-	-	*	-	-	-	0.2
	7	*	0.1	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	10.1	11.3	-	0.5	0.1	0.1	-	0.3	0.4	0.3	-	2.4
42	1 - 2	*	*	-	*	0.3	0.1	-	*	-	*	-	-
	3	1.1	0.8	-	0.1	1.3	1.4	-	0.6	*	0.3	-	*
	4	3.4	3.3	-	0.4	1.2	1.4	-	1.2	0.2	0.3	-	0.1
	5	5.7	5.3	-	0.1	0.1	0.4	-	0.5	-	0.1	-	0.1
	6	5.5	4.2	-	*	-	0.1	-	0.1	-	*	-	0.1
	7	1.6	1.5	-	-	-	*	-	*	-	*	-	*
	8	0.3	0.2	-	-	-	-	-	-	-	*	-	-
Total	----	17.6	15.4	-	0.6	2.8	3.4	-	2.4	0.2	0.7	-	0.2

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 15, 2026

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	-	*	*	-	*	-	*	-	-
	3	-	-	-	*	0.2	0.5	-	0.1	-	*	-	-
	4	*	*	-	*	0.3	0.8	-	0.2	-	*	-	-
	5	*	*	-	*	*	0.3	-	0.3	-	*	-	-
	6	0.2	0.3	-	*	*	*	-	0.1	-	*	-	-
	7	0.4	0.5	-	-	-	*	-	*	-	*	-	-
	8	0.5	0.3	-	-	-	-	-	-	-	*	-	-
Total	----	1.2	1.1	-	*	0.6	1.6	-	0.7	-	0.1	-	-
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	*	-	*	-	*	-	-
13 & 23	1 - 2	-	0.1	-	-	-	-	-	-	-	*	-	-
	3	0.3	0.8	-	-	-	-	-	-	-	*	-	*
	4	0.6	0.6	-	-	-	-	-	-	-	*	-	*
	5	0.2	0.1	-	-	-	-	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	1.1	1.6	-	-	-	-	-	-	-	*	-	*
33	1 - 2	-	*	-	-	-	*	-	*	-	*	-	*
	3	0.3	0.1	-	*	-	*	-	*	*	*	-	0.1
	4	1.8	0.6	-	*	-	*	-	*	-	*	-	0.3
	5	1.1	0.4	-	*	-	-	-	-	-	*	-	0.2
	6	0.3	0.1	-	-	-	-	-	-	-	*	-	*
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	3.5	1.3	-	*	-	*	-	*	*	*	-	0.7
43	1 - 2	-	-	-	*	-	*	-	-	-	*	-	-
	3	*	*	-	*	*	*	-	*	*	*	-	*
	4	0.3	0.3	-	*	0.1	*	-	*	0.2	*	-	-
	5	0.8	0.6	-	*	*	*	-	*	*	*	-	*
	6	0.7	0.7	-	-	-	*	-	*	-	*	-	*
	7	0.3	0.3	-	-	-	-	-	-	-	*	-	-
	8	0.2	0.1	-	-	-	-	-	-	-	*	-	-
Total	----	2.2	2.0	-	*	0.1	0.1	-	*	0.2	*	-	*
53	1 - 2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	*	-	-	-	*	-	*	-	*	-	-
	4	-	*	-	-	*	*	-	*	-	*	-	-
	5	-	*	-	-	*	*	-	*	-	*	-	-
	6	*	*	-	-	-	*	-	*	-	*	-	-
	7	*	0.1	-	-	-	-	-	*	-	*	-	-
	8	0.1	0.1	-	-	-	-	-	-	-	*	-	-
Total	----	0.1	0.2	-	-	*	*	-	*	-	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	-	-	*	-	-	-	-
24 - 54	1 - 8	*	0.1	-	-	-	*	-	-	-	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	*	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		-	*	-	-	-	-	-	*	-	*	-	-
32		*	*	-	-	-	*	-	*	-	*	-	-
33		0.2	0.2	-	0.1	*	*	-	0.2	-	0.1	-	*
34		0.6	1.0	-	1.1	0.4	0.2	-	2.1	2.5	1.4	-	2.3
35		3.9	4.2	-	10.0	2.0	1.8	-	11.5	16.0	8.1	-	10.2
36		11.3	12.3	-	26.9	15.7	10.5	-	27.7	46.3	24.2	-	15.6
37		45.2	31.4	-	42.1	61.2	48.9	-	36.4	31.4	49.0	-	32.0
38		25.5	32.7	-	15.0	19.5	33.2	-	15.0	2.8	14.2	-	32.7
39		11.0	16.0	-	4.4	1.3	4.9	-	5.4	0.9	2.7	-	6.2
40 & Longer		2.2	2.3	-	0.4	*	0.3	-	1.5	*	0.3	-	1.0
Average Staple		37.32	37.47	-	36.75	37.01	37.29	-	36.72	36.19	36.75	-	37.05
Average Length		1.17	1.17	-	1.15	1.15	1.17	-	1.15	1.13	1.15	-	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Jan 15, 2026											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	32.1	45.9	0.1	0.3	-	0.4	42.0	44.5	-	0.9
	3	4.1	7.5	0.1	0.4	-	0.1	9.7	13.3	-	1.3
	4	*	0.2	-	*	-	*	0.4	0.9	-	0.1
	5	-	*	-	-	-	*	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	36.3	53.6	0.2	0.8	-	0.5	52.1	58.8	-	2.2
31	1 - 2	19.5	13.9	1.8	2.3	-	6.9	8.5	3.7	-	8.7
	3	21.9	18.3	19.1	15.0	-	14.5	8.6	10.2	-	38.3
	4	3.9	3.6	12.6	5.5	-	3.2	2.1	4.2	-	8.2
	5	0.2	0.2	0.7	0.2	-	0.2	0.2	0.5	-	0.5
	6	-	*	-	*	-	*	*	*	-	*
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	45.5	36.1	34.2	23.0	-	24.8	19.5	18.6	-	55.7
41	1 - 2	1.4	0.4	0.4	1.9	-	7.7	0.2	0.2	-	1.7
	3	6.0	1.5	25.6	32.0	-	35.8	0.9	1.8	-	21.6
	4	3.7	1.3	31.3	31.5	-	14.2	0.6	1.7	-	15.6
	5	0.9	0.5	6.6	4.7	-	1.8	0.4	0.5	-	2.6
	6	0.1	0.1	0.5	0.1	-	0.1	0.2	0.1	-	0.1
	7	*	*	-	*	-	*	*	*	-	*
	8	-	-	-	-	-	-	*	*	-	-
Total	----	12.1	3.7	64.3	70.3	-	59.6	2.3	4.4	-	41.7
51	1 - 2	-	*	-	0.1	-	0.2	-	*	-	*
	3	*	*	0.3	1.8	-	2.4	*	0.1	-	*
	4	0.2	*	0.9	2.4	-	2.2	*	0.1	-	0.1
	5	0.3	*	0.1	0.7	-	0.5	*	*	-	*
	6	0.1	*	-	0.1	-	*	*	*	-	*
	7	*	*	-	*	-	*	*	*	-	*
	8	-	*	-	-	-	-	*	*	-	-
Total	----	0.7	0.1	1.2	5.0	-	5.3	0.1	0.3	-	0.2
61	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	*	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	*	-	-
12 & 22	1 - 2	0.3	2.1	-	-	-	*	8.1	6.8	-	-
	3	0.4	1.0	-	*	-	*	4.5	3.7	-	*
	4	0.1	0.1	-	-	-	*	0.5	0.6	-	*
	5	*	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	0.7	3.2	-	*	-	*	13.1	11.1	-	*
32	1 - 2	0.2	0.3	-	*	-	0.2	1.9	0.6	-	*
	3	1.1	1.1	*	0.1	-	0.5	2.7	1.7	-	*
	4	0.6	0.5	*	0.1	-	0.1	1.4	1.2	-	*
	5	0.1	0.1	-	*	-	*	0.3	0.3	-	*
	6	*	*	-	*	-	-	*	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	2.1	2.0	0.1	0.1	-	0.8	6.4	3.8	-	0.1
42	1 - 2	*	*	-	*	-	0.9	*	*	-	*
	3	0.1	0.1	*	0.2	-	5.0	0.2	0.3	-	*
	4	0.1	0.2	-	0.4	-	1.5	0.4	0.5	-	*
	5	0.1	0.1	-	0.1	-	0.1	0.2	0.3	-	*
	6	0.1	*	-	*	-	*	0.1	0.1	-	*
	7	*	*	-	-	-	-	*	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
Total	----	0.6	0.4	*	0.7	-	7.5	0.9	1.2	-	0.1

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 15, 2026

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	*	-	*	-	-
	3	*	*	-	*	-	0.7	*	*	-	-
	4	*	*	*	0.1	-	0.5	*	*	-	*
	5	*	*	-	*	-	0.1	*	*	-	*
	6	*	*	-	*	-	*	*	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	*	*	-	-	-	-	*	*	-	-
	Total	----	*	*	0.1	-	1.3	0.1	0.1	-	*
62	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	-	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
	Total	----	-	*	-	-	*	-	*	-	-
13 & 23	1 - 2	0.4	0.1	-	-	-	-	1.6	0.5	-	-
	3	1.0	0.2	-	-	-	-	1.0	0.4	-	*
	4	0.1	*	-	-	-	-	0.1	0.1	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
	Total	----	1.5	0.3	-	-	-	2.7	1.0	-	*
33	1 - 2	0.1	0.1	-	-	-	*	0.4	0.1	-	-
	3	0.2	0.2	-	*	-	*	1.0	0.3	-	*
	4	0.1	0.1	-	*	-	*	0.6	0.2	-	*
	5	-	*	-	*	-	-	0.3	0.1	-	*
	6	-	*	-	-	-	-	0.1	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
	Total	----	0.3	0.5	-	*	-	2.3	0.6	-	*
43	1 - 2	-	*	-	*	-	*	*	*	-	-
	3	*	*	-	*	-	*	*	*	-	*
	4	*	*	-	*	-	*	0.1	*	-	*
	5	*	*	-	*	-	*	*	*	-	*
	6	*	*	-	-	-	*	*	*	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
	Total	----	0.1	0.1	-	*	-	0.2	0.1	-	*
53	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	*	-	*	-	*	-	*	-	-
	4	-	*	-	*	-	*	-	*	-	-
	5	-	*	-	*	-	*	-	*	-	-
	6	-	*	-	-	-	-	-	*	-	-
	7	-	*	-	*	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
	Total	----	-	*	-	*	-	*	*	-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	-	-	-	-	-	-	*	-	-
24 - 54	1 - 8	*	0.1	-	*	-	-	0.4	0.1	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	*	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	*	*	-	-
30		-	-	-	-	-	-	*	*	-	-
31		*	*	-	-	-	-	0.1	0.1	-	-
32		0.1	*	0.1	*	-	*	0.8	0.5	-	*
33		0.2	0.3	1.5	0.2	-	0.1	4.3	2.6	-	*
34		2.0	1.8	2.0	1.9	-	2.6	14.4	7.9	-	0.6
35		4.7	6.2	6.3	9.5	-	9.5	23.3	15.0	-	5.5
36		12.4	13.2	31.2	33.9	-	30.9	26.1	21.9	-	23.0
37		27.4	27.0	36.9	41.3	-	44.3	23.1	32.4	-	55.3
38		22.0	20.0	18.1	10.0	-	11.3	5.6	14.2	-	12.8
39		14.2	18.5	3.8	2.6	-	1.3	1.1	4.3	-	2.6
40 & Longer		17.1	13.0	0.1	0.3	-	0.1	1.2	1.1	-	0.1
Average Staple		37.79	37.67	36.70	36.57	-	36.56	35.78	36.38	-	36.82
Average Length		1.18	1.18	1.15	1.14	-	1.14	1.12	1.14	-	1.15

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 15, 2026

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	2.1	0.5	*	*	0.1	0.1	0.3	0.1	-	1.5	5.0	1.4
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	-	0.1	-	0.1	*	1.2	-	0.1	0.1	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	*	*	-	*	0.1	*	-	*	-	-	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.6	0.1	-	1.0	*	*	-	-	-	0.3	0.1	0.3
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	-	-	-	-	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	*	*	-	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	-	-	-	-	-	-	-
23	*	*	-	*	-	-	-	-	-	-	-	*
24	*	*	-	*	-	*	-	*	-	-	0.1	*
25	0.1	*	*	*	*	0.1	-	*	-	*	0.5	0.1
26	1.5	0.1	*	*	0.1	0.4	0.4	0.4	-	*	3.3	0.6
27	11.4	1.4	0.1	0.2	0.9	1.8	0.7	1.6	-	0.4	11.0	3.4
28	18.5	7.8	0.5	1.9	7.4	7.0	7.8	8.6	-	3.3	20.8	10.9
29	21.2	21.6	6.3	11.6	15.4	14.1	24.2	17.2	-	13.1	24.4	21.0
30	17.6	29.2	25.2	34.4	23.8	21.8	21.9	17.8	-	26.8	19.1	25.0
31	12.6	21.7	27.0	33.3	21.6	21.7	25.3	13.9	-	27.4	11.7	19.4
32	14.9	11.3	19.3	13.4	13.5	14.9	6.7	5.2	-	16.9	6.1	11.2
33	2.0	4.6	12.4	3.9	7.6	8.9	4.2	4.7	-	7.3	2.4	5.3
34	0.1	1.7	4.7	1.0	4.4	5.6	7.2	8.9	-	3.8	0.5	2.1
35	*	0.4	2.8	0.2	3.0	2.3	1.3	11.5	-	0.9	0.1	0.7
36	*	0.1	1.3	0.1	1.5	0.9	0.1	7.5	-	0.1	*	0.2
37	-	*	0.3	*	0.7	0.4	0.1	2.4	-	*	*	0.1
38	-	*	*	*	0.1	*	*	0.2	-	-	*	*
39	-	-	*	*	0.1	*	-	0.1	-	-	-	*
40 & Above	-	-	*	*	-	*	-	0.1	-	-	-	*
Average	29.94	30.70	31.83	31.06	31.30	31.30	30.91	32.00	-	31.27	29.64	30.61
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	-	*	-	-	-	-	-	-	-	-	-	-
2.6	-	*	-	-	*	*	-	-	-	-	-	*
2.7	-	*	-	-	0.1	*	-	*	-	-	-	*
2.8	-	*	-	*	0.2	*	-	-	-	-	*	*
2.9	-	*	-	-	0.2	*	-	0.1	-	-	*	*
3.0	*	*	-	*	0.1	*	-	*	-	-	0.1	*
3.1	0.1	*	-	*	0.1	0.1	-	0.3	-	*	0.1	*
3.2	0.3	*	-	*	0.1	0.1	-	0.2	-	0.1	0.3	0.1
3.3	1.2	0.1	-	*	0.2	0.1	0.3	0.2	-	0.1	0.9	0.2
3.4	1.6	0.4	-	*	0.5	0.2	-	0.3	-	0.1	1.6	0.3
3.5	1.9	0.8	-	*	0.9	0.4	-	0.7	-	0.5	1.6	0.6
3.6	2.6	1.1	*	0.1	1.8	0.7	0.4	1.2	-	0.7	2.2	1.1
3.7	3.3	1.9	0.1	0.1	2.0	1.3	0.8	1.9	-	1.2	3.9	1.8
3.8	4.6	2.9	0.2	0.1	1.7	1.6	1.0	4.6	-	1.3	7.4	2.8
3.9	6.9	4.4	0.3	0.3	2.2	2.6	3.5	6.8	-	2.1	9.0	4.0
4.0	5.1	5.8	1.1	0.6	5.4	4.3	10.7	8.7	-	3.4	10.1	5.6
4.1	6.5	7.9	2.5	1.0	9.0	6.8	17.5	10.0	-	5.6	10.0	7.3
4.2	6.8	9.8	4.0	1.7	9.6	8.7	23.4	11.6	-	7.1	10.8	8.9
4.3	10.5	10.8	5.8	3.0	14.8	9.9	16.4	8.9	-	9.7	9.9	9.8
4.4	11.9	10.7	9.6	5.0	17.7	10.9	5.1	6.3	-	12.3	8.3	10.0
4.5	14.0	10.2	14.1	7.7	10.2	12.6	4.7	6.2	-	13.0	8.0	9.8
4.6	10.8	9.1	12.7	11.7	6.1	11.8	7.7	6.4	-	11.2	6.9	9.3
4.7	4.9	7.2	9.9	14.5	3.7	8.9	3.7	6.8	-	12.4	4.7	8.4
4.8	2.5	5.7	8.1	15.4	3.1	6.8	1.4	5.3	-	8.4	2.1	6.8
4.9	2.6	4.3	10.3	13.7	2.9	5.1	2.4	4.4	-	5.2	1.0	5.2
5.0	1.0	2.9	10.1	10.9	2.0	3.4	1.0	3.0	-	3.2	0.5	3.7
5.1	0.1	1.8	6.5	7.1	1.3	1.3	0.4	2.7	-	1.7	0.4	2.3
5.2	0.6	1.1	3.3	4.1	1.0	0.9	-	1.3	-	0.5	0.2	1.2
5.3	*	0.6	1.2	1.9	0.6	0.5	-	1.0	-	0.1	*	0.6
5.4	0.2	0.3	0.1	0.6	0.5	0.2	-	0.7	-	0.1	-	0.2
5.5 & Above	0.1	0.2	*	0.2	1.9	0.5	-	0.2	-	0.1	-	0.1
Average	4.27	4.39	4.67	4.76	4.36	4.45	4.26	4.35	-	4.48	4.17	4.42

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 15, 2026

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	64.0	33.3	-	0.1	*	*	-	*	0.8	1.6	-	1.1
Bark - Level 2	*	*	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	-	*	-	*	-	*	-	*	-	0.6
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	-	-	*	-	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	0.1	-	0.4	-	0.2	-	0.3	0.3	0.5	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	-	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	*	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	*	-	-	-	-	-	*
23	-	*	-	-	-	*	-	-	-	-	-	-
24	*	*	-	-	*	*	-	*	0.1	*	-	-
25	0.2	0.1	-	*	*	*	-	*	0.6	*	-	*
26	0.3	0.4	-	*	*	*	-	0.1	3.0	0.3	-	0.2
27	0.9	0.9	-	0.5	0.1	0.1	-	1.0	10.1	2.2	-	1.9
28	1.9	1.9	-	4.4	2.8	0.7	-	4.8	20.2	10.9	-	7.6
29	3.4	3.6	-	19.0	18.7	7.9	-	15.6	24.3	28.1	-	22.6
30	9.1	8.5	-	33.2	53.1	36.7	-	26.9	19.7	31.6	-	32.8
31	17.8	17.3	-	21.1	19.0	35.9	-	26.3	14.9	17.4	-	17.1
32	25.7	24.6	-	11.7	4.4	13.1	-	16.1	4.3	6.9	-	11.7
33	24.2	22.6	-	5.1	1.8	4.5	-	6.5	1.7	2.1	-	4.4
34	10.2	13.3	-	2.9	0.2	1.0	-	2.3	0.8	0.4	-	1.6
35	3.8	5.4	-	1.8	*	0.1	-	0.4	0.2	0.1	-	0.1
36	1.4	1.1	-	0.2	*	*	-	*	*	*	-	-
37	0.8	0.3	-	*	*	*	-	*	-	-	-	*
38	0.1	0.1	-	*	-	*	-	*	-	-	-	-
39	*	*	-	-	-	-	-	-	-	-	-	-
40 & Above	*	*	-	-	-	-	-	*	-	-	-	-
Average	32.50	32.56	-	30.97	30.54	31.16	-	31.06	29.66	30.26	-	30.61
Mike												
2.4 & Below	0.7	0.2	-	-	-	-	-	-	-	-	-	-
2.5	2.1	0.9	-	-	-	-	-	-	-	*	-	-
2.6	1.6	1.1	-	*	-	-	-	-	-	-	-	-
2.7	1.8	1.6	-	*	-	-	-	-	-	*	-	*
2.8	1.8	1.9	-	-	-	-	-	-	-	*	-	2.1
2.9	2.2	2.1	-	*	-	-	-	-	-	*	-	1.9
3.0	2.9	2.4	-	*	-	-	-	-	-	*	-	1.2
3.1	3.6	3.0	-	*	-	*	-	-	-	*	-	0.5
3.2	4.9	3.7	-	*	-	*	-	*	-	0.1	-	1.4
3.3	3.8	4.2	-	*	*	*	-	*	*	0.2	-	0.9
3.4	5.4	5.4	-	0.1	-	*	-	*	0.1	0.3	-	0.6
3.5	6.3	5.9	-	0.1	0.1	*	-	0.1	0.2	0.5	-	1.1
3.6	6.3	6.6	-	0.1	0.2	0.1	-	0.1	0.4	0.9	-	1.3
3.7	5.7	6.8	-	0.2	0.3	0.2	-	0.2	0.6	1.5	-	3.4
3.8	5.7	6.7	-	0.3	1.0	0.4	-	0.3	3.0	2.4	-	5.7
3.9	4.6	6.4	-	0.6	1.1	0.6	-	0.4	5.4	3.5	-	8.5
4.0	5.6	6.8	-	1.3	3.5	1.4	-	0.8	6.3	4.9	-	7.6
4.1	7.3	7.5	-	2.2	4.5	2.4	-	1.3	8.8	7.0	-	7.5
4.2	7.1	6.0	-	3.4	7.9	4.3	-	2.0	10.2	9.2	-	8.1
4.3	7.3	6.1	-	4.9	9.7	6.7	-	3.0	9.5	11.6	-	10.4
4.4	5.7	5.2	-	6.3	11.4	9.7	-	4.5	7.1	12.2	-	8.6
4.5	2.8	3.6	-	8.2	16.8	13.0	-	6.2	7.9	11.3	-	9.0
4.6	1.2	2.1	-	9.7	14.5	15.1	-	8.7	8.5	10.1	-	6.9
4.7	2.1	1.7	-	11.2	11.1	15.7	-	11.2	13.6	8.6	-	5.8
4.8	1.3	1.3	-	12.6	10.2	13.3	-	13.6	8.8	6.1	-	3.5
4.9	0.3	0.6	-	11.7	5.7	8.7	-	14.6	6.3	4.2	-	2.6
5.0	*	0.3	-	9.6	1.7	4.9	-	13.3	2.9	2.7	-	1.1
5.1	-	*	-	7.7	0.4	2.3	-	9.9	0.2	1.5	-	0.1
5.2	-	*	-	4.4	*	0.9	-	5.7	0.1	0.7	-	0.1
5.3	-	-	-	2.6	*	0.3	-	2.6	-	0.3	-	*
5.4	-	-	-	1.3	-	0.1	-	1.0	-	0.1	-	-
5.5 & Above	-	-	-	1.4	-	*	-	0.4	-	*	-	-
Average	3.73	3.78	-	4.74	4.49	4.61	-	4.80	4.41	4.41	-	4.15

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Jan 15, 2026										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	6.2	2.3	1.7	3.3	-	*	11.9	4.1	-	1.3
Bark - Level 2	-	*	-	-	-	-	*	*	-	-
Grass - Level 1	0.5	0.1	-	0.1	-	*	0.2	0.2	-	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	-	-	-	*	-	-	-	*	-	*
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	0.9	1.7	-	*	0.9	0.3	-	0.6
Seed Coat - Level 2	-	*	-	-	-	-	*	*	-	-
Oil - Level 1	*	*	-	*	-	-	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	*	-	-
Other - Level 1	-	*	-	-	-	-	*	*	-	-
Other - Level 2	-	*	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	*	*	-	-	-	-	*	*	-	-
23	-	*	-	-	-	-	*	*	-	-
24	-	*	0.1	*	-	*	0.1	0.1	-	*
25	*	*	0.5	*	-	*	0.4	0.2	-	*
26	0.1	0.2	2.8	0.4	-	*	1.4	0.8	-	1.1
27	0.2	0.7	3.5	2.5	-	0.5	5.0	2.8	-	6.2
28	1.7	3.0	9.4	12.5	-	3.8	12.0	7.7	-	19.0
29	6.2	8.6	26.2	34.8	-	21.0	20.4	15.7	-	32.2
30	13.9	14.8	32.8	30.4	-	38.7	23.5	20.9	-	25.6
31	19.4	18.4	16.6	13.3	-	24.7	17.7	18.6	-	11.1
32	17.2	16.9	6.9	4.7	-	8.2	10.4	13.4	-	3.6
33	15.9	15.3	1.0	1.2	-	2.4	5.3	9.5	-	0.8
34	10.6	11.5	0.1	0.2	-	0.7	2.4	6.3	-	0.2
35	7.7	6.4	*	*	-	0.1	0.8	2.7	-	*
36	4.2	2.5	-	*	-	*	0.3	0.9	-	*
37	2.0	1.3	-	*	-	*	0.1	0.3	-	-
38	0.7	0.3	-	-	-	-	*	0.1	-	-
39	0.1	*	-	-	-	-	*	*	-	-
40 & Above	*	*	-	-	-	-	*	*	-	-
Average	32.62	32.30	30.10	30.03	-	30.66	30.48	31.22	-	29.73
Mike										
2.4 & Below	-	*	-	-	-	-	0.1	*	-	-
2.5	0.1	*	-	-	-	-	0.2	*	-	-
2.6	*	*	-	-	-	-	0.2	0.1	-	-
2.7	*	*	-	-	-	*	0.3	0.1	-	*
2.8	0.1	*	-	*	-	*	0.5	0.2	-	*
2.9	0.2	0.1	-	*	-	*	0.8	0.4	-	*
3.0	0.1	0.1	*	*	-	*	1.2	0.6	-	0.1
3.1	0.1	0.2	-	*	-	*	1.6	0.8	-	0.1
3.2	0.4	0.4	-	0.1	-	*	2.2	1.2	-	0.1
3.3	0.9	0.7	*	0.2	-	*	2.5	1.6	-	0.2
3.4	1.0	1.0	0.2	0.3	-	0.1	2.9	2.1	-	0.4
3.5	1.4	1.5	0.1	0.4	-	0.3	3.6	2.7	-	0.7
3.6	3.1	2.7	0.8	0.8	-	0.3	4.3	3.4	-	1.3
3.7	4.1	3.9	2.4	1.7	-	0.8	4.7	4.1	-	2.6
3.8	4.6	5.3	3.9	2.5	-	1.1	5.0	5.1	-	3.9
3.9	6.6	7.1	4.9	4.0	-	1.7	5.6	6.3	-	6.7
4.0	7.7	8.6	6.0	5.5	-	2.5	6.4	7.5	-	9.2
4.1	8.2	10.0	6.8	6.9	-	3.9	7.5	8.6	-	11.5
4.2	11.9	10.1	12.3	8.4	-	5.3	8.2	9.6	-	14.1
4.3	13.0	11.0	19.9	9.9	-	6.7	8.6	9.8	-	14.5
4.4	11.4	10.1	15.0	10.6	-	9.5	8.0	9.2	-	12.8
4.5	10.5	9.4	8.1	10.7	-	11.8	7.1	8.0	-	9.1
4.6	6.8	7.5	6.0	10.0	-	13.4	6.2	6.5	-	5.9
4.7	4.6	5.2	5.3	8.7	-	13.4	5.1	4.8	-	3.2
4.8	1.5	2.9	3.4	7.0	-	11.8	3.2	3.2	-	1.8
4.9	1.2	1.4	2.0	5.1	-	8.1	1.8	1.9	-	1.1
5.0	0.2	0.6	1.4	3.4	-	5.4	1.1	1.1	-	0.6
5.1	*	0.1	0.5	2.0	-	2.7	0.6	0.6	-	0.2
5.2	*	*	0.9	1.0	-	1.0	0.3	0.3	-	*
5.3	-	*	0.1	0.4	-	0.3	0.1	0.2	-	*
5.4	-	-	-	0.2	-	*	*	0.1	-	*
5.5 & Above	-	*	-	0.1	-	*	*	0.1	-	*
Average	4.19	4.21	4.32	4.43	-	4.56	4.08	4.16	-	4.23

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE												
For The Week Ending Jan 15, 2026												
Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	*	-	-	*	*	-	-	-	-	-	*
2.7 - 2.9	-	*	-	*	0.5	0.1	-	0.1	-	-	*	*
3.0 - 3.2	0.4	0.1	-	*	0.3	0.2	-	0.5	-	0.1	0.5	0.1
3.3 - 3.4	2.8	0.5	-	*	0.8	0.4	0.3	0.6	-	0.1	2.5	0.5
3.5 - 3.6	4.5	1.8	*	0.1	2.7	1.1	0.4	1.9	-	1.2	3.8	1.7
3.7 - 4.2	33.2	32.7	8.2	3.9	30.0	25.3	56.8	43.7	-	20.7	51.2	30.4
4.3 - 4.9	57.2	58.0	70.5	71.1	58.5	66.1	41.2	44.3	-	72.1	40.9	59.2
5.0 - 5.2	1.6	5.8	20.0	22.1	4.3	5.7	1.3	7.0	-	5.4	1.1	7.2
5.3 & Above	0.3	1.1	1.3	2.8	3.0	1.2	-	1.9	-	0.3	*	0.9
Average	4.27	4.39	4.67	4.76	4.36	4.45	4.26	4.35	-	4.48	4.17	4.42
Leaf												
1 - 2	10.3	15.4	1.2	2.1	20.4	36.7	27.4	43.8	-	7.8	12.8	14.7
3	56.8	54.9	35.2	38.9	32.6	33.1	54.8	39.6	-	52.7	57.6	58.5
4	29.9	25.4	38.5	45.7	30.7	20.2	16.9	12.1	-	34.5	25.9	23.6
5	2.6	3.9	20.7	11.9	13.4	7.6	0.8	3.8	-	4.8	3.4	3.0
6	0.3	0.3	4.3	1.3	2.6	1.9	*	0.8	-	0.3	0.2	0.2
7	*	*	0.2	0.1	0.3	0.4	-	-	-	*	*	*
8	-	*	-	-	*	*	-	-	-	-	-	*
Average	3.26	3.18	3.92	3.72	3.42	2.99	2.83	2.71	-	3.37	3.21	3.15
HVI Trash 1/												
00	-	-	-	-	-	*	-	*	-	-	-	-
01	0.7	2.0	*	0.1	7.7	14.8	11.7	16.0	-	0.9	0.8	1.4
02	14.3	17.6	2.0	3.1	15.8	27.3	21.3	32.9	-	9.4	17.0	19.8
03	30.2	28.0	13.9	14.6	17.3	17.8	28.6	23.4	-	23.4	29.9	31.9
04	28.5	23.8	22.1	24.5	17.5	13.9	20.5	12.9	-	28.1	24.5	23.6
05	16.5	14.5	19.6	22.9	14.3	9.9	11.4	6.5	-	19.3	14.3	12.7
06	6.4	7.5	14.9	16.0	11.4	6.6	4.5	3.6	-	10.3	7.7	6.0
07	2.1	3.7	11.5	9.4	6.8	4.1	1.3	2.1	-	4.8	3.3	2.6
08	0.7	1.6	7.3	4.9	4.3	2.5	0.4	1.4	-	2.2	1.5	1.1
09	0.3	0.7	4.4	2.5	2.3	1.5	0.2	0.8	-	0.9	0.6	0.5
10	0.2	0.3	2.4	1.2	1.1	0.8	0.1	0.4	-	0.5	0.2	0.2
11	0.1	0.1	1.2	0.5	0.8	0.5	*	0.2	-	0.2	0.1	0.1
12	0.1	0.1	0.5	0.2	0.2	0.2	-	0.1	-	0.1	0.1	*
13	*	*	0.2	0.1	0.2	0.1	-	*	-	*	*	*
14	-	*	*	*	0.1	0.1	-	*	-	*	*	*
15	*	*	*	*	0.1	*	-	-	-	*	*	*
16	-	*	-	-	*	*	-	-	-	*	*	*
17	-	*	-	-	*	*	-	-	-	*	*	*
18 & Above	*	*	-	-	-	*	-	-	-	*	-	*
Average	0.38	0.38	0.55	0.51	0.43	0.35	0.32	0.30	-	0.43	0.38	0.37
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	-	-	-	-	-	-	-	-	-	-	*
76	*	*	-	*	*	*	-	*	-	*	*	*
77	*	*	*	*	*	*	*	*	-	*	0.2	0.1
78	2.8	0.3	0.1	0.1	0.3	0.2	0.1	0.9	-	0.1	1.7	0.9
79	9.1	2.6	0.4	0.5	2.3	1.8	0.5	5.4	-	1.1	10.0	5.5
80	23.4	13.3	3.2	3.9	14.3	12.4	28.2	21.6	-	7.8	23.2	21.3
81	43.9	31.9	20.6	20.5	32.7	34.9	55.0	28.4	-	37.1	33.2	36.3
82	17.8	34.9	37.8	42.8	38.6	39.7	16.0	26.3	-	41.9	23.0	26.4
83	2.8	14.7	28.7	27.7	10.4	9.9	0.1	13.4	-	10.9	7.6	8.1
84	0.1	2.0	7.8	4.3	1.2	0.9	-	3.8	-	1.1	1.0	1.3
85 & Above	-	0.2	1.4	0.3	0.1	*	-	0.1	-	0.1	0.1	0.1
Average	81.17	81.96	82.65	82.52	81.88	81.90	81.34	81.75	-	82.02	81.38	81.56
Tenderable 3/	83.9	90.1	71.8	69.9	83.3	86.6	96.8	85.3	-	91.0	89.7	88.3
SAMPLES CLASSED	7,106	531,511	17,694	1,376,606	16,876	155,064	4,507	66,921	-	90,067	46,937	1,677,176

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 15, 2026

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	0.7	0.2	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	3.7	2.0	-	*	-	-	-	-	-	*	-	-
2.7 - 2.9	5.9	5.7	-	*	-	-	-	-	-	*	-	4.0
3.0 - 3.2	11.3	9.1	-	*	-	*	-	*	-	0.2	-	3.1
3.3 - 3.4	9.2	9.6	-	0.1	*	*	-	*	0.1	0.5	-	1.6
3.5 - 3.6	12.6	12.4	-	0.2	0.3	0.1	-	0.2	0.7	1.4	-	2.5
3.7 - 4.2	36.0	40.2	-	8.1	18.2	9.2	-	5.0	34.3	28.4	-	40.8
4.3 - 4.9	20.7	20.6	-	64.6	79.3	82.1	-	61.8	61.7	64.1	-	46.7
5.0 - 5.2	*	0.3	-	21.7	2.1	8.1	-	29.0	3.2	5.0	-	1.3
5.3 & Above	-	-	-	5.2	*	0.5	-	4.0	-	0.4	-	*
Average	3.73	3.78	-	4.74	4.49	4.61	-	4.80	4.41	4.41	-	4.15
Leaf												
1 - 2	1.3	8.0	-	14.2	9.8	4.2	-	6.3	7.3	9.1	-	56.3
3	13.0	23.9	-	49.8	68.3	53.3	-	42.8	65.7	51.7	-	29.3
4	25.9	29.4	-	29.5	20.0	36.8	-	39.7	25.0	32.7	-	10.0
5	29.9	21.5	-	6.1	1.8	5.3	-	10.1	1.9	5.8	-	3.2
6	20.3	11.8	-	0.4	0.1	0.3	-	1.0	*	0.5	-	1.0
7	7.4	4.3	-	-	-	*	-	*	-	0.1	-	0.2
8	2.2	1.1	-	-	-	-	-	-	-	*	-	-
Average	4.86	4.22	-	3.28	3.14	3.44	-	3.57	3.22	3.37	-	2.52
HVI Trash 1/												
00	-	-	-	-	-	*	-	-	-	-	-	-
01	0.1	1.9	-	1.9	0.3	0.2	-	0.5	0.2	0.8	-	22.6
02	1.9	7.8	-	15.0	14.7	6.4	-	7.7	9.9	11.0	-	36.8
03	5.3	10.9	-	24.4	36.4	23.5	-	19.0	32.2	24.3	-	19.1
04	8.4	12.7	-	23.2	28.4	28.7	-	23.6	29.8	25.5	-	10.1
05	9.6	12.5	-	16.2	12.9	20.7	-	19.9	16.7	18.3	-	5.4
06	9.6	10.7	-	9.6	4.9	11.3	-	13.3	7.2	10.6	-	2.6
07	10.3	9.2	-	5.2	1.7	5.3	-	7.9	2.7	5.3	-	1.6
08	10.8	8.0	-	2.5	0.6	2.3	-	4.2	1.0	2.4	-	1.0
09	9.9	6.5	-	1.2	0.2	1.0	-	2.1	0.3	1.0	-	0.5
10	8.4	5.1	-	0.5	*	0.4	-	1.0	*	0.4	-	0.1
11	7.0	4.1	-	0.2	*	0.2	-	0.5	*	0.2	-	0.1
12	6.0	3.2	-	0.1	-	0.1	-	0.2	-	0.1	-	0.1
13	4.1	2.4	-	*	-	*	-	0.1	-	*	-	*
14	3.0	1.7	-	*	-	*	-	*	-	*	-	-
15	2.0	1.1	-	-	-	*	-	*	-	*	-	-
16	1.3	0.8	-	-	-	-	-	-	-	*	-	-
17	0.8	0.5	-	-	-	-	-	-	-	*	-	-
18 & Above	1.4	0.9	-	-	-	-	-	-	-	*	-	-
Average	0.83	0.66	-	0.41	0.36	0.44	-	0.47	0.39	0.43	-	0.26
UNIFORMITY 2/												
74 & Below	*	*	-	-	-	-	-	-	-	*	-	-
75	0.1	0.1	-	-	-	-	-	-	-	*	-	*
76	0.5	0.5	-	-	-	*	-	*	-	*	-	*
77	1.9	1.6	-	-	*	*	-	*	*	*	-	0.1
78	3.4	3.7	-	0.1	*	0.1	-	0.2	0.5	0.6	-	1.1
79	7.3	7.7	-	1.2	0.1	0.2	-	1.3	2.3	2.9	-	5.4
80	18.5	17.2	-	7.1	2.6	2.2	-	8.8	18.7	10.8	-	17.2
81	32.9	32.5	-	30.1	25.9	16.6	-	30.1	34.3	27.2	-	38.1
82	21.2	24.8	-	40.4	55.4	50.4	-	38.1	32.4	35.4	-	29.5
83	10.6	10.1	-	18.5	15.8	27.8	-	18.1	10.4	20.0	-	8.3
84	3.4	1.8	-	2.6	0.2	2.5	-	3.3	1.3	2.7	-	0.3
85 & Above	0.3	0.1	-	0.1	*	0.2	-	0.1	*	0.2	-	*
Average	81.45	81.43	-	82.20	82.29	82.56	-	82.18	81.78	82.11	-	81.59
Tenderable 3/	17.7	37.9	-	71.5	94.4	86.7	-	63.7	94.8	90.7	-	87.3
SAMPLES CLASSED	17,630	116,158	-	223,299	15,399	671,156	-	706,510	4,444	645,891	-	9,488

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Jan 15, 2026										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	*	-	-	-	-	0.1	*	-	-
2.5 - 2.6	0.2	*	-	-	-	-	0.4	0.1	-	-
2.7 - 2.9	0.4	0.1	-	*	-	*	1.7	0.8	-	*
3.0 - 3.2	0.7	0.8	*	0.1	-	*	5.0	2.6	-	0.3
3.3 - 3.4	1.9	1.8	0.2	0.5	-	0.2	5.5	3.6	-	0.6
3.5 - 3.6	4.5	4.2	0.9	1.2	-	0.6	7.9	6.1	-	2.0
3.7 - 4.2	43.1	44.9	36.3	29.0	-	15.1	37.3	41.1	-	47.9
4.3 - 4.9	49.0	47.5	59.6	61.9	-	74.7	40.0	43.4	-	48.3
5.0 - 5.2	0.2	0.7	2.8	6.5	-	9.0	2.0	2.0	-	0.8
5.3 & Above	-	*	0.1	0.7	-	0.3	0.1	0.3	-	*
Average	4.19	4.21	4.32	4.43	-	4.56	4.08	4.16	-	4.23
Leaf										
1 - 2	54.0	62.8	2.2	4.6	-	16.4	62.9	56.5	-	11.3
3	34.9	29.9	45.1	49.5	-	59.0	28.6	31.7	-	61.3
4	8.9	6.1	44.9	39.9	-	21.8	6.3	9.5	-	24.2
5	1.7	1.0	7.3	5.7	-	2.7	1.6	1.9	-	3.1
6	0.4	0.2	0.5	0.2	-	0.2	0.5	0.3	-	0.1
7	*	*	-	*	-	*	0.1	*	-	*
8	*	*	-	-	-	-	*	*	-	-
Average	2.44	2.25	3.59	3.47	-	3.11	2.33	2.42	-	3.20
HVI Trash 1/										
00	*	*	-	-	-	*	0.1	0.1	-	-
01	25.6	32.7	0.1	0.2	-	2.0	29.7	27.4	-	0.5
02	32.8	33.2	3.2	6.6	-	17.1	39.6	33.8	-	12.5
03	20.2	18.1	16.5	22.5	-	29.7	16.4	18.4	-	29.7
04	11.6	8.9	26.9	27.7	-	24.7	6.9	9.9	-	26.5
05	5.3	3.9	24.6	21.5	-	14.2	3.3	5.3	-	16.0
06	2.2	1.6	14.9	12.2	-	6.8	1.6	2.7	-	8.3
07	1.1	0.8	7.3	5.7	-	3.1	0.9	1.3	-	3.9
08	0.5	0.4	3.8	2.3	-	1.3	0.6	0.6	-	1.7
09	0.3	0.2	1.5	0.9	-	0.6	0.4	0.3	-	0.7
10	0.1	0.1	0.7	0.3	-	0.2	0.2	0.1	-	0.2
11	0.1	0.1	0.3	0.1	-	0.1	0.2	0.1	-	0.1
12	*	*	0.2	*	-	*	0.1	*	-	*
13	*	*	0.1	*	-	*	*	*	-	*
14	*	*	-	*	-	*	*	*	-	*
15	*	*	*	*	-	*	*	*	-	*
16	-	*	-	*	-	-	*	*	-	*
17	-	*	-	-	-	-	*	*	-	*
18 & Above	-	*	-	*	-	-	*	*	-	*
Average	0.26	0.23	0.48	0.44	-	0.38	0.23	0.25	-	0.40
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	*	*	-	-
75	0.1	*	*	*	-	-	0.1	*	-	-
76	0.1	*	0.1	*	-	*	0.3	0.2	-	*
77	0.1	0.2	0.6	*	-	*	1.3	0.8	-	*
78	0.9	0.9	1.9	0.5	-	0.1	5.9	3.8	-	0.2
79	5.2	5.2	2.5	3.6	-	0.6	17.7	12.3	-	1.3
80	19.3	17.6	13.2	16.6	-	6.9	32.8	25.9	-	8.2
81	30.1	31.8	30.0	32.3	-	32.7	27.0	29.8	-	27.9
82	27.7	26.4	32.1	33.0	-	43.1	11.7	18.5	-	38.2
83	14.4	13.9	16.6	12.8	-	15.6	2.6	6.9	-	21.0
84	2.0	3.7	2.7	1.1	-	0.9	0.5	1.6	-	2.9
85 & Above	0.2	0.3	0.1	0.1	-	0.1	0.1	0.2	-	0.2
Average	81.75	81.80	81.91	81.82	-	82.14	80.71	81.16	-	82.23
Tenderable 3/	89.0	93.0	93.6	86.5	-	82.3	71.9	82.9	-	96.1
SAMPLES CLASSED	29,770	365,090	5,286	270,016	-	340,307	217,066	4,882,198	-	172,426

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE									
For The Week Ending Jan 15, 2026									
Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	20.5	5.8	6.9	5.4	-	-	12.3	16.5
	2	2.2	0.6	6.6	6.6	-	-	28.7	17.8
	3	-	*	0.1	0.1	-	-	1.8	0.5
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		22.7	6.4	13.6	12.1	-	-	42.8	34.9
02	1	50.1	41.3	0.8	4.3	-	-	9.5	13.9
	2	14.8	17.6	24.3	33.3	-	-	41.1	41.9
	3	*	0.1	5.6	8.7	-	-	5.5	3.2
	4	-	-	*	0.1	-	-	0.2	0.1
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		64.9	59.0	30.7	46.4	-	-	56.2	59.2
03	1	2.0	10.0	0.2	0.2	-	-	0.1	0.4
	2	6.7	19.9	21.8	14.5	-	-	0.8	4.6
	3	1.4	0.9	26.9	19.5	-	-	0.1	0.8
	4	-	-	1.0	2.0	-	-	-	0.1
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		10.2	30.9	49.9	36.3	-	-	1.0	5.8
04	1	*	0.3	-	*	-	-	-	-
	2	0.8	2.6	0.6	0.6	-	-	-	0.1
	3	1.4	0.6	2.7	2.5	-	-	-	*
	4	*	*	0.3	1.0	-	-	-	*
	5	-	-	-	0.1	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		2.3	3.5	3.6	4.3	-	-	-	0.1
05	1	-	-	-	*	-	-	-	-
	2	-	0.1	0.2	0.1	-	-	-	-
	3	-	0.1	0.5	0.3	-	-	-	*
	4	-	-	0.5	0.3	-	-	-	-
	5	-	-	*	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	0.2	1.3	0.7	-	-	-	*
06	1	-	-	-	-	-	-	-	-
	2	-	-	0.2	*	-	-	-	-
	3	-	-	0.5	0.1	-	-	-	-
	4	-	-	0.2	*	-	-	-	-
	5	-	-	*	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	0.9	0.1	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	0.1	*	-	-	-	-
	4	-	-	*	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	0.1	0.1	-	-	-	-
STAPLE									
44 & Shorter		-	0.1	0.3	2.3	-	-	13.0	12.1
46		13.4	17.7	0.2	7.8	-	-	40.3	48.2
48		66.9	74.6	46.1	45.1	-	-	40.3	35.4
50		19.6	7.6	51.6	42.9	-	-	6.2	3.9
52 & Longer		0.1	0.2	1.7	2.0	-	-	0.1	0.5
Average Staple		48.13	47.80	49.09	48.69	-	-	46.80	46.65
Average Length		1.40	1.39	1.43	1.42	-	-	1.36	1.36
EXTRANEIOUS MATTER									
Bark		-	-	-	*	-	-	-	*
Grass		-	-	-	0.3	-	-	0.2	1.0
Spindle Twist		-	-	0.5	0.1	-	-	-	-
Preparation		-	*	-	*	-	-	-	-
All Other		-	*	*	*	-	-	-	*

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE								
For The Week Ending Jan 15, 2026								
Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	-
2.7 - 2.9	-	*	0.2	0.1	-	-	*	0.2
3.0 - 3.2	0.1	*	0.3	0.5	-	-	5.1	9.7
3.3 - 3.4	0.8	0.5	0.4	1.4	-	-	13.9	14.5
3.5 - 3.6	7.6	2.5	5.3	6.8	-	-	15.3	19.4
3.7 - 4.2	91.1	92.3	82.7	87.2	-	-	62.6	53.3
4.3 - 4.9	0.3	4.6	11.1	3.9	-	-	3.1	3.0
5.0 - 5.2	-	-	-	*	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	3.88	3.97	3.99	3.91	-	-	3.76	3.70
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-
2.7	-	*	*	*	-	-	-	*
2.8	-	*	0.1	*	-	-	*	*
2.9	-	*	0.1	0.1	-	-	-	0.2
3.0	0.1	*	0.1	0.1	-	-	*	1.5
3.1	*	*	0.1	0.1	-	-	2.1	3.8
3.2	-	-	0.1	0.3	-	-	2.9	4.4
3.3	0.7	0.2	0.1	0.5	-	-	2.9	5.2
3.4	0.1	0.2	0.3	0.9	-	-	11.0	9.3
3.5	3.5	0.9	1.5	2.0	-	-	8.3	10.6
3.6	4.1	1.7	3.8	4.8	-	-	7.1	8.8
3.7	16.4	6.6	6.2	9.7	-	-	7.0	9.3
3.8	17.9	13.8	9.6	16.3	-	-	16.3	10.3
3.9	21.3	21.5	17.7	22.1	-	-	16.6	11.8
4.0	14.8	24.1	22.1	20.4	-	-	12.2	10.4
4.1	13.7	18.3	17.7	12.3	-	-	7.7	8.4
4.2	7.0	8.0	9.4	6.4	-	-	2.8	3.1
4.3	0.1	2.8	5.5	2.5	-	-	1.8	1.9
4.4	0.1	1.6	3.6	0.9	-	-	0.1	0.6
4.5	0.1	0.2	1.5	0.4	-	-	*	0.3
4.6	-	*	0.4	0.1	-	-	1.1	0.2
4.7	-	*	*	*	-	-	*	*
4.8	-	-	*	*	-	-	*	*
4.9	-	-	-	*	-	-	-	*
5.0	-	-	-	-	-	-	-	-
5.1	-	-	-	*	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	3.88	3.97	3.99	3.91	-	-	3.76	3.70
STRENGTH 1/ 36 & Below	-	-	-	1.4	-	-	16.6	10.6
37	*	0.1	*	4.3	-	-	10.9	17.4
38	0.2	0.2	0.3	2.9	-	-	8.9	17.6
39	1.5	0.9	0.3	1.2	-	-	11.2	7.7
40	0.3	4.9	1.1	1.7	-	-	3.8	2.6
41	1.8	18.0	2.3	5.4	-	-	2.2	3.0
42	16.0	31.5	7.0	10.7	-	-	8.8	5.6
43	44.4	28.7	10.9	17.1	-	-	11.2	7.6
44	25.1	11.6	14.6	21.1	-	-	11.8	9.4
45	10.0	3.2	20.5	18.1	-	-	8.3	8.1
46	0.2	0.5	21.4	10.0	-	-	5.4	6.5
47	0.2	0.2	13.0	4.2	-	-	0.2	2.6
48 & Above	0.2	0.2	8.8	1.9	-	-	0.6	1.3
Average	43.62	42.79	45.47	43.77	-	-	40.94	40.87
UNIFORMITY								
83 & Below	-	0.2	1.1	1.7	-	-	7.6	2.3
84	1.5	2.7	9.2	11.8	-	-	26.7	23.1
85	36.4	41.1	41.6	33.8	-	-	43.4	44.3
86	55.9	50.9	42.0	46.7	-	-	21.8	27.2
87	5.9	4.9	5.7	5.5	-	-	0.5	2.9
88 & Above	0.2	0.1	0.4	0.5	-	-	*	0.2
Average	86.16	86.04	85.87	85.88	-	-	85.25	85.50
Samples Classed	2,291	11,705	10,296	277,145	-	-	2,808	28,890

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.