



Weekly Quality of Cotton Classed by Classing Office: Week Ending - 1/22/2026

Agricultural Marketing Service
Cotton Market News

Volume 67, No.25

January 23, 2026

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	30	67.8	52.1	64,902	31	81.5	61.1	991,926
Corpus Christi	3	95.8	86.6	4,175	42	88.1	72.5	1,523,957
Dumas	-	-	-	-	33	53.0	25.2	951,045
Florence	13	89.3	82.6	18,092	40	90.5	79.2	1,106,425
Lamesa	10	83.6	58.1	20,818	24	84.3	60.0	550,518
Lubbock	32	64.2	45.4	117,041	54	78.6	58.5	2,450,676
Macon	25	90.4	77.0	39,302	68	88.7	74.9	2,157,453
Memphis	3	91.8	69.0	8,488	65	83.4	60.0	2,305,769
Rayville*	-	-	-	-	16	69.4	47.6	281,472
Visalia	14	84.9	72.2	25,811	26	85.4	69.2	280,487
United States	131	74.2	57.7	299,947	399	81.9	62.8	12,599,728
AMERICAN PIMA								
Visalia	8			14,914	18			351,892
United States	8			14,914	18			351,892
United States all cotton	138			314,861	408			12,951,620

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

MP_CN100

Source: USDA AMS Cotton and Tobacco Market News

Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov

<https://www.ams.usda.gov/market-news/cotton>

<https://mymarketnews.ams.usda.govcottonmn@ams.usda.gov>

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 22, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	18.1	38.4	3.4	14.3	-	0.9	0.6	0.5	67.7	72.3
	3	2.7	6.8	10.3	14.3	-	0.8	0.3	0.5	7.0	6.6
	4	0.3	0.4	0.1	1.4	-	*	*	*	0.1	0.3
	5	*	*	-	*	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	21.1 45.7	13.9 30.1	1.7	0.9 1.0	74.8 79.2				
31	1 - 2	17.7	8.8	17.7	5.1	-	2.2	8.1	5.3	11.2	2.4
	3	13.4	11.4	47.0	22.2	-	16.1	24.2	21.8	3.8	1.6
	4	2.6	3.5	6.1	9.4	-	7.9	10.9	6.2	0.7	0.4
	5	0.3	0.6	0.1	1.0	-	0.5	0.5	0.3	0.1	0.1
	6	*	0.1	-	*	-	*	-	*	-	*
	7	*	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	34.1 24.3	70.8 37.7	26.8	43.7 33.6	15.7 4.5				
41	1 - 2	0.7	0.3	1.7	0.6	-	0.6	2.1	2.6	*	*
	3	5.0	1.3	7.7	5.3	-	19.0	23.7	29.1	*	*
	4	5.0	1.7	2.9	5.0	-	32.8	21.3	24.9	-	*
	5	3.0	1.4	*	1.3	-	9.1	5.5	4.3	-	*
	6	0.7	0.6	-	0.1	-	0.6	1.0	0.3	-	*
	7	*	0.1	-	*	-	*	-	*	-	*
	8	*	*	-	-	-	-	-	*	-	-
	Total	----	14.5 5.4	12.4 12.4	62.2	53.6 61.1	* *				
51	1 - 2	*	*	-	*	-	*	*	0.1	-	-
	3	*	*	-	0.2	-	1.1	0.3	0.9	-	-
	4	*	*	-	0.4	-	3.0	0.9	1.6	-	-
	5	0.4	0.1	*	0.1	-	1.5	0.1	0.7	-	-
	6	0.5	0.2	-	*	-	0.2	-	0.1	-	*
	7	0.2	0.1	-	*	-	*	*	*	-	-
	8	0.1	*	-	-	-	-	-	*	-	-
	Total	----	1.3 0.4	* 0.8	5.8	1.3 3.4	- *				
61	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	* *	- *	*	- *	- *				
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- -	- -	- *	- -				
12 & 22	1 - 2	2.7	8.9	-	4.0	-	*	-	*	6.0	10.5
	3	0.9	2.9	0.1	3.8	-	*	-	*	0.8	2.4
	4	0.3	0.4	-	1.0	-	*	-	*	0.3	0.2
	5	*	*	-	0.1	-	-	-	-	-	*
	6	*	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	3.9 12.3	0.1 8.9	*	- *	7.2 13.1				
32	1 - 2	4.6	1.5	-	0.6	-	*	*	*	0.9	0.3
	3	5.6	2.7	1.2	2.7	-	0.1	0.1	0.1	0.2	0.5
	4	2.3	1.4	1.0	2.4	-	0.1	0.1	0.1	*	0.3
	5	1.1	0.5	-	0.6	-	*	-	*	-	0.1
	6	0.2	0.1	-	*	-	*	-	*	-	*
	7	*	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	13.9 6.2	2.3 6.3	0.3	0.1 0.2	1.1 1.1				
42	1 - 2	0.2	*	-	0.1	-	*	-	*	-	*
	3	0.6	0.3	0.2	0.9	-	0.5	0.1	0.2	*	*
	4	1.2	0.7	0.1	1.1	-	1.2	0.2	0.3	-	*
	5	1.8	0.9	-	0.6	-	0.6	0.1	0.1	-	*
	6	1.1	0.6	-	0.1	-	0.1	-	*	-	*
	7	0.4	0.2	-	*	-	*	-	*	-	*
	8	0.1	*	-	-	-	-	-	*	-	-
	Total	----	5.4 2.8	0.3 2.8	2.5	0.3 0.6	* *				

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 22, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	-	*	-	*	-	*	-	*
	3	-	*	-	*	-	0.1	-	*	-	*
	4	*	*	-	0.1	-	0.2	-	*	-	-
	5	0.1	*	-	0.1	-	0.2	-	*	-	*
	6	0.1	*	-	*	-	0.1	-	*	-	-
	7	0.2	0.1	-	*	-	*	-	*	-	-
	8	0.2	0.1	-	-	-	-	-	*	-	-
Total	----	0.6	0.2	-	0.2	-	0.6	-	0.1	-	*
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	-	*	-	-
13 & 23	1 - 2	0.5	0.6	-	0.1	-	-	-	*	0.9	0.9
	3	0.2	0.4	-	0.1	-	-	-	*	*	0.4
	4	0.1	0.1	-	*	-	-	*	*	-	*
	5	*	*	-	*	-	-	-	-	-	*
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.8	1.1	-	0.2	-	-	*	*	0.9	1.3
33	1 - 2	0.4	0.2	-	*	-	*	-	*	0.1	0.1
	3	1.1	0.4	-	0.1	-	*	*	*	0.1	0.2
	4	0.7	0.3	*	0.1	-	*	*	*	*	0.2
	5	0.3	0.1	-	*	-	-	-	*	*	0.1
	6	*	*	-	*	-	-	-	*	-	*
	7	-	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	2.5	1.0	*	0.3	-	*	*	*	0.2	0.6
43	1 - 2	*	*	-	*	-	-	-	*	-	*
	3	0.2	*	-	0.1	-	*	-	*	-	*
	4	0.4	0.1	*	0.1	-	*	*	*	-	*
	5	0.6	0.1	-	0.1	-	*	*	*	-	*
	6	0.3	0.1	-	*	-	*	-	*	-	*
	7	0.1	*	-	*	-	-	-	*	-	*
	8	*	*	-	-	-	-	-	*	-	-
Total	----	1.7	0.4	*	0.3	-	*	*	*	-	*
53	1 - 2	-	-	-	*	-	*	-	-	-	-
	3	-	*	-	*	-	*	-	*	-	-
	4	-	*	-	*	-	*	-	*	-	-
	5	*	*	-	*	-	*	-	*	-	-
	6	*	*	-	*	-	*	-	*	-	*
	7	*	*	-	*	-	*	-	*	-	-
	8	*	*	-	-	-	-	-	*	-	-
Total	----	*	*	-	*	-	*	-	*	-	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	*	*	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	-	*	-	-	-	-
24 - 54	1 - 8	0.2	0.1	-	*	-	-	-	*	0.1	0.1
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	*	-	-	-	-	-	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-
30		*	*	-	-	-	-	-	-	0.1	*
31		0.1	0.1	-	*	-	*	-	*	0.3	0.2
32		0.9	0.5	-	*	-	*	-	*	3.1	1.8
33		4.1	2.9	*	0.1	-	0.1	0.2	0.1	9.3	7.4
34		13.3	8.5	0.6	0.7	-	1.3	2.5	1.4	27.7	21.0
35		18.4	15.0	12.9	3.8	-	8.2	17.4	8.2	36.2	28.3
36		16.3	18.5	28.2	15.6	-	25.2	33.9	26.6	18.1	21.6
37		22.2	24.0	14.7	45.9	-	42.7	32.9	47.8	4.8	15.3
38		14.1	14.9	20.0	25.3	-	16.4	10.0	12.9	0.4	3.8
39		7.3	10.0	21.0	7.8	-	4.9	2.8	2.7	0.1	0.6
40 & Longer		3.2	5.6	2.7	0.7	-	1.1	0.4	0.3	-	*
Average Staple		36.25	36.64	37.14	37.17	-	36.84	36.40	36.71	34.72	35.24
Average Length		1.13	1.14	1.16	1.16	-	1.15	1.13	1.15	1.08	1.10

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 22, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	44.3	58.0	2.4	1.7	-	0.4	-	3.9	8.6	21.7
	3	10.5	15.2	2.6	1.2	-	0.4	-	2.6	2.5	6.1
	4	0.3	0.8	*	*	-	*	-	0.1	0.1	0.3
	5	*	*	-	*	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	55.1 74.0	5.1 2.9	0.8	-	6.6	11.2	28.2		
31	1 - 2	10.7	3.2	10.0	8.2	1.6	2.7	-	8.0	8.8	11.3
	3	7.5	5.0	22.7	21.9	5.6	12.2	-	33.0	15.4	14.2
	4	1.2	2.0	2.9	4.2	0.2	3.4	-	11.6	2.5	3.3
	5	0.2	0.3	0.1	0.2	*	0.2	-	0.9	0.2	0.4
	6	*	*	-	*	-	*	-	*	*	*
	7	*	*	-	*	-	*	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	19.6 10.5	35.7 34.3	7.4 18.5	-	53.5	26.9	29.3		
41	1 - 2	0.1	*	4.9	5.0	6.0	2.4	-	0.7	6.6	2.9
	3	0.2	0.1	26.9	31.6	43.2	30.7	-	12.3	28.7	13.7
	4	0.6	0.2	9.7	16.6	31.6	26.6	-	16.2	15.6	9.9
	5	0.6	0.2	0.5	2.1	7.0	5.1	-	4.5	2.8	3.0
	6	0.3	0.1	*	0.1	0.1	0.4	-	0.4	0.5	0.4
	7	0.1	*	-	*	-	*	-	-	0.1	*
	8	*	*	-	-	-	-	-	-	-	*
	Total	----	1.8 0.5	42.0 55.5	88.0 65.3	-	34.2	54.3	29.9		
51	1 - 2	-	*	0.7	0.2	0.3	0.1	-	*	0.1	0.1
	3	-	*	7.9	2.3	2.8	2.9	-	*	1.6	0.9
	4	-	*	5.9	2.2	0.8	4.7	-	0.3	2.0	1.9
	5	*	*	0.6	0.5	0.1	1.7	-	0.3	0.5	1.4
	6	*	*	*	0.1	-	0.3	-	0.1	0.2	0.6
	7	*	*	-	*	-	*	-	-	0.1	0.2
	8	*	*	-	*	-	-	-	-	*	*
	Total	----	0.1 *	15.1 5.3	3.9 9.7	-	0.7	4.5	5.0		
61	1 - 2	-	*	0.1	*	-	*	-	-	-	*
	3	-	*	0.4	*	-	*	-	*	*	*
	4	-	*	0.2	*	-	*	-	*	*	*
	5	-	-	*	*	-	*	-	-	*	*
	6	-	-	*	*	-	*	-	-	-	*
	7	-	-	*	*	-	*	-	-	-	*
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	- *	0.8 0.1	- *	- *	- *	- *	- *		
71	1 - 2	-	*	-	-	-	*	-	-	-	-
	3	-	*	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- *	- -	- *	- -	- -	- -	- -		
12 & 22	1 - 2	7.8	6.0	-	*	-	*	-	0.1	0.9	2.3
	3	4.2	3.8	0.1	*	-	*	-	0.1	0.3	1.2
	4	0.6	0.5	0.1	*	-	*	-	0.1	0.1	0.2
	5	*	*	-	-	-	*	-	*	-	*
	6	*	*	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	12.7 10.3	0.1 0.1	- *	-	0.3	1.2	3.6		
32	1 - 2	1.0	0.3	*	0.1	-	*	-	0.1	0.1	0.2
	3	1.9	1.0	*	0.3	-	0.2	-	0.5	0.2	0.5
	4	1.1	0.6	*	0.1	-	0.1	-	0.8	0.1	0.4
	5	0.3	0.2	*	*	-	*	-	0.4	*	0.2
	6	0.1	*	-	*	-	*	-	0.1	-	*
	7	*	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	4.4 2.1	* 0.4	- 0.3	-	1.8	0.4	1.4		
42	1 - 2	*	*	*	*	-	0.2	-	*	0.1	*
	3	*	*	0.4	0.5	*	1.8	-	0.4	0.2	0.5
	4	0.2	0.1	0.2	0.4	0.4	1.5	-	1.2	0.3	0.5
	5	0.2	0.1	*	0.1	0.1	0.4	-	0.7	0.1	0.3
	6	0.2	*	-	*	-	0.1	-	0.4	*	0.1
	7	0.1	*	-	*	-	*	-	-	-	*
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	0.8 0.2	0.6 1.1	0.5 3.9	-	2.6	0.8	1.5		

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 22, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	*	*	*	*	-	-	*	*
	3	-	-	0.2	*	0.1	0.4	-	*	*	0.1
	4	-	*	0.2	0.1	*	0.6	-	0.1	*	0.2
	5	*	*	*	*	*	0.3	-	0.1	*	0.2
	6	*	*	*	*	-	0.1	-	*	-	0.1
	7	*	*	-	*	-	*	-	*	-	*
	8	*	*	-	*	-	-	-	-	-	*
Total	----	*	*	0.5	0.2	0.1	1.4	-	0.1	0.1	0.7
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	*	*	-	*	-	-	-	*
	4	-	-	*	*	-	*	-	-	-	*
	5	-	-	-	*	-	*	-	-	-	*
	6	-	-	-	*	-	*	-	-	-	*
	7	-	-	-	*	-	*	-	-	-	*
	8	-	-	-	*	-	-	-	-	-	*
Total	----	-	-	*	*	-	*	-	-	-	*
13 & 23	1 - 2	1.6	0.7	-	*	-	-	-	-	0.1	0.2
	3	0.8	0.6	-	*	-	-	-	-	0.3	0.1
	4	0.2	0.1	-	*	-	-	-	-	*	*
	5	*	*	-	*	-	-	-	-	-	-
	6	*	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	2.6	1.4	-	*	-	-	-	-	0.4	0.2
33	1 - 2	0.4	0.1	-	*	-	*	-	*	*	*
	3	0.6	0.3	*	*	-	*	-	*	0.2	*
	4	0.8	0.2	*	*	-	*	-	*	*	*
	5	0.5	0.1	-	*	-	*	-	*	*	*
	6	0.1	*	-	*	-	*	-	*	-	*
	7	*	*	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
Total	----	2.5	0.8	*	*	-	*	-	0.1	0.2	0.1
43	1 - 2	*	*	-	*	-	*	-	*	*	*
	3	*	*	*	*	-	*	-	*	*	*
	4	*	*	*	*	-	*	-	*	*	*
	5	*	*	*	*	-	*	-	*	*	*
	6	*	*	*	*	-	*	-	*	*	*
	7	*	*	-	*	-	*	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
Total	----	0.2	0.1	0.1	0.1	-	0.1	-	0.1	*	0.1
53	1 - 2	-	-	*	*	-	*	-	-	-	*
	3	-	-	*	*	-	*	-	-	-	*
	4	-	-	*	*	*	*	-	-	-	*
	5	-	-	*	*	-	*	-	-	-	*
	6	-	*	-	*	-	*	-	*	*	*
	7	*	*	-	*	-	*	-	-	*	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	*	*	0.1	*	*	*	-	*	*	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	*	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	-	-	-	-	-	-
24 - 54	1 - 8	0.2	0.1	*	*	-	*	-	0.1	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	*	-	*	-	-	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		*	*	-	-	-	-	-	-	-	-
30		*	*	-	*	-	-	-	-	-	-
31		0.1	0.1	*	*	-	*	-	-	-	*
32		0.7	0.5	0.2	0.1	-	*	-	*	*	*
33		3.9	2.6	0.7	0.8	-	0.1	-	0.2	0.3	0.2
34		12.9	8.6	6.1	4.6	*	0.8	-	1.6	1.7	0.9
35		25.1	18.2	22.1	15.4	0.8	4.2	-	11.3	5.2	3.6
36		28.2	25.7	33.6	30.2	23.4	15.2	-	28.9	17.6	13.9
37		22.3	29.3	28.3	35.8	55.8	47.7	-	39.8	43.2	41.4
38		5.5	10.7	6.3	10.2	17.6	26.8	-	14.1	18.7	24.3
39		1.1	3.2	1.8	2.5	2.2	4.7	-	3.8	6.7	8.8
40 & Longer		0.2	1.0	0.9	0.3	0.1	0.5	-	0.4	6.6	6.9
Average Staple		35.71	36.19	36.13	36.38	36.97	37.12	-	36.65	37.38	37.58
Average Length		1.11	1.13	1.13	1.13	1.15	1.16	-	1.14	1.17	1.18

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 22, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	20.7	8.0	1.3	0.6	-	*	5.1	2.0	1.2	1.4
Bark - Level 2	*	*	-	-	-	-	-	-	-	-
Grass - Level 1	0.2	0.1	0.5	0.3	-	0.1	-	*	0.1	0.3
Grass - Level 2	-	-	-	*	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	-	*	-	-
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	*	*	-	1.5	2.5	0.8	0.4	0.1
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	*
Other - Level 2	-	*	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	0.1	-	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	*	*	-	*	-	-	-	-	0.3	*
23	*	*	-	*	-	-	-	-	0.2	0.1
24	*	*	-	*	-	*	*	*	1.3	0.2
25	0.2	0.1	-	*	-	*	0.1	*	3.8	0.9
26	1.0	0.7	-	0.2	-	0.1	1.2	0.5	8.2	2.6
27	3.6	2.8	0.7	1.2	-	0.5	5.1	3.0	16.1	7.3
28	7.5	7.9	3.7	5.2	-	3.9	15.9	12.6	20.6	13.7
29	16.1	14.7	13.4	14.8	-	15.4	33.8	30.5	20.2	19.7
30	20.7	17.7	14.7	21.7	-	28.5	25.9	30.3	16.8	22.0
31	17.0	16.9	18.9	17.7	-	26.8	11.8	15.3	8.8	17.9
32	12.8	14.2	28.1	12.5	-	15.8	5.2	5.8	2.7	9.6
33	10.2	11.4	15.1	11.6	-	6.3	0.8	1.6	0.7	3.8
34	6.4	7.5	4.4	9.7	-	2.1	0.2	0.3	0.2	1.4
35	2.3	3.8	0.9	4.0	-	0.5	*	0.1	*	0.5
36	1.4	1.4	0.2	1.1	-	0.1	*	*	*	0.2
37	0.5	0.7	-	0.2	-	*	-	*	-	*
38	0.1	0.2	-	*	-	*	-	-	-	*
39	*	*	-	*	-	*	-	-	-	-
40 & Above	0.1	*	-	-	-	*	-	-	-	-
Average	31.23	31.46	31.65	31.59	-	31.09	29.84	30.12	28.89	30.17
Mike										
2.4 & Below	0.2	*	-	-	-	-	-	-	-	*
2.5	0.5	0.2	-	*	-	-	-	*	*	0.1
2.6	0.7	0.2	-	*	-	-	-	-	0.1	0.2
2.7	0.9	0.3	-	*	-	-	-	*	0.3	0.3
2.8	1.1	0.4	-	*	-	-	*	*	0.3	0.4
2.9	1.1	0.4	-	*	-	-	-	*	0.5	0.6
3.0	1.2	0.6	-	0.1	-	-	-	*	0.6	0.8
3.1	1.6	0.8	-	0.1	-	-	*	*	1.2	0.9
3.2	2.0	1.0	*	0.3	-	*	*	0.1	1.4	1.3
3.3	2.4	1.4	0.2	0.5	-	*	0.3	0.2	1.6	1.6
3.4	2.3	1.8	0.7	0.9	-	*	0.7	0.3	2.3	2.0
3.5	3.0	2.4	2.2	1.3	-	*	1.6	0.5	2.9	2.5
3.6	3.4	3.4	5.7	1.9	-	0.1	2.0	0.9	3.2	3.1
3.7	4.8	4.4	9.3	2.7	-	0.1	4.3	1.7	3.6	3.8
3.8	6.2	5.5	10.8	4.4	-	0.1	6.3	2.7	2.4	4.6
3.9	5.9	7.0	12.4	6.7	-	0.2	8.1	4.2	4.8	5.5
4.0	7.5	8.5	8.8	9.0	-	0.4	10.3	5.8	7.7	6.2
4.1	8.8	10.1	7.7	11.1	-	0.6	12.4	7.7	8.7	7.0
4.2	10.1	10.7	9.3	12.7	-	1.0	10.8	9.8	9.1	8.0
4.3	10.6	10.8	12.7	12.9	-	1.7	11.0	11.6	10.6	8.7
4.4	8.6	9.5	11.5	11.3	-	2.8	7.9	11.8	10.0	9.2
4.5	7.4	7.7	5.3	8.8	-	4.1	7.1	10.8	10.0	9.0
4.6	5.2	5.6	2.6	6.0	-	6.5	7.4	9.4	8.0	8.2
4.7	2.9	3.5	0.4	3.7	-	9.5	5.7	7.7	4.7	6.5
4.8	1.3	2.0	*	2.3	-	13.4	1.7	5.5	2.9	4.5
4.9	0.4	1.0	0.3	1.3	-	16.0	1.3	3.9	1.6	2.6
5.0	0.1	0.4	-	0.8	-	16.3	1.0	2.5	1.4	1.4
5.1	*	0.2	-	0.4	-	12.9	0.1	1.4	0.1	0.6
5.2	-	0.1	*	0.3	-	8.2	*	0.7	-	0.3
5.3	-	*	-	0.2	-	4.0	-	0.3	-	0.1
5.4	-	-	-	0.1	-	1.5	-	0.1	-	*
5.5 & Above	-	*	-	0.2	-	0.5	-	*	-	*
Average	4.01	4.11	4.06	4.23	-	4.88	4.20	4.38	4.17	4.19

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE

For The Week Ending Jan 22, 2026

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	20.1	7.5	2.4	1.3	-	*	-	1.8	1.4	0.3
Bark - Level 2	*	*	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	0.1	*	0.1	-	*	-	0.1	0.4	0.4
Grass - Level 2	*	*	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	-	-	*	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	2.4	0.4	*	0.3	-	0.1	-	2.9	*	*
Seed Coat - Level 2	*	*	-	-	-	-	-	-	-	-
Oil - Level 1	*	*	-	-	-	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	*
Spindle Twist - Level 2	-	*	-	-	-	-	-	-	-	-
Other - Level 1	*	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	0.1	*	*	*	-	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	*	*	-	-	-	*	-	-	-	*
23	0.1	*	-	*	-	*	-	-	-	-
24	0.2	0.1	*	*	-	*	-	-	-	*
25	0.5	0.2	0.4	0.1	-	*	-	*	*	0.1
26	1.6	0.7	2.8	0.6	-	*	-	0.1	0.4	0.4
27	4.3	2.6	12.5	3.2	*	0.2	-	1.8	2.4	1.7
28	10.3	7.1	22.5	10.5	0.5	1.8	-	6.6	12.3	7.5
29	18.2	14.5	24.0	20.5	10.6	12.4	-	18.0	24.1	15.4
30	21.9	20.2	20.5	25.2	26.9	36.1	-	30.0	24.3	20.4
31	19.1	19.9	11.4	20.1	34.4	32.5	-	20.0	16.6	18.6
32	12.6	15.1	4.3	11.6	24.5	12.2	-	12.6	10.2	12.3
33	7.0	9.8	1.2	5.3	2.9	3.7	-	6.1	5.2	8.1
34	2.9	5.6	0.3	2.1	0.1	0.9	-	3.1	3.2	6.8
35	1.0	2.5	0.1	0.7	-	0.1	-	1.6	1.0	5.0
36	0.3	1.1	*	0.2	*	*	-	0.2	0.2	2.7
37	0.1	0.4	-	*	-	*	-	*	0.1	0.9
38	*	0.2	-	*	-	*	-	*	*	0.1
39	*	*	-	*	-	-	-	-	*	*
40 & Above	-	-	-	*	-	-	-	-	-	*
Average	30.68	31.29	29.51	30.64	31.25	31.01	-	30.93	30.61	31.51
Mike										
2.4 & Below	0.4	*	-	-	-	-	-	-	-	-
2.5	0.5	0.1	-	*	-	-	-	*	*	*
2.6	0.5	0.1	-	*	-	-	-	*	*	*
2.7	0.7	0.2	-	*	-	*	-	*	0.2	*
2.8	0.8	0.4	*	*	-	*	-	*	0.6	0.1
2.9	1.2	0.6	0.1	*	-	*	-	*	0.5	0.2
3.0	1.5	0.9	*	*	-	*	-	*	0.1	0.2
3.1	1.8	1.3	0.2	*	-	*	-	*	0.2	0.4
3.2	2.2	1.8	0.3	0.1	-	*	-	0.1	0.1	0.7
3.3	2.6	2.3	0.5	0.2	-	*	-	0.1	0.7	0.6
3.4	3.3	3.0	1.2	0.3	-	0.1	-	0.1	1.4	0.7
3.5	3.9	3.8	2.0	0.6	-	0.1	-	0.2	1.5	1.2
3.6	4.5	4.4	2.2	1.1	-	0.2	-	0.4	1.3	1.6
3.7	5.0	5.0	4.4	1.9	-	0.4	-	0.5	2.8	2.5
3.8	5.6	5.5	6.2	2.8	0.1	0.6	-	0.7	4.7	3.3
3.9	5.8	6.1	6.1	4.0	1.1	1.0	-	1.1	6.5	4.4
4.0	6.3	6.5	7.6	5.5	3.5	1.7	-	1.9	7.3	5.7
4.1	6.4	6.9	9.2	7.4	2.6	2.6	-	3.5	9.1	7.5
4.2	6.5	7.3	10.8	9.0	3.8	4.0	-	4.5	8.7	9.0
4.3	6.8	7.6	11.1	10.1	9.2	5.7	-	5.6	10.3	9.2
4.4	7.1	7.7	10.6	10.3	12.7	8.2	-	6.6	9.3	9.0
4.5	6.4	7.4	7.7	10.0	15.2	11.0	-	8.6	5.8	9.7
4.6	5.5	6.6	5.8	9.2	13.1	13.9	-	9.7	6.3	9.2
4.7	4.7	5.4	4.2	8.2	8.0	15.2	-	10.6	5.7	7.7
4.8	3.9	3.8	3.5	6.6	10.4	13.8	-	11.4	4.7	5.9
4.9	2.8	2.4	3.2	5.0	12.6	10.1	-	10.6	4.3	4.4
5.0	1.7	1.4	1.7	3.4	5.6	6.3	-	8.4	2.1	2.9
5.1	0.8	0.7	0.8	2.2	1.5	3.1	-	7.0	2.0	1.6
5.2	0.4	0.4	0.3	1.2	0.4	1.2	-	4.0	1.5	1.0
5.3	0.2	0.2	0.1	0.6	*	0.4	-	2.2	1.4	0.7
5.4	*	0.1	0.1	0.2	*	0.1	-	1.1	0.7	0.3
5.5 & Above	*	0.1	0.2	0.1	-	*	-	1.1	0.3	0.3
Average	4.05	4.12	4.23	4.42	4.57	4.62	-	4.68	4.30	4.36

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 22, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	0.2	*	-	-	-	-	-	-	-	*
2.5 - 2.6	1.2	0.4	-	*	-	-	-	*	0.1	0.3
2.7 - 2.9	3.1	1.1	-	0.1	-	-	*	*	1.1	1.2
3.0 - 3.2	4.8	2.3	*	0.5	-	*	0.1	0.2	3.2	3.0
3.3 - 3.4	4.7	3.2	0.9	1.4	-	*	1.0	0.5	3.8	3.6
3.5 - 3.6	6.4	5.9	7.9	3.1	-	0.1	3.6	1.5	6.1	5.5
3.7 - 4.2	43.3	46.2	58.3	46.6	-	2.5	52.2	32.0	36.4	35.1
4.3 - 4.9	36.2	40.2	32.8	46.4	-	54.0	42.1	60.8	47.8	48.8
5.0 - 5.2	0.1	0.7	*	1.4	-	37.4	1.1	4.6	1.5	2.3
5.3 & Above	-	*	-	0.5	-	6.1	-	0.4	-	0.1
Average	4.01	4.11	4.06	4.23	-	4.88	4.20	4.38	4.17	4.19
Leaf										
1 - 2	45.1	58.7	22.9	24.8	-	3.8	10.8	8.4	86.8	86.5
3	29.7	26.4	66.7	49.7	-	37.7	48.8	52.6	12.0	11.8
4	13.0	8.6	10.4	21.1	-	45.4	33.3	33.2	1.1	1.4
5	7.7	3.8	0.1	4.0	-	12.0	6.1	5.3	0.1	0.3
6	3.1	1.7	-	0.5	-	1.1	1.0	0.4	-	0.1
7	0.9	0.6	-	0.1	-	*	*	*	-	*
8	0.4	0.2	-	*	-	-	-	*	-	-
Average	2.89	2.48	2.88	3.03	-	3.69	3.38	3.37	1.81	1.74
HVI Trash 1/										
00	*	*	-	*	-	-	-	-	0.3	0.7
01	18.6	29.4	1.8	5.2	-	0.3	1.3	0.6	56.8	60.1
02	30.3	32.7	26.0	22.5	-	4.6	12.1	10.2	34.0	29.2
03	17.2	15.6	39.8	27.9	-	14.9	22.1	24.7	6.7	6.9
04	10.3	8.1	23.0	20.4	-	22.9	24.0	26.2	1.6	1.9
05	6.2	4.5	6.7	12.1	-	22.0	18.8	18.7	0.4	0.7
06	4.1	2.7	2.1	6.5	-	15.8	11.0	10.6	0.1	0.3
07	3.2	1.8	0.4	3.1	-	9.7	5.7	5.2	*	0.1
08	2.7	1.4	0.1	1.4	-	5.2	2.6	2.2	-	0.1
09	2.3	1.0	-	0.6	-	2.6	1.3	0.9	-	*
10	1.5	0.8	-	0.3	-	1.2	0.7	0.4	-	*
11	1.1	0.6	-	0.1	-	0.5	0.3	0.1	-	*
12	0.7	0.4	-	0.1	-	0.2	0.1	0.1	-	*
13	0.5	0.3	-	*	-	0.1	*	*	-	*
14	0.4	0.2	-	*	-	*	*	*	-	*
15	0.2	0.1	-	*	-	*	-	*	-	-
16	0.2	0.1	-	*	-	-	-	*	-	*
17	0.1	0.1	-	*	-	-	-	*	-	*
18 & Above	0.2	0.1	-	*	-	-	-	*	-	-
Average	0.35	0.28	0.32	0.36	-	0.50	0.43	0.43	0.15	0.15
UNIFORMITY 2/										
74 & Below	*	*	-	*	-	-	-	*	*	*
75	0.1	0.1	-	*	-	-	-	*	*	0.1
76	0.2	0.2	-	*	-	*	0.1	*	0.3	0.5
77	1.3	0.8	0.1	0.1	-	*	0.3	*	3.2	2.4
78	5.0	3.1	0.9	0.7	-	0.2	1.3	0.5	9.5	10.1
79	16.5	12.6	6.9	3.7	-	1.0	7.1	2.9	24.9	25.0
80	31.7	27.8	27.6	13.4	-	7.0	19.1	12.0	34.7	35.8
81	24.5	29.3	43.0	30.1	-	28.1	34.1	28.7	23.2	21.4
82	14.3	17.3	19.9	31.1	-	37.9	27.9	35.1	4.0	4.3
83	5.3	7.2	1.7	16.1	-	20.5	9.1	18.2	0.1	0.5
84	1.1	1.7	-	4.3	-	5.1	1.0	2.3	*	*
85 & Above	0.1	0.1	-	0.4	-	0.2	*	0.2	-	*
Average	80.88	81.16	81.24	82.00	-	82.30	81.55	82.05	80.22	80.22
Tenderable 3/	67.8	81.5	95.8	88.1	-	53.0	89.3	90.5	83.6	84.3
SAMPLES CLASSED										
Week	64,902		4,175		-		18,092		20,818	
Season	991,926		1,523,957		951,045		1,106,425		550,518	

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 22, 2026

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	0.4	*	-	-	-	-	-	-	-	-
2.5 - 2.6	1.0	0.2	-	*	-	-	-	*	0.1	*
2.7 - 2.9	2.8	1.2	0.1	*	-	*	-	0.1	1.3	0.4
3.0 - 3.2	5.5	4.0	0.5	0.1	-	*	-	0.1	0.5	1.3
3.3 - 3.4	5.9	5.4	1.6	0.5	-	0.1	-	0.2	2.1	1.3
3.5 - 3.6	8.4	8.2	4.3	1.7	-	0.3	-	0.6	2.7	2.8
3.7 - 4.2	35.6	37.2	44.3	30.5	11.2	10.4	-	12.1	39.0	32.4
4.3 - 4.9	37.3	41.0	46.1	59.3	81.3	78.0	-	63.1	46.3	55.1
5.0 - 5.2	2.9	2.5	2.8	6.9	7.5	10.6	-	19.4	5.6	5.5
5.3 & Above	0.3	0.3	0.3	1.0	*	0.6	-	4.4	2.4	1.3
Average	4.05	4.12	4.23	4.42	4.57	4.62	-	4.68	4.30	4.36
Leaf										
1 - 2	66.0	68.4	18.2	15.3	7.9	5.8	-	12.8	25.2	38.7
3	25.7	26.0	61.3	57.8	51.7	48.7	-	48.9	49.5	37.3
4	5.2	4.5	19.2	23.7	33.0	37.0	-	30.4	20.8	16.8
5	2.1	0.9	1.3	3.0	7.2	7.6	-	6.9	3.6	5.6
6	0.8	0.2	0.1	0.2	0.1	0.8	-	1.0	0.7	1.4
7	0.3	0.1	*	*	-	0.1	-	*	0.2	0.2
8	0.1	*	-	*	-	-	-	-	*	*
Average	2.35	2.22	3.04	3.15	3.40	3.49	-	3.34	3.02	2.88
HVI Trash 1/										
00	*	*	-	-	-	*	-	-	*	*
01	28.0	33.1	1.4	1.6	0.8	0.5	-	1.6	7.5	14.8
02	43.9	41.6	23.2	19.8	10.1	7.3	-	14.1	24.2	29.6
03	15.2	15.5	34.1	31.3	24.9	21.2	-	24.1	28.7	21.1
04	5.4	5.5	23.3	23.6	26.6	26.2	-	23.2	19.1	13.7
05	2.7	2.2	11.5	12.9	17.4	20.2	-	16.3	11.0	8.5
06	1.6	1.0	4.2	6.1	10.3	12.2	-	9.7	5.0	5.2
07	1.0	0.5	1.4	2.7	6.6	6.5	-	5.3	2.4	3.1
08	0.7	0.3	0.5	1.1	2.3	3.2	-	2.7	0.9	1.8
09	0.4	0.1	0.2	0.5	0.7	1.5	-	1.5	0.5	1.1
10	0.3	0.1	0.1	0.2	0.2	0.7	-	0.8	0.2	0.5
11	0.2	0.1	*	0.1	0.1	0.3	-	0.4	0.1	0.3
12	0.2	*	*	*	*	0.1	-	0.2	0.1	0.1
13	0.1	*	*	*	-	0.1	-	0.1	*	0.1
14	0.1	*	*	*	-	*	-	*	*	*
15	*	*	-	*	-	*	-	-	*	*
16	*	*	*	*	-	-	-	-	*	*
17	*	*	*	*	-	-	-	*	*	*
18 & Above	*	*	*	*	-	-	-	-	*	*
Average	0.24	0.21	0.34	0.37	0.43	0.46	-	0.42	0.34	0.32
UNIFORMITY 2/										
74 & Below	0.1	*	-	-	-	-	-	-	-	-
75	0.2	*	-	*	-	-	-	-	-	*
76	0.8	0.2	0.1	*	-	*	-	-	*	*
77	2.4	1.0	0.3	0.1	-	*	-	-	0.1	*
78	7.5	4.4	1.7	0.8	*	0.1	-	0.2	0.8	0.6
79	19.3	14.2	9.4	5.0	*	0.5	-	1.8	4.3	3.2
80	31.8	29.9	25.8	20.1	1.3	3.9	-	10.5	27.1	15.9
81	26.2	31.8	35.5	36.5	12.6	20.8	-	32.0	34.8	32.1
82	9.5	14.8	20.6	27.9	52.2	45.7	-	37.5	26.3	34.2
83	1.9	3.1	5.9	8.3	32.8	26.1	-	15.8	5.9	11.6
84	0.3	0.4	0.8	1.2	1.0	2.7	-	2.1	0.6	2.2
85 & Above	0.1	0.1	*	0.1	-	0.2	-	0.1	0.1	0.2
Average	80.51	80.90	81.28	81.61	82.64	82.47	-	82.06	81.49	81.85
Tenderable 3/	64.2	78.6	90.4	88.7	91.8	83.4	-	69.4	84.9	85.4
SAMPLES CLASSED										
Week	117,041		39,302		8,488		-		25,811	
Season		2,450,676		2,157,453		2,305,769		281,472		280,487

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE

For The Week Ending Jan 22, 2026

Color Grade	Leaf	VISALIA			Quality Designation	VISALIA	
		Week	Season			Week	Season
01	1	6.6	6.3		MIKE		
	2	8.8	7.6		2.4 & Below	-	-
	3	0.2	0.2		2.5 - 2.6	-	-
	4	-	-		2.7 - 2.9	*	0.2
	5	-	-		3.0 - 3.2	0.4	1.6
	6	-	-		3.3 - 3.4	0.8	2.9
	7	-	-		3.5 - 3.6	8.2	8.6
Total -----		15.6	14.2		3.7 - 4.2	84.2	82.8
02	1	13.9	7.0		4.3 - 4.9	6.4	4.0
	2	42.0	34.9		5.0 - 5.2	*	*
	3	6.8	8.3		5.3 & Above	-	-
	4	*	0.2		Average	3.96	3.89
	5	-	*		ALL RANGE MIKE		
	6	-	-		2.4 & Below	-	-
	7	-	-		2.5	-	-
Total -----		62.8	50.3		2.6	-	-
03	1	1.2	0.6		2.7	-	*
	2	12.3	13.1		2.8	*	*
	3	6.9	15.9		2.9	-	0.1
	4	0.2	1.7		3.0	0.1	0.3
	5	-	*		3.1	0.1	0.5
	6	-	*		3.2	0.2	0.8
	7	-	-		3.3	0.4	1.0
Total -----		20.7	31.3		3.4	0.4	1.8
04	1	*	*		3.5	1.3	3.1
	2	0.2	0.6		3.6	6.9	5.6
	3	0.4	2.0		3.7	6.2	9.7
	4	0.2	0.8		3.8	10.0	15.2
	5	-	0.1		3.9	19.9	20.6
	6	-	*		4.0	22.3	19.1
	7	-	-		4.1	15.9	12.0
Total -----		0.9	3.5		4.2	9.9	6.1
05	1	-	*		4.3	3.8	2.5
	2	-	0.1		4.4	1.7	1.0
	3	*	0.2		4.5	0.7	0.4
	4	*	0.2		4.6	0.2	0.1
	5	-	*		4.7	*	*
	6	-	*		4.8	*	*
	7	-	-		4.9	*	*
Total -----		*	0.5		5.0	*	*
06	1	-	-		5.1	*	*
	2	-	*		5.2	-	-
	3	*	0.1		5.3 & Above	-	-
	4	*	*		Average	3.96	3.89
	5	-	*		STRENGTH 1/		
	6	-	*		36 & Below	1.1	2.8
	7	-	-		37	1.0	5.0
Total -----		*	0.1		38	2.6	3.9
07	1	-	-		39	1.2	1.8
	2	-	-		40	1.0	2.0
	3	-	*		41	2.2	5.6
	4	-	*		42	7.1	11.1
	5	-	*		43	14.3	16.8
	6	-	*		44	19.0	19.6
	7	-	-		45	21.9	16.4
Total -----		-	*		46	16.1	9.3
STAPLE					47	7.2	3.9
44 & Shorter		2.3	2.9		48 & Above	5.3	1.8
46		8.7	11.6		Average	44.64	43.45
48		47.1	46.5		UNIFORMITY		
50		39.3	37.3		83 & Below	1.5	1.6
52 & Longer		2.7	1.8		84	6.6	12.1
Average Staple		48.63	48.47		85	32.8	35.0
Average Length		1.41	1.41		86	48.3	45.3
EXTRANEEOUS MATTER					87	9.3	5.5
Bark		*	*		88 & Above	1.5	0.5
Grass		*	0.3		Average	86.06	85.87
Spindle Twist		*	0.1		Samples Classed		
Preparation		-	*		Week	14,914	
All Other		*	*		Season		351,892

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.