



State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
AL	7	89.7	77.1	8,260	21	90.1	78.1	539,771
AR*	-	-	-	-	26	70.0	42.2	1,383,239
AZ	7	84.7	68.9	16,344	9	86.4	68.4	171,408
CA	2	95.0	92.9	6,453	10	86.1	75.2	73,374
FL	-	-	-	-	4	91.0	76.3	90,067
GA	18	90.6	77.0	31,042	53	88.4	74.2	1,708,216
KS	3	18.8	15.9	12,669	3	36.0	27.7	128,776
LA	-	-	-	-	14	71.5	47.6	223,299
MO	2	95.0	82.3	1,855	16	86.7	65.1	673,011
MS	-	-	-	-	30	63.7	36.5	706,510
NC	7	90.6	85.1	7,770	26	90.7	78.7	653,661
NM*	-	-	-	-	2	84.5	76.0	9,856
OK	10	80.2	67.8	25,405	10	92.2	80.5	390,495
SC	4	88.6	81.1	9,827	10	86.5	73.5	279,843
TN	-	-	-	-	17	82.3	63.4	340,307
TX	66	69.6	49.4	172,826	144	82.5	62.4	5,054,974
VA*	-	-	-	-	4	96.1	90.4	172,921
United States	131	74.2	57.7	299,947	399	81.9	62.8	12,599,728
AMERICAN PIMA								
AZ	2			2,013	2			13,718
CA	3			10,655	10			287,800
NM	-			-	-			-
TX	3			2,246	5			31,127
United States	8			14,914	18			351,892
United States all cotton	138			314,861	408			12,951,620

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 22, 2026

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	0.1	2.2	-	0.1	9.5	19.3	1.1	20.9	-	1.7	3.1	1.5
	3	0.1	1.3	-	0.1	0.6	4.0	0.7	8.3	-	0.5	3.3	1.1
	4	-	*	-	*	*	0.2	-	0.5	-	*	*	*
	5	-	*	-	-	-	*	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	0.13.6	-	0.2	10.1	23.6	1.8	29.8	-	2.2	6.4	2.6
31	1 - 2	6.0	9.5	-	1.1	7.6	9.8	9.2	14.9	-	3.1	11.1	7.8
	3	10.9	28.1	-	9.1	15.9	11.7	9.3	12.3	-	12.5	25.8	21.8
	4	0.8	7.2	-	3.4	2.3	2.4	0.7	4.3	-	2.8	3.4	4.2
	5	-	0.5	-	0.1	0.1	0.2	-	0.8	-	0.1	0.1	0.2
	6	-	*	-	*	-	*	-	0.1	-	-	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	17.845.3	-	13.7	25.8	24.1	19.1	32.4	-	18.4	40.5	34.0
41	1 - 2	6.7	3.3	-	0.8	5.0	2.4	13.8	5.4	-	2.8	4.4	5.3
	3	31.1	22.6	-	26.1	27.8	14.6	44.4	18.0	-	37.0	25.7	32.5
	4	9.6	15.6	-	35.2	17.9	13.3	16.3	6.3	-	28.9	9.7	16.4
	5	0.6	2.8	-	8.5	3.9	3.9	1.1	1.9	-	4.0	0.5	2.1
	6	*	0.2	-	0.7	0.8	0.5	*	0.4	-	0.2	*	0.1
	7	-	*	-	*	0.1	*	-	-	-	*	-	*
	8	-	-	-	-	-	*	-	-	-	-	-	-
Total		----	48.044.5	-	71.3	55.4	34.8	75.6	32.0	-	72.9	40.4	56.3
51	1 - 2	2.5	0.3	-	*	0.1	0.1	*	0.1	-	0.1	0.2	0.2
	3	17.6	2.0	-	2.3	2.3	1.2	0.6	0.4	-	1.7	5.3	2.2
	4	9.3	1.7	-	4.8	2.9	3.0	0.8	0.3	-	2.3	4.9	2.2
	5	1.0	0.4	-	2.2	0.7	2.3	0.1	0.1	-	0.6	0.5	0.5
	6	0.1	*	-	0.4	0.2	1.0	0.1	*	-	0.1	*	0.1
	7	-	*	-	0.1	0.2	0.3	-	-	-	*	-	*
	8	-	*	-	-	*	*	-	-	-	-	-	*
Total		----	30.44.4	-	9.9	6.4	7.8	1.6	0.9	-	4.8	11.0	5.1
61	1 - 2	0.3	*	-	*	-	*	-	-	-	-	-	*
	3	1.5	0.1	-	*	*	*	-	-	-	*	0.1	*
	4	0.6	*	-	*	*	*	-	-	-	*	0.1	*
	5	0.2	*	-	*	*	*	-	-	-	*	*	*
	6	*	*	-	*	-	*	-	-	-	*	*	*
	7	-	-	-	-	-	*	-	-	-	-	*	*
	8	-	-	-	-	-	-	-	-	-	-	-	*
Total		----	2.60.1	-	*	*	*	-	-	-	*	0.3	*
71	1 - 2	-	-	-	*	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	*	-	-	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	-	-	*	-	-	-	-	-	-	-	-
12 & 22	1 - 2	-	0.1	-	*	1.1	3.5	-	0.2	-	*	-	*
	3	-	*	-	*	0.1	1.6	-	0.3	-	*	0.1	0.1
	4	-	*	-	*	-	0.2	-	*	-	-	0.1	*
	5	-	-	-	*	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	-	0.1	*	1.2	5.4	-	0.5	-	*	0.1	0.1
32	1 - 2	*	0.1	-	*	0.1	0.1	*	0.4	-	*	-	*
	3	-	0.4	-	0.1	0.1	0.5	0.2	0.7	-	0.2	*	0.2
	4	-	0.1	-	0.1	*	0.3	-	0.7	-	*	*	0.1
	5	-	*	-	*	-	0.1	-	0.4	-	-	*	*
	6	-	*	-	*	-	*	-	0.1	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	*	0.6	0.2	0.2	1.1	0.2	2.2	-	0.3	0.1	0.4
42	1 - 2	-	*	-	*	*	*	0.2	0.1	-	0.1	*	*
	3	0.1	0.4	-	1.0	0.1	0.5	0.6	0.7	-	0.7	0.5	0.6
	4	0.3	0.5	-	1.5	0.4	0.7	0.4	0.4	-	0.4	0.2	0.4
	5	*	0.1	-	0.6	0.1	0.4	0.1	0.3	-	*	*	0.1
	6	-	*	-	0.1	*	0.1	*	0.2	-	*	-	*
	7	-	*	-	*	-	*	-	-	-	*	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total		----	0.4	1.1	3.2	0.6	1.7	1.4	1.7	-	1.2	0.7	1.1

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 22, 2026

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	*	*	-	*	*	*	*	*	-	*	*	*
	3	0.1	*	-	0.2	*	0.1	0.1	0.1	-	0.1	0.2	*
	4	0.2	0.1	-	0.6	*	0.3	0.1	0.1	-	0.1	0.2	0.1
	5	*	0.1	-	0.3	*	0.4	-	*	-	*	*	*
	6	-	*	-	0.1	-	0.2	-	-	-	*	*	*
	7	-	*	-	*	-	0.1	-	-	-	*	-	*
	8	-	-	-	-	-	*	-	-	-	-	-	*
Total	----	0.3	0.2	-	1.3	0.1	1.0	0.2	0.2	-	0.2	0.5	0.2
62	1 - 2	-	*	-	-	-	-	-	-	-	-	-	-
	3	*	*	-	*	-	-	-	*	-	*	*	*
	4	*	*	-	*	-	*	-	*	-	*	*	*
	5	-	*	-	*	-	*	-	-	-	*	-	*
	6	-	*	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	*	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	*	-	-	-	-	-	*
Total	----	0.1	*	-	*	-	*	-	*	-	*	*	*
13 & 23	1 - 2	-	*	-	-	-	0.2	-	*	-	-	-	*
	3	-	*	-	-	*	0.1	-	*	-	-	-	*
	4	-	*	-	-	*	*	-	-	-	-	-	*
	5	-	-	-	-	-	-	-	-	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	*	0.3	-	*	-	-	-	*
33	1 - 2	-	*	-	-	-	*	-	*	-	-	-	*
	3	-	*	-	*	-	*	*	*	-	-	*	*
	4	-	*	-	*	-	*	-	*	-	-	*	*
	5	-	*	-	*	-	*	-	*	-	-	-	*
	6	-	*	-	-	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	0.1	*	0.1	-	-	*	*
43	1 - 2	-	-	-	*	-	-	*	*	-	-	-	*
	3	*	*	-	*	-	*	*	*	-	*	*	*
	4	-	*	-	*	*	*	*	0.1	-	*	0.1	*
	5	-	*	-	*	*	*	-	*	-	-	*	*
	6	-	*	-	*	*	*	-	*	-	-	*	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	0.1	*	0.1	0.1	0.1	-	*	0.1	0.1
53	1 - 2	0.1	*	-	-	-	*	-	-	-	-	-	-
	3	0.1	*	-	*	-	*	-	*	-	*	-	*
	4	*	*	-	*	-	*	-	*	-	*	*	*
	5	-	*	-	*	-	*	-	*	-	*	*	*
	6	-	*	-	*	*	*	-	-	-	-	-	*
	7	-	-	-	*	*	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	0.3	*	-	*	*	*	-	*	-	*	*	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	-	-	-	-	-	-	-
24 - 54	1 - 8	-	*	-	*	*	*	*	*	-	-	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	*
31		*	*	-	*	-	*	-	-	-	*	*	*
32		0.4	*	-	*	-	*	-	-	-	*	0.1	0.1
33		0.9	0.6	-	0.1	*	*	-	*	-	0.2	0.7	0.9
34		7.9	3.5	-	0.3	0.6	0.5	-	0.3	-	2.4	5.6	4.8
35		35.6	12.2	-	2.7	4.9	3.0	0.6	2.5	-	12.4	18.6	16.0
36		34.5	24.4	-	13.9	12.2	12.1	35.7	18.6	-	29.2	33.3	31.2
37		19.7	41.1	-	50.6	45.8	44.9	54.5	44.6	-	35.5	30.6	34.6
38		0.8	14.5	-	26.8	25.0	28.4	7.1	21.3	-	15.3	7.8	9.7
39		0.1	3.1	-	5.1	9.6	9.1	2.0	11.3	-	4.4	2.3	2.5
40 & Longer		*	0.5	-	0.5	1.8	1.9	0.2	1.4	-	0.6	1.1	0.4
Average Staple		35.66	36.60	-	37.18	37.26	37.33	36.75	37.24	-	36.64	36.25	36.34
Average Length		1.11	1.14	-	1.16	1.16	1.17	1.14	1.16	-	1.14	1.13	1.13

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 22, 2026

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	0.4	4.7	-	4.5	-	*	-	2.0	1.2	0.4	-	44.4
	3	2.5	5.3	-	2.6	-	*	-	1.8	0.3	0.3	-	9.6
	4	1.2	1.2	-	*	-	*	-	*	*	*	-	0.9
	5	*	0.1	-	-	-	-	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	4.2	11.4	-	7.1	-	*	-	3.8	1.5	0.8	-	55.0
31	1 - 2	0.2	1.0	-	9.2	0.4	1.5	-	3.4	15.7	5.7	-	9.2
	3	4.4	8.2	-	36.6	0.4	8.9	-	20.3	23.3	20.2	-	17.9
	4	2.9	10.3	-	12.3	0.1	1.8	-	8.6	6.5	5.8	-	8.0
	5	0.6	3.0	-	0.8	-	*	-	0.6	0.2	0.3	-	1.3
	6	0.1	0.4	-	*	-	*	-	*	-	*	-	0.1
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	8.2	23.0	-	58.9	0.9	12.3	-	32.9	45.7	32.0	-	36.6
41	1 - 2	*	*	-	0.5	7.2	2.4	-	0.9	4.1	3.1	-	*
	3	3.3	1.3	-	10.1	66.8	38.0	-	18.8	29.6	30.0	-	0.7
	4	12.6	5.9	-	16.2	15.2	26.6	-	26.1	12.2	24.6	-	1.3
	5	13.6	8.8	-	4.9	0.3	3.2	-	7.3	3.7	4.5	-	1.5
	6	3.6	4.3	-	0.3	-	0.1	-	0.6	1.1	0.4	-	0.7
	7	0.2	0.9	-	-	-	*	-	*	-	*	-	0.1
	8	*	0.1	-	-	-	-	-	-	-	*	-	-
Total	----	33.3	21.3	-	32.0	89.5	70.3	-	53.6	50.7	62.5	-	4.4
51	1 - 2	-	-	-	*	1.4	0.2	-	*	*	*	-	-
	3	-	-	-	*	6.2	4.5	-	1.1	0.5	0.8	-	-
	4	0.2	*	-	0.4	1.3	6.0	-	3.3	0.9	1.7	-	*
	5	2.0	0.4	-	0.3	0.1	1.4	-	1.5	0.1	0.8	-	*
	6	2.7	1.3	-	0.1	-	0.1	-	0.2	-	0.2	-	*
	7	1.2	0.9	-	-	-	*	-	*	*	*	-	-
	8	0.4	0.2	-	-	-	-	-	-	-	*	-	-
Total	----	6.4	2.9	-	0.7	8.9	12.2	-	6.1	1.4	3.6	-	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-	-	-
Total	----	*	*	-	*	-	*	-	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	*	-	-	-	*	-	-
12 & 22	1 - 2	*	1.3	-	0.1	-	-	-	*	-	*	-	0.2
	3	1.0	3.8	-	*	-	*	-	*	-	*	-	0.1
	4	1.2	2.0	-	*	-	-	-	*	-	*	-	0.2
	5	0.2	0.2	-	*	-	-	-	-	-	-	-	-
	6	*	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
Total	----	2.5	7.3	-	0.1	-	*	-	*	-	*	-	0.4
32	1 - 2	0.1	0.1	-	0.1	-	*	-	*	*	*	-	0.7
	3	2.0	2.6	-	0.3	-	0.1	-	0.2	0.1	0.1	-	0.4
	4	4.9	5.0	-	0.2	-	*	-	0.1	0.1	0.1	-	0.8
	5	4.2	3.0	-	*	-	*	-	*	-	*	-	0.6
	6	1.0	0.6	-	*	-	-	-	*	-	-	-	0.2
	7	*	0.1	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
Total	----	12.1	11.4	-	0.5	-	0.1	-	0.3	0.2	0.3	-	2.6
42	1 - 2	*	*	-	*	-	0.1	-	*	-	*	-	-
	3	0.2	0.8	-	0.1	0.1	1.3	-	0.6	0.2	0.3	-	*
	4	3.6	3.3	-	0.4	-	1.4	-	1.2	0.2	0.3	-	0.1
	5	8.1	5.6	-	0.1	-	0.4	-	0.5	*	0.1	-	0.1
	6	5.6	4.3	-	*	-	0.1	-	0.1	-	*	-	0.1
	7	2.0	1.5	-	-	-	*	-	*	-	*	-	*
	8	0.4	0.2	-	-	-	-	-	-	-	*	-	-
Total	----	19.8	15.8	-	0.6	0.1	3.4	-	2.4	0.4	0.7	-	0.2

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 22, 2026

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	-	0.2	*	-	*	-	*	-	-
	3	-	-	-	*	0.3	0.5	-	0.1	-	*	-	-
	4	*	*	-	*	-	0.8	-	0.2	-	*	-	-
	5	0.3	0.1	-	*	-	0.3	-	0.3	-	*	-	-
	6	0.7	0.3	-	*	-	*	-	0.1	-	*	-	-
	7	0.9	0.5	-	-	-	*	-	*	-	*	-	-
	8	1.1	0.4	-	-	-	-	-	-	-	*	-	-
	Total	----	2.91.3	-*		0.51.6		-0.7		-0.1		-	-
62	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
	Total	----	-*	-	-	-*		-*		-*		-	-
13 & 23	1 - 2	-	0.1	-	-	-	-	-	-	-	*	-	-
	3	0.1	0.7	-	-	-	-	-	-	-	*	-	*
	4	0.4	0.5	-	-	-	-	-	-	-	*	-	*
	5	0.1	0.1	-	-	-	-	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	Total	----	0.61.5	-	-	-	-	-	-	-*		-*	
33	1 - 2	-	*	-	-	-	*	-	*	-	*	-	*
	3	0.1	0.1	-	*	-	*	-	*	-	*	-	0.1
	4	1.6	0.7	-	*	-	*	-	*	*	*	-	0.3
	5	1.6	0.5	-	*	-	-	-	-	-	*	-	0.2
	6	0.2	0.1	-	-	-	-	-	-	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
	Total	----	3.61.6	-*		-*		-*		**		-0.7	
43	1 - 2	-	-	-	*	-	*	-	-	-	*	-	-
	3	*	*	-	*	-	*	-	*	-	*	-	*
	4	1.3	0.4	-	*	-	*	-	*	-	*	-	-
	5	2.9	0.8	-	*	-	*	-	*	*	*	-	*
	6	1.5	0.7	-	-	-	*	-	*	-	*	-	*
	7	0.3	0.3	-	-	-	-	-	-	-	*	-	-
	8	0.1	0.1	-	-	-	-	-	-	-	*	-	-
	Total	----	6.22.4	-*		-0.1		-*		**		-*	
53	1 - 2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	*	-	-	-	*	-	*	-	*	-	-
	4	-	*	-	-	-	*	-	*	-	*	-	-
	5	-	*	-	-	-	*	-	*	-	*	-	-
	6	*	*	-	-	-	*	-	*	-	*	-	-
	7	*	*	-	-	-	-	-	*	-	*	-	-
	8	*	0.1	-	-	-	-	-	-	-	*	-	-
	Total	----	0.10.2	-	-	-*		-*		-*		-	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
	Total	----	-*	-	-	-	-	-*		-	-	-	-
24 - 54	1 - 8	*	0.1	-	-	-	*	-	-	-	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	-	-	*	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		-	*	-	-	-	-	-	*	-	*	-	-
32		-	*	-	-	-	*	-	*	-	*	-	-
33		*	0.2	-	0.1	-	*	-	0.2	0.3	0.1	-	*
34		0.3	0.9	-	1.1	-	0.2	-	2.1	4.0	1.4	-	2.2
35		2.9	4.1	-	10.0	0.1	1.8	-	11.5	24.5	8.3	-	9.9
36		10.8	12.1	-	26.9	17.1	10.5	-	27.7	40.4	24.4	-	15.0
37		34.4	31.7	-	42.1	66.8	48.9	-	36.4	26.8	48.7	-	31.8
38		34.7	32.9	-	15.0	14.1	33.2	-	15.0	3.6	14.1	-	34.2
39		16.0	16.0	-	4.4	1.8	4.9	-	5.4	0.5	2.7	-	6.0
40 & Longer		1.0	2.2	-	0.4	0.1	0.3	-	1.5	*	0.3	-	0.9
Average Staple		37.52	37.48	-	36.75	37.01	37.29	-	36.72	36.02	36.74	-	37.08
Average Length		1.17	1.17	-	1.15	1.16	1.17	-	1.15	1.12	1.15	-	1.16

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE For The Week Ending Jan 22, 2026											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	31.4	45.0	0.2	0.3	-	0.4	40.7	44.4	-	0.9
	3	3.6	7.2	0.3	0.4	-	0.1	8.8	13.1	-	1.3
	4	*	0.2	*	*	-	*	0.3	0.9	-	0.1
	5	-	*	-	-	-	*	*	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	35.1	52.4	0.5	0.8	-	0.5	49.8	58.5	-	2.2
31	1 - 2	19.1	14.2	2.5	2.3	-	6.9	13.2	4.0	-	8.7
	3	16.8	18.2	25.6	15.4	-	14.5	9.4	10.2	-	38.2
	4	2.6	3.6	14.0	5.8	-	3.2	1.5	4.1	-	8.3
	5	0.2	0.2	0.7	0.3	-	0.2	0.2	0.5	-	0.5
	6	*	*	-	*	-	*	*	*	-	*
	7	*	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	38.7	36.2	42.9	23.7	-	24.8	24.4	18.8	-	55.6
41	1 - 2	0.9	0.4	0.6	1.9	-	7.7	0.3	0.2	-	1.7
	3	6.6	1.8	19.2	31.6	-	35.8	1.1	1.7	-	21.6
	4	3.8	1.5	27.2	31.4	-	14.2	1.0	1.7	-	15.7
	5	0.5	0.5	7.0	4.7	-	1.8	0.5	0.5	-	2.6
	6	*	0.1	1.1	0.2	-	0.1	0.2	0.1	-	0.1
	7	-	*	-	*	-	*	0.1	*	-	*
	8	-	-	-	-	-	-	*	*	-	-
Total	----	11.9	4.3	55.1	69.7	-	59.6	3.2	4.3	-	41.8
51	1 - 2	*	*	-	0.1	-	0.2	*	*	-	*
	3	*	*	0.2	1.7	-	2.4	*	0.1	-	*
	4	*	*	0.8	2.4	-	2.2	*	0.1	-	0.1
	5	0.1	*	0.1	0.6	-	0.5	*	*	-	*
	6	*	*	-	0.1	-	*	*	*	-	*
	7	*	*	-	*	-	*	*	*	-	*
	8	-	*	-	-	-	-	*	*	-	-
Total	----	0.1	0.1	1.1	4.9	-	5.3	*	0.2	-	0.2
61	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	*	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	*	-	*	-	*	-	-
71	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	-	-	-	-	-	-	*	-	-
12 & 22	1 - 2	3.4	2.2	-	-	-	*	6.6	6.8	-	-
	3	1.1	1.0	-	*	-	*	3.1	3.7	-	*
	4	*	0.1	-	-	-	*	0.5	0.6	-	*
	5	-	*	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	4.6	3.3	-	*	-	*	10.1	11.1	-	*
32	1 - 2	1.1	0.3	-	*	-	0.2	2.4	0.6	-	*
	3	3.2	1.2	*	0.1	-	0.5	2.8	1.7	-	*
	4	1.0	0.5	*	0.1	-	0.1	1.2	1.2	-	*
	5	0.2	0.1	-	*	-	*	0.3	0.3	-	*
	6	*	*	-	*	-	-	0.1	*	-	-
	7	-	-	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
Total	----	5.6	2.2	*	0.1	-	0.8	6.7	3.9	-	0.1
42	1 - 2	*	*	-	*	-	0.9	0.1	*	-	*
	3	0.5	0.1	*	0.2	-	5.0	0.2	0.3	-	*
	4	0.4	0.2	0.2	0.4	-	1.5	0.3	0.5	-	*
	5	0.2	0.1	0.1	0.1	-	0.1	0.2	0.3	-	*
	6	*	*	-	*	-	*	0.1	0.1	-	*
	7	*	*	-	-	-	-	0.1	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
Total	----	1.1	0.5	0.3	0.7	-	7.5	1.1	1.2	-	0.1

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE											
For The Week Ending Jan 22, 2026											
Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	-	*	-	*	*	*	-	-
	3	-	*	-	*	-	0.7	*	*	-	-
	4	-	*	-	0.1	-	0.5	*	*	-	*
	5	*	*	-	*	-	0.1	*	*	-	*
	6	*	*	-	*	-	*	*	*	-	-
	7	*	*	-	-	-	-	*	*	-	-
	8	-	*	-	-	-	-	*	*	-	-
	Total	----	0.1	*	-	0.1	-	1.3	*	0.1	-
62	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	-	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
	Total	----	-	*	-	-	-	*	-	*	-
13 & 23	1 - 2	0.8	0.2	-	-	-	-	1.2	0.6	-	-
	3	0.3	0.2	-	-	-	-	0.6	0.4	-	*
	4	*	*	*	*	-	-	0.2	0.1	-	-
	5	-	-	-	-	-	-	*	*	-	-
	6	-	-	-	-	-	-	*	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
	Total	----	1.1	0.4	*	*	-	-	2.0	1.1	-
33	1 - 2	0.5	0.1	-	-	-	*	0.4	0.1	-	-
	3	0.6	0.3	*	*	-	*	0.7	0.3	-	*
	4	0.3	0.1	-	*	-	*	0.6	0.2	-	*
	5	*	*	-	*	-	-	0.4	0.1	-	*
	6	-	*	-	-	-	-	0.1	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
	Total	----	1.3	0.5	*	*	-	*	2.3	0.7	-
43	1 - 2	-	*	-	*	-	*	*	*	-	-
	3	*	*	-	*	-	*	0.1	*	-	*
	4	0.1	*	*	*	-	*	0.1	*	-	*
	5	0.1	*	-	*	-	*	*	*	-	*
	6	*	*	-	-	-	*	*	*	-	*
	7	-	*	-	-	-	-	*	*	-	-
	8	-	-	-	-	-	-	*	*	-	-
	Total	----	0.2	0.1	*	*	-	*	0.2	0.1	-
53	1 - 2	-	-	-	-	-	-	-	*	-	-
	3	-	*	-	*	-	*	-	*	-	-
	4	-	*	-	*	-	*	-	*	-	-
	5	*	*	-	*	-	*	-	*	-	-
	6	*	*	-	-	-	-	-	*	-	-
	7	-	*	-	*	-	-	*	*	-	-
	8	*	*	-	-	-	-	-	*	-	-
	Total	----	*	*	-	*	-	*	*	*	-
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	*	*	-	-	-	-	*	*	-	-
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	*	*	-	-	-	-	*	*	-
24 - 54	1 - 8	0.1	0.1	-	*	-	-	0.2	0.1	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	-	-	-	*	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	*	*	-	-
30		-	-	-	-	-	-	*	*	-	-
31		*	*	-	-	-	-	0.1	0.1	-	-
32		0.1	*	-	*	-	*	1.2	0.6	-	*
33		0.3	0.3	0.1	0.2	-	0.1	5.3	2.7	-	*
34		2.9	1.9	1.4	1.9	-	2.6	16.9	8.2	-	0.6
35		12.3	6.6	12.6	9.6	-	9.5	26.9	15.4	-	5.4
36		19.5	13.6	29.6	33.8	-	30.9	24.5	22.0	-	23.0
37		32.2	27.3	35.3	41.1	-	44.3	17.2	31.8	-	55.4
38		15.2	19.7	15.7	10.2	-	11.3	5.2	13.9	-	12.8
39		10.0	17.9	4.8	2.7	-	1.3	1.6	4.2	-	2.6
40 & Longer		7.4	12.7	0.6	0.4	-	0.1	1.0	1.1	-	0.1
Average Staple		37.05	37.63	36.68	36.57	-	36.56	35.58	36.35	-	36.82
Average Length		1.16	1.18	1.14	1.14	-	1.14	1.11	1.13	-	1.15

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 22, 2026

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	2.8	0.5	-	*	0.6	0.2	0.6	0.2	-	1.5	2.3	1.4
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	-	0.1	0.3	0.1	0.7	1.2	-	0.1	*	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	-	*	-	-	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	0.1	-	1.0	*	*	-	-	-	0.3	*	0.3
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	-	-	-	-	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	*	*	-	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	-	-	-	-	-	-	-
23	-	*	-	*	-	-	-	-	-	-	-	*
24	*	*	-	*	-	*	-	*	-	-	*	*
25	0.1	*	-	*	*	0.1	-	*	-	*	0.4	0.1
26	2.2	0.2	-	*	0.6	0.4	-	0.3	-	*	3.0	0.7
27	16.2	1.6	-	0.2	2.1	1.8	4.2	1.8	-	0.4	11.5	3.5
28	29.6	8.1	-	1.9	7.5	7.1	29.6	10.5	-	3.3	20.6	11.1
29	27.2	21.7	-	11.6	20.1	14.7	41.8	19.4	-	13.1	23.1	21.0
30	16.1	29.0	-	34.3	27.1	22.3	16.8	17.7	-	26.8	21.6	24.9
31	6.9	21.5	-	33.3	21.3	21.6	3.3	13.0	-	27.4	12.5	19.3
32	1.5	11.2	-	13.5	12.8	14.7	0.7	4.8	-	16.9	5.1	11.1
33	0.1	4.6	-	3.9	5.5	8.6	1.0	4.3	-	7.3	1.6	5.2
34	*	1.6	-	1.0	2.4	5.3	1.2	8.2	-	3.8	0.4	2.1
35	-	0.4	-	0.2	0.6	2.2	0.9	10.6	-	0.9	0.1	0.7
36	-	0.1	-	0.1	0.1	0.9	0.4	6.9	-	0.1	*	0.2
37	-	*	-	*	*	0.4	0.1	2.2	-	*	-	0.1
38	-	*	-	*	-	*	*	0.2	-	-	-	*
39	-	-	-	*	*	*	-	0.1	-	-	-	*
40 & Above	-	-	-	*	-	*	-	0.1	-	-	-	*
Average	29.12	30.68	-	31.07	30.78	31.25	29.55	31.78	-	31.27	29.62	30.59
Mike												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5	-	*	-	-	-	-	-	-	-	-	-	-
2.6	-	*	-	-	-	*	-	-	-	-	-	*
2.7	-	*	-	-	-	*	-	*	-	-	-	*
2.8	-	*	-	*	*	*	-	-	-	-	*	*
2.9	-	*	-	-	*	*	-	0.1	-	-	0.1	*
3.0	*	*	-	*	*	*	*	*	-	-	*	*
3.1	0.1	*	-	*	0.2	0.1	-	0.3	-	*	0.2	*
3.2	0.2	*	-	*	*	0.1	-	0.2	-	0.1	0.3	0.1
3.3	*	0.1	-	*	*	0.1	0.2	0.2	-	0.1	0.6	0.2
3.4	*	0.4	-	*	0.1	0.2	0.8	0.4	-	0.1	1.5	0.3
3.5	2.3	0.8	-	*	0.1	0.4	0.6	0.7	-	0.5	1.9	0.6
3.6	1.6	1.1	-	0.1	0.8	0.7	0.7	1.2	-	0.7	2.4	1.1
3.7	5.8	2.0	-	0.1	1.1	1.3	5.2	2.2	-	1.2	4.0	1.9
3.8	5.2	2.9	-	0.1	1.9	1.6	11.2	5.2	-	1.3	6.5	2.9
3.9	5.3	4.4	-	0.3	2.3	2.6	17.0	7.7	-	2.1	6.4	4.1
4.0	7.4	5.9	-	0.6	2.8	4.2	19.3	9.7	-	3.4	7.6	5.6
4.1	8.2	7.9	-	1.0	4.9	6.6	22.7	11.2	-	5.6	9.5	7.4
4.2	8.4	9.8	-	1.7	8.5	8.6	12.8	11.7	-	7.1	11.5	8.9
4.3	13.5	10.8	-	3.1	12.9	10.2	4.9	8.5	-	9.7	10.5	9.8
4.4	12.0	10.7	-	5.0	13.3	11.2	1.5	5.9	-	12.3	10.2	10.0
4.5	8.0	10.2	-	7.8	8.0	12.2	0.9	5.8	-	13.0	7.6	9.7
4.6	6.4	9.0	-	11.7	9.1	11.5	0.3	5.8	-	11.2	5.7	9.2
4.7	5.7	7.2	-	14.5	8.4	8.9	0.2	6.2	-	12.4	3.7	8.3
4.8	3.7	5.7	-	15.4	6.9	6.8	0.3	4.9	-	8.4	3.5	6.7
4.9	2.8	4.3	-	13.7	6.5	5.2	0.2	4.0	-	5.2	3.4	5.2
5.0	0.9	2.8	-	10.9	3.2	3.4	0.2	2.8	-	3.2	1.9	3.6
5.1	0.4	1.8	-	7.1	3.0	1.5	0.5	2.5	-	1.7	0.9	2.3
5.2	0.6	1.1	-	4.1	2.2	1.0	0.3	1.2	-	0.5	0.2	1.2
5.3	0.2	0.6	-	1.9	2.3	0.7	0.1	0.9	-	0.1	*	0.6
5.4	0.3	0.3	-	0.6	1.1	0.3	-	0.6	-	0.1	*	0.2
5.5 & Above	0.9	0.2	-	0.2	0.5	0.5	-	0.2	-	0.1	-	0.1
Average	4.27	4.39	-	4.76	4.51	4.46	4.03	4.32	-	4.48	4.22	4.42

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 22, 2026

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	66.1	36.5	-	0.1	-	*	-	*	3.9	1.6	-	2.9
Bark - Level 2	-	*	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	-	*	-	*	-	*	-	*	-	0.6
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	-	-	*	-	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	0.1	-	0.4	-	0.2	-	0.3	1.6	0.5	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	-	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	-	*	-	*	*	*	-	0.1
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	*	-	-	-	-	-	*
23	-	*	-	-	-	*	-	-	-	-	-	-
24	*	*	-	-	-	*	-	*	-	*	-	-
25	0.1	0.1	-	*	-	*	-	*	0.2	*	-	*
26	0.5	0.4	-	*	-	*	-	0.1	1.2	0.3	-	0.2
27	1.0	0.9	-	0.5	0.1	0.1	-	1.0	5.9	2.3	-	1.9
28	2.4	1.9	-	4.4	0.8	0.7	-	4.8	18.2	10.9	-	7.4
29	4.3	3.7	-	19.0	36.0	8.0	-	15.6	33.1	28.2	-	22.0
30	8.0	8.5	-	33.2	49.5	36.8	-	26.9	25.4	31.5	-	33.4
31	12.0	16.8	-	21.1	10.7	35.8	-	26.3	10.8	17.3	-	17.9
32	23.3	24.5	-	11.7	2.9	13.1	-	16.1	3.6	6.9	-	11.3
33	27.4	23.1	-	5.1	0.1	4.5	-	6.5	1.2	2.0	-	4.3
34	15.2	13.5	-	2.9	0.1	1.0	-	2.3	0.3	0.4	-	1.5
35	4.4	5.3	-	1.8	-	0.1	-	0.4	0.1	0.1	-	0.1
36	1.1	1.1	-	0.2	-	*	-	*	-	*	-	-
37	0.2	0.2	-	*	-	*	-	*	-	-	-	*
38	*	0.1	-	*	-	*	-	*	-	-	-	-
39	*	*	-	-	-	-	-	-	-	-	-	-
40 & Above	*	*	-	-	-	-	-	*	-	-	-	-
Average	32.62	32.57	-	30.97	30.20	31.15	-	31.06	29.76	30.26	-	30.61
Mike												
2.4 & Below	0.8	0.2	-	-	-	-	-	-	-	-	-	-
2.5	2.5	1.0	-	-	-	-	-	-	-	*	-	*
2.6	1.9	1.2	-	*	-	-	-	-	-	-	-	*
2.7	2.7	1.7	-	*	-	-	-	-	-	*	-	0.2
2.8	3.3	2.1	-	-	-	-	-	-	-	*	-	3.0
2.9	3.6	2.3	-	*	-	-	-	-	-	*	-	3.0
3.0	4.4	2.6	-	*	-	-	-	-	-	*	-	1.4
3.1	4.5	3.1	-	*	-	*	-	-	*	*	-	0.8
3.2	5.8	3.9	-	*	-	*	-	*	-	0.1	-	1.4
3.3	4.8	4.3	-	*	-	*	-	*	*	0.2	-	1.0
3.4	4.8	5.3	-	0.1	-	*	-	*	0.3	0.3	-	0.8
3.5	5.1	5.8	-	0.1	-	*	-	0.1	0.7	0.5	-	1.1
3.6	5.4	6.4	-	0.1	-	0.1	-	0.1	1.2	0.9	-	1.3
3.7	5.7	6.7	-	0.2	-	0.2	-	0.2	3.3	1.5	-	3.3
3.8	4.8	6.5	-	0.3	-	0.3	-	0.3	5.0	2.4	-	5.5
3.9	4.6	6.2	-	0.6	-	0.6	-	0.4	7.7	3.5	-	8.2
4.0	4.9	6.6	-	1.3	0.9	1.4	-	0.8	10.5	4.9	-	7.4
4.1	4.8	7.2	-	2.2	1.0	2.4	-	1.3	10.5	7.0	-	7.4
4.2	5.0	5.9	-	3.4	5.5	4.3	-	2.0	9.5	9.3	-	7.8
4.3	6.9	6.1	-	4.9	5.9	6.7	-	3.0	11.8	11.6	-	10.0
4.4	4.3	5.1	-	6.3	14.3	9.7	-	4.5	8.9	12.2	-	8.3
4.5	2.4	3.5	-	8.2	19.3	13.0	-	6.2	8.7	11.3	-	8.7
4.6	2.4	2.1	-	9.7	20.9	15.1	-	8.7	11.1	10.2	-	6.6
4.7	2.5	1.8	-	11.2	14.7	15.7	-	11.2	5.4	8.5	-	5.6
4.8	1.6	1.3	-	12.6	8.7	13.3	-	13.6	1.4	6.0	-	3.3
4.9	0.4	0.6	-	11.7	4.0	8.6	-	14.6	2.0	4.1	-	2.5
5.0	-	0.2	-	9.6	3.0	4.9	-	13.3	2.0	2.7	-	1.0
5.1	-	*	-	7.7	1.0	2.3	-	9.9	0.3	1.5	-	0.1
5.2	-	*	-	4.4	1.0	0.9	-	5.7	*	0.7	-	0.1
5.3	-	-	-	2.6	-	0.3	-	2.6	-	0.3	-	*
5.4	-	-	-	1.3	-	0.1	-	1.0	-	0.1	-	-
5.5 & Above	-	-	-	1.4	-	*	-	0.4	-	*	-	-
Average	3.65	3.77	-	4.74	4.57	4.61	-	4.80	4.26	4.41	-	4.11

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE										
For The Week Ending Jan 22, 2026										
Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	10.4	2.8	5.7	3.4	-	*	15.5	4.5	-	1.3
Bark - Level 2	*	*	-	-	-	-	*	*	-	-
Grass - Level 1	0.5	0.1	-	0.1	-	*	0.1	0.2	-	*
Grass - Level 2	-	-	-	-	-	-	*	*	-	-
Prep - Level 1	-	-	-	*	-	-	*	*	-	*
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	3.2	1.7	-	*	1.7	0.3	-	0.6
Seed Coat - Level 2	-	*	-	-	-	-	*	*	-	-
Oil - Level 1	-	*	-	*	-	-	*	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	*	-	-
Other - Level 1	-	*	-	-	-	-	*	*	-	-
Other - Level 2	-	*	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	-	*	-	-	-	-	*	*	-	-
23	-	*	-	-	-	-	0.1	*	-	-
24	*	*	*	*	-	*	0.3	0.1	-	*
25	*	*	*	*	-	*	0.8	0.2	-	*
26	0.1	0.2	1.3	0.4	-	*	2.3	0.8	-	1.1
27	1.0	0.7	4.2	2.6	-	0.5	6.0	2.9	-	6.2
28	4.1	3.1	13.9	12.5	-	3.8	11.6	7.8	-	19.0
29	11.7	8.8	34.2	34.8	-	21.0	19.2	15.8	-	32.2
30	22.3	15.3	26.2	30.2	-	38.7	21.8	21.0	-	25.7
31	22.6	18.7	12.9	13.3	-	24.7	17.3	18.6	-	11.1
32	14.8	16.7	6.7	4.8	-	8.2	10.8	13.3	-	3.6
33	9.9	15.0	0.5	1.1	-	2.4	5.8	9.3	-	0.8
34	6.4	11.1	0.1	0.2	-	0.7	2.7	6.1	-	0.2
35	2.6	6.2	*	*	-	0.1	0.9	2.7	-	*
36	3.0	2.5	*	*	-	*	0.3	0.9	-	*
37	1.2	1.3	-	*	-	*	0.1	0.3	-	-
38	0.2	0.3	-	-	-	-	*	0.1	-	-
39	*	*	-	-	-	-	*	*	-	-
40 & Above	*	*	-	-	-	-	*	*	-	-
Average	31.70	32.26	29.93	30.02	-	30.66	30.43	31.20	-	29.73
Mike										
2.4 & Below	*	*	-	-	-	-	0.3	*	-	-
2.5	0.2	*	-	-	-	-	0.3	*	-	-
2.6	0.4	*	-	-	-	-	0.4	0.1	-	-
2.7	0.6	0.1	-	-	-	*	0.6	0.2	-	*
2.8	0.7	0.1	*	*	-	*	0.7	0.2	-	*
2.9	0.6	0.1	-	*	-	*	1.0	0.4	-	*
3.0	0.4	0.1	-	*	-	*	1.2	0.6	-	0.1
3.1	0.9	0.3	*	*	-	*	1.5	0.8	-	0.1
3.2	1.5	0.5	0.1	0.1	-	*	1.8	1.2	-	0.1
3.3	2.4	0.8	0.3	0.2	-	*	2.2	1.6	-	0.3
3.4	1.8	1.1	0.9	0.3	-	0.1	3.0	2.1	-	0.4
3.5	2.8	1.6	2.3	0.5	-	0.3	3.6	2.7	-	0.7
3.6	3.3	2.7	2.8	0.8	-	0.3	4.1	3.4	-	1.3
3.7	5.0	4.0	5.2	1.8	-	0.8	4.8	4.1	-	2.6
3.8	7.4	5.4	7.0	2.7	-	1.1	5.4	5.1	-	3.9
3.9	7.1	7.1	8.5	4.2	-	1.7	5.7	6.3	-	6.7
4.0	8.4	8.6	10.1	5.7	-	2.5	6.7	7.4	-	9.2
4.1	10.1	10.0	13.9	7.1	-	3.9	7.2	8.5	-	11.5
4.2	11.7	10.2	11.8	8.6	-	5.3	7.5	9.5	-	14.1
4.3	10.4	10.9	10.2	9.9	-	6.7	8.4	9.8	-	14.5
4.4	7.7	10.0	7.2	10.5	-	9.5	8.2	9.2	-	12.7
4.5	7.7	9.3	6.0	10.5	-	11.8	7.2	8.0	-	9.1
4.6	5.1	7.3	4.7	9.8	-	13.4	5.9	6.5	-	5.9
4.7	2.3	5.0	6.2	8.6	-	13.4	4.4	4.8	-	3.2
4.8	1.2	2.8	2.0	6.8	-	11.8	3.3	3.2	-	1.8
4.9	0.4	1.3	0.5	4.9	-	8.1	2.2	1.9	-	1.1
5.0	0.2	0.6	0.2	3.3	-	5.4	1.3	1.1	-	0.6
5.1	*	0.1	*	2.0	-	2.7	0.6	0.6	-	0.2
5.2	-	*	-	1.0	-	1.0	0.3	0.3	-	*
5.3	-	*	-	0.4	-	0.3	0.1	0.2	-	*
5.4	-	-	-	0.2	-	*	*	0.1	-	*
5.5 & Above	-	*	-	0.1	-	*	*	0.1	-	*
Average	4.05	4.20	4.15	4.42	-	4.56	4.07	4.16	-	4.23

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE												
For The Week Ending Jan 22, 2026												
Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	*	-	-	-	*	-	-	-	-	-	*
2.7 - 2.9	-	*	-	*	*	0.1	-	0.1	-	-	0.1	*
3.0 - 3.2	0.4	0.1	-	*	0.2	0.2	*	0.5	-	0.1	0.5	0.1
3.3 - 3.4	*	0.5	-	*	0.2	0.4	1.0	0.6	-	0.1	2.1	0.5
3.5 - 3.6	3.9	1.9	-	0.1	0.9	1.1	1.3	1.8	-	1.2	4.3	1.7
3.7 - 4.2	40.2	32.8	-	4.0	21.5	25.0	88.2	47.6	-	20.7	45.4	30.6
4.3 - 4.9	52.2	57.9	-	71.1	65.0	66.0	8.4	41.1	-	72.1	44.5	58.9
5.0 - 5.2	1.9	5.7	-	22.1	8.3	5.9	1.0	6.5	-	5.4	3.0	7.2
5.3 & Above	1.3	1.1	-	2.8	3.8	1.4	0.1	1.8	-	0.3	*	0.9
Average	4.27	4.39	-	4.76	4.51	4.46	4.03	4.32	-	4.48	4.22	4.42
Leaf												
1 - 2	15.8	15.4	-	2.1	23.5	35.5	24.4	42.1	-	7.8	18.8	14.8
3	61.5	55.0	-	39.0	46.8	34.4	55.9	41.0	-	52.7	61.2	58.5
4	20.8	25.3	-	45.7	23.6	20.5	18.3	12.6	-	34.5	18.8	23.5
5	1.8	3.9	-	11.9	4.8	7.3	1.3	3.5	-	4.8	1.2	2.9
6	0.1	0.3	-	1.3	1.0	1.8	0.1	0.7	-	0.3	*	0.2
7	-	*	-	0.1	0.3	0.4	-	-	-	*	*	*
8	-	*	-	-	*	*	-	-	-	-	-	*
Average	3.09	3.18	-	3.72	3.09	3.00	2.96	2.73	-	3.37	3.02	3.15
HVI Trash 1/												
00	-	-	-	-	*	*	-	*	-	-	-	-
01	1.3	2.0	-	0.1	8.5	14.2	4.5	15.0	-	0.9	1.4	1.4
02	19.7	17.6	-	3.1	20.3	26.7	26.8	32.4	-	9.4	24.1	19.9
03	34.2	28.1	-	14.7	26.9	18.6	32.3	24.2	-	23.4	34.0	32.0
04	25.5	23.9	-	24.5	20.3	14.5	20.0	13.5	-	28.1	22.8	23.6
05	12.0	14.5	-	22.9	12.2	10.1	10.4	6.8	-	19.3	11.4	12.7
06	4.8	7.5	-	15.9	5.9	6.6	4.0	3.6	-	10.3	4.1	5.9
07	1.6	3.6	-	9.4	3.0	4.0	1.4	2.1	-	4.8	1.4	2.6
08	0.4	1.6	-	4.9	1.2	2.4	0.4	1.3	-	2.2	0.5	1.1
09	0.2	0.7	-	2.5	0.7	1.4	0.1	0.7	-	0.9	0.2	0.5
10	0.1	0.3	-	1.2	0.4	0.7	*	0.3	-	0.5	0.1	0.2
11	*	0.1	-	0.5	0.2	0.4	*	0.2	-	0.2	*	0.1
12	*	0.1	-	0.2	0.2	0.2	*	0.1	-	0.1	*	*
13	*	*	-	0.1	0.1	0.1	-	*	-	*	*	*
14	*	*	-	*	*	0.1	-	*	-	*	*	*
15	-	*	-	*	*	*	-	-	-	*	-	*
16	-	*	-	-	0.1	*	-	-	-	*	*	*
17	*	*	-	-	*	*	-	-	-	*	-	*
18 & Above	-	*	-	-	*	*	-	-	-	*	*	*
Average	0.35	0.38	-	0.51	0.36	0.35	0.33	0.30	-	0.43	0.34	0.37
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	-	-	-	-	-	-	-	-	-	-	*
76	0.1	*	-	*	*	*	-	*	-	*	0.1	*
77	0.2	*	-	*	0.1	*	-	*	-	*	0.3	0.1
78	2.2	0.4	-	0.1	0.2	0.2	-	0.8	-	0.1	1.6	0.9
79	18.1	2.9	-	0.5	2.9	1.9	5.2	5.3	-	1.1	7.0	5.5
80	33.8	13.7	-	3.9	13.3	12.5	64.0	25.4	-	7.8	23.6	21.3
81	29.4	31.9	-	20.5	42.1	35.6	26.7	28.3	-	37.1	37.2	36.3
82	14.9	34.6	-	42.8	35.2	39.3	2.7	24.2	-	41.9	22.1	26.3
83	1.2	14.5	-	27.7	5.9	9.6	1.3	12.3	-	10.9	7.1	8.1
84	*	2.0	-	4.3	0.3	0.8	0.2	3.5	-	1.1	1.0	1.3
85 & Above	-	0.2	-	0.3	*	*	*	0.1	-	0.1	*	0.1
Average	80.83	81.94	-	82.52	81.75	81.89	80.79	81.66	-	82.02	81.40	81.56
Tenderable 3/	89.7	90.1	-	70.0	84.7	86.4	95.0	86.1	-	91.0	90.6	88.4
SAMPLES CLASSED	8,260	539,771	-	1,383,239	16,344	171,408	6,453	73,374	-	90,067	31,042	1,708,216

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 22, 2026

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	0.8	0.2	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	4.4	2.3	-	*	-	-	-	-	-	*	-	0.1
2.7 - 2.9	9.5	6.0	-	*	-	-	-	-	-	*	-	6.2
3.0 - 3.2	14.7	9.6	-	*	-	*	-	*	*	0.2	-	3.7
3.3 - 3.4	9.6	9.6	-	0.1	-	*	-	*	0.3	0.5	-	1.8
3.5 - 3.6	10.5	12.2	-	0.2	-	0.1	-	0.2	1.8	1.4	-	2.4
3.7 - 4.2	29.9	39.2	-	8.1	7.4	9.2	-	5.0	46.5	28.6	-	39.6
4.3 - 4.9	20.6	20.6	-	64.6	87.7	82.1	-	61.8	49.1	64.0	-	45.0
5.0 - 5.2	-	0.3	-	21.7	4.9	8.1	-	29.0	2.3	4.9	-	1.2
5.3 & Above	-	-	-	5.2	-	0.5	-	4.0	-	0.4	-	*
Average	3.65	3.77	-	4.74	4.57	4.61	-	4.80	4.26	4.41	-	4.11
Leaf												
1 - 2	0.8	7.3	-	14.2	9.2	4.2	-	6.3	21.0	9.3	-	54.5
3	13.8	22.9	-	49.8	73.9	53.4	-	42.8	54.0	51.8	-	28.8
4	29.9	29.5	-	29.5	16.6	36.8	-	39.7	19.9	32.6	-	11.8
5	33.6	22.7	-	6.1	0.4	5.3	-	10.1	4.0	5.8	-	3.7
6	15.3	12.1	-	0.4	-	0.3	-	1.0	1.1	0.6	-	1.0
7	4.6	4.3	-	-	-	*	-	*	*	0.1	-	0.2
8	2.0	1.1	-	-	-	-	-	-	-	*	-	-
Average	4.71	4.26	-	3.28	3.08	3.44	-	3.57	3.10	3.37	-	2.57
HVI Trash 1/												
00	-	-	-	-	-	*	-	-	-	-	-	-
01	*	1.7	-	1.9	0.2	0.2	-	0.5	2.8	0.8	-	22.0
02	1.1	7.2	-	15.0	14.7	6.5	-	7.7	22.3	11.1	-	35.5
03	5.8	10.4	-	24.4	40.6	23.5	-	19.0	26.8	24.4	-	18.6
04	9.1	12.3	-	23.2	29.8	28.7	-	23.6	21.6	25.5	-	10.5
05	11.0	12.3	-	16.2	10.4	20.7	-	19.9	12.4	18.3	-	6.4
06	11.7	10.8	-	9.6	3.3	11.2	-	13.3	6.4	10.5	-	3.1
07	12.8	9.5	-	5.2	0.7	5.3	-	7.9	3.4	5.2	-	2.0
08	12.2	8.4	-	2.5	0.3	2.3	-	4.2	1.9	2.4	-	1.1
09	11.1	6.9	-	1.2	-	1.0	-	2.1	1.2	1.0	-	0.5
10	7.2	5.3	-	0.5	-	0.4	-	1.0	0.6	0.4	-	0.2
11	5.6	4.2	-	0.2	-	0.2	-	0.5	0.3	0.2	-	0.1
12	3.7	3.3	-	0.1	-	0.1	-	0.2	0.1	0.1	-	0.1
13	2.8	2.4	-	*	-	*	-	0.1	*	*	-	*
14	2.0	1.7	-	*	-	*	-	*	-	*	-	-
15	1.3	1.1	-	-	-	*	-	*	-	*	-	-
16	0.9	0.8	-	-	-	-	-	-	-	*	-	-
17	0.6	0.5	-	-	-	-	-	-	-	*	-	-
18 & Above	1.2	0.9	-	-	-	-	-	-	-	*	-	-
Average	0.78	0.67	-	0.41	0.35	0.44	-	0.47	0.38	0.43	-	0.27
UNIFORMITY 2/												
74 & Below	*	*	-	-	-	-	-	-	-	*	-	-
75	0.2	0.1	-	-	-	-	-	-	-	*	-	*
76	0.7	0.5	-	-	-	*	-	*	0.1	*	-	0.1
77	2.2	1.7	-	-	-	*	-	*	0.4	*	-	0.1
78	4.6	3.7	-	0.1	-	0.1	-	0.2	1.2	0.6	-	2.5
79	8.5	7.7	-	1.2	-	0.2	-	1.3	8.5	3.0	-	6.8
80	17.4	17.3	-	7.1	1.3	2.1	-	8.8	21.4	11.0	-	16.8
81	26.0	31.8	-	30.1	16.7	16.6	-	30.1	27.6	27.2	-	36.7
82	25.1	24.8	-	40.4	56.2	50.4	-	38.1	29.9	35.3	-	28.6
83	12.9	10.3	-	18.5	24.2	27.8	-	18.1	9.8	19.9	-	8.0
84	2.2	1.9	-	2.6	1.7	2.5	-	3.3	1.1	2.7	-	0.3
85 & Above	0.2	0.1	-	0.1	-	0.2	-	0.1	*	0.2	-	*
Average	81.42	81.43	-	82.20	82.50	82.56	-	82.18	81.54	82.10	-	81.50
Tenderable 3/	18.8	36.0	-	71.5	95.0	86.7	-	63.7	90.6	90.7	-	84.5
SAMPLES CLASSED	12,669	128,776	-	223,299	1,855	673,011	-	706,510	7,770	653,661	-	9,856

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE

For The Week Ending Jan 22, 2026

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	*	*	-	-	-	-	0.3	*	-	-
2.5 - 2.6	0.5	0.1	-	-	-	-	0.7	0.1	-	-
2.7 - 2.9	1.8	0.2	*	*	-	*	2.2	0.8	-	*
3.0 - 3.2	2.7	0.9	0.1	0.1	-	*	4.4	2.6	-	0.3
3.3 - 3.4	4.1	1.9	1.2	0.5	-	0.2	5.2	3.7	-	0.6
3.5 - 3.6	6.0	4.3	5.0	1.3	-	0.6	7.7	6.1	-	2.0
3.7 - 4.2	49.8	45.3	56.5	30.0	-	15.1	37.4	41.0	-	48.0
4.3 - 4.9	34.7	46.6	36.9	61.1	-	74.7	39.6	43.3	-	48.2
5.0 - 5.2	0.3	0.7	0.3	6.3	-	9.0	2.2	2.0	-	0.8
5.3 & Above	-	*	-	0.7	-	0.3	0.2	0.3	-	*
Average	4.05	4.20	4.15	4.42	-	4.56	4.07	4.16	-	4.23
Leaf										
1 - 2	57.3	62.4	3.3	4.6	-	16.4	65.0	56.8	-	11.3
3	32.8	30.1	45.5	49.4	-	59.0	26.9	31.6	-	61.2
4	8.4	6.3	42.3	40.0	-	21.8	5.6	9.4	-	24.3
5	1.3	1.1	7.8	5.8	-	2.7	1.7	1.9	-	3.1
6	0.1	0.2	1.1	0.2	-	0.2	0.6	0.3	-	0.1
7	*	*	-	*	-	*	0.2	*	-	*
8	*	*	-	-	-	-	*	*	-	-
Average	2.38	2.25	3.58	3.48	-	3.11	2.33	2.42	-	3.20
HVI Trash 1/										
00	*	*	-	-	-	*	*	0.1	-	-
01	26.7	32.3	0.1	0.2	-	2.0	29.0	27.5	-	0.5
02	33.8	33.2	4.6	6.6	-	17.1	41.7	34.0	-	12.5
03	19.3	18.2	19.2	22.4	-	29.7	15.9	18.3	-	29.6
04	10.6	9.0	26.1	27.7	-	24.7	6.3	9.7	-	26.5
05	5.2	3.9	23.0	21.5	-	14.2	2.9	5.2	-	16.0
06	2.4	1.7	14.0	12.3	-	6.8	1.6	2.7	-	8.3
07	1.0	0.8	7.2	5.7	-	3.1	0.9	1.3	-	3.9
08	0.5	0.4	3.1	2.3	-	1.3	0.6	0.6	-	1.7
09	0.2	0.2	1.3	0.9	-	0.6	0.4	0.3	-	0.7
10	0.1	0.1	0.9	0.3	-	0.2	0.2	0.1	-	0.2
11	0.1	0.1	0.3	0.1	-	0.1	0.2	0.1	-	0.1
12	*	*	0.1	*	-	*	0.1	*	-	*
13	*	*	*	*	-	*	0.1	*	-	*
14	*	*	*	*	-	*	*	*	-	*
15	*	*	-	*	-	*	*	*	-	*
16	-	*	-	*	-	-	*	*	-	*
17	-	*	-	-	-	-	*	*	-	*
18 & Above	-	*	-	*	-	-	*	*	-	*
Average	0.25	0.23	0.47	0.44	-	0.38	0.23	0.25	-	0.40
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	0.1	*	-	-
75	*	*	-	*	-	-	0.1	*	-	-
76	*	*	*	*	-	*	0.6	0.2	-	*
77	0.3	0.2	0.3	0.1	-	*	2.3	0.9	-	*
78	2.2	1.0	1.5	0.5	-	0.1	7.5	3.9	-	0.2
79	10.8	5.5	6.4	3.7	-	0.6	20.4	12.6	-	1.3
80	30.8	18.5	18.0	16.6	-	6.9	33.1	26.2	-	8.2
81	29.9	31.6	40.1	32.6	-	32.7	25.1	29.6	-	27.9
82	18.1	25.9	25.6	32.7	-	43.1	8.8	18.1	-	38.3
83	6.4	13.4	7.1	12.6	-	15.6	1.7	6.7	-	21.1
84	1.5	3.5	1.0	1.1	-	0.9	0.3	1.6	-	2.9
85 & Above	*	0.3	*	0.1	-	0.1	0.1	0.2	-	0.2
Average	81.21	81.76	81.51	81.81	-	82.14	80.49	81.14	-	82.23
Tenderable 3/	80.2	92.2	88.6	86.5	-	82.3	69.6	82.5	-	96.1
SAMPLES CLASSED	25,405	390,495	9,827	279,843	-	340,307	172,826	5,054,974	-	172,921

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE									
For The Week Ending Jan 22, 2026									
Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	19.5	7.8	3.2	5.3	-	-	11.1	16.2
	2	2.8	1.0	6.9	6.6	-	-	23.4	18.3
	3	-	*	0.1	0.1	-	-	1.0	0.6
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		22.3	8.8	10.2	12.0	-	-	35.5	35.0
02	1	55.0	43.3	7.7	4.5	-	-	6.8	13.4
	2	12.2	16.8	48.0	33.8	-	-	40.5	41.8
	3	0.1	0.1	8.3	8.7	-	-	5.7	3.4
	4	-	-	*	0.1	-	-	0.1	0.1
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		67.3	60.2	64.0	47.1	-	-	53.1	58.8
03	1	4.7	9.3	0.7	0.2	-	-	0.4	0.4
	2	5.2	17.7	15.0	14.6	-	-	6.4	4.7
	3	0.2	0.8	9.0	19.1	-	-	3.1	0.9
	4	-	-	0.3	2.0	-	-	*	0.1
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		10.1	27.8	24.9	35.9	-	-	9.8	6.1
04	7	-	-	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-
	5	-	-	-	0.1	-	-	-	-
	4	-	*	0.2	1.0	-	-	0.4	*
	3	*	0.5	0.4	2.5	-	-	0.9	0.1
	2	0.2	2.3	0.3	0.6	-	-	0.1	*
	1	-	0.2	*	*	-	-	-	-
Total -----		0.2	3.0	0.9	4.1	-	-	1.5	0.2
05	1	-	-	-	*	-	-	-	-
	2	-	0.1	-	0.1	-	-	-	-
	3	-	*	*	0.3	-	-	0.1	*
	4	-	-	*	0.3	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	0.2	*	0.7	-	-	0.1	*
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	*	-	-	-	-
	3	-	-	*	0.1	-	-	-	-
	4	-	-	*	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	*	0.1	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
Total -----		-	-	-	0.1	-	-	-	-
STAPLE									
44 & Shorter		-	*	-	2.2	-	-	15.0	12.3
46		11.0	16.7	0.4	7.5	-	-	45.8	48.0
48		70.0	73.9	46.1	45.1	-	-	31.3	35.1
50		17.9	9.1	50.0	43.2	-	-	7.9	4.2
52 & Longer		1.1	0.3	3.5	2.0	-	-	0.1	0.4
Average Staple		48.18	47.86	49.13	48.71	-	-	46.65	46.65
Average Length		1.40	1.39	1.43	1.42	-	-	1.36	1.36
EXTRANEIOUS MATTER									
Bark		-	-	-	*	-	-	0.1	*
Grass		-	-	-	0.3	-	-	0.1	0.9
Spindle Twist		-	-	*	0.1	-	-	*	*
Preparation		-	*	-	*	-	-	-	-
All Other		*	*	*	*	-	-	0.1	*

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE								
For The Week Ending Jan 22, 2026								
Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	-
2.7 - 2.9	-	*	-	0.1	-	-	*	0.2
3.0 - 3.2	*	*	*	0.5	-	-	2.4	9.2
3.3 - 3.4	0.1	0.4	0.2	1.4	-	-	4.1	13.7
3.5 - 3.6	6.9	3.2	7.7	6.8	-	-	11.7	18.9
3.7 - 4.2	82.3	90.9	86.9	87.2	-	-	73.0	54.7
4.3 - 4.9	10.6	5.5	5.2	4.0	-	-	8.8	3.4
5.0 - 5.2	-	-	*	*	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	3.98	3.97	3.96	3.91	-	-	3.91	3.71
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-
2.7	-	*	-	*	-	-	-	*
2.8	-	*	-	*	-	-	*	*
2.9	-	*	-	0.1	-	-	-	0.1
3.0	-	*	*	0.1	-	-	0.4	1.5
3.1	-	*	*	0.1	-	-	0.8	3.6
3.2	*	*	-	0.3	-	-	1.2	4.1
3.3	*	0.2	*	0.5	-	-	2.3	5.0
3.4	0.1	0.2	0.2	0.9	-	-	1.8	8.8
3.5	2.0	1.0	0.8	1.9	-	-	3.0	10.0
3.6	4.9	2.2	7.0	4.9	-	-	8.7	8.8
3.7	12.5	7.5	4.6	9.5	-	-	8.4	9.2
3.8	10.3	13.3	9.5	16.1	-	-	11.6	10.4
3.9	14.0	20.4	22.7	22.1	-	-	11.9	11.8
4.0	16.3	22.9	24.7	20.6	-	-	16.4	10.8
4.1	14.8	17.8	16.2	12.5	-	-	15.7	8.9
4.2	14.5	9.0	9.2	6.5	-	-	9.0	3.5
4.3	6.4	3.3	3.0	2.5	-	-	5.1	2.1
4.4	4.1	2.0	1.4	1.0	-	-	0.7	0.6
4.5	-	0.1	0.4	0.4	-	-	2.7	0.4
4.6	*	*	0.2	0.1	-	-	0.2	0.2
4.7	*	*	*	*	-	-	*	*
4.8	-	-	*	*	-	-	*	*
4.9	-	-	*	*	-	-	-	*
5.0	-	-	*	*	-	-	-	-
5.1	-	-	*	*	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
Average	3.98	3.97	3.96	3.91	-	-	3.91	3.71
STRENGTH 1/36 & Below	*	*	*	1.4	-	-	7.4	10.4
37	-	0.1	-	4.1	-	-	6.8	16.6
38	0.2	0.2	*	2.8	-	-	16.8	17.6
39	0.1	0.8	0.1	1.2	-	-	7.1	7.7
40	1.0	4.4	0.5	1.7	-	-	3.8	2.7
41	2.3	15.7	1.7	5.2	-	-	4.2	3.1
42	20.2	29.8	4.6	10.5	-	-	7.5	5.7
43	38.0	30.0	11.1	16.9	-	-	8.1	7.6
44	27.3	13.9	17.6	20.9	-	-	18.1	10.0
45	9.9	4.2	25.3	18.4	-	-	16.6	8.8
46	0.6	0.5	21.9	10.5	-	-	2.6	6.2
47	0.3	0.2	10.0	4.4	-	-	0.1	2.4
48 & Above	0.1	0.1	7.2	2.1	-	-	0.7	1.3
Average	43.64	42.91	45.45	43.84	-	-	41.69	40.93
UNIFORMITY								
83 & Below	-	0.2	0.4	1.7	-	-	8.4	2.7
84	0.1	2.4	5.3	11.5	-	-	18.7	22.8
85	24.0	38.6	33.1	33.8	-	-	39.2	44.0
86	65.7	53.1	48.7	46.8	-	-	30.6	27.5
87	9.1	5.5	10.7	5.7	-	-	2.8	2.9
88 & Above	1.0	0.3	1.9	0.5	-	-	0.2	0.2
Average	86.31	86.08	86.15	85.89	-	-	85.45	85.50
Samples Classed	2,013	13,718	10,655	287,800	-	-	2,246	31,127

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.