



Weekly Quality of Cotton Classed by Classing Office: Week Ending - 1/29/2026

Agricultural Marketing Service
Cotton Market News

Volume 67, No.26

January 30, 2026

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	25	56.5	42.5	12,728	31	81.2	60.9	1,004,654
Corpus Christi	2	85.7	85.7	565	42	88.1	72.5	1,524,522
Dumas	-	-	-	-	33	53.0	25.2	951,045
Florence	8	77.9	76.3	4,058	40	90.5	79.2	1,110,483
Lamesa	9	80.7	52.1	10,369	24	84.3	59.8	560,887
Lubbock	26	68.0	47.6	19,576	54	78.5	58.4	2,470,252
Macon	16	85.4	70.0	18,918	68	88.6	74.9	2,176,371
Memphis	2	98.9	92.8	3,189	65	83.4	60.0	2,308,958
Rayville	-	-	-	-	16	69.4	47.6	281,472
Visalia	13	87.8	74.3	24,905	26	85.6	69.6	305,392
United States	101	78.1	61.9	94,308	399	81.8	62.8	12,694,036
AMERICAN PIMA								
Visalia	8			13,255	18			365,147
United States	8			13,255	18			365,147
United States all cotton	108			107,563	408			13,059,183

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

MP_CN100

Source: USDA AMS Cotton and Tobacco Market News

Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov

<https://www.ams.usda.gov/market-news/cotton>

<https://mymarketnews.ams.usda.govcottonmn@ams.usda.gov>

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 29, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	17.0	38.2	-	14.3	-	0.9	-	0.5	66.3	72.2
	3	3.6	6.8	0.2	14.3	-	0.8	*	0.5	5.5	6.6
	4	0.4	0.4	-	1.4	-	*	-	*	0.2	0.3
	5	*	*	-	*	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	21.1 45.4	0.2 30.1	- 1.7	- 1.7	- 1.7	* 1.0	1.0	72.0	79.1
31	1 - 2	8.0	8.8	3.4	5.1	-	2.2	2.0	5.3	4.5	2.4
	3	11.5	11.4	22.3	22.2	-	16.1	11.2	21.7	2.0	1.6
	4	3.1	3.5	12.2	9.4	-	7.9	3.5	6.2	0.2	0.4
	5	0.3	0.6	-	1.0	-	0.5	0.1	0.3	-	0.1
	6	*	0.1	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	23.0 24.3	37.9 37.7	- 26.8	- 26.8	- 26.8	16.8 33.5	33.5	6.7	4.5
41	1 - 2	0.8	0.3	11.9	0.6	-	0.6	0.2	2.5	-	*
	3	4.0	1.3	40.5	5.3	-	19.0	12.0	29.0	-	*
	4	6.6	1.7	8.7	5.0	-	32.8	37.6	25.0	-	*
	5	6.2	1.5	0.5	1.3	-	9.1	25.6	4.3	-	*
	6	1.5	0.6	-	0.1	-	0.6	4.2	0.3	-	*
	7	0.1	0.1	-	*	-	*	0.2	*	-	*
	8	-	*	-	-	-	-	-	*	-	-
	Total	----	19.1 5.6	61.6 12.4	- 62.2	- 62.2	- 62.2	79.7 61.2	61.2	-	*
51	1 - 2	-	*	-	*	-	*	-	0.1	-	-
	3	*	*	0.2	0.2	-	1.1	0.3	0.9	-	-
	4	0.1	*	-	0.4	-	3.0	1.6	1.6	-	-
	5	0.5	0.1	-	0.1	-	1.5	0.3	0.7	-	-
	6	0.5	0.2	-	*	-	0.2	0.1	0.1	-	*
	7	0.1	0.1	-	*	-	*	-	*	-	-
	8	*	*	-	-	-	-	-	*	-	-
	Total	----	1.2 0.4	0.2 0.8	- 0.8	- 5.8	- 5.8	2.3 3.4	3.4	-	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	*	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	- *	- *	- *	- *	- *	* *	* *	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- -	- -	- -	- -	- *	* *	-	-
12 & 22	1 - 2	2.8	8.8	-	4.0	-	*	-	*	17.2	10.6
	3	2.9	2.9	-	3.8	-	*	-	*	1.4	2.4
	4	1.0	0.4	-	1.0	-	*	-	*	*	0.2
	5	*	*	-	0.1	-	-	-	-	-	*
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	6.7 12.2	- 8.9	- 8.9	- *	- *	- *	* *	18.6	13.2
32	1 - 2	2.6	1.5	-	0.6	-	*	-	*	0.8	0.3
	3	5.6	2.7	-	2.6	-	0.1	-	0.1	0.4	0.5
	4	4.5	1.4	0.2	2.4	-	0.1	-	0.1	*	0.2
	5	2.1	0.5	-	0.6	-	*	-	*	-	0.1
	6	0.2	0.1	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	15.0 6.3	0.2 6.3	- 6.3	- 0.3	- 0.3	- 0.2	0.2	1.3	1.1
42	1 - 2	*	*	-	0.1	-	*	-	*	*	*
	3	0.2	0.3	-	0.9	-	0.5	-	0.2	-	*
	4	1.2	0.7	-	1.1	-	1.2	0.5	0.3	-	*
	5	1.7	0.9	-	0.6	-	0.6	0.5	0.1	-	*
	6	0.6	0.6	-	0.1	-	0.1	-	*	-	*
	7	0.1	0.2	-	*	-	*	-	*	-	*
	8	0.1	*	-	-	-	-	-	*	-	-
	Total	----	3.9 2.8	- 2.8	- 2.8	- 2.5	- 2.5	1.0 0.6	0.6	*	*

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 29, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	*	-	*	-	*	-	*
	3	-	*	-	*	-	0.1	-	*	-	*
	4	*	*	-	0.1	-	0.2	-	*	-	-
	5	-	*	-	0.1	-	0.2	*	*	-	*
	6	0.1	*	-	*	-	0.1	-	*	-	-
	7	0.1	0.1	-	*	-	*	-	*	-	-
	8	0.4	0.1	-	-	-	-	-	*	-	-
Total	----	0.5	0.2	-	0.2	-	0.6	*	0.1	-	*
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	-	*	-	-
13 & 23	1 - 2	0.7	0.6	-	0.1	-	-	-	*	1.1	0.9
	3	0.5	0.4	-	0.1	-	-	-	*	*	0.3
	4	*	0.1	-	*	-	-	-	*	-	*
	5	-	*	-	*	-	-	-	-	-	*
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	1.2	1.1	-	0.2	-	-	-	*	1.1	1.3
33	1 - 2	1.0	0.2	-	*	-	*	-	*	0.3	0.1
	3	2.1	0.5	-	0.1	-	*	-	*	-	0.2
	4	1.0	0.3	-	0.1	-	*	-	*	-	0.2
	5	0.3	0.1	-	*	-	-	-	*	-	0.1
	6	*	*	-	*	-	-	-	*	-	*
	7	-	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	4.3	1.0	-	0.3	-	*	-	*	0.3	0.6
43	1 - 2	-	*	-	*	-	-	-	*	-	*
	3	0.4	*	-	0.1	-	*	-	*	-	*
	4	0.8	0.1	-	0.1	-	*	*	*	-	*
	5	1.4	0.2	-	0.1	-	*	0.1	*	-	*
	6	0.6	0.1	-	*	-	*	-	*	-	*
	7	0.1	*	-	*	-	-	-	*	-	*
	8	*	*	-	-	-	-	-	*	-	-
Total	----	3.4	0.5	-	0.3	-	*	0.1	*	-	*
53	1 - 2	-	-	-	*	-	*	-	-	-	-
	3	-	*	-	*	-	*	-	*	-	-
	4	-	*	-	*	-	*	-	*	-	-
	5	*	*	-	*	-	*	-	*	-	-
	6	0.2	*	-	*	-	*	-	*	-	*
	7	0.2	*	-	*	-	*	-	*	-	-
	8	*	*	-	-	-	-	-	*	-	-
Total	----	0.4	*	-	*	-	*	-	*	-	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	-	-	-	-
24 - 54	1 - 8	0.1	0.1	-	*	-	-	-	*	*	0.1
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	*	-	-	-	-	-	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	0.1	*
31		*	0.1	-	*	-	*	-	*	0.1	0.2
32		0.3	0.5	-	*	-	*	-	*	3.6	1.9
33		4.0	2.9	-	0.1	-	0.1	0.2	0.1	13.2	7.5
34		8.1	8.5	5.3	0.7	-	1.3	4.2	1.4	22.0	21.0
35		17.3	15.0	17.3	3.8	-	8.2	44.5	8.3	32.5	28.3
36		18.3	18.5	31.3	15.6	-	25.2	29.2	26.6	22.6	21.6
37		26.3	24.0	45.1	45.9	-	42.7	12.4	47.7	5.2	15.1
38		19.2	14.9	0.9	25.3	-	16.4	5.6	12.9	0.6	3.8
39		4.5	10.0	-	7.8	-	4.9	3.1	2.7	0.1	0.6
40 & Longer		1.9	5.6	-	0.7	-	1.1	0.9	0.3	-	*
Average Staple		36.39	36.64	36.19	37.17	-	36.84	35.83	36.71	34.75	35.23
Average Length		1.14	1.14	1.13	1.16	-	1.15	1.12	1.14	1.08	1.10

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 29, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	41.8	57.8	1.8	1.7	-	0.4	-	3.9	9.7	20.7
	3	8.2	15.1	2.8	1.2	-	0.4	-	2.6	1.5	5.7
	4	0.1	0.8	*	*	-	*	-	0.1	*	0.3
	5	-	*	-	*	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	50.1 73.8	4.6 2.9	0.8	-	6.6	11.2 26.8			
31	1 - 2	17.9	3.3	4.8	8.1	6.6	2.7	-	8.0	11.6	11.4
	3	12.5	5.1	20.1	21.8	15.7	12.2	-	33.0	13.7	14.1
	4	0.8	2.0	4.4	4.2	0.2	3.4	-	11.6	2.1	3.2
	5	*	0.3	0.5	0.2	-	0.2	-	0.9	0.1	0.4
	6	-	*	*	*	-	*	-	*	-	*
	7	-	*	-	*	-	*	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	31.1 10.7	29.9 34.3	22.5 18.5	-	53.5	27.4 29.2			
41	1 - 2	0.5	*	2.8	5.0	7.3	2.4	-	0.7	7.3	3.3
	3	1.4	0.1	23.1	31.5	45.4	30.8	-	12.3	27.6	14.8
	4	0.3	0.2	12.6	16.6	17.8	26.6	-	16.2	9.7	9.9
	5	0.2	0.2	2.0	2.1	1.9	5.1	-	4.5	1.6	2.8
	6	0.1	0.1	0.1	0.1	-	0.4	-	0.4	0.1	0.4
	7	*	*	-	*	-	*	-	-	*	*
	8	-	*	-	-	-	-	-	-	-	*
	Total	----	2.5 0.5	40.6 55.3	72.4 65.3	-	34.2	46.4 31.2			
51	1 - 2	-	*	2.3	0.2	0.1	0.1	-	*	0.3	0.1
	3	*	*	12.7	2.4	2.8	2.9	-	*	3.5	1.1
	4	*	*	4.8	2.3	1.7	4.7	-	0.3	5.4	2.2
	5	-	*	0.4	0.5	0.5	1.7	-	0.3	3.3	1.6
	6	-	*	*	0.1	-	0.3	-	0.1	0.9	0.6
	7	-	*	-	*	-	*	-	-	0.1	0.2
	8	-	*	-	*	-	-	-	-	-	*
	Total	----	* *	20.4 5.4	5.0 9.7	-	0.7	13.4 5.7			
61	1 - 2	-	*	0.1	*	-	*	-	-	-	*
	3	-	*	1.1	*	-	*	-	*	*	*
	4	-	*	0.7	*	-	*	-	*	*	*
	5	-	-	0.1	*	-	*	-	-	*	*
	6	-	-	*	*	-	*	-	-	*	*
	7	-	-	-	*	-	*	-	-	*	*
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	- *	2.0 0.1	- *	- *	- *	0.1 *			
71	1 - 2	-	*	-	-	-	*	-	-	-	-
	3	-	*	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- *	- -	- *	- -	- -	- -			
12 & 22	1 - 2	7.3	6.0	-	*	-	*	-	0.1	*	2.1
	3	1.0	3.8	-	*	-	*	-	0.1	*	1.1
	4	0.1	0.5	-	*	-	*	-	0.1	-	0.1
	5	-	*	-	-	-	*	-	*	-	*
	6	-	*	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	8.4 10.3	- 0.1	- *	-	0.3	0.1 3.3			
32	1 - 2	0.6	0.3	*	0.1	-	*	-	0.1	*	0.2
	3	0.8	1.0	0.2	0.3	-	0.2	-	0.5	0.2	0.5
	4	0.4	0.6	0.1	0.1	-	0.1	-	0.8	*	0.4
	5	*	0.2	*	*	-	*	-	0.4	*	0.2
	6	*	*	-	*	-	*	-	0.1	-	*
	7	*	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	1.8 2.1	0.3 0.4	- 0.3	-	1.8	0.2 1.3			
42	1 - 2	*	*	*	*	-	0.2	-	*	*	*
	3	0.1	*	0.4	0.5	-	1.8	-	0.4	0.2	0.5
	4	0.5	0.1	0.3	0.4	-	1.5	-	1.2	0.3	0.5
	5	0.2	0.1	0.1	0.1	-	0.4	-	0.7	0.1	0.3
	6	*	*	*	*	-	0.1	-	0.4	*	0.1
	7	-	*	-	*	-	*	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	0.8 0.2	0.7 1.1	- 3.9	-	2.6	0.5 1.4			

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 29, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	0.1	*	-	*	-	-	-	*
	3	-	-	0.4	0.1	-	0.4	-	*	0.1	0.1
	4	-	*	0.2	0.1	-	0.6	-	0.1	0.3	0.2
	5	-	*	0.1	*	-	0.3	-	0.1	0.1	0.2
	6	-	*	*	*	-	0.1	-	*	*	0.1
	7	-	*	-	*	-	*	-	*	*	*
	8	-	*	-	*	-	-	-	-	-	*
Total	----	-	*	0.8	0.2	-	1.4	-	0.1	0.6	0.7
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	*	*	-	*	-	-	-	*
	4	-	-	*	*	-	*	-	-	*	*
	5	-	-	-	*	-	*	-	-	-	*
	6	-	-	-	*	-	*	-	-	*	*
	7	-	-	-	*	-	*	-	-	-	*
	8	-	-	-	*	-	-	-	-	-	*
Total	----	-	-	*	*	-	*	-	-	*	*
13 & 23	1 - 2	2.5	0.7	-	*	-	-	-	-	-	0.1
	3	0.6	0.6	-	*	-	-	-	-	-	0.1
	4	0.2	0.1	-	*	-	-	-	-	-	*
	5	*	*	-	*	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	3.3	1.4	-	*	-	-	-	-	-	0.2
33	1 - 2	0.2	0.1	-	*	-	*	-	*	-	*
	3	0.2	0.3	*	*	-	*	-	*	*	*
	4	0.5	0.2	*	*	-	*	-	*	-	*
	5	0.3	0.1	-	*	-	*	-	*	-	*
	6	*	*	-	*	-	*	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	1.2	0.8	0.1	*	-	*	-	0.1	*	0.1
43	1 - 2	*	*	-	*	-	*	-	*	-	*
	3	-	*	*	*	-	*	-	*	*	*
	4	*	*	*	*	-	*	-	*	*	*
	5	-	*	*	*	-	*	-	*	*	*
	6	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	*	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	*	0.1	0.1	0.1	-	0.1	-	0.1	0.1	0.1
53	1 - 2	-	-	*	*	-	*	-	-	-	*
	3	-	-	0.3	*	-	*	-	-	-	*
	4	-	-	0.2	*	-	*	-	-	-	*
	5	-	-	-	*	-	*	-	-	-	*
	6	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	*	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	*	0.4	*	-	*	-	*	-	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	*	*	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	*	*	-	-	-	-	-	-
24 - 54	1 - 8	0.8	0.1	*	*	-	*	-	0.1	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	*	-	*	-	-	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-
30		*	*	-	*	-	-	-	-	-	-
31		-	0.1	-	*	-	*	-	-	-	*
32		0.3	0.5	*	0.1	-	*	-	*	-	*
33		4.2	2.6	0.7	0.8	-	0.1	-	0.2	*	0.2
34		13.7	8.7	4.8	4.6	-	0.8	-	1.6	0.4	0.8
35		25.3	18.2	16.2	15.4	3.7	4.2	-	11.3	4.0	3.7
36		27.0	25.7	27.6	30.2	12.7	15.2	-	28.9	16.8	14.1
37		24.1	29.3	34.1	35.8	57.2	47.7	-	39.8	46.5	41.8
38		4.6	10.6	11.1	10.2	24.9	26.8	-	14.1	20.4	24.0
39		0.6	3.2	3.4	2.5	1.5	4.7	-	3.8	6.0	8.6
40 & Longer		0.1	1.0	2.1	0.4	-	0.5	-	0.4	6.0	6.8
Average Staple		35.69	36.19	36.47	36.38	37.08	37.12	-	36.65	37.43	37.57
Average Length		1.11	1.13	1.14	1.13	1.16	1.16	-	1.14	1.17	1.18

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 29, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	30.5	8.3	12.0	0.6	-	*	17.4	2.1	2.5	1.4
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	-	0.3	-	0.1	-	*	0.3	0.3
Grass - Level 2	-	-	-	*	-	-	-	-	-	-
Prep - Level 1	*	*	-	*	-	*	-	*	-	-
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	-	1.5	0.7	0.8	0.1	0.1
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	*
Other - Level 2	-	*	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	0.2	0.1	-	*	-	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	-	*	-	*	-	-	-	-	0.1	*
23	-	*	-	*	-	-	-	-	0.1	0.1
24	-	*	-	*	-	*	-	*	0.7	0.2
25	0.1	0.1	-	*	-	*	*	*	2.8	0.9
26	0.5	0.7	-	0.2	-	0.1	0.4	0.5	6.8	2.7
27	1.8	2.7	-	1.2	-	0.5	3.2	3.0	14.3	7.4
28	5.4	7.9	5.5	5.2	-	3.9	15.7	12.6	20.5	13.8
29	11.3	14.7	14.3	14.8	-	15.4	31.6	30.5	22.4	19.7
30	13.9	17.6	32.4	21.7	-	28.5	26.8	30.3	17.1	21.9
31	20.0	16.9	9.6	17.7	-	26.8	12.1	15.3	10.2	17.8
32	20.0	14.3	30.6	12.5	-	15.8	7.6	5.8	3.4	9.5
33	15.1	11.4	7.3	11.6	-	6.3	2.3	1.6	1.1	3.7
34	6.3	7.4	0.4	9.7	-	2.1	0.3	0.3	0.3	1.4
35	3.0	3.8	-	4.0	-	0.5	*	0.1	0.1	0.5
36	2.2	1.4	-	1.1	-	0.1	-	*	*	0.2
37	0.4	0.7	-	0.2	-	*	-	*	-	*
38	*	0.2	-	*	-	*	-	-	-	*
39	*	*	-	*	-	*	-	-	-	-
40 & Above	-	*	-	-	-	*	-	-	-	-
Average	31.77	31.46	31.14	31.59	-	31.09	30.07	30.12	29.15	30.15
Mike										
2.4 & Below	*	*	-	-	-	-	-	-	0.3	*
2.5	0.2	0.2	-	*	-	-	-	*	0.1	0.1
2.6	0.5	0.2	-	*	-	-	-	-	*	0.2
2.7	0.9	0.3	-	*	-	-	-	*	0.3	0.3
2.8	1.1	0.4	-	*	-	-	-	*	0.8	0.4
2.9	1.4	0.5	-	*	-	-	-	*	0.7	0.6
3.0	2.0	0.6	-	0.1	-	-	-	*	0.7	0.8
3.1	1.4	0.8	1.6	0.1	-	-	-	*	0.7	0.9
3.2	1.7	1.0	-	0.3	-	*	-	0.1	1.8	1.3
3.3	3.1	1.4	3.7	0.5	-	*	0.2	0.2	2.1	1.6
3.4	3.9	1.8	-	0.9	-	*	0.8	0.3	3.2	2.0
3.5	3.4	2.4	-	1.3	-	*	0.8	0.5	3.2	2.5
3.6	5.4	3.5	-	1.9	-	0.1	3.0	0.9	5.1	3.1
3.7	5.9	4.4	3.9	2.7	-	0.1	7.2	1.8	6.6	3.8
3.8	5.8	5.5	0.2	4.4	-	0.1	6.6	2.7	7.1	4.6
3.9	6.7	7.0	4.4	6.7	-	0.2	13.4	4.2	7.8	5.5
4.0	7.8	8.5	7.8	9.0	-	0.4	13.8	5.8	7.6	6.3
4.1	7.9	10.0	16.1	11.1	-	0.6	19.5	7.8	6.6	7.0
4.2	6.8	10.7	10.6	12.7	-	1.0	17.4	9.9	6.0	8.0
4.3	6.5	10.7	16.1	12.9	-	1.7	6.7	11.6	6.3	8.7
4.4	8.2	9.5	15.2	11.3	-	2.8	4.9	11.8	8.0	9.2
4.5	7.1	7.7	14.2	8.8	-	4.1	3.0	10.7	9.0	9.0
4.6	4.8	5.6	5.7	6.0	-	6.5	1.9	9.4	6.6	8.2
4.7	4.4	3.6	0.5	3.7	-	9.5	0.7	7.7	5.6	6.5
4.8	2.2	2.0	-	2.3	-	13.4	*	5.5	1.9	4.5
4.9	0.7	1.0	-	1.3	-	16.0	-	3.9	0.2	2.6
5.0	0.1	0.4	-	0.8	-	16.3	-	2.5	0.1	1.4
5.1	*	0.2	-	0.4	-	12.9	-	1.4	0.3	0.6
5.2	-	0.1	-	0.3	-	8.2	-	0.7	0.4	0.3
5.3	-	*	-	0.2	-	4.0	-	0.3	0.5	0.1
5.4	-	-	-	0.1	-	1.5	-	0.1	0.3	*
5.5 & Above	-	*	-	0.2	-	0.5	-	*	*	*
Average	3.98	4.11	4.20	4.23	-	4.88	4.05	4.38	4.06	4.19

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE

For The Week Ending Jan 29, 2026

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	17.6	7.6	2.3	1.3	-	*	-	1.8	0.5	0.3
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	*	0.1	-	*	-	0.1	0.3	0.4
Grass - Level 2	-	*	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	-	-	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	1.2	0.4	0.1	0.3	-	0.1	-	2.9	-	*
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	*
Spindle Twist - Level 2	-	*	-	-	-	-	-	-	-	-
Other - Level 1	*	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	-	*	-	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	*	*	-	-	-	*	-	-	-	*
23	0.1	*	*	*	-	*	-	-	*	*
24	0.2	0.1	0.1	*	-	*	-	-	*	*
25	0.5	0.2	0.3	0.1	-	*	-	*	0.1	0.1
26	1.9	0.7	2.4	0.6	*	*	-	0.1	2.0	0.5
27	4.9	2.6	7.2	3.2	0.6	0.2	-	1.8	4.4	1.9
28	11.4	7.1	19.0	10.6	5.9	1.8	-	6.6	10.3	7.8
29	18.3	14.6	22.8	20.5	32.1	12.5	-	18.0	21.8	15.9
30	19.0	20.2	23.1	25.1	39.7	36.1	-	30.0	24.2	20.7
31	16.2	19.9	14.6	20.0	18.6	32.5	-	20.0	19.1	18.7
32	12.7	15.1	7.0	11.5	3.1	12.2	-	12.6	9.9	12.1
33	8.8	9.8	2.5	5.3	*	3.7	-	6.1	5.3	7.9
34	3.6	5.6	0.7	2.1	*	0.9	-	3.1	2.3	6.4
35	1.5	2.5	0.2	0.7	-	0.1	-	1.6	0.4	4.6
36	0.6	1.1	*	0.2	-	*	-	0.2	0.1	2.5
37	0.3	0.4	*	*	-	*	-	*	*	0.8
38	0.1	0.2	-	*	-	*	-	*	*	0.1
39	*	*	-	*	-	-	-	-	*	*
40 & Above	-	-	-	*	-	-	-	-	*	*
Average	30.74	31.29	29.93	30.63	30.23	31.00	-	30.93	30.48	31.43
Mike										
2.4 & Below	0.2	*	-	-	-	-	-	-	-	-
2.5	0.1	0.1	-	*	-	-	-	*	-	*
2.6	0.3	0.1	-	*	-	-	-	*	*	*
2.7	0.7	0.2	-	*	-	*	-	*	*	*
2.8	0.9	0.4	-	*	-	*	-	*	0.1	0.1
2.9	0.9	0.6	-	*	-	*	-	*	*	0.2
3.0	0.8	0.9	0.1	*	-	*	-	*	0.5	0.2
3.1	0.9	1.3	0.1	*	-	*	-	*	0.7	0.5
3.2	1.3	1.8	0.2	0.1	-	*	-	0.1	1.4	0.7
3.3	2.4	2.3	0.7	0.2	-	*	-	0.1	1.2	0.6
3.4	3.2	3.0	1.8	0.3	-	0.1	-	0.1	1.1	0.7
3.5	4.0	3.8	3.2	0.6	-	0.1	-	0.2	1.8	1.3
3.6	4.0	4.4	4.8	1.1	-	0.2	-	0.4	2.5	1.6
3.7	4.1	5.0	6.6	1.9	-	0.4	-	0.5	4.2	2.6
3.8	3.9	5.5	6.1	2.8	0.5	0.6	-	0.7	3.8	3.4
3.9	4.9	6.0	6.6	4.0	0.4	1.0	-	1.1	6.7	4.6
4.0	6.1	6.5	7.9	5.5	6.6	1.7	-	1.9	8.9	5.9
4.1	6.7	6.8	11.2	7.4	8.8	2.6	-	3.5	9.0	7.7
4.2	7.9	7.3	11.4	9.0	8.5	4.0	-	4.5	8.2	8.9
4.3	8.6	7.6	8.5	10.1	13.8	5.7	-	5.6	9.8	9.2
4.4	7.2	7.7	8.1	10.3	15.6	8.2	-	6.6	9.8	9.1
4.5	7.0	7.4	5.4	9.9	13.8	11.0	-	8.6	7.8	9.5
4.6	6.3	6.6	3.9	9.2	16.7	14.0	-	9.7	7.9	9.1
4.7	5.5	5.4	2.8	8.2	8.6	15.2	-	10.6	4.9	7.4
4.8	3.9	3.8	2.8	6.5	4.3	13.8	-	11.4	3.1	5.6
4.9	3.8	2.4	2.5	4.9	1.2	10.1	-	10.6	2.3	4.3
5.0	2.1	1.4	2.1	3.4	1.1	6.3	-	8.4	1.3	2.7
5.1	1.6	0.7	1.5	2.2	-	3.1	-	7.0	0.3	1.5
5.2	0.4	0.4	0.9	1.2	-	1.2	-	4.0	0.9	1.0
5.3	0.1	0.2	0.6	0.6	-	0.4	-	2.2	1.3	0.7
5.4	0.1	0.1	0.3	0.3	-	0.1	-	1.1	0.6	0.4
5.5 & Above	*	0.1	-	0.1	-	*	-	1.1	*	0.3
Average	4.14	4.12	4.17	4.41	4.41	4.62	-	4.68	4.23	4.35

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 29, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	*	*	-	-	-	-	-	-	0.3	*
2.5 - 2.6	0.7	0.4	-	*	-	-	-	*	0.1	0.3
2.7 - 2.9	3.4	1.2	-	0.1	-	-	-	*	1.8	1.2
3.0 - 3.2	5.1	2.4	1.6	0.5	-	*	-	0.2	3.2	3.0
3.3 - 3.4	7.0	3.2	3.7	1.4	-	*	1.0	0.5	5.3	3.6
3.5 - 3.6	8.8	5.9	-	3.1	-	0.1	3.8	1.5	8.4	5.6
3.7 - 4.2	40.9	46.1	43.0	46.6	-	2.5	78.0	32.1	41.8	35.2
4.3 - 4.9	33.9	40.1	51.7	46.4	-	54.0	17.2	60.6	37.5	48.6
5.0 - 5.2	0.1	0.7	-	1.4	-	37.4	-	4.6	0.8	2.2
5.3 & Above	-	*	-	0.5	-	6.1	-	0.4	0.8	0.2
Average	3.98	4.11	4.20	4.23	-	4.88	4.05	4.38	4.06	4.19
Leaf										
1 - 2	32.8	58.4	15.2	24.8	-	3.8	2.2	8.4	90.1	86.6
3	30.9	26.5	63.2	49.7	-	37.7	23.6	52.5	9.4	11.7
4	18.8	8.7	21.1	21.1	-	45.4	43.2	33.2	0.5	1.4
5	12.6	3.9	0.5	4.0	-	12.0	26.5	5.4	-	0.3
6	3.8	1.7	-	0.5	-	1.1	4.3	0.4	-	0.1
7	0.6	0.6	-	0.1	-	*	0.2	*	-	*
8	0.5	0.2	-	*	-	-	-	*	-	-
Average	3.18	2.49	3.07	3.03	-	3.69	4.08	3.37	1.75	1.74
HVI Trash 1/										
00	*	*	-	*	-	-	-	-	0.3	0.7
01	15.0	29.3	-	5.1	-	0.3	*	0.6	58.4	60.1
02	19.9	32.5	18.8	22.5	-	4.6	2.9	10.2	34.6	29.3
03	17.4	15.6	32.9	27.9	-	14.9	9.2	24.6	5.6	6.8
04	12.4	8.1	27.3	20.4	-	22.9	17.6	26.2	1.0	1.9
05	8.4	4.5	14.0	12.1	-	22.0	21.7	18.8	0.1	0.7
06	7.2	2.7	5.5	6.5	-	15.8	17.1	10.7	-	0.3
07	5.7	1.9	1.2	3.1	-	9.7	13.9	5.2	*	0.1
08	4.2	1.4	0.4	1.4	-	5.2	8.7	2.3	-	0.1
09	3.4	1.1	-	0.6	-	2.6	4.9	0.9	-	*
10	2.3	0.8	-	0.3	-	1.2	2.4	0.4	-	*
11	1.6	0.6	-	0.1	-	0.5	0.7	0.2	-	*
12	0.9	0.4	-	0.1	-	0.2	0.4	0.1	-	*
13	0.6	0.3	-	*	-	0.1	0.2	*	-	*
14	0.4	0.2	-	*	-	*	0.1	*	-	*
15	0.2	0.1	-	*	-	*	*	*	-	-
16	0.1	0.1	-	*	-	-	-	*	-	*
17	0.1	0.1	-	*	-	-	-	*	-	*
18 & Above	0.2	0.1	-	*	-	-	-	*	-	-
Average	0.42	0.28	0.36	0.36	-	0.50	0.57	0.43	0.15	0.15
UNIFORMITY 2/										
74 & Below	*	*	-	*	-	-	-	*	-	*
75	0.1	0.1	-	*	-	-	-	*	0.2	0.1
76	0.4	0.2	-	*	-	*	-	*	0.8	0.5
77	1.3	0.8	-	0.1	-	*	0.1	*	1.8	2.4
78	4.7	3.1	0.2	0.7	-	0.2	1.0	0.5	10.8	10.1
79	15.0	12.6	6.9	3.7	-	1.0	5.7	2.9	29.3	25.0
80	29.1	27.8	25.7	13.4	-	7.0	22.8	12.0	37.1	35.8
81	31.7	29.3	30.4	30.1	-	28.1	54.6	28.8	17.0	21.3
82	12.1	17.2	28.7	31.1	-	37.9	14.1	35.0	2.5	4.3
83	5.2	7.1	8.0	16.1	-	20.5	1.6	18.2	0.4	0.5
84	0.5	1.7	0.2	4.3	-	5.1	0.2	2.3	*	*
85 & Above	-	0.1	-	0.4	-	0.2	-	0.2	-	*
Average	80.89	81.15	81.48	82.00	-	82.30	81.27	82.04	80.08	80.22
Tenderable 3/	56.5	81.2	85.7	88.1	-	53.0	77.9	90.5	80.7	84.3
SAMPLES CLASSED										
Week	12,728		565		-		4,058		10,369	
Season	1,004,654		1,524,522		951,045		1,110,483		560,887	

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Jan 29, 2026

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	0.2	*	-	-	-	-	-	-	-	-
2.5 - 2.6	0.5	0.2	-	*	-	-	-	*	*	*
2.7 - 2.9	2.5	1.2	-	*	-	*	-	0.1	0.1	0.4
3.0 - 3.2	3.1	4.0	0.3	0.1	-	*	-	0.1	2.5	1.4
3.3 - 3.4	5.6	5.4	2.5	0.5	-	0.1	-	0.2	2.3	1.4
3.5 - 3.6	8.0	8.2	8.0	1.8	-	0.3	-	0.6	4.3	2.9
3.7 - 4.2	33.7	37.2	49.8	30.7	24.8	10.4	-	12.1	40.9	33.1
4.3 - 4.9	42.2	41.0	34.0	59.1	74.1	78.0	-	63.1	45.5	54.3
5.0 - 5.2	4.1	2.5	4.5	6.8	1.1	10.6	-	19.4	2.5	5.2
5.3 & Above	0.2	0.3	0.9	1.0	-	0.6	-	4.4	1.9	1.4
Average	4.14	4.12	4.17	4.41	4.41	4.62	-	4.68	4.23	4.35
Leaf										
1 - 2	71.3	68.4	12.0	15.3	14.0	5.8	-	12.8	29.0	37.9
3	24.9	26.0	61.1	57.8	63.9	48.7	-	48.9	46.7	38.0
4	2.9	4.4	23.4	23.7	19.7	37.0	-	30.4	17.9	16.9
5	0.7	0.9	3.3	3.0	2.4	7.6	-	6.9	5.2	5.5
6	0.2	0.2	0.2	0.2	-	0.8	-	1.0	1.1	1.3
7	*	0.1	-	*	-	0.1	-	*	0.1	0.2
8	-	*	-	*	-	-	-	-	-	*
Average	2.12	2.22	3.18	3.15	3.11	3.49	-	3.34	2.97	2.88
HVI Trash 1/										
00	0.1	*	-	-	-	*	-	-	*	*
01	34.6	33.1	0.8	1.6	0.5	0.5	-	1.6	10.1	14.4
02	40.5	41.6	16.6	19.8	13.9	7.3	-	14.1	23.5	29.1
03	16.4	15.5	34.2	31.4	35.7	21.2	-	24.1	26.3	21.6
04	4.8	5.5	26.4	23.6	30.0	26.2	-	23.2	19.0	14.2
05	1.9	2.2	12.6	12.9	12.0	20.2	-	16.3	10.6	8.7
06	0.8	1.0	5.7	6.1	4.5	12.2	-	9.7	5.0	5.2
07	0.4	0.5	2.1	2.7	2.3	6.5	-	5.3	2.6	3.1
08	0.1	0.3	0.9	1.1	0.8	3.2	-	2.7	1.5	1.8
09	0.1	0.1	0.4	0.5	0.2	1.5	-	1.5	0.8	1.0
10	*	0.1	0.1	0.2	0.1	0.7	-	0.8	0.4	0.5
11	*	0.1	0.1	0.1	-	0.3	-	0.4	0.1	0.3
12	*	*	*	*	-	0.1	-	0.2	0.1	0.1
13	-	*	*	*	-	0.1	-	0.1	*	0.1
14	-	*	*	*	-	*	-	*	-	*
15	-	*	-	*	-	*	-	-	-	*
16	-	*	-	*	-	-	-	-	-	*
17	-	*	*	*	-	-	-	*	-	*
18 & Above	-	*	-	*	-	-	-	-	*	*
Average	0.20	0.21	0.37	0.37	0.37	0.46	-	0.42	0.34	0.33
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	-	-	-	-
75	0.1	*	-	*	-	-	-	-	*	*
76	0.4	0.2	-	*	*	*	-	-	*	*
77	1.2	1.1	*	0.1	-	*	-	-	0.1	*
78	5.0	4.4	0.4	0.8	*	0.1	-	0.2	1.0	0.6
79	16.9	14.2	5.0	5.0	1.6	0.5	-	1.8	2.2	3.1
80	32.0	29.9	23.0	20.1	12.7	3.9	-	10.5	20.4	16.3
81	29.7	31.7	33.8	36.4	23.2	20.9	-	32.0	46.1	33.2
82	11.8	14.7	25.4	27.8	46.8	45.7	-	37.5	21.8	33.2
83	2.5	3.1	10.7	8.4	15.2	26.1	-	15.8	7.3	11.3
84	0.3	0.4	1.5	1.2	0.4	2.6	-	2.1	0.8	2.1
85 & Above	*	0.1	0.1	0.1	-	0.2	-	0.1	0.3	0.2
Average	80.74	80.90	81.63	81.61	82.08	82.47	-	82.06	81.57	81.83
Tenderable 3/	68.0	78.5	85.4	88.6	98.9	83.4	-	69.4	87.8	85.6
SAMPLES CLASSED										
Week	19,576		18,918		3,189		-		24,905	
Season		2,470,252		2,176,371		2,308,958		281,472		305,392

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE

For The Week Ending Jan 29, 2026

Color Grade	Leaf	VISALIA			Quality Designation	VISALIA	
		Week	Season			Week	Season
01	1	6.4	6.3		MIKE	-	-
	2	5.8	7.6		2.4 & Below	-	-
	3	0.1	0.2		2.5 - 2.6	-	-
	4	-	-		2.7 - 2.9	0.1	0.2
	5	-	-		3.0 - 3.2	1.1	1.6
	6	-	-		3.3 - 3.4	0.8	2.8
	7	-	-		3.5 - 3.6	4.9	8.5
Total -----		12.4	14.1		3.7 - 4.2	90.0	83.0
02	1	14.2	7.2		4.3 - 4.9	3.1	3.9
	2	36.1	34.9		5.0 - 5.2	-	*
	3	6.7	8.2		5.3 & Above	-	-
	4	0.1	0.2		Average	3.95	3.89
	5	-	*		ALL RANGE MIKE		
	6	-	-		2.4 & Below	-	-
	7	-	-		2.5	-	-
Total -----		57.1	50.6		2.6	-	-
03	1	1.8	0.6		2.7	-	*
	2	13.6	13.1		2.8	0.1	*
	3	10.4	15.7		2.9	*	0.1
	4	2.3	1.7		3.0	0.1	0.3
	5	0.1	*		3.1	0.4	0.5
	6	-	*		3.2	0.6	0.8
	7	-	-		3.3	0.2	1.0
Total -----		28.2	31.2		3.4	0.6	1.8
04	1	0.1	*		3.5	1.6	3.0
	2	0.5	0.6		3.6	3.3	5.5
	3	0.7	2.0		3.7	6.3	9.6
	4	0.6	0.8		3.8	10.3	15.1
	5	*	0.1		3.9	19.2	20.5
	6	-	*		4.0	25.5	19.4
	7	-	-		4.1	20.0	12.3
Total -----		1.9	3.5		4.2	8.7	6.2
05	1	-	*		4.3	2.3	2.5
	2	0.1	0.1		4.4	0.4	0.9
	3	0.2	0.2		4.5	0.2	0.4
	4	0.2	0.2		4.6	*	0.1
	5	-	*		4.7	*	*
	6	-	*		4.8	0.1	*
	7	-	-		4.9	*	*
Total -----		0.4	0.5		5.0	-	*
06	1	-	-		5.1	-	*
	2	-	*		5.2	-	-
	3	*	0.1		5.3 & Above	-	-
	4	-	*		Average	3.95	3.89
	5	-	*		STRENGTH 1/		
	6	-	*		36 & Below	0.5	2.7
	7	-	-		37	1.3	4.9
Total -----		*	0.1		38	1.7	3.8
07	1	-	-		39	2.0	1.8
	2	-	-		40	2.0	2.0
	3	-	*		41	4.0	5.6
	4	-	*		42	7.0	11.0
	5	-	*		43	13.5	16.6
	6	-	*		44	17.0	19.5
	7	-	-		45	18.2	16.5
Total -----		-	*		46	19.1	9.7
STAPLE					47	8.9	4.1
44 & Shorter		1.0	2.8		48 & Above	4.8	2.0
46		4.6	11.3		Average	44.68	43.49
48		37.0	46.1		UNIFORMITY		
50		49.3	37.7		83 & Below	0.6	1.6
52 & Longer		8.1	2.0		84	5.1	11.9
Average Staple		49.18	48.49		85	29.2	34.8
Average Length		1.43	1.41		86	50.4	45.4
EXTRANEIOUS MATTER					87	13.3	5.8
Bark		0.1	*		88 & Above	1.4	0.5
Grass		0.1	0.3		Average	86.20	85.88
Spindle Twist		0.2	0.1		Samples Classed		
Preparation		-	*		Week	13,255	
All Other		0.1	*		Season		365,147

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.