



Weekly Quality of Cotton Classed by Classing Office: Week Ending - 2/5/2026

Agricultural Marketing Service
Cotton Market News

Volume 67, No.27

February 06, 2026

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	22	64.8	51.2	43,247	31	80.5	60.5	1,047,715
Corpus Christi	-	-	-	-	42	88.1	72.5	1,524,522
Dumas	-	-	-	-	33	53.0	25.2	951,045
Florence*	-	-	-	-	40	90.5	79.2	1,110,530
Lamesa	7	77.2	61.5	8,513	24	84.2	59.9	569,399
Lubbock	20	72.1	57.2	18,154	54	78.4	58.4	2,488,237
Macon	13	85.9	71.9	14,075	68	88.6	74.8	2,190,446
Memphis	3	91.9	62.8	10,119	65	83.4	60.0	2,319,077
Rayville*	-	-	-	-	16	69.4	47.6	281,672
Visalia	14	88.3	76.8	21,870	26	85.7	70.1	327,262
United States	81	76.2	61.2	116,225	399	81.8	62.8	12,809,905
AMERICAN PIMA								
Visalia	8			5,602	18			370,749
United States	8			5,602	18			370,749
United States all cotton	87			121,827	408			13,180,654

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

MP_CN100

Source: USDA AMS Cotton and Tobacco Market News

Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov

<https://www.ams.usda.gov/market-news/cotton>

<https://mymarketnews.ams.usda.govcottonmn@ams.usda.gov>

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 05, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 11 & 21	1 - 2	Pct. 21.7	Pct. 37.5	Pct. -	Pct. 14.3	Pct. -	Pct. 0.9	Pct. -	Pct. 0.5	Pct. 52.4	Pct. 71.9
	3	3.8	6.7	-	14.3	-	0.8	-	0.5	7.5	6.6
	4	0.2	0.4	-	1.4	-	*	-	*	0.2	0.3
	5	*	*	-	*	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	25.6 44.5	-	30.1	-	1.7	-	1.0	60.1	78.8
31	1 - 2	15.4	9.1	-	5.1	-	2.2	-	5.3	24.9	2.8
	3	13.0	11.5	-	22.2	-	16.1	-	21.7	7.0	1.7
	4	3.5	3.5	-	9.4	-	7.9	-	6.2	0.4	0.4
	5	0.4	0.6	-	1.0	-	0.5	-	0.3	-	0.1
	6	*	0.1	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	32.4 24.6	-	37.7	-	26.8	-	33.5	32.3	4.9
41	1 - 2	1.0	0.3	-	0.6	-	0.6	-	2.5	*	*
	3	2.9	1.4	-	5.3	-	19.0	-	29.0	0.4	*
	4	5.3	1.9	-	5.0	-	32.8	-	25.0	0.3	*
	5	5.1	1.6	-	1.3	-	9.1	-	4.3	0.1	*
	6	2.2	0.7	-	0.1	-	0.6	-	0.3	-	*
	7	0.4	0.1	-	*	-	*	-	*	-	*
	8	*	*	-	-	-	-	-	*	-	-
	Total	----	17.1 6.1	-	12.4	-	62.2	-	61.2	0.9	0.1
51	1 - 2	*	*	-	*	-	*	-	0.1	-	-
	3	*	*	-	0.2	-	1.1	-	0.9	-	-
	4	*	*	-	0.4	-	3.0	-	1.6	-	-
	5	0.1	0.1	-	0.1	-	1.5	-	0.7	-	-
	6	0.1	0.2	-	*	-	0.2	-	0.1	-	*
	7	0.1	0.1	-	*	-	*	-	*	-	-
	8	0.1	*	-	-	-	-	-	*	-	-
	Total	----	0.3 0.4	-	0.8	-	5.8	-	3.4	-	*
61	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	- *	- *	*	- *	*	- *	*	-	-
71	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- -	-	- -	-	- *	*	-	-
12 & 22	1 - 2	2.8	8.6	-	4.0	-	*	-	*	2.1	10.5
	3	1.0	2.8	-	3.8	-	*	-	*	0.9	2.3
	4	0.3	0.4	-	1.0	-	*	-	*	0.2	0.2
	5	*	*	-	0.1	-	-	-	-	*	*
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	4.1 11.9	-	8.9	-	*	-	*	3.1	13.0
32	1 - 2	3.4	1.6	-	0.6	-	*	-	*	1.0	0.3
	3	3.5	2.7	-	2.6	-	0.1	-	0.1	0.7	0.5
	4	1.8	1.5	-	2.4	-	0.1	-	0.1	0.2	0.2
	5	0.4	0.5	-	0.6	-	*	-	*	*	0.1
	6	*	0.1	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	9.1 6.4	-	6.3	-	0.3	-	0.2	1.8	1.1
42	1 - 2	0.1	*	-	0.1	-	*	-	*	*	*
	3	0.7	0.4	-	0.9	-	0.5	-	0.2	-	*
	4	2.3	0.8	-	1.1	-	1.2	-	0.3	-	*
	5	2.3	0.9	-	0.6	-	0.6	-	0.1	-	*
	6	0.6	0.6	-	0.1	-	0.1	-	*	-	*
	7	0.1	0.2	-	*	-	*	-	*	-	*
	8	*	*	-	-	-	-	-	*	-	-
	Total	----	6.2 3.0	-	2.8	-	2.5	-	0.6	*	*

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 05, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	*	-	*	-	*	-	*
	3	*	*	-	*	-	0.1	-	*	-	*
	4	*	*	-	0.1	-	0.2	-	*	-	-
	5	*	*	-	0.1	-	0.2	-	*	-	*
	6	*	*	-	*	-	0.1	-	*	-	-
	7	*	0.1	-	*	-	*	-	*	-	-
	8	*	0.1	-	-	-	-	-	*	-	-
Total	----	0.1	0.2	-	0.2	-	0.6	-	0.1	-	*
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	-	*	-	-
13 & 23	1 - 2	1.3	0.6	-	0.1	-	-	-	*	1.3	0.9
	3	0.5	0.5	-	0.1	-	-	-	*	0.3	0.3
	4	0.1	0.1	-	*	-	-	-	*	*	*
	5	-	*	-	*	-	-	-	-	-	*
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	2.0	1.2	-	0.2	-	-	-	*	1.6	1.3
33	1 - 2	0.3	0.2	-	*	-	*	-	*	0.1	0.1
	3	0.6	0.5	-	0.1	-	*	-	*	0.1	0.2
	4	0.3	0.3	-	0.1	-	*	-	*	-	0.2
	5	0.1	0.1	-	*	-	-	-	*	-	0.1
	6	*	*	-	*	-	-	-	*	-	*
	7	*	*	-	*	-	-	-	-	-	*
	8	*	*	-	-	-	-	-	-	-	-
Total	----	1.3	1.0	-	0.3	-	*	-	*	0.1	0.6
43	1 - 2	*	*	-	*	-	-	-	*	*	*
	3	0.2	*	-	0.1	-	*	-	*	-	*
	4	0.5	0.1	-	0.1	-	*	-	*	-	*
	5	0.6	0.2	-	0.1	-	*	-	*	-	*
	6	0.2	0.1	-	*	-	*	-	*	-	*
	7	0.1	*	-	*	-	-	-	*	-	*
	8	0.1	*	-	-	-	-	-	*	-	-
Total	----	1.6	0.5	-	0.3	-	*	-	*	*	*
53	1 - 2	-	-	-	*	-	*	-	-	-	-
	3	-	*	-	*	-	*	-	*	-	-
	4	*	*	-	*	-	*	-	*	-	-
	5	*	*	-	*	-	*	-	*	-	-
	6	*	*	-	*	-	*	-	*	-	*
	7	*	*	-	*	-	*	-	*	-	-
	8	*	*	-	-	-	-	-	*	-	-
Total	----	*	*	-	*	-	*	-	*	-	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	-	-	-	-
24 - 54	1 - 8	0.3	0.1	-	*	-	-	-	*	-	0.1
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	*	-	-	-	-	-	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	-	*
31		*	0.1	-	*	-	*	-	*	0.5	0.2
32		0.5	0.5	-	*	-	*	-	*	1.2	1.8
33		4.2	3.0	-	0.1	-	0.1	-	0.1	7.9	7.5
34		12.0	8.7	-	0.7	-	1.3	-	1.4	26.4	21.1
35		15.5	15.0	-	3.8	-	8.2	-	8.3	32.5	28.4
36		14.7	18.3	-	15.6	-	25.2	-	26.6	23.3	21.6
37		25.1	24.0	-	45.9	-	42.7	-	47.7	7.2	15.0
38		17.4	15.0	-	25.3	-	16.4	-	12.9	0.9	3.7
39		7.7	9.9	-	7.8	-	4.9	-	2.7	0.1	0.6
40 & Longer		2.8	5.5	-	0.7	-	1.1	-	0.3	-	*
Average Staple		36.40	36.63	-	37.17	-	36.84	-	36.71	34.93	35.23
Average Length		1.14	1.14	-	1.16	-	1.15	-	1.14	1.09	1.10

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 05, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	56.9	57.8	1.8	1.7	0.1	0.4	-	3.9	9.6	20.0
	3	8.7	15.1	2.9	1.2	*	0.4	-	2.6	1.2	5.4
	4	0.2	0.8	0.1	*	-	*	-	0.1	0.1	0.3
	5	-	*	-	*	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	65.8 73.7	4.8 2.9	0.1 0.8	- 6.6	10.9 25.7				
31	1 - 2	5.9	3.3	7.7	8.1	4.4	2.7	-	8.0	7.7	11.1
	3	7.4	5.1	21.4	21.8	10.3	12.2	-	33.0	11.4	14.0
	4	1.5	1.9	2.4	4.2	1.0	3.4	-	11.5	2.7	3.2
	5	0.1	0.3	*	0.2	*	0.2	-	0.9	0.3	0.4
	6	-	*	-	*	-	*	-	*	*	*
	7	-	*	-	*	-	*	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	14.8 10.7	31.5 34.3	15.7 18.5	- 53.4	22.0 28.7				
41	1 - 2	0.1	*	7.7	5.0	0.9	2.4	-	0.7	4.0	3.3
	3	0.5	0.1	31.4	31.5	31.8	30.8	-	12.3	22.5	15.3
	4	0.3	0.2	13.0	16.5	39.3	26.7	-	16.2	18.2	10.4
	5	0.1	0.2	1.0	2.1	8.2	5.1	-	4.5	7.5	3.2
	6	-	0.1	-	0.1	0.1	0.4	-	0.4	1.2	0.5
	7	-	*	-	*	-	*	-	-	0.1	*
	8	-	*	-	-	-	-	-	-	-	*
	Total	----	1.0 0.5	53.0 55.3	80.3 65.3	- 34.2	53.5 32.7				
51	1 - 2	-	*	1.5	0.2	*	0.1	-	*	0.1	0.1
	3	-	*	3.8	2.4	1.0	2.9	-	*	2.7	1.2
	4	*	*	2.2	2.3	1.1	4.7	-	0.3	4.0	2.3
	5	-	*	0.4	0.5	0.1	1.7	-	0.3	2.4	1.6
	6	-	*	*	0.1	*	0.3	-	0.1	1.2	0.7
	7	-	*	-	*	-	*	-	-	0.2	0.2
	8	-	*	-	*	-	-	-	-	-	*
	Total	----	* *	7.9 5.5	2.3 9.7	- 0.7	10.7 6.0				
61	1 - 2	-	*	*	*	-	*	-	-	-	*
	3	-	*	0.1	*	-	*	-	*	*	*
	4	-	*	0.1	*	-	*	-	*	*	*
	5	-	-	*	*	-	*	-	-	*	*
	6	-	-	*	*	-	*	-	-	-	*
	7	-	-	-	*	-	*	-	-	-	*
	8	-	-	-	*	-	-	-	-	-	-
	Total	----	- *	0.2 0.1	- *	- *	* *				
71	1 - 2	-	*	-	-	-	*	-	-	-	-
	3	-	*	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- *	- -	- *	- -	- -				
12 & 22	1 - 2	9.3	6.0	-	*	-	*	-	0.1	0.1	2.0
	3	2.1	3.8	*	*	-	*	-	0.1	0.3	1.0
	4	0.7	0.5	-	*	-	*	-	0.1	0.3	0.2
	5	0.1	*	-	-	-	*	-	*	*	*
	6	-	*	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	*	*	-	-	-	-	-	-	-	-
	Total	----	12.2 10.3	* 0.1	- *	- 0.3	0.6 3.1				
32	1 - 2	0.4	0.3	*	0.1	-	*	-	0.1	*	0.2
	3	0.3	1.0	0.1	0.3	*	0.2	-	0.5	0.3	0.5
	4	0.5	0.6	*	0.1	-	0.1	-	0.8	0.4	0.4
	5	0.2	0.2	-	*	-	*	-	0.4	0.1	0.2
	6	*	*	-	*	-	*	-	0.1	*	*
	7	-	*	-	-	-	-	-	-	*	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	1.4 2.1	0.1 0.4	* 0.3	- 1.8	0.9 1.3				
42	1 - 2	*	*	-	*	*	0.2	-	*	0.1	*
	3	*	*	0.3	0.5	0.1	1.7	-	0.4	0.4	0.5
	4	0.1	0.1	0.3	0.4	0.6	1.5	-	1.2	0.3	0.5
	5	0.1	0.1	0.1	0.1	0.8	0.4	-	0.7	0.1	0.3
	6	*	*	-	*	*	0.1	-	0.4	0.1	0.1
	7	-	*	-	*	-	*	-	-	*	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	0.2 0.2	0.6 1.1	1.6 3.8	- 2.6	1.0 1.4				

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 05, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	0.4	*	-	*	-	-	-	*
	3	-	-	0.5	0.1	-	0.4	-	*	0.1	0.1
	4	-	*	0.3	0.1	*	0.6	-	0.1	0.1	0.2
	5	-	*	*	*	*	0.3	-	0.1	0.1	0.2
	6	-	*	*	*	-	0.1	-	*	0.1	0.1
	7	-	*	*	*	-	*	-	*	*	*
	8	-	*	-	*	-	-	-	-	-	*
Total	----	-	*	1.3	0.2	0.1	1.4	-	0.1	0.3	0.6
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	*	*	-	*	-	-	-	*
	4	-	-	-	*	-	*	-	-	*	*
	5	-	-	-	*	-	*	-	-	-	*
	6	-	-	-	*	-	*	-	-	-	*
	7	-	-	-	*	-	*	-	-	-	*
	8	-	-	-	*	-	-	-	-	-	*
Total	----	-	-	*	*	-	*	-	-	*	*
13 & 23	1 - 2	3.0	0.7	-	*	-	-	-	-	-	0.1
	3	0.6	0.6	-	*	-	-	-	-	-	0.1
	4	0.1	0.1	-	*	-	-	-	-	-	*
	5	-	*	-	*	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	3.7	1.4	-	*	-	-	-	-	-	0.2
33	1 - 2	0.2	0.1	-	*	-	*	-	*	-	*
	3	0.1	0.3	-	*	-	*	-	*	*	*
	4	0.2	0.2	-	*	-	*	-	*	-	*
	5	0.1	0.1	-	*	-	*	-	*	-	*
	6	*	*	-	*	-	*	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	0.5	0.8	-	*	-	*	-	0.1	*	0.1
43	1 - 2	-	*	-	*	-	*	-	*	-	*
	3	*	*	*	*	-	*	-	*	-	*
	4	-	*	*	*	-	*	-	*	-	*
	5	*	*	*	*	-	*	-	*	-	*
	6	*	*	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	*	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	*	0.1	0.1	0.1	-	0.1	-	0.1	-	0.1
53	1 - 2	-	-	*	*	-	*	-	-	-	*
	3	-	-	0.1	*	-	*	-	-	-	*
	4	-	-	*	*	-	*	-	-	-	*
	5	-	-	*	*	-	*	-	-	-	*
	6	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	*	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	*	0.2	*	-	*	-	*	-	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	*	*	-	-	-	-	-	-
	4	-	-	*	*	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	*	*	-	-	-	-	-	-
24 - 54	1 - 8	0.4	0.1	*	*	-	*	-	0.1	-	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	0.1	*	-	*	-	-	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	*	-	-	-	-	-	-	-	-
30		-	*	-	*	-	-	-	-	-	-
31		0.1	0.1	*	*	-	*	-	-	-	*
32		0.3	0.5	0.6	0.1	-	*	-	*	*	*
33		1.6	2.6	4.4	0.8	-	0.1	-	0.2	0.2	0.2
34		9.5	8.7	12.1	4.7	*	0.8	-	1.6	0.4	0.8
35		23.4	18.3	22.8	15.4	1.1	4.1	-	11.3	4.0	3.7
36		27.0	25.8	20.5	30.1	21.7	15.2	-	28.8	19.3	14.5
37		28.5	29.3	19.7	35.7	48.1	47.7	-	39.8	43.8	42.0
38		8.0	10.6	8.8	10.2	21.9	26.8	-	14.1	20.2	23.7
39		1.5	3.2	6.2	2.5	6.1	4.7	-	3.8	5.9	8.4
40 & Longer		0.1	1.0	4.7	0.4	1.0	0.5	-	0.4	6.1	6.7
Average Staple		36.01	36.18	36.13	36.38	37.13	37.12	-	36.66	37.33	37.56
Average Length		1.12	1.13	1.13	1.13	1.16	1.16	-	1.14	1.17	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 05, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	24.8	9.0	-	0.6	-	*	-	2.1	2.9	1.4
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	*	0.1	-	0.3	-	0.1	-	*	0.3	0.3
Grass - Level 2	-	-	-	*	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	-	*	-	-
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	-	1.5	-	0.8	1.1	0.1
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	*
Other - Level 2	-	*	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	0.1	-	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	-	*	-	*	-	-	-	-	-	*
23	-	*	-	*	-	-	-	-	*	0.1
24	*	*	-	*	-	*	-	*	*	0.2
25	0.1	0.1	-	*	-	*	-	*	1.0	0.9
26	0.4	0.7	-	0.2	-	0.1	-	0.5	2.9	2.7
27	1.8	2.7	-	1.2	-	0.5	-	3.0	10.6	7.5
28	6.5	7.9	-	5.2	-	3.9	-	12.6	22.5	14.0
29	13.5	14.6	-	14.8	-	15.4	-	30.5	27.5	19.8
30	17.4	17.6	-	21.7	-	28.5	-	30.3	16.3	21.9
31	18.6	17.0	-	17.7	-	26.8	-	15.3	11.7	17.7
32	18.9	14.5	-	12.5	-	15.8	-	5.8	4.5	9.4
33	13.1	11.5	-	11.6	-	6.3	-	1.6	2.0	3.7
34	5.1	7.3	-	9.7	-	2.1	-	0.3	0.6	1.4
35	2.8	3.7	-	4.0	-	0.5	-	0.1	0.3	0.5
36	1.3	1.4	-	1.1	-	0.1	-	*	*	0.2
37	0.4	0.7	-	0.2	-	*	-	*	*	*
38	0.1	0.2	-	*	-	*	-	-	-	*
39	*	*	-	*	-	*	-	-	-	-
40 & Above	*	*	-	-	-	*	-	-	-	-
Average	31.52	31.47	-	31.59	-	31.09	-	30.12	29.55	30.14
Mike										
2.4 & Below	*	*	-	-	-	-	-	-	-	*
2.5	0.2	0.2	-	*	-	-	-	*	0.1	0.1
2.6	0.5	0.2	-	*	-	-	-	-	0.8	0.2
2.7	0.6	0.3	-	*	-	-	-	*	1.0	0.3
2.8	0.9	0.4	-	*	-	-	-	*	1.2	0.4
2.9	0.9	0.5	-	*	-	-	-	*	1.5	0.6
3.0	1.1	0.6	-	0.1	-	-	-	*	2.3	0.8
3.1	1.3	0.8	-	0.1	-	-	-	*	2.3	0.9
3.2	2.0	1.1	-	0.3	-	*	-	0.1	2.0	1.3
3.3	2.2	1.4	-	0.5	-	*	-	0.2	1.8	1.6
3.4	2.3	1.9	-	0.9	-	*	-	0.3	2.8	2.0
3.5	3.7	2.5	-	1.3	-	*	-	0.5	1.7	2.5
3.6	3.5	3.5	-	1.9	-	0.1	-	0.9	2.7	3.1
3.7	4.4	4.4	-	2.7	-	0.1	-	1.8	4.6	3.8
3.8	5.3	5.5	-	4.4	-	0.1	-	2.7	3.4	4.6
3.9	7.3	7.0	-	6.7	-	0.2	-	4.2	4.5	5.5
4.0	9.1	8.5	-	9.0	-	0.4	-	5.8	3.2	6.2
4.1	10.8	10.1	-	11.1	-	0.6	-	7.8	6.5	7.0
4.2	10.9	10.7	-	12.7	-	1.0	-	9.9	7.5	8.0
4.3	10.0	10.7	-	12.9	-	1.7	-	11.6	7.7	8.7
4.4	8.9	9.5	-	11.3	-	2.8	-	11.8	8.0	9.2
4.5	5.9	7.6	-	8.8	-	4.1	-	10.7	9.8	9.0
4.6	3.3	5.5	-	6.0	-	6.5	-	9.4	10.1	8.2
4.7	2.4	3.5	-	3.7	-	9.5	-	7.7	7.5	6.5
4.8	1.6	2.0	-	2.3	-	13.4	-	5.5	4.0	4.5
4.9	0.5	0.9	-	1.3	-	16.0	-	3.9	2.1	2.6
5.0	0.2	0.4	-	0.8	-	16.3	-	2.5	0.7	1.4
5.1	-	0.2	-	0.4	-	12.9	-	1.4	0.3	0.6
5.2	-	0.1	-	0.3	-	8.2	-	0.7	-	0.3
5.3	-	*	-	0.2	-	4.0	-	0.3	-	0.1
5.4	-	-	-	0.1	-	1.5	-	0.1	-	*
5.5 & Above	-	*	-	0.2	-	0.5	-	*	-	*
Average	4.01	4.11	-	4.23	-	4.88	-	4.38	4.11	4.19

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE

For The Week Ending Feb 05, 2026

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	12.2	7.7	2.5	1.3	-	*	-	1.8	0.5	0.3
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	0.2	0.1	*	0.1	-	*	-	0.1	0.9	0.4
Grass - Level 2	-	*	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	*	*	-	*	-	-	*	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.5	0.4	0.2	0.3	-	0.1	-	2.9	0.1	*
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	*
Spindle Twist - Level 2	-	*	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	0.1	*	*	*	*	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	-	*	-	-	-	*	-	-	*	*
23	-	*	*	*	-	*	-	-	-	*
24	*	0.1	0.1	*	-	*	-	-	*	*
25	*	0.2	0.6	0.1	-	*	-	*	0.1	0.1
26	0.3	0.7	3.3	0.6	-	*	-	0.1	0.8	0.5
27	2.3	2.6	9.5	3.2	*	0.2	-	1.8	5.1	2.1
28	7.6	7.1	21.0	10.6	0.8	1.8	-	6.6	16.0	8.3
29	18.2	14.6	20.0	20.5	8.6	12.5	-	18.0	22.5	16.3
30	22.1	20.2	17.0	25.1	29.8	36.0	-	30.0	21.2	20.7
31	21.1	19.9	11.8	20.0	27.1	32.5	-	20.1	14.4	18.4
32	15.0	15.1	8.9	11.5	19.4	12.2	-	12.6	9.6	11.9
33	8.3	9.8	6.2	5.3	10.6	3.7	-	6.0	4.2	7.7
34	3.5	5.5	1.4	2.1	3.4	0.9	-	3.1	2.5	6.1
35	1.1	2.5	0.2	0.7	0.2	0.1	-	1.6	2.1	4.4
36	0.2	1.0	*	0.2	-	*	-	0.2	1.3	2.4
37	0.1	0.4	-	*	-	*	-	*	0.3	0.8
38	*	0.1	-	*	-	*	-	*	0.1	0.1
39	-	*	-	*	-	-	-	-	*	*
40 & Above	-	-	-	*	-	-	-	-	*	*
Average	31.01	31.28	29.92	30.63	31.47	31.01	-	30.93	30.48	31.36
Mike										
2.4 & Below	*	*	-	-	-	-	-	-	-	-
2.5	*	0.1	-	*	-	-	-	*	*	*
2.6	0.1	0.1	-	*	-	-	-	*	*	*
2.7	0.2	0.2	-	*	-	*	-	*	*	*
2.8	0.3	0.4	-	*	-	*	-	*	0.5	0.2
2.9	0.7	0.6	-	*	-	*	-	*	0.3	0.2
3.0	1.4	0.9	-	*	-	*	-	*	0.7	0.2
3.1	2.1	1.3	*	*	-	*	-	*	0.6	0.5
3.2	2.8	1.8	*	0.1	-	*	-	0.1	0.9	0.7
3.3	2.8	2.3	0.2	0.2	-	*	-	0.1	0.7	0.6
3.4	3.5	3.0	0.3	0.3	-	0.1	-	0.1	1.6	0.8
3.5	3.9	3.8	0.9	0.6	-	0.1	-	0.2	2.5	1.3
3.6	4.7	4.4	1.8	1.1	-	0.2	-	0.4	3.0	1.7
3.7	5.4	5.0	3.5	1.9	-	0.4	-	0.5	3.3	2.6
3.8	6.6	5.5	5.3	2.8	*	0.6	-	0.7	4.7	3.4
3.9	7.6	6.1	6.9	4.0	0.1	1.0	-	1.1	8.1	4.8
4.0	9.0	6.5	7.6	5.5	0.4	1.7	-	1.9	8.8	6.1
4.1	8.9	6.9	10.6	7.4	1.4	2.6	-	3.5	9.8	7.8
4.2	8.8	7.3	12.7	9.1	3.9	4.0	-	4.5	11.4	9.1
4.3	8.8	7.7	10.1	10.1	8.9	5.8	-	5.6	9.7	9.3
4.4	7.1	7.7	7.7	10.3	9.1	8.2	-	6.6	8.9	9.1
4.5	5.2	7.4	5.5	9.9	13.1	11.0	-	8.6	7.7	9.4
4.6	3.9	6.6	4.7	9.1	12.0	13.9	-	9.7	6.3	8.9
4.7	2.2	5.4	4.9	8.2	15.5	15.2	-	10.6	5.0	7.3
4.8	1.3	3.8	4.5	6.5	15.6	13.8	-	11.4	2.9	5.5
4.9	0.7	2.4	4.4	4.9	13.6	10.1	-	10.6	1.1	4.1
5.0	0.6	1.4	3.6	3.4	5.1	6.3	-	8.4	0.5	2.6
5.1	0.5	0.7	2.1	2.2	1.1	3.1	-	7.0	0.5	1.4
5.2	0.3	0.4	1.2	1.2	*	1.2	-	4.0	0.3	0.9
5.3	0.2	0.2	0.6	0.6	-	0.4	-	2.2	0.1	0.7
5.4	0.1	0.1	0.3	0.3	*	0.1	-	1.1	-	0.3
5.5 & Above	*	0.1	0.7	0.1	*	*	-	1.1	-	0.3
Average	3.99	4.12	4.31	4.41	4.63	4.62	-	4.68	4.16	4.33

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 05, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	*	*	-	-	-	-	-	-	-	*
2.5 - 2.6	0.7	0.4	-	*	-	-	-	*	0.9	0.3
2.7 - 2.9	2.4	1.2	-	0.1	-	-	-	*	3.7	1.2
3.0 - 3.2	4.4	2.5	-	0.5	-	*	-	0.2	6.6	3.1
3.3 - 3.4	4.5	3.3	-	1.4	-	*	-	0.5	4.6	3.7
3.5 - 3.6	7.3	6.0	-	3.1	-	0.1	-	1.5	4.4	5.6
3.7 - 4.2	47.9	46.2	-	46.6	-	2.5	-	32.1	29.7	35.1
4.3 - 4.9	32.6	39.8	-	46.4	-	54.0	-	60.6	49.2	48.6
5.0 - 5.2	0.2	0.7	-	1.4	-	37.4	-	4.6	1.0	2.2
5.3 & Above	-	*	-	0.5	-	6.1	-	0.4	-	0.2
Average	4.01	4.11	-	4.23	-	4.88	-	4.38	4.11	4.19
Leaf										
1 - 2	46.1	57.9	-	24.8	-	3.8	-	8.4	81.8	86.5
3	26.3	26.5	-	49.7	-	37.7	-	52.5	16.9	11.8
4	14.3	9.0	-	21.1	-	45.4	-	33.2	1.3	1.4
5	9.0	4.1	-	4.0	-	12.0	-	5.4	0.1	0.3
6	3.3	1.8	-	0.5	-	1.1	-	0.4	-	0.1
7	0.7	0.6	-	0.1	-	*	-	*	-	*
8	0.2	0.1	-	*	-	-	-	*	-	-
Average	2.90	2.51	-	3.03	-	3.69	-	3.37	1.96	1.75
HVI Trash 1/										
00	*	*	-	*	-	-	-	-	0.2	0.7
01	18.6	28.8	-	5.1	-	0.3	-	0.6	42.7	59.8
02	30.5	32.4	-	22.5	-	4.6	-	10.2	43.8	29.5
03	15.4	15.6	-	27.9	-	14.9	-	24.6	10.3	6.9
04	8.4	8.2	-	20.4	-	22.9	-	26.2	2.3	1.9
05	6.5	4.6	-	12.1	-	22.0	-	18.8	0.4	0.7
06	5.3	2.8	-	6.5	-	15.8	-	10.7	0.1	0.3
07	4.4	2.0	-	3.1	-	9.7	-	5.2	*	0.1
08	3.5	1.5	-	1.4	-	5.2	-	2.3	-	0.1
09	2.5	1.1	-	0.6	-	2.6	-	0.9	-	*
10	1.7	0.8	-	0.3	-	1.2	-	0.4	-	*
11	1.1	0.6	-	0.1	-	0.5	-	0.2	-	*
12	0.8	0.5	-	0.1	-	0.2	-	0.1	-	*
13	0.4	0.3	-	*	-	0.1	-	*	-	*
14	0.3	0.2	-	*	-	*	-	*	-	*
15	0.2	0.1	-	*	-	*	-	*	-	-
16	0.2	0.1	-	*	-	-	-	*	-	*
17	0.1	0.1	-	*	-	-	-	*	-	*
18 & Above	0.1	0.1	-	*	-	-	-	*	-	-
Average	0.36	0.28	-	0.36	-	0.50	-	0.43	0.17	0.15
UNIFORMITY 2/										
74 & Below	*	*	-	*	-	-	-	*	-	*
75	*	0.1	-	*	-	-	-	*	*	0.1
76	0.3	0.2	-	*	-	*	-	*	0.1	0.5
77	1.6	0.8	-	0.1	-	*	-	*	0.7	2.4
78	5.1	3.2	-	0.7	-	0.2	-	0.5	4.0	10.0
79	15.9	12.8	-	3.7	-	1.0	-	2.9	20.1	25.0
80	30.5	27.9	-	13.4	-	7.0	-	12.0	41.7	35.9
81	27.7	29.2	-	30.1	-	28.1	-	28.8	22.5	21.4
82	13.7	17.1	-	31.1	-	37.9	-	35.0	10.1	4.4
83	4.3	7.0	-	16.1	-	20.5	-	18.2	0.8	0.5
84	0.6	1.6	-	4.3	-	5.1	-	2.3	*	*
85 & Above	0.1	0.1	-	0.4	-	0.2	-	0.2	-	*
Average	80.83	81.14	-	82.00	-	82.30	-	82.04	80.60	80.22
Tenderable 3/	64.8	80.5	-	88.1	-	53.0	-	90.5	77.2	84.2
SAMPLES CLASSED										
Week	43,247		-		-		-		8,513	
Season		1,047,715		1,524,522		951,045		1,110,530		569,399

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 05, 2026

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	*	*	-	-	-	-	-	-	-	-
2.5 - 2.6	0.2	0.2	-	*	-	-	-	*	*	*
2.7 - 2.9	1.3	1.2	-	*	-	*	-	0.1	0.8	0.4
3.0 - 3.2	6.3	4.0	0.1	0.1	-	*	-	0.1	2.2	1.4
3.3 - 3.4	6.3	5.4	0.5	0.5	-	0.1	-	0.2	2.3	1.4
3.5 - 3.6	8.6	8.2	2.7	1.8	-	0.3	-	0.6	5.5	3.1
3.7 - 4.2	46.4	37.2	46.6	30.8	5.8	10.4	-	12.1	46.1	33.9
4.3 - 4.9	29.3	40.9	41.7	59.0	87.9	78.0	-	63.1	41.8	53.5
5.0 - 5.2	1.4	2.5	6.9	6.8	6.3	10.6	-	19.4	1.3	5.0
5.3 & Above	0.3	0.3	1.5	1.0	*	0.6	-	4.4	0.1	1.3
Average	3.99	4.12	4.31	4.41	4.63	4.62	-	4.68	4.16	4.33
Leaf										
1 - 2	76.0	68.4	19.1	15.3	5.5	5.8	-	12.8	21.6	36.8
3	19.7	26.0	60.7	57.9	43.2	48.7	-	48.8	39.0	38.1
4	3.5	4.4	18.5	23.7	42.0	37.0	-	30.4	26.0	17.5
5	0.7	0.9	1.6	3.0	9.2	7.6	-	6.9	10.5	5.9
6	*	0.2	*	0.2	0.2	0.8	-	1.0	2.6	1.4
7	-	*	*	*	-	0.1	-	*	0.3	0.2
8	*	*	-	*	-	-	-	-	-	*
Average	2.04	2.21	3.03	3.15	3.55	3.49	-	3.34	3.28	2.91
HVI Trash 1/										
00	0.1	*	-	-	-	*	-	-	*	*
01	40.9	33.2	1.7	1.6	0.1	0.5	-	1.6	9.5	14.1
02	37.3	41.6	23.9	19.8	6.5	7.3	-	14.0	16.3	28.2
03	12.6	15.5	33.7	31.4	20.2	21.2	-	24.1	21.9	21.6
04	4.9	5.5	22.1	23.6	26.8	26.2	-	23.2	17.5	14.4
05	2.3	2.2	10.8	12.9	23.4	20.2	-	16.3	13.2	9.0
06	1.0	1.0	4.3	6.1	13.0	12.2	-	9.7	9.1	5.4
07	0.5	0.5	2.1	2.7	6.8	6.5	-	5.3	6.1	3.3
08	0.2	0.3	0.9	1.1	2.3	3.1	-	2.7	3.4	1.9
09	0.1	0.1	0.3	0.5	0.6	1.5	-	1.5	1.6	1.1
10	*	0.1	*	0.2	0.2	0.7	-	0.8	0.8	0.5
11	*	0.1	*	0.1	*	0.3	-	0.4	0.4	0.3
12	*	*	*	*	*	0.1	-	0.2	0.2	0.1
13	-	*	*	*	-	0.1	-	0.1	0.1	0.1
14	-	*	*	*	-	*	-	*	*	*
15	*	*	-	*	-	*	-	-	-	*
16	-	*	-	*	-	-	-	-	-	*
17	-	*	-	*	-	-	-	*	-	*
18 & Above	*	*	-	*	-	-	-	-	-	*
Average	0.20	0.21	0.35	0.37	0.45	0.46	-	0.42	0.40	0.33
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	-	-	-	-
75	*	*	-	*	-	-	-	-	*	*
76	0.2	0.2	*	*	-	*	-	-	*	*
77	1.2	1.1	0.5	0.1	-	*	-	-	0.5	0.1
78	5.4	4.4	3.7	0.8	*	0.1	-	0.2	1.0	0.6
79	16.4	14.2	10.6	5.1	0.6	0.5	-	1.8	5.8	3.3
80	29.3	29.9	23.3	20.1	7.6	3.9	-	10.5	25.8	16.9
81	29.8	31.7	29.1	36.4	26.8	20.9	-	32.0	38.5	33.6
82	13.6	14.7	22.7	27.8	45.5	45.7	-	37.5	19.6	32.3
83	3.5	3.1	9.0	8.4	18.4	26.1	-	15.8	7.6	11.0
84	0.5	0.4	1.2	1.2	1.1	2.6	-	2.1	0.9	2.0
85 & Above	0.1	0.1	0.1	0.1	*	0.2	-	0.1	0.2	0.2
Average	80.83	80.90	81.33	81.60	82.22	82.46	-	82.06	81.41	81.80
Tenderable 3/	72.1	78.4	85.9	88.6	91.9	83.4	-	69.4	88.3	85.7
SAMPLES CLASSED										
Week	18,154		14,075		10,119		-		21,870	
Season		2,488,237		2,190,446		2,319,077		281,672		327,262

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 05, 2026

Color Grade	Leaf	VISALIA			Quality Designation	VISALIA	
		Week	Season			Week	Season
01	1	4.4	6.3		MIKE	-	-
	2	6.7	7.6		2.4 & Below	-	-
	3	0.1	0.2		2.5 - 2.6	-	-
	4	-	-		2.7 - 2.9	0.5	0.2
	5	-	-		3.0 - 3.2	4.2	1.6
	6	-	-		3.3 - 3.4	1.1	2.8
	7	-	-		3.5 - 3.6	4.8	8.5
Total -----		11.2	14.1		3.7 - 4.2	85.0	83.1
02	1	11.8	7.3		4.3 - 4.9	4.4	4.0
	2	33.9	34.9		5.0 - 5.2	*	*
	3	4.9	8.2		5.3 & Above	-	-
	4	0.1	0.2		Average	3.90	3.89
	5	*	*		ALL RANGE MIKE		
	6	-	-		2.4 & Below	-	-
	7	-	-		2.5	-	-
Total -----		50.8	50.6		2.6	-	-
03	1	2.0	0.6		2.7	-	*
	2	13.4	13.1		2.8	0.1	*
	3	13.4	15.7		2.9	0.4	0.1
	4	4.3	1.7		3.0	0.9	0.3
	5	0.3	*		3.1	1.8	0.5
	6	0.1	*		3.2	1.5	0.8
	7	-	-		3.3	0.6	1.0
Total -----		33.3	31.2		3.4	0.5	1.8
04	1	0.1	*		3.5	1.7	3.0
	2	0.6	0.6		3.6	3.1	5.5
	3	0.8	2.0		3.7	9.7	9.6
	4	0.5	0.8		3.8	15.7	15.1
	5	0.2	0.1		3.9	18.3	20.5
	6	0.2	*		4.0	15.7	19.3
	7	-	-		4.1	15.6	12.4
Total -----		2.3	3.5		4.2	10.0	6.3
05	1	-	*		4.3	3.0	2.5
	2	0.4	0.1		4.4	0.9	0.9
	3	0.7	0.2		4.5	0.5	0.4
	4	0.1	0.2		4.6	0.1	0.1
	5	-	*		4.7	*	*
	6	-	*		4.8	-	*
	7	-	-		4.9	-	*
Total -----		1.1	0.5		5.0	*	*
06	1	-	-		5.1	-	*
	2	0.1	*		5.2	-	-
	3	0.6	0.1		5.3 & Above	-	-
	4	0.4	*		Average	3.90	3.89
	5	-	*		STRENGTH 1/		
	6	-	*		36 & Below	3.7	2.8
	7	-	-		37	2.2	4.8
Total -----		1.1	0.1		38	1.6	3.8
07	1	-	-		39	1.3	1.8
	2	-	-		40	4.0	2.0
	3	*	*		41	7.1	5.6
	4	*	*		42	10.6	11.0
	5	-	*		43	10.5	16.5
	6	-	*		44	11.0	19.3
	7	-	-		45	20.7	16.5
Total -----		*	*		46	18.3	9.8
STAPLE					47	5.2	4.1
44 & Shorter		5.4	2.8		48 & Above	3.9	2.0
46		7.6	11.3		Average	44.03	43.50
48		37.1	46.0		UNIFORMITY		
50		47.0	37.9		83 & Below	2.8	1.6
52 & Longer		2.9	2.0		84	7.4	11.8
Average Staple		48.69	48.50		85	28.1	34.7
Average Length		1.41	1.41		86	52.1	45.5
EXTRANEIOUS MATTER					87	7.9	5.8
Bark		*	*		88 & Above	1.7	0.5
Grass		-	0.3		Average	86.07	85.88
Spindle Twist		0.7	0.1		Samples Classed		
Preparation		-	*		Week	5,602	
All Other		-	*		Season		370,749

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.