



Weekly Quality of Cotton Classed by Classing Office: Week Ending - 2/12/2026

Agricultural Marketing Service
Cotton Market News

Volume 67, No.28

February 13, 2026

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	21	71.6	54.0	36,184	31	80.2	60.3	1,083,789
Corpus Christi	-	-	-	-	42	88.1	72.5	1,524,522
Dumas	-	-	-	-	33	53.0	25.2	951,045
Florence	-	-	-	-	40	90.5	79.2	1,110,530
Lamesa	5	78.1	54.7	10,873	24	84.1	59.8	580,272
Lubbock	14	71.1	45.8	9,157	54	78.4	58.4	2,497,373
Macon	6	83.0	70.2	3,525	68	88.6	74.8	2,193,971
Memphis	3	91.6	68.3	10,992	65	83.5	60.1	2,330,069
Rayville*	-	-	-	-	16	69.3	47.6	283,396
Visalia	9	85.3	74.1	19,478	26	85.7	70.3	346,740
United States	59	77.6	59.7	91,933	399	81.8	62.8	12,901,707
AMERICAN PIMA								
Visalia	4			5,580	18			376,329
United States	4			5,580	18			376,329
United States all cotton	63			97,513	408			13,278,036

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

MP_CN100

Source: USDA AMS Cotton and Tobacco Market News

Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov

<https://www.ams.usda.gov/market-news/cotton>

<https://mymarketnews.ams.usda.govcottonmn@ams.usda.gov>

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 12, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 11 & 21	1-2	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
	3	16.9	36.8	-	14.3	-	0.9	-	0.5	50.8	71.5
	4	4.0	6.6	-	14.3	-	0.8	-	0.5	7.2	6.6
	5	0.2	0.4	-	1.4	-	*	-	*	0.1	0.3
	6	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	*
	Total	----	21.0 43.8	-	30.1	-	1.7	-	1.0	58.0	78.4
31	1-2	16.7	9.3	-	5.1	-	2.2	-	5.3	15.1	3.0
	3	15.9	11.6	-	22.2	-	16.1	-	21.7	11.2	1.9
	4	3.9	3.5	-	9.4	-	7.9	-	6.2	1.4	0.4
	5	0.2	0.5	-	1.0	-	0.5	-	0.3	*	0.1
	6	*	0.1	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	36.8 25.0	-	37.7	-	26.8	-	33.5	27.7	5.4
41	1-2	1.6	0.4	-	0.6	-	0.6	-	2.5	-	*
	3	3.7	1.5	-	5.3	-	19.0	-	29.0	*	*
	4	3.2	1.9	-	5.0	-	32.8	-	25.0	*	*
	5	1.3	1.6	-	1.3	-	9.1	-	4.3	*	*
	6	0.9	0.7	-	0.1	-	0.6	-	0.3	-	*
	7	0.3	0.1	-	*	-	*	-	*	-	*
	8	*	*	-	-	-	-	-	*	-	-
	Total	----	11.0 6.2	-	12.4	-	62.2	-	61.2	0.1	0.1
51	1-2	*	*	-	*	-	*	-	0.1	-	-
	3	-	*	-	0.2	-	1.1	-	0.9	-	-
	4	*	*	-	0.4	-	3.0	-	1.6	-	-
	5	*	0.1	-	0.1	-	1.5	-	0.7	-	-
	6	0.1	0.2	-	*	-	0.2	-	0.1	-	*
	7	0.1	0.1	-	*	-	*	-	*	-	-
	8	0.1	*	-	-	-	-	-	*	-	-
	Total	----	0.5 0.4	-	0.8	-	5.8	-	3.4	-	*
61	1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	- *	- *	- *	- *	- *	- *	- *	-	-
71	1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	- -	- -	- -	- -	- -	- *	- *	-	-
12 & 22	1-2	2.6	8.4	-	4.0	-	*	-	*	7.2	10.4
	3	1.0	2.8	-	3.8	-	*	-	*	2.5	2.3
	4	0.2	0.4	-	1.0	-	*	-	*	*	0.2
	5	*	*	-	0.1	-	-	-	-	-	*
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	3.9 11.6	-	8.9	-	*	-	*	9.7	13.0
32	1-2	6.0	1.8	-	0.6	-	*	-	*	1.3	0.3
	3	6.6	2.9	-	2.6	-	0.1	-	0.1	1.5	0.5
	4	3.5	1.5	-	2.4	-	0.1	-	0.1	0.1	0.2
	5	0.6	0.5	-	0.6	-	*	-	*	*	0.1
	6	*	0.1	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	16.7 6.8	-	6.3	-	0.3	-	0.2	2.9	1.1
42	1-2	0.1	0.1	-	0.1	-	*	-	*	-	*
	3	0.7	0.4	-	0.9	-	0.5	-	0.2	*	*
	4	1.0	0.8	-	1.1	-	1.2	-	0.3	*	*
	5	1.1	0.9	-	0.6	-	0.6	-	0.1	*	*
	6	0.9	0.6	-	0.1	-	0.1	-	*	-	*
	7	0.3	0.2	-	*	-	*	-	*	-	*
	8	*	*	-	-	-	-	-	*	-	-
	Total	----	4.0 3.0	-	2.8	-	2.5	-	0.6	0.1	*

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 12, 2026

Quality Designation	Leaf	ABILENE Week Season		CORPUS CHRISTI Week Season		DUMAS Week Season		FLORENCE Week Season		LAMESA Week Season	
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	*	-	*	-	*	-	*	-	*
	3	-	*	-	*	-	0.1	-	*	-	*
	4	*	*	-	0.1	-	0.2	-	*	-	-
	5	*	*	-	0.1	-	0.2	-	*	-	*
	6	0.1	*	-	*	-	0.1	-	*	-	-
	7	0.1	0.1	-	*	-	*	-	*	-	-
	8	*	0.1	-	-	-	-	-	*	-	-
Total	----	0.2	0.2	-	0.2	-	0.6	-	0.1	-	*
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	-	*	-	-
13 & 23	1 - 2	0.1	0.6	-	0.1	-	-	-	*	1.0	0.9
	3	0.2	0.4	-	0.1	-	-	-	*	*	0.3
	4	0.1	0.1	-	*	-	-	-	*	-	*
	5	-	*	-	*	-	-	-	-	-	*
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	0.4	1.2	-	0.2	-	-	-	*	1.0	1.3
33	1 - 2	0.4	0.2	-	*	-	*	-	*	0.2	0.1
	3	1.1	0.5	-	0.1	-	*	-	*	0.3	0.2
	4	0.8	0.3	-	0.1	-	*	-	*	0.1	0.2
	5	0.2	0.1	-	*	-	-	-	*	-	0.1
	6	*	*	-	*	-	-	-	*	-	*
	7	-	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	2.4	1.1	-	0.3	-	*	-	*	0.6	0.6
43	1 - 2	*	*	-	*	-	-	-	*	-	*
	3	0.1	0.1	-	0.1	-	*	-	*	-	*
	4	0.5	0.1	-	0.1	-	*	-	*	-	*
	5	1.2	0.2	-	0.1	-	*	-	*	-	*
	6	0.9	0.1	-	*	-	*	-	*	-	*
	7	0.3	0.1	-	*	-	-	-	*	-	*
	8	*	*	-	-	-	-	-	*	-	-
Total	----	3.0	0.6	-	0.3	-	*	-	*	-	*
53	1 - 2	-	-	-	*	-	*	-	-	-	-
	3	*	*	-	*	-	*	-	*	-	-
	4	*	*	-	*	-	*	-	*	-	-
	5	*	*	-	*	-	*	-	*	-	-
	6	*	*	-	*	-	*	-	*	-	*
	7	*	*	-	*	-	*	-	*	-	-
	8	*	*	-	-	-	-	-	*	-	-
Total	----	*	*	-	*	-	*	-	*	-	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	*	-	-	-	-
24 - 54	1 - 8	0.1	0.1	-	*	-	-	-	*	-	0.1
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	-	*	-	*	-	-	-	-	-	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-
30		-	*	-	-	-	-	-	-	*	*
31		*	0.1	-	*	-	*	-	*	0.1	0.2
32		0.6	0.5	-	*	-	*	-	*	1.1	1.8
33		4.9	3.0	-	0.1	-	0.1	-	0.1	6.9	7.5
34		14.8	8.9	-	0.7	-	1.3	-	1.4	16.9	21.0
35		21.2	15.2	-	3.8	-	8.2	-	8.3	36.9	28.6
36		19.9	18.4	-	15.6	-	25.2	-	26.6	27.0	21.7
37		19.3	23.9	-	45.9	-	42.7	-	47.7	9.7	14.9
38		7.7	14.8	-	25.3	-	16.4	-	12.9	1.2	3.7
39		6.4	9.8	-	7.8	-	4.9	-	2.7	0.2	0.6
40 & Longer		5.2	5.4	-	0.7	-	1.1	-	0.3	-	*
Average Staple		36.08	36.61	-	37.17	-	36.84	-	36.71	35.16	35.23
Average Length		1.13	1.14	-	1.16	-	1.15	-	1.14	1.09	1.10

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 12, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1 - 2	51.4	57.8	0.7	1.7	-	0.4	-	3.8	11.2	19.5
	3	6.4	15.0	1.6	1.2	-	0.4	-	2.5	0.7	5.2
	4	*	0.8	0.5	*	-	*	-	0.1	*	0.3
	5	-	*	-	*	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	57.8	73.7	2.9	2.9	-	0.8	-	6.5	12.0	24.9
31	1 - 2	5.9	3.3	9.4	8.1	0.7	2.7	-	8.0	8.1	10.9
	3	6.3	5.1	30.6	21.9	14.8	12.2	-	32.8	12.6	13.9
	4	2.4	2.0	8.2	4.2	2.7	3.4	-	11.5	1.3	3.1
	5	0.5	0.3	0.3	0.2	*	0.2	-	0.9	0.2	0.4
	6	*	*	-	*	-	*	-	*	*	*
	7	-	*	-	*	-	*	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	15.2	10.7	48.5	34.3	18.2	18.5	-	53.2	22.2	28.3
41	1 - 2	*	*	2.8	5.0	0.7	2.4	-	0.8	5.3	3.4
	3	0.1	0.1	31.0	31.5	36.2	30.8	-	12.3	26.2	15.9
	4	0.6	0.2	10.4	16.5	28.5	26.7	-	16.3	13.4	10.6
	5	0.6	0.2	0.4	2.1	2.0	5.1	-	4.5	3.8	3.2
	6	0.1	0.1	*	0.1	0.1	0.4	-	0.4	1.5	0.5
	7	*	*	-	*	-	*	-	-	0.3	*
	8	-	*	-	-	-	-	-	-	0.1	*
Total	----	1.4	0.5	44.7	55.3	67.5	65.4	-	34.3	50.5	33.7
51	1 - 2	-	*	0.1	0.2	0.1	0.1	-	*	0.1	0.1
	3	-	*	0.9	2.4	1.4	2.9	-	*	3.9	1.3
	4	-	*	0.5	2.3	6.0	4.7	-	0.3	4.2	2.4
	5	-	*	0.3	0.5	5.1	1.7	-	0.3	1.3	1.6
	6	-	*	*	0.1	0.4	0.3	-	0.1	0.5	0.7
	7	-	*	-	*	-	*	-	-	0.5	0.2
	8	-	*	-	*	-	-	-	-	0.1	*
Total	----	-	*	1.7	5.5	13.0	9.7	-	0.7	10.5	6.3
61	1 - 2	-	*	-	*	-	*	-	-	-	*
	3	-	*	-	*	-	*	-	*	*	*
	4	-	*	-	*	-	*	-	*	*	*
	5	-	-	-	*	-	*	-	-	-	*
	6	-	-	-	*	-	*	-	-	-	*
	7	-	-	-	*	-	*	-	-	-	*
	8	-	-	-	*	-	-	-	-	-	-
Total	----	-	*	-	0.1	-	*	-	*	*	*
71	1 - 2	-	*	-	-	-	*	-	-	-	-
	3	-	*	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	*	-	-	-	-
12 & 22	1 - 2	16.0	6.0	-	*	-	*	-	0.1	0.5	1.9
	3	4.8	3.8	0.6	*	-	*	-	0.1	0.6	1.0
	4	0.1	0.5	0.1	*	-	*	-	0.1	*	0.1
	5	-	*	-	-	-	*	-	*	-	*
	6	-	*	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	20.8	10.3	0.7	0.1	-	*	-	0.3	1.2	3.0
32	1 - 2	0.3	0.3	-	0.1	*	*	-	0.1	0.1	0.2
	3	0.4	1.0	0.2	0.3	*	0.2	-	0.5	0.7	0.5
	4	0.3	0.6	0.4	0.1	*	0.1	-	0.8	1.2	0.4
	5	0.1	0.2	0.1	*	-	*	-	0.4	0.2	0.2
	6	*	*	-	*	-	*	-	0.1	*	*
	7	-	*	-	-	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	1.1	2.1	0.7	0.4	*	0.3	-	1.8	2.1	1.3
42	1 - 2	-	*	-	*	*	0.2	-	*	0.1	*
	3	*	*	-	0.5	0.3	1.7	-	0.4	0.5	0.5
	4	0.5	0.1	0.2	0.4	0.3	1.5	-	1.2	0.3	0.5
	5	*	0.1	*	0.1	0.4	0.4	-	0.7	0.2	0.3
	6	-	*	-	*	-	0.1	-	0.4	0.1	0.1
	7	-	*	-	*	-	*	-	-	*	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	0.6	0.2	0.2	1.1	1.0	3.8	-	2.7	1.1	1.4

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 12, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1 - 2	-	-	0.1	*	-	*	-	-	-	*
	3	-	-	0.1	0.1	*	0.4	-	*	*	0.1
	4	-	*	-	0.1	0.1	0.6	-	0.1	0.1	0.2
	5	-	*	-	*	0.1	0.3	-	0.1	*	0.2
	6	-	*	-	*	*	0.1	-	*	*	0.1
	7	-	*	-	*	-	*	-	*	*	*
	8	-	*	-	*	-	-	-	-	*	*
Total	----	-	*	0.1	0.2	0.2	1.4	-	0.1	0.2	0.6
62	1 - 2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	*
	4	-	-	-	*	*	*	-	-	-	*
	5	-	-	-	*	*	*	-	-	-	*
	6	-	-	-	*	-	*	-	-	-	*
	7	-	-	-	*	-	*	-	-	-	*
	8	-	-	-	*	-	-	-	-	-	*
Total	----	-	-	-	*	*	*	-	-	-	*
13 & 23	1 - 2	1.7	0.7	-	*	-	-	-	-	-	0.1
	3	0.2	0.6	-	*	-	-	-	-	-	0.1
	4	*	0.1	*	*	-	-	-	-	-	*
	5	-	*	-	*	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	1.9	1.4	*	*	-	-	-	-	-	0.2
33	1 - 2	1.0	0.1	-	*	-	*	-	*	*	*
	3	*	0.3	0.1	*	*	*	-	*	*	*
	4	-	0.2	0.3	*	-	*	-	*	*	*
	5	-	0.1	*	*	-	*	-	*	*	*
	6	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	1.0	0.8	0.5	*	*	*	-	0.1	0.1	0.1
43	1 - 2	-	*	-	*	-	*	-	*	*	*
	3	-	*	-	*	*	*	-	*	*	*
	4	-	*	-	*	-	*	-	*	*	*
	5	-	*	-	*	*	*	-	*	*	*
	6	-	*	-	*	-	*	-	*	*	*
	7	-	*	-	*	-	*	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	0.1	-	0.1	*	0.1	-	0.1	*	0.1
53	1 - 2	-	-	-	*	-	*	-	-	-	*
	3	-	-	-	*	-	*	-	-	-	*
	4	-	-	-	*	-	*	-	-	-	*
	5	-	-	-	*	-	*	-	*	*	*
	6	-	*	-	*	-	*	-	*	*	*
	7	-	*	-	*	-	*	-	-	*	*
	8	-	*	-	-	-	-	-	-	*	*
Total	----	-	*	-	*	-	*	-	*	*	*
63	1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	*	-	-	-	-	-	-
24 - 54	1 - 8	0.1	0.1	-	*	-	*	-	0.1	*	*
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-
81 - 85	1 - 8	*	*	-	*	-	*	-	-	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		0.1	*	-	-	-	-	-	-	-	-
30		0.1	*	-	*	-	-	-	-	-	-
31		0.1	0.1	-	*	-	*	-	-	-	*
32		0.5	0.5	-	0.1	-	*	-	*	-	*
33		2.8	2.6	0.1	0.8	-	0.1	-	0.2	0.3	0.2
34		12.7	8.7	5.5	4.7	*	0.8	-	1.6	1.0	0.8
35		29.4	18.3	14.4	15.4	0.3	4.1	-	11.2	5.2	3.8
36		29.4	25.8	22.9	30.1	4.5	15.2	-	28.8	18.6	14.7
37		21.4	29.2	43.8	35.7	44.4	47.7	-	39.8	45.1	42.1
38		3.3	10.6	9.8	10.2	37.3	26.8	-	14.2	23.8	23.7
39		0.3	3.2	3.0	2.5	12.2	4.7	-	3.8	5.3	8.2
40 & Longer		*	1.0	0.5	0.4	1.3	0.5	-	0.4	0.7	6.4
Average Staple		35.62	36.18	36.49	36.38	37.61	37.12	-	36.66	37.03	37.53
Average Length		1.11	1.13	1.14	1.13	1.18	1.16	-	1.14	1.16	1.17

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 12, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	19.7	9.3	-	0.6	-	*	-	2.1	5.6	1.5
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	-	0.1	-	0.3	-	0.1	-	*	0.2	0.3
Grass - Level 2	-	-	-	*	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	-	*	-	-
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	-	1.5	-	0.8	0.8	0.1
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	*
Other - Level 2	-	*	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	0.1	-	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	*	-	-	-	-	*	*
23	*	*	-	*	-	-	-	-	*	0.1
24	0.1	*	-	*	-	*	-	*	0.2	0.2
25	0.3	0.1	-	*	-	*	-	*	0.6	0.9
26	0.9	0.7	-	0.2	-	0.1	-	0.5	2.9	2.7
27	4.1	2.8	-	1.2	-	0.5	-	3.0	8.9	7.5
28	10.9	8.0	-	5.2	-	3.9	-	12.6	16.2	14.0
29	20.2	14.8	-	14.8	-	15.4	-	30.5	22.4	19.9
30	18.7	17.6	-	21.7	-	28.5	-	30.3	27.2	22.0
31	17.3	17.0	-	17.7	-	26.8	-	15.3	15.1	17.6
32	13.2	14.5	-	12.5	-	15.8	-	5.8	4.0	9.3
33	8.7	11.4	-	11.6	-	6.3	-	1.6	1.5	3.7
34	3.4	7.2	-	9.7	-	2.1	-	0.3	0.6	1.3
35	1.8	3.7	-	4.0	-	0.5	-	0.1	0.3	0.5
36	0.4	1.4	-	1.1	-	0.1	-	*	0.1	0.2
37	*	0.7	-	0.2	-	*	-	*	*	*
38	*	0.2	-	*	-	*	-	-	-	*
39	*	*	-	*	-	*	-	-	-	-
40 & Above	-	*	-	-	-	*	-	-	-	-
Average	30.80	31.44	-	31.59	-	31.09	-	30.12	29.80	30.14
Mike										
2.4 & Below	0.3	*	-	-	-	-	-	-	0.1	*
2.5	0.7	0.2	-	*	-	-	-	*	0.4	0.1
2.6	0.7	0.3	-	*	-	-	-	-	0.9	0.2
2.7	1.2	0.3	-	*	-	-	-	*	1.5	0.3
2.8	1.0	0.4	-	*	-	-	-	*	1.3	0.4
2.9	0.6	0.5	-	*	-	-	-	*	0.7	0.6
3.0	1.1	0.6	-	0.1	-	-	-	*	1.6	0.9
3.1	1.5	0.8	-	0.1	-	-	-	*	0.9	0.9
3.2	1.5	1.1	-	0.3	-	*	-	0.1	0.7	1.3
3.3	1.6	1.4	-	0.5	-	*	-	0.2	0.4	1.6
3.4	2.4	1.9	-	0.9	-	*	-	0.3	1.2	2.0
3.5	2.9	2.5	-	1.3	-	*	-	0.5	2.2	2.5
3.6	3.1	3.5	-	1.9	-	0.1	-	0.9	2.5	3.1
3.7	4.2	4.4	-	2.7	-	0.1	-	1.8	3.9	3.8
3.8	5.3	5.5	-	4.4	-	0.1	-	2.7	5.7	4.6
3.9	5.7	7.0	-	6.7	-	0.2	-	4.2	6.9	5.5
4.0	7.4	8.5	-	9.0	-	0.4	-	5.8	5.8	6.2
4.1	8.6	10.0	-	11.1	-	0.6	-	7.8	6.3	7.0
4.2	8.5	10.6	-	12.7	-	1.0	-	9.9	5.9	8.0
4.3	11.1	10.7	-	12.9	-	1.7	-	11.6	5.9	8.6
4.4	10.7	9.5	-	11.3	-	2.8	-	11.8	8.9	9.2
4.5	9.0	7.7	-	8.8	-	4.1	-	10.7	7.8	9.0
4.6	5.7	5.5	-	6.0	-	6.5	-	9.4	7.2	8.2
4.7	3.2	3.5	-	3.7	-	9.5	-	7.7	6.3	6.5
4.8	1.5	2.0	-	2.3	-	13.4	-	5.5	5.1	4.5
4.9	0.4	0.9	-	1.3	-	16.0	-	3.9	4.8	2.6
5.0	0.1	0.4	-	0.8	-	16.3	-	2.5	4.8	1.4
5.1	*	0.2	-	0.4	-	12.9	-	1.4	0.2	0.6
5.2	-	0.1	-	0.3	-	8.2	-	0.7	0.1	0.3
5.3	-	*	-	0.2	-	4.0	-	0.3	-	0.1
5.4	-	-	-	0.1	-	1.5	-	0.1	-	*
5.5 & Above	-	*	-	0.2	-	0.5	-	*	-	*
Average	4.04	4.11	-	4.23	-	4.88	-	4.38	4.18	4.19

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE

For The Week Ending Feb 12, 2026

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	14.0	7.7	1.9	1.3	-	*	-	2.0	2.4	0.4
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	0.5	0.1	-	0.1	-	*	-	0.1	0.8	0.5
Grass - Level 2	-	*	-	-	-	-	-	-	-	-
Prep - Level 1	*	*	-	*	-	*	-	-	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.5	0.4	0.6	0.3	-	0.1	-	2.9	0.6	0.1
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	*	*
Spindle Twist - Level 2	-	*	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	0.1	*	-	*	*	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	-	*	-	-	-	*	-	-	-	*
23	-	*	-	*	-	*	-	-	0.2	*
24	-	0.1	-	*	-	*	-	-	0.3	*
25	0.1	0.2	0.2	0.1	-	*	-	*	0.5	0.1
26	0.4	0.7	1.0	0.6	-	*	-	0.1	3.5	0.7
27	2.4	2.6	7.6	3.2	-	0.2	-	1.7	10.1	2.6
28	10.4	7.1	17.6	10.7	0.3	1.8	-	6.6	14.2	8.6
29	22.5	14.6	26.4	20.6	7.8	12.4	-	17.9	19.5	16.5
30	25.8	20.2	23.8	25.1	42.9	36.1	-	30.0	20.3	20.7
31	19.2	19.9	13.9	19.9	30.2	32.5	-	20.1	13.2	18.1
32	10.0	15.1	7.4	11.5	7.4	12.2	-	12.6	10.3	11.9
33	4.9	9.8	1.8	5.3	7.5	3.7	-	6.0	5.9	7.6
34	2.4	5.5	0.3	2.1	3.5	0.9	-	3.1	1.6	5.9
35	1.1	2.5	*	0.7	0.3	0.1	-	1.5	0.4	4.2
36	0.5	1.0	-	0.2	*	*	-	0.2	*	2.3
37	0.1	0.4	-	*	-	*	-	*	*	0.7
38	0.1	0.1	-	*	-	*	-	*	*	0.1
39	-	*	-	*	-	-	-	-	*	*
40 & Above	-	-	-	*	-	-	-	-	-	*
Average	30.67	31.28	29.92	30.63	31.22	31.01	-	30.93	30.08	31.29
Mike										
2.4 & Below	-	*	-	-	-	-	-	-	0.1	*
2.5	-	0.1	-	*	-	-	-	*	0.3	*
2.6	*	0.1	-	*	-	-	-	*	0.3	*
2.7	0.2	0.2	-	*	-	*	-	*	0.3	*
2.8	0.5	0.4	-	*	-	*	-	*	0.4	0.2
2.9	0.7	0.6	0.1	*	-	*	-	*	0.2	0.2
3.0	1.4	0.9	0.1	*	-	*	-	*	1.0	0.3
3.1	2.2	1.3	0.1	*	-	*	-	0.1	0.9	0.5
3.2	2.9	1.8	1.1	0.1	-	*	-	0.1	2.5	0.8
3.3	3.4	2.4	0.5	0.2	-	*	-	0.1	2.1	0.7
3.4	3.8	3.0	1.0	0.3	-	0.1	-	0.1	2.2	0.9
3.5	4.2	3.8	0.4	0.6	*	0.1	-	0.2	3.1	1.4
3.6	5.7	4.4	1.8	1.1	-	0.2	-	0.4	3.8	1.9
3.7	7.9	5.0	3.9	1.9	*	0.4	-	0.5	4.8	2.8
3.8	8.2	5.6	7.0	2.8	0.3	0.6	-	0.7	6.3	3.6
3.9	8.9	6.1	8.6	4.0	0.6	1.0	-	1.1	8.5	5.0
4.0	7.9	6.5	13.1	5.6	2.1	1.7	-	1.9	10.8	6.4
4.1	7.5	6.9	14.0	7.4	4.3	2.6	-	3.5	9.3	7.9
4.2	7.5	7.3	10.1	9.1	4.2	4.0	-	4.5	9.4	9.1
4.3	6.9	7.7	6.2	10.0	6.1	5.8	-	5.6	11.4	9.4
4.4	5.2	7.7	4.5	10.3	10.5	8.2	-	6.6	9.9	9.1
4.5	4.2	7.4	3.5	9.9	12.1	11.0	-	8.6	5.9	9.2
4.6	3.5	6.6	2.6	9.1	14.6	13.9	-	9.7	2.8	8.6
4.7	2.7	5.4	1.1	8.2	17.9	15.2	-	10.6	1.9	7.0
4.8	2.1	3.8	5.7	6.5	11.9	13.8	-	11.4	0.9	5.2
4.9	1.2	2.4	3.6	4.9	8.7	10.1	-	10.5	0.6	3.9
5.0	0.6	1.4	7.6	3.4	4.6	6.3	-	8.3	0.2	2.4
5.1	0.4	0.7	2.9	2.2	1.8	3.1	-	6.9	0.1	1.4
5.2	0.2	0.4	0.5	1.2	0.2	1.2	-	4.0	-	0.9
5.3	*	0.2	-	0.6	*	0.4	-	2.2	*	0.6
5.4	-	0.1	-	0.2	*	0.1	-	1.1	-	0.3
5.5 & Above	-	0.1	*	0.1	-	*	-	1.1	-	0.3
Average	3.95	4.12	4.24	4.41	4.59	4.62	-	4.67	4.02	4.32

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 12, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	0.3	*	-	-	-	-	-	-	0.1	*
2.5 - 2.6	1.4	0.4	-	*	-	-	-	*	1.3	0.3
2.7 - 2.9	2.8	1.3	-	0.1	-	-	-	*	3.5	1.3
3.0 - 3.2	4.1	2.5	-	0.5	-	*	-	0.2	3.3	3.1
3.3 - 3.4	4.0	3.3	-	1.4	-	*	-	0.5	1.6	3.6
3.5 - 3.6	6.1	6.0	-	3.1	-	0.1	-	1.5	4.7	5.6
3.7 - 4.2	39.7	46.0	-	46.6	-	2.5	-	32.1	34.4	35.1
4.3 - 4.9	41.5	39.9	-	46.4	-	54.0	-	60.6	46.0	48.6
5.0 - 5.2	0.1	0.6	-	1.4	-	37.4	-	4.6	5.2	2.3
5.3 & Above	-	*	-	0.5	-	6.1	-	0.4	-	0.2
Average	4.04	4.11	-	4.23	-	4.88	-	4.38	4.18	4.19
Leaf										
1 - 2	44.4	57.5	-	24.8	-	3.8	-	8.4	75.5	86.3
3	33.3	26.7	-	49.7	-	37.7	-	52.5	22.8	12.0
4	13.3	9.1	-	21.1	-	45.4	-	33.2	1.7	1.4
5	4.7	4.1	-	4.0	-	12.0	-	5.4	0.1	0.3
6	3.0	1.8	-	0.5	-	1.1	-	0.4	-	0.1
7	1.0	0.6	-	0.1	-	*	-	*	-	*
8	0.2	0.1	-	*	-	-	-	*	-	-
Average	2.84	2.52	-	3.03	-	3.69	-	3.37	1.93	1.75
HVI Trash 1/										
00	*	*	-	*	-	-	-	-	0.5	0.7
01	16.8	28.4	-	5.1	-	0.3	-	0.6	46.4	59.6
02	31.7	32.4	-	22.5	-	4.6	-	10.2	34.9	29.6
03	19.3	15.7	-	27.9	-	14.9	-	24.6	13.9	7.0
04	11.4	8.3	-	20.4	-	22.9	-	26.2	3.4	2.0
05	7.1	4.7	-	12.1	-	22.0	-	18.8	0.8	0.7
06	3.9	2.9	-	6.5	-	15.8	-	10.7	0.1	0.3
07	2.5	2.0	-	3.1	-	9.7	-	5.2	*	0.1
08	1.7	1.5	-	1.4	-	5.2	-	2.3	*	0.1
09	1.5	1.1	-	0.6	-	2.6	-	0.9	-	*
10	1.1	0.8	-	0.3	-	1.2	-	0.4	-	*
11	1.0	0.6	-	0.1	-	0.5	-	0.2	-	*
12	0.7	0.5	-	0.1	-	0.2	-	0.1	-	*
13	0.5	0.3	-	*	-	0.1	-	*	-	*
14	0.3	0.2	-	*	-	*	-	*	-	*
15	0.2	0.1	-	*	-	*	-	*	-	-
16	0.1	0.1	-	*	-	-	-	*	-	*
17	0.1	0.1	-	*	-	-	-	*	-	*
18 & Above	0.1	0.1	-	*	-	-	-	*	-	-
Average	0.34	0.29	-	0.36	-	0.50	-	0.43	0.18	0.15
UNIFORMITY 2/										
74 & Below	*	*	-	*	-	-	-	*	-	*
75	0.1	0.1	-	*	-	-	-	*	-	0.1
76	0.5	0.2	-	*	-	*	-	*	0.1	0.5
77	1.9	0.8	-	0.1	-	*	-	*	0.2	2.3
78	7.1	3.3	-	0.7	-	0.2	-	0.5	3.8	9.9
79	20.8	13.0	-	3.7	-	1.0	-	2.9	14.5	24.8
80	34.0	28.1	-	13.4	-	7.0	-	12.0	34.3	35.9
81	22.5	29.0	-	30.1	-	28.1	-	28.8	33.3	21.6
82	9.5	16.8	-	31.1	-	37.9	-	35.0	13.0	4.5
83	3.2	6.9	-	16.1	-	20.5	-	18.2	0.8	0.5
84	0.4	1.6	-	4.3	-	5.1	-	2.3	*	*
85 & Above	*	0.1	-	0.4	-	0.2	-	0.2	-	*
Average	80.54	81.12	-	82.00	-	82.30	-	82.04	80.85	80.23
Tenderable 3/	71.6	80.2	-	88.1	-	53.0	-	90.5	78.1	84.1
SAMPLES CLASSED										
Week	36,184		-		-		-		10,873	
Season		1,083,789		1,524,522		951,045		1,110,530		580,272

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 12, 2026

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	-	*	-	-	-	-	-	-	0.1	*
2.5 - 2.6	*	0.2	-	*	-	-	-	*	0.7	*
2.7 - 2.9	1.4	1.2	0.1	*	-	*	-	0.1	0.9	0.4
3.0 - 3.2	6.5	4.0	1.3	0.1	-	*	-	0.1	4.5	1.6
3.3 - 3.4	7.2	5.4	1.5	0.5	-	0.1	-	0.2	4.2	1.6
3.5 - 3.6	9.9	8.2	2.2	1.8	*	0.3	-	0.6	6.9	3.3
3.7 - 4.2	48.0	37.3	56.8	30.8	11.5	10.4	-	12.3	49.0	34.8
4.3 - 4.9	25.8	40.9	27.1	58.9	81.8	78.1	-	63.0	33.4	52.3
5.0 - 5.2	1.2	2.5	11.0	6.8	6.6	10.6	-	19.3	0.3	4.7
5.3 & Above	*	0.3	*	1.0	*	0.6	-	4.3	*	1.2
Average	3.95	4.12	4.24	4.41	4.59	4.62	-	4.67	4.02	4.32
Leaf										
1 - 2	76.4	68.5	13.0	15.3	1.5	5.8	-	12.7	25.3	36.2
3	18.2	25.9	65.0	57.9	52.7	48.7	-	48.8	45.3	38.5
4	4.0	4.4	20.7	23.7	37.5	37.0	-	30.5	20.5	17.7
5	1.2	0.9	1.2	3.0	7.7	7.6	-	6.9	5.7	5.8
6	0.1	0.2	0.1	0.2	0.5	0.8	-	1.0	2.2	1.5
7	*	*	-	*	-	0.1	-	*	0.8	0.3
8	-	*	-	*	-	-	-	-	0.3	*
Average	2.06	2.21	3.10	3.15	3.53	3.49	-	3.34	3.13	2.92
HVI Trash 1/										
00	0.1	*	-	-	-	*	-	-	-	*
01	41.4	33.2	0.5	1.6	*	0.5	-	1.6	8.5	13.8
02	37.9	41.5	16.3	19.8	3.2	7.3	-	14.0	22.0	27.9
03	11.9	15.5	32.7	31.4	22.5	21.2	-	24.1	25.4	21.8
04	4.5	5.5	27.6	23.6	31.4	26.2	-	23.3	18.2	14.6
05	2.2	2.2	14.6	12.9	20.7	20.2	-	16.3	11.3	9.1
06	0.9	1.0	5.6	6.1	11.5	12.2	-	9.7	6.0	5.5
07	0.7	0.5	1.8	2.7	5.8	6.5	-	5.3	3.5	3.3
08	0.3	0.3	0.7	1.1	2.9	3.1	-	2.7	2.0	1.9
09	0.2	0.1	0.2	0.5	1.4	1.5	-	1.5	1.2	1.1
10	0.1	0.1	*	0.2	0.4	0.7	-	0.8	0.7	0.6
11	*	0.1	-	0.1	0.1	0.3	-	0.4	0.6	0.3
12	-	*	-	*	0.1	0.1	-	0.2	0.1	0.1
13	*	*	*	*	-	0.1	-	0.1	0.2	0.1
14	-	*	-	*	-	*	-	*	0.1	*
15	-	*	-	*	-	*	-	-	*	*
16	-	*	-	*	-	-	-	-	0.1	*
17	-	*	-	*	-	-	-	*	*	*
18 & Above	-	*	-	*	-	-	-	-	*	*
Average	0.20	0.21	0.37	0.37	0.45	0.46	-	0.42	0.37	0.33
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	-	-	-	-
75	*	*	-	*	-	-	-	-	*	*
76	0.2	0.2	-	*	-	*	-	-	*	*
77	1.4	1.1	0.3	0.1	-	*	-	-	0.4	0.1
78	7.1	4.4	1.4	0.8	*	0.1	-	0.2	3.1	0.8
79	23.0	14.2	4.4	5.1	*	0.5	-	1.9	11.2	3.8
80	34.4	29.9	22.4	20.1	0.4	3.9	-	10.6	30.1	17.7
81	25.1	31.7	31.1	36.4	12.4	20.8	-	32.1	35.1	33.6
82	7.9	14.7	29.4	27.8	42.4	45.7	-	37.3	17.5	31.4
83	0.8	3.1	9.5	8.4	38.1	26.1	-	15.7	2.2	10.5
84	*	0.4	1.4	1.2	6.4	2.7	-	2.1	0.4	1.9
85 & Above	-	0.1	*	0.1	0.2	0.2	-	0.1	0.1	0.2
Average	80.46	80.90	81.61	81.60	82.83	82.47	-	82.05	81.06	81.76
Tenderable 3/	71.1	78.4	83.0	88.6	91.6	83.5	-	69.3	85.3	85.7
SAMPLES CLASSED										
Week	9,157		3,525		10,992		-		19,478	
Season	2,497,373		2,193,971		2,330,069		283,396		346,740	

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 12, 2026

Color Grade	Leaf	VISALIA			Quality Designation	VISALIA	
		Week	Season			Week	Season
01	1	6.3	6.3		MIKE		
	2	8.5	7.6		2.4 & Below	-	-
	3	0.1	0.2		2.5 - 2.6	-	-
	4	-	-		2.7 - 2.9	-	0.2
	5	-	-		3.0 - 3.2	3.9	1.6
	6	-	-		3.3 - 3.4	5.4	2.8
	7	-	-		3.5 - 3.6	13.7	8.5
Total -----		14.9	14.1		3.7 - 4.2	68.3	82.9
02	1	23.5	7.5		4.3 - 4.9	8.7	4.0
	2	28.2	34.8		5.0 - 5.2	-	*
	3	5.9	8.1		5.3 & Above	-	-
	4	0.1	0.2		Average	3.87	3.89
	5	-	*		ALL RANGE MIKE		
	6	-	-		2.4 & Below	-	-
	7	-	-		2.5	-	-
Total -----		57.8	50.7		2.6	-	-
03	1	2.5	0.7		2.7	-	*
	2	11.5	13.1		2.8	-	*
	3	8.7	15.6		2.9	-	0.1
	4	1.3	1.7		3.0	-	0.3
	5	0.1	*		3.1	1.9	0.6
	6	-	*		3.2	2.0	0.8
	7	-	-		3.3	1.2	1.0
Total -----		24.1	31.1		3.4	4.3	1.8
04	1	0.1	*		3.5	4.1	3.0
	2	0.8	0.6		3.6	9.6	5.5
	3	0.7	2.0		3.7	11.9	9.6
	4	0.6	0.8		3.8	13.4	15.0
	5	0.3	0.1		3.9	10.6	20.3
	6	0.1	*		4.0	9.0	19.2
	7	-	-		4.1	12.3	12.4
Total -----		2.6	3.4		4.2	11.1	6.4
05	1	0.1	*		4.3	5.1	2.6
	2	0.1	0.1		4.4	3.1	1.0
	3	0.2	0.2		4.5	0.4	0.4
	4	0.4	0.2		4.6	-	0.1
	5	*	*		4.7	*	*
	6	-	*		4.8	-	*
	7	-	-		4.9	-	*
Total -----		0.7	0.5		5.0	-	*
06	1	-	-		5.1	-	*
	2	-	*		5.2	-	-
	3	-	0.1		5.3 & Above	-	-
	4	-	*		Average	3.87	3.89
	5	-	*		STRENGTH 1/		
	6	-	*		36 & Below	3.7	2.8
	7	-	-		37	5.4	4.8
Total -----		-	0.1		38	4.2	3.8
07	1	-	-		39	0.5	1.7
	2	-	-		40	1.3	2.0
	3	-	*		41	7.9	5.6
	4	-	*		42	15.6	11.0
	5	-	*		43	15.1	16.5
	6	-	*		44	14.9	19.3
	7	-	-		45	16.7	16.5
Total -----		-	*		46	7.6	9.8
STAPLE					47	5.9	4.1
44 & Shorter		4.7	2.9		48 & Above	1.0	2.0
46		16.1	11.3		Average	43.27	43.50
48		40.1	45.9		UNIFORMITY		
50		37.4	37.8		83 & Below	1.7	1.6
52 & Longer		1.8	2.0		84	11.8	11.8
Average Staple		48.31	48.49		85	20.7	34.5
Average Length		1.40	1.41		86	57.5	45.7
EXTRANEIOUS MATTER					87	8.2	5.9
Bark		*	*		88 & Above	0.2	0.5
Grass		0.9	0.3		Average	86.04	85.89
Spindle Twist		0.1	0.1		Samples Classed		
Preparation		-	*		Week	5,580	
All Other		-	*		Season		376,329

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.