



State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
<i>UPLAND</i>								
AL	3	86.9	69.1	1,745	21	89.9	77.8	549,869
AR*	-	-	-	-	26	70.4	42.8	1,411,880
AZ	5	89.1	81.4	6,848	10	86.6	70.3	223,936
CA*	-	-	-	-	10	87.1	75.9	92,369
FL	-	-	-	-	4	91.0	76.3	90,067
GA	4	76.9	52.0	1,167	53	88.4	74.2	1,737,700
KS	3	13.4	7.70	4,287	3	32.9	25.0	158,445
LA	-	-	-	-	14	71.5	47.6	223,299
MO*	-	-	-	-	16	86.7	65.2	680,258
MS*	-	-	-	-	30	63.7	36.5	706,511
NC	-	-	-	-	26	90.7	78.7	653,675
NM*	-	-	-	-	2	81.6	67.3	12,080
OK	7	85.9	75.2	17,330	10	91.4	79.5	444,454
SC	-	-	-	-	10	86.4	73.5	283,934
TN	-	-	-	-	17	82.3	63.4	340,307
TX	23	74.2	54.3	21,174	144	82.3	62.1	5,187,511
VA	-	-	-	-	4	96.1	90.4	172,921
<b>United States</b>	<b>50</b>	<b>77.2</b>	<b>61.7</b>	<b>67,615</b>	<b>400</b>	<b>81.7</b>	<b>62.8</b>	<b>12,969,216</b>
<i>AMERICAN PIMA</i>								
AZ	2			906	2			21,417
CA	2			2,073	10			304,332
NM	-			-	-			-
TX*	-			-	5			34,679
United States	5			3,346	18			379,675
<b>United States</b>	<b>53</b>			<b>70,961</b>	<b>408</b>			<b>13,348,891</b>
<b>all cotton</b>								

\* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

Source: USDA AMS Cotton and Tobacco Market News

Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov

<https://www.ams.usda.gov/market-news/cotton>

<https://mymarketnews.ams.usda.gov/cottonmn@ams.usda.gov>

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Feb 19, 2026**

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1-2	-	2.2	-	0.1	1.2	16.8	-	18.3	-	1.7	2.4	1.5
	3	-	1.3	-	0.1	*	3.2	-	6.7	-	0.5	2.4	1.2
	4	-	*	-	*	-	0.2	-	0.4	-	*	-	*
	5	-	*	-	-	-	*	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>3.5</b>	-	<b>0.2</b>	<b>1.3</b>	<b>20.2</b>	-	<b>25.4</b>	-	<b>2.2</b>	<b>4.8</b>	<b>2.7</b>
31	1-2	0.3	9.3	-	1.1	2.6	9.3	-	14.0	-	3.1	11.2	7.8
	3	5.2	27.7	-	9.1	2.4	11.7	-	11.1	-	12.5	26.1	21.9
	4	2.7	7.1	-	3.4	1.0	2.2	-	3.5	-	2.8	1.9	4.2
	5	0.1	0.5	-	0.1	*	0.2	-	0.6	-	0.1	-	0.2
	6	-	*	-	*	-	*	-	0.1	-	-	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	<b>8.3</b>	<b>44.7</b>	-	<b>13.7</b>	<b>6.0</b>	<b>23.4</b>	-	<b>29.3</b>	-	<b>18.4</b>	<b>39.2</b>	<b>34.1</b>
41	1-2	1.0	3.3	-	0.8	2.7	2.6	-	7.0	-	2.8	12.2	5.3
	3	31.1	22.6	-	26.1	38.4	16.9	-	22.6	-	37.0	35.6	32.4
	4	38.1	15.6	-	35.2	27.6	14.3	-	7.2	-	28.9	4.5	16.3
	5	5.3	2.8	-	8.5	4.5	4.4	-	1.6	-	4.0	0.3	2.0
	6	0.7	0.2	-	0.7	2.0	0.7	-	0.3	-	0.2	-	0.1
	7	-	*	-	*	0.7	0.1	-	-	-	*	-	*
	8	-	-	-	-	0.1	*	-	-	-	-	-	-
<b>Total</b>	----	<b>76.2</b>	<b>44.5</b>	-	<b>71.3</b>	<b>76.1</b>	<b>39.0</b>	-	<b>38.7</b>	-	<b>72.9</b>	<b>52.5</b>	<b>56.2</b>
51	1-2	0.5	0.4	-	*	*	0.1	-	0.1	-	0.1	-	0.2
	3	2.8	2.4	-	2.3	4.9	2.0	-	0.6	-	1.7	1.0	2.2
	4	6.9	1.8	-	4.8	8.1	3.7	-	0.6	-	2.3	0.3	2.2
	5	2.9	0.4	-	2.2	1.9	2.5	-	0.2	-	0.6	-	0.5
	6	0.5	*	-	0.4	0.8	1.0	-	*	-	0.1	-	0.1
	7	-	*	-	0.1	0.2	0.3	-	*	-	*	-	*
	8	-	*	-	-	0.3	*	-	-	-	-	-	*
<b>Total</b>	----	<b>13.6</b>	<b>4.9</b>	-	<b>9.8</b>	<b>16.3</b>	<b>9.6</b>	-	<b>1.6</b>	-	<b>4.8</b>	<b>1.4</b>	<b>5.1</b>
61	1-2	-	*	-	*	-	*	-	-	-	-	-	*
	3	-	0.1	-	*	*	*	-	*	-	*	0.2	*
	4	-	0.1	-	*	*	*	-	*	-	*	-	*
	5	-	*	-	*	-	*	-	-	-	*	-	*
	6	-	*	-	*	-	*	-	-	-	*	-	*
	7	-	-	-	-	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	*
<b>Total</b>	----	-	<b>0.2</b>	-	<b>*</b>	<b>*</b>	<b>*</b>	-	<b>*</b>	-	<b>*</b>	<b>0.2</b>	<b>*</b>
71	1-2	-	-	-	*	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	*	-	-	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	-	-	<b>*</b>	-	-	-	-	-	-	-	-
12 & 22	1-2	-	0.1	-	*	-	2.7	-	0.2	-	*	-	*
	3	-	*	-	*	-	1.3	-	0.2	-	*	-	0.1
	4	-	*	-	*	-	0.2	-	*	-	-	-	*
	5	-	-	-	*	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>0.1</b>	-	<b>*</b>	-	<b>4.2</b>	-	<b>0.4</b>	-	<b>*</b>	-	<b>0.1</b>
32	1-2	-	0.1	-	*	-	0.1	-	0.3	-	*	0.3	*
	3	-	0.4	-	0.1	0.2	0.4	-	0.6	-	0.2	0.8	0.2
	4	-	0.1	-	0.1	-	0.3	-	0.5	-	*	-	0.1
	5	-	*	-	*	-	0.1	-	0.3	-	-	-	*
	6	-	*	-	*	-	*	-	0.1	-	-	-	*
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>0.6</b>	-	<b>0.2</b>	<b>0.2</b>	<b>0.9</b>	-	<b>1.9</b>	-	<b>0.3</b>	<b>1.0</b>	<b>0.4</b>
42	1-2	-	*	-	*	-	*	-	0.1	-	0.1	-	*
	3	0.1	0.4	-	1.0	-	0.4	-	0.9	-	0.7	0.2	0.6
	4	0.1	0.5	-	1.5	*	0.6	-	0.4	-	0.4	0.2	0.4
	5	-	0.1	-	0.7	*	0.3	-	0.3	-	*	0.4	0.1
	6	-	*	-	0.1	*	0.1	-	0.1	-	*	-	*
	7	-	*	-	*	-	*	-	-	-	*	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	<b>0.2</b>	<b>1.1</b>	-	<b>3.2</b>	<b>0.1</b>	<b>1.4</b>	-	<b>1.9</b>	-	<b>1.2</b>	<b>0.8</b>	<b>1.1</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Feb 19, 2026**

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1-2	-	*	-	*	-	*	-	*	-	*	-	*
	3	0.2	0.1	-	0.2	-	0.1	-	0.1	-	0.1	0.1	*
	4	-	0.1	-	0.6	*	0.3	-	0.2	-	0.1	-	0.1
	5	-	0.1	-	0.3	*	0.3	-	0.1	-	*	-	*
	6	-	*	-	0.1	-	0.2	-	0.1	-	*	-	*
	7	-	*	-	*	-	*	-	*	-	*	-	*
	8	-	-	-	-	-	*	-	*	-	-	-	*
<b>Total</b>	----	<b>0.2</b>	<b>0.3</b>	-	<b>1.3</b>	<b>0.1</b>	<b>0.9</b>	-	<b>0.5</b>	-	<b>0.2</b>	<b>0.1</b>	<b>0.2</b>
62	1-2	-	*	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	*	-	-	-	*	-	*	-	*
	4	-	*	-	*	-	*	-	*	-	*	-	*
	5	-	*	-	*	-	*	-	*	-	*	-	*
	6	-	*	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	*	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	*	-	-	-	-	-	*
<b>Total</b>	----	-	*	-	*	-	*	-	*	-	*	-	*
13 & 23	1-2	-	*	-	-	-	0.1	-	*	-	-	-	*
	3	-	*	-	-	-	*	-	*	-	-	-	*
	4	-	*	-	-	-	*	-	-	-	-	-	*
	5	-	-	-	-	-	-	-	-	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	*	-	-	-	<b>0.2</b>	-	*	-	-	-	*
33	1-2	-	*	-	-	-	*	-	*	-	-	-	*
	3	-	*	-	*	-	*	-	*	-	-	-	*
	4	-	*	-	*	-	*	-	*	-	-	-	*
	5	-	*	-	*	-	*	-	*	-	-	-	*
	6	-	*	-	-	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	*	-	*	-	*	-	<b>0.1</b>	-	-	-	*
43	1-2	-	-	-	*	-	-	-	*	-	-	-	*
	3	-	*	-	*	-	*	-	0.1	-	*	-	*
	4	-	*	-	*	-	*	-	0.1	-	*	-	*
	5	-	*	-	*	-	*	-	*	-	-	-	*
	6	-	*	-	*	-	*	-	*	-	-	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	*	-	<b>0.1</b>	-	<b>0.1</b>	-	<b>0.1</b>	-	*	-	<b>0.1</b>
53	1-2	0.1	*	-	-	-	*	-	-	-	-	-	-
	3	0.9	*	-	*	-	*	-	*	-	*	-	*
	4	0.5	*	-	*	-	*	-	*	-	*	-	*
	5	-	*	-	*	*	*	-	*	-	*	-	*
	6	-	*	-	*	-	*	-	*	-	-	-	*
	7	-	-	-	*	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	*	-	-	-	-	-	-
<b>Total</b>	----	<b>1.4</b>	<b>0.1</b>	-	*	*	*	-	*	-	*	-	*
63	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	-	-	-	-	-	-	-	-	-
	4	-	*	-	-	-	-	-	-	-	-	-	-
	5	0.1	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	<b>0.1</b>	*	-	-	-	-	-	-	-	-	-	-
24 - 54	1-8	-	*	-	*	-	*	-	*	-	-	-	*
25 - 35	1-8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1-8	0.1	*	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	*
31		-	*	-	*	-	*	-	-	-	*	-	*
32		-	*	-	*	*	*	-	-	-	*	-	0.1
33		-	0.7	-	0.1	-	*	-	0.1	-	0.2	-	0.9
34		0.2	3.6	-	0.3	2.1	0.5	-	0.4	-	2.4	14.1	4.9
35		6.2	12.3	-	2.6	10.7	3.2	-	3.3	-	12.4	33.0	16.0
36		30.0	24.6	-	13.8	32.3	13.3	-	21.2	-	29.2	14.3	31.0
37		60.1	40.9	-	50.3	36.5	44.9	-	45.6	-	35.5	29.6	34.5
38		3.3	14.3	-	27.0	14.4	27.2	-	19.4	-	15.3	7.5	9.7
39		0.2	3.1	-	5.4	3.4	8.7	-	9.0	-	4.4	0.9	2.5
40 & Longer		-	0.5	-	0.6	0.5	2.0	-	1.1	-	0.6	-	0.4
<b>Average Staple</b>		<b>36.61</b>	<b>36.59</b>	-	<b>37.19</b>	<b>36.63</b>	<b>37.29</b>	-	<b>37.12</b>	-	<b>36.64</b>	<b>35.83</b>	<b>36.34</b>
<b>Average Length</b>		<b>1.14</b>	<b>1.14</b>	-	<b>1.16</b>	<b>1.14</b>	<b>1.17</b>	-	<b>1.16</b>	-	<b>1.14</b>	<b>1.12</b>	<b>1.13</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Feb 19, 2026**

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1-2	3.1	4.1	-	4.5	-	*	-	2.0	-	0.4	-	40.4
	3	6.6	5.1	-	2.6	-	*	-	1.8	-	0.3	-	10.9
	4	0.8	1.1	-	*	-	*	-	*	-	*	-	0.8
	5	-	0.1	-	-	-	-	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	<b>----</b>	<b>10.5</b>	<b>10.4</b>	<b>-</b>	<b>7.1</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>3.8</b>	<b>-</b>	<b>0.8</b>	<b>-</b>	<b>52.2</b>
31	1-2	0.7	0.9	-	9.2	-	1.5	-	3.4	-	5.7	-	7.6
	3	4.5	7.7	-	36.6	-	9.0	-	20.3	-	20.2	-	15.3
	4	2.5	9.4	-	12.3	-	1.8	-	8.6	-	5.8	-	7.3
	5	0.3	2.6	-	0.8	-	*	-	0.6	-	0.3	-	1.1
	6	-	0.3	-	*	-	*	-	*	-	*	-	0.1
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	<b>----</b>	<b>8.0</b>	<b>20.9</b>	<b>-</b>	<b>58.9</b>	<b>-</b>	<b>12.3</b>	<b>-</b>	<b>32.9</b>	<b>-</b>	<b>32.0</b>	<b>-</b>	<b>31.4</b>
41	1-2	-	*	-	0.5	-	2.4	-	0.9	-	3.1	-	*
	3	2.9	1.6	-	10.1	-	38.1	-	18.8	-	30.0	-	0.6
	4	8.6	6.8	-	16.2	-	26.6	-	26.1	-	24.6	-	1.2
	5	5.7	9.3	-	4.9	-	3.2	-	7.3	-	4.5	-	1.3
	6	3.9	4.5	-	0.3	-	0.1	-	0.6	-	0.4	-	0.6
	7	0.6	0.9	-	-	-	*	-	*	-	*	-	0.1
	8	*	*	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	<b>----</b>	<b>21.7</b>	<b>23.2</b>	<b>-</b>	<b>32.0</b>	<b>-</b>	<b>70.4</b>	<b>-</b>	<b>53.6</b>	<b>-</b>	<b>62.5</b>	<b>-</b>	<b>3.8</b>
51	1-2	-	-	-	*	-	0.2	-	*	-	*	-	-
	3	-	-	-	*	-	4.5	-	1.1	-	0.8	-	-
	4	*	*	-	0.4	-	6.0	-	3.3	-	1.7	-	*
	5	*	0.4	-	0.3	-	1.4	-	1.5	-	0.8	-	*
	6	0.2	1.1	-	0.1	-	0.1	-	0.2	-	0.2	-	*
	7	0.2	0.8	-	-	-	*	-	*	-	*	-	-
	8	-	0.2	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	<b>----</b>	<b>0.5</b>	<b>2.6</b>	<b>-</b>	<b>0.7</b>	<b>-</b>	<b>12.1</b>	<b>-</b>	<b>6.1</b>	<b>-</b>	<b>3.6</b>	<b>-</b>	<b>*</b>
61	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	<b>----</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>-</b>
71	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	<b>----</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>-</b>
12 & 22	1-2	0.7	1.2	-	0.1	-	-	-	*	-	*	-	2.4
	3	7.7	3.8	-	*	-	*	-	*	-	*	-	3.0
	4	3.7	1.9	-	*	-	-	-	*	-	*	-	0.3
	5	0.3	0.2	-	*	-	-	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	<b>----</b>	<b>12.4</b>	<b>7.1</b>	<b>-</b>	<b>0.1</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>5.7</b>
32	1-2	0.1	0.1	-	0.1	-	*	-	*	-	*	-	0.6
	3	4.1	3.1	-	0.3	-	0.1	-	0.2	-	0.1	-	1.6
	4	8.1	5.5	-	0.2	-	*	-	0.1	-	0.1	-	2.7
	5	3.4	2.9	-	*	-	*	-	*	-	*	-	0.8
	6	0.4	0.6	-	*	-	-	-	*	-	-	-	0.1
	7	-	0.1	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	<b>----</b>	<b>16.1</b>	<b>12.2</b>	<b>-</b>	<b>0.5</b>	<b>-</b>	<b>0.1</b>	<b>-</b>	<b>0.3</b>	<b>-</b>	<b>0.3</b>	<b>-</b>	<b>5.8</b>
42	1-2	-	*	-	*	-	0.1	-	*	-	*	-	-
	3	0.3	0.7	-	0.1	-	1.3	-	0.6	-	0.3	-	*
	4	0.9	3.4	-	0.4	-	1.4	-	1.2	-	0.3	-	0.1
	5	3.4	5.5	-	0.1	-	0.4	-	0.5	-	0.1	-	0.1
	6	5.2	4.1	-	*	-	0.1	-	0.1	-	*	-	0.1
	7	3.1	1.4	-	-	-	*	-	*	-	*	-	*
	8	0.5	0.2	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	<b>----</b>	<b>13.4</b>	<b>15.4</b>	<b>-</b>	<b>0.6</b>	<b>-</b>	<b>3.3</b>	<b>-</b>	<b>2.4</b>	<b>-</b>	<b>0.7</b>	<b>-</b>	<b>0.3</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Feb 19, 2026**

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 52	1-2	-	-	-	-	-	*	-	*	-	*	-	-
	3	-	-	-	*	-	0.5	-	0.1	-	*	-	-
	4	-	*	-	*	-	0.7	-	0.2	-	*	-	-
	5	0.1	0.1	-	*	-	0.3	-	0.3	-	*	-	-
	6	0.7	0.3	-	*	-	*	-	0.1	-	*	-	-
	7	0.7	0.5	-	-	-	*	-	*	-	*	-	-
	8	1.5	0.3	-	-	-	-	-	-	-	*	-	-
	<b>Total</b>	----	<b>3.1</b>	<b>1.2</b>	-	*	-	<b>1.6</b>	-	<b>0.7</b>	-	<b>0.1</b>	-
62	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	-	*	-	-	-	*	-	*	-	*	-
13 & 23	1-2	*	0.1	-	-	-	-	-	-	-	*	-	-
	3	3.7	0.8	-	-	-	-	-	-	-	*	-	*
	4	2.5	0.6	-	-	-	-	-	-	-	*	-	*
	5	*	0.1	-	-	-	-	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>6.3</b>	<b>1.6</b>	-	-	-	-	-	-	-	*	-
33	1-2	-	*	-	-	-	*	-	*	-	*	-	*
	3	0.7	0.4	-	*	-	*	-	*	-	*	-	0.1
	4	3.6	0.9	-	*	-	*	-	*	-	*	-	0.3
	5	1.1	0.5	-	*	-	-	-	-	-	*	-	0.2
	6	0.1	0.1	-	-	-	-	-	-	-	*	-	*
	7	*	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	<b>5.5</b>	<b>2.0</b>	-	*	-	*	-	*	-	*	-
43	1-2	-	-	-	*	-	*	-	-	-	*	-	-
	3	*	0.1	-	*	-	*	-	*	-	*	-	*
	4	0.3	0.5	-	*	-	*	-	*	-	*	-	*
	5	1.0	1.2	-	*	-	*	-	*	-	*	-	*
	6	0.9	0.9	-	-	-	*	-	*	-	*	-	*
	7	0.3	0.4	-	-	-	-	-	-	-	*	-	-
	8	0.1	0.1	-	-	-	-	-	-	-	*	-	-
	<b>Total</b>	----	<b>2.5</b>	<b>3.2</b>	-	*	-	<b>0.1</b>	-	*	-	*	-
53	1-2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	*	-	-	-	*	-	*	-	*	-	-
	4	-	*	-	-	-	*	-	*	-	*	-	-
	5	-	*	-	-	-	*	-	*	-	*	-	-
	6	-	*	-	-	-	*	-	*	-	*	-	-
	7	-	0.1	-	-	-	-	-	*	-	*	-	-
	8	*	0.1	-	-	-	-	-	-	-	*	-	-
	<b>Total</b>	----	*	<b>0.2</b>	-	-	-	*	-	*	-	*	-
63	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
	<b>Total</b>	----	-	*	-	-	-	-	-	*	-	-	-
24 - 54	1-8	-	0.1	-	-	-	*	-	-	-	*	-	-
25 - 35	1-8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1-8	-	*	-	-	-	*	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		-	*	-	-	-	-	-	*	-	*	-	-
32		*	*	-	-	-	*	-	*	-	*	-	-
33		0.2	0.2	-	0.1	-	*	-	0.2	-	0.1	-	*
34		2.5	1.2	-	1.1	-	0.2	-	2.1	-	1.4	-	2.3
35		13.0	4.9	-	10.0	-	1.8	-	11.5	-	8.3	-	10.7
36		25.8	13.4	-	26.9	-	10.4	-	27.7	-	24.4	-	14.0
37		34.4	33.8	-	42.1	-	49.0	-	36.4	-	48.7	-	29.6
38		16.6	30.9	-	15.0	-	33.2	-	15.0	-	14.1	-	36.7
39		7.1	13.9	-	4.4	-	4.9	-	5.4	-	2.7	-	5.8
40 & Longer		0.4	1.8	-	0.4	-	0.3	-	1.5	-	0.3	-	0.8
<b>Average Staple</b>		<b>36.72</b>	<b>37.37</b>	-	<b>36.75</b>	-	<b>37.29</b>	-	<b>36.72</b>	-	<b>36.74</b>	-	<b>37.09</b>
<b>Average Length</b>		<b>1.14</b>	<b>1.17</b>	-	<b>1.15</b>	-	<b>1.17</b>	-	<b>1.15</b>	-	<b>1.15</b>	-	<b>1.16</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Feb 19, 2026**

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA		
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	
Color 11 & 21	1-2	Pct. 34.5	Pct. 43.5	Pct. -	Pct. 0.3	Pct. -	Pct. 0.4	Pct. 26.5	Pct. 44.3	Pct. -	Pct. 0.9	
	3	6.1	7.0	-	0.4	-	0.1	7.1	12.9	-	1.3	
	4	0.1	0.2	-	*	-	*	0.1	0.9	-	0.1	
	5	-	*	-	-	-	*	-	*	-	-	
	6	-	-	-	-	-	-	-	*	-	-	
	7	-	-	-	-	-	-	-	*	-	-	
	8	-	-	-	-	-	-	-	*	-	-	
	<b>Total</b>	----	<b>40.7</b>	<b>50.8</b>	-	<b>0.8</b>	-	<b>0.5</b>	<b>33.6</b>	<b>58.1</b>	-	<b>2.2</b>
	31	1-2	16.3	14.4	-	2.3	-	6.9	20.2	4.3	-	8.7
3		19.3	18.3	-	15.3	-	14.5	17.7	10.2	-	38.2	
4		4.7	3.6	-	5.7	-	3.2	1.6	4.0	-	8.3	
5		0.4	0.2	-	0.3	-	0.2	0.1	0.5	-	0.5	
6		*	*	-	*	-	*	-	*	-	*	
7		-	*	-	-	-	-	-	*	-	-	
8		-	-	-	-	-	-	-	*	-	-	
<b>Total</b>		----	<b>40.7</b>	<b>36.6</b>	-	<b>23.6</b>	-	<b>24.8</b>	<b>39.5</b>	<b>19.1</b>	-	<b>55.6</b>
41		1-2	0.7	0.5	-	1.9	-	7.7	0.6	0.3	-	1.7
	3	3.6	2.1	-	31.3	-	35.8	3.4	1.8	-	21.6	
	4	2.1	1.6	-	31.4	-	14.2	1.7	1.7	-	15.7	
	5	0.2	0.5	-	5.1	-	1.8	0.3	0.5	-	2.6	
	6	*	0.1	-	0.2	-	0.1	*	0.1	-	0.1	
	7	-	*	-	*	-	*	-	*	-	*	
	8	-	-	-	-	-	-	-	*	-	-	
	<b>Total</b>	----	<b>6.7</b>	<b>4.7</b>	-	<b>69.9</b>	-	<b>59.6</b>	<b>6.1</b>	<b>4.3</b>	-	<b>41.8</b>
	51	1-2	-	*	-	0.1	-	0.2	-	*	-	*
3		-	*	-	1.7	-	2.4	-	0.1	-	*	
4		*	*	-	2.3	-	2.2	*	0.1	-	0.1	
5		-	*	-	0.6	-	0.5	*	*	-	*	
6		-	*	-	0.1	-	*	*	*	-	*	
7		-	*	-	*	-	*	-	*	-	*	
8		-	*	-	-	-	-	-	*	-	-	
<b>Total</b>		----	<b>*</b>	<b>0.1</b>	-	<b>4.9</b>	-	<b>5.3</b>	<b>*</b>	<b>0.2</b>	-	<b>0.2</b>
61		1-2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	*	-	*	-	*	-	-	
	4	-	-	-	*	-	*	-	*	-	-	
	5	-	-	-	-	-	*	-	-	-	-	
	6	-	-	-	-	-	*	-	*	-	-	
	7	-	-	-	-	-	-	-	*	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	<b>Total</b>	----	-	-	-	<b>*</b>	-	<b>*</b>	-	<b>*</b>	-	-
	71	1-2	-	-	-	-	-	-	-	*	-	-
3		-	-	-	-	-	-	-	*	-	-	
4		-	-	-	-	-	-	-	-	-	-	
5		-	-	-	-	-	-	-	-	-	-	
6		-	-	-	-	-	-	-	-	-	-	
7		-	-	-	-	-	-	-	-	-	-	
8		-	-	-	-	-	-	-	-	-	-	
<b>Total</b>		----	-	-	-	-	-	-	<b>*</b>	-	-	
12 & 22		1-2	4.7	2.4	-	-	-	*	4.4	6.8	-	-
	3	0.9	1.0	-	*	-	*	1.7	3.6	-	*	
	4	*	0.1	-	-	-	*	*	0.6	-	*	
	5	-	*	-	-	-	-	-	*	-	-	
	6	-	-	-	-	-	-	-	*	-	-	
	7	-	-	-	-	-	-	-	*	-	-	
	8	-	-	-	-	-	-	-	*	-	-	
	<b>Total</b>	----	<b>5.6</b>	<b>3.4</b>	-	<b>*</b>	-	<b>*</b>	<b>6.1</b>	<b>11.0</b>	-	<b>*</b>
	32	1-2	0.5	0.5	-	*	-	0.2	5.3	0.7	-	*
3		0.7	1.3	-	0.1	-	0.5	5.3	1.7	-	*	
4		0.1	0.5	-	0.1	-	0.1	0.4	1.2	-	*	
5		-	0.1	-	*	-	*	*	0.3	-	*	
6		-	*	-	*	-	-	-	*	-	-	
7		-	-	-	-	-	-	-	*	-	-	
8		-	-	-	-	-	-	-	*	-	-	
<b>Total</b>		----	<b>1.2</b>	<b>2.4</b>	-	<b>0.1</b>	-	<b>0.8</b>	<b>11.0</b>	<b>4.0</b>	-	<b>0.1</b>
42		1-2	-	*	-	*	-	0.9	0.3	*	-	*
	3	*	0.1	-	0.2	-	5.0	1.1	0.3	-	*	
	4	*	0.2	-	0.4	-	1.5	0.6	0.5	-	*	
	5	-	0.1	-	0.1	-	0.1	0.2	0.3	-	*	
	6	-	*	-	*	-	*	*	0.1	-	*	
	7	-	*	-	-	-	-	-	*	-	-	
	8	-	*	-	-	-	-	-	*	-	-	
	<b>Total</b>	----	<b>*</b>	<b>0.5</b>	-	<b>0.7</b>	-	<b>7.5</b>	<b>2.3</b>	<b>1.2</b>	-	<b>0.1</b>

**QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE**  
**For The Week Ending Feb 19, 2026**

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1-2	-	-	-	*	-	*	-	*	-	-
	3	-	*	-	*	-	0.7	-	*	-	-
	4	-	*	-	0.1	-	0.5	*	*	-	*
	5	-	*	-	*	-	0.1	*	*	-	*
	6	-	*	-	*	-	*	*	*	-	-
	7	-	*	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
<b>Total</b>	----	-	*	-	<b>0.1</b>	-	<b>1.3</b>	*	<b>0.1</b>	-	*
62	1-2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	-	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
<b>Total</b>	----	-	*	-	-	-	*	-	*	-	-
13 & 23	1-2	4.4	0.5	-	-	-	-	0.4	0.6	-	-
	3	0.2	0.2	-	-	-	-	0.1	0.4	-	*
	4	-	*	-	*	-	-	-	0.1	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	----	<b>4.6</b>	<b>0.7</b>	-	*	-	-	<b>0.5</b>	<b>1.1</b>	-	*
33	1-2	*	0.1	-	-	-	*	0.2	0.1	-	-
	3	0.1	0.3	-	*	-	*	0.2	0.3	-	*
	4	*	0.1	-	*	-	*	*	0.2	-	*
	5	-	*	-	*	-	-	-	0.1	-	*
	6	-	*	-	-	-	-	-	*	-	-
	7	-	*	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	----	<b>0.1</b>	<b>0.6</b>	-	*	-	*	<b>0.5</b>	<b>0.7</b>	-	*
43	1-2	-	*	-	*	-	*	*	*	-	-
	3	*	*	-	*	-	*	0.2	*	-	*
	4	*	*	-	*	-	*	0.1	*	-	*
	5	*	*	-	*	-	*	*	*	-	*
	6	-	*	-	-	-	*	-	*	-	*
	7	-	*	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	----	<b>0.1</b>	<b>0.1</b>	-	*	-	*	<b>0.3</b>	<b>0.1</b>	-	*
53	1-2	-	-	-	-	-	-	-	*	-	-
	3	*	*	-	*	-	*	*	*	-	-
	4	-	*	-	*	-	*	*	*	-	-
	5	-	*	-	*	-	*	*	*	-	-
	6	-	*	-	-	-	-	*	*	-	-
	7	-	*	-	*	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
<b>Total</b>	----	*	*	-	*	-	*	*	*	-	-
63	1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	*	-	-	-	-	*	*	-	-
	8	-	*	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	*	-	-	-	-	*	*	-	-
24 - 54	1-8	0.2	0.1	-	*	-	-	*	0.1	-	*
25 - 35	1-8	-	-	-	-	-	-	-	-	-	-
81 - 85	1-8	-	*	-	-	-	-	-	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	*	-	-
30		-	-	-	-	-	-	*	*	-	-
31		-	*	-	-	-	-	0.3	0.1	-	-
32		*	0.1	-	*	-	*	3.2	0.6	-	*
33		0.4	0.5	-	0.2	-	0.1	8.4	2.8	-	*
34		6.2	2.2	-	2.0	-	2.6	20.1	8.5	-	0.6
35		18.6	7.6	-	10.1	-	9.5	28.2	15.8	-	5.4
36		21.4	14.2	-	33.7	-	30.9	26.6	22.0	-	23.0
37		19.4	26.6	-	40.7	-	44.3	12.1	31.4	-	55.4
38		15.1	19.3	-	10.2	-	11.3	0.8	13.6	-	12.8
39		13.3	17.4	-	2.7	-	1.3	*	4.1	-	2.6
40 & Longer		5.7	12.1	-	0.4	-	0.1	0.3	1.1	-	0.1
<b>Average Staple</b>		<b>36.81</b>	<b>37.55</b>	-	<b>36.56</b>	-	<b>36.56</b>	<b>35.08</b>	<b>36.33</b>	-	<b>36.82</b>
<b>Average Length</b>		<b>1.15</b>	<b>1.17</b>	-	<b>1.14</b>	-	<b>1.14</b>	<b>1.09</b>	<b>1.13</b>	-	<b>1.15</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Feb 19, 2026**

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	3.4	0.6	-	*	*	0.2	-	0.6	-	1.5	0.4	1.4
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	0.1	-	*	0.1	0.2	-	1.1	-	0.1	-	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	-	*	-	-	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	0.6	0.1	-	1.0	*	0.1	-	-	-	0.3	-	0.3
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	-	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	*	-	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	-	-	-	-	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	-	*	-	*	-	*	-	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
<b>STRENGTH 1/</b>												
22 & Below	-	*	-	-	-	*	-	-	-	-	-	-
23	-	*	-	*	-	*	-	*	-	-	-	*
24	-	*	-	*	0.1	*	-	0.1	-	-	0.2	*
25	0.1	*	-	*	0.2	0.1	-	0.1	-	*	0.1	0.1
26	-	0.2	-	*	1.7	0.8	-	0.6	-	*	0.3	0.7
27	0.9	1.7	-	0.2	5.2	2.7	-	3.5	-	0.4	0.6	3.6
28	19.4	8.5	-	1.9	13.4	8.4	-	12.1	-	3.3	5.4	11.2
29	48.4	21.7	-	11.5	21.1	15.7	-	22.5	-	13.1	51.2	21.0
30	26.6	29.0	-	34.3	20.2	22.1	-	19.0	-	26.8	25.8	24.8
31	3.7	21.3	-	33.2	18.6	20.8	-	11.7	-	27.4	10.6	19.2
32	0.8	11.0	-	13.5	10.2	14.0	-	4.1	-	16.9	5.6	11.1
33	0.1	4.5	-	4.1	6.4	7.9	-	3.7	-	7.3	0.2	5.2
34	-	1.6	-	1.1	2.5	4.4	-	6.7	-	3.8	0.1	2.1
35	-	0.4	-	0.2	0.3	1.8	-	8.4	-	0.9	-	0.7
36	-	0.1	-	0.1	*	0.8	-	5.4	-	0.1	-	0.2
37	-	*	-	*	-	0.3	-	1.7	-	*	-	0.1
38	-	*	-	*	-	*	-	0.2	-	-	-	*
39	-	-	-	*	-	*	-	*	-	-	-	*
40 & Above	-	-	-	*	-	*	-	*	-	-	-	*
<b>Average</b>	<b>29.61</b>	<b>30.66</b>	<b>-</b>	<b>31.07</b>	<b>30.42</b>	<b>31.07</b>	<b>-</b>	<b>31.31</b>	<b>-</b>	<b>31.27</b>	<b>30.03</b>	<b>30.58</b>
<b>Mike</b>												
2.4 & Below	-	-	-	-	0.2	*	-	-	-	-	-	-
2.5	-	*	-	-	0.4	*	-	-	-	-	-	-
2.6	-	*	-	-	0.5	*	-	*	-	-	-	*
2.7	-	*	-	-	0.6	0.1	-	0.1	-	-	-	*
2.8	-	*	-	*	0.6	0.1	-	*	-	-	-	*
2.9	-	*	-	-	0.7	0.1	-	0.1	-	-	-	*
3.0	-	*	-	*	0.6	0.2	-	0.1	-	-	-	*
3.1	-	*	-	*	0.3	0.2	-	0.3	-	*	-	*
3.2	-	*	-	*	0.5	0.3	-	0.3	-	0.1	-	0.1
3.3	-	0.1	-	*	0.8	0.3	-	0.4	-	0.1	1.5	0.2
3.4	1.2	0.4	-	*	1.4	0.5	-	0.5	-	0.1	-	0.3
3.5	1.7	0.8	-	*	1.0	0.6	-	1.3	-	0.5	0.5	0.6
3.6	1.6	1.1	-	0.1	1.7	1.0	-	2.3	-	0.7	0.9	1.2
3.7	6.0	2.0	-	0.1	3.9	1.7	-	3.4	-	1.2	1.2	1.9
3.8	7.5	3.0	-	0.1	4.6	2.4	-	5.4	-	1.3	3.1	2.9
3.9	5.6	4.4	-	0.3	7.5	3.5	-	8.8	-	2.1	5.1	4.1
4.0	3.0	5.9	-	0.6	13.9	5.2	-	11.2	-	3.4	9.7	5.6
4.1	4.9	8.0	-	1.1	11.5	7.2	-	11.6	-	5.6	8.8	7.4
4.2	7.4	9.8	-	1.8	12.3	9.1	-	11.0	-	7.1	6.0	9.0
4.3	10.0	10.8	-	3.2	9.5	10.6	-	7.9	-	9.7	3.3	9.8
4.4	12.1	10.6	-	5.1	8.8	11.3	-	5.2	-	12.3	1.8	10.0
4.5	13.1	10.1	-	7.9	6.2	11.1	-	5.6	-	13.0	4.8	9.7
4.6	5.4	8.9	-	11.7	3.6	10.2	-	5.5	-	11.2	0.6	9.1
4.7	1.3	7.1	-	14.5	3.8	7.8	-	5.3	-	12.4	9.7	8.2
4.8	6.8	5.6	-	15.3	1.3	5.7	-	4.1	-	8.4	6.9	6.7
4.9	6.5	4.3	-	13.6	1.2	4.3	-	3.2	-	5.2	15.3	5.1
5.0	3.9	2.8	-	10.8	2.0	2.8	-	2.2	-	3.2	10.5	3.6
5.1	1.9	1.8	-	6.9	0.5	1.2	-	2.0	-	1.7	4.1	2.3
5.2	-	1.1	-	4.0	0.2	0.9	-	0.9	-	0.5	6.0	1.2
5.3	0.1	0.7	-	1.9	-	0.7	-	0.8	-	0.1	-	0.6
5.4	-	0.3	-	0.6	-	0.3	-	0.5	-	0.1	-	0.2
5.5 & Above	-	0.2	-	0.2	-	0.4	-	0.2	-	0.1	-	0.1
<b>Average</b>	<b>4.32</b>	<b>4.39</b>	<b>-</b>	<b>4.76</b>	<b>4.12</b>	<b>4.39</b>	<b>-</b>	<b>4.25</b>	<b>-</b>	<b>4.48</b>	<b>4.52</b>	<b>4.41</b>

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE**  
**For The Week Ending Feb 19, 2026**

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	59.1	41.2	-	0.1	-	*	-	*	-	1.6	-	6.5
Bark - Level 2	-	*	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	0.1	-	*	-	*	-	*	-	*	-	0.6
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	-	-	*	-	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	0.4	-	0.2	-	0.3	-	0.5	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	-	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	-	*	-	*	-	*	-	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
<b>STRENGTH 1/</b>												
22 & Below	*	*	-	-	-	*	-	-	-	-	-	*
23	-	*	-	-	-	*	-	-	-	-	-	-
24	0.2	*	-	-	-	*	-	*	-	*	-	-
25	0.8	0.1	-	*	-	*	-	*	-	*	-	*
26	3.5	0.5	-	*	-	*	-	0.1	-	0.3	-	0.2
27	7.8	1.2	-	0.5	-	0.1	-	1.0	-	2.3	-	1.5
28	10.9	2.4	-	4.4	-	0.7	-	4.8	-	10.9	-	6.0
29	9.6	4.3	-	19.0	-	8.1	-	15.6	-	28.2	-	18.9
30	9.2	8.8	-	33.2	-	36.9	-	26.9	-	31.5	-	30.2
31	11.8	17.0	-	21.1	-	35.7	-	26.3	-	17.3	-	20.7
32	24.5	25.1	-	11.7	-	13.0	-	16.1	-	6.9	-	16.5
33	14.5	22.5	-	5.1	-	4.5	-	6.5	-	2.0	-	4.4
34	5.1	12.1	-	2.9	-	1.0	-	2.3	-	0.4	-	1.3
35	1.8	4.7	-	1.8	-	0.1	-	0.4	-	0.1	-	0.1
36	0.2	0.9	-	0.2	-	*	-	*	-	*	-	-
37	0.1	0.2	-	*	-	*	-	*	-	-	-	*
38	-	0.1	-	*	-	*	-	*	-	-	-	-
39	-	*	-	-	-	-	-	-	-	-	-	*
40 & Above	*	*	-	-	-	-	-	*	-	-	-	-
<b>Average</b>	<b>31.08</b>	<b>32.44</b>	-	<b>30.97</b>	-	<b>31.15</b>	-	<b>31.06</b>	-	<b>30.26</b>	-	<b>30.81</b>
<b>Mike</b>												
2.4 & Below	1.4	0.3	-	-	-	-	-	-	-	-	-	-
2.5	4.5	1.2	-	-	-	-	-	-	-	*	-	*
2.6	7.2	1.5	-	*	-	-	-	-	-	-	-	*
2.7	7.6	2.0	-	*	-	-	-	-	-	*	-	0.2
2.8	6.9	2.4	-	-	-	-	-	-	-	*	-	2.7
2.9	4.6	2.4	-	*	-	-	-	-	-	*	-	2.5
3.0	4.0	2.8	-	*	-	-	-	-	-	*	-	1.8
3.1	3.2	3.2	-	*	-	*	-	-	-	*	-	1.7
3.2	3.0	3.9	-	*	-	*	-	*	-	0.1	-	2.9
3.3	2.3	4.4	-	*	-	*	-	*	-	0.2	-	1.4
3.4	4.8	5.4	-	0.1	-	*	-	*	-	0.3	-	0.9
3.5	5.1	6.0	-	0.1	-	*	-	0.1	-	0.5	-	1.0
3.6	3.6	6.3	-	0.1	-	0.1	-	0.1	-	0.9	-	1.1
3.7	5.1	6.6	-	0.2	-	0.2	-	0.2	-	1.5	-	2.7
3.8	3.4	6.5	-	0.3	-	0.3	-	0.3	-	2.4	-	4.5
3.9	4.8	6.3	-	0.6	-	0.6	-	0.4	-	3.5	-	6.9
4.0	5.5	6.8	-	1.3	-	1.4	-	0.8	-	4.9	-	6.2
4.1	5.0	7.1	-	2.2	-	2.4	-	1.3	-	7.0	-	6.2
4.2	4.5	5.8	-	3.4	-	4.3	-	2.0	-	9.3	-	6.8
4.3	3.0	5.7	-	4.9	-	6.7	-	3.0	-	11.6	-	9.5
4.4	3.5	4.7	-	6.3	-	9.8	-	4.5	-	12.2	-	9.1
4.5	1.5	3.3	-	8.2	-	13.0	-	6.2	-	11.3	-	8.7
4.6	0.9	2.0	-	9.7	-	15.1	-	8.7	-	10.2	-	6.6
4.7	0.3	1.6	-	11.2	-	15.7	-	11.2	-	8.5	-	6.0
4.8	0.8	1.2	-	12.6	-	13.2	-	13.6	-	6.0	-	5.1
4.9	1.9	0.5	-	11.7	-	8.7	-	14.6	-	4.1	-	3.6
5.0	1.2	0.2	-	9.6	-	4.9	-	13.3	-	2.7	-	1.6
5.1	0.4	*	-	7.7	-	2.3	-	9.9	-	1.5	-	0.2
5.2	-	*	-	4.4	-	0.9	-	5.7	-	0.7	-	*
5.3	-	-	-	2.6	-	0.3	-	2.6	-	0.3	-	*
5.4	-	-	-	1.3	-	0.1	-	1.0	-	0.1	-	-
5.5 & Above	-	-	-	1.4	-	*	-	0.4	-	*	-	-
<b>Average</b>	<b>3.47</b>	<b>3.74</b>	-	<b>4.74</b>	-	<b>4.61</b>	-	<b>4.80</b>	-	<b>4.41</b>	-	<b>4.14</b>

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).  
 \* Less than 0.05 percent.

**QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE**  
**For The Week Ending Feb 19, 2026**

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	7.9	3.5	-	3.6	-	*	14.8	4.7	-	1.3
Bark - Level 2	-	*	-	-	-	-	-	*	-	-
Grass - Level 1	-	0.1	-	0.1	-	*	*	0.2	-	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	-	*	-	*	-	-	-	*	-	*
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	1.7	-	*	0.1	0.3	-	0.6
Seed Coat - Level 2	-	*	-	-	-	-	-	*	-	-
Oil - Level 1	-	*	-	*	-	-	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	*	-	-
Other - Level 1	-	*	-	-	-	-	-	*	-	-
Other - Level 2	-	*	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	*	-	*	*	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
<b>STRENGTH 1/</b>										
22 & Below	-	*	-	-	-	-	-	*	-	-
23	-	*	-	-	-	-	-	*	-	-
24	-	*	-	*	-	*	0.1	0.1	-	*
25	0.1	*	-	*	-	*	0.8	0.2	-	*
26	0.5	0.2	-	0.4	-	*	1.7	0.9	-	1.1
27	2.5	0.9	-	2.6	-	0.5	7.0	3.0	-	6.2
28	8.4	3.5	-	12.6	-	3.8	15.4	8.0	-	19.0
29	17.6	9.5	-	34.7	-	21.0	22.7	16.0	-	32.2
30	22.5	15.9	-	30.2	-	38.7	23.9	21.0	-	25.7
31	19.1	18.8	-	13.3	-	24.7	15.3	18.5	-	11.1
32	12.4	16.5	-	4.8	-	8.2	8.8	13.2	-	3.6
33	8.3	14.4	-	1.2	-	2.4	3.0	9.2	-	0.8
34	5.1	10.5	-	0.2	-	0.7	0.9	6.0	-	0.2
35	2.5	5.9	-	*	-	0.1	0.2	2.6	-	*
36	0.8	2.4	-	*	-	*	0.2	0.9	-	*
37	0.3	1.2	-	*	-	*	*	0.3	-	-
38	0.1	0.3	-	-	-	-	*	0.1	-	-
39	*	*	-	-	-	-	*	*	-	-
40 & Above	-	*	-	-	-	-	-	*	-	-
<b>Average</b>	<b>31.09</b>	<b>32.17</b>	<b>-</b>	<b>30.02</b>	<b>-</b>	<b>30.66</b>	<b>30.06</b>	<b>31.17</b>	<b>-</b>	<b>29.73</b>
<b>Mike</b>										
2.4 & Below	-	*	-	-	-	-	-	*	-	-
2.5	0.1	*	-	-	-	-	0.1	*	-	-
2.6	-	*	-	-	-	-	0.2	0.1	-	-
2.7	0.1	0.1	-	-	-	*	0.2	0.2	-	*
2.8	*	0.1	-	*	-	*	0.3	0.3	-	*
2.9	0.1	0.1	-	*	-	*	0.4	0.4	-	*
3.0	0.2	0.2	-	*	-	*	0.6	0.6	-	0.1
3.1	0.5	0.3	-	*	-	*	0.9	0.8	-	0.1
3.2	0.5	0.5	-	0.1	-	*	1.2	1.2	-	0.1
3.3	0.4	0.8	-	0.2	-	*	1.9	1.6	-	0.3
3.4	0.8	1.1	-	0.3	-	0.1	2.7	2.1	-	0.4
3.5	1.4	1.6	-	0.5	-	0.3	2.5	2.7	-	0.7
3.6	3.0	2.8	-	0.9	-	0.3	3.9	3.4	-	1.3
3.7	4.2	4.0	-	1.9	-	0.8	3.8	4.1	-	2.6
3.8	7.1	5.6	-	2.8	-	1.1	4.5	5.1	-	3.9
3.9	8.4	7.2	-	4.3	-	1.7	6.4	6.3	-	6.7
4.0	8.8	8.7	-	5.8	-	2.5	9.3	7.4	-	9.2
4.1	9.1	10.1	-	7.3	-	3.9	11.0	8.5	-	11.5
4.2	10.5	10.3	-	8.7	-	5.3	12.4	9.5	-	14.1
4.3	11.3	10.8	-	9.9	-	6.7	12.5	9.8	-	14.5
4.4	10.5	10.0	-	10.4	-	9.5	9.3	9.2	-	12.7
4.5	10.0	9.2	-	10.4	-	11.8	6.1	8.0	-	9.1
4.6	8.5	7.2	-	9.7	-	13.4	4.5	6.4	-	5.9
4.7	3.8	4.9	-	8.5	-	13.4	2.9	4.7	-	3.2
4.8	0.7	2.7	-	6.7	-	11.8	1.4	3.2	-	1.8
4.9	0.1	1.2	-	4.9	-	8.1	0.7	1.9	-	1.1
5.0	-	0.5	-	3.3	-	5.4	0.2	1.1	-	0.6
5.1	-	0.1	-	1.9	-	2.7	0.2	0.6	-	0.2
5.2	-	*	-	1.0	-	1.0	*	0.3	-	*
5.3	-	*	-	0.4	-	0.3	-	0.1	-	*
5.4	-	-	-	0.2	-	*	-	0.1	-	*
5.5 & Above	-	*	-	0.1	-	*	-	0.1	-	*
<b>Average</b>	<b>4.16</b>	<b>4.19</b>	<b>-</b>	<b>4.41</b>	<b>-</b>	<b>4.56</b>	<b>4.09</b>	<b>4.16</b>	<b>-</b>	<b>4.23</b>

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).  
\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Feb 19, 2026**

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	0.2	*	-	-	-	-	-	-
2.5 - 2.6	-	*	-	-	0.8	0.1	-	*	-	-	-	*
2.7 - 2.9	-	*	-	*	1.9	0.3	-	0.2	-	-	-	*
3.0 - 3.2	-	0.1	-	*	1.4	0.7	-	0.6	-	0.1	-	0.1
3.3 - 3.4	1.2	0.6	-	*	2.2	0.8	-	0.9	-	0.1	1.5	0.5
3.5 - 3.6	3.3	1.9	-	0.1	2.7	1.6	-	3.6	-	1.2	1.5	1.8
3.7 - 4.2	34.3	33.1	-	4.1	53.7	29.0	-	51.3	-	20.7	33.9	30.9
4.3 - 4.9	55.3	57.4	-	71.4	34.3	61.2	-	36.7	-	72.1	42.4	58.6
5.0 - 5.2	5.8	5.7	-	21.7	2.7	5.0	-	5.2	-	5.4	20.7	7.1
5.3 & Above	0.1	1.1	-	2.7	-	1.3	-	1.4	-	0.3	-	0.9
<b>Average</b>	<b>4.32</b>	<b>4.39</b>	-	<b>4.76</b>	<b>4.12</b>	<b>4.39</b>	-	<b>4.25</b>	-	<b>4.48</b>	<b>4.52</b>	<b>4.41</b>
Leaf												
1 - 2	1.9	15.4	-	2.1	6.6	31.7	-	40.1	-	7.8	26.0	14.8
3	40.3	55.0	-	39.0	45.9	36.1	-	43.0	-	52.7	66.4	58.6
4	48.3	25.4	-	45.6	36.8	21.9	-	12.9	-	34.5	6.9	23.5
5	8.4	3.9	-	11.9	6.6	7.8	-	3.3	-	4.8	0.7	2.9
6	1.2	0.3	-	1.3	2.8	2.1	-	0.7	-	0.3	-	0.2
7	-	*	-	0.1	0.9	0.4	-	*	-	*	-	*
8	-	*	-	-	0.4	0.1	-	*	-	-	-	*
<b>Average</b>	<b>3.67</b>	<b>3.18</b>	-	<b>3.72</b>	<b>3.56</b>	<b>3.08</b>	-	<b>2.74</b>	-	<b>3.37</b>	<b>2.82</b>	<b>3.15</b>
HVI Trash 1/												
00	-	-	-	-	-	*	-	*	-	-	-	-
01	0.1	2.0	-	0.1	2.5	12.5	-	14.5	-	0.9	0.6	1.4
02	2.2	17.6	-	3.1	6.6	24.2	-	30.8	-	9.4	36.4	19.9
03	11.3	28.1	-	14.7	26.6	19.8	-	25.2	-	23.4	40.6	32.0
04	24.4	23.9	-	24.5	24.9	15.6	-	14.4	-	28.1	13.8	23.6
05	30.3	14.5	-	22.9	19.3	11.0	-	7.2	-	19.3	5.0	12.7
06	15.1	7.5	-	15.9	9.4	7.0	-	3.6	-	10.3	2.1	5.9
07	8.3	3.6	-	9.4	3.7	4.3	-	2.0	-	4.8	0.8	2.6
08	3.4	1.6	-	4.9	2.7	2.5	-	1.2	-	2.2	0.5	1.1
09	2.3	0.7	-	2.4	1.7	1.5	-	0.6	-	0.9	0.1	0.5
10	1.0	0.3	-	1.1	1.0	0.8	-	0.3	-	0.5	-	0.2
11	0.9	0.1	-	0.5	0.5	0.5	-	0.1	-	0.2	-	0.1
12	0.3	0.1	-	0.2	0.4	0.2	-	0.1	-	0.1	0.1	*
13	0.2	*	-	0.1	0.2	0.1	-	*	-	*	-	*
14	0.1	*	-	*	0.1	0.1	-	*	-	*	-	*
15	0.1	*	-	*	0.1	*	-	*	-	*	-	*
16	0.1	*	-	-	0.1	*	-	*	-	*	-	*
17	-	*	-	-	*	*	-	*	-	*	-	*
18 & Above	-	*	-	-	0.1	*	-	*	-	*	-	*
<b>Average</b>	<b>0.51</b>	<b>0.38</b>	-	<b>0.51</b>	<b>0.44</b>	<b>0.36</b>	-	<b>0.30</b>	-	<b>0.43</b>	<b>0.30</b>	<b>0.37</b>
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	-	-	-	-	*	-	-	-	-	-	*
76	-	*	-	*	*	*	-	*	-	*	-	*
77	-	*	-	*	0.2	0.1	-	*	-	*	-	0.1
78	0.1	0.4	-	0.1	1.7	0.6	-	1.0	-	0.1	0.3	0.9
79	1.2	3.0	-	0.5	11.5	2.9	-	5.8	-	1.1	1.8	5.5
80	10.7	14.0	-	3.9	28.5	14.4	-	28.9	-	7.8	17.7	21.3
81	60.2	32.0	-	20.4	37.7	36.7	-	31.4	-	37.1	54.1	36.2
82	26.0	34.2	-	42.8	17.8	35.8	-	20.1	-	41.9	15.5	26.3
83	1.5	14.3	-	27.8	2.5	8.7	-	9.8	-	10.9	10.5	8.2
84	0.2	1.9	-	4.3	0.1	0.7	-	2.8	-	1.1	0.1	1.3
85 & Above	0.1	0.2	-	0.3	*	*	-	0.1	-	0.1	-	0.1
<b>Average</b>	<b>81.61</b>	<b>81.93</b>	-	<b>82.52</b>	<b>81.11</b>	<b>81.78</b>	-	<b>81.50</b>	-	<b>82.02</b>	<b>81.57</b>	<b>81.56</b>
Tenderable 3/	<b>86.9</b>	<b>89.9</b>	-	<b>70.4</b>	<b>89.1</b>	<b>86.6</b>	-	<b>87.1</b>	-	<b>91.0</b>	<b>76.9</b>	<b>88.4</b>
<b>SAMPLES CLASSED</b>	<b>1,745</b>	<b>549,869</b>	-	<b>1,411,880</b>	<b>6,848</b>	<b>223,936</b>	-	<b>92,369</b>	-	<b>90,067</b>	<b>1,167</b>	<b>1,737,700</b>

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. \* Less than 0.05 percent.

**QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE**  
**For The Week Ending Feb 19, 2026**

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	1.4	0.3	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	11.7	2.6	-	*	-	-	-	-	-	*	-	*
2.7 - 2.9	19.0	6.8	-	*	-	-	-	-	-	*	-	5.3
3.0 - 3.2	10.2	9.9	-	*	-	*	-	*	-	0.2	-	6.3
3.3 - 3.4	7.1	9.7	-	0.1	-	*	-	*	-	0.5	-	2.4
3.5 - 3.6	8.6	12.3	-	0.2	-	0.1	-	0.2	-	1.4	-	2.1
3.7 - 4.2	28.3	39.0	-	8.1	-	9.2	-	5.0	-	28.6	-	33.2
4.3 - 4.9	11.9	19.1	-	64.6	-	82.2	-	61.8	-	64.0	-	48.8
5.0 - 5.2	1.7	0.3	-	21.7	-	8.1	-	29.0	-	4.9	-	1.9
5.3 & Above	-	-	-	5.2	-	0.5	-	4.0	-	0.4	-	*
<b>Average</b>	<b>3.47</b>	<b>3.74</b>	-	<b>4.74</b>	-	<b>4.61</b>	-	<b>4.80</b>	-	<b>4.41</b>	-	<b>4.14</b>
Leaf												
1 - 2	4.5	6.5	-	14.2	-	4.2	-	6.3	-	9.3	-	51.1
3	30.6	23.3	-	49.8	-	53.5	-	42.8	-	51.8	-	31.5
4	31.2	30.2	-	29.5	-	36.7	-	39.7	-	32.6	-	12.8
5	15.3	23.0	-	6.1	-	5.2	-	10.1	-	5.8	-	3.6
6	11.4	12.0	-	0.4	-	0.3	-	1.0	-	0.6	-	0.9
7	4.9	4.1	-	-	-	*	-	*	-	0.1	-	0.1
8	2.2	0.9	-	-	-	-	-	-	-	*	-	-
<b>Average</b>	<b>4.22</b>	<b>4.26</b>	-	<b>3.28</b>	-	<b>3.44</b>	-	<b>3.57</b>	-	<b>3.37</b>	-	<b>2.62</b>
HVI Trash 1/												
00	-	-	-	-	-	*	-	-	-	-	-	-
01	0.3	1.4	-	1.9	-	0.2	-	0.5	-	0.8	-	18.8
02	6.3	6.6	-	15.0	-	6.4	-	7.7	-	11.1	-	36.3
03	15.4	10.7	-	24.4	-	23.6	-	19.0	-	24.4	-	19.7
04	18.7	12.6	-	23.2	-	28.8	-	23.6	-	25.5	-	11.1
05	14.7	12.6	-	16.2	-	20.7	-	19.9	-	18.3	-	6.7
06	10.0	11.2	-	9.6	-	11.2	-	13.3	-	10.5	-	3.5
07	6.8	9.8	-	5.2	-	5.2	-	7.9	-	5.2	-	2.0
08	4.7	8.5	-	2.5	-	2.2	-	4.2	-	2.4	-	1.1
09	4.4	7.0	-	1.2	-	1.0	-	2.1	-	1.0	-	0.5
10	4.1	5.3	-	0.5	-	0.4	-	1.0	-	0.4	-	0.2
11	3.2	4.2	-	0.2	-	0.2	-	0.5	-	0.2	-	0.1
12	3.1	3.2	-	0.1	-	0.1	-	0.2	-	0.1	-	0.1
13	2.3	2.3	-	*	-	*	-	0.1	-	*	-	*
14	1.6	1.6	-	*	-	*	-	*	-	*	-	-
15	1.2	1.0	-	-	-	*	-	*	-	*	-	-
16	0.8	0.7	-	-	-	-	-	-	-	*	-	-
17	0.7	0.5	-	-	-	-	-	-	-	*	-	-
18 & Above	1.5	0.8	-	-	-	-	-	-	-	*	-	-
<b>Average</b>	<b>0.63</b>	<b>0.67</b>	-	<b>0.41</b>	-	<b>0.44</b>	-	<b>0.47</b>	-	<b>0.43</b>	-	<b>0.28</b>
UNIFORMITY 2/												
74 & Below	0.3	*	-	-	-	-	-	-	-	*	-	-
75	1.6	0.2	-	-	-	-	-	-	-	*	-	*
76	5.2	0.7	-	-	-	*	-	*	-	*	-	0.1
77	10.5	2.2	-	-	-	*	-	*	-	*	-	0.1
78	12.5	4.4	-	0.1	-	0.1	-	0.2	-	0.6	-	3.0
79	11.0	8.7	-	1.2	-	0.2	-	1.3	-	3.0	-	9.2
80	16.6	18.4	-	7.1	-	2.1	-	8.8	-	11.0	-	17.2
81	22.1	31.3	-	30.1	-	16.5	-	30.1	-	27.2	-	34.5
82	14.3	23.2	-	40.4	-	50.4	-	38.1	-	35.3	-	28.8
83	5.6	9.3	-	18.5	-	27.9	-	18.1	-	19.9	-	6.7
84	0.2	1.6	-	2.6	-	2.5	-	3.3	-	2.7	-	0.3
85 & Above	*	0.1	-	0.1	-	0.2	-	0.1	-	0.2	-	*
<b>Average</b>	<b>80.16</b>	<b>81.29</b>	-	<b>82.20</b>	-	<b>82.57</b>	-	<b>82.18</b>	-	<b>82.10</b>	-	<b>81.41</b>
Tenderable 3/	<b>13.4</b>	<b>32.9</b>	-	<b>71.5</b>	-	<b>86.7</b>	-	<b>63.7</b>	-	<b>90.7</b>	-	<b>81.6</b>
<b>SAMPLES CLASSED</b>	<b>4,287</b>	<b>158,445</b>	-	<b>223,299</b>	-	<b>680,258</b>	-	<b>706,511</b>	-	<b>653,675</b>	-	<b>12,080</b>

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. \* Less than 0.05 percent.

**QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE**  
**For The Week Ending Feb 19, 2026**

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	*	-	-	-	-	-	*	-	-
2.5 - 2.6	0.1	0.1	-	-	-	-	0.3	0.1	-	-
2.7 - 2.9	0.2	0.2	-	*	-	*	1.0	0.8	-	*
3.0 - 3.2	1.3	1.0	-	0.1	-	*	2.7	2.7	-	0.3
3.3 - 3.4	1.2	1.9	-	0.5	-	0.2	4.6	3.7	-	0.6
3.5 - 3.6	4.3	4.4	-	1.4	-	0.6	6.4	6.1	-	2.0
3.7 - 4.2	48.0	45.8	-	30.7	-	15.1	47.2	40.9	-	48.0
4.3 - 4.9	44.9	46.0	-	60.4	-	74.7	37.4	43.3	-	48.2
5.0 - 5.2	-	0.6	-	6.2	-	9.0	0.5	2.0	-	0.8
5.3 & Above	-	*	-	0.7	-	0.3	-	0.3	-	*
<b>Average</b>	<b>4.16</b>	<b>4.19</b>	<b>-</b>	<b>4.41</b>	<b>-</b>	<b>4.56</b>	<b>4.09</b>	<b>4.16</b>	<b>-</b>	<b>4.23</b>
Leaf										
1 - 2	61.2	62.0	-	4.5	-	16.4	58.0	57.1	-	11.3
3	31.0	30.4	-	49.0	-	59.0	36.8	31.4	-	61.2
4	7.1	6.4	-	40.1	-	21.8	4.6	9.3	-	24.3
5	0.7	1.0	-	6.1	-	2.7	0.6	1.8	-	3.1
6	*	0.2	-	0.3	-	0.2	*	0.3	-	0.1
7	-	*	-	*	-	*	*	*	-	*
8	-	*	-	-	-	-	-	*	-	-
<b>Average</b>	<b>2.31</b>	<b>2.27</b>	<b>-</b>	<b>3.49</b>	<b>-</b>	<b>3.11</b>	<b>2.38</b>	<b>2.41</b>	<b>-</b>	<b>3.20</b>
HVI Trash 1/										
00	-	*	-	-	-	*	*	0.1	-	-
01	28.1	31.5	-	0.2	-	2.0	20.7	27.6	-	0.5
02	36.6	33.7	-	6.5	-	17.1	42.1	34.2	-	12.5
03	18.7	18.4	-	22.2	-	29.7	23.1	18.2	-	29.6
04	9.6	9.1	-	27.5	-	24.7	8.6	9.6	-	26.5
05	4.1	4.0	-	21.5	-	14.2	3.2	5.1	-	16.0
06	1.7	1.7	-	12.3	-	6.8	1.4	2.6	-	8.3
07	0.7	0.8	-	5.8	-	3.1	0.5	1.3	-	3.9
08	0.3	0.4	-	2.4	-	1.3	0.3	0.6	-	1.7
09	0.1	0.2	-	0.9	-	0.6	0.1	0.3	-	0.7
10	*	0.1	-	0.4	-	0.2	*	0.1	-	0.2
11	-	*	-	0.1	-	0.1	*	0.1	-	0.1
12	-	*	-	*	-	*	*	*	-	*
13	*	*	-	*	-	*	-	*	-	*
14	-	*	-	*	-	*	-	*	-	*
15	-	*	-	*	-	*	-	*	-	*
16	-	*	-	*	-	-	-	*	-	*
17	-	*	-	-	-	-	-	*	-	*
18 & Above	-	*	-	*	-	-	-	*	-	*
<b>Average</b>	<b>0.24</b>	<b>0.23</b>	<b>-</b>	<b>0.45</b>	<b>-</b>	<b>0.38</b>	<b>0.24</b>	<b>0.25</b>	<b>-</b>	<b>0.40</b>
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	-	*	-	-
75	*	*	-	*	-	-	*	*	-	-
76	0.2	*	-	*	-	*	0.3	0.2	-	*
77	1.0	0.2	-	0.1	-	*	2.0	0.9	-	*
78	4.9	1.4	-	0.5	-	0.1	9.1	4.0	-	0.2
79	15.4	6.6	-	3.8	-	0.6	23.4	12.8	-	1.3
80	32.8	20.1	-	16.7	-	6.9	30.9	26.4	-	8.2
81	26.8	31.2	-	32.9	-	32.7	24.3	29.5	-	27.9
82	13.4	24.5	-	32.4	-	43.1	8.9	17.9	-	38.3
83	4.6	12.5	-	12.4	-	15.6	1.0	6.6	-	21.1
84	0.9	3.2	-	1.1	-	0.9	0.1	1.5	-	2.9
85 & Above	0.1	0.3	-	0.1	-	0.1	-	0.2	-	0.2
<b>Average</b>	<b>80.87</b>	<b>81.67</b>	<b>-</b>	<b>81.80</b>	<b>-</b>	<b>82.14</b>	<b>80.42</b>	<b>81.13</b>	<b>-</b>	<b>82.23</b>
Tenderable 3/	<b>85.9</b>	<b>91.4</b>	<b>-</b>	<b>86.4</b>	<b>-</b>	<b>82.3</b>	<b>74.2</b>	<b>82.3</b>	<b>-</b>	<b>96.1</b>
<b>SAMPLES CLASSED</b>	<b>17,330</b>	<b>444,454</b>	<b>-</b>	<b>283,934</b>	<b>-</b>	<b>340,307</b>	<b>21,174</b>	<b>5,187,511</b>	<b>-</b>	<b>172,921</b>

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. \* Less than 0.05 percent.

**QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE**  
**For The Week Ending Feb 19, 2026**

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	7.1	8.2	-	5.1	-	-	-	16.5
	2	0.8	1.9	5.2	6.3	-	-	-	20.6
	3	-	*	1.2	0.1	-	-	-	0.6
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total</b>		<b>7.8</b>	<b>10.1</b>	<b>6.3</b>	<b>11.5</b>	-	-	-	<b>37.6</b>
02	1	35.2	41.5	0.1	4.6	-	-	-	12.5
	2	28.6	19.6	14.6	34.0	-	-	-	40.5
	3	0.2	0.2	26.0	8.8	-	-	-	3.4
	4	-	-	2.3	0.1	-	-	-	0.1
	5	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total</b>		<b>64.0</b>	<b>61.3</b>	<b>43.0</b>	<b>47.5</b>	-	-	-	<b>56.5</b>
03	1	4.2	8.2	-	0.2	-	-	-	0.3
	2	17.9	16.5	4.1	14.5	-	-	-	4.3
	3	0.2	0.8	20.8	19.1	-	-	-	0.9
	4	-	-	20.9	2.2	-	-	-	0.1
	5	-	-	1.8	0.1	-	-	-	-
	6	-	-	0.1	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total</b>		<b>22.3</b>	<b>25.6</b>	<b>47.8</b>	<b>36.1</b>	-	-	-	<b>5.5</b>
04	1	-	0.2	-	*	-	-	-	-
	2	0.6	2.0	*	0.6	-	-	-	0.1
	3	3.2	0.5	1.1	2.4	-	-	-	0.1
	4	0.1	*	0.9	1.0	-	-	-	0.1
	5	-	-	0.5	0.1	-	-	-	*
	6	-	-	0.2	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total</b>		<b>3.9</b>	<b>2.8</b>	<b>2.7</b>	<b>4.1</b>	-	-	-	<b>0.3</b>
05	1	-	*	-	*	-	-	-	-
	2	0.4	0.1	-	0.1	-	-	-	-
	3	1.5	0.1	-	0.3	-	-	-	*
	4	-	-	*	0.3	-	-	-	*
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total</b>		<b>2.0</b>	<b>0.3</b>	<b>*</b>	<b>0.7</b>	-	-	-	<b>*</b>
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	*	-	-	-	-
	3	-	-	*	0.1	-	-	-	-
	4	-	-	0.1	0.1	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total</b>		-	-	<b>0.1</b>	<b>0.1</b>	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total</b>		-	-	-	<b>0.1</b>	-	-	-	-
<b>STAPLE</b>									
44 & Shorter		-	*	-	2.1	-	-	-	13.0
46		8.6	14.2	0.6	7.1	-	-	-	46.6
48		74.1	71.7	45.3	44.2	-	-	-	35.4
50		17.3	13.7	53.4	44.3	-	-	-	4.6
52 & Longer		-	0.3	0.7	2.3	-	-	-	0.4
<b>Average Staple</b>		<b>48.17</b>	<b>48.00</b>	<b>49.08</b>	<b>48.75</b>	-	-	-	<b>46.65</b>
<b>Average Length</b>		<b>1.40</b>	<b>1.39</b>	<b>1.42</b>	<b>1.42</b>	-	-	-	<b>1.36</b>
<b>EXTRANEIOUS MATTER</b>									
Bark		-	*	-	*	-	-	-	*
Grass		-	-	-	0.2	-	-	-	1.0
Spindle Twist		-	*	*	0.2	-	-	-	*
Preparation		0.1	*	-	*	-	-	-	-
All Other		-	*	-	*	-	-	-	0.1

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Feb 19, 2026**

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	-
2.7 - 2.9	-	0.1	-	0.1	-	-	-	0.2
3.0 - 3.2	-	0.6	*	0.5	-	-	-	9.5
3.3 - 3.4	-	0.6	2.2	1.3	-	-	-	13.4
3.5 - 3.6	0.2	4.6	20.8	6.8	-	-	-	19.1
3.7 - 4.2	80.0	87.0	75.9	87.4	-	-	-	54.3
4.3 - 4.9	19.8	7.1	1.1	3.9	-	-	-	3.4
5.0 - 5.2	-	-	-	*	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
<b>Average</b>	<b>4.09</b>	<b>3.97</b>	<b>3.81</b>	<b>3.91</b>	-	-	-	<b>3.71</b>
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	-
2.7	-	*	-	*	-	-	-	*
2.8	-	0.1	-	*	-	-	-	*
2.9	-	*	-	0.1	-	-	-	0.2
3.0	-	0.1	-	0.1	-	-	-	1.5
3.1	-	0.2	-	0.1	-	-	-	3.8
3.2	-	0.4	*	0.2	-	-	-	4.3
3.3	-	0.2	0.1	0.5	-	-	-	4.8
3.4	-	0.4	2.1	0.9	-	-	-	8.7
3.5	-	1.6	8.3	1.9	-	-	-	9.9
3.6	0.2	3.0	12.5	4.8	-	-	-	9.2
3.7	1.8	7.5	16.9	9.4	-	-	-	9.7
3.8	4.9	12.3	20.6	16.0	-	-	-	10.4
3.9	8.9	17.8	11.8	22.0	-	-	-	11.3
4.0	28.7	21.4	11.1	20.7	-	-	-	10.4
4.1	24.3	18.7	11.7	12.7	-	-	-	8.7
4.2	11.5	9.3	3.7	6.6	-	-	-	3.8
4.3	11.4	4.2	1.0	2.5	-	-	-	2.1
4.4	7.8	2.6	-	0.9	-	-	-	0.6
4.5	0.4	0.3	-	0.4	-	-	-	0.4
4.6	-	*	-	0.1	-	-	-	0.2
4.7	-	*	*	*	-	-	-	*
4.8	-	*	-	*	-	-	-	*
4.9	0.1	*	-	*	-	-	-	*
5.0	-	-	-	*	-	-	-	-
5.1	-	-	-	*	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
<b>Average</b>	<b>4.09</b>	<b>3.97</b>	<b>3.81</b>	<b>3.91</b>	-	-	-	<b>3.71</b>
STRENGTH 1/								
36 & Below	-	0.1	-	1.3	-	-	-	10.7
37	-	0.2	-	3.9	-	-	-	16.5
38	-	0.4	-	2.6	-	-	-	17.2
39	0.1	1.2	-	1.1	-	-	-	7.4
40	0.1	4.8	0.6	1.6	-	-	-	2.7
41	5.8	15.5	0.9	5.0	-	-	-	3.1
42	14.7	28.3	4.8	10.1	-	-	-	5.4
43	29.8	28.4	26.1	16.6	-	-	-	7.6
44	40.1	14.6	35.2	20.9	-	-	-	9.9
45	6.1	5.0	19.3	18.7	-	-	-	8.9
46	2.8	1.0	10.7	11.1	-	-	-	6.6
47	0.3	0.2	2.0	4.7	-	-	-	2.7
48 & Above	0.2	0.2	0.4	2.2	-	-	-	1.3
<b>Average</b>	<b>43.83</b>	<b>42.92</b>	<b>44.56</b>	<b>43.92</b>	-	-	-	<b>40.97</b>
UNIFORMITY								
83 & Below	-	0.2	0.3	1.6	-	-	-	3.2
84	1.4	2.6	2.8	11.1	-	-	-	23.4
85	26.2	37.2	45.6	33.3	-	-	-	42.2
86	62.0	53.3	45.3	47.3	-	-	-	28.2
87	10.0	6.5	5.7	6.1	-	-	-	2.9
88 & Above	0.3	0.3	0.1	0.6	-	-	-	0.2
<b>Average</b>	<b>86.33</b>	<b>86.10</b>	<b>85.97</b>	<b>85.91</b>	-	-	-	<b>85.49</b>
<b>Samples Classed</b>	<b>906</b>	<b>21,417</b>	<b>2,073</b>	<b>304,332</b>	-	-	-	<b>34,679</b>

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

\* Less than 0.05 percent.