



Weekly Quality of Cotton Classed by Classing Office: Week Ending - 2/26/2026

Agricultural Marketing Service
Cotton Market News

Volume 67, No.30

February 27, 2026

Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	18	76.5	63.3	19,740	31	80.0	60.3	1,135,991
Corpus Christi*	-	-	-	-	42	88.1	72.5	1,525,582
Dumas	-	-	-	-	33	53.0	25.2	951,046
Florence*	-	-	-	-	40	90.5	79.2	1,110,531
Lamesa	2	79.3	66.8	2,868	24	83.9	59.7	588,421
Lubbock	4	52.2	30.8	2,737	54	78.4	58.4	2,503,646
Macon	-	-	-	-	68	88.6	74.8	2,196,821
Memphis*	-	-	-	-	65	83.4	60.0	2,351,211
Rayville	-	-	-	-	16	69.3	47.6	283,396
Visalia	5	65.1	54.6	9,616	27	85.1	69.9	367,505
United States	32	71.2	53.1	44,935	400	81.7	62.8	13,014,150
AMERICAN PIMA								
Visalia	5			4,461	19			384,136
United States	5			4,461	19			384,136
United States all cotton	37			49,396	409			13,398,286

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

MP_CN100

Source: USDA AMS Cotton and Tobacco Market News
 Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov
<https://www.ams.usda.gov/market-news/cotton>
<https://mymarketnews.ams.usda.gov/cottonmn@ams.usda.gov>

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 26, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA		
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	
Color 11 & 21	1-2	Pct. 31.3	Pct. 36.3	Pct. -	Pct. 14.3	Pct. -	Pct. 0.9	Pct. -	Pct. 0.5	Pct. 50.2	Pct. 71.1	
	3	7.4	6.5	-	14.3	-	0.8	-	0.5	9.5	6.7	
	4	0.3	0.4	-	1.4	-	*	-	*	0.2	0.3	
	5	*	*	-	*	-	*	-	*	-	*	
	6	-	*	-	-	-	-	-	-	-	*	
	7	-	-	-	-	-	-	-	-	-	*	
	8	-	-	-	-	-	-	-	-	-	-	
	Total	----	39.0	43.2	-	30.1	-	1.7	-	1.0	59.9	78.1
	31	1-2	20.4	9.7	-	5.0	-	2.2	-	5.3	19.0	3.2
3		12.8	11.8	-	22.2	-	16.1	-	21.7	16.6	2.1	
4		1.6	3.5	-	9.4	-	7.9	-	6.2	0.2	0.4	
5		0.1	0.5	-	1.0	-	0.5	-	0.3	-	0.1	
6		-	*	-	*	-	*	-	*	-	*	
7		-	*	-	*	-	-	-	-	-	*	
8		-	*	-	-	-	-	-	-	-	-	
Total		----	35.0	25.6	-	37.7	-	26.8	-	33.5	35.8	5.8
41		1-2	3.0	0.4	-	0.6	-	0.6	-	2.5	-	*
	3	3.7	1.6	-	5.3	-	19.0	-	29.0	0.1	*	
	4	1.9	2.0	-	5.0	-	32.8	-	25.0	-	*	
	5	0.4	1.6	-	1.3	-	9.1	-	4.3	-	*	
	6	*	0.7	-	0.1	-	0.6	-	0.3	-	*	
	7	-	0.1	-	*	-	*	-	*	-	*	
	8	-	*	-	-	-	-	-	*	-	-	
	Total	----	9.1	6.4	-	12.4	-	62.2	-	61.2	0.1	0.1
	51	1-2	-	*	-	*	-	*	-	0.1	-	-
3		-	*	-	0.2	-	1.1	-	0.9	-	-	
4		*	*	-	0.4	-	3.0	-	1.6	-	-	
5		-	0.1	-	0.1	-	1.5	-	0.7	-	-	
6		-	0.2	-	*	-	0.2	-	0.1	-	*	
7		-	0.1	-	*	-	*	-	*	-	-	
8		-	*	-	-	-	-	-	*	-	-	
Total		----	*	0.4	-	0.8	-	5.8	-	3.4	-	*
61		1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	
	4	-	-	-	*	-	*	-	*	-	-	
	5	-	-	-	-	-	*	-	*	-	-	
	6	-	-	-	*	-	*	-	*	-	-	
	7	-	-	-	*	-	-	-	-	-	-	
	8	-	*	-	-	-	-	-	-	-	-	
	Total	----	-	*	-	*	-	*	-	*	-	-
	71	1-2	-	-	-	-	-	-	-	-	-	-
3		-	-	-	-	-	-	-	-	-	-	
4		-	-	-	-	-	-	-	-	-	-	
5		-	-	-	-	-	-	-	*	-	-	
6		-	-	-	-	-	-	-	-	-	-	
7		-	-	-	-	-	-	-	-	-	-	
8		-	-	-	-	-	-	-	-	-	-	
Total		----	-	-	-	-	-	-	*	-	-	
12 & 22		1-2	1.2	8.1	-	4.0	-	*	-	*	1.5	10.3
	3	1.9	2.7	-	3.8	-	*	-	*	1.3	2.3	
	4	0.6	0.4	-	1.0	-	*	-	*	-	0.2	
	5	0.1	*	-	0.1	-	-	-	-	-	*	
	6	*	*	-	*	-	-	-	-	-	*	
	7	-	-	-	-	-	-	-	-	-	*	
	8	-	-	-	-	-	-	-	-	-	-	
	Total	----	3.8	11.3	-	8.8	-	*	-	*	2.8	12.9
	32	1-2	3.4	1.9	-	0.6	-	*	-	*	0.5	0.3
3		3.0	2.9	-	2.6	-	0.1	-	0.1	0.9	0.5	
4		0.8	1.5	-	2.4	-	0.1	-	0.1	*	0.2	
5		0.4	0.5	-	0.6	-	*	-	*	-	0.1	
6		0.1	0.1	-	*	-	*	-	*	-	*	
7		-	*	-	*	-	-	-	-	-	*	
8		-	*	-	-	-	-	-	-	-	-	
Total		----	7.6	6.9	-	6.3	-	0.3	-	0.2	1.4	1.1
42		1-2	0.3	0.1	-	0.1	-	*	-	*	-	*
	3	0.9	0.4	-	0.9	-	0.5	-	0.2	-	*	
	4	0.2	0.8	-	1.1	-	1.2	-	0.3	-	*	
	5	0.1	0.9	-	0.6	-	0.6	-	0.1	-	*	
	6	0.1	0.6	-	0.1	-	0.1	-	*	-	*	
	7	*	0.2	-	*	-	*	-	*	-	*	
	8	-	*	-	-	-	-	-	*	-	-	
	Total	----	1.6	3.0	-	2.8	-	2.5	-	0.6	-	*

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 26, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 52	1-2	-	*	-	*	-	*	-	*	-	*
	3	-	*	-	*	-	0.1	-	*	-	*
	4	-	*	-	0.1	-	0.2	-	*	-	-
	5	*	*	-	0.1	-	0.2	-	*	-	*
	6	*	*	-	*	-	0.1	-	*	-	-
	7	*	0.1	-	*	-	*	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
	Total	----	*	0.2	-	0.2	-	0.6	-	0.1	-
62	1-2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	*	-	*	-	-	-	-
	5	-	-	-	*	-	*	-	-	-	-
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
	Total	----	-	*	-	*	-	*	-	*	-
13 & 23	1-2	0.6	0.6	-	0.1	-	-	-	*	-	0.9
	3	0.5	0.4	-	0.1	-	-	-	*	-	0.3
	4	0.4	0.1	-	*	-	-	-	*	-	*
	5	*	*	-	*	-	-	-	-	-	*
	6	-	*	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	1.6	1.2	-	0.2	-	-	-	*	-
33	1-2	0.1	0.2	-	*	-	*	-	*	*	0.1
	3	0.5	0.5	-	0.1	-	*	-	*	*	0.2
	4	0.8	0.3	-	0.1	-	*	-	*	-	0.2
	5	0.3	0.1	-	*	-	-	-	*	-	0.1
	6	*	*	-	*	-	-	-	*	-	*
	7	-	*	-	*	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	1.7	1.1	-	0.3	-	*	-	*	0.1
43	1-2	*	*	-	*	-	-	-	*	-	*
	3	0.2	0.1	-	0.1	-	*	-	*	-	*
	4	0.1	0.1	-	0.1	-	*	-	*	-	*
	5	0.1	0.2	-	0.1	-	*	-	*	-	*
	6	*	0.1	-	*	-	*	-	*	-	*
	7	-	0.1	-	*	-	-	-	*	-	*
	8	-	*	-	-	-	-	-	*	-	-
	Total	----	0.4	0.6	-	0.3	-	*	-	*	-
53	1-2	-	-	-	*	-	*	-	-	-	-
	3	*	*	-	*	-	*	-	*	-	-
	4	*	*	-	*	-	*	-	*	-	-
	5	*	*	-	*	-	*	-	*	-	-
	6	*	*	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	*	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
	Total	----	0.1	*	-	*	-	*	-	*	-
63	1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	*	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	-	*	-	*	-	*	-	-	-
24 - 54	1-8	0.1	0.1	-	*	-	-	-	*	-	0.1
25 - 35	1-8	-	-	-	-	-	-	-	-	-	-
81 - 85	1-8	-	*	-	*	-	-	-	-	-	*
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-
30		*	*	-	-	-	-	-	-	-	*
31		0.2	0.1	-	*	-	*	-	*	*	0.2
32		1.2	0.6	-	*	-	*	-	*	0.5	1.8
33		7.0	3.2	-	0.1	-	0.1	-	0.1	7.1	7.4
34		16.0	9.1	-	0.7	-	1.3	-	1.4	25.8	20.9
35		16.0	15.4	-	3.8	-	8.2	-	8.3	45.6	28.6
36		15.9	18.4	-	15.6	-	25.2	-	26.6	14.1	21.9
37		15.3	23.5	-	45.9	-	42.7	-	47.7	6.7	14.9
38		14.4	14.6	-	25.3	-	16.4	-	12.9	0.2	3.7
39		9.1	9.7	-	7.8	-	4.9	-	2.7	-	0.6
40 & Longer		4.8	5.4	-	0.7	-	1.1	-	0.3	-	*
Average Staple		36.17	36.59	-	37.17	-	36.84	-	36.71	34.87	35.23
Average Length		1.13	1.14	-	1.16	-	1.15	-	1.14	1.09	1.10

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 26, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 11 & 21	1-2	Pct. 38.7	Pct. 57.8	Pct. -	Pct. 1.7	Pct. -	Pct. 0.4	Pct. -	Pct. 3.8	Pct. 9.0	Pct. 18.9
	3	9.0	15.0	-	1.2	-	0.4	-	2.5	1.5	5.0
	4	0.1	0.8	-	*	-	*	-	0.1	*	0.3
	5	-	*	-	*	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	47.8	73.6	-	2.9	-	0.8	-	6.5	10.6
31	1-2	14.5	3.4	-	8.1	-	2.6	-	8.0	16.9	10.8
	3	19.7	5.1	-	21.8	-	12.1	-	32.8	9.3	13.4
	4	3.3	2.0	-	4.2	-	3.4	-	11.5	1.9	3.0
	5	0.1	0.3	-	0.2	-	0.2	-	0.9	0.2	0.4
	6	-	*	-	*	-	*	-	*	*	*
	7	-	*	-	*	-	*	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	37.6	10.8	-	34.3	-	18.3	-	53.2	28.2
41	1-2	0.1	*	-	5.0	-	2.3	-	0.8	10.0	3.6
	3	0.1	0.1	-	31.5	-	30.8	-	12.3	15.5	16.5
	4	0.1	0.2	-	16.5	-	26.7	-	16.3	8.7	10.8
	5	-	0.2	-	2.1	-	5.1	-	4.5	3.6	3.2
	6	-	0.1	-	0.1	-	0.4	-	0.4	0.9	0.6
	7	-	*	-	*	-	*	-	-	0.3	0.1
	8	-	*	-	-	-	-	-	-	0.1	*
	Total	----	0.2	0.5	-	55.3	-	65.4	-	34.3	39.1
51	1-2	-	*	-	0.2	-	0.1	-	*	0.6	0.1
	3	-	*	-	2.4	-	3.0	-	*	0.7	1.4
	4	-	*	-	2.3	-	4.8	-	0.3	2.6	2.5
	5	-	*	-	0.5	-	1.7	-	0.3	3.6	1.6
	6	-	*	-	0.1	-	0.3	-	0.1	2.6	0.7
	7	-	*	-	*	-	*	-	-	1.0	0.2
	8	-	*	-	*	-	-	-	-	0.3	*
	Total	----	-	*	-	5.5	-	9.8	-	0.7	11.3
61	1-2	-	*	-	*	-	*	-	-	*	*
	3	-	*	-	*	-	*	-	*	-	*
	4	-	*	-	*	-	*	-	*	-	*
	5	-	-	-	*	-	*	-	-	-	*
	6	-	-	-	*	-	*	-	-	0.1	*
	7	-	-	-	*	-	*	-	-	0.2	*
	8	-	-	-	*	-	-	-	-	0.1	*
	Total	----	-	*	-	0.1	-	*	-	*	0.3
71	1-2	-	*	-	-	-	*	-	-	-	-
	3	-	*	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	-	*	-	-	-	*	-	-	-
12 & 22	1-2	2.8	6.1	-	*	-	*	-	0.1	1.4	1.8
	3	0.9	3.8	-	*	-	*	-	0.1	0.8	1.0
	4	-	0.5	-	*	-	*	-	0.1	*	0.1
	5	-	*	-	-	-	*	-	*	-	*
	6	-	*	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	3.8	10.3	-	0.1	-	*	-	0.3	2.3
32	1-2	*	0.3	-	0.1	-	*	-	0.1	0.1	0.2
	3	0.4	1.0	-	0.3	-	0.2	-	0.5	0.6	0.5
	4	2.0	0.6	-	0.1	-	0.1	-	0.8	*	0.4
	5	0.3	0.2	-	*	-	*	-	0.4	-	0.1
	6	-	*	-	*	-	*	-	0.1	-	*
	7	-	*	-	-	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	2.7	2.1	-	0.4	-	0.3	-	1.8	0.8
42	1-2	-	*	-	*	-	0.2	-	*	*	*
	3	0.1	*	-	0.5	-	1.7	-	0.4	0.1	0.5
	4	0.1	0.1	-	0.4	-	1.5	-	1.2	0.5	0.5
	5	0.1	0.1	-	0.1	-	0.4	-	0.7	0.4	0.3
	6	-	*	-	*	-	0.1	-	0.4	*	0.1
	7	-	*	-	*	-	*	-	-	-	*
	8	-	*	-	-	-	-	-	-	*	*
	Total	----	0.2	0.2	-	1.1	-	3.8	-	2.7	1.0

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 26, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA		
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	
Color 52	1-2	-	-	-	*	-	*	-	-	-	*	
	3	-	-	-	0.1	-	0.4	-	*	*	0.1	
	4	-	*	-	0.1	-	0.6	-	0.1	0.3	0.2	
	5	-	*	-	*	-	0.3	-	0.1	1.0	0.2	
	6	-	*	-	*	-	0.1	-	*	0.9	0.1	
	7	-	*	-	*	-	*	-	*	0.6	0.1	
	8	-	*	-	*	-	-	-	-	0.7	*	
	Total	----	-	*	-	0.2	-	1.4	-	0.1	3.5	0.8
	62	1-2	-	-	-	*	-	-	-	-	-	-
3		-	-	-	*	-	*	-	-	-	*	
4		-	-	-	*	-	*	-	-	-	*	
5		-	-	-	*	-	*	-	-	-	*	
6		-	-	-	*	-	*	-	-	0.1	*	
7		-	-	-	*	-	*	-	-	0.2	*	
8		-	-	-	*	-	-	-	-	0.2	*	
Total		----	-	-	-	*	-	*	-	-	0.4	*
13 & 23		1-2	5.4	0.7	-	*	-	-	-	-	0.8	0.1
	3	0.4	0.6	-	*	-	-	-	-	0.6	0.1	
	4	-	0.1	-	*	-	-	-	-	*	*	
	5	-	*	-	*	-	-	-	-	-	-	
	6	-	*	-	-	-	-	-	-	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	*	-	-	-	-	-	-	-	-	
	Total	----	5.8	1.4	-	*	-	-	-	-	1.4	0.2
	33	1-2	0.1	0.1	-	*	-	*	-	*	*	*
3		0.1	0.3	-	*	-	*	-	*	0.4	0.1	
4		*	0.2	-	*	-	*	-	*	0.1	*	
5		-	0.1	-	*	-	*	-	*	-	*	
6		-	*	-	*	-	*	-	*	-	*	
7		-	*	-	-	-	-	-	-	-	-	
8		-	*	-	-	-	-	-	-	-	-	
Total		----	0.2	0.8	-	*	-	*	-	0.1	0.5	0.1
43		1-2	-	*	-	*	-	*	-	*	-	*
	3	-	*	-	*	-	*	-	*	*	*	
	4	-	*	-	*	-	*	-	*	*	*	
	5	-	*	-	*	-	*	-	*	*	*	
	6	-	*	-	*	-	*	-	*	*	*	
	7	-	*	-	*	-	*	-	-	-	-	
	8	-	*	-	-	-	-	-	-	-	-	
	Total	----	-	0.1	-	0.1	-	0.1	-	0.1	0.2	0.1
	53	1-2	-	-	-	*	-	*	-	-	-	*
3		-	-	-	*	-	*	-	-	-	*	
4		-	-	-	*	-	*	-	-	-	*	
5		-	-	-	*	-	*	-	*	*	*	
6		-	*	-	*	-	*	-	*	*	*	
7		-	*	-	*	-	*	-	-	-	*	
8		-	*	-	-	-	-	-	-	-	*	
Total		----	-	*	-	*	-	*	-	*	*	*
63		1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	
	4	-	-	-	*	-	-	-	-	-	-	
	5	-	-	-	*	-	-	-	-	-	-	
	6	-	-	-	-	-	-	-	-	-	-	
	7	-	*	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	Total	----	-	*	-	*	-	-	-	-	-	-
	24 - 54	1-8	1.8	0.1	-	*	-	*	-	0.1	0.3	*
25 - 35	1-8	-	-	-	-	-	-	-	-	-	-	
81 - 85	1-8	-	*	-	*	-	*	-	-	-	-	
STAPLE												
28 & Shorter		-	-	-	-	-	-	-	-	-	-	
29		-	*	-	-	-	-	-	-	-	-	
30		-	*	-	*	-	-	-	*	*	*	
31		-	0.1	-	*	-	*	-	0.1	*	*	
32		-	0.5	-	0.1	-	*	-	*	1.0	0.1	
33		1.1	2.6	-	0.8	-	0.1	-	0.2	1.4	0.2	
34		10.1	8.7	-	4.7	-	0.8	-	1.6	5.5	1.0	
35		34.6	18.3	-	15.4	-	4.1	-	11.2	21.8	4.4	
36		41.0	25.8	-	30.1	-	15.1	-	28.8	22.2	15.6	
37		13.2	29.2	-	35.7	-	47.6	-	39.8	33.6	41.6	
38		*	10.5	-	10.2	-	26.9	-	14.2	13.0	23.2	
39		-	3.1	-	2.5	-	4.9	-	3.8	1.0	7.9	
40 & Longer		-	1.0	-	0.4	-	0.5	-	0.4	0.3	6.1	
Average Staple		35.55	36.18	-	36.38	-	37.12	-	36.66	36.23	37.46	
Average Length		1.11	1.13	-	1.13	-	1.16	-	1.14	1.13	1.17	

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 26, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	9.2	9.5	-	0.6	-	*	-	2.1	15.6	1.7
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	0.2	0.1	-	0.3	-	0.1	-	*	-	0.3
Grass - Level 2	-	-	-	*	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	-	*	-	-
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	-	1.5	-	0.8	0.1	0.1
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	*	*	-	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	*
Other - Level 2	-	*	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	0.1	-	*	-	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	*	*	-	*	-	-	-	-	*	*
23	*	*	-	*	-	-	-	-	0.1	0.1
24	0.2	*	-	*	-	*	-	*	0.7	0.2
25	0.6	0.2	-	*	-	*	-	*	3.0	0.9
26	1.9	0.7	-	0.2	-	0.1	-	0.5	6.4	2.7
27	7.3	2.9	-	1.2	-	0.5	-	3.0	11.8	7.5
28	16.6	8.2	-	5.2	-	3.9	-	12.6	19.8	14.1
29	22.7	15.0	-	14.8	-	15.4	-	30.5	23.0	19.9
30	21.1	17.8	-	21.7	-	28.5	-	30.3	19.7	22.0
31	16.2	17.0	-	17.7	-	26.8	-	15.3	9.4	17.6
32	6.7	14.2	-	12.5	-	15.8	-	5.8	3.6	9.3
33	3.3	11.1	-	11.5	-	6.3	-	1.6	1.8	3.7
34	1.9	7.0	-	9.6	-	2.1	-	0.3	0.5	1.3
35	1.0	3.6	-	4.0	-	0.5	-	0.1	0.1	0.5
36	0.4	1.3	-	1.1	-	0.1	-	*	0.1	0.2
37	0.1	0.6	-	0.2	-	*	-	*	-	*
38	*	0.2	-	*	-	*	-	-	-	*
39	*	*	-	*	-	*	-	-	-	-
40 & Above	-	*	-	-	-	*	-	-	-	-
Average	30.11	31.40	-	31.59	-	31.09	-	30.12	29.26	30.13
Mike										
2.4 & Below	0.4	0.1	-	-	-	-	-	-	0.3	*
2.5	1.0	0.2	-	*	-	-	-	*	0.5	0.1
2.6	1.2	0.3	-	*	-	-	-	-	0.4	0.2
2.7	1.5	0.4	-	*	-	-	-	*	0.2	0.3
2.8	1.7	0.5	-	*	-	-	-	*	0.9	0.4
2.9	1.6	0.5	-	*	-	-	-	*	0.4	0.6
3.0	1.1	0.6	-	0.1	-	-	-	*	*	0.9
3.1	1.6	0.8	-	0.1	-	-	-	*	0.2	0.9
3.2	1.9	1.1	-	0.3	-	*	-	0.1	0.3	1.3
3.3	1.2	1.4	-	0.5	-	*	-	0.2	0.5	1.6
3.4	1.1	1.8	-	0.9	-	*	-	0.3	1.7	2.0
3.5	1.9	2.5	-	1.3	-	*	-	0.5	2.3	2.5
3.6	3.6	3.4	-	1.9	-	0.1	-	0.9	6.1	3.2
3.7	5.6	4.4	-	2.7	-	0.1	-	1.8	8.6	3.9
3.8	7.0	5.5	-	4.4	-	0.1	-	2.7	5.9	4.7
3.9	8.1	7.0	-	6.7	-	0.2	-	4.2	5.7	5.5
4.0	8.5	8.5	-	9.0	-	0.4	-	5.8	8.3	6.2
4.1	9.3	10.0	-	11.1	-	0.6	-	7.8	10.3	7.0
4.2	10.3	10.6	-	12.8	-	1.0	-	9.9	10.6	8.0
4.3	9.6	10.7	-	12.9	-	1.7	-	11.6	14.5	8.6
4.4	9.0	9.5	-	11.3	-	2.8	-	11.8	12.2	9.1
4.5	5.6	7.7	-	8.8	-	4.1	-	10.7	7.1	8.9
4.6	3.1	5.5	-	6.0	-	6.5	-	9.4	1.8	8.1
4.7	2.8	3.5	-	3.7	-	9.5	-	7.7	0.1	6.4
4.8	1.0	2.0	-	2.3	-	13.4	-	5.5	0.2	4.4
4.9	0.2	0.9	-	1.3	-	16.0	-	3.9	1.0	2.6
5.0	*	0.4	-	0.8	-	16.3	-	2.5	-	1.4
5.1	-	0.2	-	0.4	-	12.9	-	1.4	-	0.6
5.2	-	0.1	-	0.3	-	8.2	-	0.7	-	0.3
5.3	-	*	-	0.2	-	4.0	-	0.3	-	0.1
5.4	-	-	-	0.1	-	1.5	-	0.1	-	*
5.5 & Above	-	*	-	0.2	-	0.5	-	*	-	*
Average	3.96	4.10	-	4.23	-	4.88	-	4.38	4.05	4.19

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 26, 2026

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	14.5	7.7	-	1.3	-	*	-	2.0	17.2	0.9
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	-	0.1	-	0.1	-	*	-	0.1	0.2	0.4
Grass - Level 2	-	*	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	-	-	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	0.4	-	0.3	-	0.1	-	2.9	-	0.1
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	-	-	*	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	*
Spindle Twist - Level 2	-	*	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	0.2	*	-	*	-	*	-	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	-	*	-	-	-	*	-	-	*	*
23	-	*	-	*	-	*	-	-	0.2	*
24	-	0.1	-	*	-	*	-	-	0.4	*
25	0.3	0.2	-	0.1	-	*	-	*	1.3	0.1
26	1.4	0.7	-	0.6	-	*	-	0.1	6.2	0.9
27	7.9	2.6	-	3.2	-	0.2	-	1.7	11.8	2.9
28	22.6	7.2	-	10.7	-	1.8	-	6.6	14.3	8.9
29	29.7	14.6	-	20.6	-	12.4	-	17.9	18.8	16.8
30	20.9	20.2	-	25.1	-	36.0	-	30.0	22.4	20.6
31	11.5	19.9	-	19.9	-	32.5	-	20.1	15.0	17.9
32	4.2	15.1	-	11.5	-	12.2	-	12.6	6.9	11.8
33	1.4	9.8	-	5.3	-	3.8	-	6.0	1.4	7.3
34	0.2	5.5	-	2.1	-	0.9	-	3.1	0.6	5.6
35	-	2.5	-	0.7	-	0.1	-	1.5	0.2	4.0
36	-	1.0	-	0.2	-	*	-	0.2	0.1	2.1
37	-	0.4	-	*	-	*	-	*	*	0.7
38	-	0.1	-	*	-	*	-	*	*	0.1
39	-	*	-	*	-	-	-	-	0.1	*
40 & Above	-	-	-	*	-	-	-	-	0.2	*
Average	29.64	31.28	-	30.62	-	31.01	-	30.93	29.67	31.22
Mike										
2.4 & Below	0.1	*	-	-	-	-	-	-	0.3	*
2.5	*	0.1	-	*	-	-	-	*	1.6	0.1
2.6	0.2	0.1	-	*	-	-	-	*	1.9	0.1
2.7	0.7	0.2	-	*	-	*	-	*	2.5	0.1
2.8	1.1	0.4	-	*	-	*	-	*	2.8	0.3
2.9	2.4	0.6	-	*	-	*	-	*	1.9	0.3
3.0	3.4	0.9	-	*	-	*	-	*	2.2	0.4
3.1	3.3	1.3	-	*	-	*	-	0.1	2.2	0.5
3.2	4.6	1.8	-	0.1	-	*	-	0.1	2.0	0.9
3.3	9.5	2.4	-	0.2	-	*	-	0.1	3.8	0.8
3.4	10.1	3.0	-	0.3	-	0.1	-	0.1	3.0	0.9
3.5	10.5	3.8	-	0.6	-	0.1	-	0.2	4.0	1.5
3.6	11.4	4.4	-	1.1	-	0.2	-	0.4	3.5	2.0
3.7	10.1	5.0	-	1.9	-	0.4	-	0.5	3.8	2.9
3.8	9.9	5.6	-	2.8	-	0.6	-	0.7	7.5	3.8
3.9	6.4	6.1	-	4.1	-	1.0	-	1.1	7.5	5.2
4.0	4.7	6.5	-	5.6	-	1.7	-	1.9	7.1	6.7
4.1	3.5	6.9	-	7.4	-	2.6	-	3.5	10.0	8.1
4.2	2.7	7.3	-	9.1	-	4.0	-	4.5	9.5	9.2
4.3	2.1	7.6	-	10.0	-	5.7	-	5.6	7.3	9.3
4.4	1.9	7.7	-	10.3	-	8.2	-	6.6	4.9	8.9
4.5	0.7	7.3	-	9.9	-	11.0	-	8.6	2.2	8.9
4.6	0.3	6.6	-	9.1	-	13.9	-	9.7	2.5	8.2
4.7	*	5.4	-	8.2	-	15.2	-	10.6	1.7	6.7
4.8	-	3.8	-	6.5	-	13.8	-	11.4	1.8	5.0
4.9	-	2.4	-	4.9	-	10.1	-	10.5	1.8	3.7
5.0	-	1.4	-	3.4	-	6.3	-	8.3	0.8	2.4
5.1	-	0.7	-	2.2	-	3.1	-	6.9	0.1	1.3
5.2	-	0.4	-	1.2	-	1.2	-	4.0	-	0.8
5.3	-	0.2	-	0.6	-	0.4	-	2.2	-	0.6
5.4	-	0.1	-	0.2	-	0.1	-	1.1	-	0.3
5.5 & Above	-	0.1	-	0.1	-	*	-	1.1	-	0.3
Average	3.59	4.11	-	4.41	-	4.62	-	4.67	3.84	4.29

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 26, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	0.4	0.1	-	-	-	-	-	-	0.3	*
2.5 - 2.6	2.2	0.5	-	*	-	-	-	*	0.8	0.3
2.7 - 2.9	4.8	1.4	-	0.1	-	-	-	*	1.5	1.3
3.0 - 3.2	4.6	2.5	-	0.5	-	*	-	0.2	0.5	3.1
3.3 - 3.4	2.3	3.2	-	1.4	-	*	-	0.5	2.1	3.7
3.5 - 3.6	5.6	5.9	-	3.1	-	0.1	-	1.5	8.4	5.7
3.7 - 4.2	48.8	46.0	-	46.6	-	2.5	-	32.1	49.4	35.3
4.3 - 4.9	31.3	39.8	-	46.4	-	54.0	-	60.6	36.9	48.2
5.0 - 5.2	*	0.6	-	1.4	-	37.4	-	4.6	-	2.3
5.3 & Above	-	*	-	0.5	-	6.1	-	0.4	-	0.1
Average	3.96	4.10	-	4.23	-	4.88	-	4.38	4.05	4.19
Leaf										
1 - 2	60.4	57.4	-	24.8	-	3.8	-	8.4	71.3	86.0
3	31.0	27.0	-	49.7	-	37.7	-	52.5	28.3	12.3
4	6.8	9.1	-	21.1	-	45.4	-	33.2	0.4	1.4
5	1.5	4.0	-	4.0	-	12.0	-	5.4	-	0.3
6	0.3	1.8	-	0.5	-	1.1	-	0.4	-	0.1
7	*	0.6	-	0.1	-	*	-	*	-	*
8	-	0.1	-	*	-	-	-	*	-	-
Average	2.36	2.52	-	3.03	-	3.69	-	3.37	2.17	1.76
HVI Trash 1/										
00	*	*	-	*	-	-	-	-	-	0.6
01	27.2	28.2	-	5.1	-	0.3	-	0.6	26.6	59.1
02	37.9	32.5	-	22.5	-	4.6	-	10.2	52.9	29.9
03	19.4	15.9	-	27.9	-	14.9	-	24.6	17.5	7.2
04	7.8	8.3	-	20.4	-	22.9	-	26.2	2.7	2.0
05	3.4	4.7	-	12.1	-	22.0	-	18.8	0.4	0.7
06	2.0	2.9	-	6.4	-	15.8	-	10.7	-	0.3
07	1.1	2.0	-	3.1	-	9.7	-	5.2	-	0.1
08	0.6	1.5	-	1.4	-	5.2	-	2.3	-	0.1
09	0.3	1.1	-	0.6	-	2.6	-	0.9	-	*
10	0.1	0.8	-	0.3	-	1.2	-	0.4	-	*
11	*	0.6	-	0.1	-	0.5	-	0.2	-	*
12	*	0.5	-	0.1	-	0.2	-	0.1	-	*
13	*	0.3	-	*	-	0.1	-	*	-	*
14	*	0.2	-	*	-	*	-	*	-	*
15	-	0.1	-	*	-	*	-	*	-	-
16	-	0.1	-	*	-	-	-	*	-	*
17	-	0.1	-	*	-	-	-	*	-	*
18 & Above	-	0.1	-	*	-	-	-	*	-	-
Average	0.24	0.29	-	0.36	-	0.50	-	0.43	0.20	0.16
UNIFORMITY 2/										
74 & Below	0.1	*	-	*	-	-	-	*	-	*
75	0.4	0.1	-	*	-	-	-	*	-	0.1
76	1.2	0.2	-	*	-	*	-	*	0.2	0.5
77	5.1	1.0	-	0.1	-	*	-	*	1.0	2.3
78	14.0	3.6	-	0.7	-	0.2	-	0.5	6.6	9.8
79	24.7	13.4	-	3.7	-	1.0	-	2.9	28.5	24.8
80	27.9	28.2	-	13.4	-	7.0	-	12.0	43.7	35.9
81	18.2	28.7	-	30.1	-	28.1	-	28.8	18.2	21.6
82	6.3	16.5	-	31.1	-	37.9	-	35.0	1.8	4.6
83	1.7	6.7	-	16.1	-	20.5	-	18.2	0.1	0.5
84	0.4	1.5	-	4.3	-	5.1	-	2.3	-	*
85 & Above	*	0.1	-	0.4	-	0.2	-	0.2	-	*
Average	80.06	81.09	-	82.00	-	82.30	-	82.04	80.22	80.23
Tenderable 3/	76.5	80.0	-	88.1	-	53.0	-	90.5	79.3	83.9
SAMPLES CLASSED										
Week	19,740		-		-		-		2,868	
Season		1,135,991		1,525,582		951,046		1,110,531		588,421

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 26, 2026

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	0.1	*	-	-	-	-	-	-	0.3	*
2.5 - 2.6	0.3	0.2	-	*	-	-	-	*	3.5	0.2
2.7 - 2.9	4.2	1.2	-	*	-	*	-	0.1	7.3	0.7
3.0 - 3.2	11.4	4.0	-	0.1	-	*	-	0.1	6.4	1.7
3.3 - 3.4	19.6	5.4	-	0.5	-	0.1	-	0.2	6.8	1.7
3.5 - 3.6	21.9	8.2	-	1.8	-	0.3	-	0.6	7.5	3.5
3.7 - 4.2	37.4	37.3	-	30.8	-	10.3	-	12.3	45.4	35.7
4.3 - 4.9	5.0	40.8	-	58.9	-	78.1	-	63.0	22.1	50.8
5.0 - 5.2	-	2.5	-	6.9	-	10.6	-	19.3	0.9	4.5
5.3 & Above	-	0.3	-	1.0	-	0.6	-	4.3	-	1.2
Average	3.59	4.11	-	4.41	-	4.62	-	4.67	3.84	4.29
Leaf										
1 - 2	63.3	68.5	-	15.3	-	5.7	-	12.7	39.1	35.6
3	30.6	25.9	-	57.9	-	48.6	-	48.8	29.8	38.5
4	5.7	4.4	-	23.7	-	37.1	-	30.5	14.2	17.9
5	0.5	0.9	-	3.0	-	7.7	-	6.9	8.8	5.9
6	-	0.2	-	0.2	-	0.8	-	1.0	4.6	1.6
7	-	*	-	*	-	0.1	-	*	2.2	0.3
8	-	*	-	*	-	-	-	-	1.2	0.1
Average	2.35	2.21	-	3.15	-	3.49	-	3.34	3.18	2.94
HVI Trash 1/										
00	-	*	-	-	-	*	-	-	-	*
01	19.8	33.2	-	1.6	-	0.5	-	1.6	10.6	13.4
02	43.3	41.5	-	19.8	-	7.2	-	14.0	31.1	27.6
03	21.9	15.5	-	31.4	-	21.1	-	24.1	18.5	21.9
04	8.8	5.5	-	23.6	-	26.2	-	23.3	10.2	14.7
05	4.4	2.2	-	12.9	-	20.2	-	16.3	6.7	9.2
06	1.4	1.0	-	6.1	-	12.2	-	9.7	5.7	5.5
07	0.3	0.5	-	2.7	-	6.5	-	5.3	4.5	3.3
08	*	0.3	-	1.1	-	3.2	-	2.7	3.4	2.0
09	-	0.1	-	0.5	-	1.5	-	1.5	2.4	1.1
10	-	0.1	-	0.2	-	0.7	-	0.8	1.9	0.6
11	-	0.1	-	0.1	-	0.3	-	0.4	1.4	0.4
12	-	*	-	*	-	0.1	-	0.2	1.1	0.2
13	-	*	-	*	-	0.1	-	0.1	0.7	0.1
14	-	*	-	*	-	*	-	*	0.6	0.1
15	-	*	-	*	-	*	-	-	0.4	*
16	-	*	-	*	-	-	-	-	0.2	*
17	-	*	-	*	-	-	-	*	0.2	*
18 & Above	-	*	-	*	-	-	-	-	0.5	*
Average	0.24	0.21	-	0.37	-	0.46	-	0.42	0.40	0.34
UNIFORMITY 2/										
74 & Below	*	*	-	-	-	-	-	-	-	-
75	*	*	-	*	-	-	-	-	-	*
76	0.3	0.2	-	*	-	*	-	-	0.2	*
77	3.2	1.1	-	0.1	-	*	-	-	2.2	0.2
78	11.7	4.5	-	0.8	-	0.1	-	0.2	10.7	1.1
79	24.5	14.3	-	5.1	-	0.4	-	1.9	18.4	4.3
80	30.0	29.9	-	20.1	-	3.9	-	10.6	24.3	18.2
81	18.8	31.7	-	36.4	-	20.7	-	32.1	30.7	33.7
82	7.3	14.7	-	27.8	-	45.7	-	37.3	13.1	30.6
83	3.3	3.1	-	8.4	-	26.3	-	15.7	0.3	10.0
84	0.8	0.4	-	1.2	-	2.7	-	2.1	*	1.8
85 & Above	0.1	0.1	-	0.1	-	0.2	-	0.1	*	0.2
Average	80.34	80.90	-	81.60	-	82.47	-	82.05	80.54	81.71
Tenderable 3/	52.2	78.4	-	88.6	-	83.4	-	69.3	65.1	85.1
SAMPLES CLASSIFIED										
Week	2,737		-		-		-		9,616	
Season		2,503,646		2,196,821		2,351,211		283,396		367,505

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Feb 26, 2026

Color Grade	Leaf	VISALIA		Quality Designation	VISALIA	
		Week	Season		Week	Season
01	1	5.2	6.3	MIKE		
	2	17.6	7.7	2.4 & Below	-	-
	3	2.3	0.2	2.5 - 2.6	-	-
	4	-	-	2.7 - 2.9	-	0.2
	5	-	-	3.0 - 3.2	*	1.6
	6	-	-	3.3 - 3.4	2.8	2.8
	7	-	-	3.5 - 3.6	8.4	8.6
Total		25.0	14.2	3.7 - 4.2	88.7	82.9
02	1	4.1	7.5	4.3 - 4.9	0.1	4.0
	2	18.8	34.5	5.0 - 5.2	*	*
	3	13.2	8.3	5.3 & Above	-	-
	4	0.7	0.2	Average	3.84	3.89
	5	-	*	ALL RANGE MIKE		
	6	-	-	2.4 & Below	-	-
	7	-	-	2.5	-	-
Total		36.8	50.5	2.6	-	-
03	1	1.4	0.7	2.7	-	*
	2	11.0	13.0	2.8	-	*
	3	16.0	15.6	2.9	-	0.1
	4	6.7	1.9	3.0	-	0.3
	5	0.2	0.1	3.1	-	0.6
	6	-	*	3.2	*	0.8
	7	-	-	3.3	*	1.0
Total		35.2	31.2	3.4	2.8	1.8
04	1	*	*	3.5	4.1	3.0
	2	2.1	0.6	3.6	4.2	5.5
	3	0.4	1.9	3.7	18.2	9.7
	4	0.3	0.8	3.8	26.0	15.2
	5	0.1	0.1	3.9	16.9	20.2
	6	-	*	4.0	14.5	19.1
	7	-	-	4.1	8.6	12.3
Total		2.8	3.4	4.2	4.6	6.3
05	1	-	*	4.3	*	2.5
	2	0.1	0.1	4.4	*	1.0
	3	*	0.2	4.5	*	0.4
	4	-	0.2	4.6	-	0.1
	5	*	*	4.7	-	*
	6	-	*	4.8	-	*
	7	-	-	4.9	-	*
Total		0.1	0.5	5.0	*	*
06	1	-	-	5.1	-	*
	2	-	*	5.2	-	-
	3	-	0.1	5.3 & Above	-	-
	4	-	*	Average	3.84	3.89
	5	-	*	STRENGTH 1/		
	6	-	*	36 & Below	2.0	2.7
	7	-	-	37	11.6	4.9
Total		-	0.1	38	13.4	3.9
07	1	-	-	39	1.5	1.7
	2	-	-	40	0.6	2.0
	3	-	*	41	5.5	5.6
	4	-	*	42	9.4	11.0
	5	-	*	43	16.0	16.6
	6	-	*	44	19.7	19.4
	7	-	-	45	18.8	16.6
Total		-	*	46	1.1	9.7
STAPLE	44 & Shorter	2.0	2.8	47	0.2	4.1
	46	25.5	11.4	48 & Above	0.2	1.9
	48	53.5	46.1	Average	42.30	43.49
	50	18.9	37.6	UNIFORMITY		
	52 & Longer	0.2	2.0	83 & Below	0.6	1.6
	Average Staple	47.79	48.49	84	26.6	11.9
	Average Length	1.39	1.41	85	32.5	34.5
EXTRANEOUS MATTER	Bark	-	*	86	36.8	45.7
	Grass	*	0.3	87	3.5	5.8
	Spindle Twist	*	0.1	88 & Above	*	0.5
	Preparation	-	*	Average	85.64	85.88
	All Other	-	*	Samples Classed		
				Week	4,461	
				Season		384,136

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.