



Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	5	90.2	69.0	11,977	31	80.3	60.6	1,197,990
Corpus Christi*	-	-	-	-	42	88.1	72.6	1,526,527
Dumas	-	-	-	-	33	53.0	25.2	951,056
Florence	-	-	-	-	40	90.5	79.2	1,110,533
Lamesa	-	-	-	-	24	83.8	59.6	590,576
Lubbock*	-	-	-	-	55	78.3	58.3	2,511,777
Macon	-	-	-	-	68	88.6	74.8	2,197,597
Memphis	-	-	-	-	65	83.4	60.0	2,351,211
Rayville	-	-	-	-	16	69.3	47.6	283,396
Visalia	-	-	-	-	27	85.1	69.8	369,520
United States	7	90.4	69.5	12,197	401	81.7	62.8	13,090,183
AMERICAN PIMA								
Visalia*	-	-	-	-	19	-	-	390,579
United States*	-	-	-	-	19	-	-	390,579
United States all cotton	8	-	-	12,997	410	-	-	13,480,762

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

Source: USDA AMS Cotton and Tobacco Market News
 Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov
<https://www.ams.usda.gov/market-news/cotton>
<https://mymarketnews.ams.usda.gov/cottonmn@ams.usda.gov>

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 02, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA		
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	
Color 11 & 21	1-2	Pct. 33.2	Pct. 35.8	Pct. -	Pct. 14.3	Pct. -	Pct. 0.9	Pct. -	Pct. 0.5	Pct. -	Pct. 71.1	
	3	12.7	6.9	-	14.3	-	0.8	-	0.5	-	6.7	
	4	0.1	0.4	-	1.4	-	*	-	*	-	0.3	
	5	-	*	-	*	-	*	-	*	-	*	
	6	-	*	-	-	-	-	-	-	-	*	
	7	-	-	-	-	-	-	-	-	-	*	
	8	-	-	-	-	-	-	-	-	-	-	
	Total	----	46.0	43.0	-	30.0	-	1.7	-	1.0	-	78.0
	31	1-2	13.1	10.0	-	5.0	-	2.2	-	5.3	-	3.2
3		18.1	12.4	-	22.2	-	16.1	-	21.7	-	2.1	
4		3.1	3.6	-	9.4	-	7.9	-	6.2	-	0.4	
5		0.1	0.5	-	1.0	-	0.5	-	0.3	-	0.1	
6		-	*	-	*	-	*	-	*	-	*	
7		-	*	-	*	-	-	-	-	-	*	
8		-	*	-	-	-	-	-	-	-	-	
Total		----	34.3	26.6	-	37.7	-	26.8	-	33.5	-	5.8
41		1-2	0.6	0.5	-	0.6	-	0.6	-	2.5	-	*
	3	2.3	1.6	-	5.3	-	19.0	-	29.0	-	*	
	4	1.3	1.9	-	5.0	-	32.8	-	25.0	-	*	
	5	0.2	1.5	-	1.3	-	9.1	-	4.3	-	*	
	6	*	0.6	-	0.1	-	0.6	-	0.3	-	*	
	7	-	0.1	-	*	-	*	-	*	-	*	
	8	-	*	-	-	-	-	-	*	-	-	
	Total	----	4.4	6.3	-	12.4	-	62.2	-	61.2	-	0.1
	51	1-2	-	*	-	*	-	*	-	0.1	-	-
3		-	*	-	0.2	-	1.1	-	0.9	-	-	
4		-	*	-	0.4	-	3.0	-	1.6	-	-	
5		*	0.1	-	0.1	-	1.5	-	0.7	-	-	
6		-	0.2	-	*	-	0.2	-	0.1	-	*	
7		-	0.1	-	*	-	*	-	*	-	-	
8		-	*	-	-	-	-	-	*	-	-	
Total		----	*	0.4	-	0.8	-	5.8	-	3.4	-	*
61		1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	
	4	-	-	-	*	-	*	-	*	-	-	
	5	-	-	-	-	-	*	-	*	-	-	
	6	-	-	-	*	-	*	-	*	-	-	
	7	-	-	-	*	-	-	-	-	-	-	
	8	-	*	-	-	-	-	-	-	-	-	
	Total	----	-	*	-	*	-	*	-	*	-	-
	71	1-2	-	-	-	-	-	-	-	-	-	-
3		-	-	-	-	-	-	-	-	-	-	
4		-	-	-	-	-	-	-	-	-	-	
5		-	-	-	-	-	-	-	*	-	-	
6		-	-	-	-	-	-	-	-	-	-	
7		-	-	-	-	-	-	-	-	-	-	
8		-	-	-	-	-	-	-	-	-	-	
Total		----	-	-	-	-	-	-	*	-	-	
12 & 22		1-2	4.6	7.8	-	4.0	-	*	-	*	-	10.4
	3	0.4	2.6	-	3.8	-	*	-	*	-	2.4	
	4	*	0.4	-	1.0	-	*	-	*	-	0.2	
	5	-	*	-	0.1	-	-	-	-	-	*	
	6	-	*	-	*	-	-	-	-	-	*	
	7	-	-	-	-	-	-	-	-	-	*	
	8	-	-	-	-	-	-	-	-	-	-	
	Total	----	5.0	10.9	-	8.8	-	*	-	*	-	12.9
	32	1-2	4.6	1.9	-	0.6	-	*	-	*	-	0.3
3		1.5	2.9	-	2.6	-	0.1	-	0.1	-	0.5	
4		1.0	1.5	-	2.4	-	0.1	-	0.1	-	0.2	
5		0.2	0.5	-	0.6	-	*	-	*	-	0.1	
6		-	0.1	-	*	-	*	-	*	-	*	
7		-	*	-	*	-	-	-	-	-	*	
8		-	*	-	-	-	-	-	-	-	-	
Total		----	7.3	6.9	-	6.3	-	0.3	-	0.2	-	1.1
42		1-2	0.1	0.1	-	0.1	-	*	-	*	-	*
	3	0.2	0.4	-	0.9	-	0.5	-	0.2	-	*	
	4	0.1	0.8	-	1.1	-	1.2	-	0.3	-	*	
	5	0.1	0.9	-	0.6	-	0.6	-	0.1	-	*	
	6	-	0.6	-	0.1	-	0.1	-	*	-	*	
	7	-	0.2	-	*	-	*	-	*	-	*	
	8	-	*	-	-	-	-	-	*	-	-	
	Total	----	0.4	2.9	-	2.8	-	2.5	-	0.6	-	*

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 02, 2026

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA		
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	
Color 52	1-2	-	*	-	*	-	*	-	*	-	*	
	3	-	*	-	*	-	0.1	-	*	-	*	
	4	*	*	-	0.1	-	0.2	-	*	-	-	
	5	-	*	-	0.1	-	0.2	-	*	-	*	
	6	-	*	-	*	-	0.1	-	*	-	-	
	7	-	0.1	-	*	-	*	-	*	-	-	
	8	-	*	-	-	-	-	-	*	-	-	
	Total	----	*	0.2	-	0.2	-	0.6	-	0.1	-	*
	62	1-2	-	-	-	*	-	-	-	-	-	-
3		-	-	-	*	-	*	-	-	-	-	
4		-	-	-	*	-	*	-	*	-	-	
5		-	-	-	*	-	*	-	*	-	-	
6		-	-	-	*	-	*	-	-	-	-	
7		-	-	-	*	-	-	-	-	-	-	
8		-	*	-	*	-	-	-	-	-	-	
Total		----	-	*	-	*	-	*	-	*	-	-
13 & 23		1-2	0.9	0.6	-	0.1	-	-	-	*	-	0.9
	3	0.1	0.4	-	0.1	-	-	-	*	-	0.3	
	4	-	0.1	-	*	-	-	-	*	-	*	
	5	-	*	-	*	-	-	-	-	-	*	
	6	-	*	-	*	-	-	-	-	-	*	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	Total	----	1.0	1.2	-	0.2	-	-	-	*	-	1.3
	33	1-2	0.8	0.2	-	*	-	*	-	*	-	0.1
3		0.3	0.5	-	0.1	-	*	-	*	-	0.2	
4		*	0.3	-	0.1	-	*	-	*	-	0.2	
5		-	0.1	-	*	-	-	-	*	-	0.1	
6		-	*	-	*	-	-	-	*	-	*	
7		-	*	-	*	-	-	-	-	-	*	
8		-	*	-	-	-	-	-	-	-	-	
Total		----	1.1	1.1	-	0.3	-	*	-	*	-	0.6
43		1-2	*	*	-	*	-	-	-	*	-	*
	3	*	0.1	-	0.1	-	*	-	*	-	*	
	4	*	0.1	-	0.1	-	*	-	*	-	*	
	5	-	0.2	-	0.1	-	*	-	*	-	*	
	6	-	0.1	-	*	-	*	-	*	-	*	
	7	-	*	-	*	-	-	-	*	-	*	
	8	-	*	-	-	-	-	-	*	-	-	
	Total	----	0.1	0.6	-	0.3	-	*	-	*	-	*
	53	1-2	-	-	-	*	-	*	-	-	-	-
3		*	*	-	*	-	*	-	*	-	-	
4		-	*	-	*	-	*	-	*	-	-	
5		-	*	-	*	-	*	-	*	-	-	
6		-	*	-	*	-	*	-	*	-	*	
7		-	*	-	*	-	*	-	*	-	-	
8		-	*	-	-	-	-	-	*	-	-	
Total		----	*	*	-	*	-	*	-	*	-	*
63		1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	
	4	-	-	-	*	-	-	-	-	-	-	
	5	-	-	-	-	-	*	-	-	-	-	
	6	-	-	-	*	-	-	-	-	-	-	
	7	-	*	-	-	-	-	-	-	-	-	
	8	-	*	-	-	-	-	-	-	-	-	
	Total	----	-	*	-	*	-	*	-	-	-	-
	24 - 54	1-8	0.4	0.1	-	*	-	-	-	*	-	0.1
25 - 35	1-8	-	-	-	-	-	-	-	-	-	-	
81 - 85	1-8	*	*	-	*	-	-	-	-	-	*	
STAPLE												
28 & Shorter		-	-	-	-	-	-	-	-	-	-	
29		-	-	-	-	-	-	-	-	-	-	
30		*	*	-	-	-	-	-	-	-	*	
31		0.1	0.1	-	*	-	*	-	*	-	0.2	
32		0.8	0.6	-	*	-	*	-	*	-	1.8	
33		6.1	3.3	-	0.1	-	0.1	-	0.1	-	7.4	
34		14.6	9.4	-	0.7	-	1.3	-	1.4	-	21.0	
35		11.5	15.3	-	3.8	-	8.2	-	8.3	-	28.7	
36		6.1	17.8	-	15.6	-	25.2	-	26.6	-	21.8	
37		13.2	22.7	-	45.9	-	42.7	-	47.7	-	14.8	
38		26.2	14.6	-	25.3	-	16.4	-	12.9	-	3.6	
39		13.6	10.2	-	7.8	-	4.9	-	2.7	-	0.6	
40 & Longer		7.8	6.0	-	0.7	-	1.1	-	0.3	-	*	
Average Staple		36.76	36.61	-	37.17	-	36.84	-	36.71	-	35.23	
Average Length		1.15	1.14	-	1.16	-	1.15	-	1.14	-	1.10	

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 02, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1-2	-	57.6	-	1.7	-	0.4	-	3.8	-	18.8
	3	-	15.0	-	1.2	-	0.4	-	2.5	-	5.0
	4	-	0.8	-	*	-	*	-	0.1	-	0.2
	5	-	*	-	*	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	73.5	-	2.9	-	0.8	-	6.5	-	24.0
31	1-2	-	3.4	-	8.1	-	2.6	-	8.0	-	10.9
	3	-	5.2	-	21.8	-	12.1	-	32.8	-	13.5
	4	-	2.0	-	4.2	-	3.4	-	11.5	-	3.0
	5	-	0.3	-	0.2	-	0.2	-	0.9	-	0.4
	6	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	*	-	*	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	10.9	-	34.3	-	18.3	-	53.2	-	27.7
41	1-2	-	*	-	5.0	-	2.3	-	0.8	-	3.6
	3	-	0.1	-	31.5	-	30.8	-	12.3	-	16.4
	4	-	0.2	-	16.5	-	26.7	-	16.3	-	10.8
	5	-	0.2	-	2.1	-	5.1	-	4.5	-	3.2
	6	-	0.1	-	0.1	-	0.4	-	0.4	-	0.6
	7	-	*	-	*	-	*	-	-	-	0.1
	8	-	*	-	-	-	-	-	-	-	*
Total	----	-	0.5	-	55.3	-	65.4	-	34.3	-	34.8
51	1-2	-	*	-	0.2	-	0.1	-	*	-	0.1
	3	-	*	-	2.4	-	3.0	-	*	-	1.4
	4	-	*	-	2.3	-	4.8	-	0.3	-	2.5
	5	-	*	-	0.5	-	1.7	-	0.3	-	1.6
	6	-	*	-	0.1	-	0.3	-	0.1	-	0.7
	7	-	*	-	*	-	*	-	-	-	0.2
	8	-	*	-	*	-	-	-	-	-	*
Total	----	-	*	-	5.5	-	9.8	-	0.7	-	6.6
61	1-2	-	*	-	*	-	*	-	-	-	*
	3	-	*	-	*	-	*	-	*	-	*
	4	-	*	-	*	-	*	-	*	-	*
	5	-	-	-	*	-	*	-	-	-	*
	6	-	-	-	*	-	*	-	-	-	*
	7	-	-	-	*	-	*	-	-	-	*
	8	-	-	-	*	-	-	-	-	-	*
Total	----	-	*	-	0.1	-	*	-	*	-	*
71	1-2	-	*	-	-	-	*	-	-	-	-
	3	-	*	-	-	-	*	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
Total	----	-	*	-	-	-	*	-	-	-	-
12 & 22	1-2	-	6.0	-	*	-	*	-	0.1	-	1.8
	3	-	3.8	-	*	-	*	-	0.1	-	1.0
	4	-	0.5	-	*	-	*	-	0.1	-	0.1
	5	-	*	-	-	-	*	-	*	-	*
	6	-	*	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	10.3	-	0.1	-	*	-	0.3	-	3.0
32	1-2	-	0.3	-	0.1	-	*	-	0.1	-	0.2
	3	-	1.0	-	0.3	-	0.2	-	0.5	-	0.5
	4	-	0.6	-	0.1	-	0.1	-	0.8	-	0.4
	5	-	0.2	-	*	-	*	-	0.4	-	0.1
	6	-	*	-	*	-	*	-	0.1	-	*
	7	-	*	-	-	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-
Total	----	-	2.2	-	0.4	-	0.3	-	1.8	-	1.3
42	1-2	-	*	-	*	-	0.2	-	*	-	*
	3	-	*	-	0.5	-	1.7	-	0.4	-	0.5
	4	-	0.1	-	0.4	-	1.5	-	1.2	-	0.5
	5	-	0.1	-	0.1	-	0.4	-	0.7	-	0.3
	6	-	*	-	*	-	0.1	-	0.4	-	0.1
	7	-	*	-	*	-	*	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	*
Total	----	-	0.2	-	1.1	-	3.8	-	2.7	-	1.4

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 02, 2026

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA		
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	
Color 52	1-2	-	-	-	*	-	*	-	-	-	*	
	3	-	-	-	0.1	-	0.4	-	*	-	0.1	
	4	-	*	-	0.1	-	0.6	-	0.1	-	0.2	
	5	-	*	-	*	-	0.3	-	0.1	-	0.2	
	6	-	*	-	*	-	0.1	-	*	-	0.1	
	7	-	*	-	*	-	*	-	*	-	0.1	
	8	-	*	-	*	-	-	-	-	-	*	
	Total	----	-	*	-	0.2	-	1.4	-	0.1	-	0.8
	62	1-2	-	-	-	*	-	-	-	-	-	-
3		-	-	-	*	-	*	-	-	-	*	
4		-	-	-	*	-	*	-	-	-	*	
5		-	-	-	*	-	*	-	-	-	*	
6		-	-	-	*	-	*	-	-	-	*	
7		-	-	-	*	-	*	-	-	-	*	
8		-	-	-	*	-	-	-	-	-	*	
Total		----	-	-	-	*	-	*	-	-	-	*
13 & 23		1-2	-	0.7	-	*	-	-	-	-	-	0.1
	3	-	0.6	-	*	-	-	-	-	-	0.1	
	4	-	0.1	-	*	-	-	-	-	-	*	
	5	-	*	-	*	-	-	-	-	-	-	
	6	-	*	-	-	-	-	-	-	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	*	-	-	-	-	-	-	-	-	
	Total	----	-	1.4	-	*	-	-	-	-	-	0.2
	33	1-2	-	0.1	-	*	-	*	-	*	-	*
3		-	0.3	-	*	-	*	-	*	-	*	
4		-	0.2	-	*	-	*	-	*	-	*	
5		-	0.1	-	*	-	*	-	*	-	*	
6		-	*	-	*	-	*	-	*	-	*	
7		-	*	-	-	-	-	-	-	-	-	
8		-	*	-	-	-	-	-	-	-	-	
Total		----	-	0.8	-	*	-	*	-	0.1	-	0.1
43		1-2	-	*	-	*	-	*	-	*	-	*
	3	-	*	-	*	-	*	-	*	-	*	
	4	-	*	-	*	-	*	-	*	-	*	
	5	-	*	-	*	-	*	-	*	-	*	
	6	-	*	-	*	-	*	-	*	-	*	
	7	-	*	-	*	-	*	-	-	-	-	
	8	-	*	-	-	-	-	-	-	-	-	
	Total	----	-	0.1	-	0.1	-	0.1	-	0.1	-	0.1
	53	1-2	-	-	-	*	-	*	-	-	-	*
3		-	-	-	*	-	*	-	-	-	*	
4		-	-	-	*	-	*	-	-	-	*	
5		-	-	-	*	-	*	-	*	-	*	
6		-	*	-	*	-	*	-	*	-	*	
7		-	*	-	*	-	*	-	-	-	*	
8		-	*	-	-	-	-	-	-	-	*	
Total		----	-	*	-	*	-	*	-	*	-	*
63		1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	
	4	-	-	-	*	-	-	-	-	-	-	
	5	-	-	-	*	-	-	-	-	-	-	
	6	-	-	-	-	-	-	-	-	-	-	
	7	-	*	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	Total	----	-	*	-	*	-	-	-	-	-	
	24 - 54	1-8	-	0.1	-	*	-	*	-	0.1	-	*
25 - 35	1-8	-	-	-	-	-	-	-	-	-	-	
81 - 85	1-8	-	*	-	*	-	*	-	-	-	-	
STAPLE												
28 & Shorter		-	-	-	-	-	-	-	-	-	-	
29		-	*	-	-	-	-	-	-	-	-	
30		-	*	-	*	-	-	-	-	-	*	
31		-	0.1	-	*	-	*	-	-	-	*	
32		-	0.5	-	0.1	-	*	-	*	-	0.1	
33		-	2.6	-	0.8	-	0.1	-	0.2	-	0.2	
34		-	8.8	-	4.7	-	0.8	-	1.6	-	1.0	
35		-	18.4	-	15.4	-	4.1	-	11.2	-	4.4	
36		-	25.8	-	30.1	-	15.1	-	28.8	-	15.6	
37		-	29.1	-	35.7	-	47.6	-	39.8	-	41.6	
38		-	10.5	-	10.2	-	26.9	-	14.2	-	23.2	
39		-	3.1	-	2.5	-	4.9	-	3.8	-	7.9	
40 & Longer		-	1.0	-	0.4	-	0.5	-	0.4	-	6.1	
Average Staple		-	36.18	-	36.38	-	37.12	-	36.66	-	37.46	
Average Length		-	1.13	-	1.13	-	1.16	-	1.14	-	1.17	

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 02, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	0.9	9.3	-	0.6	-	*	-	2.1	-	1.8
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	-	0.1	-	0.3	-	0.1	-	*	-	0.3
Grass - Level 2	-	-	-	*	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	-	*	-	-
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	*	-	1.5	-	0.8	-	0.1
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	*
Other - Level 2	-	*	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	-	0.1	-	*	-	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	-	*	-	*	-	-	-	-	-	*
23	*	*	-	*	-	-	-	-	-	0.1
24	0.2	*	-	*	-	*	-	*	-	0.2
25	0.9	0.2	-	*	-	*	-	*	-	0.9
26	4.2	0.8	-	0.2	-	0.1	-	0.5	-	2.7
27	15.8	3.2	-	1.2	-	0.5	-	3.0	-	7.6
28	17.2	8.5	-	5.2	-	3.9	-	12.6	-	14.1
29	15.5	15.1	-	14.8	-	15.4	-	30.5	-	19.9
30	17.6	17.9	-	21.7	-	28.5	-	30.3	-	21.9
31	16.4	17.0	-	17.7	-	26.8	-	15.3	-	17.5
32	9.1	14.1	-	12.5	-	15.8	-	5.8	-	9.3
33	2.6	10.9	-	11.5	-	6.3	-	1.6	-	3.6
34	0.5	6.8	-	9.6	-	2.1	-	0.3	-	1.3
35	0.1	3.4	-	4.0	-	0.5	-	0.1	-	0.5
36	*	1.3	-	1.1	-	0.1	-	*	-	0.2
37	-	0.6	-	0.2	-	*	-	*	-	*
38	-	0.2	-	*	-	*	-	-	-	*
39	-	*	-	*	-	*	-	-	-	-
40 & Above	-	*	-	-	-	*	-	-	-	-
Average	29.70	31.35	-	31.59	-	31.09	-	30.12	-	30.12
Mike										
2.4 & Below	-	*	-	-	-	-	-	-	-	*
2.5	-	0.2	-	*	-	-	-	*	-	0.1
2.6	*	0.3	-	*	-	-	-	-	-	0.2
2.7	0.1	0.4	-	*	-	-	-	*	-	0.3
2.8	0.2	0.5	-	*	-	-	-	*	-	0.4
2.9	0.2	0.5	-	*	-	-	-	*	-	0.6
3.0	0.3	0.6	-	0.1	-	-	-	*	-	0.9
3.1	0.3	0.8	-	0.1	-	-	-	*	-	0.9
3.2	0.4	1.1	-	0.3	-	*	-	0.1	-	1.3
3.3	1.1	1.4	-	0.5	-	*	-	0.2	-	1.6
3.4	2.0	1.9	-	0.9	-	*	-	0.3	-	2.1
3.5	3.1	2.6	-	1.3	-	*	-	0.5	-	2.5
3.6	4.1	3.6	-	1.9	-	0.1	-	0.9	-	3.2
3.7	5.0	4.6	-	2.7	-	0.1	-	1.8	-	3.9
3.8	7.1	5.7	-	4.4	-	0.1	-	2.7	-	4.7
3.9	9.6	7.1	-	6.7	-	0.2	-	4.2	-	5.5
4.0	11.9	8.6	-	9.0	-	0.4	-	5.8	-	6.2
4.1	11.6	10.0	-	11.1	-	0.6	-	7.8	-	7.0
4.2	9.4	10.6	-	12.8	-	1.0	-	9.9	-	8.0
4.3	9.4	10.6	-	12.9	-	1.7	-	11.6	-	8.6
4.4	10.5	9.4	-	11.3	-	2.8	-	11.8	-	9.1
4.5	6.1	7.6	-	8.8	-	4.1	-	10.7	-	8.9
4.6	3.1	5.4	-	6.0	-	6.5	-	9.4	-	8.1
4.7	2.1	3.4	-	3.7	-	9.5	-	7.7	-	6.4
4.8	2.0	1.9	-	2.3	-	13.4	-	5.5	-	4.4
4.9	0.4	0.9	-	1.3	-	16.0	-	3.9	-	2.6
5.0	*	0.4	-	0.8	-	16.3	-	2.5	-	1.4
5.1	-	0.1	-	0.4	-	12.9	-	1.4	-	0.6
5.2	*	0.1	-	0.3	-	8.2	-	0.7	-	0.3
5.3	-	*	-	0.2	-	4.0	-	0.3	-	0.1
5.4	-	-	-	0.1	-	1.5	-	0.1	-	*
5.5 & Above	-	*	-	0.2	-	0.5	-	*	-	*
Average	4.08	4.10	-	4.23	-	4.88	-	4.38	-	4.18

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 02, 2026

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	-	7.7	-	1.3	-	*	-	2.0	-	1.0
Bark - Level 2	-	*	-	-	-	-	-	-	-	-
Grass - Level 1	-	0.1	-	0.1	-	*	-	0.1	-	0.4
Grass - Level 2	-	*	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	-	-	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	0.4	-	0.3	-	0.1	-	2.9	-	0.1
Seed Coat - Level 2	-	*	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	-	-	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	*
Spindle Twist - Level 2	-	*	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	-	*	-	*	-	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	-	*	-	-	-	*	-	-	-	*
23	-	*	-	*	-	*	-	-	-	*
24	-	0.1	-	*	-	*	-	-	-	*
25	-	0.2	-	0.1	-	*	-	*	-	0.1
26	-	0.7	-	0.6	-	*	-	0.1	-	0.9
27	-	2.7	-	3.2	-	0.2	-	1.7	-	2.9
28	-	7.2	-	10.7	-	1.8	-	6.6	-	8.9
29	-	14.7	-	20.6	-	12.4	-	17.9	-	16.8
30	-	20.2	-	25.1	-	36.0	-	30.0	-	20.6
31	-	19.8	-	19.9	-	32.5	-	20.1	-	17.9
32	-	15.0	-	11.5	-	12.2	-	12.6	-	11.9
33	-	9.7	-	5.3	-	3.8	-	6.0	-	7.4
34	-	5.5	-	2.1	-	0.9	-	3.1	-	5.6
35	-	2.5	-	0.7	-	0.1	-	1.5	-	4.0
36	-	1.0	-	0.2	-	*	-	0.2	-	2.1
37	-	0.4	-	*	-	*	-	*	-	0.7
38	-	0.1	-	*	-	*	-	*	-	0.1
39	-	*	-	*	-	-	-	-	-	*
40 & Above	-	-	-	*	-	-	-	-	-	*
Average	-	31.27	-	30.63	-	31.01	-	30.93	-	31.22
Mike										
2.4 & Below	-	*	-	-	-	-	-	-	-	*
2.5	-	0.1	-	*	-	-	-	*	-	0.1
2.6	-	0.1	-	*	-	-	-	*	-	0.1
2.7	-	0.2	-	*	-	*	-	*	-	0.1
2.8	-	0.4	-	*	-	*	-	*	-	0.3
2.9	-	0.6	-	*	-	*	-	*	-	0.3
3.0	-	0.9	-	*	-	*	-	*	-	0.4
3.1	-	1.3	-	*	-	*	-	0.1	-	0.5
3.2	-	1.8	-	0.1	-	*	-	0.1	-	0.9
3.3	-	2.4	-	0.2	-	*	-	0.1	-	0.8
3.4	-	3.1	-	0.3	-	0.1	-	0.1	-	0.9
3.5	-	3.8	-	0.6	-	0.1	-	0.2	-	1.5
3.6	-	4.4	-	1.1	-	0.2	-	0.4	-	2.0
3.7	-	5.0	-	1.9	-	0.4	-	0.5	-	2.8
3.8	-	5.6	-	2.8	-	0.6	-	0.7	-	3.7
3.9	-	6.1	-	4.1	-	1.0	-	1.1	-	5.2
4.0	-	6.5	-	5.6	-	1.7	-	1.9	-	6.6
4.1	-	6.9	-	7.4	-	2.6	-	3.5	-	8.1
4.2	-	7.3	-	9.1	-	4.0	-	4.5	-	9.1
4.3	-	7.6	-	10.0	-	5.7	-	5.6	-	9.3
4.4	-	7.7	-	10.3	-	8.2	-	6.6	-	8.9
4.5	-	7.3	-	9.9	-	11.0	-	8.6	-	8.9
4.6	-	6.5	-	9.1	-	13.9	-	9.7	-	8.2
4.7	-	5.3	-	8.1	-	15.2	-	10.6	-	6.7
4.8	-	3.8	-	6.5	-	13.8	-	11.4	-	5.0
4.9	-	2.4	-	4.9	-	10.1	-	10.5	-	3.8
5.0	-	1.4	-	3.4	-	6.3	-	8.3	-	2.4
5.1	-	0.7	-	2.2	-	3.1	-	6.9	-	1.3
5.2	-	0.4	-	1.2	-	1.2	-	4.0	-	0.8
5.3	-	0.2	-	0.6	-	0.4	-	2.2	-	0.6
5.4	-	0.1	-	0.2	-	0.1	-	1.1	-	0.3
5.5 & Above	-	0.1	-	0.1	-	*	-	1.1	-	0.3
Average	-	4.11	-	4.41	-	4.62	-	4.67	-	4.30

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 02, 2026

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	-	*	-	-	-	-	-	-	-	*
2.5 - 2.6	*	0.5	-	*	-	-	-	*	-	0.3
2.7 - 2.9	0.6	1.3	-	0.1	-	-	-	*	-	1.3
3.0 - 3.2	1.0	2.5	-	0.5	-	*	-	0.2	-	3.1
3.3 - 3.4	3.1	3.3	-	1.4	-	*	-	0.5	-	3.7
3.5 - 3.6	7.2	6.1	-	3.1	-	0.1	-	1.5	-	5.7
3.7 - 4.2	54.6	46.5	-	46.6	-	2.5	-	32.1	-	35.3
4.3 - 4.9	33.5	39.1	-	46.4	-	54.0	-	60.6	-	48.2
5.0 - 5.2	*	0.6	-	1.4	-	37.4	-	4.6	-	2.3
5.3 & Above	-	*	-	0.5	-	6.1	-	0.4	-	0.1
Average	4.08	4.10	-	4.23	-	4.88	-	4.38	-	4.18
Leaf										
1 - 2	58.2	56.9	-	24.8	-	3.8	-	8.4	-	86.0
3	35.7	27.8	-	49.7	-	37.7	-	52.5	-	12.3
4	5.6	9.1	-	21.1	-	45.4	-	33.2	-	1.4
5	0.5	3.9	-	4.0	-	12.0	-	5.4	-	0.3
6	*	1.7	-	0.5	-	1.1	-	0.4	-	0.1
7	-	0.6	-	0.1	-	*	-	*	-	*
8	-	0.1	-	*	-	-	-	*	-	-
Average	2.37	2.52	-	3.03	-	3.69	-	3.37	-	1.76
HVI Trash 1/										
00	*	*	-	*	-	-	-	-	-	0.6
01	23.0	27.7	-	5.1	-	0.3	-	0.6	-	59.1
02	42.2	32.8	-	22.5	-	4.6	-	10.2	-	29.9
03	20.5	16.4	-	27.9	-	14.9	-	24.6	-	7.2
04	8.6	8.5	-	20.4	-	22.9	-	26.2	-	2.0
05	3.3	4.7	-	12.1	-	22.0	-	18.8	-	0.7
06	1.3	2.8	-	6.4	-	15.8	-	10.7	-	0.3
07	0.5	1.9	-	3.1	-	9.7	-	5.2	-	0.1
08	0.3	1.4	-	1.4	-	5.2	-	2.3	-	0.1
09	0.1	1.1	-	0.6	-	2.6	-	0.9	-	*
10	0.1	0.8	-	0.3	-	1.2	-	0.4	-	*
11	*	0.6	-	0.1	-	0.5	-	0.2	-	*
12	*	0.4	-	0.1	-	0.2	-	0.1	-	*
13	-	0.3	-	*	-	0.1	-	*	-	*
14	-	0.2	-	*	-	*	-	*	-	*
15	-	0.1	-	*	-	*	-	*	-	-
16	-	0.1	-	*	-	-	-	*	-	*
17	-	0.1	-	*	-	-	-	*	-	*
18 & Above	-	0.1	-	*	-	-	-	*	-	-
Average	0.24	0.28	-	0.36	-	0.50	-	0.43	-	0.16
UNIFORMITY 2/										
74 & Below	-	*	-	*	-	-	-	*	-	*
75	*	0.1	-	*	-	-	-	*	-	0.1
76	*	0.2	-	*	-	*	-	*	-	0.5
77	0.1	1.0	-	0.1	-	*	-	*	-	2.3
78	3.0	3.7	-	0.7	-	0.2	-	0.5	-	9.8
79	11.6	13.5	-	3.7	-	1.0	-	2.9	-	24.9
80	23.9	28.0	-	13.4	-	7.0	-	12.0	-	35.9
81	28.8	28.6	-	30.1	-	28.1	-	28.8	-	21.5
82	24.4	16.6	-	31.1	-	37.9	-	35.0	-	4.5
83	7.4	6.7	-	16.1	-	20.5	-	18.2	-	0.5
84	0.7	1.5	-	4.3	-	5.1	-	2.3	-	*
85 & Above	*	0.1	-	0.4	-	0.2	-	0.2	-	*
Average	81.29	81.08	-	82.00	-	82.30	-	82.04	-	80.23
Tenderable 3/	90.2	80.3	-	88.1	-	53.0	-	90.5	-	83.8
SAMPLES CLASSED										
Week	11,977		-		-		-		-	
Season		1,197,990		1,526,527		951,056		1,110,533		590,576

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 02, 2026

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	-	*	-	-	-	-	-	-	-	*
2.5 - 2.6	-	0.2	-	*	-	-	-	*	-	0.2
2.7 - 2.9	-	1.2	-	*	-	*	-	0.1	-	0.7
3.0 - 3.2	-	4.1	-	0.1	-	*	-	0.1	-	1.7
3.3 - 3.4	-	5.4	-	0.5	-	0.1	-	0.2	-	1.8
3.5 - 3.6	-	8.2	-	1.8	-	0.3	-	0.6	-	3.5
3.7 - 4.2	-	37.3	-	30.8	-	10.3	-	12.3	-	35.6
4.3 - 4.9	-	40.7	-	58.9	-	78.1	-	63.0	-	50.8
5.0 - 5.2	-	2.4	-	6.8	-	10.6	-	19.3	-	4.6
5.3 & Above	-	0.3	-	1.0	-	0.6	-	4.3	-	1.1
Average	-	4.11	-	4.41	-	4.62	-	4.67	-	4.30
Leaf										
1 - 2	-	68.4	-	15.3	-	5.7	-	12.7	-	35.5
3	-	26.0	-	57.9	-	48.6	-	48.8	-	38.5
4	-	4.5	-	23.7	-	37.1	-	30.5	-	17.9
5	-	0.9	-	3.0	-	7.7	-	6.9	-	6.0
6	-	0.2	-	0.2	-	0.8	-	1.0	-	1.6
7	-	*	-	*	-	0.1	-	*	-	0.3
8	-	*	-	*	-	-	-	-	-	0.1
Average	-	2.22	-	3.15	-	3.49	-	3.34	-	2.95
HVI Trash 1/										
00	-	*	-	-	-	*	-	-	-	*
01	-	33.1	-	1.6	-	0.5	-	1.6	-	13.3
02	-	41.5	-	19.8	-	7.2	-	14.0	-	27.6
03	-	15.5	-	31.4	-	21.1	-	24.1	-	21.9
04	-	5.5	-	23.6	-	26.2	-	23.3	-	14.7
05	-	2.2	-	12.9	-	20.2	-	16.3	-	9.2
06	-	1.0	-	6.1	-	12.2	-	9.7	-	5.5
07	-	0.5	-	2.7	-	6.5	-	5.3	-	3.3
08	-	0.3	-	1.1	-	3.2	-	2.7	-	2.0
09	-	0.1	-	0.5	-	1.5	-	1.5	-	1.1
10	-	0.1	-	0.2	-	0.7	-	0.8	-	0.6
11	-	0.1	-	0.1	-	0.3	-	0.4	-	0.4
12	-	*	-	*	-	0.1	-	0.2	-	0.2
13	-	*	-	*	-	0.1	-	0.1	-	0.1
14	-	*	-	*	-	*	-	*	-	0.1
15	-	*	-	*	-	*	-	-	-	*
16	-	*	-	*	-	-	-	-	-	*
17	-	*	-	*	-	-	-	*	-	*
18 & Above	-	*	-	*	-	-	-	-	-	*
Average	-	0.21	-	0.37	-	0.46	-	0.42	-	0.34
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	-	-	-	-
75	-	*	-	*	-	-	-	-	-	*
76	-	0.2	-	*	-	*	-	-	-	*
77	-	1.1	-	0.1	-	*	-	-	-	0.2
78	-	4.5	-	0.8	-	0.1	-	0.2	-	1.1
79	-	14.3	-	5.1	-	0.4	-	1.9	-	4.4
80	-	29.9	-	20.1	-	3.9	-	10.6	-	18.2
81	-	31.7	-	36.4	-	20.7	-	32.1	-	33.7
82	-	14.7	-	27.8	-	45.7	-	37.3	-	30.5
83	-	3.1	-	8.4	-	26.3	-	15.7	-	10.0
84	-	0.4	-	1.2	-	2.7	-	2.1	-	1.8
85 & Above	-	0.1	-	0.1	-	0.2	-	0.1	-	0.2
Average	-	80.90	-	81.60	-	82.47	-	82.05	-	81.71
Tenderable 3/	-	78.3	-	88.6	-	83.4	-	69.3	-	85.1
SAMPLES CLASSIFIED										
Week	-	-	-	-	-	-	-	-	-	-
Season	-	2,511,777	-	2,197,597	-	2,351,211	-	283,396	-	369,520

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Apr 02, 2026

Color Grade	Leaf	VISALIA		Quality Designation	VISALIA	
		Week	Season		Week	Season
01	1	-	6.2	MIKE	-	-
	2	-	7.6	2.4 & Below	-	-
	3	-	0.2	2.5 - 2.6	-	*
	4	-	-	2.7 - 2.9	-	0.2
	5	-	-	3.0 - 3.2	-	1.6
	6	-	-	3.3 - 3.4	-	2.8
	7	-	-	3.5 - 3.6	-	8.6
Total -----		-	14.0	3.7 - 4.2	-	82.8
02	1	-	7.7	4.3 - 4.9	-	4.0
	2	-	34.4	5.0 - 5.2	-	*
	3	-	8.2	5.3 & Above	-	-
	4	-	0.2	Average	-	3.89
	5	-	*	ALL RANGE MIKE	-	-
	6	-	-	2.4 & Below	-	-
	7	-	-	2.5	-	-
Total -----		-	50.5	2.6	-	*
03	1	-	0.7	2.7	-	*
	2	-	13.2	2.8	-	*
	3	-	15.5	2.9	-	0.1
	4	-	1.9	3.0	-	0.3
	5	-	0.1	3.1	-	0.5
	6	-	*	3.2	-	0.8
	7	-	-	3.3	-	1.0
Total -----		-	31.3	3.4	-	1.9
04	1	-	*	3.5	-	3.0
	2	-	0.7	3.6	-	5.6
	3	-	1.9	3.7	-	9.7
	4	-	0.8	3.8	-	15.1
	5	-	0.1	3.9	-	20.1
	6	-	*	4.0	-	19.0
	7	-	-	4.1	-	12.4
Total -----		-	3.5	4.2	-	6.4
05	1	-	*	4.3	-	2.5
	2	-	0.1	4.4	-	1.0
	3	-	0.2	4.5	-	0.4
	4	-	0.2	4.6	-	0.1
	5	-	*	4.7	-	*
	6	-	*	4.8	-	*
	7	-	-	4.9	-	*
Total -----		-	0.5	5.0	-	*
06	1	-	-	5.1	-	*
	2	-	*	5.2	-	-
	3	-	0.1	5.3 & Above	-	-
	4	-	*	Average	-	3.89
	5	-	*	STRENGTH 1/	-	-
	6	-	*	36 & Below	-	2.8
	7	-	-	37	-	4.9
Total -----		-	0.1	38	-	3.9
07	1	-	-	39	-	1.8
	2	-	-	40	-	2.0
	3	-	*	41	-	5.9
	4	-	*	42	-	11.2
	5	-	*	43	-	16.5
	6	-	*	44	-	19.2
	7	-	-	45	-	16.3
Total -----		-	*	46	-	9.5
STAPLE		-	-	47	-	4.0
44 & Shorter	-	3.0	48 & Above	-	1.9	
46	-	11.4	Average	-	43.46	
48	-	46.2	UNIFORMITY	-	-	
50	-	37.4	83 & Below	-	1.6	
52 & Longer	-	2.0	84	-	11.9	
Average Staple	-	48.48	85	-	34.1	
Average Length	-	1.41	86	-	45.7	
EXTRANEOUS MATTER		-	-	87	-	6.1
Bark	-	*	88 & Above	-	0.5	
Grass	-	0.3	Average	-	85.89	
Spindle Twist	-	0.1	Samples Classed	-	-	
Preparation	-	*	Week	-	-	
All Other	-	*	Season	-	390,579	

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.