



State	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
<i>UPLAND</i>								
AL	-	-	-	-	21	89.9	77.8	549,869
AR	-	-	-	-	26	70.4	42.7	1,421,220
AZ	-	-	-	-	10	86.3	70.2	232,176
CA	-	-	-	-	10	85.6	74.5	94,092
FL	-	-	-	-	4	91.0	76.3	90,069
GA	-	-	-	-	53	88.4	74.2	1,738,474
KS	-	-	-	-	3	32.5	24.7	160,354
LA	-	-	-	-	14	71.5	47.6	223,299
MO	-	-	-	-	16	86.7	65.2	680,258
MS	-	-	-	-	30	63.7	36.5	706,521
NC	-	-	-	-	26	90.7	78.7	653,677
NM	-	-	-	-	2	81.6	67.3	12,080
OK	2	90.2	76.2	8,407	10	90.9	78.7	498,505
SC	-	-	-	-	10	86.4	73.5	283,935
TN	-	-	-	-	17	82.3	63.4	340,307
TX	5	90.8	54.9	3,790	145	82.2	62.1	5,232,426
VA	-	-	-	-	4	96.1	90.4	172,921
<b>United States</b>	<b>7</b>	<b>90.4</b>	<b>69.5</b>	<b>12,197</b>	<b>401</b>	<b>81.7</b>	<b>62.8</b>	<b>13,090,183</b>
<i>AMERICAN PIMA</i>								
AZ*	-	-	-	-	3	-	-	27,733
CA	-	-	-	-	10	-	-	308,854
NM	-	-	-	-	-	-	-	-
TX	-	-	-	-	5	-	-	34,745
United States	-	-	-	-	19	-	-	390,579
<b>United States all cotton</b>	<b>8</b>	-	-	<b>12,997</b>	<b>410</b>	-	-	<b>13,480,762</b>

\* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

Source: USDA AMS Cotton and Tobacco Market News  
 Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov  
<https://www.ams.usda.gov/market-news/cotton>  
<https://mymarketnews.ams.usda.gov/cottonmn@ams.usda.gov>

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Apr 02, 2026**

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1-2	-	2.2	-	0.1	-	16.3	-	18.0	-	1.7	-	1.5
	3	-	1.3	-	0.1	-	3.1	-	6.5	-	0.5	-	1.2
	4	-	*	-	*	-	0.2	-	0.4	-	*	-	*
	5	-	*	-	-	-	*	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>3.5</b>	-	<b>0.2</b>	-	<b>19.6</b>	-	<b>24.9</b>	-	<b>2.2</b>	-	<b>2.7</b>
31	1-2	-	9.3	-	1.1	-	9.7	-	13.8	-	3.1	-	7.8
	3	-	27.7	-	9.0	-	11.8	-	10.9	-	12.5	-	21.9
	4	-	7.1	-	3.4	-	2.3	-	3.4	-	2.8	-	4.2
	5	-	0.5	-	0.1	-	0.2	-	0.6	-	0.1	-	0.2
	6	-	*	-	*	-	*	-	0.1	-	-	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>44.7</b>	-	<b>13.7</b>	-	<b>24.0</b>	-	<b>28.8</b>	-	<b>18.4</b>	-	<b>34.1</b>
41	1-2	-	3.3	-	0.8	-	2.9	-	6.8	-	2.8	-	5.3
	3	-	22.6	-	26.2	-	17.0	-	22.3	-	37.0	-	32.4
	4	-	15.6	-	35.2	-	14.2	-	7.3	-	28.9	-	16.3
	5	-	2.8	-	8.4	-	4.4	-	1.7	-	4.0	-	2.0
	6	-	0.2	-	0.7	-	0.7	-	0.3	-	0.2	-	0.1
	7	-	*	-	*	-	0.1	-	*	-	*	-	*
	8	-	-	-	-	-	*	-	-	-	-	-	-
<b>Total</b>	----	-	<b>44.5</b>	-	<b>71.3</b>	-	<b>39.4</b>	-	<b>38.4</b>	-	<b>72.9</b>	-	<b>56.2</b>
51	1-2	-	0.4	-	*	-	0.1	-	0.1	-	0.1	-	0.2
	3	-	2.4	-	2.4	-	1.9	-	0.6	-	1.7	-	2.2
	4	-	1.8	-	4.9	-	3.6	-	0.9	-	2.3	-	2.2
	5	-	0.4	-	2.3	-	2.4	-	0.5	-	0.6	-	0.5
	6	-	*	-	0.4	-	1.0	-	0.3	-	0.1	-	0.1
	7	-	*	-	0.1	-	0.3	-	0.1	-	*	-	*
	8	-	*	-	-	-	0.1	-	*	-	-	-	*
<b>Total</b>	----	-	<b>4.9</b>	-	<b>10.0</b>	-	<b>9.4</b>	-	<b>2.5</b>	-	<b>4.8</b>	-	<b>5.1</b>
61	1-2	-	*	-	*	-	*	-	-	-	-	-	*
	3	-	0.1	-	*	-	*	-	*	-	*	-	*
	4	-	0.1	-	*	-	*	-	*	-	*	-	*
	5	-	*	-	*	-	*	-	-	-	*	-	*
	6	-	*	-	*	-	*	-	*	-	*	-	*
	7	-	-	-	-	-	*	-	*	-	-	-	*
	8	-	-	-	-	-	*	-	*	-	-	-	*
<b>Total</b>	----	-	<b>0.2</b>	-	<b>*</b>	-	<b>*</b>	-	<b>*</b>	-	<b>*</b>	-	<b>*</b>
71	1-2	-	-	-	*	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	*	-	-	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	-	-	<b>*</b>	-	-	-	-	-	-	-	-
12 & 22	1-2	-	0.1	-	*	-	2.6	-	0.1	-	*	-	*
	3	-	*	-	*	-	1.2	-	0.2	-	*	-	0.1
	4	-	*	-	*	-	0.2	-	*	-	-	-	*
	5	-	-	-	*	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>0.1</b>	-	<b>*</b>	-	<b>4.0</b>	-	<b>0.4</b>	-	<b>*</b>	-	<b>0.1</b>
32	1-2	-	0.1	-	*	-	0.1	-	0.3	-	*	-	*
	3	-	0.4	-	0.1	-	0.4	-	0.6	-	0.2	-	0.2
	4	-	0.1	-	0.1	-	0.3	-	0.5	-	*	-	0.1
	5	-	*	-	*	-	0.1	-	0.3	-	-	-	*
	6	-	*	-	*	-	*	-	*	-	-	-	*
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>0.6</b>	-	<b>0.2</b>	-	<b>0.9</b>	-	<b>1.9</b>	-	<b>0.3</b>	-	<b>0.4</b>
42	1-2	-	*	-	*	-	*	-	0.1	-	0.1	-	*
	3	-	0.4	-	1.0	-	0.4	-	0.9	-	0.7	-	0.6
	4	-	0.5	-	1.5	-	0.6	-	0.5	-	0.4	-	0.4
	5	-	0.1	-	0.7	-	0.3	-	0.3	-	*	-	0.1
	6	-	*	-	0.1	-	0.1	-	0.1	-	*	-	*
	7	-	*	-	*	-	*	-	-	-	*	-	*
	8	-	-	-	-	-	*	-	-	-	-	-	-
<b>Total</b>	----	-	<b>1.1</b>	-	<b>3.2</b>	-	<b>1.4</b>	-	<b>1.9</b>	-	<b>1.2</b>	-	<b>1.1</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Apr 02, 2026**

Quality Designation	Leaf	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1-2	-	*	-	*	-	*	-	*	-	*	-	*
	3	-	0.1	-	0.2	-	0.1	-	0.1	-	0.1	-	*
	4	-	0.1	-	0.6	-	0.3	-	0.2	-	0.1	-	0.1
	5	-	0.1	-	0.3	-	0.3	-	0.2	-	*	-	*
	6	-	*	-	0.1	-	0.2	-	0.2	-	*	-	*
	7	-	*	-	*	-	*	-	0.1	-	*	-	*
	8	-	-	-	-	-	*	-	*	-	-	-	*
<b>Total</b>	----	-	<b>0.3</b>	-	<b>1.3</b>	-	<b>0.9</b>	-	<b>0.8</b>	-	<b>0.2</b>	-	<b>0.2</b>
62	1-2	-	*	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	*	-	-	-	*	-	*	-	*
	4	-	*	-	*	-	*	-	*	-	*	-	*
	5	-	*	-	*	-	*	-	*	-	*	-	*
	6	-	*	-	*	-	*	-	*	-	-	-	*
	7	-	-	-	*	-	*	-	*	-	-	-	*
	8	-	-	-	-	-	*	-	*	-	-	-	*
<b>Total</b>	----	-	*	-	*	-	*	-	*	-	*	-	*
13 & 23	1-2	-	*	-	-	-	0.1	-	*	-	-	-	*
	3	-	*	-	-	-	*	-	*	-	-	-	*
	4	-	*	-	-	-	*	-	-	-	-	-	*
	5	-	-	-	-	-	-	-	-	-	-	-	*
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	*	-	-	-	<b>0.2</b>	-	*	-	-	-	*
33	1-2	-	*	-	-	-	*	-	*	-	-	-	*
	3	-	*	-	*	-	*	-	*	-	-	-	*
	4	-	*	-	*	-	*	-	*	-	-	-	*
	5	-	*	-	*	-	*	-	*	-	-	-	*
	6	-	*	-	-	-	*	-	-	-	-	-	*
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	*	-	*	-	*	-	*	-	-	-	*
43	1-2	-	-	-	*	-	-	-	*	-	-	-	*
	3	-	*	-	*	-	*	-	0.1	-	*	-	*
	4	-	*	-	*	-	*	-	0.1	-	*	-	*
	5	-	*	-	*	-	*	-	*	-	-	-	*
	6	-	*	-	*	-	*	-	*	-	-	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	*	-	<b>0.1</b>	-	<b>0.1</b>	-	<b>0.2</b>	-	*	-	<b>0.1</b>
53	1-2	-	*	-	-	-	*	-	-	-	-	-	-
	3	-	*	-	*	-	*	-	*	-	*	-	*
	4	-	*	-	*	-	*	-	*	-	*	-	*
	5	-	*	-	*	-	*	-	*	-	*	-	*
	6	-	*	-	*	-	*	-	*	-	-	-	*
	7	-	-	-	*	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	*	-	-	-	-	-	-
<b>Total</b>	----	-	<b>0.1</b>	-	*	-	*	-	*	-	*	-	*
63	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	*	-	-	-	-	-	-	-	-	-	-
	4	-	*	-	-	-	-	-	-	-	-	-	-
	5	-	*	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	*	-	-	-	-	-	-	-	-	-	-
24 - 54	1-8	-	*	-	*	-	*	-	*	-	-	-	*
25 - 35	1-8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1-8	-	*	-	-	-	-	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	*
31		-	*	-	*	-	*	-	-	-	*	-	*
32		-	*	-	*	-	*	-	-	-	*	-	0.1
33		-	0.7	-	0.1	-	*	-	0.1	-	0.2	-	0.9
34		-	3.6	-	0.3	-	0.7	-	0.5	-	2.4	-	4.9
35		-	12.3	-	2.6	-	3.5	-	4.2	-	12.4	-	16.0
36		-	24.6	-	13.8	-	13.5	-	21.4	-	29.2	-	31.0
37		-	40.9	-	50.3	-	44.9	-	44.9	-	35.5	-	34.5
38		-	14.3	-	27.0	-	27.0	-	19.0	-	15.3	-	9.7
39		-	3.1	-	5.4	-	8.5	-	8.8	-	4.4	-	2.5
40 & Longer		-	0.5	-	0.6	-	1.9	-	1.1	-	0.6	-	0.4
<b>Average Staple</b>		-	<b>36.59</b>	-	<b>37.19</b>	-	<b>37.28</b>	-	<b>37.09</b>	-	<b>36.64</b>	-	<b>36.34</b>
<b>Average Length</b>		-	<b>1.14</b>	-	<b>1.16</b>	-	<b>1.16</b>	-	<b>1.16</b>	-	<b>1.14</b>	-	<b>1.13</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Apr 02, 2026**

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1-2	-	4.1	-	4.5	-	*	-	2.0	-	0.4	-	40.4
	3	-	5.3	-	2.6	-	*	-	1.8	-	0.3	-	10.9
	4	-	1.1	-	*	-	*	-	*	-	*	-	0.8
	5	-	0.1	-	-	-	-	-	*	-	*	-	*
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>10.7</b>	-	<b>7.1</b>	-	<b>*</b>	-	<b>3.8</b>	-	<b>0.8</b>	-	<b>52.2</b>
31	1-2	-	0.9	-	9.2	-	1.5	-	3.4	-	5.7	-	7.6
	3	-	7.6	-	36.6	-	9.0	-	20.3	-	20.2	-	15.3
	4	-	9.3	-	12.3	-	1.8	-	8.6	-	5.8	-	7.3
	5	-	2.6	-	0.8	-	*	-	0.6	-	0.3	-	1.1
	6	-	0.3	-	*	-	*	-	*	-	*	-	0.1
	7	-	*	-	-	-	-	-	-	-	-	-	*
	8	-	*	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>20.7</b>	-	<b>58.9</b>	-	<b>12.3</b>	-	<b>32.9</b>	-	<b>32.0</b>	-	<b>31.4</b>
41	1-2	-	*	-	0.5	-	2.4	-	0.9	-	3.1	-	*
	3	-	1.6	-	10.1	-	38.1	-	18.8	-	30.0	-	0.6
	4	-	6.7	-	16.2	-	26.6	-	26.1	-	24.6	-	1.2
	5	-	9.2	-	4.9	-	3.2	-	7.3	-	4.5	-	1.3
	6	-	4.5	-	0.3	-	0.1	-	0.6	-	0.4	-	0.6
	7	-	0.9	-	-	-	*	-	*	-	*	-	0.1
	8	-	*	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	----	-	<b>23.0</b>	-	<b>32.0</b>	-	<b>70.4</b>	-	<b>53.6</b>	-	<b>62.5</b>	-	<b>3.8</b>
51	1-2	-	-	-	*	-	0.2	-	*	-	*	-	-
	3	-	-	-	*	-	4.5	-	1.1	-	0.8	-	-
	4	-	*	-	0.4	-	6.0	-	3.3	-	1.7	-	*
	5	-	0.4	-	0.3	-	1.4	-	1.5	-	0.8	-	*
	6	-	1.1	-	0.1	-	0.1	-	0.2	-	0.2	-	*
	7	-	0.8	-	-	-	*	-	*	-	*	-	-
	8	-	0.2	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	----	-	<b>2.6</b>	-	<b>0.7</b>	-	<b>12.1</b>	-	<b>6.1</b>	-	<b>3.6</b>	-	<b>*</b>
61	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	*	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	*	-	-
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>*</b>	-	<b>*</b>	-	<b>*</b>	-	<b>*</b>	-	<b>*</b>	-	<b>-</b>
71	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	*	-	-	-	-	-	-
	5	-	-	-	-	-	*	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>-</b>	-	<b>-</b>	-	<b>*</b>	-	<b>-</b>	-	<b>*</b>	-	<b>-</b>
12 & 22	1-2	-	1.2	-	0.1	-	-	-	*	-	*	-	2.4
	3	-	3.9	-	*	-	*	-	*	-	*	-	3.0
	4	-	2.0	-	*	-	-	-	*	-	*	-	0.3
	5	-	0.2	-	*	-	-	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>7.3</b>	-	<b>0.1</b>	-	<b>*</b>	-	<b>*</b>	-	<b>*</b>	-	<b>5.7</b>
32	1-2	-	0.1	-	0.1	-	*	-	*	-	*	-	0.6
	3	-	3.1	-	0.3	-	0.1	-	0.2	-	0.1	-	1.6
	4	-	5.4	-	0.2	-	*	-	0.1	-	0.1	-	2.7
	5	-	2.9	-	*	-	*	-	*	-	*	-	0.8
	6	-	0.6	-	*	-	-	-	*	-	-	-	0.1
	7	-	0.1	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>12.2</b>	-	<b>0.5</b>	-	<b>0.1</b>	-	<b>0.3</b>	-	<b>0.3</b>	-	<b>5.8</b>
42	1-2	-	*	-	*	-	0.1	-	*	-	*	-	-
	3	-	0.7	-	0.1	-	1.3	-	0.6	-	0.3	-	*
	4	-	3.4	-	0.4	-	1.4	-	1.2	-	0.3	-	0.1
	5	-	5.5	-	0.1	-	0.4	-	0.5	-	0.1	-	0.1
	6	-	4.0	-	*	-	0.1	-	0.1	-	*	-	0.1
	7	-	1.4	-	-	-	*	-	*	-	*	-	*
	8	-	0.2	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	----	-	<b>15.3</b>	-	<b>0.6</b>	-	<b>3.3</b>	-	<b>2.4</b>	-	<b>0.7</b>	-	<b>0.3</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Apr 02, 2026**

Quality Designation	Leaf	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1-2	-	-	-	-	-	*	-	*	-	*	-	-
	3	-	-	-	*	-	0.5	-	0.1	-	*	-	-
	4	-	*	-	*	-	0.7	-	0.2	-	*	-	-
	5	-	0.1	-	*	-	0.3	-	0.3	-	*	-	-
	6	-	0.3	-	*	-	*	-	0.1	-	*	-	-
	7	-	0.5	-	-	-	*	-	*	-	*	-	-
	8	-	0.3	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	----	-	<b>1.2</b>	-	<b>*</b>	-	<b>1.6</b>	-	<b>0.7</b>	-	<b>0.1</b>	-	-
62	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	*	-	*	-	-	-	-
	4	-	-	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	*	-	-
	6	-	-	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	-	-	*	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>*</b>	-	-	-	<b>*</b>	-	<b>*</b>	-	<b>*</b>	-	-
13 & 23	1-2	-	0.1	-	-	-	-	-	-	-	*	-	-
	3	-	0.9	-	-	-	-	-	-	-	*	-	*
	4	-	0.6	-	-	-	-	-	-	-	*	-	*
	5	-	0.1	-	-	-	-	-	-	-	-	-	-
	6	-	*	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>1.7</b>	-	-	-	-	-	-	-	<b>*</b>	-	<b>*</b>
33	1-2	-	*	-	-	-	*	-	*	-	*	-	*
	3	-	0.4	-	*	-	*	-	*	-	*	-	0.1
	4	-	1.0	-	*	-	*	-	*	-	*	-	0.3
	5	-	0.6	-	*	-	-	-	-	-	*	-	0.2
	6	-	0.1	-	-	-	-	-	-	-	*	-	*
	7	-	*	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>2.1</b>	-	<b>*</b>	-	<b>*</b>	-	<b>*</b>	-	<b>*</b>	-	<b>0.7</b>
43	1-2	-	-	-	*	-	*	-	-	-	*	-	-
	3	-	0.1	-	*	-	*	-	*	-	*	-	*
	4	-	0.5	-	*	-	*	-	*	-	*	-	*
	5	-	1.2	-	*	-	*	-	*	-	*	-	*
	6	-	0.9	-	-	-	*	-	*	-	*	-	*
	7	-	0.4	-	-	-	-	-	-	-	*	-	-
	8	-	0.1	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	----	-	<b>3.1</b>	-	<b>*</b>	-	<b>0.1</b>	-	<b>*</b>	-	<b>*</b>	-	<b>0.1</b>
53	1-2	-	-	-	-	-	*	-	*	-	-	-	-
	3	-	*	-	-	-	*	-	*	-	*	-	-
	4	-	*	-	-	-	*	-	*	-	*	-	-
	5	-	*	-	-	-	*	-	*	-	*	-	-
	6	-	*	-	-	-	*	-	*	-	*	-	-
	7	-	0.1	-	-	-	-	-	*	-	*	-	-
	8	-	0.1	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	----	-	<b>0.2</b>	-	-	-	<b>*</b>	-	<b>*</b>	-	<b>*</b>	-	-
63	1-2	-	-	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	<b>*</b>	-	-	-	-	-	<b>*</b>	-	-	-	-
24 - 54	1-8	-	0.1	-	-	-	*	-	-	-	*	-	-
25 - 35	1-8	-	-	-	-	-	-	-	-	-	-	-	-
81 - 85	1-8	-	*	-	-	-	*	-	-	-	-	-	-
STAPLE													
28 & Shorter		-	-	-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	-	-	-	-	-
30		-	-	-	-	-	-	-	-	-	-	-	-
31		-	*	-	-	-	-	-	*	-	*	-	-
32		-	*	-	-	-	*	-	*	-	*	-	-
33		-	0.2	-	0.1	-	*	-	0.2	-	0.1	-	*
34		-	1.2	-	1.1	-	0.2	-	2.1	-	1.4	-	2.3
35		-	5.1	-	10.0	-	1.8	-	11.5	-	8.3	-	10.7
36		-	13.7	-	26.9	-	10.4	-	27.7	-	24.4	-	14.0
37		-	33.8	-	42.1	-	49.0	-	36.4	-	48.7	-	29.6
38		-	30.6	-	15.0	-	33.2	-	15.0	-	14.1	-	36.7
39		-	13.7	-	4.4	-	4.9	-	5.4	-	2.7	-	5.8
40 & Longer		-	1.8	-	0.4	-	0.3	-	1.5	-	0.3	-	0.8
<b>Average Staple</b>		-	<b>37.35</b>	-	<b>36.75</b>	-	<b>37.29</b>	-	<b>36.72</b>	-	<b>36.74</b>	-	<b>37.09</b>
<b>Average Length</b>		-	<b>1.17</b>	-	<b>1.15</b>	-	<b>1.17</b>	-	<b>1.15</b>	-	<b>1.15</b>	-	<b>1.16</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Apr 02, 2026**

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
11 & 21	1-2	41.0	42.0	-	0.3	-	0.4	13.7	44.1	-	0.9
	3	17.4	8.0	-	0.4	-	0.1	1.5	12.9	-	1.3
	4	0.2	0.2	-	*	-	*	-	0.9	-	0.1
	5	-	*	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	<b>----</b>	<b>58.6</b>	<b>50.2</b>	<b>-</b>	<b>0.8</b>	<b>-</b>	<b>0.5</b>	<b>15.2</b>	<b>57.9</b>	<b>-</b>	<b>2.2</b>
31	1-2	6.6	14.1	-	2.3	-	6.9	26.8	4.5	-	8.7
	3	22.4	19.2	-	15.3	-	14.5	7.6	10.3	-	38.2
	4	4.1	4.0	-	5.7	-	3.2	0.6	4.0	-	8.3
	5	0.1	0.3	-	0.3	-	0.2	-	0.5	-	0.5
	6	-	*	-	*	-	*	-	*	-	*
	7	-	*	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	<b>----</b>	<b>33.2</b>	<b>37.6</b>	<b>-</b>	<b>23.6</b>	<b>-</b>	<b>24.8</b>	<b>35.0</b>	<b>19.2</b>	<b>-</b>	<b>55.6</b>
41	1-2	*	0.6	-	1.9	-	7.7	1.8	0.3	-	1.7
	3	0.3	2.1	-	31.3	-	35.8	9.3	1.8	-	21.6
	4	0.8	1.6	-	31.4	-	14.2	4.8	1.7	-	15.7
	5	0.1	0.5	-	5.1	-	1.8	0.4	0.5	-	2.6
	6	-	0.1	-	0.2	-	0.1	*	0.1	-	0.1
	7	-	*	-	*	-	*	-	*	-	*
	8	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	<b>----</b>	<b>1.3</b>	<b>4.7</b>	<b>-</b>	<b>69.9</b>	<b>-</b>	<b>59.6</b>	<b>16.3</b>	<b>4.3</b>	<b>-</b>	<b>41.8</b>
51	1-2	-	*	-	0.1	-	0.2	-	*	-	*
	3	-	*	-	1.7	-	2.4	-	*	-	*
	4	-	*	-	2.3	-	2.2	-	0.1	-	0.1
	5	*	*	-	0.6	-	0.5	*	*	-	*
	6	-	*	-	0.1	-	*	-	*	-	*
	7	-	*	-	*	-	*	-	*	-	*
	8	-	*	-	-	-	-	-	*	-	-
<b>Total</b>	<b>----</b>	<b>*</b>	<b>0.1</b>	<b>-</b>	<b>4.9</b>	<b>-</b>	<b>5.3</b>	<b>*</b>	<b>0.2</b>	<b>-</b>	<b>0.2</b>
61	1-2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	*	-	*	-	*	-	-
	4	-	-	-	*	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	<b>----</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>-</b>
71	1-2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	-	-	*	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
<b>Total</b>	<b>----</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>-</b>
12 & 22	1-2	1.7	2.2	-	-	-	*	10.8	6.8	-	-
	3	0.4	0.9	-	*	-	*	0.2	3.6	-	*
	4	*	0.1	-	-	-	*	-	0.6	-	*
	5	-	*	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	<b>----</b>	<b>2.2</b>	<b>3.2</b>	<b>-</b>	<b>*</b>	<b>-</b>	<b>*</b>	<b>11.1</b>	<b>11.0</b>	<b>-</b>	<b>*</b>
32	1-2	0.1	0.5	-	*	-	0.2	14.5	0.8	-	*
	3	0.7	1.3	-	0.1	-	0.5	3.2	1.7	-	*
	4	1.3	0.5	-	0.1	-	0.1	0.2	1.2	-	*
	5	0.3	0.1	-	*	-	*	-	0.3	-	*
	6	-	*	-	*	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
<b>Total</b>	<b>----</b>	<b>2.3</b>	<b>2.3</b>	<b>-</b>	<b>0.1</b>	<b>-</b>	<b>0.8</b>	<b>17.8</b>	<b>4.1</b>	<b>-</b>	<b>0.1</b>
42	1-2	-	*	-	*	-	0.9	0.3	*	-	*
	3	*	0.1	-	0.2	-	5.0	0.6	0.3	-	*
	4	0.1	0.2	-	0.4	-	1.5	0.1	0.5	-	*
	5	0.1	0.1	-	0.1	-	0.1	*	0.3	-	*
	6	-	*	-	*	-	*	-	0.1	-	*
	7	-	*	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
<b>Total</b>	<b>----</b>	<b>0.2</b>	<b>0.5</b>	<b>-</b>	<b>0.7</b>	<b>-</b>	<b>7.5</b>	<b>1.0</b>	<b>1.2</b>	<b>-</b>	<b>0.1</b>

**QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE**  
**For The Week Ending Apr 02, 2026**

Quality Designation	Leaf	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color		Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
52	1-2	-	-	-	*	-	*	-	*	-	-
	3	-	*	-	*	-	0.7	-	*	-	-
	4	-	*	-	0.1	-	0.5	*	*	-	*
	5	-	*	-	*	-	0.1	-	*	-	*
	6	-	*	-	*	-	*	-	*	-	-
	7	-	*	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
<b>Total</b>	----	-	*	-	<b>0.1</b>	-	<b>1.3</b>	*	<b>0.1</b>	-	*
62	1-2	-	-	-	-	-	-	-	*	-	-
	3	-	-	-	-	-	*	-	*	-	-
	4	-	-	-	-	-	*	-	*	-	-
	5	-	-	-	-	-	*	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
<b>Total</b>	----	-	*	-	-	-	*	-	*	-	-
13 & 23	1-2	1.3	0.5	-	-	-	-	0.1	0.6	-	-
	3	0.1	0.2	-	-	-	-	*	0.4	-	*
	4	-	*	-	*	-	-	-	0.1	-	-
	5	-	-	-	-	-	-	-	*	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	----	<b>1.4</b>	<b>0.7</b>	-	*	-	-	<b>0.2</b>	<b>1.1</b>	-	*
33	1-2	0.1	0.1	-	-	-	*	2.4	0.1	-	-
	3	0.1	0.3	-	*	-	*	0.8	0.3	-	*
	4	*	0.1	-	*	-	*	-	0.2	-	*
	5	-	*	-	*	-	-	-	0.1	-	*
	6	-	*	-	-	-	-	-	*	-	-
	7	-	*	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	----	<b>0.2</b>	<b>0.5</b>	-	*	-	*	<b>3.2</b>	<b>0.7</b>	-	*
43	1-2	-	*	-	*	-	*	0.1	*	-	-
	3	-	*	-	*	-	*	0.1	*	-	*
	4	*	*	-	*	-	*	-	*	-	*
	5	-	*	-	*	-	*	-	*	-	*
	6	-	*	-	-	-	*	-	*	-	*
	7	-	*	-	-	-	-	-	*	-	-
	8	-	-	-	-	-	-	-	*	-	-
<b>Total</b>	----	*	<b>0.1</b>	-	*	-	*	<b>0.2</b>	<b>0.1</b>	-	*
53	1-2	-	-	-	-	-	-	-	*	-	-
	3	-	*	-	*	-	*	0.1	*	-	-
	4	-	*	-	*	-	*	-	*	-	-
	5	-	*	-	*	-	*	-	*	-	-
	6	-	*	-	-	-	-	-	*	-	-
	7	-	*	-	*	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	*	-	-
<b>Total</b>	----	-	*	-	*	-	*	<b>0.1</b>	*	-	-
63	1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	*	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	*	-	-
	7	-	*	-	-	-	-	-	*	-	-
	8	-	*	-	-	-	-	-	-	-	-
<b>Total</b>	----	-	*	-	-	-	-	-	*	-	-
24 - 54	1-8	0.6	0.1	-	*	-	-	*	0.1	-	*
25 - 35	1-8	-	-	-	-	-	-	-	-	-	-
81 - 85	1-8	*	*	-	-	-	-	-	*	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	-	-	-	-	-	*	-	-
30		-	-	-	-	-	-	*	*	-	-
31		-	*	-	-	-	-	0.3	0.1	-	-
32		-	0.1	-	*	-	*	2.6	0.6	-	*
33		-	0.6	-	0.2	-	0.1	19.3	2.9	-	*
34		2.3	2.4	-	2.0	-	2.6	41.1	8.7	-	0.6
35		6.9	7.5	-	10.1	-	9.5	21.2	15.9	-	5.4
36		5.4	13.5	-	33.7	-	30.9	7.6	22.0	-	23.0
37		17.7	25.0	-	40.7	-	44.3	6.0	31.2	-	55.4
38		37.2	19.5	-	10.2	-	11.3	2.0	13.5	-	12.8
39		19.4	18.3	-	2.7	-	1.3	-	4.1	-	2.6
40 & Longer		11.1	13.1	-	0.4	-	0.1	-	1.1	-	0.1
<b>Average Staple</b>		<b>37.85</b>	<b>37.60</b>	-	<b>36.56</b>	-	<b>36.56</b>	<b>34.37</b>	<b>36.32</b>	-	<b>36.82</b>
<b>Average Length</b>		<b>1.18</b>	<b>1.17</b>	-	<b>1.14</b>	-	<b>1.14</b>	<b>1.07</b>	<b>1.13</b>	-	<b>1.15</b>

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Apr 02, 2026**

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	-	0.6	-	*	-	0.4	-	1.8	-	1.5	-	1.4
Bark - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Bark - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	0.1	-	*	-	0.2	-	1.1	-	0.1	-	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	*	-	*	-	-	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	0.1	-	1.0	-	0.1	-	-	-	0.3	-	0.3
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	-	-	*	-	-	-	-	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	*	-	*	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	-	-	-	-	-	-	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	-	*	-	*	-	*	-	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
<b>STRENGTH 1/</b>												
22 & Below	-	*	-	-	-	*	-	*	-	-	-	-
23	-	*	-	*	-	*	-	*	-	-	-	*
24	-	*	-	*	-	*	-	0.1	-	-	-	*
25	-	*	-	*	-	0.1	-	0.2	-	*	-	0.1
26	-	0.2	-	*	-	1.0	-	0.8	-	*	-	0.7
27	-	1.7	-	0.2	-	2.9	-	4.0	-	0.4	-	3.6
28	-	8.5	-	1.9	-	8.5	-	12.4	-	3.3	-	11.2
29	-	21.7	-	11.4	-	15.7	-	22.4	-	13.1	-	21.0
30	-	29.0	-	34.3	-	22.2	-	18.7	-	26.8	-	24.8
31	-	21.3	-	33.2	-	20.7	-	11.5	-	27.4	-	19.2
32	-	11.0	-	13.5	-	13.8	-	4.0	-	16.9	-	11.1
33	-	4.5	-	4.1	-	7.7	-	3.7	-	7.3	-	5.2
34	-	1.6	-	1.1	-	4.3	-	6.5	-	3.8	-	2.1
35	-	0.4	-	0.2	-	1.8	-	8.3	-	0.9	-	0.7
36	-	0.1	-	0.1	-	0.8	-	5.4	-	0.1	-	0.2
37	-	*	-	*	-	0.3	-	1.7	-	*	-	0.1
38	-	*	-	*	-	*	-	0.2	-	-	-	*
39	-	-	-	*	-	*	-	*	-	-	-	*
40 & Above	-	-	-	*	-	*	-	*	-	-	-	*
<b>Average</b>	-	<b>30.66</b>	-	<b>31.08</b>	-	<b>31.04</b>	-	<b>31.25</b>	-	<b>31.27</b>	-	<b>30.58</b>
<b>Mike</b>												
2.4 & Below	-	-	-	-	-	*	-	*	-	-	-	-
2.5	-	*	-	-	-	*	-	*	-	-	-	-
2.6	-	*	-	-	-	0.1	-	0.1	-	-	-	*
2.7	-	*	-	-	-	0.1	-	0.1	-	-	-	*
2.8	-	*	-	*	-	0.2	-	0.2	-	-	-	*
2.9	-	*	-	-	-	0.1	-	0.2	-	-	-	*
3.0	-	*	-	*	-	0.2	-	0.2	-	-	-	*
3.1	-	*	-	*	-	0.2	-	0.4	-	*	-	*
3.2	-	*	-	*	-	0.4	-	0.4	-	0.1	-	0.1
3.3	-	0.1	-	*	-	0.4	-	0.6	-	0.1	-	0.2
3.4	-	0.4	-	*	-	0.5	-	0.6	-	0.1	-	0.3
3.5	-	0.8	-	*	-	0.7	-	1.5	-	0.5	-	0.6
3.6	-	1.1	-	0.1	-	1.0	-	2.4	-	0.7	-	1.2
3.7	-	2.0	-	0.1	-	1.8	-	3.4	-	1.2	-	1.9
3.8	-	3.0	-	0.1	-	2.5	-	5.4	-	1.3	-	2.9
3.9	-	4.4	-	0.3	-	3.5	-	8.8	-	2.1	-	4.1
4.0	-	5.9	-	0.6	-	5.2	-	11.0	-	3.4	-	5.6
4.1	-	8.0	-	1.1	-	7.3	-	11.4	-	5.6	-	7.4
4.2	-	9.8	-	1.8	-	9.2	-	10.8	-	7.1	-	9.0
4.3	-	10.8	-	3.2	-	10.6	-	7.7	-	9.7	-	9.8
4.4	-	10.6	-	5.1	-	11.2	-	5.1	-	12.3	-	10.0
4.5	-	10.1	-	7.9	-	10.9	-	5.5	-	13.0	-	9.7
4.6	-	8.9	-	11.7	-	10.0	-	5.4	-	11.2	-	9.1
4.7	-	7.1	-	14.5	-	7.7	-	5.2	-	12.4	-	8.2
4.8	-	5.6	-	15.4	-	5.7	-	4.0	-	8.4	-	6.7
4.9	-	4.3	-	13.6	-	4.3	-	3.2	-	5.2	-	5.1
5.0	-	2.8	-	10.8	-	2.8	-	2.2	-	3.2	-	3.6
5.1	-	1.8	-	6.9	-	1.2	-	2.0	-	1.7	-	2.3
5.2	-	1.1	-	4.0	-	0.9	-	0.9	-	0.5	-	1.2
5.3	-	0.7	-	1.9	-	0.6	-	0.7	-	0.1	-	0.6
5.4	-	0.3	-	0.6	-	0.3	-	0.5	-	0.1	-	0.2
5.5 & Above	-	0.2	-	0.2	-	0.3	-	0.2	-	0.1	-	0.1
<b>Average</b>	-	<b>4.39</b>	-	<b>4.76</b>	-	<b>4.38</b>	-	<b>4.24</b>	-	<b>4.48</b>	-	<b>4.41</b>

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE**  
**For The Week Ending Apr 02, 2026**

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter												
Bark - Level 1	-	41.1	-	0.1	-	*	-	*	-	1.6	-	6.5
Bark - Level 2	-	*	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	-	0.1	-	*	-	*	-	*	-	*	-	0.6
Grass - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	-	-	-	-	*	-	*	-	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	0.4	-	0.2	-	0.3	-	0.5	-	-
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	-	-	-	-	-	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	-	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	-	*	-	*	-	*	-	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/ 22 & Below	-	*	-	-	-	*	-	-	-	-	-	*
23	-	*	-	-	-	*	-	-	-	-	-	-
24	-	0.1	-	-	-	*	-	*	-	*	-	-
25	-	0.2	-	*	-	*	-	*	-	*	-	*
26	-	0.6	-	*	-	*	-	0.1	-	0.3	-	0.2
27	-	1.3	-	0.5	-	0.1	-	1.0	-	2.3	-	1.5
28	-	2.6	-	4.4	-	0.7	-	4.8	-	10.9	-	6.0
29	-	4.5	-	19.0	-	8.1	-	15.6	-	28.2	-	18.9
30	-	8.9	-	33.2	-	36.9	-	26.9	-	31.5	-	30.2
31	-	16.9	-	21.1	-	35.7	-	26.3	-	17.3	-	20.7
32	-	24.9	-	11.7	-	13.0	-	16.1	-	6.9	-	16.5
33	-	22.3	-	5.1	-	4.5	-	6.5	-	2.0	-	4.4
34	-	12.0	-	2.9	-	1.0	-	2.3	-	0.4	-	1.3
35	-	4.6	-	1.8	-	0.1	-	0.4	-	0.1	-	0.1
36	-	0.9	-	0.2	-	*	-	*	-	*	-	-
37	-	0.2	-	*	-	*	-	*	-	-	-	*
38	-	0.1	-	*	-	*	-	*	-	-	-	-
39	-	*	-	-	-	-	-	-	-	-	-	*
40 & Above	-	*	-	-	-	-	-	*	-	-	-	-
<b>Average</b>	-	<b>32.40</b>	-	<b>30.97</b>	-	<b>31.15</b>	-	<b>31.06</b>	-	<b>30.26</b>	-	<b>30.81</b>
Mike												
2.4 & Below	-	0.3	-	-	-	-	-	-	-	-	-	-
2.5	-	1.3	-	-	-	-	-	-	-	*	-	*
2.6	-	1.6	-	*	-	-	-	-	-	-	-	*
2.7	-	2.2	-	*	-	-	-	-	-	*	-	0.2
2.8	-	2.5	-	-	-	-	-	-	-	*	-	2.7
2.9	-	2.5	-	*	-	-	-	-	-	*	-	2.5
3.0	-	2.8	-	*	-	-	-	-	-	*	-	1.8
3.1	-	3.3	-	*	-	*	-	-	-	*	-	1.7
3.2	-	3.9	-	*	-	*	-	*	-	0.1	-	2.9
3.3	-	4.3	-	*	-	*	-	*	-	0.2	-	1.4
3.4	-	5.3	-	0.1	-	*	-	*	-	0.3	-	0.9
3.5	-	5.9	-	0.1	-	*	-	0.1	-	0.5	-	1.0
3.6	-	6.3	-	0.1	-	0.1	-	0.1	-	0.9	-	1.1
3.7	-	6.5	-	0.2	-	0.2	-	0.2	-	1.5	-	2.7
3.8	-	6.4	-	0.3	-	0.3	-	0.3	-	2.4	-	4.5
3.9	-	6.3	-	0.6	-	0.6	-	0.4	-	3.5	-	6.9
4.0	-	6.7	-	1.3	-	1.4	-	0.8	-	4.9	-	6.2
4.1	-	7.0	-	2.2	-	2.4	-	1.3	-	7.0	-	6.2
4.2	-	5.7	-	3.4	-	4.3	-	2.0	-	9.3	-	6.8
4.3	-	5.6	-	4.9	-	6.7	-	3.0	-	11.6	-	9.5
4.4	-	4.6	-	6.3	-	9.8	-	4.5	-	12.2	-	9.1
4.5	-	3.3	-	8.2	-	13.0	-	6.2	-	11.3	-	8.7
4.6	-	2.0	-	9.7	-	15.1	-	8.7	-	10.2	-	6.6
4.7	-	1.6	-	11.2	-	15.7	-	11.2	-	8.5	-	6.0
4.8	-	1.2	-	12.6	-	13.2	-	13.6	-	6.0	-	5.1
4.9	-	0.5	-	11.7	-	8.7	-	14.6	-	4.1	-	3.6
5.0	-	0.2	-	9.6	-	4.9	-	13.3	-	2.7	-	1.6
5.1	-	*	-	7.7	-	2.3	-	9.9	-	1.5	-	0.2
5.2	-	*	-	4.4	-	0.9	-	5.7	-	0.7	-	*
5.3	-	-	-	2.6	-	0.3	-	2.6	-	0.3	-	*
5.4	-	-	-	1.3	-	0.1	-	1.0	-	0.1	-	-
5.5 & Above	-	-	-	1.4	-	*	-	0.4	-	*	-	-
<b>Average</b>	-	<b>3.73</b>	-	<b>4.74</b>	-	<b>4.61</b>	-	<b>4.80</b>	-	<b>4.41</b>	-	<b>4.14</b>

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).  
\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE**  
**For The Week Ending Apr 02, 2026**

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter										
Bark - Level 1	0.7	3.7	-	3.6	-	*	1.3	4.7	-	1.3
Bark - Level 2	-	*	-	-	-	-	-	*	-	-
Grass - Level 1	-	0.1	-	0.1	-	*	-	0.2	-	*
Grass - Level 2	-	-	-	-	-	-	-	*	-	-
Prep - Level 1	-	*	-	*	-	-	-	*	-	*
Prep - Level 2	-	*	-	-	-	-	-	-	-	-
Seed Coat - Level 1	-	*	-	1.7	-	*	-	0.3	-	0.6
Seed Coat - Level 2	-	*	-	-	-	-	-	*	-	-
Oil - Level 1	-	*	-	*	-	-	-	*	-	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	*	-	-
Other - Level 1	-	*	-	-	-	-	-	*	-	-
Other - Level 2	-	*	-	-	-	-	-	-	-	-
Plastic - Level 1	-	*	-	*	-	*	0.1	*	-	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
<b>STRENGTH 1/</b>										
22 & Below	-	*	-	-	-	-	-	*	-	-
23	-	*	-	-	-	-	0.1	*	-	-
24	*	*	-	*	-	*	0.4	0.1	-	*
25	0.2	*	-	*	-	*	2.3	0.2	-	*
26	0.7	0.2	-	0.4	-	*	11.5	0.9	-	1.1
27	4.6	1.0	-	2.6	-	0.5	39.7	3.1	-	6.2
28	14.5	4.0	-	12.6	-	3.8	22.1	8.1	-	19.0
29	17.0	10.0	-	34.7	-	21.0	11.6	16.1	-	32.2
30	23.6	16.6	-	30.2	-	38.7	4.0	20.9	-	25.7
31	22.8	19.2	-	13.3	-	24.7	2.4	18.4	-	11.1
32	12.4	16.3	-	4.8	-	8.2	2.8	13.1	-	3.6
33	3.4	13.7	-	1.2	-	2.4	2.2	9.2	-	0.8
34	0.6	9.8	-	0.2	-	0.7	0.7	6.0	-	0.2
35	0.1	5.4	-	*	-	0.1	0.1	2.6	-	*
36	*	2.2	-	*	-	*	-	0.9	-	*
37	-	1.1	-	*	-	*	*	0.3	-	-
38	-	0.2	-	-	-	-	-	0.1	-	-
39	-	*	-	-	-	-	-	*	-	-
40 & Above	-	*	-	-	-	-	-	*	-	-
<b>Average</b>	<b>30.42</b>	<b>32.05</b>	<b>-</b>	<b>30.02</b>	<b>-</b>	<b>30.66</b>	<b>28.27</b>	<b>31.16</b>	<b>-</b>	<b>29.73</b>
<b>Mike</b>										
2.4 & Below	-	*	-	-	-	-	-	*	-	-
2.5	-	*	-	-	-	-	-	0.1	-	-
2.6	*	*	-	-	-	-	-	0.1	-	-
2.7	0.2	0.1	-	-	-	*	-	0.2	-	*
2.8	0.3	0.1	-	*	-	*	-	0.3	-	*
2.9	0.3	0.1	-	*	-	*	-	0.4	-	*
3.0	0.4	0.2	-	*	-	*	0.1	0.6	-	0.1
3.1	0.4	0.3	-	*	-	*	-	0.8	-	0.1
3.2	0.6	0.6	-	0.1	-	*	-	1.2	-	0.1
3.3	1.5	1.0	-	0.2	-	*	-	1.6	-	0.3
3.4	2.8	1.3	-	0.3	-	0.1	*	2.1	-	0.4
3.5	4.2	1.9	-	0.5	-	0.3	0.4	2.7	-	0.7
3.6	5.3	3.3	-	0.9	-	0.3	1.1	3.4	-	1.3
3.7	6.1	4.6	-	1.9	-	0.8	2.2	4.1	-	2.6
3.8	8.3	6.1	-	2.8	-	1.1	4.1	5.1	-	3.9
3.9	10.7	7.5	-	4.3	-	1.7	6.8	6.3	-	6.7
4.0	13.5	8.8	-	5.8	-	2.5	7.5	7.5	-	9.2
4.1	11.4	10.0	-	7.3	-	3.9	11.6	8.6	-	11.5
4.2	9.7	10.0	-	8.7	-	5.3	8.9	9.5	-	14.1
4.3	7.1	10.4	-	9.9	-	6.7	15.1	9.8	-	14.5
4.4	5.9	9.5	-	10.4	-	9.5	21.7	9.2	-	12.7
4.5	4.2	8.6	-	10.4	-	11.8	11.1	8.0	-	9.1
4.6	2.6	6.7	-	9.7	-	13.4	4.7	6.4	-	5.9
4.7	1.9	4.5	-	8.5	-	13.4	2.4	4.7	-	3.2
4.8	2.0	2.5	-	6.7	-	11.8	1.7	3.2	-	1.8
4.9	0.4	1.1	-	4.9	-	8.1	0.4	1.9	-	1.1
5.0	*	0.5	-	3.3	-	5.4	-	1.1	-	0.6
5.1	-	0.1	-	1.9	-	2.7	-	0.6	-	0.2
5.2	*	*	-	1.0	-	1.0	-	0.3	-	*
5.3	-	*	-	0.4	-	0.3	-	0.1	-	*
5.4	-	-	-	0.2	-	*	-	0.1	-	*
5.5 & Above	-	*	-	0.1	-	*	-	0.1	-	*
<b>Average</b>	<b>4.01</b>	<b>4.17</b>	<b>-</b>	<b>4.41</b>	<b>-</b>	<b>4.56</b>	<b>4.25</b>	<b>4.16</b>	<b>-</b>	<b>4.23</b>

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).  
\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Apr 02, 2026**

Quality Designation	ALABAMA		ARKANSAS		ARIZONA		CALIFORNIA		FLORIDA		GEORGIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	-	-	-	-	*	-	*	-	-	-	-
2.5 - 2.6	-	*	-	-	-	0.1	-	0.1	-	-	-	*
2.7 - 2.9	-	*	-	*	-	0.4	-	0.5	-	-	-	*
3.0 - 3.2	-	0.1	-	*	-	0.8	-	0.9	-	0.1	-	0.1
3.3 - 3.4	-	0.6	-	*	-	0.9	-	1.2	-	0.1	-	0.5
3.5 - 3.6	-	1.9	-	0.1	-	1.7	-	3.9	-	1.2	-	1.8
3.7 - 4.2	-	33.1	-	4.1	-	29.5	-	50.9	-	20.7	-	30.9
4.3 - 4.9	-	57.4	-	71.3	-	60.4	-	36.1	-	72.1	-	58.6
5.0 - 5.2	-	5.7	-	21.8	-	4.9	-	5.1	-	5.4	-	7.1
5.3 & Above	-	1.1	-	2.7	-	1.3	-	1.4	-	0.3	-	0.9
<b>Average</b>	-	<b>4.39</b>	-	<b>4.76</b>	-	<b>4.38</b>	-	<b>4.24</b>	-	<b>4.48</b>	-	<b>4.41</b>
Leaf												
1 - 2	-	15.4	-	2.1	-	31.9	-	39.4	-	7.8	-	14.8
3	-	55.0	-	39.0	-	36.1	-	42.3	-	52.7	-	58.6
4	-	25.4	-	45.6	-	21.6	-	13.2	-	34.5	-	23.5
5	-	3.9	-	11.9	-	7.7	-	3.8	-	4.8	-	2.9
6	-	0.3	-	1.3	-	2.1	-	1.1	-	0.3	-	0.2
7	-	*	-	0.1	-	0.4	-	0.2	-	*	-	*
8	-	*	-	-	-	0.1	-	0.1	-	-	-	*
<b>Average</b>	-	<b>3.18</b>	-	<b>3.71</b>	-	<b>3.08</b>	-	<b>2.79</b>	-	<b>3.37</b>	-	<b>3.15</b>
HVI Trash 1/												
00	-	-	-	-	-	*	-	*	-	-	-	-
01	-	2.0	-	0.1	-	12.4	-	14.2	-	0.9	-	1.4
02	-	17.6	-	3.1	-	24.5	-	30.2	-	9.4	-	19.9
03	-	28.1	-	14.7	-	19.8	-	24.8	-	23.4	-	32.0
04	-	23.9	-	24.5	-	15.5	-	14.2	-	28.1	-	23.6
05	-	14.5	-	22.9	-	10.9	-	7.3	-	19.3	-	12.7
06	-	7.5	-	16.0	-	6.9	-	3.8	-	10.3	-	5.9
07	-	3.6	-	9.4	-	4.3	-	2.2	-	4.8	-	2.6
08	-	1.6	-	4.9	-	2.5	-	1.4	-	2.2	-	1.1
09	-	0.7	-	2.4	-	1.5	-	0.8	-	0.9	-	0.5
10	-	0.3	-	1.1	-	0.8	-	0.5	-	0.5	-	0.2
11	-	0.1	-	0.5	-	0.5	-	0.3	-	0.2	-	0.1
12	-	0.1	-	0.2	-	0.2	-	0.2	-	0.1	-	*
13	-	*	-	0.1	-	0.1	-	0.1	-	*	-	*
14	-	*	-	*	-	0.1	-	0.1	-	*	-	*
15	-	*	-	*	-	*	-	*	-	*	-	*
16	-	*	-	-	-	*	-	*	-	*	-	*
17	-	*	-	-	-	*	-	*	-	*	-	*
18 & Above	-	*	-	-	-	*	-	*	-	*	-	*
<b>Average</b>	-	<b>0.38</b>	-	<b>0.51</b>	-	<b>0.36</b>	-	<b>0.31</b>	-	<b>0.43</b>	-	<b>0.37</b>
UNIFORMITY 2/												
74 & Below	-	-	-	-	-	-	-	-	-	-	-	-
75	-	-	-	-	-	*	-	-	-	-	-	*
76	-	*	-	*	-	*	-	*	-	*	-	*
77	-	*	-	*	-	0.2	-	0.2	-	*	-	0.1
78	-	0.4	-	0.1	-	0.8	-	1.6	-	0.1	-	0.9
79	-	3.0	-	0.5	-	3.1	-	6.6	-	1.1	-	5.5
80	-	14.0	-	3.9	-	14.8	-	28.6	-	7.8	-	21.3
81	-	32.0	-	20.3	-	36.8	-	30.8	-	37.1	-	36.2
82	-	34.2	-	42.8	-	35.2	-	19.8	-	41.9	-	26.3
83	-	14.3	-	27.9	-	8.5	-	9.6	-	10.9	-	8.2
84	-	1.9	-	4.3	-	0.7	-	2.7	-	1.1	-	1.3
85 & Above	-	0.2	-	0.3	-	*	-	0.1	-	0.1	-	0.1
<b>Average</b>	-	<b>81.93</b>	-	<b>82.52</b>	-	<b>81.75</b>	-	<b>81.45</b>	-	<b>82.02</b>	-	<b>81.56</b>
Tenderable 3/	-	<b>89.9</b>	-	<b>70.4</b>	-	<b>86.3</b>	-	<b>85.6</b>	-	<b>91.0</b>	-	<b>88.4</b>
<b>SAMPLES CLASSED</b>	-	<b>549,869</b>	-	<b>1,421,220</b>	-	<b>232,176</b>	-	<b>94,092</b>	-	<b>90,069</b>	-	<b>1,738,474</b>

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. \* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Apr 02, 2026**

Quality Designation	KANSAS		LOUISIANA		MISSOURI		MISSISSIPPI		NORTH CAROLINA		NEW MEXICO	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE												
2.4 & Below	-	0.3	-	-	-	-	-	-	-	-	-	-
2.5 - 2.6	-	2.9	-	*	-	-	-	-	-	*	-	*
2.7 - 2.9	-	7.2	-	*	-	-	-	-	-	*	-	5.3
3.0 - 3.2	-	10.0	-	*	-	*	-	*	-	0.2	-	6.3
3.3 - 3.4	-	9.6	-	0.1	-	*	-	*	-	0.5	-	2.4
3.5 - 3.6	-	12.2	-	0.2	-	0.1	-	0.2	-	1.4	-	2.1
3.7 - 4.2	-	38.6	-	8.1	-	9.2	-	5.0	-	28.6	-	33.2
4.3 - 4.9	-	18.9	-	64.6	-	82.2	-	61.8	-	64.0	-	48.8
5.0 - 5.2	-	0.3	-	21.7	-	8.1	-	29.0	-	4.9	-	1.9
5.3 & Above	-	-	-	5.2	-	0.5	-	4.0	-	0.4	-	*
<b>Average</b>	-	<b>3.73</b>	-	<b>4.74</b>	-	<b>4.61</b>	-	<b>4.80</b>	-	<b>4.41</b>	-	<b>4.14</b>
Leaf												
1 - 2	-	6.5	-	14.2	-	4.2	-	6.3	-	9.3	-	51.1
3	-	23.6	-	49.8	-	53.5	-	42.8	-	51.8	-	31.5
4	-	30.1	-	29.5	-	36.7	-	39.7	-	32.6	-	12.8
5	-	22.9	-	6.1	-	5.2	-	10.1	-	5.8	-	3.6
6	-	11.9	-	0.4	-	0.3	-	1.0	-	0.6	-	0.9
7	-	4.1	-	-	-	*	-	*	-	0.1	-	0.1
8	-	0.9	-	-	-	-	-	-	-	*	-	-
<b>Average</b>	-	<b>4.26</b>	-	<b>3.28</b>	-	<b>3.44</b>	-	<b>3.57</b>	-	<b>3.37</b>	-	<b>2.62</b>
HVI Trash 1/												
00	-	-	-	-	-	*	-	-	-	-	-	-
01	-	1.4	-	1.9	-	0.2	-	0.5	-	0.8	-	18.8
02	-	6.7	-	15.0	-	6.4	-	7.7	-	11.1	-	36.3
03	-	10.9	-	24.4	-	23.6	-	19.0	-	24.4	-	19.7
04	-	12.7	-	23.2	-	28.8	-	23.6	-	25.5	-	11.1
05	-	12.6	-	16.2	-	20.7	-	19.9	-	18.3	-	6.7
06	-	11.1	-	9.6	-	11.2	-	13.3	-	10.5	-	3.5
07	-	9.8	-	5.2	-	5.2	-	7.9	-	5.2	-	2.0
08	-	8.4	-	2.5	-	2.2	-	4.2	-	2.4	-	1.1
09	-	6.9	-	1.2	-	1.0	-	2.1	-	1.0	-	0.5
10	-	5.3	-	0.5	-	0.4	-	1.0	-	0.4	-	0.2
11	-	4.1	-	0.2	-	0.2	-	0.5	-	0.2	-	0.1
12	-	3.1	-	0.1	-	0.1	-	0.2	-	0.1	-	0.1
13	-	2.3	-	*	-	*	-	0.1	-	*	-	*
14	-	1.6	-	*	-	*	-	*	-	*	-	-
15	-	1.0	-	-	-	*	-	*	-	*	-	-
16	-	0.7	-	-	-	-	-	-	-	*	-	-
17	-	0.5	-	-	-	-	-	-	-	*	-	-
18 & Above	-	0.8	-	-	-	-	-	-	-	*	-	-
<b>Average</b>	-	<b>0.66</b>	-	<b>0.41</b>	-	<b>0.44</b>	-	<b>0.47</b>	-	<b>0.43</b>	-	<b>0.28</b>
UNIFORMITY 2/												
74 & Below	-	*	-	-	-	-	-	-	-	*	-	-
75	-	0.2	-	-	-	-	-	-	-	*	-	*
76	-	0.8	-	-	-	*	-	*	-	*	-	0.1
77	-	2.4	-	-	-	*	-	*	-	*	-	0.1
78	-	4.7	-	0.1	-	0.1	-	0.2	-	0.6	-	3.0
79	-	8.8	-	1.2	-	0.2	-	1.3	-	3.0	-	9.2
80	-	18.3	-	7.1	-	2.1	-	8.8	-	11.0	-	17.2
81	-	31.0	-	30.1	-	16.5	-	30.1	-	27.2	-	34.5
82	-	22.9	-	40.4	-	50.4	-	38.1	-	35.3	-	28.8
83	-	9.2	-	18.5	-	27.9	-	18.1	-	19.9	-	6.7
84	-	1.6	-	2.6	-	2.5	-	3.3	-	2.7	-	0.3
85 & Above	-	0.1	-	0.1	-	0.2	-	0.1	-	0.2	-	*
<b>Average</b>	-	<b>81.26</b>	-	<b>82.20</b>	-	<b>82.57</b>	-	<b>82.18</b>	-	<b>82.10</b>	-	<b>81.41</b>
Tenderable 3/	-	<b>32.5</b>	-	<b>71.5</b>	-	<b>86.7</b>	-	<b>63.7</b>	-	<b>90.7</b>	-	<b>81.6</b>
<b>SAMPLES CLASSED</b>	-	<b>160,354</b>	-	<b>223,299</b>	-	<b>680,258</b>	-	<b>706,521</b>	-	<b>653,677</b>	-	<b>12,080</b>

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. \* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Apr 02, 2026**

Quality Designation	OKLAHOMA		SOUTH CAROLINA		TENNESSEE		TEXAS		VIRGINIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE										
2.4 & Below	-	*	-	-	-	-	-	*	-	-
2.5 - 2.6	*	0.1	-	-	-	-	-	0.2	-	-
2.7 - 2.9	0.9	0.3	-	*	-	*	-	0.8	-	*
3.0 - 3.2	1.4	1.1	-	0.1	-	*	0.1	2.7	-	0.3
3.3 - 3.4	4.4	2.3	-	0.5	-	0.2	*	3.7	-	0.6
3.5 - 3.6	9.5	5.2	-	1.4	-	0.6	1.5	6.2	-	2.0
3.7 - 4.2	59.7	47.1	-	30.7	-	15.1	41.2	41.0	-	48.0
4.3 - 4.9	24.1	43.4	-	60.4	-	74.7	57.3	43.2	-	48.2
5.0 - 5.2	*	0.5	-	6.2	-	9.0	-	2.0	-	0.8
5.3 & Above	-	*	-	0.7	-	0.3	-	0.3	-	*
<b>Average</b>	<b>4.01</b>	<b>4.17</b>	<b>-</b>	<b>4.41</b>	<b>-</b>	<b>4.56</b>	<b>4.25</b>	<b>4.16</b>	<b>-</b>	<b>4.23</b>
Leaf										
1 - 2	51.1	59.9	-	4.5	-	16.4	70.5	57.2	-	11.3
3	41.7	32.1	-	49.0	-	59.0	23.3	31.4	-	61.2
4	6.6	6.8	-	40.1	-	21.8	5.7	9.2	-	24.3
5	0.6	1.0	-	6.1	-	2.7	0.4	1.8	-	3.1
6	-	0.1	-	0.3	-	0.2	*	0.3	-	0.1
7	-	*	-	*	-	*	-	*	-	*
8	-	*	-	-	-	-	-	*	-	-
<b>Average</b>	<b>2.49</b>	<b>2.30</b>	<b>-</b>	<b>3.49</b>	<b>-</b>	<b>3.11</b>	<b>2.18</b>	<b>2.41</b>	<b>-</b>	<b>3.20</b>
HVI Trash 1/										
00	-	*	-	-	-	*	*	0.1	-	-
01	16.9	29.8	-	0.2	-	2.0	35.1	27.6	-	0.5
02	43.0	33.9	-	6.5	-	17.1	38.3	34.2	-	12.5
03	24.0	19.4	-	22.2	-	29.7	13.1	18.2	-	29.6
04	9.6	9.5	-	27.5	-	24.7	8.0	9.6	-	26.5
05	3.9	4.1	-	21.5	-	14.2	3.2	5.1	-	16.0
06	1.5	1.7	-	12.3	-	6.8	1.2	2.6	-	8.3
07	0.5	0.8	-	5.8	-	3.1	0.6	1.3	-	3.9
08	0.4	0.4	-	2.4	-	1.3	0.2	0.6	-	1.7
09	0.1	0.2	-	0.9	-	0.6	0.1	0.3	-	0.7
10	0.1	0.1	-	0.4	-	0.2	0.1	0.1	-	0.2
11	*	*	-	0.1	-	0.1	*	0.1	-	0.1
12	*	*	-	*	-	*	-	*	-	*
13	-	*	-	*	-	*	-	*	-	*
14	-	*	-	*	-	*	-	*	-	*
15	-	*	-	*	-	*	-	*	-	*
16	-	*	-	*	-	-	-	*	-	*
17	-	*	-	-	-	-	-	*	-	*
18 & Above	-	*	-	*	-	-	-	*	-	*
<b>Average</b>	<b>0.25</b>	<b>0.24</b>	<b>-</b>	<b>0.45</b>	<b>-</b>	<b>0.38</b>	<b>0.21</b>	<b>0.25</b>	<b>-</b>	<b>0.40</b>
UNIFORMITY 2/										
74 & Below	-	*	-	-	-	-	-	*	-	-
75	-	*	-	*	-	-	0.1	*	-	-
76	-	*	-	*	-	*	0.1	0.2	-	*
77	*	0.3	-	0.1	-	*	0.4	0.9	-	*
78	0.5	1.5	-	0.5	-	0.1	8.3	4.0	-	0.2
79	4.6	7.1	-	3.8	-	0.6	26.6	12.9	-	1.3
80	19.9	20.5	-	16.7	-	6.9	31.8	26.4	-	8.2
81	33.6	31.2	-	32.9	-	32.7	18.4	29.4	-	27.9
82	30.5	24.2	-	32.4	-	43.1	11.9	17.8	-	38.3
83	9.9	11.9	-	12.4	-	15.6	2.5	6.6	-	21.1
84	1.0	3.0	-	1.1	-	0.9	*	1.5	-	2.9
85 & Above	*	0.2	-	0.1	-	0.1	-	0.2	-	0.2
<b>Average</b>	<b>81.68</b>	<b>81.62</b>	<b>-</b>	<b>81.80</b>	<b>-</b>	<b>82.14</b>	<b>80.48</b>	<b>81.12</b>	<b>-</b>	<b>82.23</b>
Tenderable 3/	<b>90.2</b>	<b>90.9</b>	<b>-</b>	<b>86.4</b>	<b>-</b>	<b>82.3</b>	<b>90.8</b>	<b>82.2</b>	<b>-</b>	<b>96.1</b>
<b>SAMPLES CLASSED</b>	<b>8,407</b>	<b>498,505</b>	<b>-</b>	<b>283,935</b>	<b>-</b>	<b>340,307</b>	<b>3,790</b>	<b>5,232,426</b>	<b>-</b>	<b>172,921</b>

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. \* Less than 0.05 percent.

**QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE**  
**For The Week Ending Apr 02, 2026**

Color Grade	Leaf	Arizona		California		New Mexico		Texas	
		Week	Season	Week	Season	Week	Season	Week	Season
01	1	-	6.4	-	5.1	-	-	-	16.4
	2	-	2.8	-	6.3	-	-	-	20.6
	3	-	0.3	-	0.1	-	-	-	0.6
	4	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total -----</b>		-	<b>9.5</b>	-	<b>11.6</b>	-	-	-	<b>37.6</b>
02	1	-	36.4	-	4.5	-	-	-	12.5
	2	-	21.5	-	33.8	-	-	-	40.5
	3	-	0.5	-	9.0	-	-	-	3.4
	4	-	*	-	0.1	-	-	-	0.1
	5	-	-	-	*	-	-	-	*
	6	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total -----</b>		-	<b>58.4</b>	-	<b>47.4</b>	-	-	-	<b>56.5</b>
03	1	-	7.3	-	0.2	-	-	-	0.3
	2	-	19.0	-	14.4	-	-	-	4.3
	3	-	1.7	-	19.2	-	-	-	0.9
	4	-	0.1	-	2.3	-	-	-	0.1
	5	-	-	-	0.1	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total -----</b>		-	<b>28.2</b>	-	<b>36.1</b>	-	-	-	<b>5.6</b>
04	7	-	-	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-
	5	-	-	-	0.1	-	-	-	*
	4	-	*	-	1.0	-	-	-	0.1
	3	-	0.8	-	2.3	-	-	-	0.1
	2	-	2.6	-	0.6	-	-	-	0.1
	1	-	0.2	-	*	-	-	-	-
<b>Total -----</b>		-	<b>3.7</b>	-	<b>4.0</b>	-	-	-	<b>0.3</b>
05	1	-	*	-	*	-	-	-	-
	2	-	0.2	-	0.1	-	-	-	-
	3	-	0.1	-	0.3	-	-	-	*
	4	-	-	-	0.2	-	-	-	*
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total -----</b>		-	<b>0.3</b>	-	<b>0.7</b>	-	-	-	<b>*</b>
06	1	-	-	-	-	-	-	-	-
	2	-	-	-	*	-	-	-	-
	3	-	-	-	0.1	-	-	-	-
	4	-	-	-	0.1	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total -----</b>		-	-	-	<b>0.1</b>	-	-	-	-
07	1	-	-	-	-	-	-	-	-
	2	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-
	4	-	-	-	*	-	-	-	-
	5	-	-	-	*	-	-	-	-
	6	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-
<b>Total -----</b>		-	-	-	<b>0.1</b>	-	-	-	-
<b>STAPLE</b>									
44 & Shorter	-	*	-	2.3	-	-	-	13.1	
46	-	11.5	-	7.5	-	-	-	46.6	
48	-	71.8	-	43.9	-	-	-	35.4	
50	-	16.4	-	44.0	-	-	-	4.6	
52 & Longer	-	0.2	-	2.3	-	-	-	0.4	
<b>Average Staple</b>	-	<b>48.10</b>	-	<b>48.73</b>	-	-	-	<b>46.65</b>	
<b>Average Length</b>	-	<b>1.40</b>	-	<b>1.42</b>	-	-	-	<b>1.36</b>	
<b>EXTRANEIOUS MATTER</b>									
Bark	-	*	-	*	-	-	-	0.2	
Grass	-	-	-	0.2	-	-	-	1.0	
Spindle Twist	-	*	-	0.2	-	-	-	*	
Preparation	-	*	-	*	-	-	-	-	
All Other	-	*	-	*	-	-	-	0.1	

\* Less than 0.05 percent.

**QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE**  
**For The Week Ending Apr 02, 2026**

Quality Designation	Arizona		California		New Mexico		Texas	
	Week	Season	Week	Season	Week	Season	Week	Season
MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5 - 2.6	-	-	-	-	-	-	-	*
2.7 - 2.9	-	0.1	-	0.1	-	-	-	0.3
3.0 - 3.2	-	0.5	-	0.5	-	-	-	9.6
3.3 - 3.4	-	0.5	-	1.4	-	-	-	13.4
3.5 - 3.6	-	3.9	-	6.9	-	-	-	19.1
3.7 - 4.2	-	88.3	-	87.2	-	-	-	54.2
4.3 - 4.9	-	6.7	-	3.9	-	-	-	3.4
5.0 - 5.2	-	*	-	*	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
<b>Average</b>	-	<b>3.97</b>	-	<b>3.91</b>	-	-	-	<b>3.71</b>
ALL RANGE MIKE								
2.4 & Below	-	-	-	-	-	-	-	-
2.5	-	-	-	-	-	-	-	-
2.6	-	-	-	-	-	-	-	*
2.7	-	*	-	*	-	-	-	*
2.8	-	*	-	*	-	-	-	*
2.9	-	*	-	0.1	-	-	-	0.2
3.0	-	0.1	-	0.1	-	-	-	1.5
3.1	-	0.2	-	0.1	-	-	-	3.8
3.2	-	0.3	-	0.2	-	-	-	4.3
3.3	-	0.2	-	0.5	-	-	-	4.7
3.4	-	0.4	-	1.0	-	-	-	8.7
3.5	-	1.2	-	2.0	-	-	-	9.9
3.6	-	2.7	-	4.9	-	-	-	9.2
3.7	-	7.1	-	9.6	-	-	-	9.7
3.8	-	12.4	-	16.1	-	-	-	10.4
3.9	-	18.3	-	21.8	-	-	-	11.3
4.0	-	22.2	-	20.4	-	-	-	10.3
4.1	-	19.1	-	12.7	-	-	-	8.7
4.2	-	9.3	-	6.6	-	-	-	3.8
4.3	-	3.7	-	2.5	-	-	-	2.1
4.4	-	2.3	-	0.9	-	-	-	0.6
4.5	-	0.4	-	0.4	-	-	-	0.4
4.6	-	0.2	-	0.1	-	-	-	0.2
4.7	-	*	-	*	-	-	-	*
4.8	-	*	-	*	-	-	-	*
4.9	-	*	-	*	-	-	-	*
5.0	-	*	-	*	-	-	-	-
5.1	-	-	-	*	-	-	-	-
5.2	-	-	-	-	-	-	-	-
5.3 & Above	-	-	-	-	-	-	-	-
<b>Average</b>	-	<b>3.97</b>	-	<b>3.91</b>	-	-	-	<b>3.71</b>
STRENGTH 1/								
36 & Below	-	0.1	-	1.4	-	-	-	10.7
37	-	0.2	-	4.1	-	-	-	16.5
38	-	0.6	-	2.9	-	-	-	17.2
39	-	1.2	-	1.2	-	-	-	7.4
40	-	5.2	-	1.6	-	-	-	2.7
41	-	18.2	-	4.9	-	-	-	3.1
42	-	29.1	-	10.0	-	-	-	5.4
43	-	26.8	-	16.4	-	-	-	7.6
44	-	13.4	-	20.8	-	-	-	9.9
45	-	4.2	-	18.8	-	-	-	8.9
46	-	0.8	-	11.0	-	-	-	6.6
47	-	0.2	-	4.7	-	-	-	2.8
48 & Above	-	0.2	-	2.2	-	-	-	1.3
<b>Average</b>	-	<b>42.81</b>	-	<b>43.88</b>	-	-	-	<b>40.97</b>
UNIFORMITY								
83 & Below	-	0.1	-	1.7	-	-	-	3.3
84	-	2.0	-	11.6	-	-	-	23.4
85	-	31.1	-	33.4	-	-	-	42.1
86	-	56.3	-	46.8	-	-	-	28.1
87	-	10.2	-	6.0	-	-	-	2.9
88 & Above	-	0.3	-	0.6	-	-	-	0.2
<b>Average</b>	-	<b>86.22</b>	-	<b>85.90</b>	-	-	-	<b>85.49</b>
<b>Samples Classed</b>	-	<b>27,733</b>	-	<b>308,854</b>	-	-	-	<b>34,745</b>

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

\* Less than 0.05 percent.