



| State | Week | | | | Season | | | |
|-------------------------------------|----------|----------------|--------------|------------|------------|----------------|--------------|-------------------|
| | Gins | Tenderable (%) | Eligible (%) | Bales | Gins | Tenderable (%) | Eligible (%) | Bales |
| <i>UPLAND</i> | | | | | | | | |
| AL | - | - | - | - | 21 | 89.9 | 77.8 | 549,869 |
| AR | - | - | - | - | 26 | 70.4 | 42.7 | 1,421,220 |
| AZ | - | - | - | - | 10 | 86.3 | 70.2 | 232,176 |
| CA | - | - | - | - | 10 | 85.6 | 74.5 | 94,092 |
| FL | - | - | - | - | 4 | 91.0 | 76.3 | 90,071 |
| GA | - | - | - | - | 53 | 88.4 | 74.2 | 1,738,863 |
| KS | - | - | - | - | 3 | 32.5 | 24.7 | 160,354 |
| LA | - | - | - | - | 14 | 71.5 | 47.6 | 223,299 |
| MO | - | - | - | - | 16 | 86.7 | 65.2 | 680,258 |
| MS | - | - | - | - | 30 | 63.7 | 36.5 | 706,521 |
| NC | - | - | - | - | 26 | 90.7 | 78.7 | 653,677 |
| NM | - | - | - | - | 2 | 81.6 | 67.3 | 12,080 |
| OK* | - | - | - | - | 10 | 91.1 | 78.6 | 539,396 |
| SC | - | - | - | - | 10 | 86.4 | 73.5 | 283,935 |
| TN | - | - | - | - | 17 | 82.3 | 63.4 | 340,307 |
| TX | 2 | 47.2 | 40.7 | 725 | 146 | 82.2 | 62.1 | 5,237,109 |
| VA | - | - | - | - | 4 | 96.1 | 90.4 | 172,921 |
| United States | 3 | 47.7 | 40.8 | 732 | 402 | 81.7 | 62.8 | 13,136,148 |
| <i>AMERICAN PIMA</i> | | | | | | | | |
| AZ | - | - | - | - | 3 | - | - | 27,733 |
| CA | - | - | - | - | 10 | - | - | 308,854 |
| NM | - | - | - | - | - | - | - | - |
| TX | - | - | - | - | 5 | - | - | 34,750 |
| United States | - | - | - | - | 19 | - | - | 390,584 |
| United States all cotton | 3 | - | - | 732 | 411 | - | - | 13,526,732 |

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed

Source: USDA AMS Cotton and Tobacco Market News

Memphis, Tennessee | 901-384-3016 | cottonmn@ams.usda.gov

<https://www.ams.usda.gov/market-news/cotton>

<https://mymarketnews.ams.usda.gov/cottonmn@ams.usda.gov>

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE
For The Week Ending May 21, 2026

| Quality Designation | Leaf | ALABAMA | | ARKANSAS | | ARIZONA | | CALIFORNIA | | FLORIDA | | GEORGIA | |
|---------------------|------|---------|-------------|----------|-------------|---------|-------------|------------|-------------|---------|-------------|---------|-------------|
| | | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season |
| Color | | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. |
| 11 & 21 | 1-2 | - | 2.2 | - | 0.1 | - | 16.3 | - | 18.0 | - | 1.7 | - | 1.5 |
| | 3 | - | 1.3 | - | 0.1 | - | 3.1 | - | 6.5 | - | 0.5 | - | 1.2 |
| | 4 | - | * | - | * | - | 0.2 | - | 0.4 | - | * | - | * |
| | 5 | - | * | - | - | - | * | - | * | - | - | - | * |
| | 6 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | - | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | 3.5 | - | 0.2 | - | 19.6 | - | 24.9 | - | 2.2 | - | 2.7 |
| 31 | 1-2 | - | 9.3 | - | 1.1 | - | 9.7 | - | 13.8 | - | 3.1 | - | 7.8 |
| | 3 | - | 27.7 | - | 9.0 | - | 11.8 | - | 10.9 | - | 12.5 | - | 21.9 |
| | 4 | - | 7.1 | - | 3.4 | - | 2.3 | - | 3.4 | - | 2.8 | - | 4.2 |
| | 5 | - | 0.5 | - | 0.1 | - | 0.2 | - | 0.6 | - | 0.1 | - | 0.2 |
| | 6 | - | * | - | * | - | * | - | 0.1 | - | - | - | * |
| | 7 | - | * | - | - | - | - | - | - | - | - | - | * |
| | 8 | - | - | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | 44.7 | - | 13.7 | - | 24.0 | - | 28.8 | - | 18.4 | - | 34.1 |
| 41 | 1-2 | - | 3.3 | - | 0.8 | - | 2.9 | - | 6.8 | - | 2.8 | - | 5.3 |
| | 3 | - | 22.6 | - | 26.2 | - | 17.0 | - | 22.3 | - | 37.0 | - | 32.4 |
| | 4 | - | 15.6 | - | 35.2 | - | 14.2 | - | 7.3 | - | 28.9 | - | 16.3 |
| | 5 | - | 2.8 | - | 8.4 | - | 4.4 | - | 1.7 | - | 4.0 | - | 2.0 |
| | 6 | - | 0.2 | - | 0.7 | - | 0.7 | - | 0.3 | - | 0.2 | - | 0.1 |
| | 7 | - | * | - | * | - | 0.1 | - | * | - | * | - | * |
| | 8 | - | - | - | - | - | * | - | - | - | - | - | - |
| Total | ---- | - | 44.5 | - | 71.3 | - | 39.4 | - | 38.4 | - | 72.9 | - | 56.2 |
| 51 | 1-2 | - | 0.4 | - | * | - | 0.1 | - | 0.1 | - | 0.1 | - | 0.2 |
| | 3 | - | 2.4 | - | 2.4 | - | 1.9 | - | 0.6 | - | 1.7 | - | 2.2 |
| | 4 | - | 1.8 | - | 4.9 | - | 3.6 | - | 0.9 | - | 2.3 | - | 2.2 |
| | 5 | - | 0.4 | - | 2.3 | - | 2.4 | - | 0.5 | - | 0.6 | - | 0.5 |
| | 6 | - | * | - | 0.4 | - | 1.0 | - | 0.3 | - | 0.1 | - | 0.1 |
| | 7 | - | * | - | 0.1 | - | 0.3 | - | 0.1 | - | * | - | * |
| | 8 | - | * | - | - | - | 0.1 | - | * | - | - | - | * |
| Total | ---- | - | 4.9 | - | 10.0 | - | 9.4 | - | 2.5 | - | 4.8 | - | 5.1 |
| 61 | 1-2 | - | * | - | * | - | * | - | - | - | - | - | * |
| | 3 | - | 0.1 | - | * | - | * | - | * | - | * | - | * |
| | 4 | - | 0.1 | - | * | - | * | - | * | - | * | - | * |
| | 5 | - | * | - | * | - | * | - | - | - | * | - | * |
| | 6 | - | * | - | * | - | * | - | * | - | * | - | * |
| | 7 | - | - | - | - | - | * | - | * | - | - | - | * |
| | 8 | - | - | - | - | - | * | - | * | - | - | - | * |
| Total | ---- | - | 0.2 | - | * | - | * | - | * | - | * | - | * |
| 71 | 1-2 | - | - | - | * | - | - | - | - | - | - | - | - |
| | 3 | - | - | - | * | - | - | - | - | - | - | - | - |
| | 4 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 5 | - | - | - | * | - | - | - | - | - | - | - | - |
| | 6 | - | - | - | * | - | - | - | - | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | - | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | - | - | * | - | - | - | - | - | - | - | - |
| 12 & 22 | 1-2 | - | 0.1 | - | * | - | 2.6 | - | 0.1 | - | * | - | * |
| | 3 | - | * | - | * | - | 1.2 | - | 0.2 | - | * | - | 0.1 |
| | 4 | - | * | - | * | - | 0.2 | - | * | - | - | - | * |
| | 5 | - | - | - | * | - | * | - | - | - | - | - | - |
| | 6 | - | - | - | * | - | - | - | - | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | - | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | 0.1 | - | * | - | 4.0 | - | 0.4 | - | * | - | 0.1 |
| 32 | 1-2 | - | 0.1 | - | * | - | 0.1 | - | 0.3 | - | * | - | * |
| | 3 | - | 0.4 | - | 0.1 | - | 0.4 | - | 0.6 | - | 0.2 | - | 0.2 |
| | 4 | - | 0.1 | - | 0.1 | - | 0.3 | - | 0.5 | - | * | - | 0.1 |
| | 5 | - | * | - | * | - | 0.1 | - | 0.3 | - | - | - | * |
| | 6 | - | * | - | * | - | * | - | * | - | - | - | * |
| | 7 | - | - | - | - | - | * | - | - | - | - | - | - |
| | 8 | - | - | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | 0.6 | - | 0.2 | - | 0.9 | - | 1.9 | - | 0.3 | - | 0.4 |
| 42 | 1-2 | - | * | - | * | - | * | - | 0.1 | - | 0.1 | - | * |
| | 3 | - | 0.4 | - | 1.0 | - | 0.4 | - | 0.9 | - | 0.7 | - | 0.6 |
| | 4 | - | 0.5 | - | 1.5 | - | 0.6 | - | 0.5 | - | 0.4 | - | 0.4 |
| | 5 | - | 0.1 | - | 0.7 | - | 0.3 | - | 0.3 | - | * | - | 0.1 |
| | 6 | - | * | - | 0.1 | - | 0.1 | - | 0.1 | - | * | - | * |
| | 7 | - | * | - | * | - | * | - | - | - | * | - | * |
| | 8 | - | - | - | - | - | * | - | - | - | - | - | - |
| Total | ---- | - | 1.1 | - | 3.2 | - | 1.4 | - | 1.9 | - | 1.2 | - | 1.1 |

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE
For The Week Ending May 21, 2026

| Quality Designation | Leaf | ALABAMA | | ARKANSAS | | ARIZONA | | CALIFORNIA | | FLORIDA | | GEORGIA | |
|-----------------------|--------------|---------|--------------|------------|--------------|------------|--------------|------------|--------------|------------|--------------|------------|--------------|
| | | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season |
| Color 52 | 1-2 | - | * | - | * | - | * | - | * | - | * | - | * |
| | 3 | - | 0.1 | - | 0.2 | - | 0.1 | - | 0.1 | - | 0.1 | - | * |
| | 4 | - | 0.1 | - | 0.6 | - | 0.3 | - | 0.2 | - | 0.1 | - | 0.1 |
| | 5 | - | 0.1 | - | 0.3 | - | 0.3 | - | 0.2 | - | * | - | * |
| | 6 | - | * | - | 0.1 | - | 0.2 | - | 0.2 | - | * | - | * |
| | 7 | - | * | - | * | - | * | - | 0.1 | - | * | - | * |
| | 8 | - | - | - | - | - | * | - | * | - | - | - | * |
| | Total | ---- | - | 0.3 | - | 1.3 | - | 0.9 | - | 0.8 | - | 0.2 | - |
| 62 | 1-2 | - | * | - | - | - | - | - | - | - | - | - | - |
| | 3 | - | * | - | * | - | - | - | * | - | * | - | * |
| | 4 | - | * | - | * | - | * | - | * | - | * | - | * |
| | 5 | - | * | - | * | - | * | - | * | - | * | - | * |
| | 6 | - | * | - | * | - | * | - | * | - | - | - | * |
| | 7 | - | - | - | * | - | * | - | * | - | - | - | * |
| | 8 | - | - | - | - | - | * | - | * | - | - | - | * |
| | Total | ---- | - | * | - | * | - | * | - | * | - | * | - |
| 13 & 23 | 1-2 | - | * | - | - | - | 0.1 | - | * | - | - | - | * |
| | 3 | - | * | - | - | - | * | - | * | - | - | - | * |
| | 4 | - | * | - | - | - | * | - | - | - | - | - | * |
| | 5 | - | - | - | - | - | - | - | - | - | - | - | * |
| | 6 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | - | - | - | - | - | - | - | - | - | - | - |
| | Total | ---- | - | * | - | - | - | 0.2 | - | * | - | - | - |
| 33 | 1-2 | - | * | - | - | - | * | - | * | - | - | - | * |
| | 3 | - | * | - | * | - | * | - | * | - | - | - | * |
| | 4 | - | * | - | * | - | * | - | * | - | - | - | * |
| | 5 | - | * | - | * | - | * | - | * | - | - | - | * |
| | 6 | - | * | - | - | - | * | - | - | - | - | - | * |
| | 7 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | - | - | - | - | - | - | - | - | - | - | - |
| | Total | ---- | - | * | - | * | - | * | - | * | - | - | - |
| 43 | 1-2 | - | - | - | * | - | - | - | * | - | - | - | * |
| | 3 | - | * | - | * | - | * | - | 0.1 | - | * | - | * |
| | 4 | - | * | - | * | - | * | - | 0.1 | - | * | - | * |
| | 5 | - | * | - | * | - | * | - | * | - | - | - | * |
| | 6 | - | * | - | * | - | * | - | * | - | - | - | * |
| | 7 | - | * | - | - | - | - | - | - | - | - | - | * |
| | 8 | - | - | - | - | - | - | - | - | - | - | - | - |
| | Total | ---- | - | * | - | 0.1 | - | 0.1 | - | 0.2 | - | * | - |
| 53 | 1-2 | - | * | - | - | - | * | - | - | - | - | - | - |
| | 3 | - | * | - | * | - | * | - | * | - | * | - | * |
| | 4 | - | * | - | * | - | * | - | * | - | * | - | * |
| | 5 | - | * | - | * | - | * | - | * | - | * | - | * |
| | 6 | - | * | - | * | - | * | - | * | - | - | - | * |
| | 7 | - | - | - | * | - | * | - | - | - | - | - | * |
| | 8 | - | - | - | - | - | * | - | - | - | - | - | - |
| | Total | ---- | - | 0.1 | - | * | - | * | - | * | - | * | - |
| 63 | 1-2 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 3 | - | * | - | - | - | - | - | - | - | - | - | - |
| | 4 | - | * | - | - | - | - | - | - | - | - | - | - |
| | 5 | - | * | - | - | - | - | - | - | - | - | - | - |
| | 6 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | - | - | - | - | - | - | - | - | - | - | - |
| | Total | ---- | - | * | - | - | - | - | - | - | - | - | - |
| 24 - 54 | 1-8 | - | * | - | * | - | * | - | * | - | - | - | * |
| 25 - 35 | 1-8 | - | - | - | - | - | - | - | - | - | - | - | |
| 81 - 85 | 1-8 | - | * | - | - | - | - | - | - | - | - | - | |
| STAPLE | | | | | | | | | | | | | |
| 28 & Shorter | | - | - | - | - | - | - | - | - | - | - | - | |
| 29 | | - | - | - | - | - | - | - | - | - | - | - | |
| 30 | | - | - | - | - | - | - | - | - | - | - | * | |
| 31 | | - | * | - | * | - | * | - | - | - | * | * | |
| 32 | | - | * | - | * | - | * | - | - | - | * | 0.1 | |
| 33 | | - | 0.7 | - | 0.1 | - | * | - | 0.1 | - | 0.2 | - | 0.9 |
| 34 | | - | 3.6 | - | 0.3 | - | 0.7 | - | 0.5 | - | 2.4 | - | 4.9 |
| 35 | | - | 12.3 | - | 2.6 | - | 3.5 | - | 4.2 | - | 12.4 | - | 16.0 |
| 36 | | - | 24.6 | - | 13.8 | - | 13.5 | - | 21.4 | - | 29.2 | - | 31.0 |
| 37 | | - | 40.9 | - | 50.3 | - | 44.9 | - | 44.9 | - | 35.5 | - | 34.5 |
| 38 | | - | 14.3 | - | 27.0 | - | 27.0 | - | 19.0 | - | 15.3 | - | 9.7 |
| 39 | | - | 3.1 | - | 5.4 | - | 8.5 | - | 8.8 | - | 4.4 | - | 2.5 |
| 40 & Longer | | - | 0.5 | - | 0.6 | - | 1.9 | - | 1.1 | - | 0.6 | - | 0.4 |
| Average Staple | | - | 36.59 | - | 37.19 | - | 37.28 | - | 37.09 | - | 36.64 | - | 36.34 |
| Average Length | | - | 1.14 | - | 1.16 | - | 1.16 | - | 1.16 | - | 1.14 | - | 1.13 |

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE
For The Week Ending May 21, 2026

| Quality Designation | Leaf | KANSAS | | LOUISIANA | | MISSOURI | | MISSISSIPPI | | NORTH CAROLINA | | NEW MEXICO | |
|---------------------|-------------|----------|-------------|-----------|-------------|----------|-------------|-------------|-------------|----------------|-------------|------------|-------------|
| | | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season |
| Color | | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. |
| 11 & 21 | 1-2 | - | 4.1 | - | 4.5 | - | * | - | 2.0 | - | 0.4 | - | 40.4 |
| | 3 | - | 5.3 | - | 2.6 | - | * | - | 1.8 | - | 0.3 | - | 10.9 |
| | 4 | - | 1.1 | - | * | - | * | - | * | - | * | - | 0.8 |
| | 5 | - | 0.1 | - | - | - | - | - | * | - | * | - | * |
| | 6 | - | * | - | - | - | - | - | - | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | - | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | 10.7 | - | 7.1 | - | * | - | 3.8 | - | 0.8 | - | 52.2 |
| 31 | 1-2 | - | 0.9 | - | 9.2 | - | 1.5 | - | 3.4 | - | 5.7 | - | 7.6 |
| | 3 | - | 7.6 | - | 36.6 | - | 9.0 | - | 20.3 | - | 20.2 | - | 15.3 |
| | 4 | - | 9.3 | - | 12.3 | - | 1.8 | - | 8.6 | - | 5.8 | - | 7.3 |
| | 5 | - | 2.6 | - | 0.8 | - | * | - | 0.6 | - | 0.3 | - | 1.1 |
| | 6 | - | 0.3 | - | * | - | * | - | * | - | * | - | 0.1 |
| | 7 | - | * | - | - | - | - | - | - | - | - | - | * |
| | 8 | - | * | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | 20.7 | - | 58.9 | - | 12.3 | - | 32.9 | - | 32.0 | - | 31.4 |
| 41 | 1-2 | - | * | - | 0.5 | - | 2.4 | - | 0.9 | - | 3.1 | - | * |
| | 3 | - | 1.6 | - | 10.1 | - | 38.1 | - | 18.8 | - | 30.0 | - | 0.6 |
| | 4 | - | 6.7 | - | 16.2 | - | 26.6 | - | 26.1 | - | 24.6 | - | 1.2 |
| | 5 | - | 9.2 | - | 4.9 | - | 3.2 | - | 7.3 | - | 4.5 | - | 1.3 |
| | 6 | - | 4.5 | - | 0.3 | - | 0.1 | - | 0.6 | - | 0.4 | - | 0.6 |
| | 7 | - | 0.9 | - | - | - | * | - | * | - | * | - | 0.1 |
| | 8 | - | * | - | - | - | - | - | - | - | * | - | - |
| Total | ---- | - | 23.0 | - | 32.0 | - | 70.4 | - | 53.6 | - | 62.5 | - | 3.8 |
| 51 | 1-2 | - | - | - | * | - | 0.2 | - | * | - | * | - | - |
| | 3 | - | - | - | * | - | 4.5 | - | 1.1 | - | 0.8 | - | - |
| | 4 | - | * | - | 0.4 | - | 6.0 | - | 3.3 | - | 1.7 | - | * |
| | 5 | - | 0.4 | - | 0.3 | - | 1.4 | - | 1.5 | - | 0.8 | - | * |
| | 6 | - | 1.1 | - | 0.1 | - | 0.1 | - | 0.2 | - | 0.2 | - | * |
| | 7 | - | 0.8 | - | - | - | * | - | * | - | * | - | - |
| | 8 | - | 0.2 | - | - | - | - | - | - | - | * | - | - |
| Total | ---- | - | 2.6 | - | 0.7 | - | 12.1 | - | 6.1 | - | 3.6 | - | * |
| 61 | 1-2 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 3 | - | - | - | * | - | * | - | * | - | * | - | - |
| | 4 | - | - | - | * | - | * | - | * | - | * | - | - |
| | 5 | - | - | - | - | - | * | - | * | - | * | - | - |
| | 6 | - | - | - | - | - | * | - | * | - | * | - | - |
| | 7 | - | - | - | - | - | * | - | - | - | - | - | - |
| | 8 | - | * | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | * | - | * | - | * | - | * | - | * | - | - |
| 71 | 1-2 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 3 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 4 | - | - | - | - | - | * | - | - | - | - | - | - |
| | 5 | - | - | - | - | - | * | - | - | - | * | - | - |
| | 6 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | - | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | - | - | - | - | * | - | - | - | * | - | - |
| 12 & 22 | 1-2 | - | 1.2 | - | 0.1 | - | - | - | * | - | * | - | 2.4 |
| | 3 | - | 3.9 | - | * | - | * | - | * | - | * | - | 3.0 |
| | 4 | - | 2.0 | - | * | - | - | - | * | - | * | - | 0.3 |
| | 5 | - | 0.2 | - | * | - | - | - | - | - | - | - | - |
| | 6 | - | * | - | - | - | - | - | - | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | - | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | 7.3 | - | 0.1 | - | * | - | * | - | * | - | 5.7 |
| 32 | 1-2 | - | 0.1 | - | 0.1 | - | * | - | * | - | * | - | 0.6 |
| | 3 | - | 3.1 | - | 0.3 | - | 0.1 | - | 0.2 | - | 0.1 | - | 1.6 |
| | 4 | - | 5.4 | - | 0.2 | - | * | - | 0.1 | - | 0.1 | - | 2.7 |
| | 5 | - | 2.9 | - | * | - | * | - | * | - | * | - | 0.8 |
| | 6 | - | 0.6 | - | * | - | - | - | * | - | - | - | 0.1 |
| | 7 | - | 0.1 | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | * | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | 12.2 | - | 0.5 | - | 0.1 | - | 0.3 | - | 0.3 | - | 5.8 |
| 42 | 1-2 | - | * | - | * | - | 0.1 | - | * | - | * | - | - |
| | 3 | - | 0.7 | - | 0.1 | - | 1.3 | - | 0.6 | - | 0.3 | - | * |
| | 4 | - | 3.4 | - | 0.4 | - | 1.4 | - | 1.2 | - | 0.3 | - | 0.1 |
| | 5 | - | 5.5 | - | 0.1 | - | 0.4 | - | 0.5 | - | 0.1 | - | 0.1 |
| | 6 | - | 4.0 | - | * | - | 0.1 | - | 0.1 | - | * | - | 0.1 |
| | 7 | - | 1.4 | - | - | - | * | - | * | - | * | - | * |
| | 8 | - | 0.2 | - | - | - | - | - | - | - | * | - | - |
| Total | ---- | - | 15.3 | - | 0.6 | - | 3.3 | - | 2.4 | - | 0.7 | - | 0.3 |

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE
For The Week Ending May 21, 2026

| Quality Designation | Leaf | KANSAS | | LOUISIANA | | MISSOURI | | MISSISSIPPI | | NORTH CAROLINA | | NEW MEXICO | |
|-----------------------|------|--------|--------------|-----------|--------------|----------|--------------|-------------|--------------|----------------|--------------|------------|--------------|
| | | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season |
| Color | | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. |
| 52 | 1-2 | - | - | - | - | - | * | - | * | - | * | - | - |
| | 3 | - | - | - | * | - | 0.5 | - | 0.1 | - | * | - | - |
| | 4 | - | * | - | * | - | 0.7 | - | 0.2 | - | * | - | - |
| | 5 | - | 0.1 | - | * | - | 0.3 | - | 0.3 | - | * | - | - |
| | 6 | - | 0.3 | - | * | - | * | - | 0.1 | - | * | - | - |
| | 7 | - | 0.5 | - | - | - | * | - | * | - | * | - | - |
| | 8 | - | 0.3 | - | - | - | - | - | - | - | * | - | - |
| Total | ---- | - | 1.2 | - | * | - | 1.6 | - | 0.7 | - | 0.1 | - | - |
| 62 | 1-2 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 3 | - | - | - | - | - | * | - | * | - | - | - | - |
| | 4 | - | - | - | - | - | * | - | * | - | * | - | - |
| | 5 | - | - | - | - | - | * | - | * | - | * | - | - |
| | 6 | - | - | - | - | - | * | - | * | - | - | - | - |
| | 7 | - | - | - | - | - | * | - | - | - | - | - | - |
| | 8 | - | * | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | * | - | - | - | * | - | * | - | * | - | - |
| 13 & 23 | 1-2 | - | 0.1 | - | - | - | - | - | - | - | * | - | - |
| | 3 | - | 0.9 | - | - | - | - | - | - | - | * | - | * |
| | 4 | - | 0.6 | - | - | - | - | - | - | - | * | - | * |
| | 5 | - | 0.1 | - | - | - | - | - | - | - | - | - | - |
| | 6 | - | * | - | - | - | - | - | - | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | - | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | 1.7 | - | - | - | - | - | - | - | * | - | * |
| 33 | 1-2 | - | * | - | - | - | * | - | * | - | * | - | * |
| | 3 | - | 0.4 | - | * | - | * | - | * | - | * | - | 0.1 |
| | 4 | - | 1.0 | - | * | - | * | - | * | - | * | - | 0.3 |
| | 5 | - | 0.6 | - | * | - | - | - | - | - | * | - | 0.2 |
| | 6 | - | 0.1 | - | - | - | - | - | - | - | * | - | * |
| | 7 | - | * | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | * | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | 2.1 | - | * | - | * | - | * | - | * | - | 0.7 |
| 43 | 1-2 | - | - | - | * | - | * | - | - | - | * | - | - |
| | 3 | - | 0.1 | - | * | - | * | - | * | - | * | - | * |
| | 4 | - | 0.5 | - | * | - | * | - | * | - | * | - | * |
| | 5 | - | 1.2 | - | * | - | * | - | * | - | * | - | * |
| | 6 | - | 0.9 | - | - | - | * | - | * | - | * | - | * |
| | 7 | - | 0.4 | - | - | - | - | - | - | - | * | - | - |
| | 8 | - | 0.1 | - | - | - | - | - | - | - | * | - | - |
| Total | ---- | - | 3.1 | - | * | - | 0.1 | - | * | - | * | - | 0.1 |
| 53 | 1-2 | - | - | - | - | - | * | - | * | - | - | - | - |
| | 3 | - | * | - | - | - | * | - | * | - | * | - | - |
| | 4 | - | * | - | - | - | * | - | * | - | * | - | - |
| | 5 | - | * | - | - | - | * | - | * | - | * | - | - |
| | 6 | - | * | - | - | - | * | - | * | - | * | - | - |
| | 7 | - | 0.1 | - | - | - | - | - | * | - | * | - | - |
| | 8 | - | 0.1 | - | - | - | - | - | - | - | * | - | - |
| Total | ---- | - | 0.2 | - | - | - | * | - | * | - | * | - | - |
| 63 | 1-2 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 3 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 4 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 5 | - | - | - | - | - | - | - | * | - | - | - | - |
| | 6 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | * | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | * | - | - | - | - | - | * | - | - | - | - |
| 24 - 54 | 1-8 | - | 0.1 | - | - | - | * | - | - | - | * | - | - |
| 25 - 35 | 1-8 | - | - | - | - | - | - | - | - | - | - | - | - |
| 81 - 85 | 1-8 | - | * | - | - | - | * | - | - | - | - | - | - |
| STAPLE | | | | | | | | | | | | | |
| 28 & Shorter | | - | - | - | - | - | - | - | - | - | - | - | - |
| 29 | | - | - | - | - | - | - | - | - | - | - | - | - |
| 30 | | - | - | - | - | - | - | - | - | - | - | - | - |
| 31 | | - | * | - | - | - | - | - | * | - | * | - | - |
| 32 | | - | * | - | - | - | * | - | * | - | * | - | - |
| 33 | | - | 0.2 | - | 0.1 | - | * | - | 0.2 | - | 0.1 | - | * |
| 34 | | - | 1.2 | - | 1.1 | - | 0.2 | - | 2.1 | - | 1.4 | - | 2.3 |
| 35 | | - | 5.1 | - | 10.0 | - | 1.8 | - | 11.5 | - | 8.3 | - | 10.7 |
| 36 | | - | 13.7 | - | 26.9 | - | 10.4 | - | 27.7 | - | 24.4 | - | 14.0 |
| 37 | | - | 33.8 | - | 42.1 | - | 49.0 | - | 36.4 | - | 48.7 | - | 29.6 |
| 38 | | - | 30.6 | - | 15.0 | - | 33.2 | - | 15.0 | - | 14.1 | - | 36.7 |
| 39 | | - | 13.7 | - | 4.4 | - | 4.9 | - | 5.4 | - | 2.7 | - | 5.8 |
| 40 & Longer | | - | 1.8 | - | 0.4 | - | 0.3 | - | 1.5 | - | 0.3 | - | 0.8 |
| Average Staple | | - | 37.35 | - | 36.75 | - | 37.29 | - | 36.72 | - | 36.74 | - | 37.09 |
| Average Length | | - | 1.17 | - | 1.15 | - | 1.17 | - | 1.15 | - | 1.15 | - | 1.16 |

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE
For The Week Ending May 21, 2026

| Quality Designation | Leaf | OKLAHOMA | | SOUTH CAROLINA | | TENNESSEE | | TEXAS | | VIRGINIA | |
|---------------------|------|----------|-------------|----------------|-------------|-----------|-------------|-------------|-------------|----------|-------------|
| | | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season |
| Color | | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. |
| 11 & 21 | 1-2 | - | 41.1 | - | 0.3 | - | 0.4 | 10.9 | 44.1 | - | 0.9 |
| | 3 | - | 9.4 | - | 0.4 | - | 0.1 | 8.0 | 12.9 | - | 1.3 |
| | 4 | - | 0.4 | - | * | - | * | 0.1 | 0.9 | - | 0.1 |
| | 5 | - | * | - | - | - | * | - | * | - | - |
| | 6 | - | - | - | - | - | - | - | * | - | - |
| | 7 | - | - | - | - | - | - | - | * | - | - |
| | 8 | - | - | - | - | - | - | - | * | - | - |
| Total | ---- | - | 50.9 | - | 0.8 | - | 0.5 | 19.0 | 57.8 | - | 2.2 |
| 31 | 1-2 | - | 13.6 | - | 2.3 | - | 6.9 | 12.7 | 4.5 | - | 8.7 |
| | 3 | - | 19.3 | - | 15.3 | - | 14.5 | 32.7 | 10.3 | - | 38.2 |
| | 4 | - | 4.4 | - | 5.7 | - | 3.2 | 5.0 | 4.0 | - | 8.3 |
| | 5 | - | 0.3 | - | 0.3 | - | 0.2 | 1.1 | 0.5 | - | 0.5 |
| | 6 | - | * | - | * | - | * | - | * | - | * |
| | 7 | - | * | - | - | - | - | - | * | - | - |
| | 8 | - | - | - | - | - | - | - | * | - | - |
| Total | ---- | - | 37.5 | - | 23.6 | - | 24.8 | 51.4 | 19.2 | - | 55.6 |
| 41 | 1-2 | - | 0.5 | - | 1.9 | - | 7.7 | - | 0.3 | - | 1.7 |
| | 3 | - | 1.9 | - | 31.3 | - | 35.8 | 3.3 | 1.8 | - | 21.6 |
| | 4 | - | 1.5 | - | 31.4 | - | 14.2 | 5.0 | 1.7 | - | 15.7 |
| | 5 | - | 0.4 | - | 5.1 | - | 1.8 | 0.1 | 0.5 | - | 2.6 |
| | 6 | - | 0.1 | - | 0.2 | - | 0.1 | - | 0.1 | - | 0.1 |
| | 7 | - | * | - | * | - | * | - | * | - | * |
| | 8 | - | - | - | - | - | - | - | * | - | - |
| Total | ---- | - | 4.4 | - | 69.9 | - | 59.6 | 8.4 | 4.4 | - | 41.8 |
| 51 | 1-2 | - | * | - | 0.1 | - | 0.2 | - | * | - | * |
| | 3 | - | * | - | 1.7 | - | 2.4 | - | * | - | * |
| | 4 | - | * | - | 2.3 | - | 2.2 | - | 0.1 | - | 0.1 |
| | 5 | - | * | - | 0.6 | - | 0.5 | - | * | - | * |
| | 6 | - | * | - | 0.1 | - | * | - | * | - | * |
| | 7 | - | * | - | * | - | * | - | * | - | * |
| | 8 | - | * | - | - | - | - | - | * | - | - |
| Total | ---- | - | 0.1 | - | 4.9 | - | 5.3 | - | 0.2 | - | 0.2 |
| 61 | 1-2 | - | - | - | - | - | - | - | * | - | - |
| | 3 | - | - | - | * | - | * | - | * | - | - |
| | 4 | - | - | - | * | - | * | - | * | - | - |
| | 5 | - | - | - | - | - | * | - | - | - | - |
| | 6 | - | - | - | - | - | * | - | * | - | - |
| | 7 | - | - | - | - | - | - | - | * | - | - |
| | 8 | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | - | - | * | - | * | - | * | - | - |
| 71 | 1-2 | - | - | - | - | - | - | - | * | - | - |
| | 3 | - | - | - | - | - | - | - | * | - | - |
| | 4 | - | - | - | - | - | - | - | - | - | - |
| | 5 | - | - | - | - | - | - | - | - | - | - |
| | 6 | - | - | - | - | - | - | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | - | - | - | - | - | - | - | - | - |
| Total | ---- | - | - | - | - | - | - | - | * | - | - |
| 12 & 22 | 1-2 | - | 2.1 | - | - | - | * | 0.7 | 6.8 | - | - |
| | 3 | - | 0.9 | - | * | - | * | 0.8 | 3.6 | - | * |
| | 4 | - | 0.1 | - | - | - | * | - | 0.6 | - | * |
| | 5 | - | * | - | - | - | - | - | * | - | - |
| | 6 | - | - | - | - | - | - | - | * | - | - |
| | 7 | - | - | - | - | - | - | - | * | - | - |
| | 8 | - | - | - | - | - | - | - | * | - | - |
| Total | ---- | - | 3.1 | - | * | - | * | 1.5 | 11.0 | - | * |
| 32 | 1-2 | - | 0.4 | - | * | - | 0.2 | 1.9 | 0.8 | - | * |
| | 3 | - | 1.2 | - | 0.1 | - | 0.5 | 5.8 | 1.7 | - | * |
| | 4 | - | 0.5 | - | 0.1 | - | 0.1 | 0.3 | 1.2 | - | * |
| | 5 | - | 0.1 | - | * | - | * | 0.1 | 0.3 | - | * |
| | 6 | - | * | - | * | - | - | - | * | - | - |
| | 7 | - | - | - | - | - | - | - | * | - | - |
| | 8 | - | * | - | - | - | - | - | * | - | - |
| Total | ---- | - | 2.2 | - | 0.1 | - | 0.8 | 8.1 | 4.1 | - | 0.1 |
| 42 | 1-2 | - | * | - | * | - | 0.9 | 0.1 | * | - | * |
| | 3 | - | 0.1 | - | 0.2 | - | 5.0 | 1.7 | 0.3 | - | * |
| | 4 | - | 0.2 | - | 0.4 | - | 1.5 | 1.4 | 0.5 | - | * |
| | 5 | - | 0.1 | - | 0.1 | - | 0.1 | 0.1 | 0.3 | - | * |
| | 6 | - | * | - | * | - | * | - | 0.1 | - | * |
| | 7 | - | * | - | - | - | - | - | * | - | - |
| | 8 | - | * | - | - | - | - | - | * | - | - |
| Total | ---- | - | 0.5 | - | 0.7 | - | 7.5 | 3.3 | 1.2 | - | 0.1 |

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE
For The Week Ending May 21, 2026

| Quality Designation | Leaf | OKLAHOMA | | SOUTH CAROLINA | | TENNESSEE | | TEXAS | | VIRGINIA | |
|-----------------------|-------------|----------|--------------|----------------|--------------|-----------|--------------|--------------|--------------|----------|--------------|
| | | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season |
| Color | | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. | Pct. |
| 52 | 1-2 | - | - | - | * | - | * | - | * | - | - |
| | 3 | - | * | - | * | - | 0.7 | - | * | - | - |
| | 4 | - | * | - | 0.1 | - | 0.5 | 0.1 | * | - | * |
| | 5 | - | * | - | * | - | 0.1 | - | * | - | * |
| | 6 | - | * | - | * | - | * | - | * | - | - |
| | 7 | - | * | - | - | - | - | - | * | - | - |
| | 8 | - | * | - | - | - | - | - | * | - | - |
| Total | ---- | - | * | - | 0.1 | - | 1.3 | 0.1 | 0.1 | - | * |
| 62 | 1-2 | - | - | - | - | - | - | - | * | - | - |
| | 3 | - | - | - | - | - | * | - | * | - | - |
| | 4 | - | - | - | - | - | * | - | * | - | - |
| | 5 | - | - | - | - | - | * | - | * | - | - |
| | 6 | - | - | - | - | - | - | - | * | - | - |
| | 7 | - | - | - | - | - | - | - | * | - | - |
| | 8 | - | * | - | - | - | - | - | * | - | - |
| Total | ---- | - | * | - | - | - | * | - | * | - | - |
| 13 & 23 | 1-2 | - | 0.4 | - | - | - | - | - | 0.6 | - | - |
| | 3 | - | 0.2 | - | - | - | - | - | 0.4 | - | * |
| | 4 | - | * | - | * | - | - | - | 0.1 | - | - |
| | 5 | - | - | - | - | - | - | - | * | - | - |
| | 6 | - | - | - | - | - | - | - | * | - | - |
| | 7 | - | - | - | - | - | - | - | - | - | - |
| | 8 | - | - | - | - | - | - | - | * | - | - |
| Total | ---- | - | 0.6 | - | * | - | - | - | 1.1 | - | * |
| 33 | 1-2 | - | 0.1 | - | - | - | * | 0.3 | 0.1 | - | - |
| | 3 | - | 0.3 | - | * | - | * | 2.1 | 0.3 | - | * |
| | 4 | - | 0.1 | - | * | - | * | 0.7 | 0.2 | - | * |
| | 5 | - | * | - | * | - | - | - | 0.1 | - | * |
| | 6 | - | * | - | - | - | - | - | * | - | - |
| | 7 | - | * | - | - | - | - | - | * | - | - |
| | 8 | - | - | - | - | - | - | - | * | - | - |
| Total | ---- | - | 0.5 | - | * | - | * | 3.0 | 0.7 | - | * |
| 43 | 1-2 | - | * | - | * | - | * | 0.4 | * | - | - |
| | 3 | - | * | - | * | - | * | 2.9 | * | - | * |
| | 4 | - | * | - | * | - | * | 0.8 | * | - | * |
| | 5 | - | * | - | * | - | * | - | * | - | * |
| | 6 | - | * | - | - | - | * | 0.1 | * | - | * |
| | 7 | - | * | - | - | - | - | - | * | - | - |
| | 8 | - | - | - | - | - | - | - | * | - | - |
| Total | ---- | - | 0.1 | - | * | - | * | 4.3 | 0.1 | - | * |
| 53 | 1-2 | - | - | - | - | - | - | - | * | - | - |
| | 3 | - | * | - | * | - | * | 0.1 | * | - | - |
| | 4 | - | * | - | * | - | * | - | * | - | - |
| | 5 | - | * | - | * | - | * | - | * | - | - |
| | 6 | - | * | - | - | - | - | - | * | - | - |
| | 7 | - | * | - | * | - | - | - | * | - | - |
| | 8 | - | * | - | - | - | - | - | * | - | - |
| Total | ---- | - | * | - | * | - | * | 0.1 | * | - | - |
| 63 | 1-2 | - | - | - | - | - | - | - | - | - | - |
| | 3 | - | - | - | - | - | - | - | - | - | - |
| | 4 | - | - | - | - | - | - | - | * | - | - |
| | 5 | - | - | - | - | - | - | - | - | - | - |
| | 6 | - | - | - | - | - | - | - | * | - | - |
| | 7 | - | * | - | - | - | - | - | * | - | - |
| | 8 | - | * | - | - | - | - | - | - | - | - |
| Total | ---- | - | * | - | - | - | - | - | * | - | - |
| 24 - 54 | 1-8 | - | 0.1 | - | * | - | - | 0.6 | 0.1 | - | * |
| 25 - 35 | 1-8 | - | - | - | - | - | - | - | - | - | - |
| 81 - 85 | 1-8 | - | * | - | - | - | - | - | * | - | - |
| STAPLE | | | | | | | | | | | |
| 28 & Shorter | | - | - | - | - | - | - | - | - | - | - |
| 29 | | - | - | - | - | - | - | - | * | - | - |
| 30 | | - | - | - | - | - | - | - | * | - | - |
| 31 | | - | * | - | - | - | - | - | 0.1 | - | - |
| 32 | | - | 0.1 | - | * | - | * | - | 0.6 | - | * |
| 33 | | - | 0.5 | - | 0.2 | - | 0.1 | 0.1 | 2.9 | - | * |
| 34 | | - | 2.4 | - | 2.0 | - | 2.6 | 46.9 | 8.7 | - | 0.6 |
| 35 | | - | 7.3 | - | 10.1 | - | 9.5 | 18.3 | 15.9 | - | 5.4 |
| 36 | | - | 13.1 | - | 33.7 | - | 30.9 | 23.7 | 22.0 | - | 23.0 |
| 37 | | - | 24.4 | - | 40.7 | - | 44.3 | 2.9 | 31.2 | - | 55.4 |
| 38 | | - | 19.6 | - | 10.2 | - | 11.3 | 5.5 | 13.5 | - | 12.8 |
| 39 | | - | 19.1 | - | 2.7 | - | 1.3 | 2.3 | 4.1 | - | 2.6 |
| 40 & Longer | | - | 13.6 | - | 0.4 | - | 0.1 | 0.1 | 1.1 | - | 0.1 |
| Average Staple | | - | 37.64 | - | 36.56 | - | 36.56 | 35.09 | 36.32 | - | 36.82 |
| Average Length | | - | 1.18 | - | 1.14 | - | 1.14 | 1.10 | 1.13 | - | 1.15 |

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending May 21, 2026

| Quality Designation | ALABAMA | | ARKANSAS | | ARIZONA | | CALIFORNIA | | FLORIDA | | GEORGIA | |
|-------------------------|---------|--------------|----------|--------------|---------|--------------|------------|--------------|---------|--------------|---------|--------------|
| | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season |
| Extraneous Matter | - | 0.6 | - | * | - | 0.4 | - | 1.8 | - | 1.5 | - | 1.4 |
| Bark - Level 1 | - | - | - | - | - | - | - | - | - | - | - | - |
| Bark - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| Grass - Level 1 | - | 0.1 | - | * | - | 0.2 | - | 1.1 | - | 0.1 | - | 0.1 |
| Grass - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| Prep - Level 1 | - | * | - | * | - | * | - | * | - | - | - | * |
| Prep - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| Seed Coat - Level 1 | - | 0.1 | - | 1.0 | - | 0.1 | - | - | - | 0.3 | - | 0.3 |
| Seed Coat - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| Oil - Level 1 | - | * | - | - | - | * | - | - | - | - | - | - |
| Oil - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| Spindle Twist - Level 1 | - | - | - | - | - | * | - | * | - | - | - | - |
| Spindle Twist - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| Other - Level 1 | - | - | - | * | - | - | - | - | - | - | - | * |
| Other - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| Plastic - Level 1 | - | * | - | * | - | * | - | * | - | * | - | * |
| Plastic - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| STRENGTH 1/ | | | | | | | | | | | | |
| 22 & Below | - | * | - | - | - | * | - | * | - | - | - | - |
| 23 | - | * | - | * | - | * | - | * | - | - | - | * |
| 24 | - | * | - | * | - | * | - | 0.1 | - | - | - | * |
| 25 | - | * | - | * | - | 0.1 | - | 0.2 | - | * | - | 0.1 |
| 26 | - | 0.2 | - | * | - | 1.0 | - | 0.8 | - | * | - | 0.7 |
| 27 | - | 1.7 | - | 0.2 | - | 2.9 | - | 4.0 | - | 0.4 | - | 3.6 |
| 28 | - | 8.5 | - | 1.9 | - | 8.5 | - | 12.4 | - | 3.3 | - | 11.2 |
| 29 | - | 21.7 | - | 11.4 | - | 15.7 | - | 22.4 | - | 13.1 | - | 21.0 |
| 30 | - | 29.0 | - | 34.3 | - | 22.2 | - | 18.7 | - | 26.8 | - | 24.8 |
| 31 | - | 21.3 | - | 33.2 | - | 20.7 | - | 11.5 | - | 27.4 | - | 19.2 |
| 32 | - | 11.0 | - | 13.5 | - | 13.8 | - | 4.0 | - | 16.9 | - | 11.1 |
| 33 | - | 4.5 | - | 4.1 | - | 7.7 | - | 3.7 | - | 7.3 | - | 5.2 |
| 34 | - | 1.6 | - | 1.1 | - | 4.3 | - | 6.5 | - | 3.8 | - | 2.1 |
| 35 | - | 0.4 | - | 0.2 | - | 1.8 | - | 8.3 | - | 0.9 | - | 0.7 |
| 36 | - | 0.1 | - | 0.1 | - | 0.8 | - | 5.4 | - | 0.1 | - | 0.2 |
| 37 | - | * | - | * | - | 0.3 | - | 1.7 | - | * | - | 0.1 |
| 38 | - | * | - | * | - | * | - | 0.2 | - | - | - | * |
| 39 | - | - | - | * | - | * | - | * | - | - | - | * |
| 40 & Above | - | - | - | * | - | * | - | * | - | - | - | * |
| Average | - | 30.66 | - | 31.08 | - | 31.04 | - | 31.25 | - | 31.27 | - | 30.58 |
| Mike | | | | | | | | | | | | |
| 2.4 & Below | - | - | - | - | - | * | - | * | - | - | - | - |
| 2.5 | - | * | - | - | - | * | - | * | - | - | - | - |
| 2.6 | - | * | - | - | - | 0.1 | - | 0.1 | - | - | - | * |
| 2.7 | - | * | - | - | - | 0.1 | - | 0.1 | - | - | - | * |
| 2.8 | - | * | - | * | - | 0.2 | - | 0.2 | - | - | - | * |
| 2.9 | - | * | - | - | - | 0.1 | - | 0.2 | - | - | - | * |
| 3.0 | - | * | - | * | - | 0.2 | - | 0.2 | - | - | - | * |
| 3.1 | - | * | - | * | - | 0.2 | - | 0.4 | - | * | - | * |
| 3.2 | - | * | - | * | - | 0.4 | - | 0.4 | - | 0.1 | - | 0.1 |
| 3.3 | - | 0.1 | - | * | - | 0.4 | - | 0.6 | - | 0.1 | - | 0.2 |
| 3.4 | - | 0.4 | - | * | - | 0.5 | - | 0.6 | - | 0.1 | - | 0.3 |
| 3.5 | - | 0.8 | - | * | - | 0.7 | - | 1.5 | - | 0.5 | - | 0.6 |
| 3.6 | - | 1.1 | - | 0.1 | - | 1.0 | - | 2.4 | - | 0.7 | - | 1.2 |
| 3.7 | - | 2.0 | - | 0.1 | - | 1.8 | - | 3.4 | - | 1.2 | - | 1.9 |
| 3.8 | - | 3.0 | - | 0.1 | - | 2.5 | - | 5.4 | - | 1.3 | - | 2.9 |
| 3.9 | - | 4.4 | - | 0.3 | - | 3.5 | - | 8.8 | - | 2.1 | - | 4.1 |
| 4.0 | - | 5.9 | - | 0.6 | - | 5.2 | - | 11.0 | - | 3.4 | - | 5.6 |
| 4.1 | - | 8.0 | - | 1.1 | - | 7.3 | - | 11.4 | - | 5.6 | - | 7.4 |
| 4.2 | - | 9.8 | - | 1.8 | - | 9.2 | - | 10.8 | - | 7.1 | - | 9.0 |
| 4.3 | - | 10.8 | - | 3.2 | - | 10.6 | - | 7.7 | - | 9.7 | - | 9.8 |
| 4.4 | - | 10.6 | - | 5.1 | - | 11.2 | - | 5.1 | - | 12.3 | - | 10.0 |
| 4.5 | - | 10.1 | - | 7.9 | - | 10.9 | - | 5.5 | - | 13.0 | - | 9.7 |
| 4.6 | - | 8.9 | - | 11.7 | - | 10.0 | - | 5.4 | - | 11.2 | - | 9.1 |
| 4.7 | - | 7.1 | - | 14.5 | - | 7.7 | - | 5.2 | - | 12.4 | - | 8.2 |
| 4.8 | - | 5.6 | - | 15.4 | - | 5.7 | - | 4.0 | - | 8.4 | - | 6.7 |
| 4.9 | - | 4.3 | - | 13.6 | - | 4.3 | - | 3.2 | - | 5.2 | - | 5.1 |
| 5.0 | - | 2.8 | - | 10.8 | - | 2.8 | - | 2.2 | - | 3.2 | - | 3.6 |
| 5.1 | - | 1.8 | - | 6.9 | - | 1.2 | - | 2.0 | - | 1.7 | - | 2.3 |
| 5.2 | - | 1.1 | - | 4.0 | - | 0.9 | - | 0.9 | - | 0.5 | - | 1.2 |
| 5.3 | - | 0.7 | - | 1.9 | - | 0.6 | - | 0.7 | - | 0.1 | - | 0.6 |
| 5.4 | - | 0.3 | - | 0.6 | - | 0.3 | - | 0.5 | - | 0.1 | - | 0.2 |
| 5.5 & Above | - | 0.2 | - | 0.2 | - | 0.3 | - | 0.2 | - | 0.1 | - | 0.1 |
| Average | - | 4.39 | - | 4.76 | - | 4.38 | - | 4.24 | - | 4.48 | - | 4.41 |

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending May 21, 2026

| Quality Designation | KANSAS | | LOUISIANA | | MISSOURI | | MISSISSIPPI | | NORTH CAROLINA | | NEW MEXICO | |
|---------------------------|--------|--------------|-----------|--------------|----------|--------------|-------------|--------------|----------------|--------------|------------|--------------|
| | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season |
| Extraneous Matter | | | | | | | | | | | | |
| Bark - Level 1 | - | 41.1 | - | 0.1 | - | * | - | * | - | 1.6 | - | 6.5 |
| Bark - Level 2 | - | * | - | - | - | - | - | - | - | - | - | - |
| Grass - Level 1 | - | 0.1 | - | * | - | * | - | * | - | * | - | 0.6 |
| Grass - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| Prep - Level 1 | - | - | - | - | - | * | - | * | - | * | - | - |
| Prep - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| Seed Coat - Level 1 | - | * | - | 0.4 | - | 0.2 | - | 0.3 | - | 0.5 | - | - |
| Seed Coat - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| Oil - Level 1 | - | - | - | - | - | - | - | * | - | * | - | - |
| Oil - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| Spindle Twist - Level 1 | - | - | - | - | - | - | - | - | - | - | - | - |
| Spindle Twist - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| Other - Level 1 | - | - | - | * | - | * | - | * | - | * | - | - |
| Other - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| Plastic - Level 1 | - | * | - | * | - | * | - | * | - | * | - | * |
| Plastic - Level 2 | - | - | - | - | - | - | - | - | - | - | - | - |
| STRENGTH 1/ 22 & Below | - | * | - | - | - | * | - | - | - | - | - | * |
| 23 | - | * | - | - | - | * | - | - | - | - | - | - |
| 24 | - | 0.1 | - | - | - | * | - | * | - | * | - | - |
| 25 | - | 0.2 | - | * | - | * | - | * | - | * | - | * |
| 26 | - | 0.6 | - | * | - | * | - | 0.1 | - | 0.3 | - | 0.2 |
| 27 | - | 1.3 | - | 0.5 | - | 0.1 | - | 1.0 | - | 2.3 | - | 1.5 |
| 28 | - | 2.6 | - | 4.4 | - | 0.7 | - | 4.8 | - | 10.9 | - | 6.0 |
| 29 | - | 4.5 | - | 19.0 | - | 8.1 | - | 15.6 | - | 28.2 | - | 18.9 |
| 30 | - | 8.9 | - | 33.2 | - | 36.9 | - | 26.9 | - | 31.5 | - | 30.2 |
| 31 | - | 16.9 | - | 21.1 | - | 35.7 | - | 26.3 | - | 17.3 | - | 20.7 |
| 32 | - | 24.9 | - | 11.7 | - | 13.0 | - | 16.1 | - | 6.9 | - | 16.5 |
| 33 | - | 22.3 | - | 5.1 | - | 4.5 | - | 6.5 | - | 2.0 | - | 4.4 |
| 34 | - | 12.0 | - | 2.9 | - | 1.0 | - | 2.3 | - | 0.4 | - | 1.3 |
| 35 | - | 4.6 | - | 1.8 | - | 0.1 | - | 0.4 | - | 0.1 | - | 0.1 |
| 36 | - | 0.9 | - | 0.2 | - | * | - | * | - | * | - | - |
| 37 | - | 0.2 | - | * | - | * | - | * | - | - | - | * |
| 38 | - | 0.1 | - | * | - | * | - | * | - | - | - | - |
| 39 | - | * | - | - | - | - | - | - | - | - | - | * |
| 40 & Above | - | * | - | - | - | - | - | * | - | - | - | - |
| Average | - | 32.40 | - | 30.97 | - | 31.15 | - | 31.06 | - | 30.26 | - | 30.81 |
| Mike | | | | | | | | | | | | |
| 2.4 & Below | - | 0.3 | - | - | - | - | - | - | - | - | - | - |
| 2.5 | - | 1.3 | - | - | - | - | - | - | - | * | - | * |
| 2.6 | - | 1.6 | - | * | - | - | - | - | - | - | - | * |
| 2.7 | - | 2.2 | - | * | - | - | - | - | - | * | - | 0.2 |
| 2.8 | - | 2.5 | - | - | - | - | - | - | - | * | - | 2.7 |
| 2.9 | - | 2.5 | - | * | - | - | - | - | - | * | - | 2.5 |
| 3.0 | - | 2.8 | - | * | - | - | - | - | - | * | - | 1.8 |
| 3.1 | - | 3.3 | - | * | - | * | - | - | - | * | - | 1.7 |
| 3.2 | - | 3.9 | - | * | - | * | - | * | - | 0.1 | - | 2.9 |
| 3.3 | - | 4.3 | - | * | - | * | - | * | - | 0.2 | - | 1.4 |
| 3.4 | - | 5.3 | - | 0.1 | - | * | - | * | - | 0.3 | - | 0.9 |
| 3.5 | - | 5.9 | - | 0.1 | - | * | - | 0.1 | - | 0.5 | - | 1.0 |
| 3.6 | - | 6.3 | - | 0.1 | - | 0.1 | - | 0.1 | - | 0.9 | - | 1.1 |
| 3.7 | - | 6.5 | - | 0.2 | - | 0.2 | - | 0.2 | - | 1.5 | - | 2.7 |
| 3.8 | - | 6.4 | - | 0.3 | - | 0.3 | - | 0.3 | - | 2.4 | - | 4.5 |
| 3.9 | - | 6.3 | - | 0.6 | - | 0.6 | - | 0.4 | - | 3.5 | - | 6.9 |
| 4.0 | - | 6.7 | - | 1.3 | - | 1.4 | - | 0.8 | - | 4.9 | - | 6.2 |
| 4.1 | - | 7.0 | - | 2.2 | - | 2.4 | - | 1.3 | - | 7.0 | - | 6.2 |
| 4.2 | - | 5.7 | - | 3.4 | - | 4.3 | - | 2.0 | - | 9.3 | - | 6.8 |
| 4.3 | - | 5.6 | - | 4.9 | - | 6.7 | - | 3.0 | - | 11.6 | - | 9.5 |
| 4.4 | - | 4.6 | - | 6.3 | - | 9.8 | - | 4.5 | - | 12.2 | - | 9.1 |
| 4.5 | - | 3.3 | - | 8.2 | - | 13.0 | - | 6.2 | - | 11.3 | - | 8.7 |
| 4.6 | - | 2.0 | - | 9.7 | - | 15.1 | - | 8.7 | - | 10.2 | - | 6.6 |
| 4.7 | - | 1.6 | - | 11.2 | - | 15.7 | - | 11.2 | - | 8.5 | - | 6.0 |
| 4.8 | - | 1.2 | - | 12.6 | - | 13.2 | - | 13.6 | - | 6.0 | - | 5.1 |
| 4.9 | - | 0.5 | - | 11.7 | - | 8.7 | - | 14.6 | - | 4.1 | - | 3.6 |
| 5.0 | - | 0.2 | - | 9.6 | - | 4.9 | - | 13.3 | - | 2.7 | - | 1.6 |
| 5.1 | - | * | - | 7.7 | - | 2.3 | - | 9.9 | - | 1.5 | - | 0.2 |
| 5.2 | - | * | - | 4.4 | - | 0.9 | - | 5.7 | - | 0.7 | - | * |
| 5.3 | - | - | - | 2.6 | - | 0.3 | - | 2.6 | - | 0.3 | - | * |
| 5.4 | - | - | - | 1.3 | - | 0.1 | - | 1.0 | - | 0.1 | - | - |
| 5.5 & Above | - | - | - | 1.4 | - | * | - | 0.4 | - | * | - | - |
| Average | - | 3.73 | - | 4.74 | - | 4.61 | - | 4.80 | - | 4.41 | - | 4.14 |

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending May 21, 2026

| Quality Designation | OKLAHOMA | | SOUTH CAROLINA | | TENNESSEE | | TEXAS | | VIRGINIA | |
|-------------------------|----------|--------------|----------------|--------------|-----------|--------------|--------------|--------------|----------|--------------|
| | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season |
| Extraneous Matter | - | | - | | - | | - | | - | |
| Bark - Level 1 | - | 3.4 | - | 3.6 | - | * | 0.4 | 4.7 | - | 1.3 |
| Bark - Level 2 | - | * | - | - | - | - | - | * | - | - |
| Grass - Level 1 | - | 0.1 | - | 0.1 | - | * | 33.7 | 0.2 | - | * |
| Grass - Level 2 | - | - | - | - | - | - | - | * | - | - |
| Prep - Level 1 | - | * | - | * | - | - | - | * | - | * |
| Prep - Level 2 | - | * | - | - | - | - | - | - | - | - |
| Seed Coat - Level 1 | - | * | - | 1.7 | - | * | - | 0.3 | - | 0.6 |
| Seed Coat - Level 2 | - | * | - | - | - | - | - | * | - | - |
| Oil - Level 1 | - | * | - | * | - | - | - | * | - | * |
| Oil - Level 2 | - | - | - | - | - | - | - | - | - | - |
| Spindle Twist - Level 1 | - | - | - | - | - | - | - | - | - | - |
| Spindle Twist - Level 2 | - | - | - | - | - | - | - | * | - | - |
| Other - Level 1 | - | * | - | - | - | - | - | * | - | - |
| Other - Level 2 | - | * | - | - | - | - | - | - | - | - |
| Plastic - Level 1 | - | * | - | * | - | * | - | * | - | * |
| Plastic - Level 2 | - | - | - | - | - | - | - | - | - | - |
| STRENGTH 1/ | | | | | | | | | | |
| 22 & Below | - | * | - | - | - | - | - | * | - | - |
| 23 | - | * | - | - | - | - | - | * | - | - |
| 24 | - | * | - | * | - | * | - | 0.1 | - | * |
| 25 | - | * | - | * | - | * | - | 0.2 | - | * |
| 26 | - | 0.2 | - | 0.4 | - | * | - | 0.9 | - | 1.1 |
| 27 | - | 1.2 | - | 2.6 | - | 0.5 | - | 3.1 | - | 6.2 |
| 28 | - | 4.5 | - | 12.6 | - | 3.8 | - | 8.1 | - | 19.0 |
| 29 | - | 10.7 | - | 34.7 | - | 21.0 | 5.0 | 16.1 | - | 32.2 |
| 30 | - | 17.1 | - | 30.2 | - | 38.7 | 50.3 | 20.9 | - | 25.7 |
| 31 | - | 19.4 | - | 13.3 | - | 24.7 | 37.2 | 18.4 | - | 11.1 |
| 32 | - | 16.1 | - | 4.8 | - | 8.2 | 1.4 | 13.1 | - | 3.6 |
| 33 | - | 13.2 | - | 1.2 | - | 2.4 | 1.7 | 9.2 | - | 0.8 |
| 34 | - | 9.2 | - | 0.2 | - | 0.7 | 1.8 | 6.0 | - | 0.2 |
| 35 | - | 5.0 | - | * | - | 0.1 | 1.5 | 2.6 | - | * |
| 36 | - | 2.1 | - | * | - | * | 0.8 | 0.9 | - | * |
| 37 | - | 1.0 | - | * | - | * | 0.3 | 0.3 | - | - |
| 38 | - | 0.2 | - | - | - | - | - | 0.1 | - | - |
| 39 | - | * | - | - | - | - | - | * | - | - |
| 40 & Above | - | * | - | - | - | - | - | * | - | - |
| Average | - | 31.95 | - | 30.02 | - | 30.66 | 31.10 | 31.16 | - | 29.73 |
| Mike | | | | | | | | | | |
| 2.4 & Below | - | * | - | - | - | - | - | * | - | - |
| 2.5 | - | * | - | - | - | - | - | 0.1 | - | - |
| 2.6 | - | * | - | - | - | - | - | 0.1 | - | - |
| 2.7 | - | 0.1 | - | - | - | * | - | 0.2 | - | * |
| 2.8 | - | 0.1 | - | * | - | * | - | 0.3 | - | * |
| 2.9 | - | 0.1 | - | * | - | * | - | 0.4 | - | * |
| 3.0 | - | 0.2 | - | * | - | * | - | 0.6 | - | 0.1 |
| 3.1 | - | 0.3 | - | * | - | * | - | 0.8 | - | 0.1 |
| 3.2 | - | 0.6 | - | 0.1 | - | * | - | 1.2 | - | 0.1 |
| 3.3 | - | 1.0 | - | 0.2 | - | * | - | 1.6 | - | 0.3 |
| 3.4 | - | 1.4 | - | 0.3 | - | 0.1 | - | 2.1 | - | 0.4 |
| 3.5 | - | 2.1 | - | 0.5 | - | 0.3 | - | 2.7 | - | 0.7 |
| 3.6 | - | 3.5 | - | 0.9 | - | 0.3 | - | 3.4 | - | 1.3 |
| 3.7 | - | 4.8 | - | 1.9 | - | 0.8 | - | 4.1 | - | 2.6 |
| 3.8 | - | 6.3 | - | 2.8 | - | 1.1 | - | 5.1 | - | 3.9 |
| 3.9 | - | 7.6 | - | 4.3 | - | 1.7 | 0.1 | 6.3 | - | 6.7 |
| 4.0 | - | 8.9 | - | 5.8 | - | 2.5 | 1.0 | 7.5 | - | 9.2 |
| 4.1 | - | 9.9 | - | 7.3 | - | 3.9 | 0.3 | 8.6 | - | 11.5 |
| 4.2 | - | 9.9 | - | 8.7 | - | 5.3 | 3.4 | 9.5 | - | 14.1 |
| 4.3 | - | 10.2 | - | 9.9 | - | 6.7 | 5.9 | 9.8 | - | 14.5 |
| 4.4 | - | 9.3 | - | 10.4 | - | 9.5 | 14.2 | 9.2 | - | 12.7 |
| 4.5 | - | 8.4 | - | 10.4 | - | 11.8 | 9.5 | 8.0 | - | 9.1 |
| 4.6 | - | 6.6 | - | 9.7 | - | 13.4 | 17.0 | 6.4 | - | 5.9 |
| 4.7 | - | 4.5 | - | 8.5 | - | 13.4 | 9.0 | 4.7 | - | 3.2 |
| 4.8 | - | 2.5 | - | 6.7 | - | 11.8 | 3.0 | 3.2 | - | 1.8 |
| 4.9 | - | 1.1 | - | 4.9 | - | 8.1 | - | 1.9 | - | 1.1 |
| 5.0 | - | 0.4 | - | 3.3 | - | 5.4 | 21.9 | 1.1 | - | 0.6 |
| 5.1 | - | 0.1 | - | 1.9 | - | 2.7 | 14.6 | 0.6 | - | 0.2 |
| 5.2 | - | * | - | 1.0 | - | 1.0 | - | 0.3 | - | * |
| 5.3 | - | * | - | 0.4 | - | 0.3 | - | 0.1 | - | * |
| 5.4 | - | - | - | 0.2 | - | * | - | 0.1 | - | * |
| 5.5 & Above | - | * | - | 0.1 | - | * | - | 0.1 | - | * |
| Average | - | 4.16 | - | 4.41 | - | 4.56 | 4.70 | 4.16 | - | 4.23 |

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE
For The Week Ending May 21, 2026

| Quality Designation | ALABAMA | | ARKANSAS | | ARIZONA | | CALIFORNIA | | FLORIDA | | GEORGIA | |
|------------------------|---------|----------------|----------|------------------|---------|----------------|------------|---------------|---------|---------------|---------|------------------|
| | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season |
| MIKE | | | | | | | | | | | | |
| 2.4 & Below | - | - | - | - | - | * | - | * | - | - | - | - |
| 2.5 - 2.6 | - | * | - | - | - | 0.1 | - | 0.1 | - | - | - | * |
| 2.7 - 2.9 | - | * | - | * | - | 0.4 | - | 0.5 | - | - | - | * |
| 3.0 - 3.2 | - | 0.1 | - | * | - | 0.8 | - | 0.9 | - | 0.1 | - | 0.1 |
| 3.3 - 3.4 | - | 0.6 | - | * | - | 0.9 | - | 1.2 | - | 0.1 | - | 0.5 |
| 3.5 - 3.6 | - | 1.9 | - | 0.1 | - | 1.7 | - | 3.9 | - | 1.2 | - | 1.8 |
| 3.7 - 4.2 | - | 33.1 | - | 4.1 | - | 29.5 | - | 50.9 | - | 20.7 | - | 30.9 |
| 4.3 - 4.9 | - | 57.4 | - | 71.3 | - | 60.4 | - | 36.1 | - | 72.1 | - | 58.6 |
| 5.0 - 5.2 | - | 5.7 | - | 21.8 | - | 4.9 | - | 5.1 | - | 5.4 | - | 7.1 |
| 5.3 & Above | - | 1.1 | - | 2.7 | - | 1.3 | - | 1.4 | - | 0.3 | - | 0.9 |
| Average | - | 4.39 | - | 4.76 | - | 4.38 | - | 4.24 | - | 4.48 | - | 4.41 |
| Leaf | | | | | | | | | | | | |
| 1 - 2 | - | 15.4 | - | 2.1 | - | 31.9 | - | 39.4 | - | 7.8 | - | 14.8 |
| 3 | - | 55.0 | - | 39.0 | - | 36.1 | - | 42.3 | - | 52.7 | - | 58.6 |
| 4 | - | 25.4 | - | 45.6 | - | 21.6 | - | 13.2 | - | 34.5 | - | 23.5 |
| 5 | - | 3.9 | - | 11.9 | - | 7.7 | - | 3.8 | - | 4.8 | - | 2.9 |
| 6 | - | 0.3 | - | 1.3 | - | 2.1 | - | 1.1 | - | 0.3 | - | 0.2 |
| 7 | - | * | - | 0.1 | - | 0.4 | - | 0.2 | - | * | - | * |
| 8 | - | * | - | - | - | 0.1 | - | 0.1 | - | - | - | * |
| Average | - | 3.18 | - | 3.71 | - | 3.08 | - | 2.79 | - | 3.37 | - | 3.15 |
| HVI Trash 1/ | | | | | | | | | | | | |
| 00 | - | - | - | - | - | * | - | * | - | - | - | - |
| 01 | - | 2.0 | - | 0.1 | - | 12.4 | - | 14.2 | - | 0.9 | - | 1.4 |
| 02 | - | 17.6 | - | 3.1 | - | 24.5 | - | 30.2 | - | 9.4 | - | 19.9 |
| 03 | - | 28.1 | - | 14.7 | - | 19.8 | - | 24.8 | - | 23.4 | - | 32.0 |
| 04 | - | 23.9 | - | 24.5 | - | 15.5 | - | 14.2 | - | 28.1 | - | 23.6 |
| 05 | - | 14.5 | - | 22.9 | - | 10.9 | - | 7.3 | - | 19.3 | - | 12.7 |
| 06 | - | 7.5 | - | 16.0 | - | 6.9 | - | 3.8 | - | 10.3 | - | 5.9 |
| 07 | - | 3.6 | - | 9.4 | - | 4.3 | - | 2.2 | - | 4.8 | - | 2.6 |
| 08 | - | 1.6 | - | 4.9 | - | 2.5 | - | 1.4 | - | 2.2 | - | 1.1 |
| 09 | - | 0.7 | - | 2.4 | - | 1.5 | - | 0.8 | - | 0.9 | - | 0.5 |
| 10 | - | 0.3 | - | 1.1 | - | 0.8 | - | 0.5 | - | 0.5 | - | 0.2 |
| 11 | - | 0.1 | - | 0.5 | - | 0.5 | - | 0.3 | - | 0.2 | - | 0.1 |
| 12 | - | 0.1 | - | 0.2 | - | 0.2 | - | 0.2 | - | 0.1 | - | * |
| 13 | - | * | - | 0.1 | - | 0.1 | - | 0.1 | - | * | - | * |
| 14 | - | * | - | * | - | 0.1 | - | 0.1 | - | * | - | * |
| 15 | - | * | - | * | - | * | - | * | - | * | - | * |
| 16 | - | * | - | - | - | * | - | * | - | * | - | * |
| 17 | - | * | - | - | - | * | - | * | - | * | - | * |
| 18 & Above | - | * | - | - | - | * | - | * | - | * | - | * |
| Average | - | 0.38 | - | 0.51 | - | 0.36 | - | 0.31 | - | 0.43 | - | 0.37 |
| UNIFORMITY 2/ | | | | | | | | | | | | |
| 74 & Below | - | - | - | - | - | - | - | - | - | - | - | - |
| 75 | - | - | - | - | - | * | - | - | - | - | - | * |
| 76 | - | * | - | * | - | * | - | * | - | * | - | * |
| 77 | - | * | - | * | - | 0.2 | - | 0.2 | - | * | - | 0.1 |
| 78 | - | 0.4 | - | 0.1 | - | 0.8 | - | 1.6 | - | 0.1 | - | 0.9 |
| 79 | - | 3.0 | - | 0.5 | - | 3.1 | - | 6.6 | - | 1.1 | - | 5.5 |
| 80 | - | 14.0 | - | 3.9 | - | 14.8 | - | 28.6 | - | 7.8 | - | 21.3 |
| 81 | - | 32.0 | - | 20.3 | - | 36.8 | - | 30.8 | - | 37.1 | - | 36.2 |
| 82 | - | 34.2 | - | 42.8 | - | 35.2 | - | 19.8 | - | 41.9 | - | 26.4 |
| 83 | - | 14.3 | - | 27.9 | - | 8.5 | - | 9.6 | - | 10.9 | - | 8.2 |
| 84 | - | 1.9 | - | 4.3 | - | 0.7 | - | 2.7 | - | 1.1 | - | 1.3 |
| 85 & Above | - | 0.2 | - | 0.3 | - | * | - | 0.1 | - | 0.1 | - | 0.1 |
| Average | - | 81.93 | - | 82.52 | - | 81.75 | - | 81.45 | - | 82.02 | - | 81.56 |
| Tenderable 3/ | - | 89.9 | - | 70.4 | - | 86.3 | - | 85.6 | - | 91.0 | - | 88.4 |
| SAMPLES CLASSED | - | 549,869 | - | 1,421,220 | - | 232,176 | - | 94,092 | - | 90,071 | - | 1,738,863 |

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY STATE
For The Week Ending May 21, 2026

| Quality Designation | KANSAS | | LOUISIANA | | MISSOURI | | MISSISSIPPI | | NORTH CAROLINA | | NEW MEXICO | |
|------------------------|--------|----------------|-----------|----------------|----------|----------------|-------------|----------------|----------------|----------------|------------|---------------|
| | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season |
| MIKE | | | | | | | | | | | | |
| 2.4 & Below | - | 0.3 | - | - | - | - | - | - | - | - | - | - |
| 2.5 - 2.6 | - | 2.9 | - | * | - | - | - | - | - | * | - | * |
| 2.7 - 2.9 | - | 7.2 | - | * | - | - | - | - | - | * | - | 5.3 |
| 3.0 - 3.2 | - | 10.0 | - | * | - | * | - | * | - | 0.2 | - | 6.3 |
| 3.3 - 3.4 | - | 9.6 | - | 0.1 | - | * | - | * | - | 0.5 | - | 2.4 |
| 3.5 - 3.6 | - | 12.2 | - | 0.2 | - | 0.1 | - | 0.2 | - | 1.4 | - | 2.1 |
| 3.7 - 4.2 | - | 38.6 | - | 8.1 | - | 9.2 | - | 5.0 | - | 28.6 | - | 33.2 |
| 4.3 - 4.9 | - | 18.9 | - | 64.6 | - | 82.2 | - | 61.8 | - | 64.0 | - | 48.8 |
| 5.0 - 5.2 | - | 0.3 | - | 21.7 | - | 8.1 | - | 29.0 | - | 4.9 | - | 1.9 |
| 5.3 & Above | - | - | - | 5.2 | - | 0.5 | - | 4.0 | - | 0.4 | - | * |
| Average | - | 3.73 | - | 4.74 | - | 4.61 | - | 4.80 | - | 4.41 | - | 4.14 |
| Leaf | | | | | | | | | | | | |
| 1 - 2 | - | 6.5 | - | 14.2 | - | 4.2 | - | 6.3 | - | 9.3 | - | 51.1 |
| 3 | - | 23.6 | - | 49.8 | - | 53.5 | - | 42.8 | - | 51.8 | - | 31.5 |
| 4 | - | 30.1 | - | 29.5 | - | 36.7 | - | 39.7 | - | 32.6 | - | 12.8 |
| 5 | - | 22.9 | - | 6.1 | - | 5.2 | - | 10.1 | - | 5.8 | - | 3.6 |
| 6 | - | 11.9 | - | 0.4 | - | 0.3 | - | 1.0 | - | 0.6 | - | 0.9 |
| 7 | - | 4.1 | - | - | - | * | - | * | - | 0.1 | - | 0.1 |
| 8 | - | 0.9 | - | - | - | - | - | - | - | * | - | - |
| Average | - | 4.26 | - | 3.28 | - | 3.44 | - | 3.57 | - | 3.37 | - | 2.62 |
| HVI Trash 1/ | | | | | | | | | | | | |
| 00 | - | - | - | - | - | * | - | - | - | - | - | - |
| 01 | - | 1.4 | - | 1.9 | - | 0.2 | - | 0.5 | - | 0.8 | - | 18.8 |
| 02 | - | 6.7 | - | 15.0 | - | 6.4 | - | 7.7 | - | 11.1 | - | 36.3 |
| 03 | - | 10.9 | - | 24.4 | - | 23.6 | - | 19.0 | - | 24.4 | - | 19.7 |
| 04 | - | 12.7 | - | 23.2 | - | 28.8 | - | 23.6 | - | 25.5 | - | 11.1 |
| 05 | - | 12.6 | - | 16.2 | - | 20.7 | - | 19.9 | - | 18.3 | - | 6.7 |
| 06 | - | 11.1 | - | 9.6 | - | 11.2 | - | 13.3 | - | 10.5 | - | 3.5 |
| 07 | - | 9.8 | - | 5.2 | - | 5.2 | - | 7.9 | - | 5.2 | - | 2.0 |
| 08 | - | 8.4 | - | 2.5 | - | 2.2 | - | 4.2 | - | 2.4 | - | 1.1 |
| 09 | - | 6.9 | - | 1.2 | - | 1.0 | - | 2.1 | - | 1.0 | - | 0.5 |
| 10 | - | 5.3 | - | 0.5 | - | 0.4 | - | 1.0 | - | 0.4 | - | 0.2 |
| 11 | - | 4.1 | - | 0.2 | - | 0.2 | - | 0.5 | - | 0.2 | - | 0.1 |
| 12 | - | 3.1 | - | 0.1 | - | 0.1 | - | 0.2 | - | 0.1 | - | 0.1 |
| 13 | - | 2.3 | - | * | - | * | - | 0.1 | - | * | - | * |
| 14 | - | 1.6 | - | * | - | * | - | * | - | * | - | - |
| 15 | - | 1.0 | - | - | - | * | - | * | - | * | - | - |
| 16 | - | 0.7 | - | - | - | - | - | - | - | * | - | - |
| 17 | - | 0.5 | - | - | - | - | - | - | - | * | - | - |
| 18 & Above | - | 0.8 | - | - | - | - | - | - | - | * | - | - |
| Average | - | 0.66 | - | 0.41 | - | 0.44 | - | 0.47 | - | 0.43 | - | 0.28 |
| UNIFORMITY 2/ | | | | | | | | | | | | |
| 74 & Below | - | * | - | - | - | - | - | - | - | * | - | - |
| 75 | - | 0.2 | - | - | - | - | - | - | - | * | - | * |
| 76 | - | 0.8 | - | - | - | * | - | * | - | * | - | 0.1 |
| 77 | - | 2.4 | - | - | - | * | - | * | - | * | - | 0.1 |
| 78 | - | 4.7 | - | 0.1 | - | 0.1 | - | 0.2 | - | 0.6 | - | 3.0 |
| 79 | - | 8.8 | - | 1.2 | - | 0.2 | - | 1.3 | - | 3.0 | - | 9.2 |
| 80 | - | 18.3 | - | 7.1 | - | 2.1 | - | 8.8 | - | 11.0 | - | 17.2 |
| 81 | - | 31.0 | - | 30.1 | - | 16.5 | - | 30.1 | - | 27.2 | - | 34.5 |
| 82 | - | 22.9 | - | 40.4 | - | 50.4 | - | 38.1 | - | 35.3 | - | 28.8 |
| 83 | - | 9.2 | - | 18.5 | - | 27.9 | - | 18.1 | - | 19.9 | - | 6.7 |
| 84 | - | 1.6 | - | 2.6 | - | 2.5 | - | 3.3 | - | 2.7 | - | 0.3 |
| 85 & Above | - | 0.1 | - | 0.1 | - | 0.2 | - | 0.1 | - | 0.2 | - | * |
| Average | - | 81.26 | - | 82.20 | - | 82.57 | - | 82.18 | - | 82.10 | - | 81.41 |
| Tenderable 3/ | - | 32.5 | - | 71.5 | - | 86.7 | - | 63.7 | - | 90.7 | - | 81.6 |
| SAMPLES CLASSED | - | 160,354 | - | 223,299 | - | 680,258 | - | 706,521 | - | 653,677 | - | 12,080 |

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE
For The Week Ending May 21, 2026

| Quality Designation | OKLAHOMA | | SOUTH CAROLINA | | TENNESSEE | | TEXAS | | VIRGINIA | |
|------------------------|----------|----------------|----------------|----------------|-----------|----------------|--------------|------------------|----------|----------------|
| | Week | Season | Week | Season | Week | Season | Week | Season | Week | Season |
| MIKE | | | | | | | | | | |
| 2.4 & Below | - | * | - | - | - | - | - | * | - | - |
| 2.5 - 2.6 | - | 0.1 | - | - | - | - | - | 0.2 | - | - |
| 2.7 - 2.9 | - | 0.3 | - | * | - | * | - | 0.8 | - | * |
| 3.0 - 3.2 | - | 1.1 | - | 0.1 | - | * | - | 2.7 | - | 0.3 |
| 3.3 - 3.4 | - | 2.4 | - | 0.5 | - | 0.2 | - | 3.7 | - | 0.6 |
| 3.5 - 3.6 | - | 5.7 | - | 1.4 | - | 0.6 | - | 6.2 | - | 2.0 |
| 3.7 - 4.2 | - | 47.4 | - | 30.7 | - | 15.1 | 4.8 | 41.0 | - | 48.0 |
| 4.3 - 4.9 | - | 42.6 | - | 60.4 | - | 74.7 | 58.6 | 43.2 | - | 48.2 |
| 5.0 - 5.2 | - | 0.5 | - | 6.2 | - | 9.0 | 36.6 | 2.0 | - | 0.8 |
| 5.3 & Above | - | * | - | 0.7 | - | 0.3 | - | 0.3 | - | * |
| Average | - | 4.16 | - | 4.41 | - | 4.56 | 4.70 | 4.16 | - | 4.23 |
| Leaf | | | | | | | | | | |
| 1 - 2 | - | 58.3 | - | 4.5 | - | 16.4 | 27.0 | 57.2 | - | 11.3 |
| 3 | - | 33.3 | - | 49.0 | - | 59.0 | 57.7 | 31.4 | - | 61.2 |
| 4 | - | 7.2 | - | 40.1 | - | 21.8 | 13.7 | 9.3 | - | 24.3 |
| 5 | - | 1.0 | - | 6.1 | - | 2.7 | 1.5 | 1.8 | - | 3.1 |
| 6 | - | 0.1 | - | 0.3 | - | 0.2 | 0.1 | 0.3 | - | 0.1 |
| 7 | - | * | - | * | - | * | - | * | - | * |
| 8 | - | * | - | - | - | - | - | * | - | - |
| Average | - | 2.33 | - | 3.49 | - | 3.11 | 2.90 | 2.41 | - | 3.20 |
| HVI Trash 1/ | | | | | | | | | | |
| 00 | - | * | - | - | - | * | - | 0.1 | - | - |
| 01 | - | 28.5 | - | 0.2 | - | 2.0 | 1.5 | 27.6 | - | 0.5 |
| 02 | - | 33.9 | - | 6.5 | - | 17.1 | 27.0 | 34.2 | - | 12.5 |
| 03 | - | 20.3 | - | 22.2 | - | 29.7 | 33.2 | 18.2 | - | 29.6 |
| 04 | - | 9.8 | - | 27.5 | - | 24.7 | 23.0 | 9.6 | - | 26.5 |
| 05 | - | 4.2 | - | 21.5 | - | 14.2 | 9.5 | 5.1 | - | 16.0 |
| 06 | - | 1.7 | - | 12.3 | - | 6.8 | 3.6 | 2.6 | - | 8.3 |
| 07 | - | 0.8 | - | 5.8 | - | 3.1 | 1.2 | 1.3 | - | 3.9 |
| 08 | - | 0.4 | - | 2.4 | - | 1.3 | 0.6 | 0.6 | - | 1.7 |
| 09 | - | 0.2 | - | 0.9 | - | 0.6 | - | 0.3 | - | 0.7 |
| 10 | - | 0.1 | - | 0.4 | - | 0.2 | - | 0.1 | - | 0.2 |
| 11 | - | * | - | 0.1 | - | 0.1 | 0.3 | 0.1 | - | 0.1 |
| 12 | - | * | - | * | - | * | - | * | - | * |
| 13 | - | * | - | * | - | * | - | * | - | * |
| 14 | - | * | - | * | - | * | - | * | - | * |
| 15 | - | * | - | * | - | * | - | * | - | * |
| 16 | - | * | - | * | - | - | - | * | - | * |
| 17 | - | * | - | - | - | - | - | * | - | * |
| 18 & Above | - | * | - | * | - | - | - | * | - | * |
| Average | - | 0.24 | - | 0.45 | - | 0.38 | 0.33 | 0.25 | - | 0.40 |
| UNIFORMITY 2/ | | | | | | | | | | |
| 74 & Below | - | * | - | - | - | - | - | * | - | - |
| 75 | - | * | - | * | - | - | - | * | - | - |
| 76 | - | * | - | * | - | * | - | 0.2 | - | * |
| 77 | - | 0.2 | - | 0.1 | - | * | - | 0.9 | - | * |
| 78 | - | 1.4 | - | 0.5 | - | 0.1 | - | 4.0 | - | 0.2 |
| 79 | - | 7.0 | - | 3.8 | - | 0.6 | 0.1 | 12.9 | - | 1.3 |
| 80 | - | 20.6 | - | 16.7 | - | 6.9 | 3.4 | 26.4 | - | 8.2 |
| 81 | - | 31.7 | - | 32.9 | - | 32.7 | 56.8 | 29.4 | - | 27.9 |
| 82 | - | 24.4 | - | 32.4 | - | 43.1 | 34.1 | 17.8 | - | 38.3 |
| 83 | - | 11.5 | - | 12.4 | - | 15.6 | 3.9 | 6.6 | - | 21.1 |
| 84 | - | 2.8 | - | 1.1 | - | 0.9 | 1.1 | 1.5 | - | 2.9 |
| 85 & Above | - | 0.2 | - | 0.1 | - | 0.1 | 0.6 | 0.2 | - | 0.2 |
| Average | - | 81.62 | - | 81.80 | - | 82.14 | 81.92 | 81.12 | - | 82.23 |
| Tenderable 3/ | - | 91.1 | - | 86.4 | - | 82.3 | 47.2 | 82.2 | - | 96.1 |
| SAMPLES CLASSED | - | 539,396 | - | 283,935 | - | 340,307 | 725 | 5,237,109 | - | 172,921 |

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE
For The Week Ending May 21, 2026

| Color Grade | Leaf | Arizona | | California | | New Mexico | | Texas | |
|---------------------------|------|--------------|-------------|--------------|-------------|------------|--------|--------------|-------------|
| | | Week | Season | Week | Season | Week | Season | Week | Season |
| 01 | 1 | - | 6.4 | - | 5.1 | - | - | - | 16.4 |
| | 2 | - | 2.8 | - | 6.3 | - | - | - | 20.6 |
| | 3 | - | 0.3 | - | 0.1 | - | - | - | 0.6 |
| | 4 | - | - | - | - | - | - | - | - |
| | 5 | - | - | - | - | - | - | - | - |
| | 6 | - | - | - | - | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - |
| Total ----- | | - | 9.5 | - | 11.6 | - | - | - | 37.6 |
| 02 | 1 | - | 36.4 | - | 4.5 | - | - | - | 12.5 |
| | 2 | - | 21.5 | - | 33.8 | - | - | - | 40.5 |
| | 3 | - | 0.5 | - | 9.0 | - | - | - | 3.4 |
| | 4 | - | * | - | 0.1 | - | - | - | 0.1 |
| | 5 | - | - | - | * | - | - | - | * |
| | 6 | - | - | - | - | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - |
| Total ----- | | - | 58.4 | - | 47.4 | - | - | - | 56.5 |
| 03 | 1 | - | 7.3 | - | 0.2 | - | - | - | 0.3 |
| | 2 | - | 19.0 | - | 14.4 | - | - | - | 4.3 |
| | 3 | - | 1.7 | - | 19.2 | - | - | - | 0.9 |
| | 4 | - | 0.1 | - | 2.3 | - | - | - | 0.1 |
| | 5 | - | - | - | 0.1 | - | - | - | - |
| | 6 | - | - | - | * | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - |
| Total ----- | | - | 28.2 | - | 36.1 | - | - | - | 5.6 |
| 04 | 7 | - | - | - | - | - | - | - | - |
| | 6 | - | - | - | * | - | - | - | - |
| | 5 | - | - | - | 0.1 | - | - | - | * |
| | 4 | - | * | - | 1.0 | - | - | - | 0.1 |
| | 3 | - | 0.8 | - | 2.3 | - | - | - | 0.1 |
| | 2 | - | 2.6 | - | 0.6 | - | - | - | 0.1 |
| | 1 | - | 0.2 | - | * | - | - | - | - |
| Total ----- | | - | 3.7 | - | 4.0 | - | - | - | 0.3 |
| 05 | 1 | - | * | - | * | - | - | - | - |
| | 2 | - | 0.2 | - | 0.1 | - | - | - | - |
| | 3 | - | 0.1 | - | 0.3 | - | - | - | * |
| | 4 | - | - | - | 0.2 | - | - | - | * |
| | 5 | - | - | - | * | - | - | - | - |
| | 6 | - | - | - | * | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - |
| Total ----- | | - | 0.3 | - | 0.7 | - | - | - | * |
| 06 | 1 | - | - | - | - | - | - | - | - |
| | 2 | - | - | - | * | - | - | - | - |
| | 3 | - | - | - | 0.1 | - | - | - | - |
| | 4 | - | - | - | 0.1 | - | - | - | - |
| | 5 | - | - | - | * | - | - | - | - |
| | 6 | - | - | - | * | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - |
| Total ----- | | - | - | - | 0.1 | - | - | - | - |
| 07 | 1 | - | - | - | - | - | - | - | - |
| | 2 | - | - | - | - | - | - | - | - |
| | 3 | - | - | - | * | - | - | - | - |
| | 4 | - | - | - | * | - | - | - | - |
| | 5 | - | - | - | * | - | - | - | - |
| | 6 | - | - | - | * | - | - | - | - |
| | 7 | - | - | - | - | - | - | - | - |
| Total ----- | | - | - | - | 0.1 | - | - | - | - |
| STAPLE | | | | | | | | | |
| 44 & Shorter | - | * | - | 2.3 | - | - | - | 13.1 | |
| 46 | - | 11.5 | - | 7.5 | - | - | - | 46.6 | |
| 48 | - | 71.8 | - | 43.9 | - | - | - | 35.4 | |
| 50 | - | 16.4 | - | 44.0 | - | - | - | 4.6 | |
| 52 & Longer | - | 0.2 | - | 2.3 | - | - | - | 0.4 | |
| Average Staple | - | 48.10 | - | 48.73 | - | - | - | 46.65 | |
| Average Length | - | 1.40 | - | 1.42 | - | - | - | 1.36 | |
| EXTRANEIOUS MATTER | | | | | | | | | |
| Bark | - | * | - | * | - | - | - | 0.2 | |
| Grass | - | - | - | 0.2 | - | - | - | 1.0 | |
| Spindle Twist | - | * | - | 0.2 | - | - | - | * | |
| Preparation | - | * | - | * | - | - | - | - | |
| All Other | - | * | - | * | - | - | - | 0.1 | |

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY STATE
For The Week Ending May 21, 2026

| Quality Designation | Arizona | | California | | New Mexico | | Texas | |
|------------------------|---------|---------------|------------|----------------|------------|--------|-------|---------------|
| | Week | Season | Week | Season | Week | Season | Week | Season |
| MIKE | | | | | | | | |
| 2.4 & Below | - | - | - | - | - | - | - | - |
| 2.5 - 2.6 | - | - | - | - | - | - | - | * |
| 2.7 - 2.9 | - | 0.1 | - | 0.1 | - | - | - | 0.3 |
| 3.0 - 3.2 | - | 0.5 | - | 0.5 | - | - | - | 9.6 |
| 3.3 - 3.4 | - | 0.5 | - | 1.4 | - | - | - | 13.4 |
| 3.5 - 3.6 | - | 3.9 | - | 6.9 | - | - | - | 19.1 |
| 3.7 - 4.2 | - | 88.3 | - | 87.2 | - | - | - | 54.2 |
| 4.3 - 4.9 | - | 6.7 | - | 3.9 | - | - | - | 3.4 |
| 5.0 - 5.2 | - | * | - | * | - | - | - | - |
| 5.3 & Above | - | - | - | - | - | - | - | - |
| Average | - | 3.97 | - | 3.91 | - | - | - | 3.71 |
| ALL RANGE MIKE | | | | | | | | |
| 2.4 & Below | - | - | - | - | - | - | - | - |
| 2.5 | - | - | - | - | - | - | - | - |
| 2.6 | - | - | - | - | - | - | - | * |
| 2.7 | - | * | - | * | - | - | - | * |
| 2.8 | - | * | - | * | - | - | - | * |
| 2.9 | - | * | - | 0.1 | - | - | - | 0.2 |
| 3.0 | - | 0.1 | - | 0.1 | - | - | - | 1.5 |
| 3.1 | - | 0.2 | - | 0.1 | - | - | - | 3.8 |
| 3.2 | - | 0.3 | - | 0.2 | - | - | - | 4.3 |
| 3.3 | - | 0.2 | - | 0.5 | - | - | - | 4.7 |
| 3.4 | - | 0.4 | - | 1.0 | - | - | - | 8.7 |
| 3.5 | - | 1.2 | - | 2.0 | - | - | - | 9.9 |
| 3.6 | - | 2.7 | - | 4.9 | - | - | - | 9.2 |
| 3.7 | - | 7.1 | - | 9.6 | - | - | - | 9.7 |
| 3.8 | - | 12.4 | - | 16.1 | - | - | - | 10.4 |
| 3.9 | - | 18.3 | - | 21.8 | - | - | - | 11.3 |
| 4.0 | - | 22.2 | - | 20.4 | - | - | - | 10.3 |
| 4.1 | - | 19.1 | - | 12.7 | - | - | - | 8.7 |
| 4.2 | - | 9.3 | - | 6.6 | - | - | - | 3.8 |
| 4.3 | - | 3.7 | - | 2.5 | - | - | - | 2.1 |
| 4.4 | - | 2.3 | - | 0.9 | - | - | - | 0.6 |
| 4.5 | - | 0.4 | - | 0.4 | - | - | - | 0.4 |
| 4.6 | - | 0.2 | - | 0.1 | - | - | - | 0.2 |
| 4.7 | - | * | - | * | - | - | - | * |
| 4.8 | - | * | - | * | - | - | - | * |
| 4.9 | - | * | - | * | - | - | - | * |
| 5.0 | - | * | - | * | - | - | - | - |
| 5.1 | - | - | - | * | - | - | - | - |
| 5.2 | - | - | - | - | - | - | - | - |
| 5.3 & Above | - | - | - | - | - | - | - | - |
| Average | - | 3.97 | - | 3.91 | - | - | - | 3.71 |
| STRENGTH 1/ | | | | | | | | |
| 36 & Below | - | 0.1 | - | 1.4 | - | - | - | 10.8 |
| 37 | - | 0.2 | - | 4.1 | - | - | - | 16.5 |
| 38 | - | 0.6 | - | 2.9 | - | - | - | 17.2 |
| 39 | - | 1.2 | - | 1.2 | - | - | - | 7.4 |
| 40 | - | 5.2 | - | 1.6 | - | - | - | 2.7 |
| 41 | - | 18.2 | - | 4.9 | - | - | - | 3.1 |
| 42 | - | 29.1 | - | 10.0 | - | - | - | 5.4 |
| 43 | - | 26.8 | - | 16.4 | - | - | - | 7.6 |
| 44 | - | 13.4 | - | 20.8 | - | - | - | 9.9 |
| 45 | - | 4.2 | - | 18.8 | - | - | - | 8.9 |
| 46 | - | 0.8 | - | 11.0 | - | - | - | 6.6 |
| 47 | - | 0.2 | - | 4.7 | - | - | - | 2.8 |
| 48 & Above | - | 0.2 | - | 2.2 | - | - | - | 1.3 |
| Average | - | 42.81 | - | 43.88 | - | - | - | 40.97 |
| UNIFORMITY | | | | | | | | |
| 83 & Below | - | 0.1 | - | 1.7 | - | - | - | 3.3 |
| 84 | - | 2.0 | - | 11.6 | - | - | - | 23.4 |
| 85 | - | 31.1 | - | 33.4 | - | - | - | 42.1 |
| 86 | - | 56.3 | - | 46.8 | - | - | - | 28.1 |
| 87 | - | 10.2 | - | 6.0 | - | - | - | 2.9 |
| 88 & Above | - | 0.3 | - | 0.6 | - | - | - | 0.2 |
| Average | - | 86.22 | - | 85.90 | - | - | - | 85.49 |
| Samples Classed | - | 27,733 | - | 308,854 | - | - | - | 34,750 |

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.