


# 660

## 6K, 5HS Weave Carbon Fiber



Specific Product Properties	
Type	6K Carbon Multifilament Continuous Tow
Twist	Untwisted
Weave Pattern	5 Harness Satin
Tensile Strength	610 - 700 KSI
Tensile Modulus	33.0 - 34.9 MSI
Elongation	1.4% - 1.95%
Warp ends/inch	11 - 13, 6K
Fill ends/inch	11 - 13, 6K
Weight	10.8 - 11.5 oz/yd <sup>2</sup>
Width	49.75 - 50.25 in

### 10.9 oz/sq yd, 50" Wide, .024" Thick, 6K, 5HS Weave Construction

With twice the fiber density of the 3K types, this fabric is ideal for structural applications. Also, the 5 HS weave allows it to work even with the most complex shapes. This material builds quickly to form lightweight structures with virtually no flex.

### DESCRIPTION

Graphite fibers contain up to 95% carbon and yield the highest tensile strength in the FRP industry. These fibers woven together form graphite fabric. These fabrics offer higher strength and stiffness-to-weight ratios than any other commonly available reinforcements. While there are hundreds of types to choose from, we have selected three styles of standard modulus carbon fiber which are suitable for use in racing, aircraft, competition marine, and light industrial applications. To maximize the fiber properties we recommend using only epoxy or vinyl ester resin, although polyesters will bond to the fabrics. With twice the fiber density of the 3K types, this fabric is ideal for structural applications. Also, the 5HS weave allows it to work even with the most complex shapes. This material builds quickly to form lightweight structures with virtually no flex.

### Resin Compatibility

660, Carbon Fiber Fabric, is compatible with Polyester, Vinyl Ester, and Epoxy Resins.

### General Properties for Carbon Fiber Fabrics

- Lightweight
- High Modulus
- Fire Resistant
- Dimensionally Stable
- Fatigue Resistant

Information present herein has been compiled from sources considered to be dependable and is accurate and reliable to the best of our knowledge and belief but is not guaranteed to be so. Nothing herein is to be construed as recommending any practice or any product violation of any patent or in violation of any law or regulation. It is the user's responsibility to determine for himself the suitability of any material for a specific purpose and to adopt such safety precautions as may be necessary. We make no warranty as to the results to be obtained in using any material and, since conditions of use are not under our control, we must necessarily disclaim all liability with respect to the use of any material supplied by us.