


Nylon Release Peel Ply



Easy release from your laminate

Our Nylon Released Peel Ply has been scoured, heat set and is coated with a specially designed release agent, providing for easy release from your laminate while leaving a uniform texture. It is compatible with all composite manufacturing processes at temperatures up to 480 degrees F. Nylon Released Peel Ply works with all of Fibre Glast's composite materials and resins. Due to the release coating, this product is not recommended for use where secondary bonding is planned. This peel ply is not compatible with phenolic systems. Available in 60" wide rolls/packages.

Fabric Properties	Product Standard
Material	Nylon 6,6
Areal Weight	1.7 - 2.0 oz/yd ² (57 - 68 GSM)
Weave pattern	Plain
Warp ends/inch	101 - 110
Fill ends/inch	82 - 90
Tensile Strength Warp	115 lbs (min)
Tensile Strength Fill	105 lbs (min)
Finish	060 - Natural - Scoured and Heat-Set
Fabric Width	58.0 - 61.0 inches
Thickness	.004 - .005 inches
Service Range	Up to 480°F

Application

#582 is designed for vacuum bag lay-up composites and metal-to-metal bonding structures. #582 melts at approximately 480°F (249°C). The fabric is not recommended for phenolic systems. The fabric leaves a fine surface impression.