

141

Fibre Glast Developments Corporation
 385 Carr Drive
 Brookville, Ohio 45309
 Phone: 800.214.8572
 Fax: 937.833.6555
 www.fibreglast.com

White Urethane Pigment



This White Urethane Pigment is a paste for tinting Urethane Casting Resins. Add pigments 2%-4% by weight to the urethane resin prior to the addition of catalyst. We have made every effort to accurately represent the cured color of our resins with these pigments. Due to various browsers these colors could vary.

Properties @ 77°F	Prod Standard
Hegman Grind	>=6
Density	13 - 14 lbs/gal
Viscosity (6/20 Spindle/RPM)	14,000 - 17,000 cps
Pigment Percent	50 - 60%
Tint Strength	95 - 100
DE	<=1.4
DL	-1.0 to +1.0
Da	-1.0 to +1.0
Db	-1.0 to +1.0

Information present herein has been compiled from sources considered to be dependable and is accurate and reliable to the best of our knowledge and belief but is not guaranteed to be so. Nothing herein is to be construed as recommending any practice or any product violation of any patent or in violation of any law or regulation. It is the user's responsibility to determine for himself the suitability of any material for a specific purpose and to adopt such safety precautions as may be necessary. We make no warranty as to the results to be obtained in using any material and, since conditions of use are not under our control, we must necessarily disclaim all liability with respect to the use of any material supplied by us.