FORM-A-TREAD®

FORM-A-TREAD COMPANY
Division of RGF Materials Company (LLC)

P.O. Box 941
375 Morgan Street, Suite 1-B
Phoenixville, PA 19460 USA

610-994-2138
www.form-a-tread.com

Physical Properties	ASTM	Value
Color (Part A)		Various
Color (Part B)		Neutral
Color (mixed)*		Various
Consistency		Paste
Mix Ratio		1:1 by volume
Working Time**	CC881	30 Minutes
Full Cure Time**	CC881	8 Hours
Hardness, Shore D	D2240	75 (+/-5)
Conductivity		None
Compressive Strength, 7 days	D695	11,000 psi
Specific Gravity, mixed		1.27 g/ml
Bond Strength	C882	1,600 psi
Temperature Resistance		-20°F - 200°F
% VOC	EPA Method 24	0
Slip Resistance, Wet***	F609	0.71 (SCOF)

*Standard Colors Black and Safety Yellow; Custom Colors Available

**Based on Testing at 75°F (24°C)

Note: Lower temperature slows cure; higher temperature accelerates cure

***Based on Tread Grit® HD (Heavy Duty) Application to Point of Refusal