FORM-A-TREAD COMPANY
Division of RGF Materials Company (LLC)

P.O. Box 941
375 Morgan Street, Suite 1-B
Phoenixville, PA 19460 USA

610-994-2138
www.form-a-tread.com

ATSM F609 - Test Results

Slip Resistance of Form-A-Tread with Tread Grit HD Applied*

Dry	Static Load (lbf)	Static Coefficient of Friction	Slip Index
Average	3.9	0.65	6.5

Wet	Static Load (lbf)	Static Coefficient of Friction	Slip Index
Average	4.3	0.71	7.1

**Note: Tread Grit HD was applied to the point of refusal.*