



MAXX Professional - Hybrid

Application/Uses

- Candy packaging
- Displays, Fixtures and Point of purchase
- Food packaging
- Furniture guards
- Plastics for hygiene feminine products
- Pricing channels
- Teething rails
- Tubing

Key Attributes

- Ease of processing
- Excellent chemical resistance
- Meets FDA regulations for food contact
- Sparkling clarity and high gloss
- Toughness with flexibility

Product Description

Maxx Professional Hybrid is a resin specifically developed for extrusion into profiles where aesthetics like high clarity and gloss, coupled with design flexibility drive demand. Compared to commonly used materials, Maxx Professional Hybrid can often run on most standard processing equipment at increased speeds. An extremely high melt strength makes the resin an excellent choice when extruding profiles into complicated shapes. This product is certified to ANSI/NSF Standard 51.

This product has been GREENGUARD INDOOR AIR QUALITY CERTIFIED®. The GREENGUARD INDOOR AIR QUALITY CERTIFIED® Mark is a registered certification mark used under license through the GREENGUARD Environmental Institute (GEI). GEI is an industry-independent, non-profit organization that oversees the GREENGUARD Certification Program. The GREENGUARD Certification Program is an industry independent, third-party testing program for low-emitting products and materials for indoor environments.

This product has been CRADLE TO CRADLE CERTIFIED^{cm} Silver. The CRADLE TO CRADLE CERTIFIED^{cm} Mark is a registered certification mark used under license through McDonough Braungart Design Chemistry (MBDC). MBDC is a global sustainability consulting and product certification firm. The CRADLE TO CRADLE® framework moves beyond the traditional goal of reducing the negative impacts of commerce ('eco-efficiency'), to a new paradigm of increasing its positive impacts ('eco-effectiveness'). At its core, Cradle to Cradle design perceives the safe and productive processes of nature's 'biological metabolism' as a model for developing a 'technical metabolism' flow of industrial materials. Product components can be designed for continuous recovery and reutilization as biological and technical nutrients within these metabolisms.



Property ^a	Test ^b Method	Typical Value, Units ^c
General Properties		
Specific Gravity	D 792	1.27
Mechanical Properties		
Tensile Stress @ Yield	D 638	50 MPa (7300 psi)
Tensile Stress @ Break	D 638	28 MPa (4100 psi)
Elongation @ Yield	D 638	4%
Elongation @ Break	D 638	110%
Flexural Modulus	D 790	2100 MPa (3.0 x 10 ⁵ psi)
Flexural Strength	D 790	68 MPa (9900 psi)
Rockwell Hardness, R Scale	D 785	108
Izod Impact Strength, Notched		
@ 23°C (73°F)	D 256	94 J/m (1.8 ft·lbf/in.)
@ -40°C (-40°F)	D 256	53 J/m (1.0 ft·lbf/in.)
Impact Strength, Unnotched		
@ 23°C (73°F)	D 4812	NB
@ -40°C (-40°F)	D 4812	NB
Impact Resistance (Puncture), Energy @ Max. Load		
@ 23°C (73°F)	D 3763	36 J (27 ft·lbf)
@ -40°C (-40°F)	D 3763	35 J (26 ft·lbf)
Thermal Properties		
Deflection Temperature		
@ 0.455 MPa (66 psi)	D 648	70°C (158°F)
@ 1.82 MPa (264 psi)	D 648	62°C (143°F)
Vicat Softening Temperature @ 1 kg load	D 1525	83°C (181°F)
Optical Properties		
Haze	D 1003	0.6%
Regular Transmittance	D 1003	87%
Total Transmittance	D 1003	90%
Gloss @ 60°	D 2457	152
Typical Processing Conditions		
Drying Temperature		71°C (160°F)
Drying Time		6 hrs
Processing Melt Temperature		249-271°C (480-520°F)



Comments

Properties reported here are typical of average lots. Maxx makes no representation that the material in any particular shipment will conform exactly to the values given.

Maxx and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

18-8-2014