

Received: 12/05/2013	Completed: 12/12/2013	Letter: C4	CJ	P.O.#: 17324	Test Report #: 2-99883-0-04
Client's Identification	Style: 20oz Vinyl Wallcovering with Non-Woven Backing. Content: Polycotton/Wood Pulp Non-woven Backing. Weight: 20oz Linear Yd. Color: Sample ID #150336. (see continuation)				
Tested For: Mark Rain	Key Test: FTM 5100.1/ASTM F793				135
Roysons Corp. 40 Vanderhoof Avenue Rockaway, NJ 07866	Tel: 1-(973)-625-5570		Ext: 124		
	Fax: 1-(973)-625-5917				

CLIENT'S IDENTIFICATION (continuation):

End Use of Fabric: Commercial Wallcovering.

Category: Break/Tensile Specifier: ASTM F 793 PC: 24H

TEST PERFORMED: Federal Test Standard 191A
 Method 5100.1 - Strength and Elongation, Breaking of Woven Cloth; Grab Method

RESULTS:	Machine Direction (lbs)	Cross Machine Direction (lbs)
Specimen #		
-----	-----	-----
1	86	71
2	86	75
3	87	72
4	88	70
5	88	70
	-----	-----
Avg	87	72

REMARKS: None.

CLASSIFICATION CRITERIA: As cited by ASTM F 793 Standard Classification of Wallcovering by Durability Characteristics, Commercial Serviceability --


Category	Type	Machine Direction (lbs)	Cross Machine Direction (lbs)
-----	-----	-----	-----
IV	I	Minimum 40	Minimum 30
V	II	Minimum 50	Minimum 55
VI	III	Minimum 100	Minimum 95

CONCLUSION: Based on the above Results and Classification Criteria, the item tested:

For Category IV Type I: Complies; Does not comply
 For Category V Type II: Complies; Does not comply
 For Category VI Type III: Complies; Does not comply

Received: 12/05/2013	Completed: 12/12/2013	Letter: C4	CJ	P.O.#: 17324	Test Report #: 2-99883-0-04
Client's Identification	Style: 20oz Vinyl Wallcovering with Non-Woven Backing. Content: Polycotton/Wood Pulp Non-woven Backing. Weight: 20oz Linear Yd. Color: Sample ID #150336. (see continuation)				
Tested For: Mark Rain Roysons Corp. 40 Vanderhoof Avenue Rockaway, NJ 07866	Key Test: FTM 5100.1/ASTM F793			135	
	Tel: 1-(973)-625-5570		Ext: 124		
	Fax: 1-(973)-625-5917				

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by Federal Test Standard 191A Test Method 5100.1.


 AUTHORIZED SIGNATURE
 THE GOVMARK ORGANIZATION, INC. / ec

JAN 2 4 2014
 qfb

MS. PHYLLIS PETTIT

(Page 1 of 1)