

4-GL2B-03748 MONOTAPE 940P CLEAR ASP2 PERMANENT/ASP2 PERMANENT WKPE90

Adhesive

Solvent based permanent acrylic adhesive featuring low cohesion and very high adhesion to a wide variety of substrates, including slightly rough surfaces. Suitable for mounting tapes.

Reference	ASP2 permanent
Type	Acrylic permanent
Min. Appl. Temp.	+5°C
Service Temp.	-30°C/+120°C
Shear	Low
Tack	Very High N/inch ²
Final Adhesion	High N/inch

Face Material

Self-wound construction with a clear polyester carrier.

Type	Polyester
Colour and Finish	Clear
Weight	17 g/m ² ±10% ISO-536
Thickness	12 µ ±10% ISO 534-80

Adhesive

Solvent based permanent acrylic adhesive featuring low cohesion and very high adhesion to a wide variety of substrates, including slightly rough surfaces. Suitable for mounting tapes.

Reference	ASP2 permanent
Type	Acrylic permanent
Min. Appl. Temp.	+5°C
Service Temp.	-30°C/+120°C
Shear	Low
Tack	Very High N/inch ²
Final Adhesion	High N/inch

Liner

Type	Two side silicone coated two side PE coated Kraft
Colour and Finish	White
Weight	90 g/m ² ±10% PP-032 - ISO 536
Thickness	100 µ ±10% ISO 534
Transparency	n.a. % DIN 53 147-64

Applications

For photographic and digital mounting.

Printing Methods

Not printable.
 Testing for suitability between media, printers and inks is always recommended prior to use.

Shelf life

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.