

Innovation for a Better Life













60 cell

Introducing MonoX® NeON module series, which uses highly efficient n-type materials, an elaborate process control adopting a semiconductor processing solution and a double-sided structure. Our R&D concentrates on developing a product that is not only efficient, but strives to increase practical value for customers.











N-Type Material

MonoX® NeON uses n-type cells, boasting higher mobility of electric charge, resulting in higher generation efficiency.



Near Zero LID (Light Induced Degradation)

The n-type cells used in MonoX® NeON have almost no boron, which may cause the initial efficiency to drop, leading to less LID.



Nano Level Control

MonoX® NeON uses the Nano-level process control predominant in semiconductor processing process, which ensures less electric loss from internal defects.



Double-Sided Cell Structure

The rear of the cell used in MonoX® NeON is designed to contribute to generation; the light beam reflected from the rear of the module is reabsorbed to generate a great amount of additional power.













About LG Electronics





Mechanical Properties

Cells	6 x 10
Cell vendor	LG
Cell type	Monocrystalline
Cell dimensions	156 x 156 mm / 6 x 6 in
# of busbar	3
Dimensions (L x W x H)	1640 x 1000 x 35 mm
	64.57 x 39.37 x 1.38 in
Static snow load	5400 Pa / 113 psf
Static wind load	2400 Pa / 50 psf
Weight	16.8 ± 0.5 kg / 36.96 ± 1.1 lb
Connector type	MC4 connector IP 67
Junction box	IP 67 with 3 bypass diodes
Length of cables	2 x 1000 mm / 2 x 39.37 in
Glass	High transmission tempered glass
Frame	Anodized aluminum

Certifications and Warranty


Certifications	IEC 61215, IEC 61730-1/-2, UL 1703,
	ISO 9001, IEC 61701, IEC 62716
Module fire performance (UL1703)	Type 2
Product warranty	10 years
Output warranty of Pmax (measurement Tolerance ± 3%)	Linear warranty*

 $^{^{\}star}$ 1) 1st year. 98%, 2) After 2nd year. 0.7%p annual degradation, 3) 81.2% for 25 years

Temperature Coefficients

NOCT	45 ± 2 °C
Pmpp	-0.41 %/°C
Voc	-0.29 %/°C
Isc	0.04 %/°C

Characteristic Curves



Electrical Properties (STC *)

	295 W
MPP voltage (Vmpp)	31.8
MPP current (Impp)	9.28
Open circuit voltage (Voc)	39.7
Short circuit current (Isc)	9.85
Module efficiency (%)	18.0
Operating temperature (°C)	-40 ~ +90
Maximum system voltage (V)	1000 (IEC), 600 (UL)
Maximum series fuse rating	20
Power tolerance (%)	0~+3


^{*} STC (Standard Test Condition): Irradiance 1000 W/m², module temperature 25 °C, AM 1.5

Electrical Properties (NOCT*)

	295 W
Maximum power (Pmpp)	215
MPP voltage (Vmpp)	29.1
MPP current (Impp)	7.40
Open circuit voltage (Voc)	36.8
Short circuit current (Isc)	7.94
Efficiency reduction (from 1000 W/m² to 200 W/m²)	< 2%

^{*} NOCT (Nominal Operating Cell Temperature): Irradiance 800 W/ m^2 , ambient temperature 20 °C, wind speed 1 m/s

Dimensions (mm/in)



 $[\]mbox{\ensuremath{\mbox{\scriptsize \star}}}$ The distance between the center of the mounting/grounding holes.



20

North America Solar Business Team LG Electronics U.S.A. Inc 1000 Sylvan Ave, Englewood Cliffs, NJ 07632

90

Contact: lg.solar@lge.com www.lgsolarusa.com

Product specifications are subject to change without notice. "LG Life's Good" is a registrated trademark of LG Corp. All other trademarks are the property of their respective owners. DS-N-60-C-US-F-EN-31002



^{*} The nameplate power output is measured and determined by LG Electronics at its sole and absolute discretion.