

PROTECT SERIES

CASEMENT, AWNING & FIXED WINDOWS

ENERGY VALUES

Regular glass

 Thickness	 Glass type	 U-Factor	 S.H.G.C	 V:T
5/16	Clear	1,05	0,76	0,88
5/16	Gray	1,05	0,58	0,54
7/16	Clear	1,05	0,75	0,87
7/16	Gray	1,05	0,54	0,47
9/16	Clear	0,91	0,74	0,87
9/16	Gray	0,91	0,30	0,42
11/16	Clear	0,51	0,76	0,81
11/16	Gray	0,51	0,59	0,56

Low-E glass

 Thickness	 Glass type	 U-Factor	 S.H.G.C	 V:T
5/16	CL SKN176 II LowE	1,05	0,43	0,68
5/16	CL Xtream60-28 II LowE	1,05	0,30	0,58
7/16	CL SKN176 II	1,05	0,44	0,67
7/16	CL Xtream60-28 II	1,05	0,30	0,57
9/16	CL SKN176 II	0,91	0,43	0,67
9/16	CL Xtream60-28 II	0,91	0,31	0,57
11/16	CL SKN176 II	0,33	0,38	0,69
11/16	CL Xtream60-28 II	0,33	0,29	0,59