

- Preset Sample Data

Sample Name	IBID 925 A	Dilution Material	
Description	2 BIG PLATTER	Sample Mass (g)	8.0000
Method	GoldCenter FP+	Dilution Mass (g)	0.0000
Job Number	2014_W09	Dilution Factor	1.0000
Sample Type	Alloy, 32 mm	Sample rotation	No
Sample State	Alloy	Date of Receipt	03/07/2014 14:04:29
Sample Status	A X X X X X X	Date of Evaluation	03/07/2014 14:04:31

- Results

The error is the statistical error with 1 sigma confidence interval

Z	Symbol	Element	Concentration	Abs. Error
79	Au	Gold	< 0.020 %	(0.0) %
47	Ag	Silver	<u>72.55</u> %	0.12 %
78	Pt	Platinum	< 0.020 %	(0.0) %
46	Pd	Palladium	< 0.020 %	(0.0) %
29	Cu	Copper	26.90 %	0.04 %
28	Ni	Nickel	< 0.015 %	(0.0) %
30	Zn	Zinc	0.5411 %	0.0043 %
22	Ti	Titanium	< 0.030 %	(0.0) %
23	V	Vanadium	< 0.030 %	(0.0) %
24	Cr	Chromium	< 0.020 %	(0.0) %
25	Mn	Manganese	< 0.025 %	(0.0) %
26	Fe	Iron	< 0.025 %	(0.0) %
27	Co	Cobalt	< 0.020 %	(0.0) %
31	Ga	Gallium	< 0.010 %	(0.0) %
41	Nb	Niobium	< 0.020 %	(0.0) %
42	Mo	Molybdenum	< 0.30 %	(0.0) %
44	Ru	Ruthenium	0.0 %	0.0 %
45	Rh	Rhodium	< 0.0020 %	(0.0) %
48	Cd	Cadmium	< 0.051 %	(0.0) %
49	In	Indium	< 0.030 %	(0.0) %
50	Sn	Tin	< 0.051 %	(0.0) %
51	Sb	Antimony	< 0.051 %	(0.0) %
73	Ta	Tantalum	< 0.0010 %	(0.0) %
74	W	Tungsten	< 0.025 %	(0.0) %
77	Ir	Iridium	< 0.0010 %	(0.0) %
82	Pb	Lead	< 0.020 %	(0.0) %