

— Preset Sample Data —

Sample Name	IBID 925 SMALL GOBLETT	Dilution Material	
Description	<i>3 Small Goblets</i>	Sample Mass (g)	8.0000
Method	GoldCenter FP+	Dilution Mass (g)	0.0000
Job Number	2014_W09	Dilution Factor	1.0000
Sample Type	Alloy, 32 mm	Sample rotation	No
Sample State	Alloy	Date of Receipt	03/07/2014 14:08:44
Sample Status	A X X X X X X X	Date of Evaluation	03/07/2014 14:08:46

— Results —

The error is the statistical error with 1 sigma confidence interval

Z	Symbol	Element	Concentration		Abs. Error	
79	Au	Gold	< 0.020	%	(0.0)	%
47	Ag	Silver	72.10	%	0.11	%
78	Pt	Platinum	< 0.020	%	(0.0)	%
46	Pd	Palladium	< 0.020	%	(0.0)	%
29	Cu	Copper	27.22	%	0.04	%
28	Ni	Nickel	< 0.015	%	(0.0)	%
30	Zn	Zinc	0.6634	%	0.0047	%
22	Ti	Titanium	< 0.030	%	(0.0)	%
23	V	Vanadium	< 0.030	%	(0.0)	%
24	Cr	Chromium	< 0.020	%	(0.0)	%
25	Mn	Manganese	< 0.025	%	(0.0)	%
26	Fe	Iron	< 0.025	%	(0.0)	%
27	Co	Cobalt	< 0.020	%	(0.0)	%
31	Ga	Gallium	< 0.010	%	(0.0)	%
41	Nb	Niobium	< 0.020	%	(0.0)	%
42	Mo	Molybdenum	< 0.30	%	(0.0)	%
44	Ru	Ruthenium	0.0	%	0.0	%
45	Rh	Rhodium	< 0.0020	%	(0.0)	%
48	Cd	Cadmium	< 0.051	%	(0.0)	%
49	In	Indium	< 0.030	%	(0.0)	%
50	Sn	Tin	< 0.051	%	(0.0)	%
51	Sb	Antimony	< 0.051	%	(0.0)	%
73	Ta	Tantalum	< 0.0010	%	(0.0)	%
74	W	Tungsten	< 0.025	%	(0.0)	%
77	Ir	Iridium	< 0.0010	%	(0.0)	%
82	Pb	Lead	< 0.020	%	(0.0)	%