# **SI BONDER**

Food Grade 100% RTV Silicone Sealant for the surfacing industry

### **APPLICATIONS**

Color matched sealant for: **SOLID SURFACE NATURAL STONE CERAMICS** SINTERED SURFACES QUARTZ **GLASS AND MORE** 

#### **BENEFITS**

- •100% RTV Silicone Sealant
- NSF and FDA Compliant
- Available in multiple colors
- Online cross-reference color charts for more than 9,000 surfaces
- Excellent adhesion to Solid Surface, Quartz, Stone, Ceramic
- For Indoor and Outdoor use
- Food Grade
- Meets ASTM C920, Type S, Grade NS, Class 25

# **CONTACT**

**PHONE** 

1.888.862.6665 1.604.850.1321

FAX

1.604.850.1354

**EMAIL & WEB** 

contact@integra-adhesives.com www.integra-adhesives.com



## **Product Overview**

#### Description

Si Bonder is a high performance, one component, acetoxy cure, 100% RTV Silicone Sealant and adhesive designed to color coordinate with solid surface, quartz, natural stone, ceramic and other non-porous surface applications.

#### **Applications**

Si Bonder is suitable for permanent flexible sealing and bonding of multiple surfaces allowing joint movement of +/- 25% for interior/ exterior residential and commercial installa-

# **Available Colors**

Crystal Clear, White Linen, Trans White, and many more...

For a full list of colors visit:

www.integra-adhesives.com/si-bonder

**Product Attributes** 

- UV stable, non-yellowing & mildew resistant
- · Non-sag, for horizontal, vertical and overhead surfaces
- Excellent unprimed adhesion to many substrates
- · Superior gunning throughout a wide temperature range
- · Will not crack, fade, shrink or discolor at the
- Dry tools easily to a smooth, attractive gloss finish
- · Color match charts available for solid surface, quartz, stone & ceramic

### **Characteristics**

Chemistry	Acetoxy	
Appearance	Smooth	
Colors	Various transparent, translucent and opaque colors	
Specific Gravity	1.01	
Extrusion Rate	400g/m	
Sag/Slump	Nil @120°F (49°C)	ASTM C 639
Skin Formation (*)	5–10 minutes	@ 75°F (24°C) & 50% relative humidity
Tack Free Time (*)	10-20 minutes	ASTM C 679
Curing time (*)	24 hrs, 1/8" diameter bead	@ 75°F (24°C) & 50% relative humidity
Oil Gel Test	No gel formation	
Application Temperature	-35°F to 140°F (-37°C to 60°C)	
Shore "A" Hardness (*)	25 points	ASTM C 661
Tensile Strengh (*)	265 psi	ASTM D 412
Elongation (*)	500%	ASTM D 412
Movement capability	+/- 25%	ASTM C 719
Service Temperature	-40°F to 400°F (-40°C to 204°C)	
Artificial Weathering	No Cracking	ASTM C 793
Shelf life	12 months	Stored between 41°F–77°F (5°C–25°C)
VOC	23g/L	

(\*) These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. Test results are averages obtained under laboratory

#### Meets

ASTM C-920-86	
TT-S-001543A, TT-S-00230C	
NSF STANDARD 51	
FDA/USDA requirements for use in establishments operating under Federal Meat and Poultry Inspection program. When cured	
and washed, ingredients remaining or which could migrate to food are listed on FDA Regulation No. 21 CFR 177.2600	

#### Limitations

- This product is not paintable.
- This product is not to be used as a structural glazing sealant.
- · We always recommend a preliminary adhesion test on every surface.
- · Lower temperatures and humidity will extend curing time.
- When working with Natural Stone test a sample with Si Bonder to ensure compatibility.

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use Since the supplier cannot know all the uses, or the conditions of use to which these products may be put, no warranties concerning the fitness or suitability for a particular use or purpose are made.

You should thoroughly test any proposed use of our products and independently conclude satisfactory performance application.

Likewise, if the manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain such

The supplier warrants only that its products will meet its specifications. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. The users exclusive remedy and the suppliers sole liability is limited to refund of the purchase price or replacement of any product shown to be otherwise than as warranted. The supplier will not be liable for any incidental or consequential damages of any kind.