



**Material: Hi-Flux™ 147μ Toroid**

Revision 20200519 - Generated 2020-May-26

μi (reference)	147
Typical AL tolerance	± 8%
Density	7.7 g/cm <sup>3</sup>
Bsat	15.3 kG
Core Loss (50kHz, 1000g)	509 mW/cm <sup>3</sup> (nom) 585 mW/cm <sup>3</sup> (max)
	72.9% (nom)
%Perm at DC Bias (40 Oe)	64.4% (min)

