



**Material: Sendust 75μ Toroid**

Revision 20200519 - Generated 2020-May-26

μi (reference)	075
Typical AL tolerance	± 8%
Density	5.9 g/cm <sup>3</sup>
Bsat	8.9 kG
Core Loss (50kHz, 1000g)	323 mW/cm <sup>3</sup> (nom) 372 mW/cm <sup>3</sup> (max)
	47.9% (nom)
%Perm at DC Bias (80 Oe)	39.6% (min)

