



**Material: Sendust 26μ Toroid**

Revision 20200519 - Generated 2020-May-26

μi (reference)	026
Typical AL tolerance	± 8%
Density	5.1 g/cm <sup>3</sup>
Bsat	8.1 kG
Core Loss (100kHz, 500g)	295 mW/cm <sup>3</sup> (nom) 339 mW/cm <sup>3</sup> (max)
	55.4% (nom)
%Perm at DC Bias (200 Oe)	46.3% (min)

