



Base Metal Grouping for Welding Procedure and Performance Qualification



American Welding Society®



Base Metal Grouping for Welding Procedure and Performance Qualification

3rd Edition

Supersedes AWS B2.1-B2.1M-BMG:2009-ADD1

Prepared by the
American Welding Society (AWS) B2 Committee on Procedure and Performance Qualification

Under the Direction of the
AWS Technical Activities Committee

Approved by the
AWS Board of Directors

Abstract

This document provides the AWS base metal grouping for welding procedure and performance qualification and is identical to Annex C of AWS B2.1/B2.1M:2014, *Specification for Welding Procedure and Performance Qualification*.



American Welding Society®

ISBN: 978-0-87171-849-5
© 2014 by American Welding Society
All rights reserved
Printed in the United States of America

Photocopy Rights. No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.

Authorization to photocopy items for internal, personal, or educational classroom use only or the internal, personal, or educational classroom use only of specific clients is granted by the American Welding Society provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, tel: (978) 750-8400; Internet: <www.copyright.com>.

Statement on the Use of American Welding Society Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National Standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions is entrusted to appropriately qualified and competent personnel.

This standard may be superseded by new editions. This standard may also be corrected through publication of amendments or errata or supplemented by publication of addenda. Information on the latest editions of AWS standards including amendments, errata, and addenda is posted on the AWS web page (www.aws.org). Users should ensure that they have the latest edition, amendments, errata, and addenda.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Technical Services Division, 8669 NW 36 St, # 130, Miami, FL 33166. With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS required and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS B2 Committee on Procedure and Performance Qualification. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are required and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS B2 Committee on Procedure and Performance Qualification and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS required and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS B2 Committee on Procedure and Performance Qualification to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

This page is intentionally blank.

Personnel

AWS B2 Committee on Procedure and Performance Qualification

J. J. Fluckiger, Chair	<i>Idaho National Laboratory</i>
J. L. Cooley, 1st Vice Chair	<i>J. C. & Associates, Incorporated</i>
E. W. Beckman, 2nd Vice Chair	<i>Consultant</i>
A. L. Diaz, Secretary	<i>American Welding Society</i>
D. M. Allbritten	<i>GE Capital</i>
M. Bernasek	<i>C-SPEC</i>
K. L. Bingham	<i>Los Alamos National Laboratory</i>
H. R. Castner	<i>Edison Welding Institute</i>
D. W. Craig	<i>Computer Engineering, Incorporated</i>
E. H. Gray	<i>U.S. Nuclear Regulatory Commission</i>
M. F. Herrle	<i>Arise</i>
K. G. Kofford	<i>Idaho National Laboratory</i>
R. A. LaFave	<i>Consultant</i>
G. S. Michels	<i>Summit Consulting</i>
A. S. Olivares	<i>HSB Global Standards</i>
J. F. Pike	<i>NASA Langley Research Center</i>
W. M. Ruof	<i>Bechtel Plant Machinery, Incorporated</i>
J. J. Sekely	<i>Welding Services, Incorporated</i>
M. R. Stone	<i>URS Flint</i>
M. L. Thomas	<i>Rocky Mountain Testing, LLC</i>
G. M. Wisbrock, Jr.	<i>Consultant</i>
R. K. Wiswesser	<i>Welder Training & Testing Institute</i>

Advisors to the AWS B2 Committee on Procedure and Performance Qualification

L. P. Connor	<i>Consultant</i>
W. D. Doty	<i>Doty & Associates, Incorporated</i>
B. J. Hable	<i>Ford Motor Company</i>
K. Y. Lee	<i>U.S. Department of Transportation</i>
B. B. MacDonald	<i>Consultant</i>
F. A. Schweighardt	<i>Air Liquide Industrial U.S. LP</i>
A. W. Sindel	<i>Alstom Power Steam</i>
C. E. Spaeder, Jr.	<i>Consultant</i>
W. J. Sperko	<i>Sperko Engineering Services, Incorporated</i>
R. F. Waite	<i>Consultant</i>

AWS B2B Subcommittee on Welding Qualification

M. R. Stone, Chair	<i>URS Flint</i>
A. L. Diaz, Secretary	<i>American Welding Society</i>
D. M. Allbritten	<i>GE Capital</i>
E. W. Beckman	<i>Consultant</i>
M. Bernasek	<i>C-SPEC</i>
K. L. Bingham	<i>Los Alamos National Laboratory</i>
J. L. Cooley	<i>J. C. & Associates, Incorporated</i>
D. W. Craig	<i>Computer Engineering, Incorporated</i>

AWS B2B Subcommittee on Welding Qualification (Continued)

J. J. Fluckiger	<i>Idaho National Laboratory</i>
E. H. Gray	<i>U.S. Nuclear Regulatory Commission</i>
K. G. Kofford	<i>Idaho National Laboratory</i>
G. S. Michels	<i>Summit Consulting</i>
A. S. Olivares	<i>HSB Global Standards</i>
J. F. Pike	<i>NASA Langley Research Center</i>
J. J. Sekely	<i>Welding Services, Incorporated</i>
M. L. Thomas	<i>Rocky Mountain Testing, LLC</i>
G. M. Wisbrock Jr.	<i>Consultant</i>
R. K. Wiswesser	<i>Welder Training & Testing Institute</i>

Advisors to the AWS B2B Subcommittee on Welding Qualification

L. P. Connor	<i>Consultant</i>
W. D. Doty	<i>Doty & Associates, Incorporated</i>
J. G. Feldstein	<i>Foster Wheeler North America</i>
B. J. Hable	<i>Ford Motor Company</i>
K. Y. Lee	<i>U.S. Department of Transportation</i>
A. W. Sindel	<i>Alstom Power Steam</i>
W. J. Sperko	<i>Sperko Engineering Service, Incorporated</i>

AWS B2C Subcommittee on Materials

W. M. Ruof, Chair	<i>Bechtel Plant Machinery Incorporated</i>
A. L. Diaz, Secretary	<i>American Welding Society</i>
M. Bernasek	<i>C-SPEC</i>
J. J. Fluckiger	<i>Idaho National Laboratory</i>
M. F. Herrle	<i>Arise</i>
K. G. Kofford	<i>Idaho National Laboratory</i>
R. A. LaFave	<i>Consultant</i>

Advisors to the AWS B2C Subcommittee on Materials

C. E. Cross	<i>Los Alamos National Laboratory</i>
A. Donlevy	<i>International Titanium Association</i>
W. D. Doty	<i>Doty & Associates, Incorporated</i>
P. Pollak	<i>Pollak & Associates</i>
A. W. Sindel	<i>Alstom Power Steam</i>
C. E. Spaeder, Jr.	<i>Consultant</i>
L. T. Vernam	<i>AlcoTec Wire Corporation</i>
G. M. Wisbrock, Jr.	<i>Consultant</i>

Table of Contents

	Page No.
<i>Personnel</i>	v
<i>List of Tables</i>	vii
1. Scope	1
Annex <u>C</u> —Base Metal Grouping	3

List of Tables

Table	Page No.
<u>C.1</u> Listing of Base Metal Specifications—Ferrous Alloys	4
<u>C.1</u> Listing of Base Metal Specifications—Nonferrous Alloys	54
<u>C.2</u> M-Number Listing of Base Metals—Ferrous Alloys.....	82
<u>C.2</u> M-Number Listing of Base Metals—Nonferrous Alloys.....	155
<u>C.3</u> Listing of Base Metal Specifications—Iron Castings.....	204

This page is intentionally blank.

Base Metal Grouping for Welding Procedure and Performance Qualification

1. Scope

This publication is an extract of AWS B2.1/B2.1M:2014, *Specification for Welding Procedure and Performance Qualification*, and is identical to Annex C, Base Metal Grouping, in the 2014 edition of that standard. This publication supersedes AWS B2.1/B2.1M-BMG:2009-ADD1. Underlined text or a vertical line in the margin indicates a revision from the 2009 edition.

This publication may be referred to by other codes and standards that have welding procedure and performance requirements in order to avoid duplication of materials tables in those publications.

Base metals and filler metals have been grouped into categories that will minimize the number of qualification tests required. Substitution of one base metal or filler metal for another, even when within the allowable rules, should only be made after an evaluation of the factors involved. For some materials, additional tests may be required. Materials not listed require separate qualification.

This page is intentionally blank.

Annex C (Normative)

Base Metal Grouping

(see 3, 4.3.12, 4.3.15, and Table 5.3)

This annex is part of AWS B2.1/B2.1M-BMG:2014, *Base Metal Grouping for Welding Procedure and Performance Qualification*, and includes mandatory elements for use with this standard.

C1. Base Metal Specifications

Table C.1 indexes ASTM, ABS, API, AS, AS/NZS, CSA, AMS, ISO, NACE, and MSS base metals in numerical order to provide ease of reference when determining into what grouping a particular base metal specification falls.

Table C.2 groups base metals for welding procedure and performance qualification on the basis of mechanical properties, chemical composition, and metallurgical compatibility to minimize the number of welding qualification where this can logically be done.

Table C.3 lists base metal specifications for iron castings in accordance with AWS D11.2 groups.

C2. Material Number (M-Number) Groupings

Base metal has been divided into general categories, e.g., Material Numbers (M-Numbers) 1, 1A, 3, 3A, 4, 4A, etc., and further divided into groups within each general category.

The category grouping does not imply that base metals may be substituted for other base metals within the same Material Number (M-Number) without consideration for weldability.

C3. Iron Castings Specifications

Base metal specifications for iron castings are divided into D11.2 groups.

Table C.1
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
AAR	M201	1	1	11.1	A	—	Castings
AAR	M201	1	2	11.1	B	—	Castings
AAR	M201	1	3	11.1	B+	—	Castings
AAR	M201	1	4	11.1	C	—	Castings
AAR	TC128	10C	1	11.1	B	—	Plate
ABS	ABS	1	1	1.1	E	K01801	Plate, Bar, & Shapes
ABS	ABS	1	1	1.1	D	K02101	Plate, Bar, & Shapes
ABS	ABS	1	1	1.1	B	K02102	Plate, Bar, & Shapes
ABS	ABS	1	1	1.1	A	K02300	Plate, Bar, & Shapes
ABS	ABS	1	1	1.2	AH32	K11846	Plate, Bar, & Shapes
ABS	ABS	1	1	1.2	DH32	K11846	Plate, Bar, & Shapes
ABS	ABS	1	1	1.2	EH32	K11846	Plate, Bar, & Shapes
ABS	ABS	1	1	1.2	FH32	K11846	Plate, Bar, & Shapes
ABS	ABS	1	2	1.2	AH36	K11852	Plate, Bar, & Shapes
ABS	ABS	1	2	1.2	DH36	K11852	Plate, Bar, & Shapes
ABS	ABS	1	2	1.2	EH36	K11852	Plate, Bar, & Shapes
ABS	ABS	1	2	1.2	FH36	K11852	Plate, Bar, & Shapes
ABS	ABS	1	2	1.3	AH40	K11857	Plate, Bar, & Shapes
ABS	ABS	1	2	1.3	DH40	K11857	Plate, Bar, & Shapes
ABS	ABS	1	2	1.3	EH40	K11857	Plate, Bar, & Shapes
ABS	ABS	1	2	1.3	FH40	K11857	Plate, Bar, & Shapes
API	2H	1	1	1.2	42	—	Plate
API	2H	1	2	1.2	50	—	Plate
API	2MT1	1	1	1.2	50	—	Plate
API	2W	1	1	1.2	50	—	Plate
API	2W	1	2	1.3	60	—	Plate
API	2Y	1	1	1.2	42	—	Plate
API	2Y	1	1	1.2	50	—	Plate
API	2Y	1	2	1.2	50T	—	Plate
API	2Y	1	2	1.3	60	—	Plate
API	5L	1	1	1.1	A	—	Seamless & Welded Pipe
API	5L	1	1	1.1	A25	—	Seamless & Welded Pipe
API	5L	1	1	1.1	A25, Cl. I	—	Seamless & Welded Pipe & Tube
API	5L	1	1	1.1	A25, Cl. II	—	Seamless & Welded Pipe & Tube
API	5L	1	1	1.1	A25P	—	Seamless & Welded Pipe
API	5L	1	1	11.1	B	—	Seamless & Welded Pipe
API	5L	1	1	1.1	BM	—	Welded Pipe
API	5L	1	1	1.1	BMO	—	Welded Pipe
API	5L	1	1	1.1	BMS	—	Welded Pipe
API	5L	1	1	1.1	BN	—	Seamless & Welded Pipe
API	5L	1	1	1.1	BNO	—	Seamless & Welded Pipe
API	5L	1	1	1.1	BNS	—	Seamless & Welded Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
API	5L	1	1	1.1	BQ	—	Seamless & Welded Pipe
API	5L	1	1	1.1	BQO	—	Seamless & Welded Pipe
API	5L	1	1	1.1	BQS	—	Seamless & Welded Pipe
API	5L	1	1	1.1	BR	—	Seamless & Welded Pipe
API	5L	1	1	11.1	X42	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X42M	—	Welded Pipe
API	5L	1	1	1.2	X42MO	—	Welded Pipe
API	5L	1	1	1.2	X42MS	—	Welded Pipe
API	5L	1	1	1.2	X42N	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X42NO	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X42NS	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X42Q	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X42QO	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X42QS	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X42R	—	Seamless & Welded Pipe
API	5L	1	1	11.1	X46	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X46M	—	Welded Pipe
API	5L	1	1	1.2	X46MO	—	Welded Pipe
API	5L	1	1	1.2	X46MS	—	Welded Pipe
API	5L	1	1	1.2	X46N	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X46NO	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X46NS	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X46Q	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X46QO	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X46QS	—	Seamless & Welded Pipe
API	5L	1	1	11.1	X52	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X52M	—	Welded Pipe
API	5L	1	1	1.2	X52MO	—	Welded Pipe
API	5L	1	1	1.2	X52MS	—	Welded Pipe
API	5L	1	1	1.2	X52N	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X52NO	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X52NS	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X52Q	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X52QO	—	Seamless & Welded Pipe
API	5L	1	1	1.2	X52QS	—	Seamless & Welded Pipe
API	5L	1	2	11.1	X56	—	Seamless & Welded Pipe
API	5L	1	2	2.1	X56M	—	Welded Pipe
API	5L	1	2	2.1	X56MO	—	Welded Pipe
API	5L	1	2	2.1	X56MS	—	Welded Pipe
API	5L	1	2	1.3	X56N	—	Seamless & Welded Pipe
API	5L	1	2	3.1	X56Q	—	Seamless & Welded Pipe
API	5L	1	2	3.1	X56QO	—	Seamless & Welded Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
API	5L	1	2	3.1	X56QS	—	Seamless & Welded Pipe
API	5L	1	2	11.1	X60	—	Seamless & Welded Pipe
API	5L	1	2	2.1	X60M	—	Welded Pipe
API	5L	1	2	2.1	X60MO	—	Welded Pipe
API	5L	1	2	2.1	X60MS	—	Welded Pipe
API	5L	1	2	1.3	X60N	—	Seamless & Welded Pipe
API	5L	1	2	3.1	X60Q	—	Seamless & Welded Pipe
API	5L	1	2	3.1	X60QO	—	Seamless & Welded Pipe
API	5L	1	2	3.1	X60QS	—	Seamless & Welded Pipe
API	5L	1	2	11.1	X65	—	Seamless & Welded Pipe
API	5L	1	2	2.1	X65M	—	Welded Pipe
API	5L	1	2	2.1	X65MO	—	Welded Pipe
API	5L	1	2	2.1	X65MS	—	Welded Pipe
API	5L	1	2	3.1	X65Q	—	Seamless & Welded Pipe
API	5L	1	2	3.1	X65QO	—	Seamless & Welded Pipe
API	5L	1	2	3.1	X65QS	—	Seamless & Welded Pipe
API	5L	1	3	11.1	X70	—	Seamless & Welded Pipe
API	5L	1	3	2.2	X70M	—	Welded Pipe
API	5L	1	3	2.2	X70MO	—	Welded Pipe
API	5L	1	3	2.2	X70MS	—	Welded Pipe
API	5L	1	3	3.1	X70Q	—	Seamless & Welded Pipe
API	5L	1	3	3.1	X70QO	—	Seamless & Welded Pipe
API	5L	1	3	3.1	X70QS	—	Seamless & Welded Pipe
API	5L	1	4	2.2	X80M	—	Welded Pipe
API	5L	1	4	2.2	X80MO	—	Welded Pipe
API	5L	1	4	3.1	X80Q	—	Seamless & Welded Pipe
API	5L	1	4	3.1	X80QO	—	Seamless & Welded Pipe
API	5LS	1	1	11.1	X46	—	Spiral Welded Pipe
AS							
ASTM	A945	1	2	1.2	50	—	Plate
AS							
ASTM	A945	1	2	1.3	65	—	Plate
AS	1548	1	2	1.2	5-490	—	Plate
AS	1548	1	1	1.2	7-430	—	Plate
AS	1548	1	1	1.2	7-460	—	Plate
AS	1548	1	2	1.2	7-490	—	Plate
AS	1548	1	1	1.2	PT430	—	Plate
AS	1548	1	1	1.2	PT460	—	Plate
AS	1548	1	2	1.2	PT490	—	Plate
AS/NZS	1594	1	1	1.1	HA1	—	Plate, Sheet, & Strip
AS/NZS	1594	1	1	1.1	HA200	—	Plate, Sheet, & Strip

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
AS/NZS	1594	1	1	1.1	HA250	—	Plate, Sheet, & Strip
AS/NZS	1594	1	1	1.1	HA250/1	—	Plate, Sheet, & Strip
AS/NZS	1594	1	1	1.1	HA3	—	Plate, Sheet, & Strip
AS/NZS	1594	1	1	1.2	HA300	—	Plate, Sheet, & Strip
AS/NZS	1594	1	1	1.2	HA300/1	—	Plate, Sheet, & Strip
AS/NZS	1594	1	1	1.2	HA350	—	Plate, Sheet, & Strip
AS/NZS	1594	1	1	2.1	HA400	—	Plate, Sheet, & Strip
AS/NZS	1594	1	1	1.1	HA4N	—	Plate, Sheet, & Strip
AS/NZS	1594	1	1	1.1	HU250	—	Plate, Sheet, & Strip
AS/NZS	1594	1	1	1.2	HU300	—	Plate, Sheet, & Strip
AS/NZS	1594	1	1	1.2	HU300/1	—	Plate, Sheet, & Strip
AS/NZS	1594	1	1	1.4	HW350	—	Plate, Sheet, & Strip
AS/NZS	1594	1	1	1.2	XF300	—	Plate, Sheet, & Strip
AS/NZS	1594	1	1	2.1	XF400	—	Plate, Sheet, & Strip
AS/NZS	1594	1	3	2.2	XF500	—	Plate, Sheet, & Strip
AS/NZS	3597	11B	—	3.1	700PV	—	Plate
AS/NZS	3678	1	1	1.1	200	—	Plate
AS/NZS	3678	1	1	1.2	250	—	Plate
AS/NZS	3678	1	1	1.2	250L15	—	Plate
AS/NZS	3678	1	2	1.2	300	—	Plate
AS/NZS	3678	1	2	1.2	300L15	—	Plate
AS/NZS	3678	1	2	1.2	350	—	Plate
AS/NZS	3678	1	2	1.2	350L15	—	Plate
AS/NZS	3678	1	2	1.3	400	—	Plate
AS/NZS	3678	1	2	1.3	400L15	—	Plate
AS/NZS	3678	1	2	1.3	450	—	Plate
AS/NZS	3678	1	2	1.3	450L15	—	Plate
AS/NZS	3678	3	1	1.4	WR350	—	Plate
AS/NZS	3678	3	1	1.4	WR350L0	—	Plate
AS/NZS	3679.1	1	1	1.1	250	—	Bar & Sections
AS/NZS	3679.1	1	1	1.1	250L0	—	Bar & Sections
AS/NZS	3679.1	1	1	1.1	250L15	—	Bar & Sections
AS/NZS	3679.1	1	2	1.2	300	—	Bar & Sections
AS/NZS	3679.1	1	2	1.2	300L0	—	Bar & Sections
AS/NZS	3679.1	1	2	1.2	300L15	—	Bar & Sections
AS/NZS	3679.1	1	2	1.2	350	—	Bar & Sections
AS/NZS	3679.1	1	2	1.2	350L0	—	Bar & Sections
AS/NZS	3679.1	1	2	1.2	350L15	—	Bar & Sections
AS/NZS	3679.1	1	2	1.3	400	—	Bar & Sections
AS/NZS	3679.1	1	2	1.3	400L0	—	Bar & Sections
AS/NZS	3679.1	1	2	1.3	400L15	—	Bar & Sections
ASTM	A27	1	1	11.1	60-30	J03000	Castings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM	A27	1	1	11.1	65-35	J03001	Castings
ASTM	A27	1	2	11.1	70-36	J03501	Castings
ASTM	A27	1	2	1.1	70-40	J02501	Castings
ASTM	A27	1	1	1.1	U-60-30	J03000	Castings
ASTM/ASME	A/SA-31	1	1	11.1	B	K03100	Rivets
ASTM/ASME	A/SA-36	1	1	11.1	—	—	Bar
ASTM/ASME	A/SA-36	1	1	11.1	—	K02595	Plates
ASTM/ASME	A/SA-36	1	1	11.1	—	K02596	Plates
ASTM/ASME	A/SA-36	1	1	11.1	—	K02597	Plates
ASTM/ASME	A/SA-36	1	1	1.1	—	K02598	Plates
ASTM/ASME	A/SA-36	1	1	1.1	—	K02599	Plates
ASTM/ASME	A/SA-36	1	1	11.1	—	K02600	Shapes
ASTM/ASME	A/SA-53	1	1	1.1	E, A	K02504	Resistance Welded Pipe
ASTM/ASME	A/SA-53	1	1	11.1	E, B	K03005	Resistance Welded Pipe
ASTM/ASME	A/SA-53	1	1	11.1	F	K03005	Furnace Welded Pipe
ASTM/ASME	A/SA-53	1	1	1.1	S, A	K02504	Seamless Pipe
ASTM/ASME	A/SA-53	1	1	11.1	S, B	K03005	Seamless Pipe
ASTM/ASME	A/SA-105	1	2	11.1	—	K03504	Flanges & Fittings
ASTM/ASME	A/SA-106	1	1	1.1	A	K02501	Seamless Pipe
ASTM/ASME	A/SA-106	1	1	11.1	B	K03006	Seamless Pipe
ASTM/ASME	A/SA-106	1	2	11.1	C	K03501	Seamless Pipe
ASTM	A108	1	1	1.1	1015 CW	G10150	Bar
ASTM	A108	1	1	1.1	1018 CW	G10180	Bar
ASTM	A108	1	1	1.1	1020 CW	G10200	Bar
ASTM	A108	3	3	4.1	8620 CW	G86200	Bar
ASTM	A131	1	1	1.1	A	—	Plate, Shapes, Bar, & Rivets
ASTM	A131	1	2	1.2	AH32	—	Plate, Shapes, Bar, & Rivets
ASTM	A131	1	2	1.2	AH36	—	Plate, Shapes, Bar, & Rivets
ASTM	A131	1	1	1.1	B	—	Plate, Shapes, Bar, & Rivets
ASTM	A131	1	1	1.1	CS	—	Plate, Shapes, Bar, & Rivets
ASTM	A131	1	1	1.1	D	—	Plate, Shapes, Bar, & Rivets
ASTM	A131	1	2	1.2	DH32	—	Plate, Shapes, Bar, & Rivets
ASTM	A131	1	2	1.2	DH36	—	Plate, Shapes, Bar, & Rivets
ASTM	A131	1	1	1.1	DS	—	Plate, Shapes, Bar, & Rivets
ASTM	A131	1	2	1.1	E	—	Plate, Shapes, Bar, & Rivets
ASTM	A131	1	2	1.2	EH32	—	Plate, Shapes, Bar, & Rivets
ASTM	A131	1	2	1.2	EH36	—	Plate, Shapes, Bar, & Rivets
ASTM/ASME	A/SA-134	1	1	1.1	SA283, A	K01400	Welded Pipe
ASTM/ASME	A/SA-134	1	1	1.1	SA283, B	K01702	Welded Pipe
ASTM/ASME	A/SA-134	1	1	1.1	SA283, C	K02401	Welded Pipe
ASTM/ASME	A/SA-134	1	1	11.1	SA283, D	K02702	Welded Pipe
ASTM/ASME	A/SA-134	1	1	1.1	SA285, A	K01700	Welded Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-134	1	1	1.1	SA285, B	K02200	Welded Pipe
ASTM/ASME	A/SA-134	1	1	11.1	SA285, C	K02801	Welded Pipe
ASTM/ASME	A/SA-134	1	1	1.1	SA36	K02599	Welded Pipe
ASTM/ASME	A/SA-135	1	1	1.1	A	K02509	E.R.W. Pipe
ASTM/ASME	A/SA-135	1	1	11.1	B	K03018	E.R.W. Pipe
ASTM	A139	1	1	1.1	A	K02508	Welded Pipe
ASTM	A139	1	1	11.1	B	K03003	Welded Pipe
ASTM	A139	1	1	11.1	C	K03004	Welded Pipe
ASTM	A139	1	1	11.1	D	K03010	Welded Pipe
ASTM	A139	1	1	11.1	E	K03012	Welded Pipe
ASTM	A148	4	3	—	90-60	D50600	Castings
ASTM	A161	1	1	—	Low Carbon	K01504	Tube
ASTM	A161	3	1	1.1	T1	K11522	Tube
ASTM	A167	8	1	8.1	302B	S30215	Plate, Sheet, & Strip
ASTM	A167	8	2	8.2	308	S30800	Plate, Sheet, & Strip
ASTM	A167	8	2	8.2	309	S30900	Plate, Sheet, & Strip
ASTM	A167	8	2	8.2	310	S31000	Plate, Sheet, & Strip
ASTM/ASME	A/SA-178	1	1	1.1	A	K01200	E.R.W. Tube
ASTM/ASME	A/SA-178	1	1	11.1	C	K03503	E.R.W. Tube
ASTM/ASME	A/SA-178	1	2	11.1	D	K02709	E.R.W. Tube
ASTM/ASME	A/SA-179	1	1	1.1	—	K01200	Seamless Tube
ASTM/ASME	A/SA-181	1	1	11.1	Cl. 60	K03502	Pipe Flange & Fittings
ASTM/ASME	A/SA-181	1	2	11.1	Cl. 70	K03502	Pipe Flange & Fittings
ASTM/ASME	A/SA-182	8	4	8.2	—	S32053	Forgings
ASTM/ASME	A/SA-182	10H	1	10.1	—	S32202	Forgings
ASTM/ASME	A/SA-182	3	2	1.1	F1	K12822	Forgings
ASTM/ASME	A/SA-182	8	2	8.1	F10	S33100	Forgings
ASTM/ASME	A/SA-182	4	1	5.1	F11, Cl. 1	K11597	Forgings
ASTM/ASME	A/SA-182	4	1	5.1	F11, Cl. 2	K11572	Forgings
ASTM/ASME	A/SA-182	4	1	5.1	F11, Cl. 3	K11572	Forgings
ASTM/ASME	A/SA-182	4	1	5.1	F12, Cl. 1	K11562	Forgings
ASTM/ASME	A/SA-182	4	1	5.1	F12, Cl. 2	K11564	Forgings
ASTM/ASME	A/SA-182	3	2	4.2	F2	K12122	Forgings
ASTM/ASME	A/SA-182	5A	1	5.2	F21	K31545	Forgings
ASTM/ASME	A/SA-182	5A	1	5.2	F22, Cl. 1	K21590	Forgings
ASTM/ASME	A/SA-182	5A	1	5.2	F22, Cl. 3	K21590	Forgings
ASTM/ASME	A/SA-182	5C	1	6.2	F22V	K31835	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F304	S30400	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F304	S30400	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F304H	S30409	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F304H	S30409	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F304L	S30403	Forgings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-182	8	1	8.1	F304L	S30403	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F304LN	S30453	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F304LN	S30453	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F304N	S30451	Forgings
ASTM/ASME	A/SA-182	8	2	8.2	F310	S31000	Forgings
ASTM/ASME	A/SA-182	8	2	8.2	F310	S31000	Forgings
ASTM/ASME	A/SA-182	8	2	8.2	F310MoLN	S31050	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F316	S31600	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F316	S31600	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F316H	S31609	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F316H	S31609	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F316L	S31603	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F316L	S31603	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F316LN	S31653	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F316LN	S31653	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F316N	S31651	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F317	S31700	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F317	S31700	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F317L	S31703	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F317L	S31703	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F321	S32100	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F321	S32100	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F321H	S32109	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F321H	S32109	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F347	S34700	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F347	S34700	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F347H	S34709	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F347H	S34709	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F348	S34800	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F348	S34800	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F348H	S34809	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F348H	S34809	Forgings
ASTM/ASME	A/SA-182	5C	1	6.2	F3V	K31830	Forgings
ASTM/ASME	A/SA-182	5C	1	6.2	F3VCb	K31390	Forgings
ASTM/ASME	A/SA-182	6	2	7.2	F429	S42900	Forgings
ASTM/ASME	A/SA-182	7	2	7.1	F430	S43000	Forgings
ASTM/ASME	A/SA-182	8	4	8.2	F44	S31254	Forgings
ASTM/ASME	A/SA-182	8	2	8.2	F45	S30815	Forgings
ASTM/ASME	A/SA-182	8	1	8.1	F46	S30600	Forgings
ASTM/ASME	A/SA-182	8	4	8.3	F49	S34565	Forgings
ASTM/ASME	A/SA-182	5B	1	5.3	F5	K41545	Forgings
ASTM/ASME	A/SA-182	10H	1	10.2	F50	S31200	Forgings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-182	10H	1	10.1	F51	S31803	Forgings
ASTM/ASME	A/SA-182	10H	1	10.2	F53	S32750	Forgings
ASTM/ASME	A/SA-182	10H	1	10.2	F54	S39274	Forgings
ASTM/ASME	A/SA-182	10H	1	10.1	F55	S32760	Forgings
ASTM/ASME	A/SA-182	5B	1	5.3	F5a	K42544	Forgings
ASTM/ASME	A/SA-182	10H	1	10.1	F60	S32205	Forgings
ASTM/ASME	A/SA-182	10H	1	10.2	F61	S32550	Forgings
ASTM/ASME	A/SA-182	6	1	7.2	F6a, Cl. 1	S41000	Forgings
ASTM/ASME	A/SA-182	6	3	7.2	F6a, Cl. 2	S41000	Forgings
ASTM/ASME	A/SA-182	6	3	7.2	F6a, Cl. 3	S41000	Forgings
ASTM/ASME	A/SA-182	6	3	7.2	F6a, Cl. 4	S41000	Forgings
ASTM/ASME	A/SA-182	6	3	7.2	F6b	S41026	Forgings
ASTM/ASME	A/SA-182	6	4	7.2	F6NM	S41500	Forgings
ASTM/ASME	A/SA-182	5B	1	5.4	F9	K90941	Forgings
ASTM/ASME	A/SA-182	15E	1	6.4	F91	K90901	Forgings
ASTM/ASME	A/SA-182	15E	1	6.4	F92	K92460	Forgings
ASTM/ASME	A/SA-182	9A	1	9.1	FR	K22035	Forgings
ASTM/ASME	A/SA-182	8	3	8.3	FXM-11	S21904	Forgings
ASTM/ASME	A/SA-182	8	3	8.3	FXM-19	S20910	Forgings
ASTM/ASME	A/SA-182	10I	1	7.1	FXM-27Cb	S44627	Forgings
ASTM/ASME	A/SA-192	1	1	1.1	—	K01201	Seamless Tube
ASTM	A199	4	1	5.1	T11	K11597	Seamless Tube
ASTM	A199	5A	1	—	T21	K31545	Seamless Tube
ASTM	A199	5A	1	5.2	T22	K21590	Seamless Tube
ASTM	A199	5A	1	—	T4	K31509	Seamless Tube
ASTM	A199	5B	1	5.3	T5	K41545	Seamless Tube
ASTM	A199	5B	1	5.4	T9	K81590	Seamless Tube
ASTM	A199	15E	1	6.4	T91	K90901	Seamless Tube
ASTM	A200	5A	1	—	T21	K31545	Tube
ASTM	A200	5A	1	5.2	T22	K21590	Tube
ASTM	A200	5A	1	—	T4	K31509	Tube
ASTM/ASME	A/SA-202	4	1	4.2	A	K11742	Plate
ASTM/ASME	A/SA-202	4	1	4.2	B	K12542	Plate
ASTM/ASME	A/SA-203	9A	1	9.1	A	K21703	Plate
ASTM/ASME	A/SA-203	9A	1	9.1	B	K22103	Plate
ASTM/ASME	A/SA-203	9B	1	9.2	D	K31718	Plate
ASTM/ASME	A/SA-203	9B	1	9.2	E	K32018	Plate
ASTM/ASME	A/SA-203	9B	1	9.2	F	—	Plate
ASTM/ASME	A/SA-203	9B	1	9.2	F	—	Plate
ASTM/ASME	A/SA-204	3	1	1.1	A	K11820	Plate
ASTM/ASME	A/SA-204	3	2	1.1	B	K12020	Plate
ASTM/ASME	A/SA-204	3	2	1.2	C	K12320	Plate

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-209	3	1	1.1	T1	K11522	Seamless Tube
ASTM/ASME	A/SA-209	3	1	1.1	T1a	K12023	Seamless Tube
ASTM/ASME	A/SA-209	3	1	1.1	T1b	K11422	Seamless Tube
ASTM/ASME	A/SA-210	1	1	11.1	A-1	K02707	Seamless Tube
ASTM/ASME	A/SA-210	1	2	11.1	C	K03501	Seamless Tube
ASTM	A211	1	1	1.1	A570-30	K02502	Welded Pipe
ASTM	A211	1	1	1.1	A570-33	K02502	Welded Pipe
ASTM	A211	1	1	1.1	A570-40	K02502	Welded Pipe
ASTM/ASME	A/SA-213	8	2	8.2	310	S31000	Seamless Tube
ASTM/ASME	A/SA-213	8	2	8.2	S30815	S30815	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	S32615	S32615	Seamless Tube
ASTM/ASME	A/SA-213	8	4	8.3	S34565	S34565	Seamless Tube
ASTM/ASME	A/SA-213	4	1	5.1	T11	K11597	Seamless Tube
ASTM/ASME	A/SA-213	4	1	5.1	T12	K11562	Seamless Tube
ASTM/ASME	A/SA-213	10B	1	4.1	T17	K12047	Seamless Tube
ASTM/ASME	A/SA-213	3	1	4.2	T2	K11547	Seamless Tube
ASTM/ASME	A/SA-213	5A	1	5.2	T21	K31545	Seamless Tube
ASTM/ASME	A/SA-213	5A	1	5.2	T22	K21590	Seamless Tube
ASTM/ASME	A/SA-213	5B	1	5.3	T5	K41545	Seamless Tube
ASTM/ASME	A/SA-213	5B	1	5.3	T5b	K51545	Seamless Tube
ASTM/ASME	A/SA-213	5B	1	5.3	T5c	K41245	Seamless Tube
ASTM/ASME	A/SA-213	5B	1	5.4	T9	K90941	Seamless Tube
ASTM/ASME	A/SA-213	15E	1	6.4	T91	K90901	Seamless Tube
ASTM/ASME	A/SA-213	15E	1	6.4	T92	K92460	Seamless Tube
ASTM/ASME	A/SA-213	8	3	8.3	TP201	S20100	Seamless Tube
ASTM/ASME	A/SA-213	8	3	8.3	TP202	S20200	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP304	S30400	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP304H	S30409	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP304L	S30403	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP304LN	S30453	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP304N	S30451	Seamless Tube
ASTM/ASME	A/SA-213	8	2	8.2	TP309Cb	S30940	Seamless Tube
ASTM/ASME	A/SA-213	8	2	8.2	TP309H	S30909	Seamless Tube
ASTM/ASME	A/SA-213	8	2	8.2	TP309HCb	S30941	Seamless Tube
ASTM/ASME	A/SA-213	8	2	8.2	TP309S	S30908	Seamless Tube
ASTM/ASME	A/SA-213	8	2	8.2	TP310Cb	S31040	Seamless Tube
ASTM/ASME	A/SA-213	8	2	8.2	TP310H	S31009	Seamless Tube
ASTM/ASME	A/SA-213	8	2	8.2	TP310HCb	S31041	Seamless Tube
ASTM/ASME	A/SA-213	8	3	8.2	TP310HCbN	S31042	Seamless Tube
ASTM/ASME	A/SA-213	8	2	8.2	TP310MoLN	S31050	Seamless Tube
ASTM/ASME	A/SA-213	8	2	8.2	TP310MoLN	S31050	Seamless Tube
ASTM/ASME	A/SA-213	8	2	8.2	TP310S	S31008	Seamless Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-213	8	1	8.1	TP316	S31600	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP316H	S31609	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP316L	S31603	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP316LN	S31653	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP316N	S31651	Seamless Tube
ASTM	A213	8	1	8.1	TP316Ti	S31635	Seamless Tube
ASTM	A213	8	1	8.1	TP317	S31700	Seamless Tube
ASTM	A213	8	1	8.1	TP317L	S31703	Seamless Tube
ASTM/ASME	A/SA-213	8	4	8.1	TP317LM	S31725	Seamless Tube
ASTM/ASME	A/SA-213	8	4	8.1	TP317LMN	S31726	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP321	S32100	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP321H	S32109	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP347	S34700	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP347H	S34709	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP347HFG	S34710	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP347LN	S34751	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP348	S34800	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	TP348H	S34809	Seamless Tube
ASTM/ASME	A/SA-213	8	1	8.1	XM-15	S38100	Seamless Tube
ASTM/ASME	A/SA-213	8	3	8.3	XM-19	S20910	Seamless Tube
ASTM/ASME	A/SA-214	1	1	1.1	—	K01807	E.R.W. Tube
ASTM/ASME	A/SA-216	1	1	1.1	WCA	J02502	Castings
ASTM/ASME	A/SA-216	1	2	1.1	WCB	J03002	Castings
ASTM/ASME	A/SA-216	1	2	1.1	WCC	J02503	Castings
ASTM/ASME	A/SA-217	5B	1	5.4	C12	J82090	Castings
ASTM	A217	15E	1	6.4	C12A	J84090	Castings
ASTM/ASME	A/SA-217	5B	1	5.3	C5	J42045	Castings
ASTM/ASME	A/SA-217	6	3	7.2	CA15	J91150	Castings
ASTM/ASME	A/SA-217	3	1	1.1	WC1	J12524	Castings
ASTM/ASME	A/SA-217	4	1	9.1	WC4	J12082	Castings
ASTM/ASME	A/SA-217	4	1	4.2	WC5	J22000	Castings
ASTM/ASME	A/SA-217	4	1	5.1	WC6	J12072	Castings
ASTM/ASME	A/SA-217	5A	1	5.2	WC9	J21890	Castings
ASTM/ASME	A/SA-225	10A	1	4.1	C	K12524	Plate
ASTM/ASME	A/SA-225	10A	1	2.1	D	K12004	Plate
ASTM/ASME	A/SA-225	10A	1	2.1	D	K12004	Plate
ASTM	A226	1	1	1.1	—	K01201	E.R.W. Tube
ASTM/ASME	A/SA-234	3	1	11.2	WP1	K12821	Piping Fittings
ASTM/ASME	A/SA-234	4	1	5.1	WP11, Cl.1	—	Piping Fittings
ASTM/ASME	A/SA-234	4	1	5.1	WP11, Cl.2	—	Piping Fittings
ASTM/ASME	A/SA-234	4	1	5.1	WP11, Cl.3	—	Piping Fittings
ASTM/ASME	A/SA-234	4	1	5.1	WP12, Cl.1	K12062	Piping Fittings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-234	4	1	5.1	WP12, Cl. 2	K12062	Piping Fittings
ASTM/ASME	A/SA-234	5A	1	5.2	WP22, Cl. 1	K21590	Piping Fittings
ASTM/ASME	A/SA-234	5A	1	5.2	WP22, Cl. 3	K21590	Piping Fittings
ASTM/ASME	A/SA-234	5B	1	5.3	WP5, Cl. 1	K41545	Piping Fittings
ASTM/ASME	A/SA-234	5B	1	5.3	WP5, Cl. 3	K41545	Piping Fittings
ASTM/ASME	A/SA-234	5B	1	5.4	WP9, Cl. 1	K90941	Piping Fittings
ASTM/ASME	A/SA-234	5B	1	5.4	WP9, Cl. 3	K90941	Piping Fittings
ASTM/ASME	A/SA-234	15E	1	6.4	WP91	K90901	Piping Fittings
ASTM/ASME	A/SA-234	1	1	11.1	WPB	K03006	Piping Fittings
ASTM/ASME	A/SA-234	1	2	11.1	WPC	K03501	Piping Fittings
ASTM/ASME	A/SA-234	9A	1	9.1	WPR	K22035	Piping Fittings
ASTM/ASME	A/SA-240	8	3	8.3	—	S20400	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	45	—	8.2	—	S31277	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10H	1	10.1	—	S32003	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	4	8.2	—	S32053	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10H	1	10.1	—	S32101	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10H	1	10.1	—	S32101	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10H	1	10.1	—	S32202	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	3	8.3	201-1	S20100	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	3	8.3	201-2	S20100	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	3	8.3	201LN	S20153	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	3	8.3	202	S20200	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10H	1	10.1	2205	S32205	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	301	S30100	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	302	S30200	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	304	S30400	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	304H	S30409	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	304L	S30403	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	304LN	S30453	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	304N	S30451	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	305	S30500	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	2	8.2	309Cb	S30940	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	2	8.2	309H	S30909	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	2	8.2	309Hcb	S30941	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	2	8.2	309S	S30908	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	2	8.2	310Cb	S31040	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	2	8.2	310H	S31009	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	2	8.2	310Hcb	S31041	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	2	8.2	310MoLN	S31050	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	2	8.2	310MoLN	S31050	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	2	8.2	310S	S31008	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	316	S31600	Plate, Sheet, & Strip

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-240	8	1	8.1	316Cb	S31640	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	316H	S31609	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	316L	S31603	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	316LN	S31653	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	316N	S31651	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	316Ti	S31635	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	317	S31700	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	317L	S31703	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	321	S32100	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	321H	S32109	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10H	1	10.2	329	S32900	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	347	S34700	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	347H	S34709	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	348	S34800	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	348H	S34809	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	7	1	7.1	405	S40500	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	7	1	7.1	409	S40910	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	7	1	7.1	409	S40920	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	7	1	7.1	409	S40930	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	6	1	7.2	410	S41000	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	7	1	7.2	410S	S41008	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	6	2	7.2	429	S42900	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	7	2	7.1	430	S43000	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	7	2	7.1	439	S43035	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	3	8.1	S21800	S21800	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	S30600	S30600	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	S30601	S30601	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	2	8.2	S30815	S30815	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10H	1	10.2	S31200	S31200	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	4	8.2	S31254	S31254	Sheet & Strip
ASTM/ASME	A/SA-240	8	4	8.2	S31254	S31254	Plate
ASTM/ASME	A/SA-240	10H	1	10.2	S31260	S31260	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	45	—	8.2	S31277	S31277	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	4	8.1	S31725	S31725	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	4	8.1	S31726	S31726	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	S31753	S31753	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10H	1	10.1	S31803	S31803	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10H	1	10.2	S32550	S32550	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	S32615	S32615	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10H	1	10.2	S32750	S32750	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10H	1	10.2	S32760	S32760	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10H	1	10.2	S32906	S32906	Plate, Sheet, & Strip

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-240	10H	1	10.2	S32906	S32906	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10H	1	10.2	S32950	S32950	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	4	8.3	S34565	S34565	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	6	4	7.2	S41500	S41500	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	7	2	7.1	S43932	S43932	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	7	2	7.1	S44400	S44400	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10I	1	7.1	S44635	S44635	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10K	1	7.1	S44660	S44660	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10J	1	7.1	S44700	S44700	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10K	1	7.1	S44800	S44800	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	1	8.1	XM-15	S38100	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	3	8.3	XM-17	S21600	Plate
ASTM/ASME	A/SA-240	8	3	8.3	XM-17	S21600	Sheet & Strip
ASTM/ASME	A/SA-240	8	3	8.3	XM-18	S21603	Plate
ASTM/ASME	A/SA-240	8	3	8.3	XM-18	S21603	Sheet & Strip
ASTM/ASME	A/SA-240	8	3	8.3	XM-19	S20910	Sheet & Strip
ASTM/ASME	A/SA-240	8	3	8.3	XM-19	S20910	Plate
ASTM/ASME	A/SA-240	8	1	8.1	XM-21	S30452	Plate
ASTM/ASME	A/SA-240	8	1	8.1	XM-21	S30452	Sheet & Strip
ASTM/ASME	A/SA-240	10I	1	7.1	XM-27	S44627	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	8	3	8.3	XM-29	S24000	Plate, Sheet, & Strip
ASTM/ASME	A/SA-240	10I	1	7.1	XM-33	S44626	Plate, Sheet, & Strip
ASTM	A242	1	2	1.2	1	K11510	Plate, Bar, & Shapes
ASTM	A242	1	2	1.2	1	K11510	Plate, Bar, & Shapes
ASTM	A242	1	2	1.2	1	K11510	Plate, Bar, & Shapes
ASTM/ASME	A/SA-249	8	4	8.2	—	S32053	Welded Tube
ASTM/ASME	A/SA-249	8	2	8.2	S30815	S30815	Welded Tube
ASTM/ASME	A/SA-249	8	4	8.2	S31254	S31254	Welded Tube
ASTM/ASME	A/SA-249	8	4	8.2	S31254	S31254	Welded Tube
ASTM/ASME	A/SA-249	8	4	8.1	S31725	S31725	Welded Tube
ASTM/ASME	A/SA-249	8	4	8.1	S31726	S31726	Welded Tube
ASTM/ASME	A/SA-249	8	3	8.3	TP 201	S20100	Welded Tube
ASTM/ASME	A/SA-249	8	3	8.3	TP 202	S20200	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP XM-15	S38100	Welded Tube
ASTM/ASME	A/SA-249	8	3	8.3	TP XM-19	S20910	Welded Tube
ASTM/ASME	A/SA-249	8	3	8.3	TP XM-29	S24000	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP304	S30400	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP304H	S30409	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP304L	S30403	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP304LN	S30453	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP304N	S30451	Welded Tube
ASTM/ASME	A/SA-249	8	2	8.2	TP309	S30900	Welded Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-249	8	2	8.2	TP309Cb	S30940	Welded Tube
ASTM/ASME	A/SA-249	8	2	8.2	TP309H	S30909	Welded Tube
ASTM/ASME	A/SA-249	8	2	8.2	TP309HCb	S30941	Welded Tube
ASTM/ASME	A/SA-249	8	2	8.2	TP309S	S30908	Welded Tube
ASTM/ASME	A/SA-249	8	2	8.2	TP310Cb	S31040	Welded Tube
ASTM/ASME	A/SA-249	8	2	8.2	TP310H	S31009	Welded Tube
ASTM/ASME	A/SA-249	8	2	8.2	TP310HCb	S31041	Welded Tube
ASTM/ASME	A/SA-249	8	2	8.2	TP310MoLN	S31050	Welded Tube
ASTM/ASME	A/SA-249	8	2	8.2	TP310MoLN	S31050	Welded Tube
ASTM/ASME	A/SA-249	8	2	8.2	TP310S	S31008	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP316	S31600	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP316H	S31609	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP316L	S31603	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP316LN	S31653	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP316N	S31651	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP317	S31700	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP317L	S31703	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP321	S32100	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP321H	S32109	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP347	S34700	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP347H	S34709	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP348	S34800	Welded Tube
ASTM/ASME	A/SA-249	8	1	8.1	TP348H	S34809	Welded Tube
ASTM/ASME	A/SA-250	3	1	1.1	T1	K11522	E.R.W. Tube
ASTM/ASME	A/SA-250	4	1	5.1	T11	K11597	E.R.W. Tube
ASTM/ASME	A/SA-250	4	1	5.1	T12	K11562	E.R.W. Tube
ASTM/ASME	A/SA-250	3	1	1.1	T1a	K12023	E.R.W. Tube
ASTM/ASME	A/SA-250	3	1	1.1	T1b	K11422	E.R.W. Tube
ASTM/ASME	A/SA-250	3	1	4.2	T2	K11547	E.R.W. Tube
ASTM/ASME	A/SA-250	5A	1	5.2	T22	K21590	E.R.W. Tube
ASTM	A252	1	1	—	1	—	Pipe Piles
ASTM	A252	1	1	—	2	—	Pipe Piles
ASTM	A252	1	1	—	3	—	Pipe Piles
ASTM/ASME	A/SA-266	1	1	11.1	1	K03506	Forgings
ASTM/ASME	A/SA-266	1	2	11.1	2	K03506	Forgings
ASTM/ASME	A/SA-266	1	2	11.2	3	K05001	Forgings
ASTM/ASME	A/SA-266	1	2	11.1	4	K03017	Forgings
ASTM/ASME	A/SA-268	7	2	7.1	18Cr-2Mo	S44400	Seamless & Welded Tube
ASTM/ASME	A/SA-268	10I	1	7.1	25-4-4	S44635	Seamless & Welded Tube
ASTM/ASME	A/SA-268	10K	1	7.1	26-3-3	S44660	Seamless & Welded Tube
ASTM/ASME	A/SA-268	10J	1	7.1	29-4	S44700	Seamless & Welded Tube
ASTM/ASME	A/SA-268	10K	1	7.1	29-4-2	S44800	Seamless & Welded Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-268	7	1	7.1	S40800	S40800	Seamless & Welded Tube
ASTM/ASME	A/SA-268	6	4	7.2	S41500	S41500	Seamless & Welded Tube
ASTM/ASME	A/SA-268	10J	1	7.1	S44735	S44735	Seamless & Welded Tube
ASTM/ASME	A/SA-268	10I	1	7.1	TP 446-1	S44600	Seamless & Welded Tube
ASTM/ASME	A/SA-268	10I	1	7.1	TP 446-2	S44600	Seamless & Welded Tube
ASTM/ASME	A/SA-268	10I	1	7.1	TP XM-27	S44627	Seamless & Welded Tube
ASTM/ASME	A/SA-268	10I	1	7.1	TP XM-33	S44626	Seamless & Welded Tube
ASTM/ASME	A/SA-268	7	1	7.1	TP405	S40500	Seamless & Welded Tube
ASTM/ASME	A/SA-268	7	1	7.1	TP409	S40900	Seamless & Welded Tube
ASTM/ASME	A/SA-268	6	1	7.2	TP410	S41000	Seamless & Welded Tube
ASTM/ASME	A/SA-268	6	2	7.2	TP429	S42900	Seamless & Welded Tube
ASTM/ASME	A/SA-268	7	2	7.1	TP430	S43000	Seamless & Welded Tube
ASTM/ASME	A/SA-268	7	2	7.1	TP430Ti	S43036	Seamless & Welded Tube
ASTM/ASME	A/SA-268	7	2	7.1	TP439	S43035	Seamless & Welded Tube
ASTM	A269	8	1	8.1	TP304	S30400	Seamless & Welded Tube
ASTM	A269	8	1	8.1	TP304L	S30403	Seamless & Welded Tube
ASTM	A269	8	1	8.1	TP304LN	S30453	Seamless & Welded Tube
ASTM	A269	8	1	8.1	TP316	S31600	Seamless & Welded Tube
ASTM	A269	8	1	8.1	TP316L	S31603	Seamless & Welded Tube
ASTM	A269	8	1	8.1	TP316LN	S31653	Seamless & Welded Tube
ASTM	A269	8	1	8.1	TP317	S31700	Seamless & Welded Tube
ASTM	A269	8	1	8.1	TP321	S32100	Seamless & Welded Tube
ASTM	A269	8	1	8.1	TP347	S34700	Seamless & Welded Tube
ASTM	A269	8	1	8.1	TP348	S34800	Seamless & Welded Tube
ASTM	A269	8	3	8.3	TPXM-10	S21900	Seamless & Welded Tube
ASTM	A269	8	3	8.3	TPXM-11	S21904	Seamless & Welded Tube
ASTM	A269	8	3	8.3	TPXM-15	S38100	Seamless & Welded Tube
ASTM	A269	8	3	8.3	TPXM-19	S20910	Seamless & Welded Tube
ASTM	A269	8	3	8.3	TPXM-29	S24000	Seamless & Welded Tube
ASTM	A270	8	1	8.1	TP304	S30400	Seamless & Welded Tube
ASTM	A271	8	1	8.1	TP304	S30400	Seamless Tube
ASTM	A271	8	1	8.1	TP304H	S30409	Seamless Tube
ASTM	A271	8	1	8.1	TP316	S31600	Seamless Tube
ASTM	A271	8	1	8.1	TP316H	S31609	Seamless Tube
ASTM	A271	8	1	8.1	TP321	S32100	Seamless Tube
ASTM	A271	8	1	8.1	TP321H	S32109	Seamless Tube
ASTM	A271	8	1	8.1	TP347	S34700	Seamless Tube
ASTM	A271	8	1	8.1	TP347H	S34709	Seamless Tube
ASTM	A276	10H	1	10.1	—	S32101	Bar
ASTM/ASME	A/SA-276	10H	1	10.1	—	S32550	Bars & Shapes
ASTM/ASME	A/SA-276	10H	1	10.1	S32205	S32205	Bar
ASTM/ASME	A/SA-276	8	1	8.1	TP304	S30400	Bar

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-276	8	1	8.1	TP304L	S30403	Bar
ASTM/ASME	A/SA-276	8	1	8.1	TP316	S31600	Bar
ASTM/ASME	A/SA-276	8	1	8.1	TP316L	S31603	Bar
ASTM/ASME	A/SA-276	6	1	7.2	TP410	S41000	Bar
ASTM/ASME	A/SA-283	1	1	1.1	A	K01400	Plate
ASTM/ASME	A/SA-283	1	1	1.1	B	K01702	Plate
ASTM/ASME	A/SA-283	1	1	1.1	C	K02401	Plate
ASTM/ASME	A/SA-283	1	1	1.1	D	K02702	Plate
ASTM/ASME	A/SA-285	1	1	1.1	A	K01700	Plate
ASTM/ASME	A/SA-285	1	1	1.1	B	K02200	Plate
ASTM/ASME	A/SA-285	1	1	11.1	C	K02801	Plate
ASTM	A297	8	2	8.2	HE	J93403	Castings
ASTM	A297	8	2	8.2	HF	J92603	Castings
ASTM	A297	8	2	8.2	HH	J93503	Castings
ASTM	A297	8	2	8.2	HI	J94003	Castings
ASTM	A297	8	2	8.2	HK	J94224	Castings
ASTM/ASME	A/SA-299	1	2	11.1	A	K02803	Plate
ASTM/ASME	A/SA-299	1	3	11.1	B	K02803	Plate
ASTM/ASME	A/SA-312	8	4	8.2	—	S32053	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	S30600	S30600	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	2	8.2	S30815	S30815	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	4	8.2	S31254	S31254	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	4	8.2	S31254	S31254	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	4	8.1	S31725	S31725	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	4	8.1	S31726	S31726	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	S32615	S32615	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	4	8.3	S34565	S34565	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	3	8.3	TP XM-11	S21904	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP XM-15	S38100	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	3	8.3	TP XM-19	S20910	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	3	8.3	TP XM-29	S24000	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP304	S30400	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP304H	S30409	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP304L	S30403	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP304LN	S30453	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP304N	S30451	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	2	8.2	TP309Cb	S30940	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	2	8.2	TP309H	S30909	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	2	8.2	TP309HCb	S30941	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	2	8.2	TP309S	S30908	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	2	8.2	TP310Cb	S31040	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	2	8.2	TP310H	S31009	Seamless & Welded Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-312	8	2	8.2	TP310HCb	S31041	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	2	8.2	TP310MoLN	S31050	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	2	8.2	TP310MoLN	S31050	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	2	8.2	TP310S	S31008	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP316	S31600	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP316H	S31609	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP316L	S31603	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP316LN	S31653	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP316N	S31651	Seamless & Welded Pipe
ASTM	A312	8	1	8.1	TP316Ti	S31635	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP317	S31700	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP317L	S31703	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP321	S32100	Seamless Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP321	S32100	Seamless Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP321H	S32109	Seamless Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP321H	S32109	Seamless Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP347	S34700	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP347H	S34709	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP347LN	S34751	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP348	S34800	Seamless & Welded Pipe
ASTM/ASME	A/SA-312	8	1	8.1	TP348H	S34809	Seamless & Welded Pipe
ASTM/ASME	A/SA-333	1	1	11.1	1	K03008	Seamless & Welded Pipe
ASTM/ASME	A/SA-333	1	3	11.1	10	—	Seamless & Welded Pipe
ASTM/ASME	A/SA-333	9B	1	9.2	3	K31918	Seamless & Welded Pipe
ASTM/ASME	A/SA-333	4	2	4.1	4	K11267	Seamless & Welded Pipe
ASTM/ASME	A/SA-333	1	1	11.1	6	K03006	Seamless & Welded Pipe
ASTM/ASME	A/SA-333	9A	1	9.1	7	K21903	Seamless & Welded Pipe
ASTM/ASME	A/SA-333	11A	1	9.3	8	K81340	Seamless & Welded Pipe
ASTM/ASME	A/SA-333	9A	1	9.1	9	K22035	Seamless & Welded Pipe
ASTM/ASME	A/SA-334	1	1	11.1	1	K03008	Welded Tube
ASTM/ASME	A/SA-334	9B	1	9.2	3	K31918	Welded Tube
ASTM/ASME	A/SA-334	1	1	11.1	6	K03006	Welded Tube
ASTM/ASME	A/SA-334	9A	1	9.1	7	K21903	Welded Tube
ASTM/ASME	A/SA-334	11A	1	9.3	8	K81340	Welded Tube
ASTM/ASME	A/SA-334	9A	1	9.1	9	K22035	Welded Tube
ASTM/ASME	A/SA-335	3	1	1.1	P1	K11522	Seamless Pipe
ASTM/ASME	A/SA-335	4	1	5.1	P11	K11597	Seamless Pipe
ASTM/ASME	A/SA-335	4	1	5.1	P12	K11562	Seamless Pipe
ASTM/ASME	A/SA-335	3	1	—	P15	K11578	Seamless Pipe
ASTM/ASME	A/SA-335	3	1	4.2	P2	K11547	Seamless Pipe
ASTM/ASME	A/SA-335	5A	1	5.2	P21	K31545	Seamless Pipe
ASTM/ASME	A/SA-335	5A	1	5.2	P22	K21590	Seamless Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-335	5B	1	5.3	P5	K41545	Seamless Pipe
ASTM/ASME	A/SA-335	5B	1	5.3	P5b	K51545	Seamless Pipe
ASTM/ASME	A/SA-335	5B	1	5.3	P5c	K41245	Seamless Pipe
ASTM/ASME	A/SA-335	5B	1	5.4	P9	K90941	Seamless Pipe
ASTM/ASME	A/SA-335	15E	1	6.4	P91	K90901	Seamless Pipe
ASTM/ASME	A/SA-335	15E	1	6.4	P92	K92460	Seamless Pipe
ASTM/ASME	A/SA-336	3	2	1.1	F1	K12520	Forgings
ASTM/ASME	A/SA-336	4	1	5.1	F11, Cl. 1	K11597	Forgings
ASTM/ASME	A/SA-336	4	1	5.1	F11, Cl. 2	K11572	Forgings
ASTM/ASME	A/SA-336	4	1	5.1	F11, Cl. 3	K11572	Forgings
ASTM/ASME	A/SA-336	4	1	5.1	F12	K11564	Forgings
ASTM/ASME	A/SA-336	5A	1	5.2	F21, Cl. 1	K31545	Forgings
ASTM/ASME	A/SA-336	5A	1	5.2	F21, Cl. 3	K31545	Forgings
ASTM/ASME	A/SA-336	5A	1	5.2	F22, Cl. 1	K21590	Forgings
ASTM/ASME	A/SA-336	5A	1	5.2	F22, Cl. 3	K21590	Forgings
ASTM/ASME	A/SA-336	5C	1	6.2	F22V	K31835	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F304	S30400	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F304H	S30409	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F304L	S30403	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F304LN	S30453	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F304N	S30451	Forgings
ASTM/ASME	A/SA-336	8	2	8.2	F310	S31000	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F316	S31600	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F316H	S31609	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F316L	S31603	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F316LN	S31653	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F316N	S31651	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F321	S32100	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F321H	S32109	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F347	S34700	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F347H	S34709	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F348	S34800	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F348H	S34809	Forgings
ASTM/ASME	A/SA-336	5C	1	6.2	F3V	K31830	Forgings
ASTM/ASME	A/SA-336	5C	1	6.2	F3VCb	K31390	Forgings
ASTM/ASME	A/SA-336	8	1	8.1	F46	S30600	Forgings
ASTM/ASME	A/SA-336	5B	1	5.3	F5	K41545	Forgings
ASTM/ASME	A/SA-336	5B	1	5.3	F5A	K42544	Forgings
ASTM/ASME	A/SA-336	6	3	7.2	F6	S41000	Forgings
ASTM/ASME	A/SA-336	5B	1	5.4	F9	K90941	Forgings
ASTM/ASME	A/SA-336	15E	1	6.4	F91	K90901	Forgings
ASTM/ASME	A/SA-336	8	3	8.3	FXM-11	S21904	Forgings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-336	8	3	8.3	FXM-19	S20910	Forgings
ASTM/ASME	A/SA-336	10I	1	7.1	FXM-27Cb	S44627	Forgings
ASTM/ASME	A/SA-350	1	1	11.1	LF1	K03009	Forgings
ASTM/ASME	A/SA-350	1	2	11.1	LF2	K03011	Forgings
ASTM/ASME	A/SA-350	9B	1	9.2	LF3	K32025	Forgings
ASTM/ASME	A/SA-350	9A	1	9.1	LF5, Cl. 1	K13050	Forgings
ASTM/ASME	A/SA-350	9A	1	9.1	LF5, Cl. 2	K13050	Forgings
ASTM/ASME	A/SA-350	1	1	1.2	LF6, Cl. 1	K12202	Forgings
ASTM/ASME	A/SA-350	1	3	4.1	LF6, Cl. 2	K12202	Forgings
ASTM/ASME	A/SA-350	1	2	1.3	LF6, Cl. 3	K12202	Forgings
ASTM/ASME	A/SA-350	1	2	3.3	LF787, Cl. 2	K20747	Forgings
ASTM/ASME	A/SA-350	1	3	3.3	LF787, Cl. 3	K20747	Forgings
ASTM/ASME	A/SA-350	9A	1	9.1	LF9	K22036	Forgings
ASTM	A351	6	3	7.2	CA15	J91150	Castings
ASTM/ASME	A/SA-351	10H	1	10.2	CD3MWCuN	J93380	Castings
ASTM/ASME	A/SA-351	10H	1	10.2	CD4MCu	J93370	Castings
ASTM/ASME	A/SA-351	8	2	8.2	CE20N	J92802	Castings
ASTM/ASME	A/SA-351	10H	1	10.2	CE8MN	J93345	Castings
ASTM/ASME	A/SA-351	8	1	8.1	CF10	J92590	Castings
ASTM/ASME	A/SA-351	8	1	8.1	CF10M	J92901	Castings
ASTM/ASME	A/SA-351	8	1	8.1	CF10MC	J92971	Castings
ASTM/ASME	A/SA-351	8	1	8.1	CF3	J92500	Castings
ASTM/ASME	A/SA-351	8	1	8.1	CF3A	J92500	Castings
ASTM/ASME	A/SA-351	8	1	8.1	CF3M	J92800	Castings
ASTM/ASME	A/SA-351	8	1	8.1	CF8	J92600	Castings
ASTM/ASME	A/SA-351	8	1	8.1	CF8A	J92600	Castings
ASTM/ASME	A/SA-351	8	1	8.1	CF8C	J92710	Castings
ASTM/ASME	A/SA-351	8	1	8.1	CF8M	J92900	Castings
ASTM/ASME	A/SA-351	8	3	8.3	CG6MMN	J93790	Castings
ASTM/ASME	A/SA-351	8	1	8.1	CG8M	J93000	Castings
ASTM/ASME	A/SA-351	8	2	8.2	CH10	J93401	Castings
ASTM/ASME	A/SA-351	8	2	8.2	CH20	J93402	Castings
ASTM/ASME	A/SA-351	8	2	8.2	CH8	J93400	Castings
ASTM/ASME	A/SA-351	8	2	8.2	CK20	J94202	Castings
ASTM/ASME	A/SA-351	8	4	8.2	CK3MCuN	J93254	Castings
ASTM/ASME	A/SA-351	45	—	8.2	CN3MN	J94651	Castings
ASTM/ASME	A/SA-351	8	2	8.2	HK30	J94203	Castings
ASTM/ASME	A/SA-351	8	2	8.2	HK40	J94204	Castings
ASTM/ASME	A/SA-351	45	—	45	HT30	N08603	Castings
ASTM/ASME	A/SA-352	6	4	7.2	CA6NM	J91540	Castings
ASTM/ASME	A/SA-352	3	1	1.1	LC1	J12522	Castings
ASTM/ASME	A/SA-352	9A	1	9.1	LC2	J22500	Castings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-352	11A	5	9.2	LC2-1	J42215	Castings
ASTM/ASME	A/SA-352	9B	1	9.3	LC3	J31550	Castings
ASTM/ASME	A/SA-352	9C	1	9.3	LC4	J41500	Castings
ASTM/ASME	A/SA-352	1	1	11.1	LCA	J02504	Castings
ASTM/ASME	A/SA-352	1	1	1.1	LCB	J03003	Castings
ASTM/ASME	A/SA-352	1	2	11.1	LCC	J02505	Castings
ASTM/ASME	A/SA-353	11A	1	9.3	—	K81340	Plate
ASTM	A356	1	2	11.1	1	J03502	Castings
ASTM	A356	5A	1	5.2	10	J22090	Castings
ASTM	A356	15E	1	6.4	12A	J84090	Castings
ASTM	A356	3	1	1.1	2	J12523	Castings
ASTM	A356	4	1	5.1	6	J12073	Castings
ASTM	A356	4	1	6.2	8	J11697	Castings
ASTM	A356	4	1	6.2	9	J21610	Castings
ASTM/ASME	A/SA-358	8	4	8.2	—	S32053	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	1	8.1	304	S30400	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	1	8.1	304H	S30409	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	1	8.1	304L	S30403	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	1	8.1	304LN	S30453	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	1	8.1	304N	S30451	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	2	8.2	309	S30900	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	2	8.2	309Cb	S30940	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	2	8.2	309S	S30908	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	2	8.2	310	S31000	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	2	8.2	310Cb	S31040	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	2	8.2	310S	S31008	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	1	8.1	316	S31600	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	1	8.1	316H	S31609	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	1	8.1	316L	S31603	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	1	8.1	316LN	S31653	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	1	8.1	316N	S31651	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	1	8.1	321	S32100	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	1	8.1	347	S34700	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	1	8.1	348	S34800	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	2	8.2	S30815	S30815	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	4	8.2	S31254	S31254	Fusion Welded Tube
ASTM/ASME	A/SA-358	8	4	8.1	S31725	S31725	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	4	8.1	S31726	S31726	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	3	8.3	XM-19	S20910	Fusion Welded Pipe
ASTM/ASME	A/SA-358	8	3	8.3	XM-29	S24000	Fusion Welded Pipe
ASTM	A366	1	1	1.1	CS	—	Sheet
ASTM/ASME	A/SA-369	3	1	1.1	FP1	K11522	Forged Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-369	4	1	5.1	FP11	K11597	Forged Pipe
ASTM/ASME	A/SA-369	4	1	5.1	FP12	K11562	Forged Pipe
ASTM/ASME	A/SA-369	3	1	4.2	FP2	K11547	Forged Pipe
ASTM/ASME	A/SA-369	5A	1	5.2	FP21	K31545	Forged Pipe
ASTM/ASME	A/SA-369	5A	1	5.2	FP22	K21590	Forged Pipe
ASTM/ASME	A/SA-369	5B	1	5.3	FP5	K41545	Forged Pipe
ASTM/ASME	A/SA-369	5B	1	5.4	FP9	K90941	Forged Pipe
ASTM/ASME	A/SA-369	15E	1	6.4	FP91	K90901	Forged Pipe
ASTM/ASME	A/SA-369	15E	1	6.4	FP92	K92460	Forged Pipe
ASTM/ASME	A/SA-369	1	1	1.1	FPA	K02501	Forged Pipe
ASTM/ASME	A/SA-369	1	1	1.1	FPB	K03006	Forged Pipe
ASTM/ASME	A/SA-372	1	1	11.1	A	K03002	Forgings
ASTM/ASME	A/SA-372	1	2	11.1	B	K04001	Forgings
ASTM/ASME	A/SA-376	8	1	8.1	16-8-2H	S16800	Seamless Pipe
ASTM/ASME	A/SA-376	8	4	8.1	S31725	S31725	Seamless Pipe
ASTM/ASME	A/SA-376	8	4	8.1	S31726	S31726	Seamless Pipe
ASTM/ASME	A/SA-376	8	4	8.3	S34565	S34565	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP304	S30400	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP304	S30400	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP304H	S30409	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP304LN	S30453	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP304N	S30451	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP316	S31600	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP316H	S31609	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP316LN	S31653	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP316N	S31651	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP321	S32100	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP321	S32100	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP321H	S32109	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP321H	S32109	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP347	S34700	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP347H	S34709	Seamless Pipe
ASTM/ASME	A/SA-376	8	1	8.1	TP348	S34800	Seamless Pipe
ASTM	A381	1	1	11.1	Y35	—	Welded Pipe
ASTM	A381	1	1	11.1	Y42	—	Welded Pipe
ASTM	A381	1	1	11.1	Y46	—	Welded Pipe
ASTM	A381	1	1	11.1	Y48	—	Welded Pipe
ASTM	A381	1	1	11.1	Y50	—	Welded Pipe
ASTM	A381	1	2	11.1	Y52	—	Welded Pipe
ASTM	A381	1	2	11.1	Y56	—	Welded Pipe
ASTM	A381	1	2	11.1	Y60	—	Welded Pipe
ASTM	A381	1	3	11.1	Y65	—	Welded Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-387	4	1	5.1	11, Cl. 1	K11789	Plate
ASTM/ASME	A/SA-387	4	1	5.1	11, Cl. 2	K11789	Plate
ASTM/ASME	A/SA-387	4	1	5.1	12, Cl. 1	K11757	Plate
ASTM/ASME	A/SA-387	4	1	5.1	12, Cl. 2	K11757	Plate
ASTM/ASME	A/SA-387	3	1	4.2	2, Cl. 1	K12143	Plate
ASTM/ASME	A/SA-387	3	2	4.2	2, Cl. 2	K12143	Plate
ASTM/ASME	A/SA-387	5A	1	5.2	21, Cl. 1	K31545	Plate
ASTM/ASME	A/SA-387	5A	1	5.2	21, Cl. 2	K31545	Plate
ASTM/ASME	A/SA-387	5A	1	5.2	22, Cl. 1	K21590	Plate
ASTM/ASME	A/SA-387	5A	1	5.2	22, Cl. 2	K21590	Plate
ASTM/ASME	A/SA-387	5B	1	5.3	5, Cl. 1	K41545	Plate
ASTM/ASME	A/SA-387	5B	1	5.3	5, Cl. 2	K41545	Plate
ASTM/ASME	A/SA-387	5B	1	5.4	9, Cl. 1	K90941	Plate
ASTM/ASME	A/SA-387	5B	1	5.4	9, Cl. 2	K90941	Plate
ASTM/ASME	A/SA-387	15E	1	5.4	91, Cl. 2	K90901	Plate
ASTM	A389	4	1	6.2	C23	J12080	Castings
ASTM	A389	4	1	6.2	C24	J12092	Castings
ASTM/ASME	A/SA-403	8	4	8.2	—	S31254	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	4	8.2	—	S32053	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	4	8.3	S34565	S34565	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP304	S30400	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP304H	S30409	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP304L	S30403	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP304LN	S30453	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP304N	S30451	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	2	8.2	WP309	S30900	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	2	8.2	WP310	S31000	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	2	8.2	WP310S	S31008	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP316	S31600	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP316H	S31609	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP316L	S31603	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP316LN	S31653	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP316N	S31651	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP317	S31700	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP317L	S31703	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP321	S32100	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP321H	S32109	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP347	S34700	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP347H	S34709	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP348	S34800	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	1	8.1	WP348H	S34809	Wrought Piping Fittings
ASTM/ASME	A/SA-403	8	3	8.3	WPXM-19	S20910	Wrought Piping Fittings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM	A405	4	1	6.2	P24	K11591	Seamless Pipe
ASTM/ASME	A/SA-409	8	4	8.2	—	S32053	Welded Pipe
ASTM/ASME	A/SA-409	8	2	8.2	S30815	S30815	Welded Pipe
ASTM/ASME	A/SA-409	8	4	8.2	S31254	S31254	Welded Pipe
ASTM/ASME	A/SA-409	8	4	8.1	S31725	S31725	Welded Pipe
ASTM/ASME	A/SA-409	8	4	8.1	S31726	S31726	Welded Pipe
ASTM/ASME	A/SA-409	8	4	8.3	S34565	S34565	Welded Pipe
ASTM/ASME	A/SA-409	8	1	8.1	TP304	S30400	Welded Pipe
ASTM/ASME	A/SA-409	8	1	8.1	TP304L	S30403	Welded Pipe
ASTM/ASME	A/SA-409	8	2	8.2	TP309Cb	S30940	Welded Pipe
ASTM/ASME	A/SA-409	8	2	8.2	TP309S	S30908	Welded Pipe
ASTM/ASME	A/SA-409	8	2	8.2	TP310Cb	S31040	Welded Pipe
ASTM/ASME	A/SA-409	8	2	8.2	TP310S	S31008	Welded Pipe
ASTM/ASME	A/SA-409	8	1	8.1	TP316	S31600	Welded Pipe
ASTM/ASME	A/SA-409	8	1	8.1	TP316L	S31603	Welded Pipe
ASTM/ASME	A/SA-409	8	1	8.1	TP317	S31700	Welded Pipe
ASTM/ASME	A/SA-409	8	1	8.1	TP321	S32100	Welded Pipe
ASTM/ASME	A/SA-409	8	1	8.1	TP347	S34700	Welded Pipe
ASTM/ASME	A/SA-409	8	1	8.1	TP348	S34800	Welded Pipe
ASTM/ASME	A/SA-414	1	1	1.1	A	K01501	Sheet
ASTM/ASME	A/SA-414	1	1	1.1	B	K02201	Sheet
ASTM/ASME	A/SA-414	1	1	1.1	C	K02503	Sheet
ASTM/ASME	A/SA-414	1	1	1.1	D	K02505	Sheet
ASTM/ASME	A/SA-414	1	1	11.1	E	K02704	Sheet
ASTM/ASME	A/SA-414	1	2	11.1	F	K03102	Sheet
ASTM/ASME	A/SA-414	1	2	11.1	G	K03103	Sheet
ASTM/ASME	A/SA-420	9B	1	9.2	WPL3	K31918	Piping Fittings
ASTM/ASME	A/SA-420	1	1	11.1	WPL6	K03006	Piping Fittings
ASTM/ASME	A/SA-420	11A	1	9.3	WPL8	K81340	Piping Fittings
ASTM/ASME	A/SA-420	9A	1	9.1	WPL9	K22035	Piping Fittings
ASTM/ASME	A/SA-423	4	2	5.1	1	K11535	Seamless & Welded Tube
ASTM/ASME	A/SA-423	4	2	5.1	2	K11540	Seamless & Welded Tube
ASTM/ASME	A/SA-426	3	1	1.1	CP1	J12521	Centrifugal Cast Pipe
ASTM/ASME	A/SA-426	4	1	5.1	CP11	J12072	Centrifugal Cast Pipe
ASTM/ASME	A/SA-426	4	1	5.1	CP12	J11562	Centrifugal Cast Pipe
ASTM/ASME	A/SA-426	3	1	1.1	CP15	J11522	Centrifugal Cast Pipe
ASTM/ASME	A/SA-426	3	1	4.2	CP2	J11547	Centrifugal Cast Pipe
ASTM/ASME	A/SA-426	5A	1	5.2	CP21	J31545	Centrifugal Cast Pipe
ASTM/ASME	A/SA-426	5A	1	5.2	CP22	J21890	Centrifugal Cast Pipe
ASTM/ASME	A/SA-426	5B	1	5.3	CP5	J42045	Centrifugal Cast Pipe
ASTM/ASME	A/SA-426	5B	1	5.3	CP5b	J51545	Centrifugal Cast Pipe
ASTM/ASME	A/SA-426	5B	1	5.4	CP9	J82090	Centrifugal Cast Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-426	6	3	7.2	CPCA15	J91150	Centrifugal Cast Pipe
ASTM	A430	8	1	8.1	FP16-8-2H	S16800	Forged Pipe
ASTM	A430	8	1	8.1	FP304	S30400	Forged Pipe
ASTM	A430	8	1	8.1	FP304H	S30409	Forged Pipe
ASTM	A430	8	1	8.1	FP304N	S30451	Forged Pipe
ASTM	A430	8	1	8.1	FP316	S31600	Forged Pipe
ASTM	A430	8	1	8.1	FP316H	S31609	Forged Pipe
ASTM	A430	8	1	8.1	FP316N	S31651	Forged Pipe
ASTM	A430	8	1	8.1	FP321	S32100	Forged Pipe
ASTM	A430	8	1	8.1	FP321H	S32109	Forged Pipe
ASTM	A430	8	1	8.1	FP347	S34700	Forged Pipe
ASTM	A430	8	1	8.1	FP347H	S34709	Forged Pipe
ASTM	A441	1	2	—	—	K12211	Plate & Bar
ASTM	A441	1	2	—	—	K12211	Plate & Bar
ASTM	A441	1	2	—	—	K12211	Plate & Bar
ASTM	A441	1	2	—	—	K12211	Plate & Bar
ASTM	A441	1	2	—	Group 1	—	Shapes
ASTM	A441	1	2	—	Group 2	—	Shapes
ASTM	A441	1	2	—	Group 3	—	Shapes
ASTM	A441	1	2	—	Group 4	—	Shapes
ASTM	A441	1	2	—	Group 5	—	Shapes
ASTM/ASME	A/SA-451	8	2	8.2	CPE20N	J92802	Centrifugal Cast Pipe
ASTM/ASME	A/SA-451	8	1	8.1	CPF10MC	J92971	Centrifugal Cast Pipe
ASTM/ASME	A/SA-451	8	1	8.1	CPF3	J92500	Centrifugal Cast Pipe
ASTM/ASME	A/SA-451	8	1	8.1	CPF3A	J92500	Centrifugal Cast Pipe
ASTM/ASME	A/SA-451	8	1	8.1	CPF3M	J92800	Centrifugal Cast Pipe
ASTM/ASME	A/SA-451	8	1	8.1	CPF8	J92600	Centrifugal Cast Pipe
ASTM/ASME	A/SA-451	8	1	8.1	CPF8A	J92600	Centrifugal Cast Pipe
ASTM/ASME	A/SA-451	8	1	8.1	CPF8C	J92710	Centrifugal Cast Pipe
ASTM/ASME	A/SA-451	8	1	8.1	CPF8M	J92900	Centrifugal Cast Pipe
ASTM/ASME	A/SA-451	8	2	8.2	CPH10	J93402	Centrifugal Cast Pipe
ASTM/ASME	A/SA-451	8	2	8.2	CPH20	J93402	Centrifugal Cast Pipe
ASTM/ASME	A/SA-451	8	2	8.2	CPH8	J93400	Centrifugal Cast Pipe
ASTM/ASME	A/SA-451	8	2	8.2	CPK20	J94202	Centrifugal Cast Pipe
ASTM	A452	8	1	8.1	TP304H	S30409	Centrifugal Cast Pipe
ASTM	A452	8	1	8.1	TP316H	S31609	Centrifugal Cast Pipe
ASTM	A452	8	1	8.1	TP347H	S34709	Centrifugal Cast Pipe
ASTM/ASME	A/SA-455	1	2	11.2	—	K03300	Plate
ASTM/ASME	A/SA-455	1	2	11.2	—	K03300	Plate
ASTM/ASME	A/SA-455	1	2	11.2	—	K03300	Plate
ASTM	A473	8	3	8.3	201	S20100	Forgings
ASTM	A473	8	3	8.3	202	S20200	Forgings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM	A473	8	1	8.1	302	S30200	Forgings
ASTM	A473	8	1	8.1	302B	S30215	Forgings
ASTM	A473	8	1	8.1	303	S30300	Forgings
ASTM	A473	8	1	8.1	303Se	S30323	Forgings
ASTM	A473	8	1	8.1	304	S30400	Forgings
ASTM	A473	8	1	8.1	304	S30400	Forgings
ASTM	A473	8	1	8.1	304L	S30403	Forgings
ASTM	A473	8	1	8.1	305	S30500	Forgings
ASTM	A473	8	2	8.2	308	S30800	Forgings
ASTM	A473	8	2	8.2	309	S30900	Forgings
ASTM	A473	8	2	8.2	309S	S30908	Forgings
ASTM	A473	8	2	8.2	310	S31000	Forgings
ASTM	A473	8	2	8.2	310S	S31008	Forgings
ASTM	A473	8	2	8.2	314	S31400	Forgings
ASTM	A473	8	1	8.1	316	S31600	Forgings
ASTM	A473	8	1	8.1	316	S31600	Forgings
ASTM	A473	8	1	8.1	316L	S31603	Forgings
ASTM	A473	8	1	8.1	317	S31700	Forgings
ASTM	A473	8	1	8.1	321	S32100	Forgings
ASTM	A473	8	1	8.1	347	S34700	Forgings
ASTM	A473	8	1	8.1	348	S34800	Forgings
ASTM	A473	6	1	7.1	403	S40300	Forgings
ASTM	A473	7	1	7.1	405	S40500	Forgings
ASTM	A473	6	1	7.2	410	S41000	Forgings
ASTM	A473	6	4	7.2	414	S41400	Forgings
ASTM	A473	6	2	7.2	420	S42000	Forgings
ASTM	A473	6	2	7.2	429	S42900	Forgings
ASTM	A473	7	2	7.1	430	S43000	Forgings
ASTM	A473	8	2	8.2	S30815	S30815	Forgings
ASTM	A473	8	3	8.3	XM-10	S21900	Forgings
ASTM	A473	8	3	8.3	XM-11	S21904	Forgings
ASTM/ASME	A/SA-479	10H	1	10.1	—	S31803	Bars & Shapes
ASTM/ASME	A/SA-479	8	4	8.2	—	S32053	Bars & Shapes
ASTM/ASME	A/SA-479	10H	1	10.1	—	S32101	Bars & Shapes
ASTM/ASME	A/SA-479	10H	1	10.1	—	S32202	Bars & Shapes
ASTM/ASME	A/SA-479	10H	1	10.1	2205	S32205	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	302	S30200	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	304	S30400	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	304H	S30409	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	304L	S30403	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	304LN	S30453	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	304N	S30451	Bars & Shapes

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-479	8	2	8.2	309Cb	S30940	Bars & Shapes
ASTM/ASME	A/SA-479	8	2	8.2	309S	S30908	Bars & Shapes
ASTM/ASME	A/SA-479	8	2	8.2	310Cb	S31040	Bars & Shapes
ASTM/ASME	A/SA-479	8	2	8.2	310S	S31008	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	316	S31600	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	316Cb	S31640	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	316H	S31609	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	316L	S31603	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	316LN	S31653	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	316N	S31651	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	316Ti	S31635	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	321	S32100	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	321H	S32109	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	347	S34700	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	347H	S34709	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	348	S34800	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	348H	S34809	Bars & Shapes
ASTM/ASME	A/SA-479	6	1	7.1	403	S40300	Bars & Shapes
ASTM/ASME	A/SA-479	7	1	7.1	405	S40500	Bars & Shapes
ASTM/ASME	A/SA-479	6	1	7.2	410	S41000	Bars & Shapes
ASTM/ASME	A/SA-479	6	4	7.2	414	S41400	Bars & Shapes
ASTM/ASME	A/SA-479	7	2	7.1	430	S43000	Bars & Shapes
ASTM/ASME	A/SA-479	7	2	7.1	439	S43035	Bars & Shapes
ASTM/ASME	A/SA-479	8	3	8.1	S21800	S21800	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	S30600	S30600	Bars & Shapes
ASTM/ASME	A/SA-479	8	2	8.2	S30815	S30815	Bars & Shapes
ASTM/ASME	A/SA-479	8	4	8.2	S31254	S31254	Bars & Shapes
ASTM/ASME	A/SA-479	8	4	8.1	S31725	S31725	Bars & Shapes
ASTM/ASME	A/SA-479	8	4	8.1	S31726	S31726	Bars & Shapes
ASTM/ASME	A/SA-479	10H	1	10.2	S32550	S32550	Bars & Shapes
ASTM/ASME	A/SA-479	8	1	8.1	S32615	S32615	Bars & Shapes
ASTM/ASME	A/SA-479	10H	1	10.2	S32750	S32750	Bars & Shapes
ASTM	A479	10H	1	10.2	S32906	S32906	Bars & Shapes
ASTM/ASME	A/SA-479	8	4	8.3	S34565	S34565	Bars & Shapes
ASTM/ASME	A/SA-479	6	4	7.2	S41500	S41500	Bars & Shapes
ASTM/ASME	A/SA-479	7	2	7.1	S44400	S44400	Bars & Shapes
ASTM/ASME	A/SA-479	10J	1	7.1	S44700	S44700	Bars & Shapes
ASTM/ASME	A/SA-479	10K	1	7.1	S44800	S44800	Bars & Shapes
ASTM/ASME	A/SA-479	8	3	8.3	XM-11	S21904	Bars & Shapes
ASTM/ASME	A/SA-479	8	3	8.3	XM-17	S21600	Bars & Shapes
ASTM/ASME	A/SA-479	8	3	8.3	XM-18	S21603	Bars & Shapes
ASTM/ASME	A/SA-479	8	3	8.3	XM-19	S20910	Bars & Shapes

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-479	10I	1	7.1	XM-27	S44627	Bars & Shapes
ASTM/ASME	A/SA-479	8	3	8.3	XM-29	S24000	Bars & Shapes
ASTM/ASME	A/SA-479	6	1	7.2	XM-30	S41040	Bars & Shapes
ASTM/ASME	A/SA-487	10A	1	2.1	1, Cl. A	J13002	Castings
ASTM/ASME	A/SA-487	10A	1	2.1	1, Cl. B	J13002	Castings
ASTM/ASME	A/SA-487	1	2	1.1	16, Cl. A	J31200	Castings
ASTM/ASME	A/SA-487	3	3	2.1	2, Cl. A	J13005	Castings
ASTM/ASME	A/SA-487	3	3	2.1	2, Cl. B	J13005	Castings
ASTM/ASME	A/SA-487	3	3	3.1	4, Cl. A	J13047	Castings
ASTM/ASME	A/SA-487	11A	3	3.1	4, Cl. B	J13047	Castings
ASTM/ASME	A/SA-487	3	3	3.1	4, Cl. C	J13047	Castings
ASTM/ASME	A/SA-487	11A	3	3.1	4, Cl. E	J13047	Castings
ASTM/ASME	A/SA-487	5C	1	5.2	8, Cl. A	J22091	Castings
ASTM/ASME	A/SA-487	5C	4	5.2	8, Cl. B	J22091	Castings
ASTM/ASME	A/SA-487	5C	4	5.2	8, Cl. C	J22091	Castings
ASTM/ASME	A/SA-487	6	3	7.2	CA15, Cl. B	J91171	Castings
ASTM/ASME	A/SA-487	6	3	7.2	CA15, Cl. C	J91150	Castings
ASTM/ASME	A/SA-487	6	3	7.2	CA15, Cl. D	J91171	Castings
ASTM/ASME	A/SA-487	6	3	7.2	CA15M, Cl. A	J91151	Castings
ASTM/ASME	A/SA-487	6	4	7.2	CA6NM, Cl. A	J91540	Castings
ASTM/ASME	A/SA-487	6	4	7.2	CA6NM, Cl. B	J91540	Castings
ASTM	A500	1	1	11.1	A	K03000	Seamless & Welded Tube
ASTM	A500	1	1	11.1	B	K03000	Seamless & Welded Tube
ASTM	A500	1	1	1.2	C	K02705	Seamless & Welded Tube
ASTM	A500	1	1	11.1	D	K03000	Seamless & Welded Tube
ASTM	A501	1	1	11.1	A	K03000	Seamless & Welded Tube
ASTM	A501	1	1	1.2	B	K03000	Seamless & Welded Tube
ASTM/ASME	A/SA-508	1	2	11.1	1	K13502	Forgings
ASTM/ASME	A/SA-508	1	2	11.1	1A	K13502	Forgings
ASTM/ASME	A/SA-508	3	3	3.1	2, Cl. 1	K12766	Forgings
ASTM/ASME	A/SA-508	3	3	3.1	2, Cl. 2	K12766	Forgings
ASTM/ASME	A/SA-508	5C	1	5.2	22, Cl. 3	K21590	Forgings
ASTM/ASME	A/SA-508	3	3	3.1	3, Cl. 1	K12042	Forgings
ASTM/ASME	A/SA-508	3	3	3.1	3, Cl. 2	K12042	Forgings
ASTM/ASME	A/SA-508	5C	1	6.2	3V	K31830	Forgings
ASTM/ASME	A/SA-508	5C	1	6.2	3VCb	K31390	Forgings
ASTM/ASME	A/SA-508	11A	5	3.1	4N, Cl. 1	K22375	Forgings
ASTM/ASME	A/SA-508	11B	10	3.1	4N, Cl. 2	K22375	Forgings
ASTM/ASME	A/SA-508	3	3	3.1	4N, Cl. 3	K22375	Forgings
ASTM/ASME	A/SA-508	11A	5	3.1	5, Cl. 1	K42365	Forgings
ASTM/ASME	A/SA-508	11B	10	3.1	5, Cl. 2	K42365	Forgings
ASTM	A511	8	1	8.1	MT 302	S30200	Seamless Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM	A511	8	1	8.1	MT 304	S30400	Seamless Tube
ASTM	A511	8	1	8.1	MT 304L	S30403	Seamless Tube
ASTM	A511	8	2	8.2	MT 309S	S30908	Seamless Tube
ASTM	A511	8	2	8.2	MT 310S	S31008	Seamless Tube
ASTM	A511	8	1	8.1	MT 316	S31600	Seamless Tube
ASTM	A511	8	1	8.1	MT 316L	S31603	Seamless Tube
ASTM	A511	8	1	8.1	MT 317	S31700	Seamless Tube
ASTM	A511	8	1	8.1	MT 321	S32100	Seamless Tube
ASTM	A511	8	1	8.1	MT 347	S34700	Seamless Tube
ASTM	A512	1	1	1.1	1008	G10080	Tube
ASTM	A512	1	1	1.1	1010	G10100	Tube
ASTM	A512	1	1	1.1	1012	G10120	Tube
ASTM	A512	1	1	1.1	1015	G10150	Tube
ASTM	A512	1	1	—	1016	G10160	Tube
ASTM	A512	1	1	1.1	1018	G10180	Tube
ASTM	A512	1	1	—	1019	G10190	Tube
ASTM	A512	1	1	1.1	1020	G10200	Tube
ASTM	A512	1	1	—	1021	G10210	Tube
ASTM	A512	1	2	11.1	1025	G10250	Tube
ASTM	A512	1	1	11.1	1026	G10260	Tube
ASTM	A512	1	2	11.1	1030	G10300	Tube
ASTM	A512	1	1	—	1110	G11100	Tube
ASTM	A512	1	1	—	1115	G11150	Tube
ASTM	A512	1	1	—	1117	G11170	Tube
ASTM	A512	1	1	1.1	MT 1010	G10100	Tube
ASTM	A512	1	1	1.1	MT 1015	G10150	Tube
ASTM	A512	1	1	1.1	MT 1020	G10200	Tube
ASTM	A512	1	1	1.1	MTX 1015	—	Tube
ASTM	A512	1	1	1.1	MTX 1020	—	Tube
ASTM/ASME	A/SA-513	1	1	1.1	1008	G10080	Tube
ASTM/ASME	A/SA-513	1	1	1.1	1010	G10100	Tube
ASTM/ASME	A/SA-513	1	1	1.1	1015	G10150	Tube
ASTM	A513	1	1	1.1	1015 CW	G10150	Tube
ASTM/ASME	A/SA-513	1	1	—	1017	G10170	Tube
ASTM/ASME	A/SA-513	1	1	1.1	1018	G10180	Tube
ASTM/ASME	A/SA-513	1	1	—	1019	G10190	Tube
ASTM/ASME	A/SA-513	1	1	1.1	1020	G10200	Tube
ASTM	A513	1	2	1.1	1020 CW	G10200	Tube
ASTM/ASME	A/SA-513	1	1	1.1	1021	G10210	Tube
ASTM/ASME	A/SA-513	1	1	1.1	1022	G10220	Tube
ASTM/ASME	A/SA-513	1	1	—	1023	G10230	Tube
ASTM/ASME	A/SA-513	1	1	—	1024	G10240	Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-513	1	2	11.1	1025	G10250	Tube
ASTM	A513	1	2	1.2	1025 CW	G10250	Tube
ASTM/ASME	A/SA-513	1	1	11.1	1026	G10260	Tube
ASTM	A513	1	3	11.1	1026 CW	G10260	Tube
ASTM/ASME	A/SA-513	1	2	11.1	1030	G10300	Tube
ASTM/ASME	A/SA-513	1	1	1.1	MT 1010	G10100	Tube
ASTM/ASME	A/SA-513	1	1	1.1	MT 1015	G10150	Tube
ASTM/ASME	A/SA-513	1	1	1.1	MT 1020	G10200	Tube
ASTM/ASME	A/SA-513	1	1	—	MTX 1015	—	Tube
ASTM/ASME	A/SA-513	1	1	—	MTX 1020	—	Tube
ASTM	A514	11B	1	3.1	A	K11856	Plate
ASTM	A514	11B	4	3.1	B	K11630	Plate
ASTM	A514	11B	6	3.1	C	K11511	Plate
ASTM	A514	11B	6	3.1	C	K11511	Plate
ASTM	A514	11B	2	3.1	E	K21604	Plate
ASTM	A514	11B	2	3.1	E	K21604	Plate
ASTM	A514	11B	3	3.1	F	K11576	Plate
ASTM	A514	11B	3	3.1	H	K11646	Plate
ASTM	A514	11B	6	3.1	J	K11625	Plate
ASTM	A514	11B	6	3.1	J	K11625	Plate
ASTM	A514	11B	6	3.1	K	K11523	Plate
ASTM	A514	11B	6	3.1	K	K11523	Plate
ASTM	A514	11B	10	3.1	M	K11683	Plate
ASTM	A514	11B	10	3.1	M	K11683	Plate
ASTM	A514	11B	10	3.1	M	K11683	Plate
ASTM	A514	11B	8	3.1	P	K21650	Plate
ASTM	A514	11B	8	3.1	P	K21650	Plate
ASTM	A514	11B	9	3.1	Q	—	Plate
ASTM	A514	11B	9	3.1	Q	—	Plate
ASTM	A514	11B	12	3.1	R	—	Plate
ASTM	A514	11B	12	3.1	R	—	Plate
ASTM	A514	11B	6	3.1	S	—	Plate
ASTM	A514	11B	6	3.1	T	—	Plate
ASTM	A514	11B	6	3.1	T	—	Plate
ASTM	A515	1	1	1.1	55	K02001	Plate
ASTM/ASME	A/SA-515	1	1	11.1	60	—	Plate
ASTM/ASME	A/SA-515	1	1	1.1	60	K02401	Plate
ASTM/ASME	A/SA-515	1	1	11.1	65	K02800	Plate
ASTM/ASME	A/SA-515	1	2	11.1	70	K03101	Plate
ASTM/ASME	A/SA-516	1	1	1.1	55	K01800	Plate
ASTM/ASME	A/SA-516	1	1	1.1	60	K02100	Plate
ASTM/ASME	A/SA-516	1	1	1.1	65	K02403	Plate

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-516	1	2	11.1	70	K02700	Plate
ASTM/ASME	A/SA-517	11B	1	3.1	A	K11856	Plate
ASTM/ASME	A/SA-517	11B	4	3.1	B	K11630	Plate
ASTM	A517	11B	14	3.1	C	K11511	Plate
ASTM/ASME	A/SA-517	11B	2	3.1	E	K21604	Plate
ASTM/ASME	A/SA-517	11B	2	3.1	E	K21604	Plate
ASTM/ASME	A/SA-517	11B	3	3.1	F	K11576	Plate
ASTM/ASME	A/SA-517	11B	3	3.1	H	K11646	Plate
ASTM	A517	11B	6	3.1	J	K11625	Plate
ASTM	A517	11B	6	3.1	K	K11523	Plate
ASTM	A517	11B	10	3.1	M	K11683	Plate
ASTM/ASME	A/SA-517	11B	8	3.1	P	K21650	Plate
ASTM/ASME	A/SA-517	11B	8	3.1	P	K21650	Plate
ASTM/ASME	A/SA-517	11B	9	3.1	Q	—	Plate
ASTM/ASME	A/SA-517	11B	9	3.1	Q	—	Plate
ASTM/ASME	A/SA-517	11B	6	3.1	S	—	Plate
ASTM	A517	11B	6	3.1	T	—	Plate
ASTM	A519	1	1	1.1	1008	G10080	Tube
ASTM	A519	1	1	1.1	1012	G10120	Tube
ASTM	A519	1	1	1.1	1015	G10150	Tube
ASTM	A519	1	1	—	1016	G10160	Tube
ASTM	A519	1	1	—	1017	G10170	Tube
ASTM	A519	1	1	1.1	1018	G10180	Tube
ASTM	A519	1	2	1.1	1018 CW	G10180	Tube
ASTM	A519	1	1	1.1	1018 HR	G10180	Tube
ASTM	A519	1	1	—	1019	G10190	Tube
ASTM	A519	1	1	1.1	1020	G10200	Tube
ASTM	A519	1	2	1.1	1020 CW	G10200	Tube
ASTM	A519	1	1	1.1	1020 HR	G10200	Tube
ASTM	A519	1	1	—	1021	G10210	Tube
ASTM	A519	1	1	1.1	1022	G10220	Tube
ASTM	A519	1	2	1.1	1022 CW	G10220	Tube
ASTM	A519	1	1	1.1	1022 HR	G10220	Tube
ASTM	A519	1	2	11.1	1025	G10250	Tube
ASTM	A519	1	2	1.2	1025 CW	G10250	Tube
ASTM	A519	1	1	1.1	1025 HR	G10250	Tube
ASTM	A519	1	1	—	1026	G10260	Tube
ASTM	A519	1	2	11.1	1026 CW	G10260	Tube
ASTM	A519	1	1	11.1	1026 HR	G10260	Tube
ASTM	A519	1	2	—	1030	G10300	Tube
ASTM	A519	11B	9	—	4130	G41300	Tube
ASTM	A519	11B	9	—	8630	G86300	Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM	A519	1	1	1.1	MT 1010	G10100	Tube
ASTM	A519	1	1	1.1	MT 1015	G10150	Tube
ASTM	A519	1	1	1.1	MT 1020	G10200	Tube
ASTM	A519	1	1	—	MTX 1015	—	Tube
ASTM	A519	1	1	—	MTX 1020	—	Tube
ASTM	A521	1	1	—	CC	—	Die Forging
ASTM	A521	1	1	—	CC1	—	Die Forging
ASTM	A521	1	2	—	CE	—	Die Forging
ASTM/ASME	A/SA-522	11A	1	9.3	I	K81340	Forgings
ASTM/ASME	A/SA-522	11A	1	9.3	II	K71340	Forgings
ASTM	A523	1	1	1.1	A	K02504	Pipe
ASTM	A523	1	1	11.1	B	K03005	Pipe
ASTM/ASME	A/SA-524	1	1	1.1	I	K02104	Seamless Pipe
ASTM/ASME	A/SA-524	1	1	1.1	II	K02104	Seamless Pipe
ASTM	A526	1	1	—	II	—	Galvanized Sheet
ASTM	A527	1	1	—	II	—	Galvanized Sheet
ASTM	A529	1	1	11.1	42	K02703	Plate, Bar, & Shapes
ASTM	A529	1	2	11.1	50	—	Plate, Bar, & Shapes
ASTM	A529	1	2	11.1	55	—	Plate, Bar, & Shapes
ASTM/ASME	A/SA-533	3	3	3.1	A, Cl. 1	K12521	Plate
ASTM/ASME	A/SA-533	3	3	3.1	A, Cl. 2	K12521	Plate
ASTM/ASME	A/SA-533	11A	4	3.1	A, Cl. 3	K12521	Plate
ASTM/ASME	A/SA-533	3	3	3.1	B, Cl. 1	K12539	Plate
ASTM/ASME	A/SA-533	3	3	3.1	B, Cl. 2	K12539	Plate
ASTM/ASME	A/SA-533	11A	4	3.2	B, Cl. 3	K12539	Plate
ASTM/ASME	A/SA-533	3	3	3.1	C, Cl. 1	K12554	Plate
ASTM/ASME	A/SA-533	3	3	3.1	C, Cl. 2	K12554	Plate
ASTM/ASME	A/SA-533	11A	4	3.2	C, Cl. 3	K12554	Plate
ASTM/ASME	A/SA-533	3	3	3.1	D, Cl. 1	K12529	Plate
ASTM/ASME	A/SA-533	3	3	3.1	D, Cl. 2	K12529	Plate
ASTM/ASME	A/SA-533	11A	4	3.1	D, Cl. 3	K12529	Plate
ASTM/ASME	A/SA-533	3	3	3.1	E, Cl. 1	K12554	Plate
ASTM/ASME	A/SA-533	3	3	3.1	E, Cl. 2	K12554	Plate
ASTM/ASME	A/SA-537	1	2	1.2	Cl. 1	K12437	Plate
ASTM/ASME	A/SA-537	1	2	1.2	Cl. 1	K12437	Plate
ASTM/ASME	A/SA-537	1	3	1.2	Cl. 2	K12437	Plate
ASTM/ASME	A/SA-537	1	3	1.2	Cl. 2	K12437	Plate
ASTM/ASME	A/SA-537	1	3	1.2	Cl. 2	K12437	Plate
ASTM/ASME	A/SA-537	1	3	1.2	Cl. 3	K12437	Plate
ASTM/ASME	A/SA-537	1	3	1.2	Cl. 3	K12437	Plate
ASTM/ASME	A/SA-537	1	3	1.2	Cl. 3	K12437	Plate
ASTM	A539	1	1	—	—	K01506	Coiled Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-541	1	2	11.1	1	K03506	Forgings
ASTM/ASME	A/SA-541	4	1	5.2	11, Cl. 4	K11572	Forgings
ASTM/ASME	A/SA-541	1	2	11.1	1A	K03020	Forgings
ASTM/ASME	A/SA-541	3	3	4.2	2, Cl.1	K12765	Forgings
ASTM/ASME	A/SA-541	3	3	4.2	2, Cl.2	K12765	Forgings
ASTM/ASME	A/SA-541	5C	1	5.2	22, Cl. 3	K21390	Forgings
ASTM/ASME	A/SA-541	5C	4	5.2	22, Cl. 4	K21390	Forgings
ASTM/ASME	A/SA-541	5C	5	5.2	22, Cl. 5	K21390	Forgings
ASTM/ASME	A/SA-541	5C	1	5.2	22V	K31835	Forgings
ASTM/ASME	A/SA-541	3	3	4.1	3, Cl. 1	K12045	Forgings
ASTM/ASME	A/SA-541	3	3	4.1	3, Cl. 2	K12045	Forgings
ASTM/ASME	A/SA-541	5C	1	6.2	3V	K31830	Forgings
ASTM/ASME	A/SA-541	5C	1	6.2	3VCb	K31390	Forgings
ASTM/ASME	A/SA-542	5C	4	5.2	A, Cl. 1	K21590	Plate
ASTM/ASME	A/SA-542	5C	5	5.2	A, Cl. 2	K21590	Plate
ASTM/ASME	A/SA-542	5C	3	5.2	A, Cl. 3	K21590	Plate
ASTM/ASME	A/SA-542	5C	1	5.2	A, Cl. 4	K21590	Plate
ASTM/ASME	A/SA-542	5C	1	5.2	A, Cl. 4a	K21590	Plate
ASTM/ASME	A/SA-542	5C	4	5.2	B, Cl. 1	K21590	Plate
ASTM/ASME	A/SA-542	5C	5	5.2	B, Cl. 2	K21590	Plate
ASTM/ASME	A/SA-542	5C	3	5.2	B, Cl. 3	K21590	Plate
ASTM/ASME	A/SA-542	5C	1	5.2	B, Cl. 4	K21590	Plate
ASTM/ASME	A/SA-542	5C	1	5.2	B, Cl. 4a	K21590	Plate
ASTM/ASME	A/SA-542	5C	4	6.2	C, Cl. 1	K31830	Plate
ASTM/ASME	A/SA-542	5C	5	6.2	C, Cl. 2	K31830	Plate
ASTM/ASME	A/SA-542	5C	3	6.2	C, Cl. 3	K31830	Plate
ASTM/ASME	A/SA-542	5C	1	6.2	C, Cl. 4	K31830	Plate
ASTM/ASME	A/SA-542	5C	1	6.2	C, Cl. 4a	K31830	Plate
ASTM/ASME	A/SA-542	5C	1	6.3	D, Cl. 4a	K31835	Plate
ASTM/ASME	A/SA-542	5C	1	6.2	E, Cl. 4a	K31390	Plate
ASTM/ASME	A/SA-543	11A	5	3.1	B Cl. 1	K42339	Plate
ASTM/ASME	A/SA-543	11B	10	3.1	B Cl. 2	K42339	Plate
ASTM/ASME	A/SA-543	3	3	3.1	B Cl. 3	K42339	Plate
ASTM/ASME	A/SA-543	11A	5	3.1	C Cl. 1	—	Plate
ASTM/ASME	A/SA-543	11B	10	3.1	C Cl. 2	—	Plate
ASTM/ASME	A/SA-543	3	3	3.1	C Cl. 3	—	Plate
ASTM/ASME	A/SA-553	11A	1	9.3	I	K81340	Plate
ASTM/ASME	A/SA-553	11A	1	9.3	II	K71340	Plate
ASTM	A554	8	1	8.1	MT 302	S30200	Welded Tube
ASTM	A554	8	1	8.1	MT 304	S30400	Welded Tube
ASTM	A554	8	1	8.1	MT 304L	S30403	Welded Tube
ASTM	A554	8	2	8.2	MT 309S	S30908	Welded Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM	A554	8	2	8.2	MT 309S-Cb	S30940	Welded Tube
ASTM	A554	8	2	8.2	MT 310S	S31008	Welded Tube
ASTM	A554	8	1	8.1	MT 316	S31600	Welded Tube
ASTM	A554	8	1	8.1	MT 316L	S31603	Welded Tube
ASTM	A554	8	1	8.1	MT 317	S31700	Welded Tube
ASTM	A554	8	1	8.1	MT 321	S32100	Welded Tube
ASTM	A554	8	1	8.1	MT 347	S34700	Welded Tube
ASTM/ASME	A/SA-556	1	1	1.1	A2	K01807	Seamless Tube
ASTM/ASME	A/SA-556	1	1	11.1	B2	K02707	Seamless Tube
ASTM/ASME	A/SA-556	1	2	11.1	C2	K03006	Seamless Tube
ASTM/ASME	A/SA-557	1	1	1.1	A2	K01807	E.R.W. Tube
ASTM/ASME	A/SA-557	1	1	11.1	B2	K03007	E.R.W. Tube
ASTM/ASME	A/SA-557	1	2	11.1	C2	K03505	E.R.W. Tube
ASTM/ASME	A/SA-562	1	1	1.1	—	K11224	Plate
ASTM	A569	1	1	1.1	30	K02502	Sheet & Strip
ASTM	A569	1	1	1.1	33	K02502	Sheet & Strip
ASTM	A569	1	1	1.1	36	K02502	Sheet & Strip
ASTM	A569	1	1	1.1	40	K02502	Sheet & Strip
ASTM	A569	1	1	1.2	45	K02502	Sheet & Strip
ASTM	A569	1	1	1.2	50	K02502	Sheet & Strip
ASTM	A570	1	1	1.1	30	K02502	Sheet & Strip
ASTM	A570	1	1	1.1	33	K02502	Sheet & Strip
ASTM	A570	1	1	1.1	36	K02502	Sheet & Strip
ASTM	A570	1	1	1.1	40	K02502	Sheet & Strip
ASTM	A570	1	1	1.2	45	K02502	Sheet & Strip
ASTM	A570	1	1	1.2	50	K02502	Sheet & Strip
ASTM	A570	1	1	1.3	55	K02502	Sheet & Strip
ASTM/ASME	A/SA-572	1	1	1.2	42	—	Plate & Shapes
ASTM/ASME	A/SA-572	1	1	1.2	50	—	Plate & Shapes
ASTM	A572	1	2	1.3	55	—	Plate, Sheet, Bar, & Shapes
ASTM/ASME	A/SA-572	1	2	11.1	60	—	Plate & Shapes
ASTM	A572	1	3	11.1	65	—	Plate, Sheet, Bar, & Shapes
ASTM	A573	1	1	11.1	58	—	Plate
ASTM	A573	1	1	11.1	65	—	Plate
ASTM	A573	1	2	11.1	70	—	Plate
ASTM	A575	1	1	1.1	M1008	—	Bar
ASTM	A575	1	1	1.1	M1010	—	Bar
ASTM	A575	1	1	1.1	M1012	—	Bar
ASTM	A575	1	1	1.1	M1015	—	Bar
ASTM	A575	1	1	1.1	M1017	—	Bar
ASTM	A575	1	1	11.1	M1020	—	Bar
ASTM	A575	1	1	11.1	M1023	—	Bar

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM	A575	1	1	11.1	M1025	—	Bar
ASTM	A576	1	1	1.1	G10080	—	Bar
ASTM	A576	1	1	1.1	G10100	—	Bar
ASTM	A576	1	1	1.1	G10120	—	Bar
ASTM	A576	1	1	1.1	G10150	—	Bar
ASTM	A576	1	1	1.1	G10160	—	Bar
ASTM	A576	1	1	1.1	G10170	—	Bar
ASTM	A576	1	1	1.1	G10180	—	Bar
ASTM	A576	1	1	1.1	G10190	—	Bar
ASTM	A576	1	1	1.1	G10200	—	Bar
ASTM	A576	1	1	11.1	G10210	—	Bar
ASTM	A576	1	1	11.1	G10220	—	Bar
ASTM	A576	1	1	11.1	G10230	—	Bar
ASTM	A576	1	1	11.1	G10250	—	Bar
ASTM/ASME	A/SA-587	1	1	1.1	—	K11500	E.R.W. Pipe
ASTM/ASME	A/SA-587	1	1	1.1	A2	K01807	E.R.W. Tube
ASTM/ASME	A/SA-587	1	1	—	B2	K03007	E.R.W. Tube
ASTM	A588	3	1	1.4	A	K11430	Shapes
ASTM	A588	3	1	1.4	A	K11430	Plate & Bar
ASTM	A588	3	1	1.4	A	K11430	Plate & Bar
ASTM	A588	3	1	1.4	A	K11430	Plate & Bar
ASTM	A588	3	1	1.4	B	K12043	Plate & Bar
ASTM	A588	3	1	1.4	B	K12043	Plate & Bar
ASTM	A588	3	1	1.4	B	K12043	Shapes
ASTM	A588	3	1	1.4	B	K12043	Plate & Bar
ASTM	A588	3	1	1.4	C	K11538	Plate & Bar
ASTM	A588	3	1	1.4	C	K11538	Plate & Bar
ASTM	A588	3	1	1.4	C	K11538	Shapes
ASTM	A588	3	1	1.4	C	K11538	Plate & Bar
ASTM	A588	3	1	1.4	K	—	Shapes
ASTM	A588	3	1	1.4	K	—	Plate & Bar
ASTM	A588	3	1	1.4	K	—	Plate & Bar
ASTM	A588	3	1	1.4	K	—	Plate & Bar
ASTM/ASME	A/SA-592	11B	1	3.1	A	K11856	Forgings
ASTM/ASME	A/SA-592	11B	2	3.1	E	K11695	Forgings
ASTM/ASME	A/SA-592	11B	2	3.1	E	K11695	Forgings
ASTM/ASME	A/SA-592	11B	3	3.1	F	K11576	Forgings
ASTM/ASME	A/SA-592	11B	3	3.1	F	K11576	Forgings
ASTM	A595	1	2	11.1	A	K02004	Welded Tube
ASTM	A595	1	2	11.1	B	K02005	Welded Tube
ASTM	A595	3	1	11.1	C	K11526	Welded Tube
ASTM	A606	1	2	1.4	2, CR, AR	—	Sheet & Strip

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM	A606	1	2	1.4	2, HR, A	—	Sheet & Strip
ASTM	A606	1	2	1.4	2, HR, AR	—	Sheet & Strip
ASTM	A606	1	2	1.4	2, HR, N	—	Sheet & Strip
ASTM	A606	1	2	1.4	4, CR, AR	—	Sheet & Strip
ASTM	A606	1	2	1.4	4, HR, A	—	Sheet & Strip
ASTM	A606	1	2	1.4	4, HR, AR	—	Sheet & Strip
ASTM	A606	1	2	1.4	4, HR, N	—	Sheet & Strip
ASTM	A607	1	1	—	45	—	Sheet & Strip
ASTM	A607	1	1	—	50	—	Sheet & Strip
ASTM	A607	1	2	—	55	—	Sheet & Strip
ASTM	A607	1	3	—	60	—	Sheet & Strip
ASTM	A607	1	3	—	65	—	Sheet & Strip
ASTM	A607	1	3	—	70	—	Sheet & Strip
ASTM	A611	1	1	—	A	G10170	Sheet & Strip
ASTM	A611	1	1	—	B	G10170	Sheet & Strip
ASTM	A611	1	1	—	C	G10170	Sheet & Strip
ASTM	A611	1	1	1.1	D	G10120	Sheet & Strip
ASTM	A611	1	3	—	E	G10170	Sheet & Strip
ASTM/ASME	A/SA-612	10C	1	1.3	—	K02900	Plate
ASTM/ASME	A/SA-612	10C	1	1.3	—	K02900	Plate
ASTM	A615	1A	4	—	40	—	Rebar
ASTM	A615	1A	4	—	60	—	Rebar
ASTM	A618	1	2	1.2	Ia	—	Tube
ASTM	A618	1	2	1.2	Ia	—	Tube
ASTM	A618	1	2	1.2	Ib	—	Seamless & Welded Tube
ASTM	A618	1	2	1.2	Ib	K02601	Tube
ASTM	A618	1	2	1.2	Ib	K02601	Tube
ASTM	A618	1	2	1.2	II	K12609	Tube
ASTM	A618	1	2	1.2	II	K12609	Tube
ASTM	A618	1	1	1.2	III	K12700	Tube
ASTM	A620	1	1	1.1	A	K00040	Sheet
ASTM	A620	1	1	1.1	B	K00040	Sheet
ASTM	A633	1	1	1.1	A	K01802	Plate & Shapes
ASTM	A633	1	2	1.1	C	K12000	Plate & Shapes
ASTM	A633	1	1	1.1	C	K12000	Plate & Shapes
ASTM	A633	1	1	1.1	D	K12037	Plate & Shapes
ASTM	A633	1	2	1.1	D	K12037	Plate & Shapes
ASTM	A633	1	3	4.1	E	K12202	Plate & Shapes
ASTM/ASME	A/SA-645	11A	2	9.2	A	K41583	Plate
ASTM	A653	1	1	—	33	—	Galvanized Sheet
ASTM	A653	1	1	—	37	—	Galvanized Sheet
ASTM	A653	1	1	—	40	—	Galvanized Sheet

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM	A653	1	1	—	80	—	Galvanized Sheet
ASTM/ASME	A/SA-656	1	1	1.2	50	K11804	Plate
ASTM/ASME	A/SA-656	1	1	1.3	60	K11804	Plate
ASTM/ASME	A/SA-656	1	2	1.3	70	K11804	Plate
ASTM/ASME	A/SA-656	1	3	1.3	80	K11804	Plate
ASTM/ASME	A/SA-656	1	1	1.2	T3, 50	—	Plate
ASTM/ASME	A/SA-656	1	2	1.3	T3, 60	—	Plate
ASTM/ASME	A/SA-656	1	3	2.2	T3, 70	—	Plate
ASTM/ASME	A/SA-656	1	4	2.2	T3, 80	—	Plate
ASTM/ASME	A/SA-656	1	1	1.2	T7, 50	—	Plate
ASTM/ASME	A/SA-656	1	2	1.3	T7, 60	—	Plate
ASTM/ASME	A/SA-656	1	3	2.2	T7, 70	—	Plate
ASTM/ASME	A/SA-656	1	4	2.2	T7, 80	—	Plate
ASTM	A659	1	1	1.1	1015	G10150	Sheet & Strip
ASTM	A659	1	1	—	1016	G10160	Sheet & Strip
ASTM	A659	1	1	—	1017	G10170	Sheet & Strip
ASTM	A659	1	1	1.1	1018	G10180	Sheet & Strip
ASTM	A659	1	1	1.1	1020	G10200	Sheet & Strip
ASTM	A659	1	1	—	1021	G10210	Sheet & Strip
ASTM	A659	1	1	—	1023	G10230	Sheet & Strip
ASTM/ASME	A/SA-660	1	1	11.1	WCA	J02504	Centrifugal Cast Pipe
ASTM/ASME	A/SA-660	1	2	1.1	WCB	J03003	Centrifugal Cast Pipe
ASTM/ASME	A/SA-660	1	2	11.1	WCC	J02505	Centrifugal Cast Pipe
ASTM/ASME	A/SA-662	1	1	1.1	A	K01701	Plate
ASTM/ASME	A/SA-662	1	1	1.1	B	K02203	Plate
ASTM/ASME	A/SA-662	1	2	1.1	C	K02007	Plate
ASTM	A663	1	1	—	—	—	Bar
ASTM	A663	1	1	—	45	—	Bars & Shapes
ASTM	A663	1	1	—	50	—	Bars & Shapes
ASTM	A663	1	1	—	55	—	Bars & Shapes
ASTM	A663	1	1	—	60	—	Bars & Shapes
ASTM	A663	1	1	—	65	—	Bars & Shapes
ASTM	A663	1	2	—	70	—	Bars & Shapes
ASTM	A663	1	2	—	75	—	Bars & Shapes
ASTM	A663	1	3	—	80	—	Bars & Shapes
ASTM/ASME	A/SA-666	8	3	8.3	201-1	S20100	Plate, Sheet, & Strip
ASTM/ASME	A/SA-666	8	3	8.3	201-2	S20100	Plate, Sheet, & Strip
ASTM/ASME	A/SA-666	8	1	8.1	302	S30200	Plate, Sheet, & Strip
ASTM/ASME	A/SA-666	8	1	8.1	304	S30400	Plate, Sheet, & Strip
ASTM/ASME	A/SA-666	8	1	8.1	304L	S30403	Plate, Sheet, & Strip
ASTM/ASME	A/SA-666	8	1	8.1	304LN	S30453	Plate, Sheet, & Strip
ASTM/ASME	A/SA-666	8	1	8.1	304N	S30451	Plate, Sheet, & Strip

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-666	8	1	8.1	316	S31600	Plate, Sheet, & Strip
ASTM/ASME	A/SA-666	8	1	8.1	316L	S31603	Plate, Sheet, & Strip
ASTM/ASME	A/SA-666	8	1	8.1	316N	S31651	Plate, Sheet, & Strip
ASTM/ASME	A/SA-666	8	3	8.3	XM-11	S21904	Plate, Sheet, & Strip
ASTM	A668	1	1	1.1	B	G10200	Forgings
ASTM	A668	1	2	11.1	C	G10250	Forgings
ASTM	A668	1	2	11.1	D	G10300	Forgings
ASTM	A668	1	3	11.1	F	—	Forgings
ASTM	A668	1	3	11.1	F	—	Forgings
ASTM	A668	1	3	11.1	F	—	Forgings
ASTM/ASME	A/SA-671	1	1	11.1	CA55	K02801	Fusion Welded Pipe
ASTM/ASME	A/SA-671	1	1	1.1	CB60	K02401	Fusion Welded Pipe
ASTM/ASME	A/SA-671	1	1	11.1	CB65	K02800	Fusion Welded Pipe
ASTM/ASME	A/SA-671	1	2	11.1	CB70	K03101	Fusion Welded Pipe
ASTM/ASME	A/SA-671	1	1	1.1	CC60	K02100	Fusion Welded Pipe
ASTM/ASME	A/SA-671	1	1	1.1	CC65	K02403	Fusion Welded Pipe
ASTM/ASME	A/SA-671	1	2	11.1	CC70	K02700	Fusion Welded Pipe
ASTM/ASME	A/SA-671	1	2	1.2	CD70	K12437	Fusion Welded Pipe
ASTM/ASME	A/SA-671	1	3	1.2	CD80	K12437	Fusion Welded Pipe
ASTM/ASME	A/SA-671	1	1	11.1	CE55	K02202	Fusion Welded Pipe
ASTM/ASME	A/SA-671	1	1	11.1	CE60	K02402	Fusion Welded Pipe
ASTM/ASME	A/SA-671	1	2	11.1	CK75	K02803	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	1	1.1	A45	K01700	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	1	1.1	A50	K02200	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	1	11.1	A55	K02801	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	1	1.1	B55	K02001	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	1	1.1	B60	K02401	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	1	11.1	B65	K02800	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	2	11.1	B70	K03101	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	1	1.1	C55	K01800	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	1	1.1	C60	K02100	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	1	1.1	C65	K02403	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	2	11.1	C70	K02700	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	2	1.2	D70	K12437	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	3	1.2	D80	K12437	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	1	11.1	E55	K02202	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	1	11.1	E60	K02402	Fusion Welded Pipe
ASTM/ASME	A/SA-672	3	2	1.1	H75	K12021	Fusion Welded Pipe
ASTM/ASME	A/SA-672	3	3	1.2	H80	K12022	Fusion Welded Pipe
ASTM/ASME	A/SA-672	11A	4	3.2	J100	K12521	Fusion Welded Pipe
ASTM/ASME	A/SA-672	3	3	3.1	J80	—	Fusion Welded Pipe
ASTM/ASME	A/SA-672	3	3	3.1	J90	—	Fusion Welded Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-672	3	1	1.1	L65	K11820	Fusion Welded Pipe
ASTM/ASME	A/SA-672	3	2	1.2	L70	K12020	Fusion Welded Pipe
ASTM/ASME	A/SA-672	3	2	1.2	L75	K12320	Fusion Welded Pipe
ASTM/ASME	A/SA-672	1	2	11.1	N75	K02803	Fusion Welded Pipe
ASTM/ASME	A/SA-675	1	1	11.1	45	—	Bar
ASTM/ASME	A/SA-675	1	1	11.1	50	—	Bar
ASTM/ASME	A/SA-675	1	1	11.1	55	—	Bar
ASTM/ASME	A/SA-675	1	1	11.1	60	—	Bar
ASTM/ASME	A/SA-675	1	1	11.1	65	—	Bar
ASTM/ASME	A/SA-675	1	2	11.1	70	—	Bar
ASTM/ASME	A/SA-675	1	3	—	80	—	Bar
ASTM/ASME	A/SA-675	1	4	—	90	—	Bar
ASTM	A678	1	2	1.2	A	K01600	Plate
ASTM	A678	1	3	1.3	B	K02002	Plate
ASTM	A678	1	3	1.3	C	K02204	Plate
ASTM	A678	1	4	1.3	C	K02204	Plate
ASTM	A678	1	4	1.3	C	K02204	Plate
ASTM	A678	1	4	1.3	D	K12202	Plate
ASTM/ASME	A/SA-688	8	1	8.1	TP304	S30400	Welded Tube
ASTM/ASME	A/SA-688	8	1	8.1	TP304L	S30403	Welded Tube
ASTM/ASME	A/SA-688	8	1	8.1	TP304LN	S30453	Welded Tube
ASTM/ASME	A/SA-688	8	1	8.1	TP304N	S30451	Welded Tube
ASTM/ASME	A/SA-688	8	1	8.1	TP316	S31600	Welded Tube
ASTM/ASME	A/SA-688	8	1	8.1	TP316L	S31603	Welded Tube
ASTM/ASME	A/SA-688	8	1	8.1	TP316LN	S31653	Welded Tube
ASTM/ASME	A/SA-688	8	1	8.1	TP316N	S31651	Welded Tube
ASTM/ASME	A/SA-688	8	3	8.3	XM-29	S24000	Welded Tube
ASTM	A690	1	2	1.4	—	K12249	Marine Piling—Plate & Bar
ASTM/ASME	A/SA-691	3	1	4.2	0.5Cr, Cl. 1	K12143	Fusion Welded Pipe
ASTM/ASME	A/SA-691	3	2	4.2	0.5Cr, Cl. 2	K12143	Fusion Welded Pipe
ASTM/ASME	A/SA-691	4	1	5.1	1.25CR, Cl. 1	K11789	Fusion Welded Pipe
ASTM/ASME	A/SA-691	4	1	5.1	1.25CR, Cl. 2	K11789	Fusion Welded Pipe
ASTM/ASME	A/SA-691	4	1	5.1	1CR, Cl. 1	K11757	Fusion Welded Pipe
ASTM/ASME	A/SA-691	4	1	5.1	1CR, Cl. 2	K11757	Fusion Welded Pipe
ASTM/ASME	A/SA-691	5A	1	5.2	2.25CR, Cl. 1	K21590	Fusion Welded Pipe
ASTM/ASME	A/SA-691	5A	1	5.2	2.25CR, Cl. 2	K21590	Fusion Welded Pipe
ASTM/ASME	A/SA-691	5A	1	5.2	3CR, Cl. 1	K31545	Fusion Welded Pipe
ASTM/ASME	A/SA-691	5A	1	5.2	3CR, Cl. 2	K31545	Fusion Welded Pipe
ASTM/ASME	A/SA-691	5B	1	5.3	5CR, Cl. 1	K41545	Fusion Welded Pipe
ASTM/ASME	A/SA-691	5B	1	5.3	5CR, Cl. 2	K41545	Fusion Welded Pipe
ASTM/ASME	A/SA-691	15E	1	6.4	91	K91560	Fusion Welded Pipe
ASTM/ASME	A/SA-691	3	1	1.1	CM-65	K11820	Fusion Welded Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-691	3	2	1.2	CM-70	K12020	Fusion Welded Pipe
ASTM/ASME	A/SA-691	3	2	1.2	CM-75	K12320	Fusion Welded Pipe
ASTM/ASME	A/SA-691	1	2	11.1	CMS-75	K02803	Fusion Welded Pipe
ASTM/ASME	A/SA-691	1	2	1.2	CMSH-70	K12437	Fusion Welded Pipe
ASTM/ASME	A/SA-691	1	2	1.2	CMSH-70	K12437	Fusion Welded Pipe
ASTM/ASME	A/SA-691	1	3	1.2	CMSH-80	K12437	Fusion Welded Pipe
ASTM/ASME	A/SA-691	1	3	1.2	CMSH-80	K12437	Fusion Welded Pipe
ASTM	A694	1	1	11.1	F42	K03014	Forgings
ASTM	A694	1	1	11.1	F46	K03014	Forgings
ASTM	A694	1	1	11.1	F48	K03014	Forgings
ASTM	A694	1	1	11.1	F50	K03014	Forgings
ASTM	A694	1	1	11.1	F52	K03014	Forgings
ASTM	A694	1	2	11.1	F56	K03014	Forgings
ASTM	A694	1	2	11.1	F60	K03014	Forgings
ASTM	A694	1	2	11.1	F65	K03014	Forgings
ASTM	A694	1	3	11.1	F70	K03014	Forgings
ASTM/ASME	A/SA-695	1	1	11.1	B, 35	K03504	Bar
ASTM/ASME	A/SA-695	1	2	11.1	B, 40	K03504	Bar
ASTM/ASME	A/SA-696	1	1	11.1	B	K03200	Bar
ASTM/ASME	A/SA-696	1	2	11.1	C	K03200	Bar
ASTM	A706	1A	4	1.3	60	—	Rebar
ASTM	A707	1	1	1.2	L1, Cl. 1	K02302	Forgings
ASTM	A707	1	1	1.2	L1, Cl. 2	K02302	Forgings
ASTM	A707	1	1	11.1	L2, Cl. 1	K03301	Forgings
ASTM	A707	1	1	11.1	L2, Cl. 2	K03301	Forgings
ASTM	A707	1	2	11.1	L2, Cl. 3	K03301	Forgings
ASTM	A707	1	1	1.2	L3, Cl. 1	K12510	Forgings
ASTM	A707	1	1	1.2	L3, Cl. 2	K12510	Forgings
ASTM	A707	1	2	1.3	L3, Cl. 3	K12510	Forgings
ASTM	A707	1	1	—	L4, Cl. 1	K12089	Forgings
ASTM	A707	1	1	—	L4, Cl. 2	K12089	Forgings
ASTM	A707	1	2	—	L4, Cl. 3	K12089	Forgings
ASTM	A707	1	1	—	L5, Cl. 1	K20934	Forgings
ASTM	A707	1	1	—	L5, Cl. 2	K20934	Forgings
ASTM	A707	1	2	—	L5, Cl. 3	K20934	Forgings
ASTM	A707	1	4	—	L5, Cl. 4	K20934	Forgings
ASTM	A707	3	1	—	L6, Cl. 1	K02902	Forgings
ASTM	A707	3	1	—	L6, Cl. 2	K02902	Forgings
ASTM	A707	3	2	—	L6, Cl. 3	K02902	Forgings
ASTM	A707	3	4	—	L6, Cl. 4	K02902	Forgings
ASTM	A707	9B	1	—	L7, Cl. 1	K32218	Forgings
ASTM	A707	9B	1	—	L7, Cl. 2	K32218	Forgings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM	A707	9B	1	—	L8, Cl. 1	K42247	Forgings
ASTM	A707	9B	1	—	L8, Cl. 2	K42247	Forgings
ASTM	A707	9B	1	—	L8, Cl. 3	K42247	Forgings
ASTM	A707	9B	1	—	L8, Cl. 4	K42247	Forgings
ASTM	A709	1	1	11.1	36	—	Plate, Bar, & Shapes
ASTM	A709	1	1	1.2	50	—	Plate, Bar, & Shapes
ASTM	A709	1	1	1.2	50S	—	Plate, Bar, & Shapes
ASTM	A709	1	2	1.4	50W, A	—	Plate, Bar, & Shapes
ASTM	A709	1	2	1.4	50W, B	—	Plate, Bar, & Shapes
ASTM	A709	1	2	1.4	HPS 50W	—	Plate, Bar, & Shapes
ASTM	A709	11B	11	1.4	HPS 70W	—	Plate, Bar, & Shapes
ASTM	A710	12C	1	3.3	A, Cl. 1	K20747	Plate
ASTM	A710	12A	1	3.3	A, Cl. 2	K20747	Plate
ASTM	A710	12A	1	3.3	A, Cl. 2	K20747	Plate
ASTM	A710	12B	1	3.3	A, Cl. 3	K20747	Plate
ASTM	A710	12B	1	3.3	A, Cl. 3	K20747	Plate
ASTM	A714	9A	1	9.1	V	K22035	Seamless & Welded Pipe
ASTM	A714	9A	1	9.1	V, E	K22035	Seamless & Welded Pipe
ASTM/ASME	A/SA-724	1	4	3.1	A	K11831	Plate
ASTM/ASME	A/SA-724	1	4	3.1	B	K12031	Plate
ASTM/ASME	A/SA-724	1	4	1.1	C	K12037	Plate
ASTM/ASME	A/SA-727	1	1	11.1	—	K02506	Forgings
ASTM/ASME	A/SA-731	7	2	7.1	18Cr-2Mo	S44400	Seamless & Welded Pipe
ASTM/ASME	A/SA-731	6	4	7.2	S41500	S41500	Seamless & Welded Pipe
ASTM/ASME	A/SA-731	10K	1	7.1	S44660	S44660	Seamless & Welded Pipe
ASTM/ASME	A/SA-731	10J	1	7.1	S44700	S44700	Seamless & Welded Pipe
ASTM/ASME	A/SA-731	10K	1	7.1	S44800	S44800	Seamless & Welded Pipe
ASTM/ASME	A/SA-731	7	2	7.1	TP439	S43035	Seamless & Welded Pipe
ASTM/ASME	A/SA-731	10I	1	7.1	TPXM-27	S44627	Seamless & Welded Pipe
ASTM/ASME	A/SA-731	10I	1	7.1	TPXM-33	S44626	Seamless & Welded Pipe
ASTM	A734	11A	2	3.1	A	K21205	Plate
ASTM/ASME	A/SA-737	1	2	11.1	B	K12001	Plate
ASTM/ASME	A/SA-737	1	3	4.1	C	K12202	Plate
ASTM/ASME	A/SA-738	1	2	11.1	A	K12447	Plate
ASTM/ASME	A/SA-738	1	3	11.1	B	K12007	Plate
ASTM/ASME	A/SA-738	1	3	11.1	C	K02008	Plate
ASTM/ASME	A/SA-738	1	3	11.1	C	K02008	Plate
ASTM/ASME	A/SA-738	1	3	11.1	C	K02008	Plate
ASTM/ASME	A/SA-739	4	1	5.1	B11	K11797	Bar
ASTM/ASME	A/SA-739	5A	1	5.2	B22	K21390	Bar
ASTM	A743	6	3	7.2	CA15	J91150	Castings
ASTM	A743	6	3	7.2	CA15M	J91151	Castings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM	A743	6	4	7.2	CA40	J91153	Castings
ASTM	A743	6	4	7.2	CA6NM	J91540	Castings
ASTM	A743	6	4	7.2	CB6	J91804	Castings
ASTM	A743	7	1	7.1	CC50	J92615	Castings
ASTM	A743	8	2	8.2	CE30	J93423	Castings
ASTM	A743	8	1	8.1	CF10SMnN	J92972	Castings
ASTM	A743	8	1	8.2	CF16F	J92701	Castings
ASTM	A743	8	2	8.2	CF20	J92602	Castings
ASTM	A743	8	1	8.1	CF3	J92500	Castings
ASTM	A743	8	1	8.1	CF3M	J92800	Castings
ASTM	A743	8	1	8.2	CF3MN	J92804	Castings
ASTM	A743	8	1	8.1	CF8	J92600	Castings
ASTM	A743	8	1	8.1	CF8C	J92710	Castings
ASTM	A743	8	1	8.1	CF8M	J92900	Castings
ASTM	A743	8	2	8.2	CG12	J93001	Castings
ASTM	A743	8	1	8.2	CG3M	J92999	Castings
ASTM	A743	8	1	8.1	CG8M	J93000	Castings
ASTM	A743	8	2	8.2	CH10	J93401	Castings
ASTM	A743	8	2	8.2	CH20	J93402	Castings
ASTM	A743	8	4	8.2	CK3MCuN	J93254	Castings
ASTM	A743	8	2	8.2	CN3M	J94652	Castings
ASTM/ASME	A/SA-765	1	1	11.1	I	K03046	Forgings
ASTM/ASME	A/SA-765	1	2	11.1	II	K03047	Forgings
ASTM/ASME	A/SA-765	9B	1	9.2	III	K32026	Forgings
ASTM/ASME	A/SA-765	1	3	1.1	IV	K02009	Forgings
ASTM	A774	8	1	8.1	304L	S30403	Wrought Piping Fittings
ASTM	A774	8	1	8.1	316L	S31603	Wrought Piping Fittings
ASTM	A774	8	1	8.1	321	S32100	Wrought Piping Fittings
ASTM	A774	8	1	8.1	347	S34700	Wrought Piping Fittings
ASTM	A774	8	1	8.1	F317L	S31703	Wrought Piping Fittings
ASTM	A778	8	1	8.1	304L	S30403	Welded Unannealed Tube
ASTM	A778	8	1	8.1	316L	S31603	Welded Unannealed Tube
ASTM	A778	8	1	8.1	321	S32100	Welded Unannealed Tube
ASTM	A778	8	1	8.1	347	S34700	Welded Unannealed Tube
ASTM	A778	8	1	8.1	F317L	S31703	Welded Unannealed Tube
ASTM	A782	11B	4	—	1	—	Plate
ASTM	A782	11B	4	—	1	—	Plate
ASTM	A782	11B	4	—	1	—	Plate
ASTM/ASME	A/SA-789	10H	1	10.1	—	S32003	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.1	—	S32101	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.1	—	S32101	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.1	—	S32202	Seamless & Welded Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-789	10H	1	10.2	S31200	S31200	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.2	S31260	S31260	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.1	S31500	S31500	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.1	S31803	S31803	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.1	S32205	S32205	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.1	S32304	S32304	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.1	S32304	S32304	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.2	S32550	S32550	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.2	S32750	S32750	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.2	S32760	S32760	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.2	S32900	S32900	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.2	S32906	S32906	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.2	S32906	S32906	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.2	S32950	S32950	Seamless & Welded Tube
ASTM/ASME	A/SA-789	10H	1	10.2	S39274	S39274	Seamless & Welded Tube
ASTM/ASME	A/SA-790	10H	1	10.1	—	S32003	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.1	—	S32101	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.1	—	S32101	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.1	—	S32202	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.2	S31200	S31200	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.2	S31260	S31260	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.1	S31500	S31500	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.1	S31803	S31803	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.1	S32205	S32205	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.1	S32304	S32304	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.2	S32550	S32550	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.2	S32750	S32750	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.2	S32760	S32760	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.2	S32900	S32900	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.2	S32906	S32906	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.2	S32906	S32906	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.2	S32950	S32950	Seamless & Welded Pipe
ASTM/ASME	A/SA-790	10H	1	10.2	S39274	S39274	Seamless & Welded Pipe
ASTM	A795	1	1	—	E, A	—	Resistance Welded Pipe
ASTM	A795	1	1	—	E, B	—	Resistance Welded Pipe
ASTM	A795	1	1	—	F	—	Furnace Welded Pipe
ASTM	A795	1	1	—	S, A	—	Seamless Pipe
ASTM	A795	1	1	—	S, B	—	Seamless Pipe
ASTM/ASME	A/SA-803	10K	1	7.1	26-3-3	S44660	Welded Tube
ASTM/ASME	A/SA-803	7	2	7.1	TP439	S43035	Welded Tube
ASTM	A808	1	1	1.4	—	K11852	Plate
ASTM/ASME	A/SA-813	8	4	8.2	—	S32053	Welded Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-813	8	2	8.2	S30815	S30815	Welded Pipe
ASTM/ASME	A/SA-813	8	4	8.2	S31254	S31254	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP304	S30400	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP304H	S30409	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP304L	S30403	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP304LN	S30453	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP304N	S30451	Welded Pipe
ASTM/ASME	A/SA-813	8	2	8.2	TP309Cb	S30940	Welded Pipe
ASTM/ASME	A/SA-813	8	2	8.2	TP309S	S30908	Welded Pipe
ASTM/ASME	A/SA-813	8	2	8.2	TP310Cb	S31040	Welded Pipe
ASTM/ASME	A/SA-813	8	2	8.2	TP310S	S31008	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP316	S31600	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP316H	S31609	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP316L	S31603	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP316LN	S31653	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP316N	S31651	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP317	S31700	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP317L	S31703	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP321	S32100	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP321H	S32109	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP347	S34700	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP347H	S34709	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP348	S34800	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TP348H	S34809	Welded Pipe
ASTM/ASME	A/SA-813	8	3	8.3	TPXM-11	S21904	Welded Pipe
ASTM/ASME	A/SA-813	8	1	8.1	TPXM-15	S38100	Welded Pipe
ASTM/ASME	A/SA-813	8	3	8.3	TPXM-19	S20910	Welded Pipe
ASTM/ASME	A/SA-813	8	3	8.3	TPXM-29	S24000	Welded Pipe
ASTM/ASME	A/SA-814	8	4	8.2	—	S32053	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	2	8.2	S30815	S30815	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	4	8.2	S31254	S31254	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP304	S30400	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP304H	S30409	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP304L	S30403	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP304LN	S30453	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP304N	S30451	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	2	8.2	TP309Cb	S30940	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	2	8.2	TP309S	S30908	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	2	8.2	TP310Cb	S31040	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	2	8.2	TP310S	S31008	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP316	S31600	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP316H	S31609	Cold Worked Welded Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-814	8	1	8.1	TP316L	S31603	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP316LN	S31653	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP316N	S31651	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP317	S31700	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP317L	S31703	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP321	S32100	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP321H	S32109	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP347	S34700	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP347H	S34709	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP348	S34800	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TP348H	S34809	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	3	8.3	TPXM-11	S21904	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	1	8.1	TPXM-15	S38100	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	3	8.3	TPXM-19	S20910	Cold Worked Welded Pipe
ASTM/ASME	A/SA-814	8	3	8.3	TPXM-29	S24000	Cold Worked Welded Pipe
ASTM/ASME	A/SA-815	10H	1	10.1	—	S32101	Fittings
ASTM/ASME	A/SA-815	10H	1	10.1	—	S32202	Fittings
ASTM/ASME	A/SA-815	10H	1	10.1	S31803	S31803	Fittings
ASTM/ASME	A/SA-815	10H	1	10.1	S32205	S32205	Fittings
ASTM/ASME	A/SA-815	10H	1	10.2	S32550	S32550	Fittings
ASTM/ASME	A/SA-815	10H	1	10.2	S32750	S32750	Fittings
ASTM/ASME	A/SA-815	10H	1	10.2	S32760	S32760	Fittings
ASTM/ASME	A/SA-815	6	4	7.2	S41500	S41500	Fittings
ASTM	A830	1	1	1.1	1006	G10060	Plate
ASTM	A830	1	1	1.1	1008	G10080	Plate
ASTM	A830	1	1	1.1	1009	G10090	Plate
ASTM	A830	1	1	1.1	1010	G10100	Plate
ASTM	A830	1	1	1.1	1012	G10120	Plate
ASTM	A830	1	1	1.1	1015	G10150	Plate
ASTM	A830	1	1	1.1	1016	G10160	Plate
ASTM	A830	1	1	1.1	1017	G10170	Plate
ASTM	A830	1	1	1.1	1018	G10180	Plate
ASTM	A830	1	1	1.1	1019	G10190	Plate
ASTM	A830	1	1	1.1	1020	G10200	Plate
ASTM	A830	1	1	1.1	1021	G10210	Plate
ASTM	A830	1	1	1.1	1022	G10220	Plate
ASTM	A830	1	1	11.1	1023	G10230	Plate
ASTM	A830	1	2	11.1	1025	G10250	Plate
ASTM/ASME	A/SA-832	5C	1	6.2	21V	K31830	Plate
ASTM/ASME	A/SA-832	5C	1	6.2	22V	K31835	Plate
ASTM/ASME	A/SA-832	5C	1	6.2	23V	—	Plate
ASTM/ASME	A/SA-836	1	1	1.1	—	—	Forgings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-841	1	2	1.2	A, Cl. 1	—	Plate
ASTM/ASME	A/SA-841	1	2	1.2	A, Cl. 1	—	Plate
ASTM/ASME	A/SA-841	1	3	1.3	B, Cl. 2	—	Plate
ASTM/ASME	A/SA-841	1	3	1.3	B, Cl. 2	—	Plate
ASTM	A844	11A	1	9.3	—	K81340	Plate
ASTM	A852	11B	11	4.2	—	K12043	Plate
ASTM	A857	1	1	1.1	25	—	Sheet & Strip
ASTM	A857	1	1	1.1	30	—	Sheet & Strip
ASTM	A857	1	1	1.1	33	—	Sheet & Strip
ASTM	A857	1	1	1.1	36	—	Sheet & Strip
ASTM/ASME	A/SA-859	11C	1	3.3	A, Cl. 1	K20747	Forgings
ASTM/ASME	A/SA-859	11C	1	3.3	A, Cl. 2	K20747	Forgings
ASTM	A871	3	2	4.2	60	—	Plate
ASTM	A871	3	3	4.2	65	—	Plate
ASTM	A890	10H	1	10.2	1A	J93370	Castings
ASTM	A890	10H	1	10.2	1B	J93372	Castings
ASTM	A890	10H	1	10.2	1C	J93373	Castings
ASTM	A890	10H	1	10.2	2A	J93345	Castings
ASTM	A890	10H	1	10.2	3A	J93371	Castings
ASTM	A890	10H	1	10.1	4A	J92205	Castings
ASTM	A890	10H	1	10.2	5A	J93404	Castings
ASTM	A890	10H	1	10.2	6A	J93380	Castings
ASTM	A913	1	2	1.2	50	—	Shapes
ASTM	A913	1	3	3.1	60	—	Shapes
ASTM	A913	1	3	3.1	65	—	Shapes
ASTM	A913	1	3	3.1	70	—	Shapes
ASTM	A928	10H	1	10.2	—	S32760	Welded Pipe
ASTM	A928	10H	1	10.1	2205	S32205	Welded Pipe
ASTM	A928	10H	1	10.2	255	S32550	Welded Pipe
ASTM	A935	1	1	1.2	45, Cl. 1	—	Sheet & Strip
ASTM	A935	1	1	1.2	45, Cl. 2	—	Sheet & Strip
ASTM	A935	1	1	1.2	50, Cl. 1	—	Sheet & Strip
ASTM	A935	1	1	1.2	50, Cl. 2	—	Sheet & Strip
ASTM	A935	1	2	1.3	55, Cl. 1	—	Sheet & Strip
ASTM	A935	1	1	1.3	55, Cl. 2	—	Sheet & Strip
ASTM	A935	1	2	11.1	60, Cl. 1	—	Sheet & Strip
ASTM	A935	1	2	1.3	60, Cl. 2	—	Sheet & Strip
ASTM	A935	1	3	11.1	65, Cl. 1	—	Sheet & Strip
ASTM	A935	1	2	1.3	65, Cl. 2	—	Sheet & Strip
ASTM	A935	1	3	11.1	70, Cl. 1	—	Sheet & Strip
ASTM	A935	1	3	1.3	70, Cl. 2	—	Sheet & Strip
ASTM/ASME	A/SA-965	8	1	8.1	F304	S30400	Forgings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM/ASME	A/SA-965	8	1	8.1	F304H	S30409	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F304L	S30403	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F304LN	S30453	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F304N	S30451	Forgings
ASTM/ASME	A/SA-965	8	2	8.2	F310	S31000	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F316	S31600	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F316H	S31609	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F316L	S31603	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F316LN	S31653	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F316N	S31651	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F321	S32100	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F321H	S32109	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F347	S34700	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F347H	S34709	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F348	S34800	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F348H	S34809	Forgings
ASTM/ASME	A/SA-965	8	1	8.1	F46	S30600	Forgings
ASTM/ASME	A/SA-965	8	3	8.3	FXM-11	S21904	Forgings
ASTM/ASME	A/SA-965	8	3	8.3	FXM-19	S20910	Forgings
ASTM	A984	1	1	1.1	35	—	Pipe
ASTM	A984	1	2	1.2	50	—	Pipe
ASTM	A984	1	2	1.3	60	—	Pipe
ASTM	A984	1	3	—	70	—	Pipe
ASTM	A984	1	4	—	80	—	Pipe
ASTM	A992	1	1	1.1	—	—	Shapes
ASTM	A992	1	1	1.2	—	—	Plate & Shapes
ASTM/ASME	A/SA-995	10H	1	10.2	1B	J93372	Castings
ASTM/ASME	A/SA-995	10H	1	10.2	2A	J93345	Castings
ASTM/ASME	A/SA-995	10H	1	10.2	3A	J93371	Castings
ASTM/ASME	A/SA-995	10H	1	10.1	4A	J92205	Castings
ASTM/ASME	A/SA-995	10H	1	10.2	5A	J93404	Castings
ASTM/ASME	A/SA-995	10H	1	10.2	6A	J93380	Castings
ASTM/ASME	A/SA-1008	1	1	1.1	CS, A	—	Sheet
ASTM/ASME	A/SA-1008	1	1	1.1	CS, B	—	Sheet
ASTM	A1008	1	1	1.1	CS, C	—	Sheet
ASTM	A1008	1	1	1.1	DS, A	—	Sheet
ASTM/ASME	A/SA-1008	1	1	1.1	DS, B	—	Sheet
ASTM	A1008	1	1	1.2	HSLAS 45, Cl. 1	—	Sheet
ASTM	A1008	1	1	1.2	HSLAS 45, Cl. 2	—	Sheet
ASTM	A1008	1	1	1.2	HSLAS 50, Cl. 1	—	Sheet
ASTM	A1008	1	1	1.2	HSLAS 50, Cl. 2	—	Sheet
ASTM	A1008	1	2	1.3	HSLAS 55, Cl. 1	—	Sheet

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM	A1008	1	1	1.3	HSLAS 55, Cl. 2	—	Sheet
ASTM	A1008	1	2	11.1	HSLAS 60, Cl. 1	—	Sheet
ASTM	A1008	1	2	1.3	HSLAS 60, Cl. 2	—	Sheet
ASTM	A1008	1	3	11.1	HSLAS 65, Cl. 1	—	Sheet
ASTM	A1008	1	2	1.3	HSLAS 65, Cl. 2	—	Sheet
ASTM	A1008	1	3	11.1	HSLAS 70, Cl. 1	—	Sheet
ASTM	A1008	1	3	1.3	HSLAS 70, Cl. 2	—	Sheet
ASTM	A1008	1	1	1.2	HSLAS-F 50	—	Sheet
ASTM	A1008	1	2	1.3	HSLAS-F 60	—	Sheet
ASTM	A1008	1	3	1.3	HSLAS-F 70	—	Sheet
ASTM	A1008	1	4	1.3	HSLAS-F 80	—	Sheet
ASTM	A1008	1	1	1.1	SS 25	—	Sheet
ASTM	A1008	1	1	1.1	SS 30	—	Sheet
ASTM	A1008	1	1	1.1	SS 33, 1	—	Sheet
ASTM	A1008	1	1	1.1	SS 33, 2	—	Sheet
ASTM	A1008	1	1	1.1	SS 40, 1	—	Sheet
ASTM	A1008	1	1	1.1	SS 40, 2	—	Sheet
ASTM	A1008	1	3	1.3	SS 80	—	Sheet
ASTM/ASME	A/SA-1010	7	1	7.2	40	S41003	Plate, Sheet, & Strip
ASTM/ASME	A/SA-1010	7	1	7.2	50	S41003	Plate, Sheet, & Strip
ASTM	A1011	1	1	1.1	CS, A	—	Sheet & Strip
ASTM/ASME	A/SA-1011	1	1	1.1	CS, B	—	Sheet & Strip
ASTM	A1011	1	1	1.1	CS, C	—	Sheet & Strip
ASTM	A1011	1	1	1.1	CS, D	—	Sheet & Strip
ASTM	A1011	1	1	1.1	DS, A	—	Sheet & Strip
ASTM/ASME	A/SA-1011	1	1	1.1	DS, B	—	Sheet & Strip
ASTM	A1011	1	1	1.2	HSLAS 45, Cl. 1	—	Sheet & Strip
ASTM	A1011	1	1	1.2	HSLAS 45, Cl. 2	—	Sheet & Strip
ASTM	A1011	1	1	1.2	HSLAS 50, Cl. 1	—	Sheet & Strip
ASTM	A1011	1	1	1.2	HSLAS 50, Cl. 2	—	Sheet & Strip
ASTM	A1011	1	2	1.3	HSLAS 55, Cl. 1	—	Sheet & Strip
ASTM	A1011	1	1	1.3	HSLAS 5,5 Cl. 2	—	Sheet & Strip
ASTM	A1011	1	2	11.1	HSLAS 60, Cl. 1	—	Sheet & Strip
ASTM	A1011	1	2	1.3	HSLAS 60, Cl. 2	—	Sheet & Strip
ASTM	A1011	1	3	11.1	HSLAS 65, Cl. 1	—	Sheet & Strip
ASTM	A1011	1	2	1.3	HSLAS 65, Cl. 2	—	Sheet & Strip
ASTM	A1011	1	3	11.1	HSLAS 70, Cl. 1	—	Sheet & Strip
ASTM	A1011	1	3	1.3	HSLAS 70, Cl. 2	—	Sheet & Strip
ASTM	A1011	1	1	1.2	HSLAS-F 50	—	Sheet & Strip
ASTM	A1011	1	2	1.3	HSLAS-F 60	—	Sheet & Strip
ASTM	A1011	1	3	1.3	HSLAS-F 70	—	Sheet & Strip
ASTM	A1011	1	4	1.3	HSLAS-F 80	—	Sheet & Strip

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
ASTM	A1011	1	1	1.1	SS 30	—	Sheet & Strip
ASTM	A1011	1	1	1.1	SS 33	—	Sheet & Strip
ASTM	A1011	1	1	1.1	SS 36, 1	—	Sheet & Strip
ASTM	A1011	1	1	1.1	SS 36, 2	—	Sheet & Strip
ASTM	A1011	1	1	1.1	SS 40	—	Sheet & Strip
ASTM	A1011	1	1	1.2	SS 45, 1	—	Sheet & Strip
ASTM	A1011	1	1	1.2	SS 45, 2	—	Sheet & Strip
ASTM	A1011	1	1	1.2	SS 50	—	Sheet & Strip
ASTM	A1011	1	2	1.3	SS 55	—	Sheet & Strip
ASTM	A1011	1	2	1.3	SS 60	—	Sheet & Strip
ASTM	A1011	1	3	1.3	SS 70	—	Sheet & Strip
ASTM	A1011	1	4	1.3	SS 80	—	Sheet & Strip
ASTM	A1018	1	1	1.2	HSLAS 45, Cl. 1	—	Sheet & Strip
ASTM	A1018	1	1	1.2	HSLAS 45, Cl. 2	—	Sheet & Strip
ASTM	A1018	1	1	1.2	HSLAS 50, Cl. 1	—	Sheet & Strip
ASTM	A1018	1	1	1.2	HSLAS 50, Cl. 2	—	Sheet & Strip
ASTM	A1018	1	2	1.3	HSLAS 55, Cl. 1	—	Sheet & Strip
ASTM	A1018	1	1	1.3	HSLAS 5,5 Cl. 2	—	Sheet & Strip
ASTM	A1018	1	2	11.1	HSLAS 60, Cl. 1	—	Sheet & Strip
ASTM	A1018	1	2	1.3	HSLAS 60, Cl. 2	—	Sheet & Strip
ASTM	A1018	1	2	11.1	HSLAS 65, Cl. 1	—	Sheet & Strip
ASTM	A1018	1	2	1.3	HSLAS 65, Cl. 2	—	Sheet & Strip
ASTM	A1018	1	3	11.1	HSLAS 70, Cl. 1	—	Sheet & Strip
ASTM	A1018	1	3	1.3	HSLAS 70, Cl. 2	—	Sheet & Strip
ASTM	A1018	1	1	1.2	HSLAS-F 50	—	Sheet & Strip
ASTM	A1018	1	3	1.3	HSLAS-F 60	—	Sheet & Strip
ASTM	A1018	1	3	1.3	HSLAS-F 70	—	Sheet & Strip
ASTM	A1018	1	4	1.3	HSLAS-F 80	—	Sheet & Strip
ASTM	A1018	1	1	1.1	SS 30	—	Sheet & Strip
ASTM	A1018	1	1	1.1	SS 33	—	Sheet & Strip
ASTM	A1018	1	1	1.1	SS 36, 1	—	Sheet & Strip
ASTM	A1018	1	1	1.1	SS 36, 2	—	Sheet & Strip
ASTM	A1018	1	1	1.1	SS 40	—	Sheet & Strip
CSA	G30.18	1A	4	—	300R	—	Rebar
CSA	G30.18	1A	4	—	400R	—	Rebar
CSA	G30.18	1A	4	11.1	400W	—	Rebar
CSA	G30.18	1A	4	—	500R	—	Rebar
CSA	G30.18	1A	4	11.1	500W	—	Rebar
CSA	G40.21	1	1	1.1	260W	—	Plate, Bar, & Shapes
CSA	G40.21	1	1	1.1	260WT	—	Plate, Bar, & Shapes
CSA	G40.21	1	1	1.2	300W	—	Plate, Bar, & Shapes
CSA	G40.21	1	1	1.2	300WT	—	Plate, Bar, & Shapes

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
CSA	G40.21	1	2	1.4	350A	—	HSLA Plate, Bar, & Shapes
CSA	G40.21	1	2	1.4	350AT	—	HSLA Plate, Bar, & Shapes
CSA	G40.21	1	2	1.4	350R	—	HSLA Plate, Bar, & Shapes
CSA	G40.21	1	1	1.2	350W	—	Plate, Bar, & Shapes
CSA	G40.21	1	2	1.2	350WT	—	Plate, Bar, & Shapes
CSA	G40.21	1	2	1.3	380W	—	Plate, Bar, & Shapes
CSA	G40.21	1	2	1.3	380WT	—	Plate, Bar, & Shapes
CSA	G40.21	1	2	1.4	400A	—	HSLA Plate, Bar, & Shapes
CSA	G40.21	1	2	1.4	400AT	—	HSLA Plate, Bar, & Shapes
CSA	G40.21	1	2	1.3	400W	—	HSLA Plate, Bar, & Shapes
CSA	G40.21	1	2	1.3	400WT	—	HSLA Plate, Bar, & Shapes
CSA	G40.21	1	3	1.4	480A	—	HSLA Plate, Bar, & Shapes
CSA	G40.21	1	3	1.4	480AT	—	HSLA Plate, Bar, & Shapes
CSA	G40.21	1	3	11.1	480W	—	HSLA Plate, Bar, & Shapes
CSA	G40.21	1	3	11.1	480WT	—	HSLA Plate, Bar, & Shapes
CSA	G40.21	1	4	1.4	550A	—	Plate, Bar, & Shapes
CSA	G40.21	1	4	1.4	550AT	—	Plate, Bar, & Shapes
CSA	G40.21	1	4	1.3	550W	—	Plate, Bar, & Shapes
CSA	G40.21	1	4	1.3	550WT	—	Plate, Bar, & Shapes
CSA	Z245.1	1	1	11.1	172	—	Pipe
CSA	Z245.1	1	1	11.1	207	—	Pipe
CSA	Z245.1	1	1	11.1	241	—	Pipe
CSA	Z245.1	1	1	11.1	290	—	Pipe
CSA	Z245.1	1	2	11.1	317	—	Pipe
CSA	Z245.1	1	2	11.1	359	—	Pipe
CSA	Z245.1	1	2	11.1	386	—	Pipe
CSA	Z245.1	1	3	11.1	414	—	Pipe
CSA	Z245.1	1	3	11.1	448	—	Pipe
CSA	Z245.1	1	3	11.1	483	—	Pipe
CSA	Z245.1	1	4	11.1	550	—	Pipe
CSA	Z245.11	1	1	11.1	207	—	Fittings
CSA	Z245.11	1	1	11.1	241	—	Fittings
CSA	Z245.11	1	1	11.1	290	—	Fittings
CSA	Z245.11	1	2	11.1	317	—	Fittings
CSA	Z245.11	1	2	11.1	359	—	Fittings
CSA	Z245.11	1	2	11.1	386	—	Fittings
CSA	Z245.11	1	3	11.1	414	—	Fittings
CSA	Z245.11	1	3	11.1	448	—	Fittings
CSA	Z245.11	1	3	11.1	483	—	Fittings
CSA	Z245.11	1	4	11.1	550	—	Fittings
CSA	Z245.12	1	1	11.1	248	—	Flanges
CSA	Z245.12	1	1	11.1	290	—	Flanges

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Ferrous Alloys

Standard	Base Metal Specification	Material Number	Group Number	ISO 15608 Group	Type, Grade, or Alloy Designation	UNS Number	Product Form
Steel and Steel Alloys							
CSA	Z245.12	1	2	11.1	317	—	Flanges
CSA	Z245.12	1	2	11.1	359	—	Flanges
CSA	Z245.12	1	2	11.1	386	—	Flanges
CSA	Z245.12	1	3	11.1	414	—	Flanges
CSA	Z245.12	1	3	11.1	448	—	Flanges
CSA	Z245.12	1	3	11.1	483	—	Flanges
MSS	SP-75	1	1	11.1	WPHY-42	—	Seamless & Welded Fittings
MSS	SP-75	1	1	11.1	WPHY-46	—	Seamless & Welded Fittings
MSS	SP-75	1	1	11.1	WPHY-52	—	Seamless & Welded Fittings
MSS	SP-75	1	2	11.1	WPHY-56	—	Seamless & Welded Fittings
MSS	SP-75	1	2	11.1	WPHY-60	—	Seamless & Welded Fittings
MSS	SP-75	1	2	11.1	WPHY-65	—	Seamless & Welded Fittings
MSS	SP-75	1	3	11.1	WPHY-70	—	Seamless & Welded Fittings

Table C.1
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
AMS	4914	—	53	R58153	54	Sheet
AMS	4915	—	54	R54810	52	Plate
AMS	4915	—	54	R54810	52	Plate
AMS	4915	—	54	R54810	52	Plate
AMS	4915	—	54	R54810	52	Plate
AMS	4915	—	54	R54810	52	Sheet & Strip
AMS	4919	—	54	R54620	52	Sheet
AMS	4973	—	54	R54810	52	Forgings
AMS	4973	—	54	R54810	52	Forgings
AMS	4975	—	54	R54620	52	Bar
AMS	4976	—	54	R54620	52	Forgings
AMS	5711	—	44	N06635	43	Sheet
ASTM	B21	—	32	C46400	32.2	Rod & Bar
ASTM	B21	—	32	C46400	32.2	Rod & Bar
ASTM	B21	—	32	C46400	32.2	Rod & Bar
ASTM	B21	—	32	C46400	32.2	Shapes
ASTM/ASME	B/SB-26	208.0	26	A02080	25	Castings
ASTM/ASME	B/SB-26	222.0, O	26	A02220	—	Castings
ASTM/ASME	B/SB-26	222.0, T61	26	A02220	—	Castings
ASTM/ASME	B/SB-26	319.0, F	26	A03190	25	Castings
ASTM/ASME	B/SB-26	319.0, T5	26	A03190	25	Castings
ASTM/ASME	B/SB-26	319.0, T6	26	A03190	25	Castings
ASTM/ASME	B/SB-26	328.0, F	26	A03280	25	Castings
ASTM/ASME	B/SB-26	328.0, T6	26	A03280	25	Castings
ASTM/ASME	B/SB-26	356.0, F	26	A03560	24.2	Castings
ASTM/ASME	B/SB-26	356.0, T51	26	A03560	24.2	Castings
ASTM/ASME	B/SB-26	356.0, T6	26	A03560	24.2	Castings
ASTM/ASME	B/SB-26	356.0, T7	26	A03560	24.2	Castings
ASTM/ASME	B/SB-26	356.0, T71	26	A03560	24.2	Castings
ASTM/ASME	B/SB-26	443.0	26	A04430	24.1	Castings
ASTM/ASME	B/SB-26	512.0	26	A05120	23.1	Castings
ASTM/ASME	B/SB-26	514.0	26	A05140	23.1	Castings
ASTM/ASME	B/SB-26	535.0	26	A05350	—	Castings
ASTM/ASME	B/SB-26	705.0, T5	26	A07050	23.2	Castings
ASTM/ASME	B/SB-26	710.0, T5	26	A07100	23.2	Castings
ASTM/ASME	B/SB-26	A356.0, T6	26	A13560	24.2	Castings
ASTM/ASME	B/SB-26	A356.0, T61	26	A13560	24.2	Castings
ASTM/ASME	B/SB-26	B443.0	26	A24430	24.1	Castings
ASTM/ASME	B/SB-42	—	31	C10200	31	Seamless Pipe
ASTM/ASME	B/SB-42	—	31	C10300	31	Seamless Pipe
ASTM/ASME	B/SB-42	—	31	C10800	31	Seamless Pipe
ASTM/ASME	B/SB-42	—	31	C12000	31	Seamless Pipe
ASTM/ASME	B/SB-42	—	31	C12200	31	Seamless Pipe
ASTM/ASME	B/SB-43	—	32	C23000	32.1	Seamless Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM	B68	—	31	C10200	31	Tube
ASTM	B68	—	31	C10300	31	Tube
ASTM	B68	—	31	C10800	31	Tube
ASTM	B68	—	31	C12000	31	Tube
ASTM	B68	—	31	C12200	31	Tube
ASTM/ASME	B/SB-75	—	31	C10100	31	Seamless Tube
ASTM/ASME	B/SB-75	—	31	C10200	31	Seamless Tube
ASTM/ASME	B/SB-75	—	31	C10300	31	Seamless Tube
ASTM/ASME	B/SB-75	—	31	C10800	31	Seamless Tube
ASTM/ASME	B/SB-75	—	31	C12000	31	Seamless Tube
ASTM/ASME	B/SB-75	—	31	C12200	31	Seamless Tube
ASTM/ASME	B/SB-75	—	31	C14200	31	Seamless Tube
ASTM	B80	AZ91C, F	83	M11914	—	Castings
ASTM	B80	AZ92A, F	83	M11920	—	Castings
ASTM	B80	K1A	83	M18010	—	Castings
ASTM	B88	—	31	C10200	31	Tube
ASTM	B88	—	31	C12000	31	Tube
ASTM	B88	—	31	C12200	31	Tube
ASTM	B90	AZ31B	81	M11311	—	Plate & Sheet
ASTM	B90	AZ31C	81	M11312	—	Sheet
ASTM	B90	AZ31C	81	M11312	—	Plate & Sheet
ASTM	B90	HK31A	81	M13310	—	Plate
ASTM	B90	HK31A	81	M13310	—	Plate & Sheet
ASTM	B90	HK31A	81	M13310	—	Plate
ASTM	B90	ZE10A	81	M16100	—	Sheet
ASTM	B90	ZE10A	81	M16100	—	Plate
ASTM	B90	ZE10A	81	M16100	—	Sheet
ASTM	B91	AZ31B	81	M11311	—	Forgings
ASTM	B91	AZ61A	81	M11610	—	Forgings
ASTM/ASME	B/SB-96	—	33	C65100	37	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-96	—	33	C65400	37	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-96	—	33	C65500	37	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-98	—	33	C65100	37	Rod, Bar, & Shapes
ASTM/ASME	B/SB-98	—	33	C65500	37	Rod, Bar, & Shapes
ASTM/ASME	B/SB-98	—	33	C66100	37	Rod, Bar, & Shapes
ASTM	B107	AZ31B	81	M11311	—	Bar, Rods, Profiles, & Wire
ASTM	B107	AZ31B	81	M11311	—	Bar, Rods, Profiles, & Wire
ASTM	B107	AZ31B	81	M11311	—	Bar, Rods, Profiles, & Wire
ASTM	B107	AZ31B	81	M11311	—	Bar, Rods, Profiles, & Wire
ASTM	B107	AZ31B	81	M11311	—	Hollow Profiles
ASTM	B107	AZ31B	81	M11311	—	Tube
ASTM	B107	AZ31B	81	M11311	—	Tube
ASTM	B107	AZ31C	81	M11312	—	Tube
ASTM	B107	AZ31C	81	M11312	—	Bar, Rods, Profiles, & Wire

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM	B107	AZ31C	81	M11312	—	Bar, Rods, Profiles, & Wire
ASTM	B107	AZ31C	81	M11312	—	Bar, Rods, Profiles, & Wire
ASTM	B107	AZ31C	81	M11312	—	Bar, Rods, Profiles, & Wire
ASTM	B107	AZ31C	81	M11312	—	Tube
ASTM	B107	AZ31C	81	M11312	—	Hollow Profiles
ASTM	B107	AZ61A	81	M11610	—	Hollow Profiles
ASTM	B107	AZ61A	81	M11610	—	Bar, Rods, Profiles, & Wire
ASTM	B107	AZ61A	81	M11610	—	Bar, Rods, Profiles, & Wire
ASTM	B107	AZ61A	81	M11610	—	Tube
ASTM	B107	AZ61A	81	M11610	—	Bar, Rods, Profiles, & Wire
ASTM	B107	M1A	81	M15100	—	Tube
ASTM	B107	M1A	81	M15100	—	Bar, Rods, Profiles, & Wire
ASTM	B107	M1A	81	M15100	—	Bar, Rods, Profiles, & Wire
ASTM	B107	M1A	81	M15100	—	Bar, Rods, Profiles, & Wire
ASTM	B107	M1A	81	M15100	—	Hollow Profiles
ASTM/ASME	B/SB-108	308.0	26	A03080	25	Castings
ASTM/ASME	B/SB-108	319.0	26	A03190	25	Castings
ASTM/ASME	B/SB-108	333.0, F	26	A03330	25	Castings
ASTM/ASME	B/SB-108	333.0, T5	26	A03330	25	Castings
ASTM/ASME	B/SB-108	333.0, T6	26	A03330	25	Castings
ASTM/ASME	B/SB-108	333.0, T7	26	A03330	25	Castings
ASTM/ASME	B/SB-108	356.0, F	26	A03560	24.2	Castings
ASTM/ASME	B/SB-108	356.0, T6	26	A03560	24.2	Castings
ASTM/ASME	B/SB-108	356.0, T71	26	A03560	24.2	Castings
ASTM/ASME	B/SB-108	443.0	26	A04430	24.1	Castings
ASTM/ASME	B/SB-108	513.0	26	A05130	23.2	Castings
ASTM/ASME	B/SB-108	535.0	26	A05350	—	Castings
ASTM/ASME	B/SB-108	A356.0	26	A13560	24.2	Castings
ASTM/ASME	B/SB-108	A444.0	26	A14440	24.1	Castings
ASTM/ASME	B/SB-108	B443.0	26	A24430	24.1	Castings
ASTM/ASME	B/SB-111	—	31	C10100	31	Seamless Tube
ASTM/ASME	B/SB-111	—	31	C10200	31	Seamless Tube
ASTM/ASME	B/SB-111	—	31	C10300	31	Seamless Tube
ASTM/ASME	B/SB-111	—	31	C10800	31	Seamless Tube
ASTM/ASME	B/SB-111	—	31	C12000	31	Seamless Tube
ASTM/ASME	B/SB-111	—	31	C12200	31	Seamless Tube
ASTM/ASME	B/SB-111	—	31	C14200	31	Seamless Tube
ASTM/ASME	B/SB-111	—	31	C19200	31	Seamless Tube
ASTM/ASME	B/SB-111	—	32	C23000	32.1	Seamless Tube
ASTM/ASME	B/SB-111	—	32	C28000	32.1	Seamless Tube
ASTM/ASME	B/SB-111	—	32	C44300	32.2	Seamless Tube
ASTM/ASME	B/SB-111	—	32	C44400	32.2	Seamless Tube
ASTM/ASME	B/SB-111	—	32	C44500	32.2	Seamless Tube
ASTM/ASME	B/SB-111	—	35	C60800	35	Seamless Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-111	—	35	C61300	35	Seamless Tube
ASTM/ASME	B/SB-111	—	35	C61400	35	Seamless Tube
ASTM/ASME	B/SB-111	—	32	C68700	32.2	Seamless Tube
ASTM/ASME	B/SB-111	—	34	C70400	34	Seamless Tube
ASTM/ASME	B/SB-111	—	34	C70600	34	Seamless Tube
ASTM/ASME	B/SB-111	—	34	C71000	34	Seamless Tube
ASTM/ASME	B/SB-111	—	34	C71500	34	Seamless Tube
ASTM/ASME	B/SB-111	—	34	C71640	34	Seamless Tube
ASTM/ASME	B/SB-111	—	34	C72200	34	Seamless Tube
ASTM/ASME	B/SB-127	—	42	N04400	42	Plate, Sheet, & Strip
ASTM/ASME	B/SB-135	—	32	C22000	32.1	Seamless Tube
ASTM/ASME	B/SB-135	—	32	C23000	32.1	Seamless Tube
ASTM/ASME	B/SB-148	—	35	C95200	35	Castings
ASTM/ASME	B/SB-148	—	35	C95300	35	Castings
ASTM/ASME	B/SB-148	—	35	C95400	35	Castings
ASTM/ASME	B/SB-148	—	35	C95410	35	Castings
ASTM/ASME	B/SB-148	—	35	C95500	35	Castings
ASTM/ASME	B/SB-148	—	35	C95600	35	Castings
ASTM/ASME	B/SB-148	—	35	C95700	35	Castings
ASTM/ASME	B/SB-148	—	35	C95800	35	Castings
ASTM/ASME	B/SB-150	—	35	C61300	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C61300	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C61300	35	Bar & Rod (Hex & Oct)
ASTM/ASME	B/SB-150	—	35	C61300	35	Bar & Rod (Hex & Oct)
ASTM/ASME	B/SB-150	—	35	C61300	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C61300	35	Bar & Rod (Hex & Oct)
ASTM/ASME	B/SB-150	—	35	C61300	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C61400	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C61400	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C61400	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C61400	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C61900	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C61900	35	Shapes
ASTM/ASME	B/SB-150	—	35	C61900	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C61900	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C61900	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C61900	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C61900	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C62300	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C62300	35	Shapes
ASTM/ASME	B/SB-150	—	35	C62300	35	Bar & Rod (Hex & Oct)
ASTM/ASME	B/SB-150	—	35	C62300	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C62300	35	Bar & Rod (Hex & Oct)
ASTM/ASME	B/SB-150	—	35	C62300	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C62300	35	Rod (Round)

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-150	—	35	C62300	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C62300	35	Bar & Rod (Hex & Oct)
ASTM/ASME	B/SB-150	—	35	C62400	35	Shapes
ASTM/ASME	B/SB-150	—	35	C62400	35	Bar & Rod (Hex & Oct)
ASTM/ASME	B/SB-150	—	35	C62400	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C62400	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C62400	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C62400	35	Rod (Round)
ASTM/ASME	B/SB-150	—	35	C63000	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C63000	35	Shapes
ASTM/ASME	B/SB-150	—	35	C63000	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C63000	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C63000	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C63020	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C63020	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C63020	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C63200	35	Bar, Rod, & Shapes
ASTM/ASME	B/SB-150	—	35	C64200	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C64200	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C64200	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C64200	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C64200	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C64200	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C64200	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C64200	35	Bar & Rod
ASTM/ASME	B/SB-150	—	35	C64200	35	Shapes
ASTM/ASME	B/SB-151	—	34	C70600	34	Rod & Bar
ASTM/ASME	B/SB-151	—	34	C71500	34	Sq Bar & Rod (Rnd, Hex, Oct)
ASTM/ASME	B/SB-151	—	34	C71500	34	Sq Bar & Rod (Rnd, Hex, Oct)
ASTM/ASME	B/SB-151	—	34	C71500	34	Sq Bar & Rod (Rnd, Hex, Oct)
ASTM/ASME	B/SB-151	—	34	C71500	34	Bar (Rect.) & Shapes
ASTM/ASME	B/SB-152	—	31	C10100	31	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-152	—	31	C10200	31	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-152	—	31	C10300	31	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-152	—	31	C10400	31	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-152	—	31	C10500	31	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-152	—	31	C10700	31	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-152	—	31	C10800	31	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-152	—	31	C11000	31	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-152	—	31	C12000	31	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-152	—	31	C12200	31	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-152	—	31	C12300	31	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-152	—	31	C14200	31	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-152	—	31	C14420	31	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-160	—	41	N02200	41	Rod & Bar
ASTM/ASME	B/SB-160	—	41	N02201	41	Rod & Bar

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-161	—	41	N02200	41	Seamless Pipe & Tube
ASTM/ASME	B/SB-161	—	41	N02201	41	Seamless Pipe & Tube
ASTM/ASME	B/SB-162	—	41	N02200	41	Plate, Sheet, & Strip
ASTM/ASME	B/SB-162	—	41	N02201	41	Plate, Sheet, & Strip
ASTM/ASME	B/SB-163	—	41	N02200	41	Seamless Tube
ASTM/ASME	B/SB-163	—	41	N02201	41	Seamless Tube
ASTM/ASME	B/SB-163	—	42	N04400	42	Seamless Tube
ASTM/ASME	B/SB-163	—	43	N06025	43	Seamless Tube
ASTM/ASME	B/SB-163	—	46	N06045	45	Seamless Tube
ASTM/ASME	B/SB-163	—	43	N06600	43	Seamless Tube
ASTM/ASME	B/SB-163	—	43	N06601	43	Seamless Tube
ASTM/ASME	B/SB-163	—	43	N06690	43	Seamless Tube
ASTM/ASME	B/SB-163	—	45	N08120	45	Seamless Tube
ASTM/ASME	B/SB-163	—	45	N08800	45	Seamless Tube
ASTM/ASME	B/SB-163	—	45	N08801	45	Seamless Tube
ASTM/ASME	B/SB-163	—	45	N08810	45	Seamless Tube
ASTM/ASME	B/SB-163	—	45	N08811	45	Seamless Tube
ASTM/ASME	B/SB-163	—	45	N08825	45	Seamless Tube
ASTM/ASME	B/SB-164	—	42	N04400	42	Rod, Bar, & Wire
ASTM/ASME	B/SB-164	—	42	N04405	42	Rod, Bar, & Wire
ASTM/ASME	B/SB-165	—	42	N04400	42	Seamless Pipe & Tube
ASTM/ASME	B/SB-166	—	43	N06025	43	Rod, Bar, & Wire
ASTM/ASME	B/SB-166	—	46	N06045	45	Rod, Bar, & Wire
ASTM/ASME	B/SB-166	—	43	N06600	43	Rod, Bar, & Wire
ASTM/ASME	B/SB-166	—	43	N06601	43	Rod, Bar, & Wire
ASTM/ASME	B/SB-166	—	43	N06617	46	Rod, Bar, & Wire
ASTM/ASME	B/SB-166	—	43	N06690	43	Rod, Bar, & Wire
ASTM/ASME	B/SB-167	—	43	N06025	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-167	—	46	N06045	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-167	—	43	N06600	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-167	—	43	N06601	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-167	—	43	N06617	46	Seamless Pipe & Tube
ASTM/ASME	B/SB-167	—	43	N06690	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-168	—	43	N06025	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-168	—	46	N06045	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-168	—	43	N06600	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-168	—	43	N06601	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-168	—	43	N06617	46	Plate, Sheet, & Strip
ASTM/ASME	B/SB-168	—	43	N06690	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-169	—	35	C61300	35	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-169	—	35	C61300	35	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-169	—	35	C61300	35	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-169	—	35	C61400	35	Plate, Sheet, Strip, & Bar
ASTM/ASME	B/SB-169	—	35	C61400	35	Plate, Sheet, Strip, & Bar

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-169	—	35	C61400	35	Plate, Sheet, Strip, & Bar
ASTM	B170	1	31	C10100	31	Shapes
ASTM	B170	2	31	C10200	31	Shapes
ASTM/ASME	B/SB-171	—	32	C44300	32.2	Plate & Sheet
ASTM/ASME	B/SB-171	—	32	C44400	32.2	Plate & Sheet
ASTM/ASME	B/SB-171	—	32	C44500	32.2	Plate & Sheet
ASTM/ASME	B/SB-171	—	32	C46400	32.2	Plate & Sheet
ASTM/ASME	B/SB-171	—	32	C46500	32.2	Plate & Sheet
ASTM/ASME	B/SB-171	—	35	C61300	35	Plate & Sheet
ASTM/ASME	B/SB-171	—	35	C61300	35	Plate & Sheet
ASTM/ASME	B/SB-171	—	35	C61300	35	Plate & Sheet
ASTM/ASME	B/SB-171	—	35	C61400	35	Plate & Sheet
ASTM/ASME	B/SB-171	—	35	C61400	35	Plate & Sheet
ASTM/ASME	B/SB-171	—	35	C63000	35	Plate & Sheet
ASTM/ASME	B/SB-171	—	35	C63000	35	Plate & Sheet
ASTM/ASME	B/SB-171	—	35	C63000	35	Plate & Sheet
ASTM/ASME	B/SB-171	—	35	C63200	35	Plate & Sheet
ASTM/ASME	B/SB-171	—	35	C63200	35	Plate & Sheet
ASTM/ASME	B/SB-171	—	35	C63200	35	Plate & Sheet
ASTM/ASME	B/SB-171	—	35	C63200	35	Plate & Sheet
ASTM/ASME	B/SB-171	—	34	C70600	34	Plate & Sheet
ASTM/ASME	B/SB-171	—	34	C71500	34	Plate & Sheet
ASTM/ASME	B/SB-171	—	34	C71500	34	Plate & Sheet
ASTM/ASME	B/SB-171	—	34	C72200	34	Plate & Sheet
ASTM	A182	F904L	45	N08904	8.2	Forgings
ASTM/ASME	B/SB-187	—	31	C10100	31	Rod & Bar
ASTM/ASME	B/SB-187	—	31	C10200	31	Rod & Bar
ASTM/ASME	B/SB-187	—	31	C10300	31	Rod & Bar
ASTM/ASME	B/SB-187	—	31	C10400	31	Rod & Bar
ASTM/ASME	B/SB-187	—	31	C10700	31	Rod & Bar
ASTM/ASME	B/SB-187	—	31	C10940	31	Rod & Bar
ASTM/ASME	B/SB-187	—	31	C11000	31	Rod & Bar
ASTM/ASME	B/SB-187	—	31	C14420	31	Rod & Bar
ASTM	B199	AM100A	83	M10100	—	Castings
ASTM	B199	AZ91C, F	83	M11914	—	Castings
ASTM	B199	AZ92A, F	83	M11920	—	Castings
ASTM/ASME	B/SB-209	1060	21	A91060	21	Plate & Sheet
ASTM/ASME	B/SB-209	1100	21	A91100	21	Plate & Sheet
ASTM/ASME	B/SB-209	2014	24	A92014	26	Plate & Sheet
ASTM/ASME	B/SB-209	2219	24	A92219	26	Plate & Sheet
ASTM/ASME	B/SB-209	3003	21	A93003	22.1	Plate & Sheet
ASTM/ASME	B/SB-209	3004	22	A93004	22.2	Plate & Sheet
ASTM/ASME	B/SB-209	3005	22	A93005	22.2	Plate & Sheet
ASTM/ASME	B/SB-209	3105	22	A93105	22.2	Plate & Sheet
ASTM/ASME	B/SB-209	5005	22	A95005	22.2	Plate & Sheet

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-209	5010	22	A95010	22.2	Plate & Sheet
ASTM/ASME	B/SB-209	5050	21	A95050	22.2	Plate & Sheet
ASTM/ASME	B/SB-209	5052	22	A95052	22.3	Plate & Sheet
ASTM/ASME	B/SB-209	5083	25	A95083	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5083	25	A95083	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5083	25	A95083	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5083	25	A95083	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5083	25	A95083	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5083	25	A95083	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5086	25	A95086	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5154	22	A95154	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5252	22	A95252	22.3	Plate & Sheet
ASTM/ASME	B/SB-209	5254	22	A95254	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5454	22	A95454	22.3	Plate & Sheet
ASTM/ASME	B/SB-209	5456	25	A95456	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5456	25	A95456	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5456	25	A95456	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5456	25	A95456	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5456	25	A95456	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5456	25	A95456	22.4	Plate & Sheet
ASTM/ASME	B/SB-209	5457	22	A95457	22.2	Plate & Sheet
ASTM/ASME	B/SB-209	5652	22	A95652	22.3	Plate & Sheet
ASTM/ASME	B/SB-209	6061	23	A96061	23.1	Plate & Sheet
ASTM/ASME	B/SB-209	Alclad 2014	24	A82014	—	Plate & Sheet
ASTM/ASME	B/SB-209	Alclad 2219	24	A82219	—	Plate & Sheet
ASTM/ASME	B/SB-209	Alclad 3003	21	—	—	Plate & Sheet
ASTM/ASME	B/SB-209	Alclad 3003	21	—	—	Plate & Sheet
ASTM/ASME	B/SB-209	Alclad 3003	21	A83003	—	Plate & Sheet
ASTM/ASME	B/SB-209	Alclad 3003	21	A83003	—	Plate & Sheet
ASTM/ASME	B/SB-209	Alclad 3004	22	—	—	Plate & Sheet
ASTM/ASME	B/SB-209	Alclad 3004	22	—	—	Plate & Sheet
ASTM/ASME	B/SB-209	Alclad 3004	22	—	—	Plate & Sheet
ASTM/ASME	B/SB-209	Alclad 3004	22	—	—	Plate & Sheet
ASTM/ASME	B/SB-209	Alclad 6061	23	—	—	Plate & Sheet
ASTM/ASME	B/SB-209	Alclad 6061	23	A86061	—	Plate & Sheet
ASTM/ASME	B/SB-209	Alclad 6061	23	A86061	—	Plate & Sheet
ASTM/ASME	B/SB-210	1060	21	A91060	21	Seamless Tube
ASTM	B210	1100	21	A91100	21	Seamless Tube
ASTM	B210	2014	24	A92014	26	Seamless Tube
ASTM/ASME	B/SB-210	3003	21	A93003	22.1	Seamless Tube
ASTM	B210	3102	21	A93102	22.1	Seamless Tube
ASTM	B210	3303	21	A93303	—	Seamless Tube
ASTM	B210	5005	22	A95005	22.2	Seamless Tube
ASTM	B210	5050	21	A95050	22.2	Seamless Tube
ASTM/ASME	B/SB-210	5052	22	A95052	22.3	Seamless Tube
ASTM	B210	5083	25	A95083	22.4	Seamless Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM	B210	5086	25	A95086	22.4	Seamless Tube
ASTM/ASME	B/SB-210	5154	22	A95154	22.4	Seamless Tube
ASTM	B210	5456	25	A95456	22.4	Seamless Tube
ASTM/ASME	B/SB-210	6061	23	A96061	23.1	Seamless Tube
ASTM/ASME	B/SB-210	6063	23	A96063	23.1	Seamless Tube
ASTM/ASME	B/SB-210	Alclad 3003	21	—	—	Seamless Tube
ASTM	B210	Alclad 3003	21	A83003	—	Seamless Tube
ASTM	B210	Alclad 3102	21	—	—	Seamless Tube
ASTM	B210	Alclad 3303	21	—	—	Seamless Tube
ASTM/ASME	B/SB-211	1060	21	A91060	21	Bar, Rod, & Wire
ASTM/ASME	B/SB-211	1100	21	A91100	21	Bar, Rod, & Wire
ASTM/ASME	B/SB-211	2014	24	A92014	26	Bar, Rod, & Wire
ASTM/ASME	B/SB-211	2219	24	A92219	26	Bar, Rod, & Wire
ASTM/ASME	B/SB-211	3003	21	A93003	22.1	Bar, Rod, & Wire
ASTM/ASME	B/SB-211	5052	22	A95052	22.3	Bar, Rod, & Wire
ASTM/ASME	B/SB-211	5056	25	A95056	22.4	Bar, Rod, & Wire
ASTM/ASME	B/SB-211	5154	22	A95154	22.4	Bar, Rod, & Wire
ASTM/ASME	B/SB-211	6061	23	A96061	23.1	Bar, Rod, & Wire
ASTM/ASME	B/SB-211	Alclad 5056	25	—	—	Bar, Rod, & Wire
ASTM/ASME	B/SB-221	1060	21	A91060	21	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	1100	21	A91100	21	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	2014	24	A92014	26	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	2219	24	A92219	26	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	3003	21	A93003	22.1	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	3004	22	A93004	22.2	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	3102	21	A93102	22.1	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	5052	22	A95052	22.3	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	5083	25	A95083	22.4	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	5086	25	A95086	22.4	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	5154	22	A95154	22.4	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	5454	22	A95454	22.3	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	5456	25	A95456	22.4	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	6005	23	A96005	23.1	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	6005A	23	A96005	23.1	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	6061	23	A96061	23.1	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	6063	23	A96063	23.1	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	6105	23	A96105	23.1	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	6162	23	A96162	23.1	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	6351	23	A96351	23.1	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	6463	23	A96463	23.1	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	7005	27	A97005	23.2	Bar, Rod, & Shapes
ASTM/ASME	B/SB-221	Alclad 3003	21	A83003	—	Bar, Rod, & Shapes
ASTM	B230	1350	21	A91350	21	Wire
ASTM/ASME	B/SB-234	1060	21	A91060	21	Seamless Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-234	3003	21	A93003	22.1	Seamless Tube
ASTM/ASME	B/SB-234	5052	22	A95052	22.3	Seamless Tube
ASTM/ASME	B/SB-234	5454	22	A95454	22.3	Seamless Tube
ASTM/ASME	B/SB-234	6061	23	A96061	23.1	Seamless Tube
ASTM/ASME	B/SB-234	Alclad 3003	21	—	—	Seamless Tube
ASTM/ASME	B/SB-234	Alclad 3003	21	A83003	—	Seamless Tube
ASTM	B236	1350	21	A91350	21	Bar
ASTM	A240	—	45	N08367	8.2	Sheet & Strip
ASTM	A240	—	45	N08367	8.2	Plate
ASTM	A240	904L	45	N08904	8.2	Plate, Sheet, & Strip
ASTM/ASME	B/SB-241	1060	21	A91060	21	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	1100	21	A91100	21	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	2014	24	A92014	26	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	2219	24	A92219	26	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	3003	21	A93003	22.1	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	5052	22	A95052	22.3	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	5083	25	A95083	22.4	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	5086	25	A95086	22.4	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	5454	22	A95454	22.3	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	5456	25	A95456	22.4	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	6061	23	A96061	23.1	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	6063	23	A96063	23.1	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	6162	23	A96162	23.1	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	6351	23	A96351	23.1	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	Alclad 3003	21	—	—	Seamless Pipe & Tube
ASTM/ASME	B/SB-241	Alclad 3003	21	A83003	—	Seamless Pipe & Tube
ASTM/ASME	B/SB-247	1100	21	A91100	21	Forgings
ASTM/ASME	B/SB-247	2014	24	A92014	26	Forgings
ASTM/ASME	B/SB-247	2219	24	A92219	26	Forgings
ASTM/ASME	B/SB-247	3003	21	A93003	22.1	Forgings
ASTM/ASME	B/SB-247	5083	25	A95083	22.4	Forgings
ASTM/ASME	B/SB-247	6061	23	A96061	23.1	Forgings
ASTM/ASME	B/SB-247	6151	23	A96151	23.1	Forgings
ASTM	A249	—	45	N08367	8.2	Welded Tube
ASTM	A249	—	45	N08367	8.2	Welded Tube
ASTM/ASME	A/SA-249	—	45	N08904	8.2	Welded Tube
ASTM/ASME	B/SB-265	1	51	R50250	51	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	11	51	R52250	51	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	12	52	R53400	52	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	13	51	R53413	52	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	14	52	R53414	52	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	15	52	R53415	52	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	16	51	R52402	51	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	16H	51	R52402	51	Plate, Sheet, & Strip

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-265	17	51	R52252	51	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	18	53	R56322	53	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	19	53	R58640	54	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	2	51	R50400	51	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	20	53	R58645	54	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	21	53	R58210	54	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	24	54	R56405	53	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	25	54	R56403	53	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	26	51	R52404	51	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	26H	51	R52404	51	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	27	51	R52254	51	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	28	53	R56323	53	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	29	54	R56404	53	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	2H	51	R50400	51	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	3	52	R50550	52	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	30	51	R53530	52	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	31	52	R53532	52	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	32	53	R55111	52	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	33	51	R53442	54	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	34	52	R53445	54	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	35	54	R56340	53	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	4	53	R50700	51.4	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	5	54	R56400	53	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	6	54	R54520	52	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	7	51	R52400	51	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	7H	51	R52400	51	Plate, Sheet, & Strip
ASTM/ASME	B/SB-265	9	53	R56320	53	Plate, Sheet, & Strip
ASTM/ASME	B/SB-271	—	35	C95200	35	Castings
ASTM/ASME	B/SB-271	—	35	C95300	35	Castings
ASTM/ASME	B/SB-271	—	35	C95400	35	Castings
ASTM/ASME	B/SB-271	—	35	C95410	35	Castings
ASTM/ASME	B/SB-271	—	35	C95500	35	Castings
ASTM	B280	102	31	C10200	31	Seamless Tube
ASTM	B280	120	31	C12000	31	Seamless Tube
ASTM	B280	122	31	C12200	31	Seamless Tube
ASTM/ASME	B/SB-283	—	35	C64200	35	Forgings
ASTM/ASME	B/SB-283	—	35	C64200	35	Forgings
ASTM/ASME	B/SB-283	—	33	C65500	31	Forgings
ASTM	B302	—	31	C12000	31	Pipe
ASTM	B302	—	31	C12200	31	Pipe
ASTM/ASME	B/SB-308	6061	23	A96061	23.1	Shapes
ASTM	A312	—	45	N08904	8.2	Seamless & Welded Pipe
ASTM	A312	N08367	45	N08367	8.2	Seamless & Welded Pipe
ASTM	A312	N08367	45	N08367	8.2	Seamless & Welded Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM	B313	1100	21	A91100	21	Welded Tube
ASTM	B313	3003	21	A93003	22.1	Welded Tube
ASTM	B313	3004	22	A93004	22.2	Welded Tube
ASTM	B313	3005	22	A93005	22.2	Welded Tube
ASTM	B313	5050	21	A95050	22.2	Welded Tube
ASTM	B313	5052	22	A95052	22.3	Welded Tube
ASTM	B313	5086	25	A95086	22.4	Welded Tube
ASTM	B313	5154	22	A95154	22.4	Welded Tube
ASTM	B313	6061	23	A96061	23.1	Welded Tube
ASTM	B313	Alclad 3004	22	—	—	Welded Tube
ASTM/ASME	B/SB-315	—	35	C61300	35	Seamless Pipe & Tube
ASTM/ASME	B/SB-315	—	35	C61400	35	Seamless Pipe & Tube
ASTM/ASME	B/SB-315	—	33	C65100	37	Seamless Pipe & Tube
ASTM/ASME	B/SB-315	—	33	C65500	33	Seamless Pipe & Tube
ASTM	B317	6101	23	A96101	23.1	Bar, Rod, Shapes, & Tube
ASTM	B324	1350	21	A91350	21	Wire
ASTM/ASME	B/SB-333	—	44	N10001	44	Plate, Sheet, & Strip
ASTM/ASME	B/SB-333	—	44	N10001	44	Plate, Sheet, & Strip
ASTM/ASME	B/SB-333	—	44	N10624	44	Plate, Sheet, & Strip
ASTM/ASME	B/SB-333	—	44	N10629	44	Plate, Sheet, & Strip
ASTM/ASME	B/SB-333	—	44	N10665	44	Plate, Sheet, & Strip
ASTM/ASME	B/SB-333	—	44	N10675	44	Plate, Sheet, & Strip
ASTM/ASME	B/SB-335	—	44	N10001	44	Rod
ASTM/ASME	B/SB-335	—	44	N10001	44	Rod
ASTM/ASME	B/SB-335	—	44	N10624	44	Rod
ASTM/ASME	B/SB-335	—	44	N10629	44	Rod
ASTM/ASME	B/SB-335	—	44	N10665	44	Rod
ASTM/ASME	B/SB-335	—	44	N10675	44	Rod
ASTM	B337	1	51	R50250	51	Seamless & Welded Pipe
ASTM	B337	11	51	R52250	51	Seamless & Welded Pipe
ASTM	B337	12	52	R53400	52	Seamless & Welded Pipe
ASTM	B337	2	51	R50400	51	Seamless & Welded Pipe
ASTM	B337	3	52	R50550	52	Seamless & Welded Pipe
ASTM	B337	7	51	R52400	51	Seamless & Welded Pipe
ASTM	B337	9	53	R56320	53	Seamless & Welded Pipe
ASTM/ASME	B/SB-338	1	51	R50250	51	Seamless & Welded Tube
ASTM/ASME	B/SB-338	11	51	R52250	51	Seamless & Welded Tube
ASTM/ASME	B/SB-338	12	52	R53400	52	Seamless & Welded Tube
ASTM/ASME	B/SB-338	13	51	R53413	52	Seamless & Welded Tube
ASTM/ASME	B/SB-338	14	52	R53414	52	Seamless & Welded Tube
ASTM/ASME	B/SB-338	15	52	R53415	52	Seamless & Welded Tube
ASTM/ASME	B/SB-338	16	51	R52402	51	Seamless & Welded Tube
ASTM/ASME	B/SB-338	16H	51	R52402	51	Seamless & Welded Tube
ASTM/ASME	B/SB-338	17	51	R52252	51	Seamless & Welded Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-338	18	53	R56322	53	Seamless & Welded Tube
ASTM/ASME	B/SB-338	2	51	R50400	51	Seamless & Welded Tube
ASTM/ASME	B/SB-338	26	51	R52404	51	Seamless & Welded Tube
ASTM/ASME	B/SB-338	26H	51	R52404	51	Seamless & Welded Tube
ASTM/ASME	B/SB-338	27	51	R52254	51	Seamless & Welded Tube
ASTM/ASME	B/SB-338	28	53	R56323	53	Seamless & Welded Tube
ASTM/ASME	B/SB-338	2H	51	R50400	51	Seamless & Welded Tube
ASTM/ASME	B/SB-338	3	52	R50550	52	Seamless & Welded Tube
ASTM/ASME	B/SB-338	30	51	R53530	52	Seamless & Welded Tube
ASTM/ASME	B/SB-338	31	52	R53532	52	Seamless & Welded Tube
ASTM/ASME	B/SB-338	33	51	R53442	54	Seamless & Welded Tube
ASTM/ASME	B/SB-338	34	52	R53445	54	Seamless & Welded Tube
ASTM/ASME	B/SB-338	35	54	R56340	53	Seamless & Welded Tube
ASTM/ASME	B/SB-338	7	51	R52400	51	Seamless & Welded Tube
ASTM/ASME	B/SB-338	7H	51	R52400	51	Seamless & Welded Tube
ASTM/ASME	B/SB-338	9	53	R56320	53	Seamless & Welded Tube
ASTM	B345	1060	21	A91060	21	Seamless Pipe & Tube
ASTM	B345	3003	21	A93003	22.1	Seamless Pipe & Tube
ASTM	B345	5083	25	A95083	22.4	Seamless Pipe & Tube
ASTM	B345	5086	25	A95086	22.4	Seamless Pipe & Tube
ASTM	B345	6061	23	A96061	23.1	Seamless Pipe & Tube
ASTM	B345	6063	23	A96063	23.1	Seamless Pipe & Tube
ASTM	B345	6351	23	A96351	23.1	Seamless Pipe & Tube
ASTM	B345	Alclad 3003	21	A83003	—	Seamless Pipe & Tube
ASTM/ASME	B/SB-348	1	51	R50250	51	Bars & Billets
ASTM/ASME	B/SB-348	11	51	R52250	51	Bars & Billets
ASTM/ASME	B/SB-348	12	52	R53400	52	Bars & Billets
ASTM/ASME	B/SB-348	13	51	R53413	52	Bars & Billets
ASTM/ASME	B/SB-348	14	52	R53414	52	Bars & Billets
ASTM/ASME	B/SB-348	15	52	R53415	52	Bars & Billets
ASTM/ASME	B/SB-348	16	51	R52402	51	Bars & Billets
ASTM/ASME	B/SB-348	16H	51	R52402	51	Bars & Billets
ASTM/ASME	B/SB-348	17	51	R52252	51	Bars & Billets
ASTM/ASME	B/SB-348	18	53	R56322	53	Bars & Billets
ASTM/ASME	B/SB-348	19	53	R58640	54	Bars & Billets
ASTM/ASME	B/SB-348	2	51	R50400	51	Bars & Billets
ASTM/ASME	B/SB-348	20	53	R58645	54	Bars & Billets
ASTM/ASME	B/SB-348	21	53	R58210	54	Bars & Billets
ASTM/ASME	B/SB-348	23	54	R56407	53	Bars & Billets
ASTM/ASME	B/SB-348	24	54	R56405	53	Bars & Billets
ASTM/ASME	B/SB-348	25	54	R56403	53	Bars & Billets
ASTM/ASME	B/SB-348	26	51	R52404	51	Bars & Billets
ASTM/ASME	B/SB-348	26H	51	R52404	51	Bars & Billets
ASTM/ASME	B/SB-348	28	53	R56323	53	Bars & Billets

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-348	2H	51	R50400	51	Bars & Billets
ASTM/ASME	B/SB-348	3	52	R50550	52	Bars & Billets
ASTM/ASME	B/SB-348	30	51	R53530	52	Bars & Billets
ASTM/ASME	B/SB-348	31	52	R53532	52	Bars & Billets
ASTM/ASME	B/SB-348	32	53	R55111	52	Bars & Billets
ASTM/ASME	B/SB-348	33	51	R53442	54	Bars & Billets
ASTM/ASME	B/SB-348	34	52	R53445	54	Bars & Billets
ASTM/ASME	B/SB-348	35	54	R56340	53	Bars & Billets
ASTM/ASME	B/SB-348	4	53	R50700	51.4	Bars & Billets
ASTM/ASME	B/SB-348	5	54	R56400	53	Bars & Billets
ASTM/ASME	B/SB-348	6	54	R54520	52	Bars & Billets
ASTM/ASME	B/SB-348	7	51	R52400	51	Bars & Billets
ASTM/ASME	B/SB-348	7H	51	R52400	51	Bars & Billets
ASTM/ASME	B/SB-348	9	53	R56320	53	Bars & Billets
ASTM/ASME	A/SA-351	CN7M	45	N08007	8.2	Castings
ASTM/ASME	A/SA-351	CT15C	45	N08151	45	Castings
ASTM	B351	R60001	61	R60001	61	Bar, Rod, & Wire
ASTM	B351	R60802	61	R60802	61	Bar, Rod, & Wire
ASTM	B351	R60804	61	R60804	61	Bar, Rod, & Wire
ASTM	B351	R60901	62	R60901	62	Bar, Rod, & Wire
ASTM	B353	R60001	61	R60001	61	Plate, Sheet, & Strip
ASTM	B352	R60802	61	R60802	61	Plate, Sheet, & Strip
ASTM	B352	R60804	61	R60804	61	Sheet & Strip
ASTM	B352	R60804	61	R60804	61	Plate
ASTM	B352	R60901	62	R60901	62	Plate, Sheet, & Strip
ASTM	B353	R60001	61	R60001	61	Seamless & Welded Tube
ASTM	B353	R60802	61	R60802	61	Seamless & Welded Tube
ASTM	B353	R60804	61	R60804	61	Seamless & Welded Tube
ASTM	B353	R60901	62	R60901	62	Seamless & Welded Tube
ASTM	B353	R60904	62	R60904	62	Seamless & Welded Tube
ASTM	A358	N08367	45	N08367	8.2	Fusion Welded Pipe
ASTM	A358	N08367	45	N08367	8.2	Fusion Welded Pipe
ASTM	B359	—	31	C10100	31	Seamless Tube
ASTM	B359	—	31	C10200	31	Seamless Tube
ASTM	B359	—	31	C10300	31	Seamless Tube
ASTM	B359	—	31	C10800	31	Seamless Tube
ASTM	B359	—	31	C12000	31	Seamless Tube
ASTM/ASME	B/SB-359	—	31	C12200	31	Seamless Tube
ASTM	B359	—	31	C14200	31	Seamless Tube
ASTM	B359	—	31	C19200	31	Seamless Tube
ASTM	B359	—	32	C23000	32.1	Seamless Tube
ASTM/ASME	B/SB-359	—	32	C44300	32.2	Seamless Tube
ASTM/ASME	B/SB-359	—	32	C44400	32.2	Seamless Tube
ASTM/ASME	B/SB-359	—	32	C44500	32.2	Seamless Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM	B359	—	35	C60800	35	Seamless Tube
ASTM	B359	—	32	C68700	32.2	Seamless Tube
ASTM	B359	—	34	C70400	34	Seamless Tube
ASTM/ASME	B/SB-359	—	34	C70600	34	Seamless Tube
ASTM/ASME	B/SB-359	—	34	C71000	34	Seamless Tube
ASTM/ASME	B/SB-359	—	34	C71500	34	Seamless Tube
ASTM	B359	—	34	C72200	34	Seamless Tube
ASTM	B361	5083	25	A95083	22.4	Fittings
ASTM	B361	5154	22	A95154	22.3	Fittings
ASTM	B361	WP Alclad 3003	21	A83003	—	Fittings
ASTM	B361	WP1060	21	A91060	21	Fittings
ASTM	B361	WP1100	21	A91100	21	Fittings
ASTM	B361	WP3003	21	A93003	22.1	Fittings
ASTM	B361	WP6061	23	A96061	23.1	Fittings
ASTM	B361	WP6063	23	A96063	23.1	Fittings
ASTM/ASME	B/SB-363	WPT 1	51	R50250	51	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 11	51	R52250	51	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 12	52	R53400	52	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 13	51	R53413	52	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 14	52	R53414	52	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 15	52	R53415	52	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 16	51	R52402	51	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 16H	51	R52402	51	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 17	51	R52252	51	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 18	53	R56322	53	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 19	53	R58640	54	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 2	51	R50400	51	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 20	53	R58645	54	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 21	53	R58210	54	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 23	54	R56407	53	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 24	54	R56405	53	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 25	54	R56403	53	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 26	51	R52404	51	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 26H	51	R52404	51	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 28	53	R56323	53	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 3	52	R50550	52	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 30	51	R53530	52	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 7	51	R52400	51	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 7H	51	R52400	51	Seamless & Welded Fittings
ASTM/ASME	B/SB-363	WPT 9	53	R56320	53	Seamless & Welded Fittings
ASTM/ASME	B/SB-366	—	41	N02200	41	Fittings
ASTM/ASME	B/SB-366	—	41	N02201	41	Fittings
ASTM/ASME	B/SB-366	—	42	N04400	42	Fittings
ASTM/ASME	B/SB-366	—	43	N06002	43	Fittings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-366	—	45	N06007	43	Fittings
ASTM/ASME	B/SB-366	—	43	N06022	44	Fittings
ASTM/ASME	B/SB-366	—	43	N06025	43	Fittings
ASTM/ASME	B/SB-366	—	45	N06030	45	Fittings
ASTM/ASME	B/SB-366	—	43	N06035	43	Fittings
ASTM/ASME	B/SB-366	—	46	N06045	45	Fittings
ASTM/ASME	B/SB-366	—	43	N06059	43	Fittings
ASTM/ASME	B/SB-366	—	43	N06200	43	Fittings
ASTM/ASME	B/SB-366	—	43	N06210	43	Fittings
ASTM/ASME	B/SB-366	—	43	N06230	43	Fittings
ASTM/ASME	B/SB-366	—	43	N06455	43	Fittings
ASTM/ASME	B/SB-366	—	43	N06600	43	Fittings
ASTM/ASME	B/SB-366	—	43	N06603	43	Fittings
ASTM/ASME	B/SB-366	—	43	N06625	43	Fittings
ASTM/ASME	B/SB-366	—	45	N06985	45	Fittings
ASTM/ASME	B/SB-366	—	45	N08020	45	Fittings
ASTM/ASME	B/SB-366	—	45	N08031	45	Fittings
ASTM/ASME	B/SB-366	—	45	N08120	45	Fittings
ASTM/ASME	B/SB-366	—	46	N08330	45	Fittings
ASTM/ASME	B/SB-366	—	45	N08367	8.2	Fittings
ASTM/ASME	B/SB-366	—	45	N08367	8.2	Fittings
ASTM/ASME	B/SB-366	—	45	N08800	45	Fittings
ASTM/ASME	B/SB-366	—	45	N08810	45	Fittings
ASTM/ASME	B/SB-366	—	45	N08811	45	Fittings
ASTM/ASME	B/SB-366	—	45	N08825	45	Fittings
ASTM/ASME	B/SB-366	—	45	N08904	8.2	Fittings
ASTM/ASME	B/SB-366	—	45	N08925	8.2	Fittings
ASTM/ASME	B/SB-366	—	45	N08926	8.2	Fittings
ASTM/ASME	B/SB-366	—	44	N10001	44	Fittings
ASTM/ASME	B/SB-366	—	44	N10003	44	Fittings
ASTM/ASME	B/SB-366	—	44	N10242	44	Fittings
ASTM/ASME	B/SB-366	—	43	N10276	43	Fittings
ASTM/ASME	B/SB-366	—	44	N10624	44	Fittings
ASTM/ASME	B/SB-366	—	44	N10629	44	Fittings
ASTM/ASME	B/SB-366	—	44	N10665	44	Fittings
ASTM/ASME	B/SB-366	—	44	N10675	44	Fittings
ASTM/ASME	B/SB-366	—	46	N12160	46	Fittings
ASTM/ASME	B/SB-366	—	45	R20033	45	Fittings
ASTM/ASME	B/SB-366	—	45	R30556	45	Fittings
ASTM/ASME	B/SB-367	C-16	51	R52402	51	Castings
ASTM/ASME	B/SB-367	C-17	51	R52252	51	Castings
ASTM/ASME	B/SB-367	C-2	51	R50400	51	Castings
ASTM/ASME	B/SB-367	C-3	52	R50550	52	Castings
ASTM/ASME	B/SB-367	C-5	54	R56400	53	Castings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-367	C-6	54	R54520	52	Castings
ASTM/ASME	B/SB-367	C-7	51	—	51	Castings
ASTM/ASME	B/SB-367	C-8	52	—	52	Castings
ASTM/ASME	B/SB-369	—	34	C96200	34	Castings
ASTM/ASME	B/SB-381	F-1	51	R50250	51	Forgings
ASTM/ASME	B/SB-381	F-11	51	R52250	51	Forgings
ASTM/ASME	B/SB-381	F-12	52	R53400	52	Forgings
ASTM/ASME	B/SB-381	F-13	51	R53413	52	Forgings
ASTM/ASME	B/SB-381	F-14	52	R53414	52	Forgings
ASTM/ASME	B/SB-381	F-15	52	R53415	52	Forgings
ASTM/ASME	B/SB-381	F-16	51	R52402	51	Forgings
ASTM/ASME	B/SB-381	F-16H	51	R52402	51	Forgings
ASTM/ASME	B/SB-381	F-17	51	R52252	51	Forgings
ASTM/ASME	B/SB-381	F-18	53	R56322	53	Forgings
ASTM/ASME	B/SB-381	F-19	53	R58640	54	Forgings
ASTM/ASME	B/SB-381	F-2	51	R50400	51	Forgings
ASTM/ASME	B/SB-381	F-20	53	R58645	54	Forgings
ASTM/ASME	B/SB-381	F-21	53	R58210	54	Forgings
ASTM/ASME	B/SB-381	F-23	54	R56407	53	Forgings
ASTM/ASME	B/SB-381	F-24	54	R56405	53	Forgings
ASTM/ASME	B/SB-381	F-25	54	R56403	53	Forgings
ASTM/ASME	B/SB-381	F-26	51	R52404	51	Forgings
ASTM/ASME	B/SB-381	F-26H	51	R52404	51	Forgings
ASTM/ASME	B/SB-381	F-28	53	R56323	53	Forgings
ASTM/ASME	B/SB-381	F-2H	51	R50400	51	Forgings
ASTM/ASME	B/SB-381	F-3	52	R50550	52	Forgings
ASTM/ASME	B/SB-381	F-30	51	R53530	52	Forgings
ASTM/ASME	B/SB-381	F-31	52	R53532	52	Forgings
ASTM/ASME	B/SB-381	F-4	53	R50700	51.4	Forgings
ASTM/ASME	B/SB-381	F-5	54	R56400	53	Forgings
ASTM/ASME	B/SB-381	F-6	54	R54520	52	Forgings
ASTM/ASME	B/SB-381	F-7	51	R52400	51	Forgings
ASTM/ASME	B/SB-381	F-7H	51	R52400	51	Forgings
ASTM/ASME	B/SB-381	F-9	53	R56320	53	Forgings
ASTM/ASME	B/SB-395	—	31	C10200	31	Seamless Tube
ASTM/ASME	B/SB-395	—	31	C10300	31	Seamless Tube
ASTM/ASME	B/SB-395	—	31	C10800	31	Seamless Tube
ASTM/ASME	B/SB-395	—	31	C12000	31	Seamless Tube
ASTM/ASME	B/SB-395	—	31	C12200	31	Seamless Tube
ASTM/ASME	B/SB-395	—	31	C14200	31	Seamless Tube
ASTM/ASME	B/SB-395	—	31	C19200	31	Seamless Tube
ASTM/ASME	B/SB-395	—	32	C23000	32.1	Seamless Tube
ASTM/ASME	B/SB-395	—	32	C44300	32.2	Seamless Tube
ASTM/ASME	B/SB-395	—	32	C44400	32.2	Seamless Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-395	—	32	C44500	32.2	Seamless Tube
ASTM/ASME	B/SB-395	—	35	C60800	35	Seamless Tube
ASTM/ASME	B/SB-395	—	32	C68700	32.2	Seamless Tube
ASTM/ASME	B/SB-395	—	34	C70400	34	Seamless Tube
ASTM/ASME	B/SB-395	—	34	C70600	34	Seamless Tube
ASTM/ASME	B/SB-395	—	34	C71000	34	Seamless Tube
ASTM/ASME	B/SB-395	—	34	C71500	34	Seamless Tube
ASTM/ASME	B/SB-395	—	34	C72200	34	Seamless Tube
ASTM	B396	5005	22	A95005	22.2	Wire
ASTM	B403	AM100A, F	83	M10100	—	Castings
ASTM	B403	AZ91C, F	83	M11914	—	Castings
ASTM	B403	AZ92A, F	83	M11920	—	Castings
ASTM	B403	K1A	83	M18010	—	Castings
ASTM/ASME	B/SB-407	—	45	N08120	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-407	—	45	N08800	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-407	—	45	N08801	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-407	—	45	N08810	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-407	—	45	N08811	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-408	—	45	N08120	45	Rod & Bar
ASTM/ASME	B/SB-408	—	45	N08800	45	Rod & Bar
ASTM/ASME	B/SB-408	—	45	N08810	45	Rod & Bar
ASTM/ASME	B/SB-408	—	45	N08811	45	Rod & Bar
ASTM/ASME	B/SB-409	—	45	N08120	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-409	—	45	N08800	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-409	—	45	N08810	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-409	—	45	N08811	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-423	—	45	N08221	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-423	—	45	N08825	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-424	—	45	N08221	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-424	—	45	N08825	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-425	—	45	N08221	45	Rod & Bar
ASTM/ASME	B/SB-425	—	45	N08825	45	Rod & Bar
ASTM	B429	6061	23	A96061	23.1	Pipe & Tube
ASTM	B429	6063	23	A96063	23.1	Pipe & Tube
ASTM/ASME	B/SB-434	—	44	N10003	44	Plate, Sheet, & Strip
ASTM/ASME	B/SB-434	—	44	N10242	44	Plate, Sheet, & Strip
ASTM/ASME	B/SB-435	—	43	N06002	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-435	—	43	N06230	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-435	—	46	N12160	46	Plate, Sheet, & Strip
ASTM/ASME	B/SB-435	—	45	R30556	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-443	1	43	N06625	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-443	2	43	N06625	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-444	1	43	N06625	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-444	2	43	N06625	43	Seamless Pipe & Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-446	1	43	N06625	43	Rod & Bar
ASTM/ASME	B/SB-446	2	43	N06625	43	Rod & Bar
ASTM/ASME	B/SB-462	—	43	N06022	44	Forgings
ASTM/ASME	B/SB-462	—	45	N06030	45	Forgings
ASTM/ASME	B/SB-462	—	43	N06035	43	Forgings
ASTM/ASME	B/SB-462	—	46	N06045	45	Forgings
ASTM/ASME	B/SB-462	—	43	N06059	43	Forgings
ASTM/ASME	B/SB-462	—	43	N06200	43	Forgings
ASTM/ASME	B/SB-462	—	43	N06686	43	Forgings
ASTM/ASME	B/SB-462	—	45	N08020	45	Forgings
ASTM/ASME	B/SB-462	—	45	N08024	45	Forgings
ASTM/ASME	B/SB-462	—	45	N08026	45	Forgings
ASTM/ASME	B/SB-462	—	45	N08031	45	Forgings
ASTM/ASME	B/SB-462	—	45	N08367	8.2	Forgings
ASTM/ASME	B/SB-462	—	43	N10276	43	Forgings
ASTM/ASME	B/SB-462	—	44	N10629	44	Forgings
ASTM/ASME	B/SB-462	—	44	N10665	44	Forgings
ASTM/ASME	B/SB-462	—	44	N10675	44	Forgings
ASTM/ASME	B/SB-462	—	45	R20033	45	Forgings
ASTM/ASME	B/SB-463	—	45	N08020	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-463	—	45	N08024	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-463	—	45	N08026	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-464	—	45	N08020	45	Welded Pipe
ASTM/ASME	B/SB-464	—	45	N08024	45	Welded Pipe
ASTM/ASME	B/SB-464	—	45	N08026	45	Welded Pipe
ASTM/ASME	B/SB-466	—	34	C70400	34	Seamless Pipe & Tube
ASTM/ASME	B/SB-466	—	34	C70600	34	Seamless Pipe & Tube
ASTM/ASME	B/SB-466	—	34	C71000	34	Seamless Pipe & Tube
ASTM/ASME	B/SB-466	—	34	C71500	34	Seamless Pipe & Tube
ASTM/ASME	B/SB-466	—	34	C72200	34	Seamless Pipe & Tube
ASTM/ASME	B/SB-467	—	34	C70600	34	Welded Pipe
ASTM/ASME	B/SB-467	—	34	C70600	34	Welded Pipe
ASTM/ASME	B/SB-467	—	34	C71500	34	Welded Pipe
ASTM/ASME	B/SB-467	—	34	C71500	34	Welded Pipe
ASTM/ASME	B/SB-468	—	45	N08020	45	Welded Tube
ASTM/ASME	B/SB-468	—	45	N08024	45	Welded Tube
ASTM/ASME	B/SB-468	—	45	N08026	45	Welded Tube
ASTM/ASME	B/SB-473	—	45	N08020	45	Bar
ASTM/ASME	B/SB-473	—	45	N08024	45	Bar
ASTM/ASME	B/SB-473	—	45	N08026	45	Bar
ASTM	A479	904L	45	N08904	8.2	Bars & Shapes
ASTM	B483	1060	21	A91060	21	Tube
ASTM	B483	1100	21	A91100	21	Tube
ASTM	B483	1435	21	A91435	21	Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM	B483	3003	21	A93003	22.1	Tube
ASTM	B483	3102	21	A93102	22.1	Tube
ASTM	B483	5005	22	A95005	22.2	Tube
ASTM	B483	5050	21	A95050	22.2	Tube
ASTM	B483	5052	22	A95052	22.3	Tube
ASTM	B483	6061	23	A96061	23.1	Tube
ASTM	B483	6063	23	A96063	23.1	Tube
ASTM	B491	1050	21	A91050	21	Extruded Tube
ASTM	B491	1100	21	A91100	21	Extruded Tube
ASTM	B491	1200	21	A91200	21	Extruded Tube
ASTM	B491	1235	21	A91235	21	Extruded Tube
ASTM	B491	3003	21	A93003	22.1	Extruded Tube
ASTM	B491	3102	21	A93102	22.1	Extruded Tube
ASTM	B491	6063	23	A96063	23.1	Extruded Tube
ASTM/ASME	B/SB-493	R60702	61	R60702	61	Forgings
ASTM/ASME	B/SB-493	R60704	62	R60704	62	Forgings
ASTM/ASME	B/SB-493	R60705	62	R60705	62	Forgings
ASTM/ASME	A/SA-494	CU5MCuC	45	N08826	45	Castings
ASTM/ASME	A/SA-494	CW2M	43	N26455	43	Castings
ASTM/ASME	A/SA-494	CW6M	44	N30107	44	Castings
ASTM/ASME	A/SA-494	CW6MC	43	N26625	43	Castings
ASTM/ASME	A/SA-494	CX2MW	43	N26022	44	Castings
ASTM/ASME	A/SA-494	CY40	43	N06040	43	Castings
ASTM/ASME	A/SA-494	M30C	42	N24130	42	Castings
ASTM/ASME	A/SA-494	M35-1	42	N24135	42	Castings
ASTM/ASME	A/SA-494	M35-2	42	N04020	42	Castings
ASTM/ASME	A/SA-494	N7M	44	N30007	44	Castings
ASTM/ASME	B/SB-505	—	35	C95200	35	Castings
ASTM/ASME	B/SB-511	—	46	N08330	45	Bars & Shapes
ASTM/ASME	B/SB-511	—	46	N08332	45	Bars & Shapes
ASTM	B512	—	46	N08330	45	Bars & Billets
ASTM/ASME	B/SB-514	—	45	N08120	45	Welded Pipe
ASTM/ASME	B/SB-514	—	45	N08800	45	Welded Pipe
ASTM/ASME	B/SB-514	—	45	N08810	45	Welded Pipe
ASTM/ASME	B/SB-515	—	45	N08120	45	Welded Tube
ASTM/ASME	B/SB-515	—	45	N08800	45	Welded Tube
ASTM/ASME	B/SB-515	—	45	N08810	45	Welded Tube
ASTM/ASME	B/SB-515	—	45	N08811	45	Welded Tube
ASTM/ASME	B/SB-516	—	43	N06025	43	Welded Tube
ASTM/ASME	B/SB-516	—	46	N06045	45	Welded Tube
ASTM/ASME	B/SB-516	—	43	N06600	43	Welded Tube
ASTM/ASME	B/SB-516	—	43	N06603	43	Welded Tube
ASTM/ASME	B/SB-517	—	43	N06025	43	Welded Pipe
ASTM/ASME	B/SB-517	—	46	N06045	45	Welded Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-517	—	43	N06600	43	Welded Pipe
ASTM/ASME	B/SB-517	—	43	N06603	43	Welded Pipe
ASTM/ASME	B/SB-523	R60702	61	R60702	61	Seamless & Welded Tube
ASTM/ASME	B/SB-523	R60704	62	R60704	62	Seamless & Welded Tube
ASTM/ASME	B/SB-523	R60705	62	R60705	62	Seamless & Welded Tube
ASTM/ASME	B/SB-535	—	46	N08330	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-535	—	46	N08332	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-536	—	46	N08330	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-536	—	46	N08332	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-543	—	31	C10800	31	Welded Tube
ASTM/ASME	B/SB-543	—	31	C12200	31	Welded Tube
ASTM/ASME	B/SB-543	—	31	C19400	31	Welded Tube
ASTM/ASME	B/SB-543	—	32	C23000	32.1	Welded Tube
ASTM/ASME	B/SB-543	—	32	C44300	32.2	Welded Tube
ASTM/ASME	B/SB-543	—	32	C44400	32.2	Welded Tube
ASTM/ASME	B/SB-543	—	32	C44500	32.2	Welded Tube
ASTM/ASME	B/SB-543	—	32	C68700	32.2	Welded Tube
ASTM/ASME	B/SB-543	—	34	C70400	34	Welded Tube
ASTM/ASME	B/SB-543	—	34	C70600	34	Welded Tube
ASTM	B543	—	34	C71000	34	Welded Tube
ASTM/ASME	B/SB-543	—	34	C71500	34	Welded Tube
ASTM/ASME	B/SB-543	—	34	C71640	34	Welded Tube
ASTM	B543	—	34	C72200	34	Welded Tube
ASTM	B547	1100	21	A91100	21	Welded Tube
ASTM	B547	3003	21	A93003	22.1	Welded Tube
ASTM	B547	3004	22	A93004	22.2	Welded Tube
ASTM	B547	5050	21	A95050	22.2	Welded Tube
ASTM	B547	5052	22	A95052	22.3	Welded Tube
ASTM	B547	5083	25	A95083	22.4	Welded Tube
ASTM	B547	5086	25	A95086	22.4	Welded Tube
ASTM	B547	5154	22	A95154	22.4	Welded Tube
ASTM	B547	5454	22	A95454	22.3	Welded Tube
ASTM	B547	6061	23	A96061	23.1	Welded Tube
ASTM	B547	Alclad 3003	21	A83003	—	Welded Tube
ASTM	B547	Alclad 3004	22	—	—	Welded Tube
ASTM/ASME	B/SB-550	R60702	61	R60702	61	Bar & Wire
ASTM/ASME	B/SB-550	R60704	62	R60704	62	Bar & Wire
ASTM/ASME	B/SB-550	R60705	62	R60705	62	Bar & Wire
ASTM/ASME	B/SB-551	R60702	61	R60702	61	Plate, Sheet, & Strip
ASTM/ASME	B/SB-551	R60704	62	R60704	62	Plate, Sheet, & Strip
ASTM/ASME	B/SB-551	R60705	62	R60705	62	Plate, Sheet, & Strip
ASTM/ASME	B/SB-551	R60706	62	R60706	62	Plate, Sheet, & Strip
ASTM/ASME	B/SB-564	—	41	N02200	41	Forgings
ASTM/ASME	B/SB-564	—	42	N04400	42	Forgings

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-564	—	43	N06022	44	Forgings
ASTM/ASME	B/SB-564	—	43	N06025	43	Forgings
ASTM/ASME	B/SB-564	—	43	N06025	43	Forgings
ASTM/ASME	B/SB-564	—	43	N06035	43	Forgings
ASTM/ASME	B/SB-564	—	46	N06045	45	Forgings
ASTM/ASME	B/SB-564	—	43	N06059	43	Forgings
ASTM/ASME	B/SB-564	—	43	N06110	43	Forgings
ASTM/ASME	B/SB-564	—	43	N06110	43	Forgings
ASTM/ASME	B/SB-564	—	43	N06200	43	Forgings
ASTM/ASME	B/SB-564	—	43	N06210	43	Forgings
ASTM/ASME	B/SB-564	—	43	N06230	43	Forgings
ASTM/ASME	B/SB-564	—	43	N06600	43	Forgings
ASTM/ASME	B/SB-564	—	43	N06603	43	Forgings
ASTM/ASME	B/SB-564	—	43	N06617	46	Forgings
ASTM/ASME	B/SB-564	—	43	N06625	43	Forgings
ASTM/ASME	B/SB-564	—	43	N06625	43	Forgings
ASTM/ASME	B/SB-564	—	43	N06686	43	Forgings
ASTM/ASME	B/SB-564	—	43	N06690	43	Forgings
ASTM/ASME	B/SB-564	—	45	N08031	45	Forgings
ASTM/ASME	B/SB-564	—	45	N08120	45	Forgings
ASTM/ASME	B/SB-564	—	45	N08367	8.2	Forgings
ASTM/ASME	B/SB-564	—	45	N08800	45	Forgings
ASTM/ASME	B/SB-564	—	45	N08810	45	Forgings
ASTM/ASME	B/SB-564	—	45	N08811	44	Forgings
ASTM/ASME	B/SB-564	—	45	N08825	45	Forgings
ASTM/ASME	B/SB-564	—	44	N10242	44	Forgings
ASTM/ASME	B/SB-564	—	43	N10276	43	Forgings
ASTM/ASME	B/SB-564	—	44	N10624	44	Forgings
ASTM/ASME	B/SB-564	—	44	N10629	44	Forgings
ASTM/ASME	B/SB-564	—	44	N10665	44	Forgings
ASTM/ASME	B/SB-564	—	44	N10675	44	Forgings
ASTM/ASME	B/SB-564	—	46	N12160	46	Forgings
ASTM/ASME	B/SB-564	—	45	R20033	45	Forgings
ASTM/ASME	B/SB-572	—	43	N06002	43	Rod
ASTM/ASME	B/SB-572	—	43	N06230	43	Rod
ASTM/ASME	B/SB-572	—	46	N12160	46	Rod
ASTM/ASME	B/SB-572	—	45	R30556	45	Rod
ASTM/ASME	B/SB-573	—	44	N10003	44	Rod
ASTM/ASME	B/SB-573	—	44	N10242	44	Rod
ASTM/ASME	B/SB-574	—	43	N06022	44	Rod
ASTM/ASME	B/SB-574	—	43	N06035	43	Rod
ASTM/ASME	B/SB-574	—	43	N06059	43	Rod
ASTM/ASME	B/SB-574	—	43	N06200	43	Rod
ASTM/ASME	B/SB-574	—	43	N06210	43	Rod

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-574	—	43	N06455	43	Rod
ASTM/ASME	B/SB-574	—	43	N06686	43	Rod
ASTM/ASME	B/SB-574	—	43	N10276	43	Rod
ASTM/ASME	B/SB-575	—	43	N06022	44	Plate, Sheet, & Strip
ASTM/ASME	B/SB-575	—	43	N06035	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-575	—	43	N06059	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-575	—	43	N06200	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-575	—	43	N06210	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-575	—	43	N06455	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-575	—	43	N06686	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-575	—	43	N10276	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-581	—	45	N06007	43	Rod
ASTM/ASME	B/SB-581	—	45	N06007	43	Rod
ASTM/ASME	B/SB-581	—	45	N06030	45	Rod
ASTM/ASME	B/SB-581	—	45	N06975	45	Rod
ASTM/ASME	B/SB-581	—	45	N06985	45	Rod
ASTM/ASME	B/SB-581	—	45	N06985	45	Rod
ASTM/ASME	B/SB-581	—	45	N08031	45	Rod
ASTM/ASME	B/SB-582	—	45	N06007	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-582	—	45	N06007	43	Plate, Sheet, & Strip
ASTM/ASME	B/SB-582	—	45	N06030	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-582	—	45	N06975	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-582	—	45	N06985	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-582	—	45	N06985	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-599	—	45	N08700	8.2	Plate, Sheet, & Strip
ASTM	B608	—	35	C61300	35	Welded Pipe
ASTM	B608	—	35	C61400	35	Welded Pipe
ASTM	B608	—	34	C70620	34	Welded Pipe
ASTM	B608	—	34	C71520	34	Welded Pipe
ASTM	B609	1350	21	A91350	21	Wire
ASTM	B618	208.0	26	A02080	25	Castings
ASTM	B618	319.0	26	A03190	25	Castings
ASTM	B618	328.0	26	A03280	25	Castings
ASTM	B618	356.0	26	A03560	24.2	Castings
ASTM	B618	443.0	26	A04430	24.1	Castings
ASTM	B618	514.0	26	A05140	23.1	Castings
ASTM	B618	535.0	26	A05350	—	Castings
ASTM	B618	A356.0	26	A13560	24.2	Castings
ASTM	B618	B443.0	26	A24430	24.1	Castings
ASTM/ASME	B/SB-619	—	43	N06002	43	Welded Pipe
ASTM/ASME	B/SB-619	—	45	N06007	43	Welded Pipe
ASTM/ASME	B/SB-619	—	43	N06022	44	Welded Pipe
ASTM/ASME	B/SB-619	—	45	N06030	45	Welded Pipe
ASTM/ASME	B/SB-619	—	43	N06035	43	Welded Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-619	—	43	N06059	43	Welded Pipe
ASTM/ASME	B/SB-619	—	43	N06200	43	Welded Pipe
ASTM/ASME	B/SB-619	—	43	N06210	43	Welded Pipe
ASTM/ASME	B/SB-619	—	43	N06230	43	Welded Pipe
ASTM/ASME	B/SB-619	—	43	N06455	43	Welded Pipe
ASTM/ASME	B/SB-619	—	43	N06686	43	Welded Pipe
ASTM/ASME	B/SB-619	—	45	N06975	45	Welded Pipe
ASTM/ASME	B/SB-619	—	45	N06985	45	Welded Pipe
ASTM/ASME	B/SB-619	—	45	N08031	45	Welded Pipe
ASTM/ASME	B/SB-619	—	45	N08320	8.2	Welded Pipe
ASTM/ASME	B/SB-619	—	44	N10001	44	Welded Pipe
ASTM/ASME	B/SB-619	—	44	N10242	44	Welded Pipe
ASTM/ASME	B/SB-619	—	43	N10276	43	Welded Pipe
ASTM/ASME	B/SB-619	—	44	N10624	44	Welded Pipe
ASTM/ASME	B/SB-619	—	44	N10629	44	Welded Pipe
ASTM/ASME	B/SB-619	—	44	N10665	44	Welded Pipe
ASTM/ASME	B/SB-619	—	44	N10675	44	Welded Pipe
ASTM/ASME	B/SB-619	—	46	N12160	46	Welded Pipe
ASTM/ASME	B/SB-619	—	45	R20033	45	Welded Pipe
ASTM/ASME	B/SB-619	—	45	R30556	45	Welded Pipe
ASTM/ASME	B/SB-620	—	45	N08320	8.2	Plate, Sheet, & Strip
ASTM/ASME	B/SB-621	—	45	N08320	8.2	Rod
ASTM/ASME	B/SB-622	—	43	N06002	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	45	N06007	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	43	N06022	44	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	45	N06030	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	43	N06035	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	43	N06059	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	43	N06060	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	43	N06200	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	43	N06210	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	43	N06230	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	43	N06250	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	43	N06255	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	43	N06455	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	43	N06686	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	45	N06975	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	45	N06985	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	45	N08031	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	45	N08135	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	45	N08320	8.2	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	45	N08535	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	44	N10001	44	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	44	N10242	44	Seamless Pipe & Tube

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-622	—	43	N10276	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	44	N10624	44	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	44	N10629	44	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	44	N10665	44	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	44	N10675	44	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	46	N12160	46	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	45	R20033	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-622	—	45	R30556	45	Seamless Pipe & Tube
ASTM/ASME	B/SB-625	—	45	N08031	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-625	—	45	N08904	8.2	Plate, Sheet, & Strip
ASTM/ASME	B/SB-625	—	45	N08925	8.2	Plate, Sheet, & Strip
ASTM/ASME	B/SB-625	—	45	N08926	8.2	Plate, Sheet, & Strip
ASTM/ASME	B/SB-625	—	45	N08932	8.2	Plate, Sheet, & Strip
ASTM/ASME	B/SB-625	—	45	R20033	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-626	—	43	N06002	43	Welded Tube
ASTM/ASME	B/SB-626	—	45	N06007	43	Welded Tube
ASTM/ASME	B/SB-626	—	43	N06022	44	Welded Tube
ASTM/ASME	B/SB-626	—	45	N06030	45	Welded Tube
ASTM/ASME	B/SB-626	—	43	N06035	43	Welded Tube
ASTM/ASME	B/SB-626	—	43	N06059	43	Welded Tube
ASTM/ASME	B/SB-626	—	43	N06200	43	Welded Tube
ASTM/ASME	B/SB-626	—	43	N06210	43	Welded Tube
ASTM/ASME	B/SB-626	—	43	N06230	43	Welded Tube
ASTM/ASME	B/SB-626	—	43	N06455	43	Welded Tube
ASTM/ASME	B/SB-626	—	43	N06686	43	Welded Tube
ASTM/ASME	B/SB-626	—	45	N06975	45	Welded Tube
ASTM/ASME	B/SB-626	—	45	N06985	45	Welded Tube
ASTM/ASME	B/SB-626	—	45	N08031	45	Welded Tube
ASTM/ASME	B/SB-626	—	45	N08320	8.2	Welded Tube
ASTM/ASME	B/SB-626	—	44	N10001	44	Welded Tube
ASTM/ASME	B/SB-626	—	44	N10242	44	Welded Tube
ASTM/ASME	B/SB-626	—	43	N10276	43	Welded Tube
ASTM/ASME	B/SB-626	—	44	N10624	44	Welded Tube
ASTM/ASME	B/SB-626	—	44	N10629	44	Welded Tube
ASTM/ASME	B/SB-626	—	44	N10665	44	Welded Tube
ASTM/ASME	B/SB-626	—	44	N10675	44	Welded Tube
ASTM/ASME	B/SB-626	—	46	N12160	46	Welded Tube
ASTM/ASME	B/SB-626	—	45	R20033	45	Welded Tube
ASTM/ASME	B/SB-626	—	45	R30556	45	Welded Tube
ASTM/ASME	B/SB-649	—	45	N08031	45	Bar & Wire
ASTM/ASME	B/SB-649	—	45	N08904	8.2	Bar & Wire
ASTM/ASME	B/SB-649	—	45	N08925	8.2	Bar & Wire
ASTM/ASME	B/SB-649	—	45	N08926	8.2	Bar & Wire
ASTM/ASME	B/SB-649	—	45	R20033	45	Bar & Wire

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-653	R60702	61	R60702	61	Seamless & Welded Fittings
ASTM/ASME	B/SB-658	R60702	61	R60702	61	Seamless & Welded Pipe
ASTM/ASME	B/SB-658	R60704	62	R60704	62	Seamless & Welded Pipe
ASTM/ASME	B/SB-658	R60705	62	R60705	62	Seamless & Welded Pipe
ASTM/ASME	B/SB-668	—	45	N08028	45	Seamless Tube
ASTM/ASME	B/SB-672	—	45	N08700	8.2	Bar & Wire
ASTM/ASME	B/SB-673	—	45	N08904	8.2	Welded Pipe
ASTM/ASME	B/SB-673	—	45	N08925	8.2	Welded Pipe
ASTM/ASME	B/SB-673	—	45	N08926	8.2	Welded Pipe
ASTM/ASME	B/SB-674	—	45	N08904	8.2	Welded Tube
ASTM/ASME	B/SB-674	—	45	N08925	8.2	Welded Tube
ASTM/ASME	B/SB-674	—	45	N08926	8.2	Welded Tube
ASTM/ASME	B/SB-675	—	45	N08367	8.2	Welded Pipe
ASTM/ASME	B/SB-675	—	45	N08367	8.2	Welded Pipe
ASTM/ASME	B/SB-676	—	45	N08367	8.2	Welded Tube
ASTM/ASME	B/SB-676	—	45	N08367	8.2	Welded Tube
ASTM/ASME	B/SB-677	—	45	N08904	8.2	Seamless Pipe & Tube
ASTM/ASME	B/SB-677	—	45	N08925	8.2	Seamless Pipe & Tube
ASTM/ASME	B/SB-677	—	45	N08926	8.2	Seamless Pipe & Tube
ASTM	B686	A356.0	26	A13560	24.2	Castings
ASTM/ASME	B/SB-688	—	45	N08366	8.2	Plate, Sheet, & Strip
ASTM/ASME	B/SB-688	—	45	N08367	8.2	Plate, Sheet, & Strip
ASTM/ASME	B/SB-688	—	45	N08367	8.2	Plate, Sheet, & Strip
ASTM/ASME	B/SB-690	—	45	N08366	8.2	Seamless Pipe & Tube
ASTM/ASME	B/SB-690	—	45	N08367	8.2	Seamless Pipe & Tube
ASTM/ASME	B/SB-690	—	45	N08367	8.2	Seamless Pipe & Tube
ASTM/ASME	B/SB-691	—	45	N08366	8.2	Rod, Bar, & Wire
ASTM/ASME	B/SB-691	—	45	N08367	8.2	Rod, Bar, & Wire
ASTM/ASME	B/SB-704	—	43	N06625	43	Welded Tube
ASTM/ASME	B/SB-704	—	45	N08825	45	Welded Tube
ASTM/ASME	B/SB-705	—	43	N06625	43	Welded Pipe
ASTM/ASME	B/SB-705	—	45	N08825	45	Welded Pipe
ASTM/ASME	B/SB-709	—	45	N08028	45	Plate, Sheet, & Strip
ASTM/ASME	B/SB-710	—	46	N08330	45	Welded Pipe
ASTM/ASME	B/SB-710	—	46	N08332	45	Welded Pipe
ASTM	B718	—	45	N06333	43	Plate, Sheet, & Strip
ASTM	B719	—	45	N06333	43	Bar
ASTM	B720	—	45	N08310	—	Seamless Tube
ASTM	B722	—	45	N06333	43	Seamless Pipe & Tube
ASTM	B723	—	45	N06333	43	Welded Pipe
ASTM	B725	—	41	N02200	41	Welded Pipe
ASTM	B726	—	45	N06333	43	Welded Tube
ASTM/ASME	B/SB-729	—	45	N08020	45	Seamless Pipe & Tube
ASTM	B755	—	43	N06110	43	Plate, Sheet, & Strip

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM	B756	—	43	N06110	43	Rod & Bar
ASTM	B756	—	43	N06110	43	Rod & Bar
ASTM	B757	—	43	N06110	43	Welded Pipe
ASTM	B758	—	43	N06110	43	Welded Tube
ASTM	B759	—	43	N06110	43	Seamless Pipe & Tube
ASTM/ASME	B/SB-804	—	45	N08367	8.2	Welded Pipe
ASTM/ASME	B/SB-804	—	45	N08367	8.2	Welded Pipe
ASTM	A813	N08367	45	N08367	8.2	Welded Pipe
ASTM	A813	N08367	45	N08367	8.2	Welded Pipe
ASTM	B814	—	45	N06920	43	Plate, Sheet, & Strip
ASTM	A814	N08367	45	N08367	8.2	Cold Worked Welded Pipe
ASTM	A814	N08367	45	N08367	8.2	Cold Worked Welded Pipe
ASTM/ASME	B/SB-815	—	49	R31233	—	Rod
ASTM/ASME	B/SB-818	—	49	R31233	—	Plate, Sheet, & Strip
ASTM/ASME	B/SB-861	1	51	R50250	51	Seamless Pipe
ASTM/ASME	B/SB-861	11	51	R52250	51	Seamless Pipe
ASTM/ASME	B/SB-861	12	52	R53400	52	Seamless Pipe
ASTM/ASME	B/SB-861	13	51	R53413	52	Seamless Pipe
ASTM/ASME	B/SB-861	14	52	R53414	52	Seamless Pipe
ASTM/ASME	B/SB-861	15	52	R53415	52	Seamless Pipe
ASTM/ASME	B/SB-861	16	51	R52402	51	Seamless Pipe
ASTM/ASME	B/SB-861	16H	51	R52402	51	Seamless Pipe
ASTM/ASME	B/SB-861	17	51	R52252	51	Seamless Pipe
ASTM/ASME	B/SB-861	18	53	R56322	53	Seamless Pipe
ASTM/ASME	B/SB-861	19	53	R58640	54	Seamless Pipe
ASTM/ASME	B/SB-861	2	51	R50400	51	Seamless Pipe
ASTM/ASME	B/SB-861	20	53	R58645	54	Seamless Pipe
ASTM/ASME	B/SB-861	21	53	R58210	54	Seamless Pipe
ASTM/ASME	B/SB-861	23	54	R56407	53	Seamless Pipe
ASTM/ASME	B/SB-861	24	54	R56405	53	Seamless Pipe
ASTM/ASME	B/SB-861	25	54	R56403	53	Seamless Pipe
ASTM/ASME	B/SB-861	26	51	R52404	51	Seamless Pipe
ASTM/ASME	B/SB-861	26H	51	R52404	51	Seamless Pipe
ASTM/ASME	B/SB-861	28	53	R56323	53	Seamless Pipe
ASTM/ASME	B/SB-861	29	54	R56404	53	Seamless Pipe
ASTM/ASME	B/SB-861	2H	51	R50400	51	Seamless Pipe
ASTM/ASME	B/SB-861	3	52	R50550	52	Seamless Pipe
ASTM/ASME	B/SB-861	33	51	R53442	54	Seamless Pipe
ASTM/ASME	B/SB-861	34	52	R53445	54	Seamless Pipe
ASTM/ASME	B/SB-861	35	54	R56340	53	Seamless Pipe
ASTM/ASME	B/SB-861	5	54	R56400	53	Seamless Pipe
ASTM/ASME	B/SB-861	7	51	R52400	51	Seamless Pipe
ASTM/ASME	B/SB-861	7H	51	R52400	51	Seamless Pipe
ASTM/ASME	B/SB-861	9	53	R56320	53	Seamless Pipe

(Continued)

Table C.1 (Continued)
List of Base Metal Specifications—Nonferrous Alloys

Standard	Base Metal Specification	Type, Grade, or Alloy Designation	Material Number	UNS Number	ISO 15608 Group	Product Form
ASTM/ASME	B/SB-862	1	51	R50250	51	Welded Pipe
ASTM/ASME	B/SB-862	11	51	R52250	51	Welded Pipe
ASTM/ASME	B/SB-862	12	52	R53400	52	Welded Pipe
ASTM/ASME	B/SB-862	13	51	R53413	52	Welded Pipe
ASTM/ASME	B/SB-862	14	52	R53414	52	Welded Pipe
ASTM/ASME	B/SB-862	15	52	R53415	52	Welded Pipe
ASTM/ASME	B/SB-862	16	51	R52402	51	Welded Pipe
ASTM/ASME	B/SB-862	16H	51	R52402	51	Welded Pipe
ASTM/ASME	B/SB-862	17	51	R52252	51	Welded Pipe
ASTM/ASME	B/SB-862	18	53	R56322	53	Welded Pipe
ASTM/ASME	B/SB-862	19	53	R58640	54	Welded Pipe
ASTM/ASME	B/SB-862	2	51	R50400	51	Welded Pipe
ASTM/ASME	B/SB-862	20	53	R58645	54	Welded Pipe
ASTM/ASME	B/SB-862	21	53	R58210	54	Welded Pipe
ASTM/ASME	B/SB-862	23	54	R56407	53	Welded Pipe
ASTM/ASME	B/SB-862	24	54	R56405	53	Welded Pipe
ASTM/ASME	B/SB-862	25	54	R56403	53	Welded Pipe
ASTM/ASME	B/SB-862	26	51	R52404	51	Welded Pipe
ASTM/ASME	B/SB-862	26H	51	R52404	51	Welded Pipe
ASTM/ASME	B/SB-862	27	51	R52254	51	Welded Pipe
ASTM/ASME	B/SB-862	28	53	R56323	53	Welded Pipe
ASTM/ASME	B/SB-862	29	54	R56404	53	Welded Pipe
ASTM/ASME	B/SB-862	2H	51	R50400	51	Welded Pipe
ASTM/ASME	B/SB-862	3	52	R50550	52	Welded Pipe
ASTM/ASME	B/SB-862	33	51	R53442	54	Welded Pipe
ASTM/ASME	B/SB-862	34	52	R53445	54	Welded Pipe
ASTM/ASME	B/SB-862	35	54	R56340	53	Welded Pipe
ASTM/ASME	B/SB-862	5	54	R56400	53	Welded Pipe
ASTM/ASME	B/SB-862	7	51	R52400	51	Welded Pipe
ASTM/ASME	B/SB-862	7H	51	R52400	51	Welded Pipe
ASTM/ASME	B/SB-862	9	53	R56320	53	Welded Pipe
ASTM/ASME	B/SB-928	5083	25	A95083	22.4	Plate & Sheet
ASTM/ASME	B/SB-928	5086	25	A95086	22.4	Plate & Sheet
ASTM/ASME	B/SB-928	5456	25	A95456	22.4	Plate & Sheet
ASTM/ASME	B/SB-956	—	34	C70600	34	Finned Welded Tube
ASTM/ASME	B/SB-956	—	34	C71500	34	Finned Welded Tube
ISO	209	6082, T4, T6	23	A96082	23.1	Bar, Rod, Shapes, & Tube
ISO	209	7020, T5	27	A97020	23.2	Bar, Rod, Shapes, & Tube
NACE	MR 01-75	100	45	N06950	43	Pipe
NACE	MR 01-75	110	45	N06950	43	Pipe
NACE	MR 01-75	125	45	N06950	43	Pipe
NACE	MR 01-75	140	45	N06950	43	Pipe

Table C.2
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	1.1	AAR	M201	A	—		60/30 [415/205]	Castings	C-Mn-Si
1	1.1	ASTM	A1018	SS 40	—		55/40 [380/275]	Sheet & Strip	C
1	1.1	ABS	ABS	A	K02300		58/34 [400/235]	Plate, Bar, & Shapes	C
1	1.2	ABS	ABS	AH32	K11846		64/46 [440/315]	Plate, Bar, & Shapes	C-Mn-Si
1	1.1	ABS	ABS	B	K02102		58/34 [400/235]	Plate, Bar, & Shapes	C
1	1.1	ABS	ABS	D	K02101		58/34 [400/235]	Plate, Bar, & Shapes	C-Si
1	1.2	ABS	ABS	DH32	K11846		64/46 [440/315]	Plate, Bar, & Shapes	C-Mn-Si
1	1.1	ABS	ABS	E	K01801		58/34 [400/235]	Plate, Bar, & Shapes	C-Si
1	1.2	ABS	ABS	EH32	K11846		64/46 [440/315]	Plate, Bar, & Shapes	C-Mn-Si
1	1.2	ABS	ABS	FH32	K11846		64/46 [440/315]	Plate, Bar, & Shapes	C-Mn-Si
1	1.2	API	2H	42	—		62/42 [425/290]	Plate	C-Mn
1	1.2	API	2MT1	50	—		65/50 [450/345]	Plate	C-Mn
1	1.2	API	2W	50	—		65/50 [450/345]	Plate	C-Mn
1	1.2	API	2Y	42	—		62/42 [425/290]	Plate	C-Mn
1	1.2	API	2Y	50	—		65/50 [450/345]	Plate	C-Mn
1	1.1	API	5L	A	—		49/30 [340/205]	Seamless & Welded Pipe	C-Mn
1	1.1	API	5L	A25	—		45/25 [310/175]	Seamless & Welded Pipe	C-Mn
1	1.1	API	5L	A25, Cl. I	—		45/25 [310/170]	Seamless & Wld. Pipe & Tube	C-Mn
1	1.1	API	5L	A25, Cl. II	—		45/25 [310/170]	Seamless & Wld. Pipe & Tube	C-Mn
1	1.1	API	5L	A25P	—		45/25 [310/175]	Seamless & Welded Pipe	C-Mn
1	1.1	API	5L	B	—		60/35 [415/240]	Seamless & Welded Pipe	C-Mn
1	1.1	API	5L	BM	—		60/35 [415/240]	Welded Pipe	C-Mn
1	1.1	API	5L	BMO	—		60/35 [415/240]	Welded Pipe	C-Mn
1	1.1	API	5L	BMS	—		60/35 [415/240]	Welded Pipe	C-Mn
1	1.1	API	5L	BN	—		60/35 [415/240]	Seamless & Welded Pipe	C-Mn
1	1.1	API	5L	BNO	—		60/35 [415/240]	Seamless & Welded Pipe	C-Mn
1	1.1	API	5L	BNS	—		60/35 [415/240]	Seamless & Welded Pipe	C-Mn
1	1.1	API	5L	BQ	—		60/35 [415/240]	Seamless & Welded Pipe	C-Mn
1	1.1	API	5L	BQO	—		60/35 [415/240]	Seamless & Welded Pipe	C-Mn

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	1.1	API	5L	BQS	—		60/35 [415/240]	Seamless & Welded Pipe	C-Mn
1	1.1	API	5L	BR	—		60/35 [415/240]	Seamless & Welded Pipe	C-Mn
1	1.1.1	API	5L	X42	—		60/42 [415/290]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X42M	—		60/42 [415/290]	Welded Pipe	C-Mn
1	1.2	API	5L	X42MO	—		60/42 [415/290]	Welded Pipe	C-Mn
1	1.2	API	5L	X42MS	—		60/42 [415/290]	Welded Pipe	C-Mn
1	1.2	API	5L	X42N	—		60/42 [415/290]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X42NO	—		60/42 [415/290]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X42NS	—		60/42 [415/290]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X42Q	—		60/42 [415/290]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X42QO	—		60/42 [415/290]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X42QS	—		60/42 [415/290]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X42R	—		60/42 [415/290]	Seamless & Welded Pipe	C-Mn
1	1.1.1	API	5L	X46	—		63/46 [435/315]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X46M	—		63/46 [435/315]	Welded Pipe	C-Mn
1	1.2	API	5L	X46MO	—		63/46 [435/315]	Welded Pipe	C-Mn
1	1.2	API	5L	X46MS	—		63/46 [435/315]	Welded Pipe	C-Mn
1	1.2	API	5L	X46N	—		63/46 [435/315]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X46NO	—		63/46 [435/315]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X46NS	—		63/46 [435/315]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X46Q	—		63/46 [435/315]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X46QO	—		63/46 [435/315]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X46QS	—		63/46 [435/315]	Seamless & Welded Pipe	C-Mn
1	1.1.1	API	5L	X52	—		67/52 [460/360]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X52M	—		67/52 [460/360]	Welded Pipe	C-Mn
1	1.2	API	5L	X52MO	—		67/52 [460/360]	Welded Pipe	C-Mn
1	1.2	API	5L	X52MS	—		67/52 [460/360]	Welded Pipe	C-Mn
1	1.2	API	5L	X52N	—		67/52 [460/360]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X52NO	—		67/52 [460/360]	Seamless & Welded Pipe	C-Mn

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Steel and Steel Alloys									
1	1.2	API	5L	X52NS	—		67/52 [460/360]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X52Q	—		67/52 [460/360]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X52QO	—		67/52 [460/360]	Seamless & Welded Pipe	C-Mn
1	1.2	API	5L	X52QS	—		67/52 [460/360]	Seamless & Welded Pipe	C-Mn
1	11.1	API	5LS	X46	—		63/46 [435/315]	Spiral Welded Pipe	C-Mn
1	1.2	AS	1548	7-430	—		62.5/43.5 [430/300]	Plate	C
1	1.2	AS	1548	7-460	—		66.5/44 [460/305]	Plate	C
1	1.2	AS	1548	PT430	—		62.5/43.5 [430/300]	Plate	C
1	1.2	AS	1548	PT460	—		66.5/44 [460/305]	Plate	C
1	1.1	AS/NZS	1594	HA1	—		48/29 [330/200]	Plate, Sheet, & Strip	C
1	1.1	AS/NZS	1594	HA200	—		43.5/29 [300/200]	Plate, Sheet, & Strip	C
1	1.1	AS/NZS	1594	HA250	—		51/36 [350/250]	Plate, Sheet, & Strip	C
1	1.1	AS/NZS	1594	HA250/1	—		55/36 [380/250]	Plate, Sheet, & Strip	C
1	1.1	AS/NZS	1594	HA3	—		43.5/29 [300/200]	Plate, Sheet, & Strip	C
1	1.2	AS/NZS	1594	HA300	—		58/43.5 [400/300]	Plate, Sheet, & Strip	C-Mn
1	1.2	AS/NZS	1594	HA300/1	—		62.5/43.5 [430/300]	Plate, Sheet, & Strip	C-Mn
1	1.2	AS/NZS	1594	HA350	—		62.5/51 [430/350]	Plate, Sheet, & Strip	C-Mn
1	2.1	AS/NZS	1594	HA400	—		67/55 [460/380]	Plate, Sheet, & Strip	C-Mn
1	1.1	AS/NZS	1594	HA4N	—		40.5/25 [280/170]	Plate, Sheet, & Strip	C
1	1.1	AS/NZS	1594	HU250	—		51/36 [350/250]	Plate, Sheet, & Strip	C
1	1.2	AS/NZS	1594	HU300	—		58/43.5 [400/300]	Plate, Sheet, & Strip	C-Mn
1	1.2	AS/NZS	1594	HU300/1	—		62.5/43.5 [430/300]	Plate, Sheet, & Strip	C-Mn
1	1.4	AS/NZS	1594	HW350	—		65/50 [450/340]	Plate, Sheet, & Strip	C-Mn
1	1.2	AS/NZS	1594	XF300	—		64/43.5 [440/300]	Plate, Sheet, & Strip	C-Mn-Cr-Ni-Cu
1	2.1	AS/NZS	1594	XF400	—		67/55 [460/380]	Plate, Sheet, & Strip	C-Mn
1	1.1	AS/NZS	3678	200	—		43.5/29 [300/200]	Plate	C-Mn
1	1.2	AS/NZS	3678	250	—		59.5/40.5 [410/280]	Plate	C-Mn
1	1.2	AS/NZS	3678	250L15	—		59.5/40.5 [410/280]	Plate	C-Mn
1	1.1	AS/NZS	3679.1	250	—		59.5/38 [410/260]	Bar & Sections	C-Mn

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	1.1	AS/NZS	3679.1	250L0	—		59.5/38 [410/260]	Bar & Sections	C-Mn
1	1.1	AS/NZS	3679.1	250L15	—		59.5/38 [410/260]	Bar & Sections	C-Mn
1	1.1	ASTM	A27	60-30	J03000		60/30 [415/205]	Castings	C
1	1.1	ASTM	A27	65-35	J03001		65/35 [450/240]	Castings	C
1	1.1	ASTM	A27	U-60-30	J03000		60/30 [415/205]	Castings	C
1	1.1	ASTM/ASME	A/SA-31	B	K03100		58/29 [400/200]	Rivets	C
1	1.1	ASTM/ASME	A/SA-36	—	—		58/36 [400/250]	Bar	C-Mn-Si
1	1.1	ASTM/ASME	A/SA-36	—	K02595	>4 [≥100]	58/36 [400/250]	Plates	C-Mn-Si
1	1.1	ASTM/ASME	A/SA-36	—	K02596	>2.5 and ≤4 [≥65 and ≤100]	58/36 [400/250]	Plates	C-Mn-Si
1	1.1	ASTM/ASME	A/SA-36	—	K02597	>1.5 and ≤2.5 [≥40 and ≤65]	58/36 [400/250]	Plates	C-Mn-Si
1	1.1	ASTM/ASME	A/SA-36	—	K02598	>0.75 and ≤1.5 [≥20 and ≤40]	58/36 [400/250]	Plates	C-Mn-Si
1	1.1	ASTM/ASME	A/SA-36	—	K02599	≤0.75 [≤20]	58/36 [400/250]	Plates	C-Mn-Si
1	1.1	ASTM/ASME	A/SA-36	—	K02600		58/36 [400/250]	Shapes	C-Mn-Si
1	1.1	ASTM/ASME	A/SA-53	E, A	K02504		48/30 [330/205]	Resistance Welded Pipe	C
1	1.1	ASTM/ASME	A/SA-53	E, B	K03005		60/35 [415/240]	Resistance Welded Pipe	C-Mn
1	1.1	ASTM/ASME	A/SA-53	F	K03005		48/30 [330/205]	Furnace Welded Pipe	C
1	1.1	ASTM/ASME	A/SA-53	S, A	K02504		48/30 [330/205]	Seamless Pipe	C
1	1.1	ASTM/ASME	A/SA-53	S, B	K03005		60/35 [415/240]	Seamless Pipe	C-Mn
1	1.1	ASTM/ASME	A/SA-106	A	K02501		48/30 [330/205]	Seamless Pipe	C-Si
1	1.1	ASTM/ASME	A/SA-106	B	K03006		60/35 [415/240]	Seamless Pipe	C-Mn-Si
1	1.1	ASTM	A108	1015 CW	G10150		— [—]	Bar	C
1	1.1	ASTM	A108	1018 CW	G10180		— [—]	Bar	C
1	1.1	ASTM	A108	1020 CW	G10200		— [—]	Bar	C
1	1.1	ASTM	A131	A	—		58/34 [400/235]	Plate, Shapes, Bar, & Rivets	C
1	1.1	ASTM	A131	B	—		58/34 [400/235]	Plate, Shapes, Bar, & Rivets	C-Mn-Si
1	1.1	ASTM	A131	CS	—		58/34 [400/235]	Plate, Shapes, Bar, & Rivets	C-Mn-Si

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	1.1	ASTM	A131	D	—		58/34 [400/235]	Plate, Shapes, Bar, & Rivets	C-Mn-Si
1	1.1	ASTM	A131	DS	—		58/34 [400/235]	Plate, Shapes, Bar, & Rivets	C-Mn-Si
1	1.1	ASTM/ASME	A/SA-134	SA283, A	K01400		45/24 [310/165]	Welded Pipe	C
1	1.1	ASTM/ASME	A/SA-134	SA283, B	K01702		50/27 [345/185]	Welded Pipe	C
1	1.1	ASTM/ASME	A/SA-134	SA283, C	K02401		55/30 [380/205]	Welded Pipe	C
1	1.1	ASTM/ASME	A/SA-134	SA283, D	K02702		60/33 [415/230]	Welded Pipe	C
1	1.1	ASTM/ASME	A/SA-134	SA285, A	K01700		45/24 [310/165]	Welded Pipe	C
1	1.1	ASTM/ASME	A/SA-134	SA285, B	K02200		50/27 [345/185]	Welded Pipe	C
1	1.1	ASTM/ASME	A/SA-134	SA285, C	K02801		55/30 [380/205]	Welded Pipe	C
1	1.1	ASTM/ASME	A/SA-134	SA36	K02599		58/36 [400/250]	Welded Pipe	C
1	1.1	ASTM/ASME	A/SA-135	A	K02509		48/30 [330/205]	E.R.W. Pipe	C
1	1.1	ASTM/ASME	A/SA-135	B	K03018		60/35 [415/240]	E.R.W. Pipe	C
1	1.1	ASTM	A139	A	K02508		48/30 [330/205]	Welded Pipe	C
1	1.1	ASTM	A139	B	K03003		60/35 [415/240]	Welded Pipe	C
1	1.1	ASTM	A139	C	K03004		60/42 [415/290]	Welded Pipe	C
1	1.1	ASTM	A139	D	K03010		60/46 [415/315]	Welded Pipe	C
1	1.1	ASTM	A139	E	K03012		66/52 [455/360]	Welded Pipe	C
1	—	ASTM	A161	Low Carbon	K01504		47/26 [325/180]	Tube	C
1	1.1	ASTM/ASME	A/SA-178	A	K01200		47/26 [325/180]	E.R.W. Tube	C
1	1.1	ASTM/ASME	A/SA-178	C	K03503		60/37 [415/255]	E.R.W. Tube	C
1	1.1	ASTM/ASME	A/SA-179	—	K01200		47/26 [325/180]	Seamless Tube	C
1	1.1	ASTM/ASME	A/SA-181	Cl. 60	K03502		60/30 [415/205]	Pipe Flange & Fittings	C-Si
1	1.1	ASTM/ASME	A/SA-192	—	K01201		47/26 [325/180]	Seamless Tube	C-Si
1	1.1	ASTM/ASME	A/SA-210	A-1	K02707		60/37 [415/255]	Seamless Tube	C-Si
1	1.1	ASTM	A211	A570-30	K02502		49/30 [340/205]	Welded Pipe	C
1	1.1	ASTM	A211	A570-33	K02502		52/33 [360/230]	Welded Pipe	C
1	1.1	ASTM	A211	A570-40	K02502		55/40 [380/275]	Welded Pipe	C
1	1.1	ASTM/ASME	A/SA-214	—	K01807		47/26 [325/180]	E.R.W. Tube	C
1	1.1	ASTM/ASME	A/SA-216	WCA	J02502		60/30 [415/205]	Castings	C-Si

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	1	1.1	ASTM	A226	—	K01201		47/26 [325/180]	E.R.W. Tube	C-Si
1	1	11.1	ASTM/ASME	A/SA-234	WPB	K03006		60/35 [415/240]	Piping Fittings	C-Mn-Si
1	1	—	ASTM	A252	1	—		50/30 [345/205]	Pipe Piles	C
1	1	—	ASTM	A252	2	—		60/35 [415/240]	Pipe Piles	C
1	1	—	ASTM	A252	3	—		66/45 [455/310]	Pipe Piles	C
1	1	11.1	ASTM/ASME	A/SA-266	1	K03506		60/30 [415/205]	Forgings	C-Si
1	1	1.1	ASTM/ASME	A/SA-283	A	K01400		45/24 [310/165]	Plate	C
1	1	1.1	ASTM/ASME	A/SA-283	B	K01702		50/27 [345/185]	Plate	C
1	1	1.1	ASTM/ASME	A/SA-283	C	K02401		55/30 [380/205]	Plate	C
1	1	1.1	ASTM/ASME	A/SA-283	D	K02702		60/33 [415/230]	Plate	C
1	1	1.1	ASTM/ASME	A/SA-285	A	K01700		45/24 [310/165]	Plate	C
1	1	1.1	ASTM/ASME	A/SA-285	B	K02200		50/27 [345/185]	Plate	C
1	1	1.1	ASTM/ASME	A/SA-285	C	K02801		55/30 [380/205]	Plate	C
1	1	11.1	ASTM/ASME	A/SA-333	1	K03008		55/30 [380/205]	Seamless & Welded Pipe	C-Mn
1	1	11.1	ASTM/ASME	A/SA-333	6	K03006		60/35 [415/240]	Seamless & Welded Pipe	C-Mn-Si
1	1	11.1	ASTM/ASME	A/SA-334	1	K03008		55/30 [380/205]	Welded Tube	C-Mn
1	1	11.1	ASTM/ASME	A/SA-334	6	K03006		60/35 [415/240]	Welded Tube	C-Mn-Si
1	1	11.1	ASTM/ASME	A/SA-350	LF1	K03009		60/30 [415/205]	Forgings	C-Mn-Si
1	1	1.2	ASTM/ASME	A/SA-350	LF6, Cl.1	K12202		66/52 [455/360]	Forgings	C-Mn-Si-V
1	1	11.1	ASTM/ASME	A/SA-352	LCA	J02504		60/30 [415/205]	Castings	C-Si
1	1	1.1	ASTM/ASME	A/SA-352	LCB	J03003		65/35 [450/240]	Castings	C-Si
1	1	1.1	ASTM	A366	CS	—		43/20 [295/140]	Sheet	C
1	1	1.1	ASTM/ASME	A/SA-369	FPA	K02501		48/30 [330/205]	Forged Pipe	C-Si
1	1	1.1	ASTM/ASME	A/SA-369	FPB	K03006		60/35 [415/240]	Forged Pipe	C-Mn-Si
1	1	11.1	ASTM/ASME	A/SA-372	A	K03002		60/35 [415/240]	Forgings	C-Si
1	1	11.1	ASTM	A381	Y35	—		60/35 [415/240]	Welded Pipe	C
1	1	11.1	ASTM	A381	Y42	—		60/42 [415/290]	Welded Pipe	C
1	1	11.1	ASTM	A381	Y46	—		63/46 [435/315]	Welded Pipe	C
1	1	11.1	ASTM	A381	Y48	—		62/48 [425/330]	Welded Pipe	C

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	11.1	ASTM	A381	Y50	—		64/50 [440/345]	Welded Pipe	C
1	1.1	ASTM/ASME	A/SA-414	A	K01501		45/25 [310/170]	Sheet	C
1	1.1	ASTM/ASME	A/SA-414	B	K02201		50/30 [345/205]	Sheet	C
1	1.1	ASTM/ASME	A/SA-414	C	K02503		55/33 [380/230]	Sheet	C
1	1.1	ASTM/ASME	A/SA-414	D	K02505		60/35 [415/240]	Sheet	C-Mn
1	1.1	ASTM/ASME	A/SA-414	E	K02704		65/38 [450/260]	Sheet	C-Mn
1	1.1	ASTM/ASME	A/SA-420	WPL6	K03006		60/35 [415/240]	Piping Fittings	C-Mn-Si
1	1.1	ASTM	A500	A	K03000		45/33 [310/230]	Seamless & Welded Tube	C
1	1.1	ASTM	A500	B	K03000		58/42 [400/290]	Seamless & Welded Tube	C
1	1.2	ASTM	A500	C	K02705		62/46 [425/315]	Seamless & Welded Tube	C
1	1.1	ASTM	A500	D	K03000		58/36 [400/250]	Seamless & Welded Tube	C
1	1.1	ASTM	A501	A	K03000		58/36 [400/250]	Seamless & Welded Tube	C
1	1.2	ASTM	A501	B	K03000		70/50 [485/345]	Seamless & Welded Tube	C
1	1.1	ASTM	A512	1008	G10080		40/20 [275/140]	Tube	C
1	1.1	ASTM	A512	1010	G10100		40/20 [275/140]	Tube	C
1	1.1	ASTM	A512	1012	G10120		40/20 [275/140]	Tube	C
1	1.1	ASTM	A512	1015	G10150		40/20 [275/140]	Tube	C
1	—	ASTM	A512	1016	G10160		40/20 [275/140]	Tube	C
1	1.1	ASTM	A512	1018	G10180		43/25 [295/170]	Tube	C
1	—	ASTM	A512	1019	G10190		43/25 [295/170]	Tube	C
1	1.1	ASTM	A512	1020	G10200		50/30 [345/205]	Tube	C
1	—	ASTM	A512	1021	G10210		50/30 [345/205]	Tube	C
1	1.1	ASTM	A512	1026	G10260		55/35 [380/240]	Tube	C
1	—	ASTM	A512	1110	G11100		55/35 [380/240]	Tube	C
1	—	ASTM	A512	1115	G11150		55/35 [380/240]	Tube	C
1	—	ASTM	A512	1117	G11170		40/20 [275/140]	Tube	C
1	1.1	ASTM	A512	MT 1010	G10100		40/20 [275/140]	Tube	C
1	1.1	ASTM	A512	MT 1015	G10150		43/25 [295/170]	Tube	C
1	1.1	ASTM	A512	MT 1020	G10200		50/30 [345/205]	Tube	C

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	1	1.1	ASTM	A512	MTX 1015	—	40/20 [275/140]	Tube	C	
1	1	1.1	ASTM	A512	MTX 1020	—	50/30 [345/205]	Tube	C	
1	1	1.1	ASTM/ASME	A/SA-513	1008	G10080	42/30 [290/205]	Tube	C	
1	1	1.1	ASTM/ASME	A/SA-513	1010	G10100	45/32 [310/220]	Tube	C	
1	1	1.1	ASTM/ASME	A/SA-513	1015	G10150	48/35 [330/240]	Tube	C	
1	1	1.1	ASTM	A513	1015 CW	G10150	—/— [—/—]	Tube	C	
1	1	—	ASTM/ASME	A/SA-513	1017	G10170	48/35 [330/240]	Tube	C	
1	1	1.1	ASTM/ASME	A/SA-513	1018	G10180	48/35 [330/240]	Tube	C	
1	1	—	ASTM/ASME	A/SA-513	1019	G10190	48/35 [330/240]	Tube	C	
1	1	1.1	ASTM/ASME	A/SA-513	1020	G10200	52/38 [360/260]	Tube	C	
1	1	1.1	ASTM/ASME	A/SA-513	1021	G10210	54/40 [370/275]	Tube	C	
1	1	1.1	ASTM/ASME	A/SA-513	1022	G10220	52/38 [360/260]	Tube	C	
1	1	—	ASTM/ASME	A/SA-513	1023	G10230	52/38 [360/260]	Tube	C	
1	1	—	ASTM/ASME	A/SA-513	1024	G10240	52/38 [360/260]	Tube	C	
1	1	1.1.1	ASTM/ASME	A/SA-513	1026	G10260	62/45 [425/310]	Tube	C	
1	1	1.1	ASTM/ASME	A/SA-513	MT 1010	G10100	45/32 [310/220]	Tube	C	
1	1	1.1	ASTM/ASME	A/SA-513	MT 1015	G10150	—/— [—/—]	Tube	C	
1	1	1.1	ASTM/ASME	A/SA-513	MT 1020	G10200	—/— [—/—]	Tube	C	
1	1	—	ASTM/ASME	A/SA-513	MTX 1015	—	—/— [—/—]	Tube	C	
1	1	—	ASTM/ASME	A/SA-513	MTX 1020	—	—/— [—/—]	Tube	C	
1	1	1.1	ASTM	A515	55	K02001	55/30 [380/205]	Plate	C-Si	
1	1	1.1.1	ASTM/ASME	A/SA-515	60	—	60/32 [415/220]	Plate	C-Si	
1	1	1.1	ASTM/ASME	A/SA-515	60	K02401	60/32 [415/220]	Plate	C	
1	1	1.1.1	ASTM/ASME	A/SA-515	65	K02800	65/35 [450/240]	Plate	C-Si	
1	1	1.1	ASTM/ASME	A/SA-516	55	K01800	55/30 [380/205]	Plate	C-Si	
1	1	1.1	ASTM/ASME	A/SA-516	60	K02100	60/32 [415/220]	Plate	C-Mn-Si	
1	1	1.1	ASTM/ASME	A/SA-516	65	K02403	65/35 [450/240]	Plate	C-Mn-Si	
1	1	1.1	ASTM	A519	1008	G10080	40/20 [275/140]	Tube	C	
1	1	1.1	ASTM	A519	1012	G10120	40/20 [275/140]	Tube	C	

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	1.1	ASTM	A519	1015	G10150		40/20 [275/140]	Tube	C
1	—	ASTM	A519	1016	G10160		40/20 [275/140]	Tube	C
1	—	ASTM	A519	1017	G10170		40/20 [275/140]	Tube	C
1	1.1	ASTM	A519	1018	G10180		43/25 [295/170]	Tube	C
1	1.1	ASTM	A519	1018 HR	G10180		— [—]	Tube	C
1	—	ASTM	A519	1019	G10190		50/30 [345/205]	Tube	C
1	1.1	ASTM	A519	1020	G10200		48/28 [330/195]	Tube	C
1	1.1	ASTM	A519	1020 HR	G10200		—/32 [—/220]	Tube	C
1	—	ASTM	A519	1021	G10210		50/30 [345/205]	Tube	C
1	1.1	ASTM	A519	1022	G10220		50/30 [345/205]	Tube	C
1	1.1	ASTM	A519	1022 HR	G10220		— [—]	Tube	C
1	1.1	ASTM	A519	1025 HR	G10250		—/35 [—/240]	Tube	C
1	—	ASTM	A519	1026	G10260		55/35 [380/240]	Tube	C
1	1.1	ASTM	A519	1026 HR	G10260		— [—]	Tube	C
1	1.1	ASTM	A519	MT 1010	G10100		40/20 [275/140]	Tube	C
1	1.1	ASTM	A519	MT 1015	G10150		43/25 [295/170]	Tube	C
1	1.1	ASTM	A519	MT 1020	G10200		50/30 [345/205]	Tube	C
1	—	ASTM	A519	MTX 1015	—		40/20 [275/140]	Tube	C
1	—	ASTM	A519	MTX 1020	—		50/30 [345/205]	Tube	C
1	—	ASTM	A521	CC	—		60/30 [415/205]	Die Forging	C
1	—	ASTM	A521	CC1	—		66/33 [455/230]	Die Forging	C
1	1.1	ASTM	A523	A	K02504		48/30 [330/205]	Pipe	C-Mn
1	1.1	ASTM	A523	B	K03005		60/35 [415/240]	Pipe	C-Mn
1	1.1	ASTM/ASME	A/SA-524	I	K02104		60/35 [415/240]	Seamless Pipe	C-Mn-Si
1	1.1	ASTM/ASME	A/SA-524	II	K02104		55/30 [380/205]	Seamless Pipe	C-Mn-Si
1	—	ASTM	A526	II	—		42/25 [290/170]	Galvanized Sheet	
1	—	ASTM	A527	II	—		42/25 [290/170]	Galvanized Sheet	
1	1.1	ASTM	A529	42	K02703		60/42 [415/290]	Plate, Bar, & Shapes	C-Mn
1	—	ASTM	A539	—	K01506		45/35 [310/240]	Coiled Tube	C

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	1.1	ASTM/ASME	A/SA-556	A2	K01807		47/26 [325/180]	Seamless Tube	C
1	1.1.1	ASTM/ASME	A/SA-556	B2	K02707		60/37 [415/255]	Seamless Tube	C-Si
1	1.1	ASTM/ASME	A/SA-557	A2	K01807		47/26 [325/180]	E.R.W. Tube	C
1	1.1.1	ASTM/ASME	A/SA-557	B2	K03007		60/37 [415/255]	E.R.W. Tube	C
1	1.1	ASTM/ASME	A/SA-562	—	K11224		55/30 [380/205]	Plate	C-Mn-Ti
1	1.1	ASTM	A569	30	K02502		49/30 [340/205]	Sheet & Strip	C
1	1.1	ASTM	A569	33	K02502		52/33 [360/230]	Sheet & Strip	C
1	1.1	ASTM	A569	36	K02502		53/36 [365/250]	Sheet & Strip	C
1	1.1	ASTM	A569	40	K02502		55/40 [380/275]	Sheet & Strip	C
1	1.2	ASTM	A569	45	K02502		60/45 [415/310]	Sheet & Strip	C
1	1.2	ASTM	A569	50	K02502		65/50 [450/345]	Sheet & Strip	C
1	1.1	ASTM	A570	30	K02502		49/30 [340/205]	Sheet & Strip	C
1	1.1	ASTM	A570	33	K02502		52/33 [360/230]	Sheet & Strip	C
1	1.1	ASTM	A570	36	K02502		53/36 [365/250]	Sheet & Strip	C
1	1.1	ASTM	A570	40	K02502		55/40 [380/275]	Sheet & Strip	C
1	1.2	ASTM	A570	45	K02502		60/45 [415/310]	Sheet & Strip	C
1	1.2	ASTM	A570	50	K02502		65/50 [450/345]	Sheet & Strip	C
1	1.3	ASTM	A570	55	K02502		70/55 [485/380]	Sheet & Strip	C
1	1.2	ASTM/ASME	A/SA-572	42	—		60/42 [415/290]	Plate & Shapes	C-Mn-Si
1	1.2	ASTM/ASME	A/SA-572	50	—		65/50 [450/345]	Plate & Shapes	C-Mn-Si
1	1.1.1	ASTM	A573	58	—		58/32 [400/220]	Plate	C
1	1.1.1	ASTM	A573	65	—		65/35 [450/240]	Plate	C
1	1.1	ASTM	A575	M1008	—		—/— [—/—]	Bar	C
1	1.1	ASTM	A575	M1010	—		—/— [—/—]	Bar	C
1	1.1	ASTM	A575	M1012	—		—/— [—/—]	Bar	C
1	1.1	ASTM	A575	M1015	—		—/— [—/—]	Bar	C
1	1.1	ASTM	A575	M1017	—		—/— [—/—]	Bar	C
1	1.1.1	ASTM	A575	M1020	—		—/— [—/—]	Bar	C
1	1.1.1	ASTM	A575	M1023	—		—/— [—/—]	Bar	C

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	1.1	ASTM	A575	M1025	—	—	—	Bar	C
1	1.1	ASTM	A576	G10080	—	—	—	Bar	C
1	1.1	ASTM	A576	G10100	—	—	—	Bar	C
1	1.1	ASTM	A576	G10120	—	—	—	Bar	C
1	1.1	ASTM	A576	G10150	—	—	—	Bar	C
1	1.1	ASTM	A576	G10160	—	—	—	Bar	C
1	1.1	ASTM	A576	G10170	—	—	—	Bar	C
1	1.1	ASTM	A576	G10180	—	—	—	Bar	C
1	1.1	ASTM	A576	G10190	—	—	—	Bar	C
1	1.1	ASTM	A576	G10200	—	—	—	Bar	C
1	1.1	ASTM	A576	G10210	—	—	—	Bar	C
1	1.1	ASTM	A576	G10220	—	—	—	Bar	C
1	1.1	ASTM	A576	G10230	—	—	—	Bar	C
1	1.1	ASTM	A576	G10250	—	—	—	Bar	C
1	1.1	ASTM/ASME	A/SA-587	—	K11500	—	48/30 [330/205]	E.R.W. Pipe	C
1	1.1	ASTM/ASME	A/SA-587	A2	K01807	—	47/26 [325/180]	E.R.W. Tube	C
1	—	ASTM/ASME	A/SA-587	B2	K03007	—	60/37 [415/255]	E.R.W. Tube	C
1	—	ASTM	A607	45	—	—	65/45 [450/310]	Sheet & Strip	C-Mn-Cb-V
1	—	ASTM	A607	50	—	—	65/50 [450/345]	Sheet & Strip	C-Mn-Cb-V
1	—	ASTM	A611	A	G10170	—	42/25 [290/170]	Sheet & Strip	C
1	—	ASTM	A611	B	G10170	—	45/30 [310/205]	Sheet & Strip	C
1	—	ASTM	A611	C	G10170	—	48/33 [330/230]	Sheet & Strip	C
1	1.1	ASTM	A611	D	G10120	—	52/40 [360/275]	Sheet & Strip	C
1	1.2	ASTM	A618	III	K12700	—	65/50 [450/345]	Tube	Mn-V
1	1.1	ASTM	A620	A	K00040	—	40/22 [275/150]	Sheet	C
1	1.1	ASTM	A620	B	K00040	—	40/22 [275/150]	Sheet	C
1	1.1	ASTM	A633	A	K01802	—	63/42 [435/290]	Plate & Shapes	Mn-Cb
1	1.1	ASTM	A633	C	K12000	>2.5 and ≤4 [>64 and ≤102]	65/46 [450/315]	Plate & Shapes	Mn-Cb

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	1	1.1	ASTM	A633	D	K12037	>2.5 and ≤4 [>64 and ≤102]	65/46 [450/315]	Plate & Shapes	C-Mn-Si
1	1	—	ASTM	A653	33	—	—	45/33 [310/230]	Galvanized Sheet	C
1	1	—	ASTM	A653	37	—	—	52/37 [360/255]	Galvanized Sheet	C
1	1	—	ASTM	A653	40	—	—	55/40 [380/275]	Galvanized Sheet	C
1	1	—	ASTM	A653	80	—	—	82/80 [565/550]	Galvanized Sheet	C
1	1	1.2	ASTM/ASME	A/SA-656	50	K11804	≤2 [≤50]	60/50 [415/345]	Plate	C-Mn-V
1	1	1.3	ASTM/ASME	A/SA-656	60	K11804	≤1.5 [≤40]	70/60 [485/415]	Plate	C-Mn-V
1	1	1.2	ASTM/ASME	A/SA-656	T3, 50	—	—	60/50 [415/345]	Plate	C-Mn-Si-V-Cb
1	1	1.2	ASTM/ASME	A/SA-656	T7, 50	—	—	60/50 [415/345]	Plate	C-Mn-Si-V-Cb
1	1	1.1	ASTM	A659	1015	G10150	—	— [—]	Sheet & Strip	C
1	1	—	ASTM	A659	1016	G10160	—	— [—]	Sheet & Strip	C
1	1	—	ASTM	A659	1017	G10170	—	— [—]	Sheet & Strip	C
1	1	1.1	ASTM	A659	1018	G10180	—	— [—]	Sheet & Strip	C
1	1	1.1	ASTM	A659	1020	G10200	—	— [—]	Sheet & Strip	C
1	1	—	ASTM	A659	1021	G10210	—	— [—]	Sheet & Strip	C
1	1	—	ASTM	A659	1023	G10230	—	— [—]	Sheet & Strip	C
1	1	11.1	ASTM/ASME	A/SA-660	WCA	J02504	—	60/30 [415/205]	Centrifugal Cast Pipe	C-Si
1	1	1.1	ASTM/ASME	A/SA-662	A	K01701	—	58/40 [400/275]	Plate	C-Mn-Si
1	1	1.1	ASTM/ASME	A/SA-662	B	K02203	—	65/40 [450/275]	Plate	C-Mn-Si
1	1	—	ASTM	A663	—	—	—	— [—]	Bar	C
1	1	—	ASTM	A663	45	—	—	45/25 [310/175]	Bars & Shapes	C
1	1	—	ASTM	A663	50	—	—	50/28 [345/195]	Bars & Shapes	C
1	1	—	ASTM	A663	55	—	—	55/30 [380/205]	Bars & Shapes	C
1	1	—	ASTM	A663	60	—	—	60/33 [415/230]	Bars & Shapes	C
1	1	—	ASTM	A663	65	—	—	65/36 [450/250]	Bars & Shapes	C
1	1	1.1	ASTM	A668	B	G10200	—	60/30 [415/205]	Forgings	C
1	1	11.1	ASTM/ASME	A/SA-671	CA55	K02801	—	55/30 [380/205]	Fusion Welded Pipe	C
1	1	1.1	ASTM/ASME	A/SA-671	CB60	K02401	—	60/32 [415/220]	Fusion Welded Pipe	C

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	11.1	ASTM/ASME	A/SA-671	CB65	K02800		65/35 [450/240]	Fusion Welded Pipe	C-Si
1	11.1	ASTM/ASME	A/SA-671	CC60	K02100		60/32 [415/220]	Fusion Welded Pipe	C-Mn-Si
1	11.1	ASTM/ASME	A/SA-671	CC65	K02403		65/35 [450/240]	Fusion Welded Pipe	C-Mn-Si
1	11.1	ASTM/ASME	A/SA-671	CE55	K02202		55/30 [380/205]	Fusion Welded Pipe	C
1	11.1	ASTM/ASME	A/SA-671	CE60	K02402		60/32 [415/220]	Fusion Welded Pipe	C-Mn-Si
1	11.1	ASTM/ASME	A/SA-672	A45	K01700		45/24 [310/165]	Fusion Welded Pipe	C
1	11.1	ASTM/ASME	A/SA-672	A50	K02200		50/27 [345/185]	Fusion Welded Pipe	C
1	11.1	ASTM/ASME	A/SA-672	A55	K02801		55/30 [380/205]	Fusion Welded Pipe	C
1	11.1	ASTM/ASME	A/SA-672	B55	K02001		55/30 [380/205]	Fusion Welded Pipe	C-Si
1	11.1	ASTM/ASME	A/SA-672	B60	K02401		60/32 [415/220]	Fusion Welded Pipe	C
1	11.1	ASTM/ASME	A/SA-672	B65	K02800		65/35 [450/240]	Fusion Welded Pipe	C-Si
1	11.1	ASTM/ASME	A/SA-672	C55	K01800		55/30 [380/205]	Fusion Welded Pipe	C-Si
1	11.1	ASTM/ASME	A/SA-672	C60	K02100		60/32 [415/220]	Fusion Welded Pipe	C-Mn-Si
1	11.1	ASTM/ASME	A/SA-672	C65	K02403		65/35 [450/240]	Fusion Welded Pipe	C-Mn-Si
1	11.1	ASTM/ASME	A/SA-672	E55	K02202		55/30 [380/205]	Fusion Welded Pipe	C
1	11.1	ASTM/ASME	A/SA-672	E60	K02402		60/32 [415/220]	Fusion Welded Pipe	C-Mn-Si
1	11.1	ASTM/ASME	A/SA-675	45	—		45/23 [310/160]	Bar	C
1	11.1	ASTM/ASME	A/SA-675	50	—		50/25 [345/170]	Bar	C
1	11.1	ASTM/ASME	A/SA-675	55	—		55/27 [380/185]	Bar	C
1	11.1	ASTM/ASME	A/SA-675	60	—		60/30 [415/205]	Bar	C
1	11.1	ASTM/ASME	A/SA-675	65	—		65/32 [450/220]	Bar	C
1	11.1	ASTM	A694	F42	K03014		60/42 [415/290]	Forgings	C-Mn
1	11.1	ASTM	A694	F46	K03014		60/46 [415/315]	Forgings	C-Mn
1	11.1	ASTM	A694	F48	K03014		62/48 [425/330]	Forgings	C-Mn
1	11.1	ASTM	A694	F50	K03014		64/50 [440/345]	Forgings	C-Mn
1	11.1	ASTM	A694	F52	K03014		66/52 [455/360]	Forgings	C-Mn
1	11.1	ASTM/ASME	A/SA-695	B, 35	K03504		60/35 [415/240]	Bar	C
1	11.1	ASTM/ASME	A/SA-696	B	K03200		60/35 [415/240]	Bar	C-Mn-Si
1	1.2	ASTM	A707	L1, Cl. 1	K02302		60/42 [415/290]	Forgings	C-Mn

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	1.2	ASTM	A707	L1, Cl. 2	K02302		66/52 [455/360]	Forgings	C-Mn
1	11.1	ASTM	A707	L2, Cl. 1	K03301		60/42 [415/290]	Forgings	C-Mn
1	11.1	ASTM	A707	L2, Cl. 2	K03301		66/52 [455/360]	Forgings	C-Mn
1	1.2	ASTM	A707	L3, Cl. 1	K12510		60/42 [415/290]	Forgings	C-Mn-V-N
1	1.2	ASTM	A707	L3, Cl. 2	K12510		66/52 [455/360]	Forgings	C-Mn-V-N
1	—	ASTM	A707	L4, Cl. 1	K12089		60/42 [415/290]	Forgings	1.8Ni-0.6Mn-0.3Mo
1	—	ASTM	A707	L4, Cl. 2	K12089		66/52 [455/360]	Forgings	1.8Ni-0.6Mn-0.3Mo
1	—	ASTM	A707	L5, Cl. 1	K20934		60/42 [415/290]	Forgings	1.1.2Cu-1Ni-0.7Cr-0.5Mn
1	—	ASTM	A707	L5, Cl. 2	K20934		66/52 [455/360]	Forgings	1.2Cu-1Ni-0.7Cr-0.5Mn
1	11.1	ASTM	A709	36	—		58/36 [400/250]	Plate, Bar, & Shapes	C-Mn
1	1.2	ASTM	A709	50	—		65/50 [450/345]	Plate, Bar, & Shapes	C-Mn
1	1.2	ASTM	A709	50S	—		65/50 [450/345]	Plate, Bar, & Shapes	C-Mn
1	11.1	ASTM/ASME	A/SA-727	—	K02506		60/36 [415/250]	Forgings	C-Mn-Si
1	11.1	ASTM/ASME	A/SA-765	I	K03046		60/30 [415/205]	Forgings	C-Mn-Si
1	—	ASTM	A795	E, A	—		60/— [415/—]	Resistance Welded Pipe	C-Mn
1	—	ASTM	A795	E, B	—		60/— [415/—]	Resistance Welded Pipe	C-Mn
1	—	ASTM	A795	F	—		60/— [415/—]	Furnace Welded Pipe	C-Mn
1	—	ASTM	A795	S, A	—		60/— [415/—]	Seamless Pipe	C-Mn
1	—	ASTM	A795	S, B	—		60/— [415/—]	Seamless Pipe	C-Mn
1	1.4	ASTM	A808	—	K11852	≤2.5 [≤64]	60/42 [415/290]	Plate	C-Mn-Cb-V
1	1.1	ASTM	A830	1006	G10060		40/20 [275/140]	Plate	C
1	1.1	ASTM	A830	1008	G10080		40/20 [275/140]	Plate	C
1	1.1	ASTM	A830	1009	G10090		40/20 [275/140]	Plate	C
1	1.1	ASTM	A830	1010	G10100		40/20 [275/140]	Plate	C
1	1.1	ASTM	A830	1012	G10120		40/20 [275/140]	Plate	C
1	1.1	ASTM	A830	1015	G10150		40/20 [275/140]	Plate	C
1	1.1	ASTM	A830	1016	G10160		40/20 [275/140]	Plate	C
1	1.1	ASTM	A830	1017	G10170		40/20 [275/140]	Plate	C
1	1.1	ASTM	A830	1018	G10180		43/25 [295/170]	Plate	C

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	1.1	ASTM	A830	1019	G10190		43/25 [295/170]	Plate	C
1	1.1	ASTM	A830	1020	G10200		43/25 [295/170]	Plate	C
1	1.1	ASTM	A830	1021	G10210		43/25 [295/170]	Plate	C
1	1.1	ASTM	A830	1022	G10220		43/25 [295/170]	Plate	C
1	1.1	ASTM	A830	1023	G10230		43/25 [295/170]	Plate	C
1	1.1	ASTM/ASME	A/SA-836	—	—		55/25 [380/175]	Forgings	C-Si-Ti
1	1.1	ASTM	A857	25	—		38/25 [260/170]	Sheet & Strip	C
1	1.1	ASTM	A857	30	—		49/30 [340/205]	Sheet & Strip	C
1	1.1	ASTM	A857	33	—		52/33 [360/230]	Sheet & Strip	C
1	1.1	ASTM	A857	36	—		53/36 [365/250]	Sheet & Strip	C
1	1.2	ASTM	A935	45 Cl. 1	—		60/45 [415/310]	Sheet & Strip	C-Mn-Cb-V
1	1.2	ASTM	A935	45 Cl. 2	—		55/45 [380/310]	Sheet & Strip	C-Mn-Cb-V
1	1.2	ASTM	A935	50 Cl. 1	—		65/50 [450/345]	Sheet & Strip	C-Mn-Cb-V
1	1.2	ASTM	A935	50 Cl. 2	—		60/50 [415/345]	Sheet & Strip	C-Mn-Cb-V
1	1.3	ASTM	A935	55 Cl. 2	—		65/55 [450/380]	Sheet & Strip	C-Mn-Cb-V
1	1.1	ASTM	A984	35	—		60/35 [415/240]	Pipe	C
1	1.1	ASTM	A992	—	—		65/50 [450/345]	Shapes	C-Mn-Si
1	1.2	ASTM	A992	—	—		65/50 [450/345]	Plate & Shapes	C-Mn
1	1.1	ASTM/ASME	A/SA-1008	CS, A	—		40/20 [275/140]	Sheet	C
1	1.1	ASTM/ASME	A/SA-1008	CS, B	—		40/20 [275/140]	Sheet	C
1	1.1	ASTM	A1008	CS, C	—		40/20 [275/140]	Sheet	C
1	1.1	ASTM	A1008	DS, A	—		40/22 [275/150]	Sheet	C
1	1.1	ASTM/ASME	A/SA-1008	DS, B	—		40/22 [275/150]	Sheet	C
1	1.2	ASTM	A1008	HSLAS 45 Cl. 1	—		60/45 [415/310]	Sheet	C
1	1.2	ASTM	A1008	HSLAS 45 Cl. 2	—		55/45 [380/310]	Sheet	C
1	1.2	ASTM	A1008	HSLAS 50 Cl. 1	—		65/50 [450/345]	Sheet	C
1	1.2	ASTM	A1008	HSLAS 50 Cl. 2	—		60/50 [415/345]	Sheet	C
1	1.3	ASTM	A1008	HSLAS 55 Cl. 2	—		65/55 [450/380]	Sheet	C
1	1.2	ASTM	A1008	HSLAS-F 50	—		60/50 [415/345]	Sheet	C

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	1	1.1	ASTM	A1008	SS 25	—	42/25 [290/170]	Sheet	C	
1	1	1.1	ASTM	A1008	SS 30	—	45/30 [310/205]	Sheet	C	
1	1	1.1	ASTM	A1008	SS 33, 1	—	48/33 [330/230]	Sheet	C	
1	1	1.1	ASTM	A1008	SS 33, 2	—	48/33 [330/230]	Sheet	C	
1	1	1.1	ASTM	A1008	SS 40, 1	—	52/40 [360/275]	Sheet	C	
1	1	1.1	ASTM	A1008	SS 40, 2	—	52/40 [360/275]	Sheet	C	
1	1	1.1	ASTM	A1011	CS, A	—	40/30 [275/205]	Sheet & Strip	C	
1	1	1.1	ASTM/ASME	A/SA-1011	CS, B	—	40/30 [275/205]	Sheet & Strip	C	
1	1	1.1	ASTM	A1011	CS, C	—	40/30 [275/205]	Sheet & Strip	C	
1	1	1.1	ASTM	A1011	CS, D	—	40/30 [275/205]	Sheet & Strip	C	
1	1	1.1	ASTM	A1011	DS, A	—	40/30 [275/205]	Sheet & Strip	C	
1	1	1.1	ASTM/ASME	A/SA-1011	DS, B	—	40/30 [275/205]	Sheet & Strip	C	
1	1	1.2	ASTM	A1011	HSLAS 45 Cl. 1	—	60/45 [415/310]	Sheet & Strip	C	
1	1	1.2	ASTM	A1011	HSLAS 45 Cl. 2	—	55/45 [380/310]	Sheet & Strip	C	
1	1	1.2	ASTM	A1011	HSLAS 50 Cl. 1	—	65/50 [450/345]	Sheet & Strip	C	
1	1	1.2	ASTM	A1011	HSLAS 50 Cl. 2	—	60/50 [415/345]	Sheet & Strip	C	
1	1	1.3	ASTM	A1011	HSLAS 55 Cl. 2	—	65/55 [450/380]	Sheet & Strip	C	
1	1	1.2	ASTM	A1011	HSLAS-F 50	—	60/50 [415/345]	Sheet & Strip	C	
1	1	1.1	ASTM	A1011	SS 30	—	49/30 [340/205]	Sheet & Strip	C	
1	1	1.1	ASTM	A1011	SS 33	—	52/33 [360/230]	Sheet & Strip	C	
1	1	1.1	ASTM	A1011	SS 36, 1	—	53/36 [365/250]	Sheet & Strip	C	
1	1	1.1	ASTM	A1011	SS 36, 2	—	53/36 [365/250]	Sheet & Strip	C	
1	1	1.1	ASTM	A1011	SS 40	—	55/40 [380/275]	Sheet & Strip	C	
1	1	1.2	ASTM	A1011	SS 45, 1	—	60/45 [415/310]	Sheet & Strip	C	
1	1	1.2	ASTM	A1011	SS 45, 2	—	60/45 [415/310]	Sheet & Strip	C	
1	1	1.2	ASTM	A1011	SS 50	—	65/50 [450/345]	Sheet & Strip	C	
1	1	1.2	ASTM	A1018	HSLAS 45 Cl. 1	—	60/45 [415/310]	Sheet & Strip	C	
1	1	1.2	ASTM	A1018	HSLAS 45 Cl. 2	—	55/45 [380/310]	Sheet & Strip	C	
1	1	1.2	ASTM	A1018	HSLAS 50 Cl. 1	—	65/50 [450/345]	Sheet & Strip	C	

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	1	1.2	ASTM	A1018	HSLAS 50 Cl. 2	—		60/50 [415/345]	Sheet & Strip	C
1	1	1.3	ASTM	A1018	HSLAS 55 Cl. 2	—		65/55 [450/380]	Sheet & Strip	C
1	1	1.2	ASTM	A1018	HSLAS-F 50	—		60/50 [415/345]	Sheet & Strip	C
1	1	1.1	ASTM	A1018	SS 30	—		49/30 [340/205]	Sheet & Strip	C
1	1	1.1	ASTM	A1018	SS 33	—		52/33 [360/230]	Sheet & Strip	C
1	1	1.1	ASTM	A1018	SS 36, 1	—		53/36 [365/250]	Sheet & Strip	C
1	1	1.1	ASTM	A1018	SS 36, 2	—		58/36 [400/250]	Sheet & Strip	C
1	1	1.1	CSA	G40.21	260W	—		60/38 [415/260]	Plate, Bar, & Shapes	C-Mn
1	1	1.1	CSA	G40.21	260WT	—		60/38 [415/260]	Plate, Bar, & Shapes	C-Mn-Si-Cb-V
1	1	1.2	CSA	G40.21	300W	—		65/44 [450/305]	Plate, Bar, & Shapes	C-Mn
1	1	1.2	CSA	G40.21	300WT	—		65/44 [450/305]	Plate, Bar, & Shapes	C-Mn-Si-Cb-V
1	1	1.2	CSA	G40.21	350W	—		65/50 [450/345]	Plate, Bar, & Shapes	C-Mn
1	1	1.1	CSA	Z245.1	172	—		45/25 [310/170]	Pipe	C
1	1	1.1	CSA	Z245.1	207	—		48/30 [330/205]	Pipe	C
1	1	1.1	CSA	Z245.1	241	—		60/35 [415/240]	Pipe	C
1	1	1.1	CSA	Z245.1	290	—		60/42 [415/290]	Pipe	C
1	1	1.1	CSA	Z245.11	207	—		48/30 [330/205]	Fittings	C-Mn-Si
1	1	1.1	CSA	Z245.11	241	—		60/35 [415/240]	Fittings	C-Mn-Si
1	1	1.1	CSA	Z245.11	290	—		60/42 [415/290]	Fittings	C-Mn-Si
1	1	1.1	CSA	Z245.12	248	—		60/36 [415/250]	Flanges	C-Mn-Si
1	1	1.1	CSA	Z245.12	290	—		60/42 [415/290]	Flanges	C-Mn-Si
1	1	1.1	MSS	SP-75	WPHY-42	—		60/42 [415/290]	Seamless & Welded Fittings	C-Mn
1	1	1.1	MSS	SP-75	WPHY-46	—		63/46 [435/315]	Seamless & Welded Fittings	C-Mn
1	1	1.1	MSS	SP-75	WPHY-52	—		66/52 [455/360]	Seamless & Welded Fittings	C-Mn
1	2	1.1	AAR	M201	B	—		70/38 [485/260]	Castings	C-Mn-Si
1	2	1.2	ABS	ABS	AH36	K11852		71/51 [490/350]	Plate, Bar, & Shapes	C-Mn-Si
1	2	1.3	ABS	ABS	AH40	K11857		74/57 [510/395]	Plate, Bar, & Shapes	C-Mn-Si
1	2	1.2	ABS	ABS	DH36	K11852		71/51 [490/350]	Plate, Bar, & Shapes	C-Mn-Si
1	2	1.3	ABS	ABS	DH40	K11857		74/57 [510/395]	Plate, Bar, & Shapes	C-Mn-Si

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	2	1.2	ABS	ABS	EH36	K11852		71/51 [490/350]	Plate, Bar, & Shapes	C-Mn-Si
1	2	1.3	ABS	ABS	EH40	K11857		74/57 [510/395]	Plate, Bar, & Shapes	C-Mn-Si
1	2	1.2	ABS	ABS	FH36	K11852		71/51 [490/350]	Plate, Bar, & Shapes	C-Mn-Si
1	2	1.3	ABS	ABS	FH40	K11857		74/57 [510/395]	Plate, Bar, & Shapes	C-Mn-Si
1	2	1.2	API	2H	50	—		70/50 [485/345]	Plate	C-Mn
1	2	1.3	API	2W	60	—		75/60 [515/415]	Plate	C-Mn
1	2	1.2	API	2Y	50T	—		70/50 [485/345]	Plate	C-Mn
1	2	1.3	API	2Y	60	—		75/60 [515/415]	Plate	C-Mn
1	2	11.1	API	5L	X56	—		71/56 [490/385]	Seamless & Welded Pipe	C-Mn
1	2	2.1	API	5L	X56M	—		71/56 [490/385]	Welded Pipe	C-Mn
1	2	2.1	API	5L	X56MO	—		71/56 [490/385]	Welded Pipe	C-Mn
1	2	2.1	API	5L	X56MS	—		71/56 [490/385]	Welded Pipe	C-Mn
1	2	1.3	API	5L	X56N	—		71/56 [490/385]	Seamless & Welded Pipe	C-Mn
1	2	3.1	API	5L	X56Q	—		71/56 [490/385]	Seamless & Welded Pipe	C-Mn
1	2	3.1	API	5L	X56QO	—		71/56 [490/385]	Seamless & Welded Pipe	C-Mn
1	2	3.1	API	5L	X56QS	—		71/56 [490/385]	Seamless & Welded Pipe	C-Mn
1	2	11.1	API	5L	X60	—		75/60 [515/415]	Seamless & Welded Pipe	C-Mn
1	2	2.1	API	5L	X60M	—		75/60 [515/415]	Welded Pipe	C-Mn
1	2	2.1	API	5L	X60MO	—		75/60 [515/415]	Welded Pipe	C-Mn
1	2	2.1	API	5L	X60MS	—		75/60 [515/415]	Welded Pipe	C-Mn
1	2	1.3	API	5L	X60N	—		75/60 [515/415]	Seamless & Welded Pipe	C-Mn
1	2	3.1	API	5L	X60Q	—		75/60 [515/415]	Seamless & Welded Pipe	C-Mn
1	2	3.1	API	5L	X60QO	—		75/60 [515/415]	Seamless & Welded Pipe	C-Mn
1	2	3.1	API	5L	X60QS	—		75/60 [515/415]	Seamless & Welded Pipe	C-Mn
1	2	11.1	API	5L	X65	—		78/65 [535/450]	Seamless & Welded Pipe	C-Mn
1	2	2.1	API	5L	X65M	—		78/65 [535/450]	Welded Pipe	C-Mn
1	2	2.1	API	5L	X65MO	—		78/65 [535/450]	Welded Pipe	C-Mn
1	2	2.1	API	5L	X65MS	—		78/65 [535/450]	Welded Pipe	C-Mn
1	2	3.1	API	5L	X65Q	—		78/65 [535/450]	Seamless & Welded Pipe	C-Mn

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	2	3.1	API	5L	X65Q0	—		78/65 [535/450]	Seamless & Welded Pipe	C-Mn
1	2	3.1	API	5L	X65QS	—		78/65 [535/450]	Seamless & Welded Pipe	C-Mn
1	2	1.2	AS ASTM	A945	50	—		70/50 [485/345]	Plate	C-Mn-Si
1	2	1.3	AS ASTM	A945	65	—		78/65 [540/450]	Plate	C-Mn-Si-Ti
1	2	1.2	AS	1548	5-490	—		71/52 [490/360]	Plate	C
1	2	1.2	AS	1548	7-490	—		71/46 [490/320]	Plate	C
1	2	1.2	AS	1548	PT490	—		71/46 [490/320]	Plate	C
1	2	1.2	AS/NZS	3678	300	—		62.5/46 [430/320]	Plate	C-Mn
1	2	1.2	AS/NZS	3678	300L15	—		62.5/46 [430/320]	Plate	C-Mn
1	2	1.2	AS/NZS	3678	350	—		65/52 [450/360]	Plate	C-Mn
1	2	1.2	AS/NZS	3678	350L15	—		65/52 [450/360]	Plate	C-Mn
1	2	1.3	AS/NZS	3678	400	—		70/58 [485/400]	Plate	C-Mn
1	2	1.3	AS/NZS	3678	400L15	—		69.5/58 [480/400]	Plate	C-Mn
1	2	1.3	AS/NZS	3678	450	—		75.5/65 [520/450]	Plate	C-Mn
1	2	1.3	AS/NZS	3678	450L15	—		75.5/65 [520/450]	Plate	C-Mn
1	2	1.2	AS/NZS	3679.1	300	—		64/46 [440/320]	Bar & Sections	C-Mn
1	2	1.2	AS/NZS	3679.1	300L0	—		64/46 [440/320]	Bar & Sections	C-Mn
1	2	1.2	AS/NZS	3679.1	300L15	—		64/46 [440/320]	Bar & Sections	C-Mn
1	2	1.2	AS/NZS	3679.1	350	—		70/52 [485/360]	Bar & Sections	C-Mn
1	2	1.2	AS/NZS	3679.1	350L0	—		69.5/52 [480/360]	Bar & Sections	C-Mn
1	2	1.2	AS/NZS	3679.1	350L15	—		69.5/52 [480/360]	Bar & Sections	C-Mn
1	2	1.3	AS/NZS	3679.1	400	—		75.5/58 [520/400]	Bar & Sections	C-Mn
1	2	1.3	AS/NZS	3679.1	400L0	—		75.5/58 [520/400]	Bar & Sections	C-Mn
1	2	1.3	AS/NZS	3679.1	400L15	—		75.5/58 [520/400]	Bar & Sections	C-Mn
1	2	11.1	ASTM	A27	70-36	J03501		70/36 [485/250]	Castings	C
1	2	1.1	ASTM	A27	70-40	J02501		70/40 [485/275]	Castings	C
1	2	11.1	ASTM/ASME	A/SA-105	—	K03504		70/36 [485/250]	Flanges & Fittings	C
1	2	11.1	ASTM/ASME	A/SA-106	C	K03501		70/40 [485/275]	Seamless Pipe	C-Mn-Si
1	2	1.2	ASTM	A131	AH32	—		64/46 [440/315]	Plate, Shapes, Bar, & Rivets	C-Mn-Si

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	2	1.2	ASTM	A131	AH36	—		71/51 [490/350]	Plate, Shapes, Bar, & Rivets	C-Mn-Si
1	2	1.2	ASTM	A131	DH32	—		64/46 [440/315]	Plate, Shapes, Bar, & Rivets	C-Mn-Si
1	2	1.2	ASTM	A131	DH36	—		71/51 [490/350]	Plate, Shapes, Bar, & Rivets	C-Mn-Si
1	2	1.1	ASTM	A131	E	—		58/34 [400/235]	Plate, Shapes, Bar, & Rivets	C-Mn-Si
1	2	1.2	ASTM	A131	EH32	—		64/46 [440/315]	Plate, Shapes, Bar, & Rivets	C-Mn-Si
1	2	1.2	ASTM	A131	EH36	—		71/51 [490/350]	Plate, Shapes, Bar, & Rivets	C-Mn-Si
1	2	11.1	ASTM/ASME	A/SA-178	D	K02709		70/40 [485/275]	E.R.W. Tube	C-Mn-Si
1	2	11.1	ASTM/ASME	A/SA-181	Cl. 70	K03502		70/36 [485/250]	Pipe Flange & Fittings	C-Si
1	2	11.1	ASTM/ASME	A/SA-210	C	K03501		70/40 [485/275]	Seamless Tube	C-Mn-Si
1	2	1.1	ASTM/ASME	A/SA-216	WCB	J03002		70/36 [485/250]	Castings	C-Si
1	2	1.1	ASTM/ASME	A/SA-216	WCC	J02503		70/40 [485/275]	Castings	C-Mn-Si
1	2	11.1	ASTM/ASME	A/SA-234	WPC	K03501		70/40 [485/275]	Piping Fittings	C-Mn-Si
1	2	1.2	ASTM	A242	1	K11510	>1.5 and ≤4 [>38 and ≤100]	63/42 [435/290]	Plate, Bar, & Shapes	C
1	2	1.2	ASTM	A242	1	K11510	≤0.75 [≤19]	70/50 [485/345]	Plate, Bar, & Shapes	C
1	2	1.2	ASTM	A242	1	K11510	>0.75 and ≤1.5 [>19 and ≤38]	67/46 [460/315]	Plate, Bar, & Shapes	C
1	2	11.1	ASTM/ASME	A/SA-266	2	K03506		70/36 [485/250]	Forgings	C-Si
1	2	11.2	ASTM/ASME	A/SA-266	3	K05001		75/37.5 [515/260]	Forgings	C-Si
1	2	11.1	ASTM/ASME	A/SA-266	4	K03017		70/36 [485/250]	Forgings	C-Mn-Si
1	2	11.1	ASTM/ASME	A/SA-299	A	K02803		75/40 [515/275]	Plate	C-Mn-Si
1	2	11.1	ASTM/ASME	A/SA-350	LF2	K03011		70/36 [485/250]	Forgings	C-Mn-Si
1	2	1.3	ASTM/ASME	A/SA-350	LF6, Cl. 3	K12202		75/60 [515/415]	Forgings	C-Mn-Si-V
1	2	3.3	ASTM/ASME	A/SA-350	LF787, Cl. 2	K20747		65/55 [450/380]	Forgings	1Ni-1Cu-0.75Cr-Mo-Nb
1	2	11.1	ASTM/ASME	A/SA-352	LCC	J02505		70/40 [485/275]	Castings	C-Mn-Si
1	2	11.1	ASTM	A356	1	J03502		70/36 [485/250]	Castings	C-Si
1	2	11.1	ASTM/ASME	A/SA-372	B	K04001		75/45 [515/310]	Forgings	C-Mn-Si
1	2	11.1	ASTM	A381	Y52	—		66/52 [455/360]	Welded Pipe	C
1	2	11.1	ASTM	A381	Y56	—		71/56 [490/385]	Welded Pipe	C

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	2	11.1	ASTM	A381	Y60	—		75/60 [515/415]	Welded Pipe	C
1	2	11.1	ASTM/ASME	A/SA-414	F	K03102		70/42 [485/290]	Sheet	C-Mn
1	2	11.1	ASTM/ASME	A/SA-414	G	K03103		75/45 [515/310]	Sheet	C-Mn
1	2	—	ASTM	A441	—	K12211	>0.75 and <1.5 [≥ 20 and <40]	67/46 [460/315]	Plate & Bar	C-Mn-Si-Cb-V
1	2	—	ASTM	A441	—	K12211	>1.5 and ≤ 4 [≥ 40 and ≤ 100]	63/42 [435/290]	Plate & Bar	C-Mn-Si-Cb-V
1	2	—	ASTM	A441	—	K12211	>4 and ≤ 8 [≥ 100 and ≤ 200]	60/40 [415/275]	Plate & Bar	C-Mn-Si-Cb-V
1	2	—	ASTM	A441	—	K12211	≤ 0.75 [≤ 20]	70/50 [485/345]	Plate & Bar	C-Mn-Si-Cb-V
1	2	—	ASTM	A441	Group 1	—		70/50 [485/345]	Shapes	C-Mn-Si-Cb-V
1	2	—	ASTM	A441	Group 2	—		70/50 [485/345]	Shapes	C-Mn-Si-Cb-V
1	2	—	ASTM	A441	Group 3	—		67/46 [460/315]	Shapes	C-Mn-Si-Cb-V
1	2	—	ASTM	A441	Group 4	—		63/42 [435/290]	Shapes	C-Mn-Si-Cb-V
1	2	—	ASTM	A441	Group 5	—		63/42 [435/290]	Shapes	C-Mn-Si-Cb-V
1	2	11.2	ASTM/ASME	A/SA-455	—	K03300	>0.375 and <0.580 [≥ 10 and <15]	73/37 [505/255]	Plate	C-Mn-Si
1	2	11.2	ASTM/ASME	A/SA-455	—	K03300	>0.580 and <0.750 [≥ 15 and <19]	70/35 [485/240]	Plate	C-Mn-Si
1	2	11.2	ASTM/ASME	A/SA-455	—	K03300	≤ 0.375 [≤ 10]	75/38 [515/260]	Plate	C-Mn-Si
1	2	1.1	ASTM/ASME	A/SA-487	16, Cl. A	J31200		70/40 [485/275]	Castings	Low C-Mn-Ni
1	2	11.1	ASTM/ASME	A/SA-508	1	K13502		70/36 [485/250]	Forgings	C
1	2	11.1	ASTM/ASME	A/SA-508	1A	K13502		70/36 [485/250]	Forgings	C
1	2	11.1	ASTM	A512	1025	G10250		55/35 [380/240]	Tube	C
1	2	11.1	ASTM	A512	1030	G10300		65/40 [450/275]	Tube	C
1	2	1.1	ASTM	A513	1020 CW	G10200		— [—]	Tube	C
1	2	11.1	ASTM/ASME	A/SA-513	1025	G10250		56/40 [385/275]	Tube	C
1	2	1.2	ASTM	A513	1025 CW	G10250		— [—]	Tube	C
1	2	11.1	ASTM/ASME	A/SA-513	1030	G10300		62/45 [425/310]	Tube	C
1	2	11.1	ASTM/ASME	A/SA-515	70	K03101		70/38 [485/260]	Plate	C-Si

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	2	11.1	ASTM/ASME	A/SA-516	70	K02700		70/38 [485/260]	Plate	C-Mn-Si
1	2	1.1	ASTM	A519	1018 CW	G10180		-/- [-/-]	Tube	C
1	2	1.1	ASTM	A519	1020 CW	G10200		-60 [-/415]	Tube	C
1	2	1.1	ASTM	A519	1022 CW	G10220		-/- [-/-]	Tube	C
1	2	11.1	ASTM	A519	1025	G10250		53/30 [365/205]	Tube	C
1	2	1.2	ASTM	A519	1025 CW	G10250		-65 [-/450]	Tube	C
1	2	11.1	ASTM	A519	1026 CW	G10260		-/- [-/-]	Tube	C
1	2	—	ASTM	A519	1030	G10300		75/55 [515/380]	Tube	C
1	2	—	ASTM	A521	CE	—		75/37 [515/255]	Die Forging	C
1	2	11.1	ASTM	A529	50	—		70/50 [485/345]	Plate, Bar, & Shapes	C-Mn
1	2	11.1	ASTM	A529	55	—		70/55 [485/380]	Plate, Bar, & Shapes	C-Mn
1	2	1.2	ASTM/ASME	A/SA-537	Cl. 1	K12437	≤2.5 [≤64]	70/50 [485/345]	Plate	C-Mn-Si
1	2	1.2	ASTM/ASME	A/SA-537	Cl. 1	K12437	>2.5 and ≤4 [>64 and ≤102]	65/45 [450/310]	Plate	C-Mn-Si
1	2	11.1	ASTM/ASME	A/SA-541	1	K03506		70/36 [485/250]	Forgings	C-Si
1	2	11.1	ASTM/ASME	A/SA-541	1A	K03020		70/36 [485/250]	Forgings	C-Mn-Si
1	2	11.1	ASTM/ASME	A/SA-556	C2	K03006		70/40 [485/275]	Seamless Tube	C-Mn-Si
1	2	11.1	ASTM/ASME	A/SA-557	C2	K03505		70/40 [485/275]	E.R.W. Tube	C-Mn
1	2	1.3	ASTM	A572	55	—		70/55 [485/380]	Plate, Sheet, Bar, & Shapes	C-Mn-Si-Cb-V
1	2	11.1	ASTM/ASME	A/SA-572	60	—		75/60 [515/415]	Plate & Shapes	C-Mn-Si
1	2	11.1	ASTM	A573	70	—		70/42 [485/290]	Plate	C
1	2	11.1	ASTM	A595	A	K02004		65/55 [450/380]	Welded Tube	Low C
1	2	11.1	ASTM	A595	B	K02005		70/60 [485/415]	Welded Tube	Low C
1	2	1.4	ASTM	A606	2, CR, AR	—		65/45 [450/310]	Sheet & Strip	C-Mn
1	2	1.4	ASTM	A606	2, HR, A	—		65/45 [450/310]	Sheet & Strip	C-Mn
1	2	1.4	ASTM	A606	2, HR, AR	—		70/50 [485/345]	Sheet & Strip	C-Mn
1	2	1.4	ASTM	A606	2, HR, N	—		65/45 [450/310]	Sheet & Strip	C-Mn
1	2	1.4	ASTM	A606	4, CR, AR	—		65/45 [450/310]	Sheet & Strip	C-Mn
1	2	1.4	ASTM	A606	4, HR, A	—		65/45 [450/310]	Sheet & Strip	C-Mn

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	2	1.4	ASTM	A606	4, HR, AR	—		70/50 [485/345]	Sheet & Strip	C-Mn
1	2	1.4	ASTM	A606	4, HR, N	—		65/45 [450/310]	Sheet & Strip	C-Mn
1	2	—	ASTM	A607	55	—		70/55 [485/380]	Sheet & Strip	C-Mn-Cb-V
1	2	1.2	ASTM	A618	Ia	—	≤0.75 [≤19]	70/50 [485/345]	Tube	Mn-Cu-V
1	2	1.2	ASTM	A618	Ia	—	>0.75 and <1.5 [>19 and <38]	67/46 [460/315]	Tube	Mn-Cu-V
1	2	1.2	ASTM	A618	Ib	—		65/50 [450/345]	Seamless & Welded Tube	C-Mn
1	2	1.2	ASTM	A618	Ib	K02601	>0.75 and <1.5 [>19 and <38]	67/46 [460/315]	Tube	Mn-Cu-V
1	2	1.2	ASTM	A618	Ib	K02601	≤0.75 [≤19]	70/50 [485/345]	Tube	Mn-Cu-V
1	2	1.2	ASTM	A618	II	K12609	>0.75 and <1.5 [>19 and <38]	67/46 [460/315]	Tube	Mn-Cu-V
1	2	1.2	ASTM	A618	II	K12609	≤0.75 [≤19]	70/50 [485/345]	Tube	Mn-Cu-V
1	2	1.1	ASTM	A633	C	K12000	≤2.5 [≤64]	70/50 [485/345]	Plate & Shapes	Mn-Cb
1	2	1.1	ASTM	A633	D	K12037	≤2.5 [≤64]	70/50 [485/345]	Plate & Shapes	C-Mn-Si
1	2	1.3	ASTM/ASME	A/SA-656	70	K11804	≤1 [≤25]	80/70 [550/485]	Plate	C-Mn-V
1	2	1.3	ASTM/ASME	A/SA-656	T3, 60	—		70/60 [485/415]	Plate	C-Mn-Si-V-Cb
1	2	1.3	ASTM/ASME	A/SA-656	T7, 60	—		70/60 [485/415]	Plate	C-Mn-Si-V-Cb
1	2	1.1	ASTM/ASME	A/SA-660	WCB	J03003		70/36 [485/250]	Centrifugal Cast Pipe	C-Si
1	2	11.1	ASTM/ASME	A/SA-660	WCC	J02505		70/40 [485/275]	Centrifugal Cast Pipe	C-Mn-Si
1	2	1.1	ASTM/ASME	A/SA-662	C	K02007		70/43 [485/295]	Plate	C-Mn-Si
1	2	—	ASTM	A663	70	—		70/39 [485/270]	Bars & Shapes	C
1	2	—	ASTM	A663	75	—		75/41 [515/285]	Bars & Shapes	C
1	2	11.1	ASTM	A668	C	G10250		66/33 [455/230]	Forgings	C
1	2	11.1	ASTM	A668	D	G10300		75/37 [515/255]	Forgings	C
1	2	11.1	ASTM/ASME	A/SA-671	CB70	K03101		70/38 [485/260]	Fusion Welded Pipe	C-Si
1	2	11.1	ASTM/ASME	A/SA-671	CC70	K02700		70/38 [485/260]	Fusion Welded Pipe	C-Mn-Si
1	2	1.2	ASTM/ASME	A/SA-671	CD70	K12437		70/50 [485/345]	Fusion Welded Pipe	C-Mn-Si
1	2	11.1	ASTM/ASME	A/SA-671	CK75	K02803		75/40 [515/275]	Fusion Welded Pipe	C-Mn-Si

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	2	11.1	ASTM/ASME	A/SA-672	B70	K03101		70/38 [485/260]	Fusion Welded Pipe	C-Si
1	2	11.1	ASTM/ASME	A/SA-672	C70	K02700		70/38 [485/260]	Fusion Welded Pipe	C-Mn-Si
1	2	1.2	ASTM/ASME	A/SA-672	D70	K12437		70/45 [485/310]	Fusion Welded Pipe	C-Mn-Si
1	2	11.1	ASTM/ASME	A/SA-672	N75	K02803		75/40 [515/275]	Fusion Welded Pipe	C-Mn-Si
1	2	11.1	ASTM/ASME	A/SA-675	70	—		70/35 [485/240]	Bar	C
1	2	1.2	ASTM	A678	A	K01600	≤1.5 [≤40]	70/50 [485/345]	Plate	C-Mn-Si
1	2	1.4	ASTM	A690	—	K12249	>4 [≥100]	70/50 [485/345]	Marine Piling—Plate & Bar	0.75Mn-0.6Ni-0.12P
1	2	11.1	ASTM/ASME	A/SA-691	CMS-75	K02803		75/40 [515/275]	Fusion Welded Pipe	C-Mn-Si
1	2	1.2	ASTM/ASME	A/SA-691	CMSH-70	K12437	>2.5 and <4 [≥64 and <102]	65/45 [450/310]	Fusion Welded Pipe	C-Mn-Si
1	2	1.2	ASTM/ASME	A/SA-691	CMSH-70	K12437	≤2.5 [≤64]	70/50 [485/345]	Fusion Welded Pipe	C-Mn-Si
1	2	11.1	ASTM	A694	F56	K03014		68/56 [470/385]	Forgings	C-Mn
1	2	11.1	ASTM	A694	F60	K03014		75/60 [515/415]	Forgings	C-Mn
1	2	11.1	ASTM	A694	F65	K03014		77/65 [530/450]	Forgings	C-Mn
1	2	11.1	ASTM/ASME	A/SA-695	B, 40	K03504		70/40 [485/275]	Bar	C
1	2	11.1	ASTM/ASME	A/SA-696	C	K03200		70/40 [485/275]	Bar	C-Mn-Si
1	2	11.1	ASTM	A707	L2, Cl.3	K03301		75/60 [515/415]	Forgings	C-Mn
1	2	1.3	ASTM	A707	L3, Cl.3	K12510		75/60 [515/415]	Forgings	C-Mn-V-N
1	2	—	ASTM	A707	L4, Cl.3	K12089		75/60 [515/415]	Forgings	1.8Ni-0.6Mn-0.3Mo
1	2	—	ASTM	A707	L5, Cl.3	K20934		75/60 [515/415]	Forgings	1.2Cu-1Ni-0.7Cr-0.5Mn
1	2	1.4	ASTM	A709	50W, A	—		70/50 [485/345]	Plate, Bar, & Shapes	C-Mn
1	2	1.4	ASTM	A709	50W, B	—		70/50 [485/345]	Plate, Bar, & Shapes	C-Mn
1	2	1.4	ASTM	A709	HPS 50W	—		70/50 [485/345]	Plate, Bar, & Shapes	C-Mn
1	2	11.1	ASTM/ASME	A/SA-737	B	K12001		70/50 [485/345]	Plate	C-Mn-Si-Cb
1	2	11.1	ASTM/ASME	A/SA-738	A	K12447		75/45 [515/310]	Plate	C-Mn-Si
1	2	11.1	ASTM/ASME	A/SA-765	II	K03047		70/36 [485/250]	Forgings	C-Mn-Si
1	2	11.1	ASTM	A830	1025	G10250		43/25 [295/170]	Plate	C
1	2	1.2	ASTM/ASME	A/SA-841	A, Cl. 1	—	>2.5 [≥65]	65/45 [450/310]	Plate	C-Mn-Si
1	2	1.2	ASTM/ASME	A/SA-841	A, Cl. 1	—	≤2.5 [≤65]	70/50 [485/345]	Plate	C-Mn-Si

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	2	1.2	ASTM	A913	50	—	65/50 [450/345]	Shapes	C-Mn-Ni-Cr-Cb-V	
1	2	1.3	ASTM	A935	55 Cl. 1	—	70/55 [485/380]	Sheet & Strip	C-Mn-Cb-V	
1	2	11.1	ASTM	A935	60 Cl. 1	—	75/60 [515/415]	Sheet & Strip	C-Mn-Cb-V	
1	2	1.3	ASTM	A935	60 Cl. 2	—	70/60 [485/415]	Sheet & Strip	C-Mn-Cb-V	
1	2	1.3	ASTM	A935	65 Cl. 2	—	75/65 [515/450]	Sheet & Strip	C-Mn-Cb-V	
1	2	1.2	ASTM	A984	50	—	70/50 [485/345]	Pipe	C	
1	2	1.3	ASTM	A984	60	—	75/60 [515/415]	Pipe	C	
1	2	1.3	ASTM	A1008	HSLAS 55 Cl. 1	—	70/55 [485/380]	Sheet	C	
1	2	11.1	ASTM	A1008	HSLAS 60 Cl. 1	—	75/60 [515/415]	Sheet	C	
1	2	1.3	ASTM	A1008	HSLAS 60 Cl. 2	—	70/60 [485/415]	Sheet	C	
1	2	1.3	ASTM	A1008	HSLAS 65 Cl. 2	—	75/65 [515/450]	Sheet	C	
1	2	1.3	ASTM	A1008	HSLAS-F 60	—	70/60 [485/415]	Sheet	C	
1	2	1.3	ASTM	A1011	HSLAS 55 Cl. 1	—	70/55 [485/380]	Sheet & Strip	C	
1	2	11.1	ASTM	A1011	HSLAS 60 Cl. 1	—	75/60 [515/415]	Sheet & Strip	C	
1	2	1.3	ASTM	A1011	HSLAS 60 Cl. 2	—	70/60 [485/415]	Sheet & Strip	C	
1	2	1.3	ASTM	A1011	HSLAS 65 Cl. 2	—	75/65 [515/450]	Sheet & Strip	C	
1	2	1.3	ASTM	A1011	HSLAS-F 60	—	70/60 [485/415]	Sheet & Strip	C	
1	2	1.3	ASTM	A1011	SS 55	—	70/55 [485/380]	Sheet & Strip	C	
1	2	1.3	ASTM	A1011	SS 60	—	75/60 [515/415]	Sheet & Strip	C	
1	2	1.3	ASTM	A1018	HSLAS 55 Cl. 1	—	70/55 [485/380]	Sheet & Strip	C	
1	2	11.1	ASTM	A1018	HSLAS 60 Cl. 1	—	70/60 [485/415]	Sheet & Strip	C	
1	2	1.3	ASTM	A1018	HSLAS 60 Cl. 2	—	70/60 [485/415]	Sheet & Strip	C	
1	2	11.1	ASTM	A1018	HSLAS 65 Cl. 1	—	80/65 [550/450]	Sheet & Strip	C	
1	2	1.3	ASTM	A1018	HSLAS 65 Cl. 2	—	75/65 [515/450]	Sheet & Strip	C	
1	2	1.4	CSA	G40.21	350A	—	70/50 [485/345]	HSLA Plate, Bar, & Shapes	C-Mn-Si-Cb-V	
1	2	1.4	CSA	G40.21	350AT	—	70/50 [485/345]	HSLA Plate, Bar, & Shapes	C-Mn-Si-Cb-V	
1	2	1.4	CSA	G40.21	350R	—	70/50 [485/345]	HSLA Plate, Bar, & Shapes	C-Mn-P	
1	2	1.2	CSA	G40.21	350WT	—	70/50 [485/345]	Plate, Bar, & Shapes	C-Mn-Si-Cb-V	
1	2	1.3	CSA	G40.21	380W	—	70/55 [485/380]	Plate, Bar, & Shapes	C-Mn	

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	2	1.3	CSA	G40.21	380WT	—	70/55 [485/380]	Plate, Bar, & Shapes	C-Mn-Si-Cb-V	
1	2	1.4	CSA	G40.21	400A	—	75/60 [515/415]	HSLA Plate, Bar, & Shapes	C-Mn-Si-Cb-V	
1	2	1.4	CSA	G40.21	400AT	—	75/60 [515/415]	HSLA Plate, Bar, & Shapes	C-Mn-Si-Cb-V	
1	2	1.3	CSA	G40.21	400W	—	75/60 [515/415]	HSLA Plate, Bar, & Shapes	C-Mn	
1	2	1.3	CSA	G40.21	400WT	—	75/60 [515/415]	HSLA Plate, Bar, & Shapes	C-Mn-Si-Cb-V	
1	2	11.1	CSA	Z245.1	317	—	63/46 [435/315]	Pipe	C-Mn	
1	2	11.1	CSA	Z245.1	359	—	66/52 [455/360]	Pipe	C-Mn	
1	2	11.1	CSA	Z245.1	386	—	71/56 [490/385]	Pipe	C-Mn	
1	2	11.1	CSA	Z245.11	317	—	63/46 [435/315]	Fittings	C-Mn-Si	
1	2	11.1	CSA	Z245.11	359	—	66/52 [455/360]	Fittings	C-Mn-Si	
1	2	11.1	CSA	Z245.11	386	—	71/56 [490/385]	Fittings	C-Mn-Si	
1	2	11.1	CSA	Z245.12	317	—	63/46 [435/315]	Flanges	C-Mn-Si	
1	2	11.1	CSA	Z245.12	359	—	66/52 [455/360]	Flanges	C-Mn-Si	
1	2	11.1	CSA	Z245.12	386	—	71/56 [490/385]	Flanges	C-Mn-Si	
1	2	11.1	MSS	SP-75	WPHY-56	—	71/56 [490/385]	Seamless & Welded Fittings	C-Mn	
1	2	11.1	MSS	SP-75	WPHY-60	—	75/60 [515/415]	Seamless & Welded Fittings	C-Mn	
1	2	11.1	MSS	SP-75	WPHY-65	—	77/65 [530/450]	Seamless & Welded Fittings	C-Mn	
1	3	11.1	AAR	M201	B+	—	80/50 [550/345]	Castings	C-Mn-Si	
1	3	11.1	API	5L	X70	—	83/70 [570/485]	Seamless & Welded Pipe	C-Mn	
1	3	2.2	API	5L	X70M	—	83/70 [570/485]	Welded Pipe	C-Mn	
1	3	2.2	API	5L	X70MO	—	83/70 [570/485]	Welded Pipe	C-Mn	
1	3	2.2	API	5L	X70MS	—	83/70 [570/485]	Welded Pipe	C-Mn	
1	3	3.1	API	5L	X70Q	—	83/70 [570/485]	Seamless & Welded Pipe	C-Mn	
1	3	3.1	API	5L	X70QO	—	83/70 [570/485]	Seamless & Welded Pipe	C-Mn	
1	3	3.1	API	5L	X70QS	—	83/70 [570/485]	Seamless & Welded Pipe	C-Mn	
1	3	2.2	AS/NZS	1594	XF500	—	83/69.5 [570/480]	Plate, Sheet, Strip	C-Mn	
1	3	11.1	ASTM/ASME	A/SA-299	B	K02803	80/45 [550/310]	Plate	C-Mn-Si	
1	3	11.1	ASTM/ASME	A/SA-333	10	—	80/65 [550/450]	Seamless & Welded Pipe	C-Mn-Si	
1	3	4.1	ASTM/ASME	A/SA-350	LF6, Cl.2	K12202	75/60 [515/415]	Forgings	C-Mn-Si-V	

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	3	3.3	ASTM/ASME	A/SA-350	LF787, Cl.3	K20747		75/65 [515/450]	Forgings	INi-1Cu-0.75Cr-Mo-Nb
1	3	11.1	ASTM	A381	Y65	—		77/65 [530/450]	Welded Pipe	C
1	3	11.1	ASTM	A513	1026 CW	G10260		— [—]	Tube	C
1	3	1.2	ASTM/ASME	A/SA-537	Cl. 2	K12437	>2.5 and ≤4 [>64 and ≤102]	75/55 [515/380]	Plate	C-Mn-Si
1	3	1.2	ASTM/ASME	A/SA-537	Cl. 2	K12437	≤2.5 [≤64]	80/60 [550/415]	Plate	C-Mn-Si
1	3	1.2	ASTM/ASME	A/SA-537	Cl. 2	K12437	>4 and ≤6 [>102 and ≤152]	70/46 [485/315]	Plate	C-Mn-Si
1	3	1.2	ASTM/ASME	A/SA-537	Cl. 3	K12437	>4 [>102]	70/40 [485/275]	Plate	C-Mn-Si
1	3	1.2	ASTM/ASME	A/SA-537	Cl. 3	K12437	>2.5 and ≤4 [>64 and ≤102]	75/50 [515/345]	Plate	C-Mn-Si
1	3	1.2	ASTM/ASME	A/SA-537	Cl. 3	K12437	≤2.5 [≤64]	80/55 [550/380]	Plate	C-Mn-Si
1	3	11.1	ASTM	A572	65	—		80/65 [550/450]	Plate, Sheet, Bar, & Shapes	C-Mn-Si-Cb-V
1	3	—	ASTM	A607	60	—		75/60 [515/415]	Sheet & Strip	C-Mn-Cb-V
1	3	—	ASTM	A607	65	—		80/65 [550/450]	Sheet & Strip	C-Mn-Cb-V
1	3	—	ASTM	A607	70	—		85/70 [585/485]	Sheet & Strip	C-Mn-Cb-V
1	3	—	ASTM	A611	E	G10170		82/80 [565/550]	Sheet & Strip	C
1	3	4.1	ASTM	A633	E	K12202		80/55 [550/380]	Plate & Shapes	C-Mn-Si-V
1	3	1.3	ASTM/ASME	A/SA-656	80	K11804	≤0.75 [≤20]	90/80 [620/550]	Plate	C-Mn-V
1	3	2.2	ASTM/ASME	A/SA-656	T3, 70	—		80/70 [550/485]	Plate	C-Mn-Si-V-Cb
1	3	2.2	ASTM/ASME	A/SA-656	T7, 70	—		80/70 [550/485]	Plate	C-Mn-Si-V-Cb
1	3	—	ASTM	A663	80	—		80/44 [550/305]	Bars & Shapes	C
1	3	11.1	ASTM	A668	F	—	≤4 [≤100]	90/55 [620/380]	Forgings	C
1	3	11.1	ASTM	A668	F	—	>4 and ≤10 [>100 and ≤250]	85/50 [585/345]	Forgings	C
1	3	11.1	ASTM	A668	F	—	>10 and ≤20 [>250 and ≤500]	82/48 [565/330]	Forgings	C
1	3	1.2	ASTM/ASME	A/SA-671	CD80	K12437		80/60 [550/415]	Fusion Welded Pipe	C-Mn-Si
1	3	1.2	ASTM/ASME	A/SA-672	D80	K12437		80/46 [550/315]	Fusion Welded Pipe	C-Mn-Si
1	3	—	ASTM/ASME	A/SA-675	80	—		80/40 [550/275]	Bar	C

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	3	ASTM	A678	B	K02002	≤2.5 [≤65]	80/60 [550/415]	Plate	C-Mn-Si
1	3	ASTM	A678	C	K02204	>1.5 and ≤2 [≥40 and ≤50]	85/65 [585/450]	Plate	C-Mn-Si
1	3	ASTM/ASME	A/SA-691	CMSH-80	K12437	≤2.5 [≤64]	80/60 [550/415]	Fusion Welded Pipe	C-Mn-Si
1	3	ASTM/ASME	A/SA-691	CMSH-80	K12437	>2.5 and <4 [≥64 and <102]	75/55 [515/380]	Fusion Welded Pipe	C-Mn-Si
1	3	ASTM	A694	F70	K03014		82/70 [565/485]	Forgings	C-Mn
1	3	ASTM/ASME	A/SA-737	C	K12202		80/60 [550/415]	Plate	C-Mn-Si-V
1	3	ASTM/ASME	A/SA-738	B	K12007		85/60 [585/415]	Plate	C-Mn-Si-Cb
1	3	ASTM/ASME	A/SA-738	C	K02008	>2.5 and ≤4 [≥64 and ≤102]	75/55 [515/380]	Plate	C-Mn-Si
1	3	ASTM/ASME	A/SA-738	C	K02008	≤2.5 [≤64]	80/60 [550/415]	Plate	C-Mn-Si
1	3	ASTM/ASME	A/SA-738	C	K02008	>4 and ≤6 [≥102 and ≤152]	70/46 [485/315]	Plate	C-Mn-Si
1	3	ASTM/ASME	A/SA-765	IV	K02009		80/50 [550/345]	Forgings	C-Mn-Si
1	3	ASTM/ASME	A/SA-841	B, Cl. 2	—	≤2.5 [≤65]	80/60 [550/415]	Plate	C-Mn-Si
1	3	ASTM/ASME	A/SA-841	B, Cl. 2	—	>2.5 [≥65]	75/55 [515/380]	Plate	C-Mn-Si
1	3	ASTM	A913	60	—		75/60 [515/415]	Shapes	C-Mn-Ni-Cr-Cb-V
1	3	ASTM	A913	65	—		80/65 [550/450]	Shapes	C-Mn-Ni-Cr-Cb-V
1	3	ASTM	A913	70	—		80/70 [550/485]	Shapes	C-Mn-Ni-Cr-Cb-V
1	3	ASTM	A935	65 Cl. 1	—		80/65 [550/450]	Sheet & Strip	C-Mn-Cb-V
1	3	ASTM	A935	70 Cl. 1	—		85/70 [585/485]	Sheet & Strip	C-Mn-Cb-V
1	3	ASTM	A935	70 Cl. 2	—		80/70 [550/485]	Sheet & Strip	C-Mn-Cb-V
1	3	ASTM	A984	70	—		80/70 [550/485]	Pipe	C
1	3	ASTM	A1008	HSLAS 65 Cl. 1	—		80/65 [550/450]	Sheet	C
1	3	ASTM	A1008	HSLAS 70 Cl. 1	—		85/70 [585/485]	Sheet	C
1	3	ASTM	A1008	HSLAS 70 Cl. 2	—		80/70 [550/485]	Sheet	C
1	3	ASTM	A1008	HSLAS-F 70	—		80/70 [550/485]	Sheet	C
1	3	ASTM	A1008	SS 80	—		82/80 [565/550]	Sheet	C

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	3	11.1	ASTM	A1011	HSLAS 65 Cl. 1	—		80/65 [550/450]	Sheet & Strip	C
1	3	11.1	ASTM	A1011	HSLAS 70 Cl. 1	—		85/70 [585/485]	Sheet & Strip	C
1	3	1.3	ASTM	A1011	HSLAS 70 Cl. 2	—		80/70 [550/485]	Sheet & Strip	C
1	3	1.3	ASTM	A1011	HSLAS-F 70	—		80/70 [550/485]	Sheet & Strip	C
1	3	1.3	ASTM	A1011	SS 70	—		85/70 [585/485]	Sheet & Strip	C
1	3	11.1	ASTM	A1018	HSLAS 70 Cl. 1	—		80/70 [550/485]	Sheet & Strip	C
1	3	1.3	ASTM	A1018	HSLAS 70 Cl. 2	—		80/70 [550/485]	Sheet & Strip	C
1	3	1.3	ASTM	A1018	HSLAS-F 60	—		70/60 [485/415]	Sheet & Strip	C
1	3	1.3	ASTM	A1018	HSLAS-F 70	—		80/70 [550/485]	Sheet & Strip	C
1	3	1.4	CSA	G40.21	480A	—		85/70 [585/485]	HSLA Plate, Bar, & Shapes	C-Mn-Si-Cb-V
1	3	1.4	CSA	G40.21	480AT	—		85/70 [585/485]	HSLA Plate, Bar, & Shapes	C-Mn-Si-Cb-V
1	3	11.1	CSA	G40.21	480W	—		85/70 [585/485]	HSLA Plate, Bar, & Shapes	C-Mn
1	3	11.1	CSA	G40.21	480WT	—		85/70 [585/485]	HSLA Plate, Bar, & Shapes	C-Mn-Si-Cb-V
1	3	11.1	CSA	Z245.1	414	—		75/60 [515/415]	Pipe	C-Mn
1	3	11.1	CSA	Z245.1	448	—		77/65 [530/450]	Pipe	C-Mn
1	3	11.1	CSA	Z245.1	483	—		82/70 [565/485]	Pipe	C-Mn
1	3	11.1	CSA	Z245.11	414	—		75/60 [515/415]	Fittings	C-Mn-Si
1	3	11.1	CSA	Z245.11	448	—		77/65 [530/450]	Fittings	C-Mn-Si
1	3	11.1	CSA	Z245.11	483	—		82/70 [565/485]	Fittings	C-Mn-Si
1	3	11.1	CSA	Z245.12	414	—		75/60 [515/415]	Flanges	C-Mn-Si
1	3	11.1	CSA	Z245.12	448	—		77/65 [530/450]	Flanges	C-Mn-Si
1	3	11.1	CSA	Z245.12	483	—		82/70 [565/485]	Flanges	C-Mn-Si
1	3	11.1	MSS	SP-75	WPHY-70	—		82/70 [565/485]	Seamless & Welded Fittings	C-Mn
1	4	11.1	AAR	M201	C	—		90/60 [620/415]	Castings	C-Mn-Si
1	4	2.2	API	5L	X80M	—		91/80 [625/550]	Welded Pipe	C-Mn
1	4	2.2	API	5L	X80MO	—		91/80 [625/550]	Welded Pipe	C-Mn
1	4	3.1	API	5L	X80Q	—		91/80 [625/550]	Seamless & Welded Pipe	C-Mn
1	4	3.1	API	5L	X80QO	—		91/80 [625/550]	Seamless & Welded Pipe	C-Mn
1	4	2.2	ASTM/ASME	A/SA-656	T3, 80	—		90/80 [620/550]	Plate	C-Mn-Si-V-Cb

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
1	4	2.2	ASTM/ASME	A/SA-656	T7, 80	—	—	90/80 [620/550]	Plate	C-Mn-Si-V-Cb
1	4	—	ASTM/ASME	A/SA-675	90	—	—	90/55 [620/380]	Bar	C
1	4	1.3	ASTM	A678	C	K02204	≤0.75 [≤20]	95/75 [655/515]	Plate	C-Mn-Si
1	4	1.3	ASTM	A678	C	K02204	>0.75 and ≤1.5 [≥20 and ≤40]	90/70 [620/485]	Plate	C-Mn-Si
1	4	1.3	ASTM	A678	D	K12202	≤3 [≤75]	90/75 [620/515]	Plate	C-Mn-Si-V-N
1	4	—	ASTM	A707	L5, Cl. 4	K20934	—	90/75 [620/515]	Forgings	1.2Cu-1Ni-0.7Cr-0.5Mn
1	4	3.1	ASTM/ASME	A/SA-724	A	K11831	—	90/70 [620/485]	Plate	C-Mn-Si
1	4	3.1	ASTM/ASME	A/SA-724	B	K12031	—	95/75 [655/515]	Plate	C-Mn-Si
1	4	1.1	ASTM/ASME	A/SA-724	C	K12037	—	90/70 [620/485]	Plate	C-Mn-Si
1	4	—	ASTM	A984	80	—	—	90/80 [620/550]	Pipe	C
1	4	1.3	ASTM	A1008	HSLAS-F 80	—	—	90/80 [620/550]	Sheet	C
1	4	1.3	ASTM	A1011	HSLAS-F 80	—	—	90/80 [620/550]	Sheet & Strip	C
1	4	1.3	ASTM	A1011	SS 80	—	—	95/80 [655/550]	Sheet & Strip	C
1	4	1.3	ASTM	A1018	HSLAS-F 80	—	—	90/80 [620/550]	Sheet & Strip	C
1	4	1.4	CSA	G40.21	550A	—	—	90/80 [620/550]	Plate, Bar, & Shapes	C-Mn-Si
1	4	1.4	CSA	G40.21	550AT	—	—	90/80 [620/550]	Plate, Bar, & Shapes	C-Mn-Si
1	4	1.3	CSA	G40.21	550W	—	—	90/80 [620/550]	Plate, Bar, & Shapes	C-Mn
1	4	1.3	CSA	G40.21	550WT	—	—	90/80 [620/550]	Plate, Bar, & Shapes	C-Mn-Si
1	4	11.1	CSA	Z245.1	550	—	—	90/80 [620/550]	Pipe	C-Mn
1	4	11.1	CSA	Z245.11	550	—	—	90/80 [620/550]	Fittings	C-Mn-Si
10A	1	4.1	ASTM/ASME	A/SA-225	C	K12524	—	105/70 [725/485]	Plate	Mn-0.5Ni-V
10A	1	2.1	ASTM/ASME	A/SA-225	D	K12004	>3 [>76]	75/55 [515/380]	Plate	Mn-0.5Ni-V
10A	1	2.1	ASTM/ASME	A/SA-225	D	K12004	≤3 [≤76]	80/60 [550/415]	Plate	Mn-0.5Ni-V
10A	1	2.1	ASTM/ASME	A/SA-487	1, Cl. A	J13002	—	85/55 [585/380]	Castings	Mn-V
10A	1	2.1	ASTM/ASME	A/SA-487	1, Cl. B	J13002	—	90/65 [620/450]	Castings	Mn-V
10B	1	4.1	ASTM/ASME	A/SA-213	TT17	K12047	—	60/30 [415/205]	Seamless Tube	1Cr-V
10C	1	11.1	AAR	TC128	B	—	—	81/50 [560/345]	Plate	C-Mn-Si
10C	1	1.3	ASTM/ASME	A/SA-612	—	K02900	≤0.5 [≤13]	83/50 [570/345]	Plate	C-Mn-Si

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
10C	1	1.3	ASTM/ASME	A/SA-612	—	K02900	>0.5 and <1 [>13 and <25]	81/50 [560/345]	Plate	C-Mn-Si
10H	1	10.1	ASTM/ASME	A/SA-182	—	S32202		94/65 [650/450]	Forgings	22Cr-2Ni-Mo-N
10H	1	10.2	ASTM/ASME	A/SA-182	F50	S31200		100/65 [690/450]	Forgings	25Cr-6Ni-Mo-N
10H	1	10.1	ASTM/ASME	A/SA-182	F51	S31803		90/65 [620/450]	Forgings	22Cr-5Ni-3Mo-N
10H	1	10.2	ASTM/ASME	A/SA-182	F53	S32750		116/80 [800/550]	Forgings	25Cr-7Ni-4Mo-N
10H	1	10.2	ASTM/ASME	A/SA-182	F54	S39274		116/80 [800/550]	Forgings	25Cr-7Ni-3Mo-2W-Cu-N
10H	1	10.1	ASTM/ASME	A/SA-182	F55	S32760		109/80 [750/550]	Forgings	25Cr-8Ni-3Mo-W-Cu-N
10H	1	10.1	ASTM/ASME	A/SA-182	F60	S32205		95/70 [655/485]	Forgings	22Cr-5Ni-3Mo-N
10H	1	10.2	ASTM/ASME	A/SA-182	F61	S32550		109/80 [750/550]	Forgings	25Cr-5Ni-3Mo-2Cu
10H	1	10.1	ASTM/ASME	A/SA-240	—	S32003		90/65 [620/450]	Plate, Sheet, & Strip	21Cr-3.5Ni-Mo-N
10H	1	10.1	ASTM/ASME	A/SA-240	—	S32101	>0.25 [>6]	95/65 [655/450]	Plate, Sheet, & Strip	21Cr-5Mn-1.5Ni-Cu-N
10H	1	10.1	ASTM/ASME	A/SA-240	—	S32101	≤0.25 [≤6]	101/77 [700/530]	Plate, Sheet, & Strip	21Cr-5Mn-1.5Ni-Cu-N
10H	1	10.1	ASTM/ASME	A/SA-240	—	S32202		94/65 [650/450]	Plate, Sheet, & Strip	22Cr-2Ni-Mo-N
10H	1	10.1	ASTM/ASME	A/SA-240	2205	S32205		95/65 [655/450]	Plate, Sheet, & Strip	22Cr-5Ni-3Mo-N
10H	1	10.2	ASTM/ASME	A/SA-240	329	S32900		90/70 [620/485]	Plate, Sheet, & Strip	26Cr-4Ni-Mo
10H	1	10.2	ASTM/ASME	A/SA-240	S31200	S31200		100/65 [690/450]	Plate, Sheet, & Strip	25Cr-6Ni-Mo-N
10H	1	10.2	ASTM/ASME	A/SA-240	S31260	S31260		100/70 [690/485]	Plate, Sheet, & Strip	25Cr-6.5Ni-3Mo-N
10H	1	10.1	ASTM/ASME	A/SA-240	S31803	S31803		90/65 [620/450]	Plate, Sheet, & Strip	22Cr-5Ni-3Mo-N
10H	1	10.2	ASTM/ASME	A/SA-240	S32550	S32550		110/80 [760/550]	Plate, Sheet, & Strip	25Cr-5Ni-3Mo-2Cu
10H	1	10.2	ASTM/ASME	A/SA-240	S32750	S32750		116/80 [800/550]	Plate, Sheet, & Strip	25Cr-7Ni-4Mo-N
10H	1	10.2	ASTM/ASME	A/SA-240	S32760	S32760		108/80 [745/550]	Plate, Sheet, & Strip	25Cr-8Ni-3Mo-W-Cu-N
10H	1	10.2	ASTM/ASME	A/SA-240	S32906	S32906	≥0.40 [≥10]	109/80 [750/550]	Plate, Sheet, & Strip	29Cr-6.5Ni-2Mo-N
10H	1	10.2	ASTM/ASME	A/SA-240	S32906	S32906	<0.40 [<10]	116/94 [800/650]	Plate, Sheet, & Strip	29Cr-6.5Ni-2Mo-N
10H	1	10.2	ASTM/ASME	A/SA-240	S32950	S32950		100/70 [690/485]	Plate, Sheet, & Strip	26Cr-4Ni-Mo-N
10H	1	10.1	ASTM	A276	—	S32101		94/65 [650/450]	Bar	21Cr-5Mn-1.5Ni-Cu-N
10H	1	10.1	ASTM/ASME	A/SA-276	—	S32550		94/65 [650/450]	Bars & Shapes	25Cr-5Ni-3Mo-2Cu
10H	1	10.1	ASTM/ASME	A/SA-276	S32205	S32205		95/65 [655/450]	Bar	22Cr-5Ni-3Mo-N
10H	1	10.2	ASTM/ASME	A/SA-351	CD3MWCuN	J93380		100/65 [690/450]	Castings	25Cr-8Ni-3Mo-W-Cu-N

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
10H	1	10.2	ASTM/ASME	A/SA-351	CD4MCu	J93370		100/70 [690/485]	Castings	26Cr-5Ni-2Mo-3Cu
10H	1	10.2	ASTM/ASME	A/SA-351	CE8MN	J93345		95/65 [655/450]	Castings	24Cr-10Ni-4Mo-N
10H	1	10.1	ASTM/ASME	A/SA-479	—	S31803		90/65 [620/450]	Bars & Shapes	22Cr-5Ni-3Mo-N
10H	1	10.1	ASTM/ASME	A/SA-479	—	S32101		94/65 [650/450]	Bars & Shapes	21Cr-5Mn-1.5Ni-Cu-N
10H	1	10.1	ASTM/ASME	A/SA-479	—	S32202		94/65 [650/450]	Bars & Shapes	22Cr-2Ni-Mo-N
10H	1	10.1	ASTM/ASME	A/SA-479	2205	S32205		95/65 [655/450]	Bars & Shapes	22Cr-5Ni-3Mo-N
10H	1	10.2	ASTM/ASME	A/SA-479	S32550	S32550		110/80 [760/550]	Bars & Shapes	25Cr-5Ni-3Mo-2Cu
10H	1	10.2	ASTM/ASME	A/SA-479	S32750	S32750		116/80 [800/550]	Bars & Shapes	25Cr-7Ni-4Mo-N
10H	1	10.2	ASTM	A479	S32906	S32906		109/80 [750/550]	Bars & Shapes	29Cr-6.5Ni-2Mo-N
10H	1	10.1	ASTM/ASME	A/SA-789	—	S32003		100/70 [690/485]	Seamless & Welded Tube	21Cr-3.5Ni-Mo-N
10H	1	10.1	ASTM/ASME	A/SA-789	—	S32101	>0.187 [≥ 5]	94/65 [650/450]	Seamless & Welded Tube	21Cr-5Mn-1.5Ni-Cu-N
10H	1	10.1	ASTM/ASME	A/SA-789	—	S32101	≤ 0.187 [≤ 5]	101/77 [700/530]	Seamless & Welded Tube	21Cr-5Mn-1.5Ni-Cu-N
10H	1	10.1	ASTM/ASME	A/SA-789	—	S32202		94/65 [650/450]	Seamless & Welded Tube	22Cr-2Ni-Mo-N
10H	1	10.2	ASTM/ASME	A/SA-789	S31200	S31200		100/65 [690/450]	Seamless & Welded Tube	25Cr-6Ni-Mo-N
10H	1	10.2	ASTM/ASME	A/SA-789	S31260	S31260		100/65 [690/450]	Seamless & Welded Tube	25Cr-6.5Ni-3Mo-N
10H	1	10.1	ASTM/ASME	A/SA-789	S31500	S31500		92/64 [635/440]	Seamless & Welded Tube	18Cr-5Ni-3Mo-N
10H	1	10.1	ASTM/ASME	A/SA-789	S31803	S31803		90/65 [620/450]	Seamless & Welded Tube	22Cr-5Ni-3Mo-N
10H	1	10.1	ASTM/ASME	A/SA-789	S32205	S32205		95/70 [655/485]	Seamless & Welded Tube	22Cr-5Ni-3Mo-N
10H	1	10.1	ASTM/ASME	A/SA-789	S32304	S32304	>1 [> 25]	87/58 [600/400]	Seamless & Welded Tube	23Cr-4Ni-Mo-Cu-N
10H	1	10.1	ASTM/ASME	A/SA-789	S32304	S32304	≤ 1 [≤ 25]	100/65 [690/450]	Seamless & Welded Tube	23Cr-4Ni-Mo-Cu-N
10H	1	10.2	ASTM/ASME	A/SA-789	S32550	S32550		110/80 [760/550]	Seamless & Welded Tube	25Cr-5Ni-3Mo-2Cu
10H	1	10.2	ASTM/ASME	A/SA-789	S32750	S32750		116/80 [800/550]	Seamless & Welded Tube	25Cr-7Ni-4Mo-N
10H	1	10.2	ASTM/ASME	A/SA-789	S32760	S32760		109/80 [750/550]	Seamless & Welded Tube	25Cr-8Ni-3Mo-W-Cu-N
10H	1	10.2	ASTM/ASME	A/SA-789	S32900	S32900		90/70 [620/485]	Seamless & Welded Tube	26Cr-4Ni-Mo
10H	1	10.2	ASTM/ASME	A/SA-789	S32906	S32906	≥ 0.40 [≥ 10]	109/80 [750/550]	Seamless & Welded Tube	29Cr-6.5Ni-2Mo-N
10H	1	10.2	ASTM/ASME	A/SA-789	S32906	S32906	<0.40 [< 10]	116/94 [800/650]	Seamless & Welded Tube	29Cr-6.5Ni-2Mo-N
10H	1	10.2	ASTM/ASME	A/SA-789	S32950	S32950		100/70 [690/485]	Seamless & Welded Tube	26Cr-4Ni-Mo-N
10H	1	10.2	ASTM/ASME	A/SA-789	S32974	S32974		116/80 [800/550]	Seamless & Welded Tube	25Cr-7Ni-3Mo-2W-Cu-N
10H	1	10.1	ASTM/ASME	A/SA-790	—	S32003		90/65 [620/450]	Seamless & Welded Pipe	21Cr-3.5Ni-Mo-N

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
10H	1	10.1	ASTM/ASME	A/SA-790	—	S32101	≤0.187 [≤5]	101/77 [700/530]	Seamless & Welded Pipe	21Cr-5Mn-1.5Ni-Cu-N
10H	1	10.1	ASTM/ASME	A/SA-790	—	S32101	>0.187 [>5]	94/65 [650/450]	Seamless & Welded Pipe	21Cr-5Mn-1.5Ni-Cu-N
10H	1	10.1	ASTM/ASME	A/SA-790	—	S32202		94/65 [650/450]	Seamless & Welded Pipe	22Cr-2Ni-Mo-N
10H	1	10.2	ASTM/ASME	A/SA-790	S31200	S31200		100/65 [690/450]	Seamless & Welded Pipe	25Cr-6Ni-Mo-N
10H	1	10.2	ASTM/ASME	A/SA-790	S31260	S31260		100/65 [690/450]	Seamless & Welded Pipe	25Cr-6.5Ni-3Mo-N
10H	1	10.1	ASTM/ASME	A/SA-790	S31500	S31500		92/64 [635/440]	Seamless & Welded Pipe	18Cr-5Ni-3Mo-N
10H	1	10.1	ASTM/ASME	A/SA-790	S31803	S31803		90/65 [620/450]	Seamless & Welded Pipe	22Cr-5Ni-3Mo-N
10H	1	10.1	ASTM/ASME	A/SA-790	S32205	S32205		95/65 [655/450]	Seamless & Welded Pipe	22Cr-5Ni-3Mo-N
10H	1	10.1	ASTM/ASME	A/SA-790	S32304	S32304		87/58 [600/400]	Seamless & Welded Pipe	23Cr-4Ni-Mo-Cu-N
10H	1	10.2	ASTM/ASME	A/SA-790	S32550	S32550		110/80 [760/550]	Seamless & Welded Pipe	25Cr-5Ni-3Mo-2Cu
10H	1	10.2	ASTM/ASME	A/SA-790	S32750	S32750		116/80 [800/550]	Seamless & Welded Pipe	25Cr-7Ni-4Mo-N
10H	1	10.2	ASTM/ASME	A/SA-790	S32760	S32760		109/80 [750/550]	Seamless & Welded Pipe	25Cr-8Ni-3Mo-W-Cu-N
10H	1	10.2	ASTM/ASME	A/SA-790	S32900	S32900		90/70 [620/485]	Seamless & Welded Pipe	26Cr-4Ni-Mo
10H	1	10.2	ASTM/ASME	A/SA-790	S32906	S32906	≥0.40 [≥10]	109/80 [750/550]	Seamless & Welded Pipe	29Cr-6.5Ni-2Mo-N
10H	1	10.2	ASTM/ASME	A/SA-790	S32906	S32906	<0.40 [<10]	116/94 [800/650]	Seamless & Welded Pipe	29Cr-6.5Ni-2Mo-N
10H	1	10.2	ASTM/ASME	A/SA-790	S32950	S32950		100/70 [690/485]	Seamless & Welded Pipe	26Cr-4Ni-Mo-N
10H	1	10.2	ASTM/ASME	A/SA-790	S39274	S39274		116/80 [800/550]	Seamless & Welded Pipe	25Cr-7Ni-3Mo-2W-Cu-N
10H	1	10.1	ASTM/ASME	A/SA-815	—	S32101		94/65 [650/450]	Fittings	21Cr-5Mn-1.5Ni-Cu-N
10H	1	10.1	ASTM/ASME	A/SA-815	—	S32202		94/65 [650/450]	Fittings	22Cr-2Ni-Mo-N
10H	1	10.1	ASTM/ASME	A/SA-815	S31803	S31803		90/65 [620/450]	Fittings	22Cr-5Ni-3Mo-N
10H	1	10.1	ASTM/ASME	A/SA-815	S32205	S32205		95/65 [655/450]	Fittings	22Cr-5Ni-3Mo-N
10H	1	10.2	ASTM/ASME	A/SA-815	S32550	S32550		110/80 [760/550]	Fittings	25Cr-5Ni-3Mo-2Cu
10H	1	10.2	ASTM/ASME	A/SA-815	S32750	S32750		116/80 [800/550]	Fittings	25Cr-7Ni-4Mo-N
10H	1	10.2	ASTM/ASME	A/SA-815	S32760	S32760		109/80 [750/550]	Fittings	25Cr-8Ni-3Mo-W-Cu-N
10H	1	10.2	ASTM	A890	1A	J93370		100/70 [690/485]	Castings	26Cr-5Ni-2Mo-3Cu
10H	1	10.2	ASTM	A890	1B	J93372		100/70 [690/485]	Castings	25Cr-5Ni-3Mo-2Cu
10H	1	10.2	ASTM	A890	1C	J93373		100/65 [690/450]	Castings	25Cr-6Ni-3Mo-Cu-N
10H	1	10.2	ASTM	A890	2A	J93345		95/65 [655/450]	Castings	24Cr-10Ni-4Mo-N
10H	1	10.2	ASTM	A890	3A	J93371		95/65 [655/450]	Castings	25Cr-5Ni-2Mo-N

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
10H	1	10.1	ASTM	A890	4A	J92205		90/60 [620/415]	Castings	22Cr-5Ni-3Mo-N
10H	1	10.2	ASTM	A890	5A	J93404		100/75 [690/515]	Castings	25Cr-7Ni-4Mo-N
10H	1	10.2	ASTM	A890	6A	J93380		100/65 [690/450]	Castings	25Cr-8Ni-3Mo-W-Cu-N
10H	1	10.2	ASTM	A928	—	S32760		108/80 [745/550]	Welded Pipe	25Cr-8Ni-3Mo-W-Cu-N
10H	1	10.1	ASTM	A928	2205	S32205		90/65 [620/450]	Welded Pipe	22Cr-5Ni-3Mo-N
10H	1	10.2	ASTM	A928	255	S32550		110/80 [760/550]	Welded Pipe	25Cr-5Ni-3Mo-2Cu
10H	1	10.2	ASTM/ASME	A/SA-995	1B	J93372		100/70 [690/485]	Castings	25Cr-5Ni-3Mo-2Cu
10H	1	10.2	ASTM/ASME	A/SA-995	2A	J93345		95/65 [655/450]	Castings	24Cr-10Ni-4Mo-N
10H	1	10.2	ASTM/ASME	A/SA-995	3A	J93371		95/65 [655/450]	Castings	25Cr-5Ni-2Mo-N
10H	1	10.1	ASTM/ASME	A/SA-995	4A	J92205		90/60 [620/415]	Castings	22Cr-5Ni-3Mo-N
10H	1	10.2	ASTM/ASME	A/SA-995	5A	J93404		100/75 [690/515]	Castings	25Cr-7Ni-4Mo-N
10H	1	10.2	ASTM/ASME	A/SA-995	6A	J93380		100/65 [690/450]	Castings	25Cr-8Ni-3Mo-W-Cu-N
10I	1	7.1	ASTM/ASME	A/SA-182	FXM-27Cb	S44627		60/35 [415/240]	Forgings	27Cr-1Mo
10I	1	7.1	ASTM/ASME	A/SA-240	S44635	S44635		90/75 [620/515]	Plate, Sheet, & Strip	25Cr-4Ni-4Mo-Ti
10I	1	7.1	ASTM/ASME	A/SA-240	XM-27	S44627		65/40 [450/275]	Plate, Sheet, & Strip	27Cr-1Mo
10I	1	7.1	ASTM/ASME	A/SA-240	XM-33	S44626		68/45 [470/310]	Plate, Sheet, & Strip	27Cr-1Mo-Ti
10I	1	7.1	ASTM/ASME	A/SA-268	25-4-4	S44635		90/75 [620/515]	Seamless & Welded Tube	25Cr-4Ni-4Mo-Ti
10I	1	7.1	ASTM/ASME	A/SA-268	TP 446-1	S44600		70/40 [485/275]	Seamless & Welded Tube	27Cr
10I	1	7.1	ASTM/ASME	A/SA-268	TP 446-2	S44600		65/40 [450/275]	Seamless & Welded Tube	27Cr
10I	1	7.1	ASTM/ASME	A/SA-268	TP XM-27	S44627		65/40 [450/275]	Seamless & Welded Tube	27Cr-1Mo
10I	1	7.1	ASTM/ASME	A/SA-268	TP XM-33	S44626		68/45 [470/310]	Seamless & Welded Tube	27Cr-1Mo-Ti
10I	1	7.1	ASTM/ASME	A/SA-336	FXM-27Cb	S44627		60/35 [415/240]	Forgings	27Cr-1Mo
10I	1	7.1	ASTM/ASME	A/SA-479	XM-27	S44627		65/40 [450/275]	Bars & Shapes	27Cr-1Mo
10I	1	7.1	ASTM/ASME	A/SA-731	TPXM-27	S44627		65/40 [450/275]	Seamless & Welded Pipe	27Cr-1Mo
10I	1	7.1	ASTM/ASME	A/SA-731	TPXM-33	S44626		65/40 [450/275]	Seamless & Welded Pipe	27Cr-1Mo-Ti
10J	1	7.1	ASTM/ASME	A/SA-240	S44700	S44700		80/60 [550/415]	Plate, Sheet, & Strip	29Cr-4Mo
10J	1	7.1	ASTM/ASME	A/SA-268	29-4	S44700		80/60 [550/415]	Seamless & Welded Tube	29Cr-4Mo
10J	1	7.1	ASTM/ASME	A/SA-268	S44735	S44735		75/60 [515/415]	Seamless & Welded Tube	29Cr-4Mo-Ti
10J	1	7.1	ASTM/ASME	A/SA-479	S44700	S44700		70/55 [485/380]	Bars & Shapes	29Cr-4Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
10J	7.1	ASTM/ASME	A/SA-731	S44700	S44700		80/60 [550/415]	Seamless & Welded Pipe	29Cr-4Mo
10K	7.1	ASTM/ASME	A/SA-240	S44660	S44660		85/65 [585/450]	Plate, Sheet, & Strip	26Cr-3Ni-3Mo
10K	7.1	ASTM/ASME	A/SA-240	S44800	S44800		80/60 [550/415]	Plate, Sheet, & Strip	29Cr-4Mo-2Ni
10K	7.1	ASTM/ASME	A/SA-268	26-3-3	S44660		85/65 [585/450]	Seamless & Welded Tube	26Cr-3Ni-3Mo
10K	7.1	ASTM/ASME	A/SA-268	29-4-2	S44800		80/60 [550/415]	Seamless & Welded Tube	29Cr-4Mo-2Ni
10K	7.1	ASTM/ASME	A/SA-479	S44800	S44800		70/55 [485/380]	Bars & Shapes	29Cr-4Mo-2Ni
10K	7.1	ASTM/ASME	A/SA-731	S44660	S44660		85/65 [585/450]	Seamless & Welded Pipe	26Cr-3Ni-3Mo
10K	7.1	ASTM/ASME	A/SA-731	S44800	S44800		80/60 [550/415]	Seamless & Welded Pipe	29Cr-4Mo-2Ni
10K	7.1	ASTM/ASME	A/SA-803	26-3-3	S44660		85/65 [585/450]	Welded Tube	26Cr-3Ni-3Mo
11A	9.3	ASTM/ASME	A/SA-333	8	K81340		100/75 [690/515]	Seamless & Welded Pipe	9Ni
11A	9.3	ASTM/ASME	A/SA-334	8	K81340		100/75 [690/515]	Welded Tube	9Ni
11A	9.3	ASTM/ASME	A/SA-353	—	K81340		100/75 [690/515]	Plate	9Ni
11A	9.3	ASTM/ASME	A/SA-420	WPL8	K81340		100/75 [690/515]	Piping Fittings	9Ni
11A	9.3	ASTM/ASME	A/SA-522	I	K81340		100/75 [690/515]	Forgings	9Ni
11A	9.3	ASTM/ASME	A/SA-522	II	K71340		100/75 [690/515]	Forgings	8Ni
11A	9.3	ASTM/ASME	A/SA-553	I	K81340		100/85 [690/585]	Plate	9Ni
11A	9.3	ASTM/ASME	A/SA-553	II	K71340		100/85 [690/585]	Plate	8Ni
11A	9.3	ASTM	A844	—	K81340		100/85 [690/585]	Plate	9Ni
11A	9.2	ASTM/ASME	A/SA-645	A	K41583		95/65 [655/450]	Plate	5Ni-0.25Mo
11A	3.1	ASTM	A734	A	K21205		77/65 [530/450]	Plate	C-Mn-1Ni-1Cr-0.3Mo
11A	3.1	ASTM/ASME	A/SA-487	4, Cl. B	J13047		105/85 [725/585]	Castings	0.5Ni-0.5Cr-0.25Mo-V
11A	3.1	ASTM/ASME	A/SA-487	4, Cl. E	J13047		115/95 [795/655]	Castings	0.5Ni-0.5Cr-0.25Mo-V
11A	3.1	ASTM/ASME	A/SA-533	A, Cl. 3	K12521		100/83 [690/570]	Plate	Mn-0.5Mo
11A	3.2	ASTM/ASME	A/SA-533	B, Cl. 3	K12539		100/83 [690/570]	Plate	Mn-0.5Mo-0.5Ni
11A	3.2	ASTM/ASME	A/SA-533	C, Cl. 3	K12554		100/83 [690/570]	Plate	Mn-0.5Mo-0.75Ni
11A	3.1	ASTM/ASME	A/SA-533	D, Cl. 3	K12529		100/83 [690/570]	Plate	Mn-0.5Mo-0.25Ni
11A	3.2	ASTM/ASME	A/SA-672	J100	K12521		100/83 [690/570]	Fusion Welded Pipe	Mn-0.5Mo
11A	9.2	ASTM/ASME	A/SA-352	LC2-1	J42215		105/80 [725/550]	Castings	3Ni-1.5Cr-0.5Mo
11A	3.1	ASTM/ASME	A/SA-508	4N, Cl. 1	K22375		105/85 [725/585]	Forgings	3.5Ni-1.75Cr-0.5Mo-V

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
11A	5	3.1	ASTM/ASME	A/SA-508	5, Cl.1	K42365		105/85 [725/585]	Forgings	3.5Ni-1.75Cr-0.5Mo-V
11A	5	3.1	ASTM/ASME	A/SA-543	B Cl.1	K42339		105/85 [725/585]	Plate	3Ni-1.75Cr-0.5Mo
11A	5	3.1	ASTM/ASME	A/SA-543	C Cl.1	—		105/85 [725/585]	Plate	2.75Ni-1.5Cr-0.5Mo
11B	—	3.1	AS/NZS	3597	700PV	—		120/109 [830/750]	Plate	C-Mn-1Cr.25Mo
11B	1	3.1	ASTM	A514	A	K11856	≤1.25 [≤32]	110/100 [760/690]	Plate	0.5Cr-0.25Mo-Si
11B	1	3.1	ASTM/ASME	A/SA-517	A	K11856	≤1.25 [≤32]	115/100 [795/690]	Plate	0.5Cr-0.25Mo-Si
11B	1	3.1	ASTM/ASME	A/SA-592	A	K11856	≤1.5 [≤38]	115/100 [795/690]	Forgings	0.5Cr-0.25Mo-Si
11B	10	3.1	ASTM/ASME	A/SA-508	4N, Cl.2	K22375		115/100 [795/690]	Forgings	3.5Ni-1.75Cr-0.5Mo-V
11B	10	3.1	ASTM/ASME	A/SA-508	5, Cl.2	K42365		115/100 [795/690]	Forgings	3.5Ni-1.75Cr-0.5Mo-V
11B	10	3.1	ASTM	A514	M	K11683	≤2 [≤50]	115/100 [795/690]	Plate	1.3Ni-0.5Mo
11B	10	3.1	ASTM	A514	M	K11683	>2.5 and ≤6 [≥64 and ≤152]	100/90 [690/620]	Plate	1.3Ni-0.5Mo
11B	10	3.1	ASTM	A514	M	K11683	>2 and ≤2.5 [≥50 and ≤64]	110/100 [760/690]	Plate	1.3Ni-0.5Mo
11B	10	3.1	ASTM	A517	M	K11683	≤2 [≤50]	115/100 [795/690]	Plate	1.3Ni-0.5Mo
11B	10	3.1	ASTM/ASME	A/SA-543	B Cl.2	K42339		115/100 [795/690]	Plate	3Ni-1.75Cr-0.5Mo
11B	10	3.1	ASTM/ASME	A/SA-543	C Cl.2	—		115/100 [795/690]	Plate	2.75Ni-1.5Cr-0.5Mo
11B	11	1.4	ASTM	A709	HPS 70W	—		85/70 [585/485]	Plate, Bar, & Shapes	C-Mn
11B	11	4.2	ASTM	A852	—	K12043		90/70 [620/485]	Plate	C-Mn
11B	12	3.1	ASTM	A514	R	—	≤2.5 [≤64]	110/100 [760/690]	Plate	C-Mn-Ni-Cu-V
11B	12	3.1	ASTM	A514	R	—	>2.5 and ≤6 [≥64 and ≤152]	100/90 [690/620]	Plate	C-Mn-Ni-Cu-V
11B	14	3.1	ASTM	A517	C	K11511	<1.25 [≤32]	115/100 [795/690]	Plate	1.2Mn-0.2Mo
11B	2	3.1	ASTM	A514	E	K21604	>2.5 and ≤6 [≥64 and ≤152]	100/90 [690/620]	Plate	1.75Cr-0.5Mo-Cu
11B	2	3.1	ASTM	A514	E	K21604	≤2.5 [≤64]	110/100 [760/690]	Plate	1.75Cr-0.5Mo-Cu
11B	2	3.1	ASTM/ASME	A/SA-517	E	K21604	>2.5 and ≤6 [≥64 and ≤152]	105/90 [725/620]	Plate	1.75Cr-0.5Mo-Cu
11B	2	3.1	ASTM/ASME	A/SA-517	E	K21604	≤2.5 [≤64]	115/100 [795/690]	Plate	1.75Cr-0.5Mo-Cu
11B	2	3.1	ASTM/ASME	A/SA-592	E	K11695	≤2.5 [≤64]	115/100 [795/690]	Forgings	1.75Cr-0.5Mo-Cu

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
11B 2	3.1	ASTM/ASME	A/SA-592	E	K11695	≥2.5 and ≤4 [≥64 and ≤102]	105/90 [725/620]	Forgings	1.75Cr-0.5Mo-Cu	
11B 3	3.1	ASTM	A514	F	K11576	≤2.5 [≤64]	110/100 [760/690]	Plate	0.75Ni-0.5Cr-0.5Mo-V	
11B 3	3.1	ASTM	A514	H	K11646	≤2 [≤50]	110/100 [760/690]	Plate	0.5Ni-0.5Cr-0.25Mo-V	
11B 3	3.1	ASTM/ASME	A/SA-517	F	K11576	≤2.5 [≤64]	115/100 [795/690]	Plate	0.75Ni-0.5Cr-0.5Mo-V	
11B 3	3.1	ASTM/ASME	A/SA-517	H	K11646	≤2 [≤50]	115/100 [795/690]	Plate	0.5Ni-0.5Cr-0.25Mo-V	
11B 3	3.1	ASTM/ASME	A/SA-592	F	K11576	≥2.5 and ≤4 [≥64 and ≤102]	105/90 [725/620]	Forgings	0.75Ni-0.5Cr-0.5Mo-V	
11B 3	3.1	ASTM/ASME	A/SA-592	F	K11576	≤2.5 [≤64]	115/100 [795/690]	Forgings	0.75Ni-0.5Cr-0.5Mo-V	
11B 4	3.1	ASTM	A514	B	K11630	≤1.25 [≤32]	110/100 [760/690]	Plate	0.5Cr-0.2Mo-V	
11B 4	3.1	ASTM/ASME	A/SA-517	B	K11630	≤1.25 [≤32]	115/100 [795/690]	Plate	0.5Cr-0.2Mo-V	
11B 4	—	ASTM	A782	I	—	—	115/100 [795/690]	Plate	1Mn-1Cr-1Si-0.5Mo-Zr	
11B 4	—	ASTM	A782	I	—	—	97/80 [670/550]	Plate	1Mn-1Cr-1Si-0.5Mo-Zr	
11B 4	—	ASTM	A782	I	—	—	107/90 [740/620]	Plate	1Mn-1Cr-1Si-0.5Mo-Zr	
11B 6	3.1	ASTM	A514	C	K11511	≤2.5 [≤64]	110/100 [760/690]	Plate	1.2Mn-0.2Mo	
11B 6	3.1	ASTM	A514	C	K11511	>2.5 and ≤6 [>64 and ≤152]	100/90 [690/620]	Plate	1.2Mn-0.2Mo	
11B 6	3.1	ASTM	A514	J	K11625	≤2.5 [≤64]	110/100 [760/690]	Plate	C-0.5Mo	
11B 6	3.1	ASTM	A514	J	K11625	>2.5 and ≤6 [>64 and ≤152]	100/90 [690/620]	Plate	C-0.5Mo	
11B 6	3.1	ASTM	A514	K	K11523	≤2.5 [≤64]	110/100 [760/690]	Plate	Mn-Mo-B	
11B 6	3.1	ASTM	A514	K	K11523	>2.5 and ≤6 [>64 and ≤152]	100/90 [690/620]	Plate	Mn-Mo-B	
11B 6	3.1	ASTM	A514	S	—	≤2.5 [≤64]	110/100 [760/690]	Plate	Mn-Mo-B	
11B 6	3.1	ASTM	A514	T	—	>2.5 and ≤6 [>64 and ≤152]	100/90 [690/620]	Plate	Mn-Mo-B	
11B 6	3.1	ASTM	A514	T	—	≤2.5 [≤64]	110/100 [760/690]	Plate	Mn-Mo-B	
11B 6	3.1	ASTM	A517	J	K11625	≤1.25 [≤32]	115/100 [795/690]	Plate	C-0.5Mo	
11B 6	3.1	ASTM	A517	K	K11523	≤2 [≤50]	115/100 [795/690]	Plate	Mn-Mo-B	
11B 6	3.1	ASTM/ASME	A/SA-517	S	—	≤2 [≤50]	115/100 [795/690]	Plate	Mn-Mo-B	

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
11B 6	3.1	3.1	ASTM	A517	T	—	≤2 [≤50]	115/100 [795/690]	Plate	Mn-Mo-B
11B 8	3.1	3.1	ASTM	A514	P	K21650	>2.5 and ≤6 >64 and ≤152]	100/90 [690/620]	Plate	1.25Ni-1Cr-0.5Mo
11B 8	3.1	3.1	ASTM	A514	P	K21650	≤2.5 [≤64]	110/100 [760/690]	Plate	1.25Ni-1Cr-0.5Mo
11B 8	3.1	3.1	ASTM/ASME	A/SA-517	P	K21650	>2.5 and ≤4 >64 and ≤102]	105/90 [725/620]	Plate	1.25Ni-1Cr-0.5Mo
11B 8	3.1	3.1	ASTM/ASME	A/SA-517	P	K21650	≤2.5 [≤64]	115/100 [795/690]	Plate	1.25Ni-1Cr-0.5Mo
11B 9	3.1	3.1	ASTM	A514	Q	—	≤2.5 [≤64]	110/100 [760/690]	Plate	1.3Ni-1.3Cr-0.5Mo-V
11B 9	3.1	3.1	ASTM	A514	Q	—	>2.5 and ≤6 >64 and ≤152]	100/90 [690/620]	Plate	1.3Ni-1.3Cr-0.5Mo-V
11B 9	3.1	3.1	ASTM/ASME	A/SA-517	Q	—	≤2.5 [≤64]	115/100 [795/690]	Plate	1.3Ni-1.3Cr-0.5Mo-V
11B 9	3.1	3.1	ASTM/ASME	A/SA-517	Q	—	>2.5 and ≤6 >64 and ≤152]	105/90 [725/620]	Plate	1.3Ni-1.3Cr-0.5Mo-V
11B 9	—	—	ASTM	A519	4130	G41300		75/55 [515/380]	Tube	1Cr-0.2Mo
11B 9	—	—	ASTM	A519	8630	G86300		75/55 [515/380]	Tube	0.5Ni-0.5Cr-0.2Mo
11C 1	3.3	3.3	ASTM/ASME	A/SA-859	A Cl. 1	K20747		65/55 [450/380]	Forgings	1Ni-1Cu-0.75Cr-Mo-Nb
11C 1	3.3	3.3	ASTM/ASME	A/SA-859	A Cl. 2	K20747		75/65 [515/450]	Forgings	1Ni-1Cu-0.75Cr-Mo-Nb
12A 1	3.3	3.3	ASTM	A710	A Cl. 2	K20747	≤2 [≤51]	72/60 [495/415]	Plate	1Ni-1Cu-0.75Cr-Mo-Nb
12A 1	3.3	3.3	ASTM	A710	A Cl. 2	K20747	>2 [>51]	60/50 [415/345]	Plate	1Ni-1Cu-0.75Cr-Mo-Nb
12B 1	3.3	3.3	ASTM	A710	A Cl. 3	K20747	≤2 [≤51]	85/75 [585/515]	Plate	1Ni-1Cu-0.75Cr-Mo-Nb
12B 1	3.3	3.3	ASTM	A710	A Cl. 3	K20747	>2 [>51]	75/60 [515/415]	Plate	1Ni-1Cu-0.75Cr-Mo-Nb
12C 1	3.3	3.3	ASTM	A710	A Cl. 1	K20747	≤0.75 [≤19]	90/80 [620/550]	Plate	1Ni-1Cu-0.75Cr-Mo-Nb
15E 1	6.4	6.4	ASTM/ASME	A/SA-182	F91	K90901		85/60 [585/415]	Forgings	9Cr-1Mo-V
15E 1	6.4	6.4	ASTM/ASME	A/SA-182	F92	K92460		90/64 [620/440]	Forgings	9Cr-2W
15E 1	6.4	6.4	ASTM	A199	T91	K90901		85/60 [585/415]	Seamless Tube	9Cr-1Mo-V
15E 1	6.4	6.4	ASTM/ASME	A/SA-213	T91	K90901		85/60 [585/415]	Seamless Tube	9Cr-1Mo-V
15E 1	6.4	6.4	ASTM/ASME	A/SA-213	T92	K92460		90/64 [620/440]	Seamless Tube	9Cr-2W
15E 1	6.4	6.4	ASTM	A217	C12A	J84090		85/60 [585/415]	Castings	9Cr-1Mo-V
15E 1	6.4	6.4	ASTM/ASME	A/SA-234	WP91	K90901		85/60 [585/415]	Piping Fittings	9Cr-1Mo-V

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
15E	1	6.4	ASTM/ASME	A/SA-335	P91	K90901		85/60 [585/415]	Seamless Pipe	9Cr-1Mo-V
15E	1	6.4	ASTM/ASME	A/SA-335	P92	K92460		90/64 [620/440]	Seamless Pipe	9Cr-2W
15E	1	6.4	ASTM/ASME	A/SA-336	F91	K90901		85/60 [585/415]	Forgings	9Cr-1Mo-V
15E	1	6.4	ASTM	A356	I2A	J84090		85/60 [585/415]	Castings	9Cr-1Mo-V
15E	1	6.4	ASTM/ASME	A/SA-369	FP91	K90901		85/60 [585/415]	Forged Pipe	9Cr-1Mo-V
15E	1	6.4	ASTM/ASME	A/SA-369	FP92	K92460		90/64 [620/440]	Forged Pipe	9Cr-2W
15E	1	5.4	ASTM/ASME	A/SA-387	91, Cl. 2	K90901		85/60 [585/415]	Plate	9Cr-1Mo-V
15E	1	6.4	ASTM/ASME	A/SA-691	91	K91560		85/60 [585/415]	Fusion Welded Pipe	9Cr-1Mo-V
1A	4	—	ASTM	A615	40	—		60/40 [415/275]	Rebar	C
1A	4	—	ASTM	A615	60	—		90/60 [620/415]	Rebar	C
1A	4	1.3	ASTM	A706	60	—		80/60 [550/415]	Rebar	C
1A	4	—	CSA	G30.18	300R	—		60/40 [415/275]	Rebar	C
1A	4	—	CSA	G30.18	400R	—		78.5/58 [540/400]	Rebar	C
1A	4	11.1	CSA	G30.18	400W	—		78.5/58 [540/400]	Rebar	C
1A	4	—	CSA	G30.18	500R	—		98/72.5 [675/500]	Rebar	C
1A	4	11.1	CSA	G30.18	500W	—		90.5/72.5 [625/500]	Rebar	C
3	1	1.1	ASTM	A161	T1	K11522		55/30 [380/205]	Tube	C-0.5Mo
3	1	1.1	ASTM/ASME	A/SA-204	A	K11820		65/37 [450/255]	Plate	C-0.5Mo
3	1	1.1	ASTM/ASME	A/SA-209	T1	K11522		55/30 [380/205]	Seamless Tube	C-0.5Mo
3	1	1.1	ASTM/ASME	A/SA-209	T1a	K12023		60/32 [415/220]	Seamless Tube	C-0.5Mo
3	1	1.1	ASTM/ASME	A/SA-209	T1b	K11422		53/28 [365/195]	Seamless Tube	C-0.5Mo
3	1	4.2	ASTM/ASME	A/SA-213	T2	K11547		60/30 [415/205]	Seamless Tube	0.5Cr-0.5Mo
3	1	1.1	ASTM/ASME	A/SA-217	WC1	J12524		65/35 [450/240]	Castings	C-0.5Mo
3	1	11.2	ASTM/ASME	A/SA-234	WP1	K12821		55/30 [380/205]	Piping Fittings	C-0.5Mo
3	1	1.1	ASTM/ASME	A/SA-250	T1	K11522		55/30 [380/205]	E.R.W. Tube	C-0.5Mo
3	1	1.1	ASTM/ASME	A/SA-250	T1a	K12023		60/32 [415/220]	E.R.W. Tube	C-0.5Mo
3	1	1.1	ASTM/ASME	A/SA-250	T1b	K11422		53/28 [365/195]	E.R.W. Tube	C-0.5Mo
3	1	4.2	ASTM/ASME	A/SA-250	T2	K11547		60/30 [415/205]	E.R.W. Tube	0.5Cr-0.5Mo
3	1	1.1	ASTM/ASME	A/SA-335	P1	K11522		55/30 [380/205]	Seamless Pipe	C-0.5Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
3	1	—	ASTM/ASME	A/SA-335	P15	K11578		60/30 [415/205]	Seamless Pipe	1.5Si-0.5Mo
3	1	4.2	ASTM/ASME	A/SA-335	P2	K11547		55/30 [380/205]	Seamless Pipe	0.5Cr-0.5Mo
3	1	1.1	ASTM/ASME	A/SA-352	LC1	J12522		65/35 [450/240]	Castings	C-0.5Mo
3	1	1.1	ASTM	A356	2	J12523		65/35 [450/240]	Castings	C-0.5Mo
3	1	1.1	ASTM/ASME	A/SA-369	FP1	K11522		55/30 [380/205]	Forged Pipe	C-0.5Mo
3	1	4.2	ASTM/ASME	A/SA-369	FP2	K11547		55/30 [380/205]	Forged Pipe	0.5Cr-0.5Mo
3	1	4.2	ASTM/ASME	A/SA-387	2, Cl. 1	K12143		55/33 [380/230]	Plate	0.5Cr-0.5Mo
3	1	1.1	ASTM/ASME	A/SA-426	CP1	J12521		65/35 [450/240]	Centrifugal Cast Pipe	C-0.5Mo
3	1	1.1	ASTM/ASME	A/SA-426	CP15	J11522		60/30 [415/205]	Centrifugal Cast Pipe	C-0.5Mo-Si
3	1	4.2	ASTM/ASME	A/SA-426	CP2	J11547		60/30 [415/205]	Centrifugal Cast Pipe	0.5Cr-0.5Mo
3	1	1.4	ASTM	A588	A	K11430		70/50 [485/345]	Shapes	Mn-0.5Cr-0.3Cu-Si-V
3	1	1.4	ASTM	A588	A	K11430	>5 and ≤8 [>125 and ≤200]	63/42 [435/290]	Plate & Bar	Mn-0.5Cr-0.3Cu-Si-V
3	1	1.4	ASTM	A588	A	K11430	>4 and ≤5 [>100 and ≤125]	67/46 [460/315]	Plate & Bar	Mn-0.5Cr-0.3Cu-Si-V
3	1	1.4	ASTM	A588	A	K11430	≤4 [≤100]	70/50 [485/345]	Plate & Bar	Mn-0.5Cr-0.3Cu-Si-V
3	1	1.4	ASTM	A588	B	K12043		70/50 [485/345]	Shapes	Mn-0.6Cr-0.3Cu-Si-V
3	1	1.4	ASTM	A588	B	K12043	>5 and ≤8 [>125 and ≤200]	63/42 [435/290]	Plate & Bar	Mn-0.6Cr-0.3Cu-Si-V
3	1	1.4	ASTM	A588	B	K12043	>4 and ≤5 [>100 and ≤125]	67/46 [460/315]	Plate & Bar	Mn-0.6Cr-0.3Cu-Si-V
3	1	1.4	ASTM	A588	B	K12043	≤4 [≤100]	70/50 [485/345]	Plate & Bar	Mn-0.6Cr-0.3Cu-Si-V
3	1	1.4	ASTM	A588	C	K11538	>5 and ≤8 [>125 and ≤200]	63/42 [435/290]	Plate & Bar	Mn-0.4Cr-0.4Cu-Si-V
3	1	1.4	ASTM	A588	C	K11538	≤4 [≤100]	70/50 [485/345]	Plate & Bar	Mn-0.4Cr-0.4Cu-Si-V
3	1	1.4	ASTM	A588	C	K11538	>4 and ≤5 [>100 and ≤125]	67/46 [460/315]	Plate & Bar	Mn-0.4Cr-0.4Cu-Si-V
3	1	1.4	ASTM	A588	C	K11538		70/50 [485/345]	Shapes	Mn-0.4Cr-0.4Cu-Si-V
3	1	1.4	ASTM	A588	K	—	>4 and ≤5 [>100 and ≤125]	67/46 [460/315]	Plate & Bar	Mn-0.6Cr-0.4Cu-Si-Nb

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
3	1	1.4	ASTM	A588	K	—	>5 and ≤8 [>125 and ≤200]	63/42 [435/290]	Plate & Bar	Mn-0.6Cr-0.4Cu-Si-Nb
3	1	1.4	ASTM	A588	K	—	≤4 [≤100]	70/50 [485/345]	Plate & Bar	Mn-0.6Cr-0.4Cu-Si-Nb
3	1	1.4	ASTM	A588	K	—		70/50 [485/345]	Shapes	Mn-0.6Cr-0.4Cu-Si-Nb
3	1	11.1	ASTM	A595	C	K11526		70/60 [485/415]	Welded Tube	Low C
3	1	1.1	ASTM/ASME	A/SA-672	L65	K11820		65/37 [450/255]	Fusion Welded Pipe	C-0.5Mo
3	1	4.2	ASTM/ASME	A/SA-691	0.5Cr, Cl. 1	K12143		55/33 [380/230]	Fusion Welded Pipe	0.5Cr-0.5Mo
3	1	1.1	ASTM/ASME	A/SA-691	CM-65	K11820		65/37 [450/255]	Fusion Welded Pipe	C-0.5Mo
3	1	—	ASTM	A707	L6, Cl. 1	K02902		60/42 [415/290]	Forgings	2Mn-0.3Mo-Cb
3	1	—	ASTM	A707	L6, Cl. 2	K02902		66/52 [455/360]	Forgings	2Mn-0.3Mo-Cb
3	1	1.4	AS/NZS	3678	WR350	—		65/50 [450/340]	Plate	C-Mn-Cr-Ni-Cu
3	1	1.4	AS/NZS	3678	WR350L0	—		65/50 [450/340]	Plate	C-Mn-Cr-Ni-Cu
3	2	1.1	ASTM/ASME	A/SA-182	F1	K12822		70/40 [485/275]	Forgings	C-0.5Mo
3	2	4.2	ASTM/ASME	A/SA-182	F2	K12122		70/40 [485/275]	Forgings	0.5Cr-0.5Mo
3	2	1.1	ASTM/ASME	A/SA-204	B	K12020		70/40 [485/275]	Plate	C-0.5Mo
3	2	1.2	ASTM/ASME	A/SA-204	C	K12320		75/43 [515/295]	Plate	C-0.5Mo
3	2	1.1	ASTM/ASME	A/SA-336	F1	K12520		70/40 [485/275]	Forgings	C-0.5Mo
3	2	4.2	ASTM/ASME	A/SA-387	2, Cl. 2	K12143		70/45 [485/310]	Plate	0.5Cr-0.5Mo
3	2	1.1	ASTM/ASME	A/SA-672	H75	K12021		75/45 [515/310]	Fusion Welded Pipe	Mn-0.5Mo
3	2	1.2	ASTM/ASME	A/SA-672	L70	K12020		70/40 [485/275]	Fusion Welded Pipe	C-0.5Mo
3	2	1.2	ASTM/ASME	A/SA-672	L75	K12320		75/43 [515/295]	Fusion Welded Pipe	C-0.5Mo
3	2	4.2	ASTM/ASME	A/SA-691	0.5Cr, Cl. 2	K12143		70/45 [485/310]	Fusion Welded Pipe	0.5Cr-0.5Mo
3	2	1.2	ASTM/ASME	A/SA-691	CM-70	K12020		70/40 [485/275]	Fusion Welded Pipe	C-0.5Mo
3	2	1.2	ASTM/ASME	A/SA-691	CM-75	K12320		75/43 [515/295]	Fusion Welded Pipe	C-0.5Mo
3	2	—	ASTM	A707	L6, Cl. 3	K02902		75/60 [515/415]	Forgings	2Mn-0.3Mo-Cb
3	2	4.2	ASTM	A871	60	—		75/60 [515/415]	Plate	C-Mn-Ni-Cr-Cu-V
3	3	4.1	ASTM	A108	8620 CW	G86200		— [—]	Bar	0.5Ni-0.5Cr-Mo
3	3	2.1	ASTM/ASME	A/SA-487	2, Cl. A	J13005		85/53 [585/365]	Castings	Mn-0.25Mo-V
3	3	2.1	ASTM/ASME	A/SA-487	2, Cl. B	J13005		90/65 [620/450]	Castings	Mn-0.25Mo-V

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
3	3.1	ASTM/ASME	A/SA-487	4, Cl. A	J13047		90/60 [620/415]	Castings	0.5Ni-0.5Cr-0.25Mo-V
3	3.1	ASTM/ASME	A/SA-487	4, Cl. C	J13047		90/60 [620/415]	Castings	0.5Ni-0.5Cr-0.25Mo-V
3	3.1	ASTM/ASME	A/SA-508	2, Cl. 1	K12766		80/50 [550/345]	Forgings	0.75Ni-0.5Mo-0.3Cr-V
3	3.1	ASTM/ASME	A/SA-508	2, Cl. 2	K12766		90/65 [620/450]	Forgings	0.75Ni-0.5Mo-0.3Cr-V
3	3.1	ASTM/ASME	A/SA-508	3, Cl. 1	K12042		80/50 [550/345]	Forgings	0.75Ni-0.5Mo-Cr-V
3	3.1	ASTM/ASME	A/SA-508	3, Cl. 2	K12042		90/65 [620/450]	Forgings	0.75Ni-0.5Mo-Cr-V
3	3.1	ASTM/ASME	A/SA-508	4N, Cl. 3	K22375		90/70 [620/485]	Forgings	3.5Ni-1.75Cr-0.5Mo-V
3	3.1	ASTM/ASME	A/SA-533	A, Cl. 1	K12521		80/50 [550/345]	Plate	Mn-0.5Mo
3	3.1	ASTM/ASME	A/SA-533	A, Cl. 2	K12521		90/70 [620/485]	Plate	Mn-0.5Mo
3	3.1	ASTM/ASME	A/SA-533	B, Cl. 1	K12539		80/50 [550/345]	Plate	Mn-0.5Mo-0.5Ni
3	3.1	ASTM/ASME	A/SA-533	B, Cl. 2	K12539		90/70 [620/485]	Plate	Mn-0.5Mo-0.5Ni
3	3.1	ASTM/ASME	A/SA-533	C, Cl. 1	K12554		80/50 [550/345]	Plate	Mn-0.5Mo-0.75Ni
3	3.1	ASTM/ASME	A/SA-533	C, Cl. 2	K12554		90/70 [620/485]	Plate	Mn-0.5Mo-0.75Ni
3	3.1	ASTM/ASME	A/SA-533	D, Cl. 1	K12529		80/50 [550/345]	Plate	Mn-0.5Mo-0.25Ni
3	3.1	ASTM/ASME	A/SA-533	D, Cl. 2	K12529		90/70 [620/485]	Plate	Mn-0.5Mo-0.25Ni
3	3.1	ASTM/ASME	A/SA-533	E, Cl. 1	K12554		80/50 [550/345]	Plate	Mn-0.5Mo-0.75Ni
3	3.1	ASTM/ASME	A/SA-533	E, Cl. 2	K12554		90/70 [620/485]	Plate	Mn-0.5Mo-0.75Ni
3	4.2	ASTM/ASME	A/SA-541	2, Cl. 1	K12765		80/50 [550/345]	Forgings	0.75Ni-0.5Mo-0.3Cr-V
3	4.2	ASTM/ASME	A/SA-541	2, Cl. 2	K12765		90/65 [620/450]	Forgings	0.75Ni-0.5Mo-0.3Cr-V
3	4.1	ASTM/ASME	A/SA-541	3, Cl. 1	K12045		80/50 [550/345]	Forgings	0.5Ni-0.5Mo-V
3	4.1	ASTM/ASME	A/SA-541	3, Cl. 2	K12045		90/65 [620/450]	Forgings	0.5Ni-0.5Mo-V
3	3.1	ASTM/ASME	A/SA-543	B, Cl. 3	K42339		90/70 [620/485]	Plate	3Ni-1.75Cr-0.5Mo
3	3.1	ASTM/ASME	A/SA-543	C, Cl. 3	—		90/70 [620/485]	Plate	2.75Ni-1.5Cr-0.5Mo
3	1.2	ASTM/ASME	A/SA-672	H80	K12022		80/50 [550/345]	Fusion Welded Pipe	Mn-0.5Mo
3	3.1	ASTM/ASME	A/SA-672	J80	—		80/50 [550/345]	Fusion Welded Pipe	Mn-0.5Mo-0.75Ni
3	3.1	ASTM/ASME	A/SA-672	J90	—		90/70 [620/485]	Fusion Welded Pipe	Mn-0.5Mo-0.75Ni
3	4.2	ASTM	A871	65	—		80/65 [550/450]	Plate	C-Mn-Ni-Cr-Cu-V
3	4	—	A707	L6, Cl. 4	K02902		90/75 [620/515]	Forgings	2Mn-0.3Mo-Cb
4	1	ASTM/ASME	A/SA-182	F11, Cl. 1	K11597		60/30 [415/205]	Forgings	1.25Cr-0.5Mo-Si

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
4	1	5.1	ASTM/ASME A/SA-182	F11, Cl. 2	K11572	70/40 [485/275]	Forgings	1.25Cr-0.5Mo-Si	
4	1	5.1	ASTM/ASME A/SA-182	F11, Cl. 3	K11572	75/45 [515/310]	Forgings	1.25Cr-0.5Mo-Si	
4	1	5.1	ASTM/ASME A/SA-182	F12, Cl. 1	K11562	60/32 [415/220]	Forgings	1Cr-0.5Mo	
4	1	5.1	ASTM/ASME A/SA-182	F12, Cl. 2	K11564	70/40 [485/275]	Forgings	1Cr-0.5Mo	
4	1	5.1	ASTM A199	T11	K11597	60/25 [415/170]	Seamless Tube	1.25Cr-0.5Mo-Si	
4	1	4.2	ASTM/ASME A/SA-202	A	K11742	75/45 [515/310]	Plate	0.5Cr-1.25Mn-Si	
4	1	4.2	ASTM/ASME A/SA-202	B	K12542	85/47 [585/325]	Plate	0.5Cr-1.25Mn-Si	
4	1	5.1	ASTM/ASME A/SA-213	T11	K11597	60/30 [415/205]	Seamless Tube	1.25Cr-0.5Mo-Si	
4	1	5.1	ASTM/ASME A/SA-213	T12	K11562	60/32 [415/220]	Seamless Tube	1Cr-0.5Mo	
4	1	9.1	ASTM/ASME A/SA-217	WC4	J12082	70/40 [485/275]	Castings	1Ni-0.5Cr-0.5Mo	
4	1	4.2	ASTM/ASME A/SA-217	WC5	J22000	70/40 [485/275]	Castings	0.75Ni-1Mo-0.75Cr	
4	1	5.1	ASTM/ASME A/SA-217	WC6	J12072	70/40 [485/275]	Castings	1.25Cr-0.5Mo	
4	1	5.1	ASTM/ASME A/SA-234	WP11, Cl. 1	—	60/30 [415/205]	Piping Fittings	1.25Cr-0.5Mo-Si	
4	1	5.1	ASTM/ASME A/SA-234	WP11, Cl. 2	—	70/40 [485/275]	Piping Fittings	1.25Cr-0.5Mo-Si	
4	1	5.1	ASTM/ASME A/SA-234	WP11, Cl. 3	—	75/45 [515/310]	Piping Fittings	1.25Cr-0.5Mo-Si	
4	1	5.1	ASTM/ASME A/SA-234	WP12, Cl. 1	K12062	60/32 [415/220]	Piping Fittings	1Cr-0.5Mo	
4	1	5.1	ASTM/ASME A/SA-234	WP12, Cl. 2	K12062	70/40 [485/275]	Piping Fittings	1Cr-0.5Mo	
4	1	5.1	ASTM/ASME A/SA-250	T11	K11597	60/30 [415/205]	E.R.W. Tube	1.25Cr-0.5Mo-Si	
4	1	5.1	ASTM/ASME A/SA-250	T12	K11562	60/32 [415/220]	E.R.W. Tube	1Cr-0.5Mo	
4	1	5.1	ASTM/ASME A/SA-335	P11	K11597	60/30 [415/205]	Seamless Pipe	1.25Cr-0.5Mo-Si	
4	1	5.1	ASTM/ASME A/SA-335	P12	K11562	60/32 [415/220]	Seamless Pipe	1Cr-0.5Mo	
4	1	5.1	ASTM/ASME A/SA-336	F11, Cl. 1	K11597	60/30 [415/205]	Forgings	1.25Cr-0.5Mo-Si	
4	1	5.1	ASTM/ASME A/SA-336	F11, Cl. 2	K11572	70/40 [485/275]	Forgings	1.25Cr-0.5Mo-Si	
4	1	5.1	ASTM/ASME A/SA-336	F11, Cl. 3	K11572	75/45 [515/310]	Forgings	1.25Cr-0.5Mo-Si	
4	1	5.1	ASTM/ASME A/SA-336	F12	K11564	70/40 [485/275]	Forgings	1Cr-0.5Mo	
4	1	5.1	ASTM A356	6	J12073	70/45 [485/310]	Castings	1.25Cr-0.5Mo	
4	1	6.2	ASTM A356	8	J11697	80/50 [550/345]	Castings	1Cr-1Mo-V	
4	1	6.2	ASTM A356	9	J21610	85/60 [585/415]	Castings	1Cr-1Mo-V	
4	1	5.1	ASTM/ASME A/SA-369	FP11	K11597	60/30 [415/205]	Forged Pipe	1.25Cr-0.5Mo-Si	

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group	15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
4	1	5.1	ASTM/ASME	A/SA-369	FP12	K11562		60/32 [415/220]	Forged Pipe	1Cr-0.5Mo
4	1	5.1	ASTM/ASME	A/SA-387	11, Cl. 1	K11789		60/35 [415/240]	Plate	1.25Cr-0.5Mo-Si
4	1	5.1	ASTM/ASME	A/SA-387	11, Cl. 2	K11789		75/45 [515/310]	Plate	1.25Cr-0.5Mo-Si
4	1	5.1	ASTM/ASME	A/SA-387	12, Cl. 1	K11757		55/33 [380/230]	Plate	1Cr-0.5Mo
4	1	5.1	ASTM/ASME	A/SA-387	12, Cl. 2	K11757		65/40 [450/275]	Plate	1Cr-0.5Mo
4	1	6.2	ASTM	A389	C23	J12080		70/40 [485/275]	Castings	1.25Cr-0.5Mo-V
4	1	6.2	ASTM	A389	C24	J12092		80/50 [550/345]	Castings	1Cr-1Mo-V
4	1	6.2	ASTM	A405	P24	K11591		80/50 [550/345]	Seamless Pipe	1.25Cr-Mo
4	1	5.1	ASTM/ASME	A/SA-426	CP11	J12072		70/40 [485/275]	Centrifugal Cast Pipe	1.25Cr-0.5Mo
4	1	5.1	ASTM/ASME	A/SA-426	CP12	J11562		60/30 [415/205]	Centrifugal Cast Pipe	1Cr-0.5Mo
4	1	5.2	ASTM/ASME	A/SA-541	11, Cl. 4	K11572		80/50 [550/345]	Forgings	1.25Cr-0.5Mo-Si
4	1	5.1	ASTM/ASME	A/SA-691	1.25CR, Cl. 1	K11789		60/35 [415/240]	Fusion Welded Pipe	1.25Cr-0.5Mo-Si
4	1	5.1	ASTM/ASME	A/SA-691	1.25CR, Cl. 2	K11789		75/45 [515/310]	Fusion Welded Pipe	1.25Cr-0.5Mo-Si
4	1	5.1	ASTM/ASME	A/SA-691	1CR, Cl. 1	K11757		55/33 [380/230]	Fusion Welded Pipe	1Cr-0.5Mo
4	1	5.1	ASTM/ASME	A/SA-691	1CR, Cl. 2	K11757		65/40 [450/275]	Fusion Welded Pipe	1Cr-0.5Mo
4	1	5.1	ASTM/ASME	A/SA-739	B11	K11797		70/45 [485/310]	Bar	1.25Cr-0.5Mo
4	2	4.1	ASTM/ASME	A/SA-333	4	K11267		60/35 [415/240]	Seamless & Welded Pipe	0.75Cr-0.75Ni-Cu-Al
4	2	5.1	ASTM/ASME	A/SA-423	1	K11535		60/37 [415/255]	Seamless & Welded Tube	0.75Cr-0.5Ni-Cu
4	2	5.1	ASTM/ASME	A/SA-423	2	K11540		60/37 [415/255]	Seamless & Welded Tube	0.75Ni-0.5Cu-Mo
4	3	—	ASTM	A148	90-60	D50600		90/60 [620/415]	Castings	C
45	8.2	8.2	ASTM/ASME	A/SA-240	—	S31277		112/52 [770/360]	Plate, Sheet, & Strip	27Ni-22Cr-7Mo-Mn-Cu
45	8.2	8.2	ASTM/ASME	A/SA-240	S31277	S31277		112/52 [770/360]	Plate, Sheet, & Strip	27Ni-22Cr-7Mo-Mn-Cu
45	8.2	8.2	ASTM/ASME	A/SA-351	CN3MN	J94651		80/38 [550/260]	Castings	46Fe-24Ni-21Cr-6Mo-Cu-N
45	45	45	ASTM/ASME	A/SA-351	HT30	N08603		65/28 [450/195]	Castings	35Ni-15Cr-0.5Mo
5A	1	5.2	ASTM/ASME	A/SA-182	F21	K31545		75/45 [515/310]	Forgings	3Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-182	F22, Cl. 1	K21590		60/30 [415/205]	Forgings	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-182	F22, Cl. 3	K21590		75/45 [515/310]	Forgings	2.25Cr-1Mo
5A	1	—	ASTM	A199	T21	K31545		60/25 [415/170]	Seamless Tube	3Cr-1Mo
5A	1	5.2	ASTM	A199	T22	K21590		60/25 [415/170]	Seamless Tube	2.25Cr-1Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
5A	1	—	ASTM	A199	T4	K31509		60/25 [415/170]	Seamless Tube	2.25Cr-0.5Mo-0.75Si
5A	1	—	ASTM	A200	T21	K31545		60/25 [415/170]	Tube	3Cr-1Mo
5A	1	5.2	ASTM	A200	T22	K21590		60/25 [415/170]	Tube	2.25Cr-1Mo
5A	1	—	ASTM	A200	T4	K31509		60/25 [415/170]	Tube	2.25Cr-0.5Mo-0.75Si
5A	1	5.2	ASTM/ASME	A/SA-213	T21	K31545		60/30 [415/205]	Seamless Tube	3Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-213	T22	K21590		60/30 [415/205]	Seamless Tube	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-217	WC9	J21890		70/40 [485/275]	Castings	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-234	WP22, Cl. 1	K21590		60/30 [415/205]	Piping Fittings	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-234	WP22, Cl. 3	K21590		75/45 [515/310]	Piping Fittings	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-250	T22	K21590		60/30 [415/205]	E.R.W. Tube	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-335	P21	K31545		60/30 [415/205]	Seamless Pipe	3Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-335	P22	K21590		60/30 [415/205]	Seamless Pipe	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-336	F21, Cl. 1	K31545		60/30 [415/205]	Forgings	3Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-336	F21, Cl. 3	K31545		75/45 [515/310]	Forgings	3Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-336	F22, Cl. 1	K21590		60/30 [415/205]	Forgings	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-336	F22, Cl. 3	K21590		75/45 [515/310]	Forgings	2.25Cr-1Mo
5A	1	5.2	ASTM	A356	10	J22090		85/55 [585/380]	Castings	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-369	FP21	K31545		60/30 [415/205]	Forged Pipe	3Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-369	FP22	K21590		60/30 [415/205]	Forged Pipe	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-387	21, Cl. 1	K31545		60/30 [415/205]	Plate	3Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-387	21, Cl. 2	K31545		75/45 [515/310]	Plate	3Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-387	22, Cl. 1	K21590		60/30 [415/205]	Plate	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-387	22, Cl. 2	K21590		75/45 [515/310]	Plate	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-426	CP21	J31545		60/30 [415/205]	Centrifugal Cast Pipe	3Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-426	CP22	J21890		70/40 [485/275]	Centrifugal Cast Pipe	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-691	2.25CR, Cl. 1	K21590		60/30 [415/205]	Fusion Welded Pipe	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-691	2.25CR, Cl. 2	K21590		75/45 [515/310]	Fusion Welded Pipe	2.25Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-691	3CR, Cl. 1	K31545		60/30 [415/205]	Fusion Welded Pipe	3Cr-1Mo
5A	1	5.2	ASTM/ASME	A/SA-691	3CR, Cl. 2	K31545		75/45 [515/310]	Fusion Welded Pipe	3Cr-1Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
5A	1	5.2	ASTM/ASME	A/SA-739	B22	K21390		75/45 [515/310]	Bar	2.25Cr-1Mo
5B	1	5.3	ASTM/ASME	A/SA-182	F5	K41545		70/40 [485/275]	Forgings	5Cr-0.5Mo
5B	1	5.3	ASTM/ASME	A/SA-182	F5a	K42544		90/65 [620/450]	Forgings	5Cr-0.5Mo
5B	1	5.4	ASTM/ASME	A/SA-182	F9	K90941		85/55 [585/380]	Forgings	9Cr-1Mo
5B	1	5.3	ASTM	A199	T5	K41545		60/25 [415/170]	Seamless Tube	5Cr-0.5Mo
5B	1	5.4	ASTM	A199	T9	K81590		60/25 [415/170]	Seamless Tube	9Cr-1Mo
5B	1	5.3	ASTM/ASME	A/SA-213	T5	K41545		60/30 [415/205]	Seamless Tube	5Cr-0.5Mo
5B	1	5.3	ASTM/ASME	A/SA-213	T5b	K51545		60/30 [415/205]	Seamless Tube	5Cr-0.5Mo-Si
5B	1	5.3	ASTM/ASME	A/SA-213	T5c	K41245		60/30 [415/205]	Seamless Tube	5Cr-0.5Mo-Ti
5B	1	5.4	ASTM/ASME	A/SA-213	T9	K90941		60/30 [415/205]	Seamless Tube	9Cr-1Mo
5B	1	5.4	ASTM/ASME	A/SA-217	C12	J82090		90/60 [620/415]	Castings	9Cr-1Mo
5B	1	5.3	ASTM/ASME	A/SA-217	C5	J42045		90/60 [620/415]	Castings	5Cr-0.5Mo
5B	1	5.3	ASTM/ASME	A/SA-234	WP5, Cl. 1	K41545		60/30 [415/205]	Piping Fittings	5Cr-0.5Mo
5B	1	5.3	ASTM/ASME	A/SA-234	WP5, Cl. 3	K41545		75/45 [515/310]	Piping Fittings	5Cr-0.5Mo
5B	1	5.4	ASTM/ASME	A/SA-234	WP9, Cl. 1	K90941		60/30 [415/205]	Piping Fittings	9Cr-1Mo
5B	1	5.4	ASTM/ASME	A/SA-234	WP9, Cl. 3	K90941		75/45 [515/310]	Piping Fittings	9Cr-1Mo
5B	1	5.3	ASTM/ASME	A/SA-335	P5	K41545		60/30 [415/205]	Seamless Pipe	5Cr-0.5Mo
5B	1	5.3	ASTM/ASME	A/SA-335	P5b	K51545		60/30 [415/205]	Seamless Pipe	5Cr-0.5Mo-Si
5B	1	5.3	ASTM/ASME	A/SA-335	P5c	K41245		60/30 [415/205]	Seamless Pipe	5Cr-0.5Mo-Ti
5B	1	5.4	ASTM/ASME	A/SA-335	P9	K90941		60/30 [415/205]	Seamless Pipe	9Cr-1Mo
5B	1	5.3	ASTM/ASME	A/SA-336	F5	K41545		60/36 [415/250]	Forgings	5Cr-0.5Mo
5B	1	5.3	ASTM/ASME	A/SA-336	F5A	K42544		80/50 [550/345]	Forgings	5Cr-0.5Mo
5B	1	5.4	ASTM/ASME	A/SA-336	F9	K90941		85/55 [585/380]	Forgings	9Cr-1Mo
5B	1	5.3	ASTM/ASME	A/SA-369	FP5	K41545		60/30 [415/205]	Forged Pipe	5Cr-0.5Mo
5B	1	5.4	ASTM/ASME	A/SA-369	FP9	K90941		60/30 [415/205]	Forged Pipe	9Cr-1Mo
5B	1	5.3	ASTM/ASME	A/SA-387	5, Cl. 1	K41545		60/30 [415/205]	Plate	5Cr-0.5Mo
5B	1	5.3	ASTM/ASME	A/SA-387	5, Cl. 2	K41545		75/45 [515/310]	Plate	5Cr-0.5Mo
5B	1	5.4	ASTM/ASME	A/SA-387	9, Cl. 1	K90941		60/30 [415/205]	Plate	9Cr-1Mo
5B	1	5.4	ASTM/ASME	A/SA-387	9, Cl. 2	K90941		75/45 [515/310]	Plate	9Cr-1Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
5B	1	5.3	ASTM/ASME	A/SA-426	CP5	J42045		90/60 [620/415]	Centrifugal Cast Pipe	5Cr-0.5Mo
5B	1	5.3	ASTM/ASME	A/SA-426	CP5b	J51545		60/30 [415/205]	Centrifugal Cast Pipe	5Cr-1.5Si-0.5Mo
5B	1	5.4	ASTM/ASME	A/SA-426	CP9	J82090		90/60 [620/415]	Centrifugal Cast Pipe	9Cr-1Mo
5B	1	5.3	ASTM/ASME	A/SA-691	5CR, Cl. 1	K41545		60/30 [415/205]	Fusion Welded Pipe	5Cr-0.5Mo
5B	1	5.3	ASTM/ASME	A/SA-691	5CR, Cl. 2	K41545		75/45 [515/310]	Fusion Welded Pipe	5Cr-0.5Mo
5C	1	6.2	ASTM/ASME	A/SA-182	F22V	K31835		85/60 [585/415]	Forgings	2.25Cr-1Mo-V
5C	1	6.2	ASTM/ASME	A/SA-182	F3V	K31830		85/60 [585/415]	Forgings	3Cr-1Mo-V-Ti-B
5C	1	6.2	ASTM/ASME	A/SA-182	F3VCb	K31390		85/60 [585/415]	Forgings	3Cr-1Mo-0.25V-Cb-Ca
5C	1	6.2	ASTM/ASME	A/SA-336	F22V	K31835		85/60 [585/415]	Forgings	2.25Cr-1Mo-V
5C	1	6.2	ASTM/ASME	A/SA-336	F3V	K31830		85/60 [585/415]	Forgings	3Cr-1Mo-V-Ti-B
5C	1	6.2	ASTM/ASME	A/SA-336	F3VCb	K31390		85/60 [585/415]	Forgings	3Cr-1Mo-0.25V-Cb-Ca
5C	1	5.2	ASTM/ASME	A/SA-487	8, Cl. A	J22091		85/55 [585/380]	Castings	2.25Cr-1Mo
5C	1	5.2	ASTM/ASME	A/SA-508	22, Cl. 3	K21590		85/55 [585/380]	Forgings	2.25Cr-1Mo
5C	1	6.2	ASTM/ASME	A/SA-508	3V	K31830		85/60 [585/415]	Forgings	3Cr-1Mo-V-Ti-B
5C	1	6.2	ASTM/ASME	A/SA-508	3VCb	K31390		85/60 [585/415]	Forgings	3Cr-1Mo-0.25V-Cb-Ca
5C	1	5.2	ASTM/ASME	A/SA-541	22, Cl. 3	K21390		85/55 [585/380]	Forgings	2.25Cr-1Mo
5C	1	5.2	ASTM/ASME	A/SA-541	22V	K31835		85/60 [585/415]	Forgings	2.25Cr-1Mo-V
5C	1	6.2	ASTM/ASME	A/SA-541	3V	K31830		85/60 [585/415]	Forgings	3Cr-1Mo-V-Ti-B
5C	1	6.2	ASTM/ASME	A/SA-541	3VCb	K31390		85/60 [585/415]	Forgings	3Cr-1Mo-0.25V-Cb-Ca
5C	1	5.2	ASTM/ASME	A/SA-542	A, Cl. 4	K21590		85/55 [585/380]	Plate	2.25Cr-1Mo
5C	1	5.2	ASTM/ASME	A/SA-542	A, Cl. 4a	K21590		85/60 [585/415]	Plate	2.25Cr-1Mo
5C	1	5.2	ASTM/ASME	A/SA-542	B, Cl. 4	K21590		85/55 [585/380]	Plate	2.25Cr-1Mo
5C	1	5.2	ASTM/ASME	A/SA-542	B, Cl. 4a	K21590		85/60 [585/415]	Plate	2.25Cr-1Mo
5C	1	6.2	ASTM/ASME	A/SA-542	C, Cl. 4	K31830		85/55 [585/380]	Plate	3Cr-1Mo-V-Ti-B
5C	1	6.2	ASTM/ASME	A/SA-542	C, Cl. 4a	K31830		85/60 [585/415]	Plate	3Cr-1Mo-V-Ti-B
5C	1	6.3	ASTM/ASME	A/SA-542	D, Cl. 4a	K31835		85/60 [585/415]	Plate	2.25Cr-1Mo-V
5C	1	6.2	ASTM/ASME	A/SA-542	E, Cl. 4a	K31390		85/60 [585/415]	Plate	3Cr-1Mo-0.25V-Cb-Ca
5C	1	6.2	ASTM/ASME	A/SA-832	21V	K31830		85/60 [585/415]	Plate	3Cr-1Mo-V-Ti-B
5C	1	6.2	ASTM/ASME	A/SA-832	22V	K31835		85/60 [585/415]	Plate	2.25Cr-1Mo-V

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
5C	1	6.2	ASTM/ASME	A/SA-832	23V	—	85/60 [585/415]	Plate	3Cr-1Mo-0.25V-Cb-Ca	
5C	3	5.2	ASTM/ASME	A/SA-542	A, Cl. 3	K21590	95/75 [655/515]	Plate	2.25Cr-1Mo	
5C	3	5.2	ASTM/ASME	A/SA-542	B, Cl. 3	K21590	95/75 [655/515]	Plate	2.25Cr-1Mo	
5C	3	6.2	ASTM/ASME	A/SA-542	C, Cl. 3	K31830	95/75 [655/515]	Plate	3Cr-1Mo-V-Ti-B	
5C	4	5.2	ASTM/ASME	A/SA-487	8, Cl. B	J22091	105/85 [725/585]	Castings	2.25Cr-1Mo	
5C	4	5.2	ASTM/ASME	A/SA-487	8, Cl. C	J22091	100/75 [690/515]	Castings	2.25Cr-1Mo	
5C	4	5.2	ASTM/ASME	A/SA-541	22, Cl. 4	K21390	105/85 [725/585]	Forgings	2.25Cr-1Mo	
5C	4	5.2	ASTM/ASME	A/SA-542	A, Cl. 1	K21590	105/85 [725/585]	Plate	2.25Cr-1Mo	
5C	4	5.2	ASTM/ASME	A/SA-542	B, Cl. 1	K21590	105/85 [725/585]	Plate	2.25Cr-1Mo	
5C	4	6.2	ASTM/ASME	A/SA-542	C, Cl. 1	K31830	105/85 [725/585]	Plate	3Cr-1Mo-V-Ti-B	
5C	5	5.2	ASTM/ASME	A/SA-541	22, Cl. 5	K21390	115/100 [795/690]	Forgings	2.25Cr-1Mo	
5C	5	5.2	ASTM/ASME	A/SA-542	A, Cl. 2	K21590	115/100 [795/690]	Plate	2.25Cr-1Mo	
5C	5	5.2	ASTM/ASME	A/SA-542	B, Cl. 2	K21590	115/100 [795/690]	Plate	2.25Cr-1Mo	
5C	5	6.2	ASTM/ASME	A/SA-542	C, Cl. 2	K31830	115/100 [795/690]	Plate	3Cr-1Mo-V-Ti-B	
6	1	7.2	ASTM/ASME	A/SA-182	F6a, Cl. 1	S41000	70/40 [485/275]	Forgings	13Cr	
6	1	7.2	ASTM/ASME	A/SA-240	410	S41000	65/30 [450/205]	Plate, Sheet, & Strip	13Cr	
6	1	7.2	ASTM/ASME	A/SA-268	TP410	S41000	60/30 [415/205]	Seamless & Welded Tube	13Cr	
6	1	7.2	ASTM/ASME	A/SA-276	TP410	S41000	70/40 [485/275]	Bar	13Cr	
6	1	7.1	ASTM	A473	403	S40300	70/40 [485/275]	Forgings	12Cr	
6	1	7.2	ASTM	A473	410	S41000	70/40 [485/275]	Forgings	13Cr	
6	1	7.1	ASTM/ASME	A/SA-479	403	S40300	70/40 [485/275]	Bars & Shapes	12Cr	
6	1	7.2	ASTM/ASME	A/SA-479	410	S41000	70/40 [485/275]	Bars & Shapes	13Cr	
6	1	7.2	ASTM/ASME	A/SA-479	XM-30	S41040	70/40 [485/275]	Bars & Shapes	13Cr-Cb	
6	2	7.2	ASTM/ASME	A/SA-182	F429	S42900	60/35 [415/240]	Forgings	15Cr	
6	2	7.2	ASTM/ASME	A/SA-240	429	S42900	65/30 [450/205]	Plate, Sheet, & Strip	15Cr	
6	2	7.2	ASTM/ASME	A/SA-268	TP429	S42900	60/35 [415/240]	Seamless & Welded Tube	15Cr	
6	2	7.2	ASTM	A473	420	S42000	70/35 [485/240]	Forgings	13Cr	
6	2	7.2	ASTM	A473	429	S42900	65/35 [450/240]	Forgings	15Cr	
6	3	7.2	ASTM/ASME	A/SA-182	F6a, Cl. 2	S41000	85/55 [585/380]	Forgings	13Cr	

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
6	3	ASTM/ASME	A/SA-182	F6a, Cl. 3	S41000		110/85 [760/585]	Forgings	13Cr
6	3	ASTM/ASME	A/SA-182	F6a, Cl. 4	S41000		130/110 [895/760]	Forgings	13Cr
6	3	ASTM/ASME	A/SA-182	F6b	S41026		110/90 [760/620]	Forgings	13Cr-0.5Mo
6	3	ASTM/ASME	A/SA-217	CA15	J91150		90/65 [620/450]	Castings	13Cr
6	3	ASTM/ASME	A/SA-336	F6	S41000		85/55 [585/380]	Forgings	13Cr
6	3	ASTM	A351	CA15	J91150		90/- [620/-]	Castings	13Cr
6	3	ASTM/ASME	A/SA-426	CPCA15	J91150		90/65 [620/450]	Centrifugal Cast Pipe	13Cr
6	3	ASTM/ASME	A/SA-487	CA15 Cl. B	J91171		90/65 [620/450]	Castings	13Cr
6	3	ASTM/ASME	A/SA-487	CA15 Cl. C	J91150		90/60 [620/415]	Castings	13Cr
6	3	ASTM/ASME	A/SA-487	CA15 Cl. D	J91171		100/75 [690/515]	Castings	13Cr
6	3	ASTM/ASME	A/SA-487	CA15M Cl. A	J91151		90/65 [620/450]	Castings	13Cr-Mo
6	3	ASTM	A743	CA15	J91150		90/65 [620/450]	Castings	13Cr
6	3	ASTM	A743	CA15M	J91151		90/65 [620/450]	Castings	13Cr-Mo
6	4	ASTM/ASME	A/SA-182	F6NM	S41500		115/90 [795/620]	Forgings	13Cr-4.5Ni-Mo
6	4	ASTM/ASME	A/SA-240	S41500	S41500		115/90 [795/620]	Plate, Sheet, & Strip	13Cr-4.5Ni-Mo
6	4	ASTM/ASME	A/SA-268	S41500	S41500		115/90 [795/620]	Seamless & Welded Tube	13Cr-4.5Ni-Mo
6	4	ASTM/ASME	A/SA-352	CA6NM	J91540		110/80 [760/550]	Castings	13Cr-4Ni
6	4	ASTM	A473	414	S41400		65/35 [450/240]	Forgings	12.5Cr-2Ni-Si
6	4	ASTM/ASME	A/SA-479	414	S41400		115/90 [795/620]	Bars & Shapes	12.5Cr-2Ni-Si
6	4	ASTM/ASME	A/SA-479	S41500	S41500		115/90 [795/620]	Bars & Shapes	13Cr-4.5Ni-Mo
6	4	ASTM/ASME	A/SA-487	CA6NM, Cl. A	J91540		110/80 [760/550]	Castings	13Cr-4Ni
6	4	ASTM/ASME	A/SA-487	CA6NM, Cl. B	J91540		100/75 [690/515]	Castings	13Cr-4Ni
6	4	ASTM/ASME	A/SA-731	S41500	S41500		115/90 [795/620]	Seamless & Welded Pipe	13Cr-4.5Ni-Mo
6	4	ASTM	A743	CA40	J91153		100/70 [690/485]	Castings	13Cr
6	4	ASTM	A743	CA6NM	J91540		110/80 [760/550]	Castings	13Cr-4Ni
6	4	ASTM	A743	CB6	J91804		115/85 [795/585]	Castings	17Cr-5Ni
6	4	ASTM/ASME	A/SA-815	S41500	S41500		110/90 [760/620]	Fittings	13Cr-4.5Ni-Mo
7	1	ASTM/ASME	A/SA-240	405	S40500		60/25 [415/170]	Plate, Sheet, & Strip	12Cr-1Al
7	1	ASTM/ASME	A/SA-240	409	S40910		55/25 [380/170]	Plate, Sheet, & Strip	11Cr-Ti

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Steel and Steel Alloys									
7	1	7.1	ASTM/ASME A/SA-240	409	S40920		55/25 [380/170]	Plate, Sheet, & Strip	11Cr-Ti
7	1	7.1	ASTM/ASME A/SA-240	409	S40930		55/25 [380/170]	Plate, Sheet, & Strip	11Cr-Ti
7	1	7.2	ASTM/ASME A/SA-240	410S	S41008		60/30 [415/205]	Plate, Sheet, & Strip	13Cr
7	1	7.1	ASTM/ASME A/SA-268	S40800	S40800		55/30 [380/205]	Seamless & Welded Tube	12Cr-Ti
7	1	7.1	ASTM/ASME A/SA-268	TP405	S40500		60/30 [415/205]	Seamless & Welded Tube	12Cr-1Al
7	1	7.1	ASTM/ASME A/SA-268	TP409	S40900		55/25 [380/170]	Seamless & Welded Tube	11Cr-Ti
7	1	7.1	ASTM A473	405	S40500		60/30 [415/205]	Forgings	12Cr-1Al
7	1	7.1	ASTM/ASME A/SA-479	405	S40500		60/25 [415/170]	Bars & Shapes	12Cr-1Al
7	1	7.1	ASTM A743	CC50	J92615		55/- [380/-]	Castings	28Cr-3Ni
7	1	7.2	ASTM/ASME A/SA-1010	40	S41003		66/40 [455/275]	Plate, Sheet, & Strip	12Cr-1Ni
7	1	7.2	ASTM/ASME A/SA-1010	50	S41003		70/50 [485/350]	Plate, Sheet, & Strip	12Cr-1Ni
7	2	7.1	ASTM/ASME A/SA-182	F430	S43000		60/35 [415/240]	Forgings	17Cr
7	2	7.1	ASTM/ASME A/SA-240	430	S43000		65/30 [450/205]	Plate, Sheet, & Strip	17Cr
7	2	7.1	ASTM/ASME A/SA-240	439	S43035		60/30 [415/205]	Plate, Sheet, & Strip	18Cr-Ti
7	2	7.1	ASTM/ASME A/SA-240	S43932	S43932		60/30 [415/205]	Plate, Sheet, & Strip	18Cr-Ti-Cb
7	2	7.1	ASTM/ASME A/SA-240	S44400	S44400		60/40 [415/275]	Plate, Sheet, & Strip	18Cr-2Mo
7	2	7.1	ASTM/ASME A/SA-268	18Cr-2Mo	S44400		60/40 [415/275]	Seamless & Welded Tube	18Cr-2Mo
7	2	7.1	ASTM/ASME A/SA-268	TP430	S43000		60/35 [415/240]	Seamless & Welded Tube	17Cr
7	2	7.1	ASTM/ASME A/SA-268	TP430Ti	S43036		60/35 [415/240]	Seamless & Welded Tube	18Cr-Ti
7	2	7.1	ASTM/ASME A/SA-268	TP439	S43035		60/30 [415/205]	Seamless & Welded Tube	18Cr-Ti
7	2	7.1	ASTM A473	430	S43000		70/35 [485/240]	Forgings	17Cr
7	2	7.1	ASTM/ASME A/SA-479	430	S43000		70/40 [485/275]	Bars & Shapes	17Cr
7	2	7.1	ASTM/ASME A/SA-479	439	S43035		70/40 [485/275]	Bars & Shapes	18Cr-Ti
7	2	7.1	ASTM/ASME A/SA-479	S44400	S44400		60/45 [415/310]	Bars & Shapes	18Cr-2Mo
7	2	7.1	ASTM/ASME A/SA-731	18Cr-2Mo	S44400		60/40 [415/275]	Seamless & Welded Pipe	18Cr-2Mo
7	2	7.1	ASTM/ASME A/SA-731	TP439	S43035		60/30 [415/205]	Seamless & Welded Pipe	18Cr-Ti
7	2	7.1	ASTM/ASME A/SA-803	TP439	S43035		60/30 [415/205]	Welded Tube	18Cr-Ti
8	1	8.1	ASTM A167	302B	S30215		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-8Ni-2Si
8	1	8.1	ASTM/ASME A/SA-182	F304	S30400		75/30 [515/205]	Forgings	18Cr-8Ni

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	1	8.1	ASTM/ASME A/SA-182	F304	S30400	>5 [>127]	70/30 [485/205]	Forgings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-182	F304H	S30409	>5 [>127]	70/30 [485/205]	Forgings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-182	F304H	S30409		75/30 [515/205]	Forgings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-182	F304L	S30403		70/25 [485/170]	Forgings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-182	F304L	S30403	>5 [>127]	65/25 [450/170]	Forgings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-182	F304LN	S30453		75/30 [515/205]	Forgings	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-182	F304LN	S30453	>5 [>127]	70/30 [485/205]	Forgings	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-182	F304N	S30451		80/35 [550/240]	Forgings	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-182	F316	S31600		75/30 [515/205]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-182	F316	S31600	>5 [>127]	70/30 [485/205]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-182	F316H	S31609		75/30 [515/205]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-182	F316H	S31609	>5 [>127]	70/30 [485/205]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-182	F316L	S31603		70/25 [485/170]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-182	F316L	S31603	>5 [>127]	65/25 [450/170]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-182	F316LN	S31653	>5 [>127]	70/30 [485/205]	Forgings	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME A/SA-182	F316LN	S31653		75/30 [515/205]	Forgings	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME A/SA-182	F316N	S31651		80/35 [550/240]	Forgings	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME A/SA-182	F317	S31700	>5 [>127]	70/30 [485/205]	Forgings	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME A/SA-182	F317	S31700		75/30 [515/205]	Forgings	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME A/SA-182	F317L	S31703	>5 [>127]	65/25 [450/170]	Forgings	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME A/SA-182	F317L	S31703		70/25 [485/170]	Forgings	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME A/SA-182	F321	S32100		75/30 [515/205]	Forgings	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-182	F321	S32100	>5 [>127]	70/30 [485/205]	Forgings	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-182	F321H	S32109		75/30 [515/205]	Forgings	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-182	F321H	S32109	>5 [>127]	70/30 [485/205]	Forgings	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-182	F347	S34700		75/30 [515/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-182	F347	S34700	>5 [>127]	70/30 [485/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-182	F347H	S34709	>5 [>127]	70/30 [485/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-182	F347H	S34709		75/30 [515/205]	Forgings	18Cr-10Ni-Cb

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	1	8.1	ASTM/ASME	A/SA-182	F348	S34800		75/30 [515/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-182	F348	S34800	>5 [>127]	70/30 [485/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-182	F348H	S34809	>5 [>127]	70/30 [485/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-182	F348H	S34809		75/30 [515/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-182	F46	S30600		78/35 [540/240]	Forgings	18Cr-15Ni-4Si
8	1	8.1	ASTM/ASME	A/SA-213	S32615	S32615		80/32 [550/220]	Seamless Tube	18Cr-20Ni-5.5Si
8	1	8.1	ASTM/ASME	A/SA-213	TP304	S30400		75/30 [515/205]	Seamless Tube	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-213	TP304H	S30409		75/30 [515/205]	Seamless Tube	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-213	TP304L	S30403		70/25 [485/170]	Seamless Tube	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-213	TP304LN	S30453		75/30 [515/205]	Seamless Tube	18Cr-8Ni-N
8	1	8.1	ASTM/ASME	A/SA-213	TP304N	S30451		80/35 [550/240]	Seamless Tube	18Cr-8Ni-N
8	1	8.1	ASTM/ASME	A/SA-213	TP316	S31600		75/30 [515/205]	Seamless Tube	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-213	TP316H	S31609		75/30 [515/205]	Seamless Tube	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-213	TP316L	S31603		70/25 [485/170]	Seamless Tube	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-213	TP316LN	S31653		75/30 [515/205]	Seamless Tube	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME	A/SA-213	TP316N	S31651		80/35 [550/240]	Seamless Tube	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM	A213	TP316Ti	S31635		75/30 [515/205]	Seamless Tube	16Cr-12Ni-2Mo-Ti
8	1	8.1	ASTM	A213	TP317	S31700		75/30 [515/205]	Seamless Tube	18Cr-13Ni-3Mo
8	1	8.1	ASTM	A213	TP317L	S31703		75/30 [515/205]	Seamless Tube	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME	A/SA-213	TP321	S32100		75/30 [515/205]	Seamless Tube	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME	A/SA-213	TP321H	S32109		75/30 [515/205]	Seamless Tube	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME	A/SA-213	TP347	S34700		75/30 [515/205]	Seamless Tube	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-213	TP347H	S34709		75/30 [515/205]	Seamless Tube	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-213	TP347HFG	S34710		80/30 [550/205]	Seamless Tube	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-213	TP347LN	S34751		75/30 [515/205]	Seamless Tube	18Cr-10Ni-Cb-N
8	1	8.1	ASTM/ASME	A/SA-213	TP348	S34800		75/30 [515/205]	Seamless Tube	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-213	TP348H	S34809		75/30 [515/205]	Seamless Tube	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-213	XM-15	S38100		75/30 [515/205]	Seamless Tube	18Cr-18Ni-2Si
8	1	8.1	ASTM/ASME	A/SA-240	301	S30100		75/30 [515/205]	Plate, Sheet, & Strip	17Cr-7Ni

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	1	8.1	ASTM/ASME	A/SA-240	302	S30200		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-240	304	S30400		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-240	304H	S30409		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-240	304L	S30403		70/25 [485/170]	Plate, Sheet, & Strip	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-240	304LN	S30453		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-8Ni-N
8	1	8.1	ASTM/ASME	A/SA-240	304N	S30451		80/35 [550/240]	Plate, Sheet, & Strip	18Cr-8Ni-N
8	1	8.1	ASTM/ASME	A/SA-240	305	S30500		70/25 [485/170]	Plate, Sheet, & Strip	18Cr-11Ni
8	1	8.1	ASTM/ASME	A/SA-240	316	S31600		75/30 [515/205]	Plate, Sheet, & Strip	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-240	316Cb	S31640		75/30 [515/205]	Plate, Sheet, & Strip	16Cr-12Ni-2Mo-Cb
8	1	8.1	ASTM/ASME	A/SA-240	316H	S31609		75/30 [515/205]	Plate, Sheet, & Strip	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-240	316L	S31603		70/25 [485/170]	Plate, Sheet, & Strip	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-240	316LN	S31653		75/30 [515/205]	Plate, Sheet, & Strip	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME	A/SA-240	316N	S31651		80/35 [550/240]	Plate, Sheet, & Strip	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME	A/SA-240	316Ti	S31635		75/30 [515/205]	Plate, Sheet, & Strip	16Cr-12Ni-2Mo-Ti
8	1	8.1	ASTM/ASME	A/SA-240	317	S31700		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME	A/SA-240	317L	S31703		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME	A/SA-240	321	S32100		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME	A/SA-240	321H	S32109		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME	A/SA-240	347	S34700		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-240	347H	S34709		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-240	348	S34800		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-240	348H	S34809		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-240	S30600	S30600		78/35 [540/240]	Plate, Sheet, & Strip	18Cr-15Ni-4Si
8	1	8.1	ASTM/ASME	A/SA-240	S30601	S30601		78/37 [540/255]	Plate, Sheet, & Strip	17.5Cr-17.5Ni-5.3Si
8	1	8.1	ASTM/ASME	A/SA-240	S31753	S31753		80/35 [550/240]	Plate, Sheet, & Strip	18Cr-13Ni-3Mo-N
8	1	8.1	ASTM/ASME	A/SA-240	S32615	S32615		80/32 [550/220]	Plate, Sheet, & Strip	18Cr-20Ni-5.5Si
8	1	8.1	ASTM/ASME	A/SA-240	XM-15	S38100		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-18Ni-2Si
8	1	8.1	ASTM/ASME	A/SA-240	XM-21	S30452		85/40 [585/275]	Plate	18Cr-8Ni-N
8	1	8.1	ASTM/ASME	A/SA-240	XM-21	S30452		90/50 [620/345]	Sheet & Strip	18Cr-8Ni-N

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group 15608 Number	Group Number	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	8.1	1	ASTM/ASME	A/SA-249	TP XM-15	S38100		75/30 [515/205]	Welded Tube	18Cr-18Ni-2Si
8	8.1	1	ASTM/ASME	A/SA-249	TP304	S30400		75/30 [515/205]	Welded Tube	18Cr-8Ni
8	8.1	1	ASTM/ASME	A/SA-249	TP304H	S30409		75/30 [515/205]	Welded Tube	18Cr-8Ni
8	8.1	1	ASTM/ASME	A/SA-249	TP304L	S30403		70/25 [485/170]	Welded Tube	18Cr-8Ni
8	8.1	1	ASTM/ASME	A/SA-249	TP304LN	S30453		75/30 [515/205]	Welded Tube	18Cr-8Ni-N
8	8.1	1	ASTM/ASME	A/SA-249	TP304N	S30451		80/35 [550/240]	Welded Tube	18Cr-8Ni-N
8	8.1	1	ASTM/ASME	A/SA-249	TP316	S31600		75/30 [515/205]	Welded Tube	16Cr-12Ni-2Mo
8	8.1	1	ASTM/ASME	A/SA-249	TP316H	S31609		75/30 [515/205]	Welded Tube	16Cr-12Ni-2Mo
8	8.1	1	ASTM/ASME	A/SA-249	TP316L	S31603		70/25 [485/170]	Welded Tube	16Cr-12Ni-2Mo
8	8.1	1	ASTM/ASME	A/SA-249	TP316LN	S31653		75/30 [515/205]	Welded Tube	16Cr-12Ni-2Mo-N
8	8.1	1	ASTM/ASME	A/SA-249	TP316N	S31651		80/35 [550/240]	Welded Tube	16Cr-12Ni-2Mo-N
8	8.1	1	ASTM/ASME	A/SA-249	TP317	S31700		75/30 [515/205]	Welded Tube	18Cr-13Ni-3Mo
8	8.1	1	ASTM/ASME	A/SA-249	TP317L	S31703		75/30 [515/205]	Welded Tube	18Cr-13Ni-3Mo
8	8.1	1	ASTM/ASME	A/SA-249	TP321	S32100		75/30 [515/205]	Welded Tube	18Cr-10Ni-Ti
8	8.1	1	ASTM/ASME	A/SA-249	TP321H	S32109		75/30 [515/205]	Welded Tube	18Cr-10Ni-Ti
8	8.1	1	ASTM/ASME	A/SA-249	TP347	S34700		75/30 [515/205]	Welded Tube	18Cr-10Ni-Cb
8	8.1	1	ASTM/ASME	A/SA-249	TP347H	S34709		75/30 [515/205]	Welded Tube	18Cr-10Ni-Cb
8	8.1	1	ASTM/ASME	A/SA-249	TP348	S34800		75/30 [515/205]	Welded Tube	18Cr-10Ni-Cb
8	8.1	1	ASTM/ASME	A/SA-249	TP348H	S34809		75/30 [515/205]	Welded Tube	18Cr-10Ni-Cb
8	8.1	1	ASTM	A269	TP304	S30400		-/- [-/-]	Seamless & Welded Tube	18Cr-8Ni
8	8.1	1	ASTM	A269	TP304L	S30403		-/- [-/-]	Seamless & Welded Tube	18Cr-8Ni
8	8.1	1	ASTM	A269	TP304LN	S30453		75/30 [515/205]	Seamless & Welded Tube	18Cr-8Ni-N
8	8.1	1	ASTM	A269	TP316	S31600		-/- [-/-]	Seamless & Welded Tube	16Cr-12Ni-2Mo
8	8.1	1	ASTM	A269	TP316L	S31603		-/- [-/-]	Seamless & Welded Tube	16Cr-12Ni-2Mo
8	8.1	1	ASTM	A269	TP316LN	S31653		75/30 [515/205]	Seamless & Welded Tube	16Cr-12Ni-2Mo-N
8	8.1	1	ASTM	A269	TP317	S31700		75/30 [515/205]	Seamless & Welded Tube	18Cr-13Ni-3Mo
8	8.1	1	ASTM	A269	TP321	S32100		75/30 [515/205]	Seamless & Welded Tube	18Cr-10Ni-Ti
8	8.1	1	ASTM	A269	TP347	S34700		75/30 [515/205]	Seamless & Welded Tube	18Cr-10Ni-Cb
8	8.1	1	ASTM	A269	TP348	S34800		75/30 [515/205]	Seamless & Welded Tube	18Cr-10Ni-Cb

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	1	8.1	ASTM	A270	TP304	S30400		75/30 [515/205]	Seamless & Welded Tube	18Cr-8Ni
8	1	8.1	ASTM	A271	TP304	S30400		75/30 [515/205]	Seamless Tube	18Cr-8Ni
8	1	8.1	ASTM	A271	TP304H	S30409		75/30 [515/205]	Seamless Tube	18Cr-8Ni
8	1	8.1	ASTM	A271	TP316	S31600		75/30 [515/205]	Seamless Tube	16Cr-12Ni-2Mo
8	1	8.1	ASTM	A271	TP316H	S31609		75/30 [515/205]	Seamless Tube	16Cr-12Ni-2Mo
8	1	8.1	ASTM	A271	TP321	S32100		75/30 [515/205]	Seamless Tube	18Cr-10Ni-Ti
8	1	8.1	ASTM	A271	TP321H	S32109		75/30 [515/205]	Seamless Tube	18Cr-10Ni-Ti
8	1	8.1	ASTM	A271	TP347	S34700		75/30 [515/205]	Seamless Tube	18Cr-10Ni-Cb
8	1	8.1	ASTM	A271	TP347H	S34709		75/30 [515/205]	Seamless Tube	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-276	TP304	S30400		75/30 [515/205]	Bar	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-276	TP304L	S30403		70/25 [485/170]	Bar	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-276	TP316	S31600		75/30 [515/205]	Bar	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-276	TP316L	S31603		70/25 [485/170]	Bar	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-312	S30600	S30600		78/35 [540/240]	Seamless & Welded Pipe	18Cr-15Ni-4Si
8	1	8.1	ASTM/ASME	A/SA-312	S32615	S32615		80/32 [550/220]	Seamless & Welded Pipe	18Cr-20Ni-5.5Si
8	1	8.1	ASTM/ASME	A/SA-312	TP XM-15	S38100		75/30 [515/205]	Seamless & Welded Pipe	18Cr-18Ni-2Si
8	1	8.1	ASTM/ASME	A/SA-312	TP304	S30400		75/30 [515/205]	Seamless & Welded Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-312	TP304H	S30409		75/30 [515/205]	Seamless & Welded Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-312	TP304L	S30403		70/25 [485/170]	Seamless & Welded Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-312	TP304LN	S30453		75/30 [515/205]	Seamless & Welded Pipe	18Cr-8Ni-N
8	1	8.1	ASTM/ASME	A/SA-312	TP304N	S30451		80/35 [550/240]	Seamless & Welded Pipe	18Cr-8Ni-N
8	1	8.1	ASTM/ASME	A/SA-312	TP316	S31600		75/30 [515/205]	Seamless & Welded Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-312	TP316H	S31609		75/30 [515/205]	Seamless & Welded Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-312	TP316L	S31603		70/25 [485/170]	Seamless & Welded Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-312	TP316LN	S31653		75/30 [515/205]	Seamless & Welded Pipe	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME	A/SA-312	TP316N	S31651		80/35 [550/240]	Seamless & Welded Pipe	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM	A312	TP316Ti	S31635		75/30 [515/205]	Seamless & Welded Pipe	16Cr-12Ni-2Mo-Ti
8	1	8.1	ASTM/ASME	A/SA-312	TP317	S31700		75/30 [515/205]	Seamless & Welded Pipe	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME	A/SA-312	TP317L	S31703		75/30 [515/205]	Seamless & Welded Pipe	18Cr-13Ni-3Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	1	8.1	ASTM/ASME A/SA-312	TP321	S32100	≤0.375 [≤10]	75/30 [515/205]	Seamless Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-312	TP321	S32100	>0.375 [>10]	70/25 [485/170]	Seamless Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-312	TP321H	S32109	>0.375 [>10]	70/25 [485/170]	Seamless Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-312	TP321H	S32109	≤0.375 [≤10]	75/30 [515/205]	Seamless Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-312	TP347	S34700		75/30 [515/205]	Seamless & Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-312	TP347H	S34709		75/30 [515/205]	Seamless & Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-312	TP347LN	S34751		75/30 [515/205]	Seamless & Welded Pipe	18Cr-10Ni-Cb-N
8	1	8.1	ASTM/ASME A/SA-312	TP348	S34800		75/30 [515/205]	Seamless & Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-312	TP348H	S34809		75/30 [515/205]	Seamless & Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-336	F304	S30400		70/30 [485/205]	Forgings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-336	F304H	S30409		70/30 [485/205]	Forgings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-336	F304L	S30403		65/25 [450/170]	Forgings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-336	F304LN	S30453		70/30 [485/205]	Forgings	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-336	F304N	S30451		80/35 [550/240]	Forgings	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-336	F316	S31600		70/30 [485/205]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-336	F316H	S31609		70/30 [485/205]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-336	F316L	S31603		65/25 [450/170]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-336	F316LN	S31653		70/30 [485/205]	Forgings	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME A/SA-336	F316N	S31651		80/35 [550/240]	Forgings	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME A/SA-336	F321	S32100		70/30 [485/205]	Forgings	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-336	F321H	S32109		70/30 [485/205]	Forgings	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-336	F347	S34700		70/30 [485/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-336	F347H	S34709		70/30 [485/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-336	F348	S34800		70/30 [485/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-336	F348H	S34809		65/25 [450/170]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-336	F46	S30600		78/32 [540/220]	Forgings	18Cr-15Ni-4Si
8	1	8.1	ASTM/ASME A/SA-351	CF10	J92590		70/30 [485/205]	Castings	19Cr-9Ni-0.5Mo
8	1	8.1	ASTM/ASME A/SA-351	CF10M	J92901		70/30 [485/205]	Castings	19Cr-9Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-351	CF10MC	J92971		70/30 [485/205]	Castings	16Cr-14Ni-2Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	1	8.1	ASTM/ASME A/SA-351	CF3	J92500		70/30 [485/205]	Castings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-351	CF3A	J92500		77/35 [530/240]	Castings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-351	CF3M	J92800		70/30 [485/205]	Castings	18Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-351	CF8	J92600		70/30 [485/205]	Castings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-351	CF8A	J92600		77/35 [530/240]	Castings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-351	CF8C	J92710		70/30 [485/205]	Castings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-351	CF8M	J92900		70/30 [485/205]	Castings	18Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-351	CG8M	J93000		75/35 [515/240]	Castings	19Cr-10Ni-3Mo
8	1	8.1	ASTM/ASME A/SA-358	304	S30400		75/30 [515/205]	Fusion Welded Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-358	304H	S30409		75/30 [515/205]	Fusion Welded Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-358	304L	S30403		70/25 [485/170]	Fusion Welded Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-358	304LN	S30453		75/30 [515/205]	Fusion Welded Pipe	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-358	304N	S30451		80/35 [550/240]	Fusion Welded Pipe	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-358	316	S31600		75/30 [515/205]	Fusion Welded Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-358	316H	S31609		75/30 [515/205]	Fusion Welded Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-358	316L	S31603		70/25 [485/170]	Fusion Welded Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-358	316LN	S31653		75/30 [515/205]	Fusion Welded Pipe	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME A/SA-358	316N	S31651		80/35 [550/240]	Fusion Welded Pipe	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME A/SA-358	321	S32100		75/30 [515/205]	Fusion Welded Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-358	347	S34700		75/30 [515/205]	Fusion Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-358	348	S34800		75/30 [515/205]	Fusion Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-376	16-8-2H	S16800		75/30 [515/205]	Seamless Pipe	16Cr-8Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-376	TP304	S30400	≥0.812 [≥21]	70/30 [485/205]	Seamless Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-376	TP304	S30400	<0.812 [<21]	75/30 [515/205]	Seamless Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-376	TP304H	S30409		75/30 [515/205]	Seamless Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-376	TP304LN	S30453		75/30 [515/205]	Seamless Pipe	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-376	TP304N	S30451		80/35 [550/240]	Seamless Pipe	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-376	TP316	S31600		75/30 [515/205]	Seamless Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-376	TP316H	S31609		75/30 [515/205]	Seamless Pipe	16Cr-12Ni-2Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Steel and Steel Alloys									
8	1	8.1	ASTM/ASME A/SA-376	TP316LN	S31653		75/30 [515/205]	Seamless Pipe	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME A/SA-376	TP316N	S31651		80/35 [550/240]	Seamless Pipe	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME A/SA-376	TP321	S32100	≤0.375 [≤10]	75/30 [515/205]	Seamless Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-376	TP321	S32100	>0.375 [>10]	70/25 [485/170]	Seamless Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-376	TP321H	S32109	≤0.375 [≤10]	75/30 [515/205]	Seamless Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-376	TP321H	S32109	>0.375 [>10]	70/25 [485/170]	Seamless Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-376	TP347	S34700		75/30 [515/205]	Seamless Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-376	TP347H	S34709		75/30 [515/205]	Seamless Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-376	TP348	S34800		75/30 [515/205]	Seamless Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-403	WP304	S30400		75/30 [515/205]	Wrought Piping Fittings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-403	WP304H	S30409		75/30 [515/205]	Wrought Piping Fittings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-403	WP304L	S30403		70/25 [485/170]	Wrought Piping Fittings	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-403	WP304LN	S30453		75/30 [515/205]	Wrought Piping Fittings	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-403	WP304N	S30451		80/35 [550/240]	Wrought Piping Fittings	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-403	WP316	S31600		75/30 [515/205]	Wrought Piping Fittings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-403	WP316H	S31609		75/30 [515/205]	Wrought Piping Fittings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-403	WP316L	S31603		70/25 [485/170]	Wrought Piping Fittings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-403	WP316LN	S31653		75/30 [515/205]	Wrought Piping Fittings	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME A/SA-403	WP316N	S31651		80/35 [550/240]	Wrought Piping Fittings	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME A/SA-403	WP317	S31700		75/30 [515/205]	Wrought Piping Fittings	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME A/SA-403	WP317L	S31703		75/30 [515/205]	Wrought Piping Fittings	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME A/SA-403	WP321	S32100		75/30 [515/205]	Wrought Piping Fittings	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-403	WP321H	S32109		75/30 [515/205]	Wrought Piping Fittings	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-403	WP347	S34700		75/30 [515/205]	Wrought Piping Fittings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-403	WP347H	S34709		75/30 [515/205]	Wrought Piping Fittings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-403	WP348	S34800		75/30 [515/205]	Wrought Piping Fittings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-403	WP348H	S34809		75/30 [515/205]	Wrought Piping Fittings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-409	TP304	S30400		75/30 [515/205]	Welded Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-409	TP304L	S30403		70/25 [485/170]	Welded Pipe	18Cr-8Ni

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	1	8.1	ASTM/ASME A/SA-409	TP316	S31600		75/30 [515/205]	Welded Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-409	TP316L	S31603		70/25 [485/170]	Welded Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-409	TP317	S31700		75/30 [515/205]	Welded Pipe	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME A/SA-409	TP321	S32100		75/30 [515/205]	Welded Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-409	TP347	S34700		75/30 [515/205]	Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-409	TP348	S34800		75/30 [515/205]	Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM A430	FP16-8-2H	S16800		70/30 [485/205]	Forged Pipe	16Cr-8Ni-2Mo
8	1	8.1	ASTM A430	FP304	S30400		70/30 [485/205]	Forged Pipe	18Cr-8Ni
8	1	8.1	ASTM A430	FP304H	S30409		70/30 [485/205]	Forged Pipe	18Cr-8Ni
8	1	8.1	ASTM A430	FP304N	S30451		75/35 [515/240]	Forged Pipe	18Cr-8Ni-N
8	1	8.1	ASTM A430	FP316	S31600		70/30 [485/205]	Forged Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM A430	FP316H	S31609		70/30 [485/205]	Forged Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM A430	FP316N	S31651		75/35 [515/240]	Forged Pipe	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM A430	FP321	S32100		70/30 [485/205]	Forged Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM A430	FP321H	S32109		70/30 [485/205]	Forged Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM A430	FP347	S34700		70/30 [485/205]	Forged Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM A430	FP347H	S34709		70/30 [485/205]	Forged Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-451	CPF10MC	J92971		70/30 [485/205]	Centrifugal Cast Pipe	16Cr-14Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-451	CPF3	J92500		70/30 [485/205]	Centrifugal Cast Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-451	CPF3A	J92500		77/35 [530/240]	Centrifugal Cast Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-451	CPF3M	J92800		70/30 [485/205]	Centrifugal Cast Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-451	CPF8	J92600		70/30 [485/205]	Centrifugal Cast Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-451	CPF8A	J92600		77/35 [530/240]	Centrifugal Cast Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-451	CPF8C	J92710		70/30 [485/205]	Centrifugal Cast Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-451	CPF8M	J92900		70/30 [485/205]	Centrifugal Cast Pipe	18Cr-12Ni-2Mo
8	1	8.1	ASTM A452	TP304H	S30409		75/30 [515/205]	Centrifugal Cast Pipe	18Cr-8Ni
8	1	8.1	ASTM A452	TP316H	S31609		75/30 [515/205]	Centrifugal Cast Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM A452	TP347H	S34709		75/30 [515/205]	Centrifugal Cast Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM A473	302	S30200		75/30 [515/205]	Forgings	18Cr-8Ni

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	1	8.1	ASTM	A473	302B	S30215	75/30 [515/205]	Forgings	18Cr-8Ni-2Si
8	1	8.1	ASTM	A473	303	S30300	75/30 [515/205]	Forgings	18Cr-8Ni-S
8	1	8.1	ASTM	A473	303Se	S30323	75/30 [515/205]	Forgings	18Cr-8Ni-Se
8	1	8.1	ASTM	A473	304	S30400	70/30 [485/205]	Forgings	18Cr-8Ni
8	1	8.1	ASTM	A473	304	S30400	75/30 [515/205]	Forgings	18Cr-8Ni
8	1	8.1	ASTM	A473	304L	S30403	65/25 [450/170]	Forgings	18Cr-8Ni
8	1	8.1	ASTM	A473	305	S30500	75/30 [515/205]	Forgings	18Cr-11Ni
8	1	8.1	ASTM	A473	316	S31600	70/30 [485/205]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM	A473	316	S31600	75/30 [515/205]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM	A473	316L	S31603	65/25 [450/170]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM	A473	317	S31700	75/30 [515/205]	Forgings	18Cr-13Ni-3Mo
8	1	8.1	ASTM	A473	321	S32100	75/30 [515/205]	Forgings	18Cr-10Ni-Ti
8	1	8.1	ASTM	A473	347	S34700	75/30 [515/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM	A473	348	S34800	75/30 [515/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-479	302	S30200	75/30 [515/205]	Bars & Shapes	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-479	304	S30400	75/30 [515/205]	Bars & Shapes	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-479	304H	S30409	75/30 [515/205]	Bars & Shapes	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-479	304L	S30403	70/25 [485/170]	Bars & Shapes	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-479	304LN	S30453	75/30 [515/205]	Bars & Shapes	18Cr-8Ni-N
8	1	8.1	ASTM/ASME	A/SA-479	304N	S30451	80/35 [550/240]	Bars & Shapes	18Cr-8Ni-N
8	1	8.1	ASTM/ASME	A/SA-479	316	S31600	75/30 [515/205]	Bars & Shapes	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-479	316Cb	S31640	75/30 [515/205]	Bars & Shapes	16Cr-12Ni-2Mo-Cb
8	1	8.1	ASTM/ASME	A/SA-479	316H	S31609	75/30 [515/205]	Bars & Shapes	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-479	316L	S31603	70/25 [485/170]	Bars & Shapes	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-479	316LN	S31653	75/30 [515/205]	Bars & Shapes	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME	A/SA-479	316N	S31651	80/35 [550/240]	Bars & Shapes	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME	A/SA-479	316Ti	S31635	75/30 [515/205]	Bars & Shapes	16Cr-12Ni-2Mo-Ti
8	1	8.1	ASTM/ASME	A/SA-479	321	S32100	75/30 [515/205]	Bars & Shapes	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME	A/SA-479	321H	S32109	75/30 [515/205]	Bars & Shapes	18Cr-10Ni-Ti

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group	ISO 15608	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	1	8.1	ASTM/ASME	A/SA-479	347	S34700		75/30 [515/205]	Bars & Shapes	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-479	347H	S34709		75/30 [515/205]	Bars & Shapes	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-479	348	S34800		75/30 [515/205]	Bars & Shapes	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-479	348H	S34809		75/30 [515/205]	Bars & Shapes	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-479	S30600	S30600		78/35 [540/240]	Bars & Shapes	18Cr-15Ni-4Si
8	1	8.1	ASTM/ASME	A/SA-479	S32615	S32615		80/32 [550/220]	Bars & Shapes	18Cr-20Ni-5.5Si
8	1	8.1	ASTM	A511	MT 302	S30200		75/30 [515/205]	Seamless Tube	18Cr-8Ni
8	1	8.1	ASTM	A511	MT 304	S30400		75/30 [515/205]	Seamless Tube	18Cr-8Ni
8	1	8.1	ASTM	A511	MT 304L	S30403		75/30 [515/205]	Seamless Tube	18Cr-8Ni
8	1	8.1	ASTM	A511	MT 316	S31600		75/30 [515/205]	Seamless Tube	16Cr-12Ni-2Mo
8	1	8.1	ASTM	A511	MT 316L	S31603		75/30 [515/205]	Seamless Tube	16Cr-12Ni-2Mo
8	1	8.1	ASTM	A511	MT 317	S31700		75/30 [515/205]	Seamless Tube	18Cr-13Ni-3Mo
8	1	8.1	ASTM	A511	MT 321	S32100		75/30 [515/205]	Seamless Tube	18Cr-10Ni-Ti
8	1	8.1	ASTM	A511	MT 347	S34700		75/30 [515/205]	Seamless Tube	18Cr-10Ni-Cb
8	1	8.1	ASTM	A554	MT 302	S30200		75/30 [515/205]	Welded Tube	18Cr-8Ni
8	1	8.1	ASTM	A554	MT 304	S30400		75/30 [515/205]	Welded Tube	18Cr-8Ni
8	1	8.1	ASTM	A554	MT 304L	S30403		70/25 [485/170]	Welded Tube	18Cr-8Ni
8	1	8.1	ASTM	A554	MT 316	S31600		75/30 [515/205]	Welded Tube	16Cr-12Ni-2Mo
8	1	8.1	ASTM	A554	MT 316L	S31603		70/25 [485/170]	Welded Tube	16Cr-12Ni-2Mo
8	1	8.1	ASTM	A554	MT 317	S31700		75/30 [515/205]	Welded Tube	18Cr-13Ni-3Mo
8	1	8.1	ASTM	A554	MT 321	S32100		75/30 [515/205]	Welded Tube	18Cr-10Ni-Ti
8	1	8.1	ASTM	A554	MT 347	S34700		75/30 [515/205]	Welded Tube	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-666	302	S30200		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-666	304	S30400		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-666	304L	S30403		70/25 [485/170]	Plate, Sheet, & Strip	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-666	304LN	S30453		75/30 [515/205]	Plate, Sheet, & Strip	18Cr-8Ni-N
8	1	8.1	ASTM/ASME	A/SA-666	304N	S30451		80/35 [550/240]	Plate, Sheet, & Strip	18Cr-8Ni-N
8	1	8.1	ASTM/ASME	A/SA-666	316	S31600		75/30 [515/205]	Plate, Sheet, & Strip	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-666	316L	S31603		70/25 [485/170]	Plate, Sheet, & Strip	16Cr-12Ni-2Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	1	ASTM/ASME	A/SA-666	316N	S31651		80/35 [550/240]	Plate, Sheet, & Strip	16Cr-12Ni-2Mo-N
8	1	ASTM/ASME	A/SA-688	TP304	S30400		75/30 [515/205]	Welded Tube	18Cr-8Ni
8	1	ASTM/ASME	A/SA-688	TP304L	S30403		70/25 [485/170]	Welded Tube	18Cr-8Ni
8	1	ASTM/ASME	A/SA-688	TP304LN	S30453		75/30 [515/205]	Welded Tube	18Cr-8Ni-N
8	1	ASTM/ASME	A/SA-688	TP304N	S30451		80/35 [550/240]	Welded Tube	18Cr-8Ni-N
8	1	ASTM/ASME	A/SA-688	TP316	S31600		75/30 [515/205]	Welded Tube	16Cr-12Ni-2Mo
8	1	ASTM/ASME	A/SA-688	TP316L	S31603		70/25 [485/170]	Welded Tube	16Cr-12Ni-2Mo
8	1	ASTM/ASME	A/SA-688	TP316LN	S31653		75/30 [515/205]	Welded Tube	16Cr-12Ni-2Mo-N
8	1	ASTM/ASME	A/SA-688	TP316N	S31651		80/35 [550/240]	Welded Tube	16Cr-12Ni-2Mo-N
8	1	ASTM	A743	CF10SMnN	J92972		85/42 [585/290]	Castings	17Cr-9Ni-8Mn-4Si-N
8	1	ASTM	A743	CF16F	J92701		70/30 [485/205]	Castings	20Cr-11Ni-0.3Se
8	1	ASTM	A743	CF3	J92500		70/30 [485/205]	Castings	18Cr-8Ni
8	1	ASTM	A743	CF3M	J92800		70/30 [485/205]	Castings	18Cr-12Ni-2Mo
8	1	ASTM	A743	CF3MIN	J92804		75/37 [515/255]	Castings	20Cr-11Ni-3Mo-N
8	1	ASTM	A743	CF8	J92600		70/30 [485/205]	Castings	18Cr-8Ni
8	1	ASTM	A743	CF8C	J92710		70/30 [485/205]	Castings	18Cr-10Ni-Cb
8	1	ASTM	A743	CF8M	J92900		70/30 [485/205]	Castings	18Cr-12Ni-2Mo
8	1	ASTM	A743	CG3M	J92999		75/35 [515/240]	Castings	19Cr-11Ni-4Mo
8	1	ASTM	A743	CG8M	J93000		75/35 [515/240]	Castings	19Cr-10Ni-3Mo
8	1	ASTM	A774	304L	S30403		70/25 [485/170]	Wrought Piping Fittings	18Cr-8Ni
8	1	ASTM	A774	316L	S31603		70/25 [485/170]	Wrought Piping Fittings	16Cr-12Ni-2Mo
8	1	ASTM	A774	321	S32100		75/30 [515/205]	Wrought Piping Fittings	18Cr-10Ni-Ti
8	1	ASTM	A774	347	S34700		75/30 [515/205]	Wrought Piping Fittings	18Cr-10Ni-Cb
8	1	ASTM	A774	F317L	S31703		75/30 [515/205]	Wrought Piping Fittings	18Cr-13Ni-3Mo
8	1	ASTM	A778	304L	S30403		70/25 [485/170]	Welded Unannealed Tube	18Cr-8Ni
8	1	ASTM	A778	316L	S31603		70/25 [485/170]	Welded Unannealed Tube	16Cr-12Ni-2Mo
8	1	ASTM	A778	321	S32100		75/30 [515/205]	Welded Unannealed Tube	18Cr-10Ni-Ti
8	1	ASTM	A778	347	S34700		75/30 [515/205]	Welded Unannealed Tube	18Cr-10Ni-Cb
8	1	ASTM	A778	F317L	S31703		75/30 [515/205]	Welded Unannealed Tube	18Cr-13Ni-3Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	1	8.1	ASTM/ASME A/SA-813	TP304	S30400		75/30 [515/205]	Welded Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-813	TP304H	S30409		75/30 [515/205]	Welded Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-813	TP304L	S30403		70/25 [485/170]	Welded Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-813	TP304LN	S30453		75/30 [515/205]	Welded Pipe	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-813	TP304N	S30451		80/35 [550/240]	Welded Pipe	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-813	TP316	S31600		75/30 [515/205]	Welded Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-813	TP316H	S31609		75/30 [515/205]	Welded Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-813	TP316L	S31603		70/25 [485/170]	Welded Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-813	TP316LN	S31653		75/30 [515/205]	Welded Pipe	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME A/SA-813	TP316N	S31651		80/35 [550/240]	Welded Pipe	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME A/SA-813	TP317	S31700		75/30 [515/205]	Welded Pipe	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME A/SA-813	TP317L	S31703		75/30 [515/205]	Welded Pipe	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME A/SA-813	TP321	S32100		75/30 [515/205]	Welded Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-813	TP321H	S32109		75/30 [515/205]	Welded Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME A/SA-813	TP347	S34700		75/30 [515/205]	Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-813	TP347H	S34709		75/30 [515/205]	Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-813	TP348	S34800		75/30 [515/205]	Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-813	TP348H	S34809		75/30 [515/205]	Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME A/SA-813	TPXM-15	S38100		75/30 [515/205]	Welded Pipe	18Cr-18Ni-2Si
8	1	8.1	ASTM/ASME A/SA-814	TP304	S30400		75/30 [515/205]	Cold Worked Welded Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-814	TP304H	S30409		75/30 [515/205]	Cold Worked Welded Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-814	TP304L	S30403		70/25 [485/170]	Cold Worked Welded Pipe	18Cr-8Ni
8	1	8.1	ASTM/ASME A/SA-814	TP304LN	S30453		75/30 [515/205]	Cold Worked Welded Pipe	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-814	TP304N	S30451		80/35 [550/240]	Cold Worked Welded Pipe	18Cr-8Ni-N
8	1	8.1	ASTM/ASME A/SA-814	TP316	S31600		75/30 [515/205]	Cold Worked Welded Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-814	TP316H	S31609		75/30 [515/205]	Cold Worked Welded Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-814	TP316L	S31603		70/25 [485/170]	Cold Worked Welded Pipe	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME A/SA-814	TP316LN	S31653		75/30 [515/205]	Cold Worked Welded Pipe	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME A/SA-814	TP316N	S31651		80/35 [550/240]	Cold Worked Welded Pipe	16Cr-12Ni-2Mo-N

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	1	8.1	ASTM/ASME	A/SA-814	TP317	S31700		75/30 [515/205]	Cold Worked Welded Pipe	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME	A/SA-814	TP317L	S31703		75/30 [515/205]	Cold Worked Welded Pipe	18Cr-13Ni-3Mo
8	1	8.1	ASTM/ASME	A/SA-814	TP321	S32100		75/30 [515/205]	Cold Worked Welded Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME	A/SA-814	TP321H	S32109		75/30 [515/205]	Cold Worked Welded Pipe	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME	A/SA-814	TP347	S34700		75/30 [515/205]	Cold Worked Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-814	TP347H	S34709		75/30 [515/205]	Cold Worked Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-814	TP348	S34800		75/30 [515/205]	Cold Worked Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-814	TP348H	S34809		75/30 [515/205]	Cold Worked Welded Pipe	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-814	TPXM-15	S38100		75/30 [515/205]	Cold Worked Welded Pipe	18Cr-18Ni-2Si
8	1	8.1	ASTM/ASME	A/SA-965	F304	S30400		70/30 [485/205]	Forgings	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-965	F304H	S30409		70/30 [485/205]	Forgings	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-965	F304L	S30403		65/25 [450/170]	Forgings	18Cr-8Ni
8	1	8.1	ASTM/ASME	A/SA-965	F304LN	S30453		70/30 [485/205]	Forgings	18Cr-8Ni-N
8	1	8.1	ASTM/ASME	A/SA-965	F304N	S30451		80/35 [550/240]	Forgings	18Cr-8Ni-N
8	1	8.1	ASTM/ASME	A/SA-965	F316	S31600		70/30 [485/205]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-965	F316H	S31609		70/30 [485/205]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-965	F316L	S31603		65/25 [450/170]	Forgings	16Cr-12Ni-2Mo
8	1	8.1	ASTM/ASME	A/SA-965	F316LN	S31653		70/30 [485/205]	Forgings	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME	A/SA-965	F316N	S31651		80/35 [550/240]	Forgings	16Cr-12Ni-2Mo-N
8	1	8.1	ASTM/ASME	A/SA-965	F321	S32100		70/30 [485/205]	Forgings	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME	A/SA-965	F321H	S32109		70/30 [485/205]	Forgings	18Cr-10Ni-Ti
8	1	8.1	ASTM/ASME	A/SA-965	F347	S34700		70/30 [485/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-965	F347H	S34709		70/30 [485/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-965	F348	S34800		70/30 [485/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-965	F348H	S34809		70/30 [485/205]	Forgings	18Cr-10Ni-Cb
8	1	8.1	ASTM/ASME	A/SA-965	F46	S30600		78/32 [540/220]	Forgings	18Cr-15Ni-4Si
8	2	8.2	ASTM	A167	308	S30800		75/30 [515/205]	Plate, Sheet, & Strip	20Cr-10Ni
8	2	8.2	ASTM	A167	309	S30900		75/30 [515/205]	Plate, Sheet, & Strip	23Cr-12Ni
8	2	8.2	ASTM	A167	310	S31000		75/30 [515/205]	Plate, Sheet, & Strip	25Cr-20Ni

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	2	8.1	ASTM/ASME	A/SA-182	F10	S33100		80/30 [550/205]	Forgings	20Ni-8Cr
8	2	8.2	ASTM/ASME	A/SA-182	F310	S31000		75/30 [515/205]	Forgings	25Cr-20Ni
8	2	8.2	ASTM/ASME	A/SA-182	F310	S31000	>5 [>127]	70/30 [485/205]	Forgings	25Cr-20Ni
8	2	8.2	ASTM/ASME	A/SA-182	F310MoLN	S31050		78/37 [540/255]	Forgings	25Cr-22Ni-2Mo-N
8	2	8.2	ASTM/ASME	A/SA-182	F45	S30815		87/45 [600/310]	Forgings	21Cr-11Ni-N
8	2	8.2	ASTM/ASME	A/SA-213	310	S31000		75/30 [515/205]	Seamless Tube	25Cr-20Ni
8	2	8.2	ASTM/ASME	A/SA-213	S30815	S30815		87/45 [600/310]	Seamless Tube	21Cr-11Ni-N
8	2	8.2	ASTM/ASME	A/SA-213	TP309Cb	S30940		75/30 [515/205]	Seamless Tube	23Cr-12Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-213	TP309H	S30909		75/30 [515/205]	Seamless Tube	23Cr-12Ni
8	2	8.2	ASTM/ASME	A/SA-213	TP309HCb	S30941		75/30 [515/205]	Seamless Tube	23Cr-12Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-213	TP309S	S30908		75/30 [515/205]	Seamless Tube	23Cr-12Ni
8	2	8.2	ASTM/ASME	A/SA-213	TP310Cb	S31040		75/30 [515/205]	Seamless Tube	25Cr-20Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-213	TP310H	S31009		75/30 [515/205]	Seamless Tube	25Cr-20Ni
8	2	8.2	ASTM/ASME	A/SA-213	TP310HCb	S31041		75/30 [515/205]	Seamless Tube	25Cr-20Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-213	TP310MoLN	S31050	>0.25 [>6]	78/37 [540/255]	Seamless Tube	25Cr-22Ni-2Mo-N
8	2	8.2	ASTM/ASME	A/SA-213	TP310MoLN	S31050	≤0.25 [≤6]	84/39 [580/270]	Seamless Tube	25Cr-22Ni-2Mo-N
8	2	8.2	ASTM/ASME	A/SA-213	TP310S	S31008		75/30 [515/205]	Seamless Tube	25Cr-20Ni
8	2	8.2	ASTM/ASME	A/SA-240	309Cb	S30940		75/30 [515/205]	Plate, Sheet, & Strip	23Cr-12Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-240	309H	S30909		75/30 [515/205]	Plate, Sheet, & Strip	23Cr-12Ni
8	2	8.2	ASTM/ASME	A/SA-240	309HCb	S30941		75/30 [515/205]	Plate, Sheet, & Strip	23Cr-12Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-240	309S	S30908		75/30 [515/205]	Plate, Sheet, & Strip	23Cr-12Ni
8	2	8.2	ASTM/ASME	A/SA-240	310Cb	S31040		75/30 [515/205]	Plate, Sheet, & Strip	25Cr-20Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-240	310H	S31009		75/30 [515/205]	Plate, Sheet, & Strip	25Cr-20Ni
8	2	8.2	ASTM/ASME	A/SA-240	310HCb	S31041		75/30 [515/205]	Plate, Sheet, & Strip	25Cr-20Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-240	310MoLN	S31050	≤0.25 [≤6]	84/39 [580/270]	Plate, Sheet, & Strip	25Cr-22Ni-2Mo-N
8	2	8.2	ASTM/ASME	A/SA-240	310MoLN	S31050	>0.25 [>6]	78/37 [540/255]	Plate, Sheet, & Strip	25Cr-22Ni-2Mo-N
8	2	8.2	ASTM/ASME	A/SA-240	310S	S31008		75/30 [515/205]	Plate, Sheet, & Strip	25Cr-20Ni
8	2	8.2	ASTM/ASME	A/SA-240	S30815	S30815		87/45 [600/310]	Plate, Sheet, & Strip	21Cr-11Ni-N
8	2	8.2	ASTM/ASME	A/SA-249	S30815	S30815		87/45 [600/310]	Welded Tube	21Cr-11Ni-N

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	2	8.2	ASTM/ASME	A/SA-249	TP309	S30900		75/30 [515/205]	Welded Tube	23Cr-12Ni
8	2	8.2	ASTM/ASME	A/SA-249	TP309Cb	S30940		75/30 [515/205]	Welded Tube	23Cr-12Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-249	TP309H	S30909		75/30 [515/205]	Welded Tube	23Cr-12Ni
8	2	8.2	ASTM/ASME	A/SA-249	TP309HCb	S30941		75/30 [515/205]	Welded Tube	23Cr-12Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-249	TP309S	S30908		75/30 [515/205]	Welded Tube	23Cr-12Ni
8	2	8.2	ASTM/ASME	A/SA-249	TP310Cb	S31040		75/30 [515/205]	Welded Tube	25Cr-20Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-249	TP310H	S31009		75/30 [515/205]	Welded Tube	25Cr-20Ni
8	2	8.2	ASTM/ASME	A/SA-249	TP310HCb	S31041		75/30 [515/205]	Welded Tube	25Cr-20Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-249	TP310MoLN	S31050	≤0.25 [≤6]	84/39 [580/270]	Welded Tube	25Cr-22Ni-2Mo-N
8	2	8.2	ASTM/ASME	A/SA-249	TP310MoLN	S31050	>0.25 [>6]	78/37 [540/255]	Welded Tube	25Cr-22Ni-2Mo-N
8	2	8.2	ASTM/ASME	A/SA-249	TP310S	S31008		75/30 [515/205]	Welded Tube	25Cr-20Ni
8	2	8.2	ASTM	A297	HE	J93403		85/40 [585/275]	Castings	28Cr-10Ni-2Mn-2Si
8	2	8.2	ASTM	A297	HF	J92603		70/35 [485/240]	Castings	21Cr-10Ni-2Mn-2Si
8	2	8.2	ASTM	A297	HH	J93503		75/35 [515/240]	Castings	26Cr-13Ni-2Mn-2Si
8	2	8.2	ASTM	A297	HI	J94003		70/35 [485/240]	Castings	28Cr-16Ni-2Mn-2Si
8	2	8.2	ASTM	A297	HK	J94224		65/35 [450/240]	Castings	26Cr-20Ni-2Mn-2Si
8	2	8.2	ASTM/ASME	A/SA-312	S30815	S30815		87/45 [600/310]	Seamless & Welded Pipe	21Cr-11Ni-N
8	2	8.2	ASTM/ASME	A/SA-312	TP309Cb	S30940		75/30 [515/205]	Seamless & Welded Pipe	23Cr-12Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-312	TP309H	S30909		75/30 [515/205]	Seamless & Welded Pipe	23Cr-12Ni
8	2	8.2	ASTM/ASME	A/SA-312	TP309HCb	S30941		75/30 [515/205]	Seamless & Welded Pipe	23Cr-12Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-312	TP309S	S30908		75/30 [515/205]	Seamless & Welded Pipe	23Cr-12Ni
8	2	8.2	ASTM/ASME	A/SA-312	TP310Cb	S31040		75/30 [515/205]	Seamless & Welded Pipe	25Cr-20Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-312	TP310H	S31009		75/30 [515/205]	Seamless & Welded Pipe	25Cr-20Ni
8	2	8.2	ASTM/ASME	A/SA-312	TP310HCb	S31041		75/30 [515/205]	Seamless & Welded Pipe	25Cr-20Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-312	TP310MoLN	S31050	≤0.25 [≤6]	84/39 [580/270]	Seamless & Welded Pipe	25Cr-22Ni-2Mo-N
8	2	8.2	ASTM/ASME	A/SA-312	TP310MoLN	S31050	>0.25 [>6]	78/37 [540/255]	Seamless & Welded Pipe	25Cr-22Ni-2Mo-N
8	2	8.2	ASTM/ASME	A/SA-312	TP310S	S31008		75/30 [515/205]	Seamless & Welded Pipe	25Cr-20Ni
8	2	8.2	ASTM/ASME	A/SA-336	F310	S31000		75/30 [515/205]	Forgings	25Cr-20Ni
8	2	8.2	ASTM/ASME	A/SA-351	CE20N	J92802		80/40 [550/275]	Castings	25Cr-8Ni-N

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	2	ASTM/ASME	A/SA-351	CH10	J93401		70/30 [485/205]	Castings	25Cr-12Ni
8	2	ASTM/ASME	A/SA-351	CH20	J93402		70/30 [485/205]	Castings	25Cr-12Ni
8	2	ASTM/ASME	A/SA-351	CH8	J93400		65/28 [450/195]	Castings	25Cr-12Ni
8	2	ASTM/ASME	A/SA-351	CK20	J94202		65/28 [450/195]	Castings	25Cr-20Ni
8	2	ASTM/ASME	A/SA-351	HK30	J94203		65/35 [450/240]	Castings	25Cr-20Ni-0.5Mo
8	2	ASTM/ASME	A/SA-351	HK40	J94204		62/35 [425/240]	Castings	25Cr-20Ni-0.5Mo
8	2	ASTM/ASME	A/SA-358	309	S30900		75/30 [515/205]	Fusion Welded Pipe	23Cr-12Ni
8	2	ASTM/ASME	A/SA-358	309Cb	S30940		75/30 [515/205]	Fusion Welded Pipe	23Cr-12Ni-Cb
8	2	ASTM/ASME	A/SA-358	309S	S30908		75/30 [515/205]	Fusion Welded Pipe	23Cr-12Ni
8	2	ASTM/ASME	A/SA-358	310	S31000		75/30 [515/205]	Fusion Welded Pipe	23Cr-12Ni
8	2	ASTM/ASME	A/SA-358	310Cb	S31040		75/30 [515/205]	Fusion Welded Pipe	25Cr-20Ni-Cb
8	2	ASTM/ASME	A/SA-358	310S	S31008		75/30 [515/205]	Fusion Welded Pipe	25Cr-20Ni
8	2	ASTM/ASME	A/SA-358	S30815	S30815		87/45 [600/310]	Fusion Welded Pipe	21Cr-11Ni-N
8	2	ASTM/ASME	A/SA-403	WP309	S30900		75/30 [515/205]	Wrought Piping Fittings	23Cr-12Ni
8	2	ASTM/ASME	A/SA-403	WP310	S31000		75/30 [515/205]	Wrought Piping Fittings	23Cr-12Ni
8	2	ASTM/ASME	A/SA-403	WP310S	S31008		75/30 [515/205]	Wrought Piping Fittings	25Cr-20Ni
8	2	ASTM/ASME	A/SA-409	S30815	S30815		87/45 [600/310]	Welded Pipe	21Cr-11Ni-N
8	2	ASTM/ASME	A/SA-409	TP309Cb	S30940		75/30 [515/205]	Welded Pipe	23Cr-12Ni-Cb
8	2	ASTM/ASME	A/SA-409	TP309S	S30908		75/30 [515/205]	Welded Pipe	23Cr-12Ni
8	2	ASTM/ASME	A/SA-409	TP310Cb	S31040		75/30 [515/205]	Welded Pipe	25Cr-20Ni-Cb
8	2	ASTM/ASME	A/SA-409	TP310S	S31008		75/30 [515/205]	Welded Pipe	25Cr-20Ni
8	2	ASTM/ASME	A/SA-451	CPE20N	J92802		80/40 [550/275]	Centrifugal Cast Pipe	25Cr-8Ni-N
8	2	ASTM/ASME	A/SA-451	CPH10	J93402		70/30 [485/205]	Centrifugal Cast Pipe	25Cr-12Ni
8	2	ASTM/ASME	A/SA-451	CPH20	J93402		70/30 [485/205]	Centrifugal Cast Pipe	25Cr-12Ni
8	2	ASTM/ASME	A/SA-451	CPH8	J93400		65/28 [450/195]	Centrifugal Cast Pipe	25Cr-12Ni
8	2	ASTM/ASME	A/SA-451	CPK20	J94202		65/28 [450/195]	Centrifugal Cast Pipe	25Cr-20Ni
8	2	ASTM	A473	308	S30800		75/30 [515/205]	Forgings	20Cr-10Ni
8	2	ASTM	A473	309	S30900		75/30 [515/205]	Forgings	23Cr-12Ni
8	2	ASTM	A473	309S	S30908		75/30 [515/205]	Forgings	23Cr-12Ni

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	2	8.2	ASTM	A473	310	S31000		75/30 [515/205]	Forgings	25Cr-20Ni
8	2	8.2	ASTM	A473	310S	S31008		75/30 [515/205]	Forgings	25Cr-20Ni
8	2	8.2	ASTM	A473	314	S31400		75/30 [515/205]	Forgings	25Cr-21Ni-S
8	2	8.2	ASTM	A473	S30815	S30815		87/45 [600/310]	Forgings	21Cr-11Ni-N
8	2	8.2	ASTM/ASME	A/SA-479	309Cb	S30940		75/30 [515/205]	Bars & Shapes	23Cr-12Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-479	309S	S30908		75/30 [515/205]	Bars & Shapes	23Cr-12Ni
8	2	8.2	ASTM/ASME	A/SA-479	310Cb	S31040		75/30 [515/205]	Bars & Shapes	25Cr-20Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-479	310S	S31008		75/30 [515/205]	Bars & Shapes	25Cr-20Ni
8	2	8.2	ASTM/ASME	A/SA-479	S30815	S30815		87/45 [600/310]	Bars & Shapes	21Cr-11Ni-N
8	2	8.2	ASTM	A511	MT 309S	S30908		75/30 [515/205]	Seamless Tube	23Cr-12Ni
8	2	8.2	ASTM	A511	MT 310S	S31008		75/30 [515/205]	Seamless Tube	25Cr-20Ni
8	2	8.2	ASTM	A554	MT 309S	S30908		75/30 [515/205]	Welded Tube	23Cr-12Ni
8	2	8.2	ASTM	A554	MT 309S-Cb	S30940		75/30 [515/205]	Welded Tube	23Cr-12Ni-Cb
8	2	8.2	ASTM	A554	MT 310S	S31008		75/30 [515/205]	Welded Tube	25Cr-20Ni
8	2	8.2	ASTM	A743	CE30	J93423		80/40 [550/275]	Castings	29Cr-9Ni-2Mn-2Si
8	2	8.2	ASTM	A743	CF20	J92602		70/30 [485/205]	Castings	20Cr-10Ni
8	2	8.2	ASTM	A743	CG12	J93001		70/28 [485/195]	Castings	22Cr-12Ni
8	2	8.2	ASTM	A743	CH10	J93401		70/30 [485/205]	Castings	25Cr-12Ni
8	2	8.2	ASTM	A743	CH20	J93402		70/30 [485/205]	Castings	25Cr-12Ni
8	2	8.2	ASTM	A743	CN3M	J94652		63/25 [435/170]	Castings	25Ni-21Cr-5Mo
8	2	8.2	ASTM/ASME	A/SA-813	S30815	S30815		87/45 [600/310]	Welded Pipe	21Cr-11Ni-N
8	2	8.2	ASTM/ASME	A/SA-813	TP309Cb	S30940		75/30 [515/205]	Welded Pipe	23Cr-12Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-813	TP309S	S30908		75/30 [515/205]	Welded Pipe	23Cr-12Ni
8	2	8.2	ASTM/ASME	A/SA-813	TP310Cb	S31040		75/30 [515/205]	Welded Pipe	25Cr-20Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-813	TP310S	S31008		75/30 [515/205]	Welded Pipe	25Cr-20Ni
8	2	8.2	ASTM/ASME	A/SA-814	S30815	S30815		87/45 [600/310]	Cold Worked Welded Pipe	21Cr-11Ni-N
8	2	8.2	ASTM/ASME	A/SA-814	TP309Cb	S30940		75/30 [515/205]	Cold Worked Welded Pipe	23Cr-12Ni-Cb
8	2	8.2	ASTM/ASME	A/SA-814	TP309S	S30908		75/30 [515/205]	Cold Worked Welded Pipe	23Cr-12Ni
8	2	8.2	ASTM/ASME	A/SA-814	TP310Cb	S31040		75/30 [515/205]	Cold Worked Welded Pipe	25Cr-20Ni-Cb

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	2	ASTM/ASME	A/SA-814	TP310S	S31008		75/30 [515/205]	Cold Worked Welded Pipe	25Cr-20Ni
8	2	ASTM/ASME	A/SA-965	F310	S31000		75/30 [515/205]	Forgings	25Cr-20Ni
8	3	ASTM/ASME	A/SA-182	FXM-11	S21904		90/50 [620/345]	Forgings	21Cr-6Ni-9Mn
8	3	ASTM/ASME	A/SA-182	FXM-19	S20910		100/55 [690/380]	Forgings	22Cr-13Ni-5Mn
8	3	ASTM/ASME	A/SA-213	TP201	S20100		95/38 [655/260]	Seamless Tube	17Cr-4Ni-6Mn
8	3	ASTM/ASME	A/SA-213	TP202	S20200		90/45 [620/310]	Seamless Tube	18Cr-5Ni-9Mn
8	3	ASTM/ASME	A/SA-213	TP310HCbN	S31042		95/43 [655/295]	Seamless Tube	25Cr-20Ni-Cb-N
8	3	ASTM/ASME	A/SA-213	XM-19	S20910		100/55 [690/380]	Seamless Tube	22Cr-13Ni-5Mn
8	3	ASTM/ASME	A/SA-240	—	S20400		95/48 [655/330]	Plate, Sheet, & Strip	16Cr-9Mn-2Ni-N
8	3	ASTM/ASME	A/SA-240	201-1	S20100		75/38 [515/260]	Plate, Sheet, & Strip	17Cr-4Ni-6Mn
8	3	ASTM/ASME	A/SA-240	201-2	S20100		95/45 [655/310]	Plate, Sheet, & Strip	17Cr-4Ni-6Mn
8	3	ASTM/ASME	A/SA-240	201LN	S20153		95/45 [655/310]	Plate, Sheet, & Strip	16Cr-4Ni-6Mn
8	3	ASTM/ASME	A/SA-240	202	S20200		90/38 [620/260]	Plate, Sheet, & Strip	18Cr-5Ni-9Mn
8	3	ASTM/ASME	A/SA-240	S21800	S21800		95/50 [655/345]	Plate, Sheet, & Strip	18Cr-8Ni-4Si-N
8	3	ASTM/ASME	A/SA-240	XM-17	S21600		90/50 [620/345]	Plate	19Cr-8Mn-6Ni-Mo-N
8	3	ASTM/ASME	A/SA-240	XM-17	S21600		100/60 [690/415]	Sheet & Strip	19Cr-8Mn-6Ni-Mo-N
8	3	ASTM/ASME	A/SA-240	XM-18	S21603		90/50 [620/345]	Plate	19Cr-8Mn-6Ni-Mo-N
8	3	ASTM/ASME	A/SA-240	XM-18	S21603		100/60 [690/415]	Sheet & Strip	19Cr-8Mn-6Ni-Mo-N
8	3	ASTM/ASME	A/SA-240	XM-19	S20910		105/60 [725/415]	Sheet & Strip	22Cr-13Ni-5Mn
8	3	ASTM/ASME	A/SA-240	XM-19	S20910		100/55 [690/380]	Plate	22Cr-13Ni-5Mn
8	3	ASTM/ASME	A/SA-240	XM-29	S24000		100/55 [690/380]	Plate, Sheet, & Strip	18Cr-3Ni-12Mn
8	3	ASTM/ASME	A/SA-249	TP 201	S20100		95/38 [655/260]	Welded Tube	17Cr-4Ni-6Mn
8	3	ASTM/ASME	A/SA-249	TP 202	S20200		90/38 [620/260]	Welded Tube	18Cr-5Ni-9Mn
8	3	ASTM/ASME	A/SA-249	TP XM-19	S20910		100/55 [690/380]	Welded Tube	22Cr-13Ni-5Mn
8	3	ASTM/ASME	A/SA-249	TP XM-29	S24000		100/55 [690/380]	Welded Tube	18Cr-3Ni-12Mn
8	3	ASTM	A269	TPXM-10	S21900		90/50 [620/345]	Seamless & Welded Tube	20Cr-6Ni-9Mn
8	3	ASTM	A269	TPXM-11	S21904		90/50 [620/345]	Seamless & Welded Tube	21Cr-6Ni-9Mn
8	3	ASTM	A269	TPXM-15	S38100		90/50 [620/345]	Seamless & Welded Tube	18Cr-18Ni-2Si
8	3	ASTM	A269	TPXM-19	S20910		100/55 [690/380]	Seamless & Welded Tube	22Cr-13Ni-5Mn

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	3	ASTM	A269	TPXM-29	S24000		100/55 [690/380]	Seamless & Welded Tube	18Cr-3Ni-12Mn
8	3	ASTM/ASME	A/SA-312	TP XM-11	S21904		90/50 [620/345]	Seamless & Welded Pipe	21Cr-6Ni-9Mn
8	3	ASTM/ASME	A/SA-312	TP XM-19	S20910		100/55 [690/380]	Seamless & Welded Pipe	22Cr-13Ni-5Mn
8	3	ASTM/ASME	A/SA-312	TP XM-29	S24000		100/55 [690/380]	Seamless & Welded Pipe	18Cr-3Ni-12Mn
8	3	ASTM/ASME	A/SA-336	FXM-11	S21904		90/50 [620/345]	Forgings	21Cr-6Ni-9Mn
8	3	ASTM/ASME	A/SA-336	FXM-19	S20910		100/55 [690/380]	Forgings	22Cr-13Ni-5Mn
8	3	ASTM/ASME	A/SA-351	CG6MMN	J93790		85/42 [585/290]	Castings	22Cr-12Ni-5Mn
8	3	ASTM/ASME	A/SA-358	XM-19	S20910		100/55 [690/380]	Fusion Welded Pipe	22Cr-13Ni-5Mn
8	3	ASTM/ASME	A/SA-358	XM-29	S24000		100/55 [690/380]	Fusion Welded Pipe	18Cr-3Ni-12Mn
8	3	ASTM/ASME	A/SA-403	WPXM-19	S20910		100/55 [690/380]	Wrought Piping Fittings	22Cr-13Ni-5Mn
8	3	ASTM	A473	201	S20100		75/30 [515/205]	Forgings	17Cr-4Ni-6Mn
8	3	ASTM	A473	202	S20200		90/45 [620/310]	Forgings	18Cr-5Ni-9Mn
8	3	ASTM	A473	XM-10	S21900		90/50 [620/345]	Forgings	20Cr-6Ni-9Mn
8	3	ASTM	A473	XM-11	S21904		90/50 [620/345]	Forgings	21Cr-6Ni-9Mn
8	3	ASTM/ASME	A/SA-479	S21800	S21800		95/50 [655/345]	Bars & Shapes	18Cr-8Ni-4Si-N
8	3	ASTM/ASME	A/SA-479	XM-11	S21904		90/50 [620/345]	Bars & Shapes	21Cr-6Ni-9Mn
8	3	ASTM/ASME	A/SA-479	XM-17	S21600		90/50 [620/345]	Bars & Shapes	19Cr-8Mn-6Ni-Mo-N
8	3	ASTM/ASME	A/SA-479	XM-18	S21603		90/50 [620/345]	Bars & Shapes	19Cr-8Mn-6Ni-Mo-N
8	3	ASTM/ASME	A/SA-479	XM-19	S20910		100/55 [690/380]	Bars & Shapes	22Cr-13Ni-5Mn
8	3	ASTM/ASME	A/SA-479	XM-29	S24000		100/55 [690/380]	Bars & Shapes	18Cr-3Ni-12Mn
8	3	ASTM/ASME	A/SA-666	201-1	S20100		75/38 [515/260]	Plate, Sheet, & Strip	17Cr-4Ni-6Mn
8	3	ASTM/ASME	A/SA-666	201-2	S20100		95/45 [655/310]	Plate, Sheet, & Strip	17Cr-4Ni-6Mn
8	3	ASTM/ASME	A/SA-666	XM-11	S21904		90/50 [620/345]	Plate, Sheet, & Strip	21Cr-6Ni-9Mn
8	3	ASTM/ASME	A/SA-688	XM-29	S24000		100/55 [690/380]	Welded Tube	18Cr-3Ni-12Mn
8	3	ASTM/ASME	A/SA-813	TPXM-11	S21904		90/50 [620/345]	Welded Pipe	21Cr-6Ni-9Mn
8	3	ASTM/ASME	A/SA-813	TPXM-19	S20910		100/55 [690/380]	Welded Pipe	22Cr-13Ni-5Mn
8	3	ASTM/ASME	A/SA-813	TPXM-29	S24000		100/55 [690/380]	Welded Pipe	18Cr-3Ni-12Mn
8	3	ASTM/ASME	A/SA-814	TPXM-11	S21904		90/50 [620/345]	Cold Worked Welded Pipe	21Cr-6Ni-9Mn
8	3	ASTM/ASME	A/SA-814	TPXM-19	S20910		100/55 [690/380]	Cold Worked Welded Pipe	22Cr-13Ni-5Mn

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	3	8.3	ASTM/ASME	A/SA-814	TPXM-29	S24000		100/55 [690/380]	Cold Worked Welded Pipe	18Cr-3Ni-12Mn
8	3	8.3	ASTM/ASME	A/SA-965	FXM-11	S21904		90/50 [620/345]	Forgings	21Cr-6Ni-9Mn
8	3	8.3	ASTM/ASME	A/SA-965	FXM-19	S20910		100/55 [690/380]	Forgings	22Cr-13Ni-5Mn
8	4	8.2	ASTM/ASME	A/SA-182	—	S32053		93/43 [640/295]	Forgings	23Cr-25Ni-5.5Mo-N
8	4	8.2	ASTM/ASME	A/SA-182	F44	S31254		94/44 [650/305]	Forgings	20Cr-18Ni-6Mo
8	4	8.3	ASTM/ASME	A/SA-182	F49	S34565		115/60 [795/415]	Forgings	24Cr-17Ni-6Mn-4.5Mo-N
8	4	8.3	ASTM/ASME	A/SA-213	S34565	S34565		115/60 [795/415]	Seamless Tube	24Cr-17Ni-6Mn-4.5Mo-N
8	4	8.1	ASTM/ASME	A/SA-213	TP317LM	S31725		75/30 [515/205]	Seamless Tube	19Cr-15Ni-4Mo
8	4	8.1	ASTM/ASME	A/SA-213	TP317LMN	S31726		80/35 [550/240]	Seamless Tube	19Cr-15.5Ni-4Mo
8	4	8.2	ASTM/ASME	A/SA-240	—	S32053		93/43 [640/295]	Plate, Sheet, & Strip	23Cr-25Ni-5.5Mo-N
8	4	8.2	ASTM/ASME	A/SA-240	S31254	S31254		95/45 [655/310]	Plate	20Cr-18Ni-6Mo
8	4	8.2	ASTM/ASME	A/SA-240	S31254	S31254		100/45 [690/310]	Sheet & Strip	20Cr-18Ni-6Mo
8	4	8.1	ASTM/ASME	A/SA-240	S31725	S31725		75/30 [515/205]	Plate, Sheet, & Strip	19Cr-15Ni-4Mo
8	4	8.1	ASTM/ASME	A/SA-240	S31726	S31726		80/35 [550/240]	Plate, Sheet, & Strip	19Cr-15.5Ni-4Mo
8	4	8.3	ASTM/ASME	A/SA-240	S34565	S34565		115/60 [795/415]	Plate, Sheet, & Strip	24Cr-17Ni-6Mn-4.5Mo-N
8	4	8.2	ASTM/ASME	A/SA-249	—	S32053		93/43 [640/295]	Welded Tube	23Cr-25Ni-5.5Mo-N
8	4	8.2	ASTM/ASME	A/SA-249	S31254	S31254	≤0.1875 [≤5]	98/45 [675/310]	Welded Tube	20Cr-18Ni-6Mo
8	4	8.2	ASTM/ASME	A/SA-249	S31254	S31254	>0.1875 [>5]	95/45 [655/310]	Welded Tube	20Cr-18Ni-6Mo
8	4	8.1	ASTM/ASME	A/SA-249	S31725	S31725		75/30 [515/205]	Welded Tube	19Cr-15Ni-4Mo
8	4	8.1	ASTM/ASME	A/SA-249	S31726	S31726		80/35 [550/240]	Welded Tube	19Cr-15.5Ni-4Mo
8	4	8.2	ASTM/ASME	A/SA-312	—	S32053		93/43 [640/295]	Seamless & Welded Pipe	23Cr-25Ni-5.5Mo-N
8	4	8.2	ASTM/ASME	A/SA-312	S31254	S31254	>0.1875 [>5]	95/45 [655/310]	Seamless & Welded Pipe	20Cr-18Ni-6Mo
8	4	8.2	ASTM/ASME	A/SA-312	S31254	S31254	≤0.1875 [≤5]	98/45 [675/310]	Seamless & Welded Pipe	20Cr-18Ni-6Mo
8	4	8.1	ASTM/ASME	A/SA-312	S31725	S31725		75/30 [515/205]	Seamless & Welded Pipe	19Cr-15Ni-4Mo
8	4	8.1	ASTM/ASME	A/SA-312	S31726	S31726		80/35 [550/240]	Seamless & Welded Pipe	19Cr-15.5Ni-4Mo
8	4	8.3	ASTM/ASME	A/SA-312	S34565	S34565		115/60 [795/415]	Seamless & Welded Pipe	24Cr-17Ni-6Mn-4.5Mo-N
8	4	8.2	ASTM/ASME	A/SA-351	CK3MCuN	J93254		80/38 [550/260]	Castings	20Cr-18Ni-6Mo
8	4	8.2	ASTM/ASME	A/SA-358	—	S32053		93/43 [640/295]	Fusion Welded Pipe	23Cr-25Ni-5.5Mo-N
8	4	8.2	ASTM/ASME	A/SA-358	S31254	S31254		94/45 [650/310]	Fusion Welded Tube	20Cr-18Ni-6Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
8	4	8.1	ASTM/ASME A/SA-358	S31725	S31725	75/30 [515/205]	Fusion Welded Pipe	19Cr-15Ni-4Mo	
8	4	8.1	ASTM/ASME A/SA-358	S31726	S31726	80/35 [550/240]	Fusion Welded Pipe	19Cr-15.5Ni-4Mo	
8	4	8.1	ASTM/ASME A/SA-376	S31725	S31725	75/30 [515/205]	Seamless Pipe	19Cr-15Ni-4Mo	
8	4	8.1	ASTM/ASME A/SA-376	S31726	S31726	80/35 [550/240]	Seamless Pipe	19Cr-15.5Ni-4Mo	
8	4	8.3	ASTM/ASME A/SA-376	S34565	S34565	115/60 [795/415]	Seamless Pipe	24Cr-17Ni-6Mn-4.5Mo-N	
8	4	8.2	ASTM/ASME A/SA-403	—	S31254	94/44 [650/305]	Wrought Piping Fittings	20Cr-18Ni-6Mo	
8	4	8.2	ASTM/ASME A/SA-403	—	S32053	93/43 [640/295]	Wrought Piping Fittings	23Cr-25Ni-5.5Mo-N	
8	4	8.3	ASTM/ASME A/SA-403	S34565	S34565	115/60 [795/415]	Wrought Piping Fittings	24Cr-17Ni-6Mn-4.5Mo-N	
8	4	8.2	ASTM/ASME A/SA-409	—	S32053	93/43 [640/295]	Welded Pipe	23Cr-25Ni-5.5Mo-N	
8	4	8.2	ASTM/ASME A/SA-409	S31254	S31254	94/44 [650/305]	Welded Pipe	20Cr-18Ni-6Mo	
8	4	8.1	ASTM/ASME A/SA-409	S31725	S31725	75/30 [515/205]	Welded Pipe	19Cr-15Ni-4Mo	
8	4	8.1	ASTM/ASME A/SA-409	S31726	S31726	80/35 [550/240]	Welded Pipe	19Cr-15.5Ni-4Mo	
8	4	8.3	ASTM/ASME A/SA-409	S34565	S34565	115/60 [795/415]	Welded Pipe	24Cr-17Ni-6Mn-4.5Mo-N	
8	4	8.2	ASTM/ASME A/SA-479	—	S32053	93/43 [640/295]	Bars & Shapes	23Cr-25Ni-5.5Mo-N	
8	4	8.2	ASTM/ASME A/SA-479	S31254	S31254	95/44 [655/305]	Bars & Shapes	20Cr-18Ni-6Mo	
8	4	8.1	ASTM/ASME A/SA-479	S31725	S31725	75/30 [515/205]	Bars & Shapes	19Cr-15Ni-4Mo	
8	4	8.1	ASTM/ASME A/SA-479	S31726	S31726	80/35 [550/240]	Bars & Shapes	19Cr-15.5Ni-4Mo	
8	4	8.3	ASTM/ASME A/SA-479	S34565	S34565	115/60 [795/415]	Bars & Shapes	24Cr-17Ni-6Mn-4.5Mo-N	
8	4	8.2	ASTM A743	CK3MCuN	J93254	80/38 [550/260]	Castings	20Cr-18Ni-6Mo	
8	4	8.2	ASTM/ASME A/SA-813	—	S32053	93/43 [640/295]	Welded Pipe	23Cr-25Ni-5.5Mo-N	
8	4	8.2	ASTM/ASME A/SA-813	S31254	S31254	94/44 [650/305]	Welded Pipe	20Cr-18Ni-6Mo	
8	4	8.2	ASTM/ASME A/SA-814	—	S32053	93/43 [640/295]	Cold Worked Welded Pipe	23Cr-25Ni-5.5Mo-N	
8	4	8.2	ASTM/ASME A/SA-814	S31254	S31254	94/44 [650/305]	Cold Worked Welded Pipe	20Cr-18Ni-6Mo	
9A	1	9.1	ASTM/ASME A/SA-182	FR	K22035	63/46 [435/315]	Forgings	2Ni-1Cu	
9A	1	9.1	ASTM/ASME A/SA-203	A	K21703	65/37 [450/255]	Plate	2.5Ni	
9A	1	9.1	ASTM/ASME A/SA-203	B	K22103	70/40 [485/275]	Plate	2.5Ni	
9A	1	9.1	ASTM/ASME A/SA-234	WPR	K22035	63/46 [435/315]	Piping Fittings	2Ni-1Cu	
9A	1	9.1	ASTM/ASME A/SA-333	7	K21903	65/35 [450/240]	Seamless & Welded Pipe	2.5Ni	
9A	1	9.1	ASTM/ASME A/SA-333	9	K22035	63/46 [435/315]	Seamless & Welded Pipe	2Ni-1Cu	

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Ferrous Alloys (see C.1, I2.2.1, and I3)

Material Group Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
9A	1	9.1	ASTM/ASME A/SA-334	7	K21903		65/35 [450/240]	Welded Tube	2.5Ni
9A	1	9.1	ASTM/ASME A/SA-334	9	K22035		63/46 [435/315]	Welded Tube	2Ni-1Cu
9A	1	9.1	ASTM/ASME A/SA-350	LF5, Cl. 1	K13050		60/30 [415/205]	Forgings	1.5Ni
9A	1	9.1	ASTM/ASME A/SA-350	LF5, Cl. 2	K13050		70/37.5 [485/260]	Forgings	1.5Ni
9A	1	9.1	ASTM/ASME A/SA-350	LF9	K22036		63/46 [435/315]	Forgings	2Ni-1Cu
9A	1	9.1	ASTM/ASME A/SA-352	LC2	J22500		70/40 [485/275]	Castings	2.5Ni
9A	1	9.1	ASTM/ASME A/SA-420	WPL9	K22035		63/46 [435/315]	Piping Fittings	2Ni-1Cu
9A	1	9.1	ASTM A714	V	K22035		65/46 [450/315]	Seamless & Welded Pipe	2Ni-1Cu
9A	1	9.1	ASTM A714	V, E	K22035		65/46 [450/315]	Seamless & Welded Pipe	2Ni-1Cu
9B	1	9.2	ASTM/ASME A/SA-203	D	K31718		65/37 [450/255]	Plate	3.5Ni
9B	1	9.2	ASTM/ASME A/SA-203	E	K32018		70/40 [485/275]	Plate	3.5Ni
9B	1	9.2	ASTM/ASME A/SA-203	F	—	>2 [>51]	75/50 [515/345]	Plate	3.5Ni
9B	1	9.2	ASTM/ASME A/SA-203	F	—	≤2 [≤51]	80/55 [550/380]	Plate	3.5Ni
9B	1	9.2	ASTM/ASME A/SA-333	3	K31918		65/35 [450/240]	Seamless & Welded Pipe	3.5Ni
9B	1	9.2	ASTM/ASME A/SA-334	3	K31918		65/35 [450/240]	Welded Tube	3.5Ni
9B	1	9.2	ASTM/ASME A/SA-350	LF3	K32025		70/37.5 [485/260]	Forgings	3.5Ni
9B	1	9.3	ASTM/ASME A/SA-352	LC3	J31550		70/40 [485/275]	Castings	3.5Ni
9B	1	9.2	ASTM/ASME A/SA-420	WPL3	K31918		65/35 [450/240]	Piping Fittings	3.5Ni
9B	1	—	ASTM A707	L7, Cl. 1	K32218		60/42 [415/290]	Forgings	3.5Ni
9B	1	—	ASTM A707	L7, Cl. 2	K32218		66/52 [455/360]	Forgings	3.5Ni
9B	1	—	ASTM A707	L8, Cl. 1	K42247		60/42 [415/290]	Forgings	3.5Ni-1.8Cr-0.5Mo-0.3Mn
9B	1	—	ASTM A707	L8, Cl. 2	K42247		66/52 [455/360]	Forgings	3.5Ni-1.8Cr-0.5Mo-0.3Mn
9B	1	—	ASTM A707	L8, Cl. 3	K42247		75/60 [515/415]	Forgings	3.5Ni-1.8Cr-0.5Mo-0.3Mn
9B	1	—	ASTM A707	L8, Cl. 4	K42247		90/75 [620/515]	Forgings	3.5Ni-1.8Cr-0.5Mo-0.3Mn
9B	1	9.2	ASTM/ASME A/SA-765	III	K32026		70/37.5 [485/260]	Forgings	3.5Ni
9C	1	9.3	ASTM/ASME A/SA-352	LC4	J41500		70/40 [485/275]	Castings	4.5Ni

Table C.2
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Specification	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
21	21	ASTM/ASME	B/SB-209	1060	A91060		8/2.5 [55/17]	Plate & Sheet	99.60Al
21	21	ASTM/ASME	B/SB-209	1100	A91100		11/3.5 [76/24]	Plate & Sheet	99.0Al-Cu
21	22.1	ASTM/ASME	B/SB-209	3003	A93003		14/5 [97/34]	Plate & Sheet	Al-Mn-Cu
21	22.2	ASTM/ASME	B/SB-209	5050	A95050		18/6 [125/41]	Plate & Sheet	Al-1.5Mg
21	—	ASTM/ASME	B/SB-209	Alclad 3003	—	≥0.5 and ≤3 [≥13 and ≤76]	14/5 [97/34]	Plate & Sheet	Al-Mn-Cu
21	—	ASTM/ASME	B/SB-209	Alclad 3003	—	>0.05 and <0.5 [>1.3 and <13]	13/4.5 [90/31]	Plate & Sheet	Al-Mn-Cu
21	—	ASTM/ASME	B/SB-209	Alclad 3003	A83003	≥0.5 [≥13]	14/5 [97/34]	Plate & Sheet	Al-Mn-Cu
21	—	ASTM/ASME	B/SB-209	Alclad 3003	A83003	<0.5 [<13]	13/4.5 [90/31]	Plate & Sheet	Al-Mn-Cu
21	21	ASTM/ASME	B/SB-210	1060	A91060		8.5/2.5 [59/17]	Seamless Tube	99.60Al
21	21	ASTM	B210	1100	A91100		11/3.5 [76/24]	Seamless Tube	99.0Al-Cu
21	22.1	ASTM/ASME	B/SB-210	3003	A93003		14/5 [97/34]	Seamless Tube	Al-Mn-Cu
21	22.1	ASTM	B210	3102	A93102		12/4 [82/28]	Seamless Tube	Al-0.3Mg
21	—	ASTM	B210	3303	A93303		14/5 [97/34]	Seamless Tube	Al-Mn
21	22.2	ASTM	B210	5050	A95050		18/6 [125/41]	Seamless Tube	Al-1.5Mg
21	—	ASTM/ASME	B/SB-210	Alclad 3003	—		13/4.5 [90/31]	Seamless Tube	Al-Mn-Cu
21	—	ASTM	B210	Alclad 3003	A83003		13/4.5 [90/31]	Seamless Tube	Al-Mn-Cu
21	—	ASTM	B210	Alclad 3102	—		10/3.5 [69/24]	Seamless Tube	Al-0.3Mg
21	—	ASTM	B210	Alclad 3303	—		13/4.5 [90/31]	Seamless Tube	Al-Mn
21	21	ASTM/ASME	B/SB-211	1060	A91060		8/2.5 [55/17]	Bar, Rod, & Wire	99.60Al
21	21	ASTM/ASME	B/SB-211	1100	A91100		11/3 [76/21]	Bar, Rod, & Wire	99.0Al-Cu
21	22.1	ASTM/ASME	B/SB-211	3003	A93003		14/5 [97/34]	Bar, Rod, & Wire	Al-Mn-Cu
21	21	ASTM/ASME	B/SB-221	1060	A91060		8.5/2.5 [59/17]	Bar, Rod, & Shapes	99.60Al
21	21	ASTM/ASME	B/SB-221	1100	A91100		11/3 [76/21]	Bar, Rod, & Shapes	99.0Al-Cu
21	22.1	ASTM/ASME	B/SB-221	3003	A93003		14/5 [97/34]	Bar, Rod, & Shapes	Al-Mn-Cu
21	22.1	ASTM/ASME	B/SB-221	3102	A93102		12/4 [82/28]	Bar, Rod, & Shapes	Al-0.3Mg
21	—	ASTM/ASME	B/SB-221	Alclad 3003	A83003		13/4.5 [90/31]	Bar, Rod, & Shapes	Al-Mn-Cu
21	21	ASTM	B230	1350	A91350		8/— [55/—]	Wire	99.50Al

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Specification	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
21	21	ASTM/ASME	B/SB-234	1060	A91060		8.5/2.5 [59/17]	Seamless Tube	99.60Al
21	22.1	ASTM/ASME	B/SB-234	3003	A93003		14/5 [97/34]	Seamless Tube	Al-Mn-Cu
21	—	ASTM/ASME	B/SB-234	Alclad 3003	—		13/4.5 [90/31]	Seamless Tube	Al-Mn-Cu
21	—	ASTM/ASME	B/SB-234	Alclad 3003	A83003		13/4.5 [90/31]	Seamless Tube	Al-Mn-Cu
21	21	ASTM	B236	1350	A91350		8/— [55/—]	Bar	99.50Al
21	21	ASTM/ASME	B/SB-241	1060	A91060		8.5/2.5 [59/17]	Seamless Pipe & Tube	99.60Al
21	21	ASTM/ASME	B/SB-241	1100	A91100		11/3 [76/21]	Seamless Pipe & Tube	99.0Al-Cu
21	22.1	ASTM/ASME	B/SB-241	3003	A93003		14/5 [97/34]	Seamless Pipe & Tube	Al-Mn-Cu
21	—	ASTM/ASME	B/SB-241	Alclad 3003	—		13/4.5 [90/31]	Seamless Pipe & Tube	Al-Mn-Cu
21	—	ASTM/ASME	B/SB-241	Alclad 3003	A83003		13/4.5 [90/31]	Seamless Pipe & Tube	Al-Mn-Cu
21	21	ASTM/ASME	B/SB-247	1100	A91100		11/4 [76/28]	Forgings	99.0Al-Cu
21	22.1	ASTM/ASME	B/SB-247	3003	A93003		14/5 [97/34]	Forgings	Al-Mn-Cu
21	21	ASTM	B313	1100	A91100		11/3.5 [76/24]	Welded Tube	99.0Al-Cu
21	22.1	ASTM	B313	3003	A93003		14/5 [97/34]	Welded Tube	Al-Mn-Cu
21	22.2	ASTM	B313	5050	A95050		18/6 [125/41]	Welded Tube	Al-1.5Mg
21	21	ASTM	B324	1350	A91350		8.5/— [59/—]	Wire	99.50Al
21	21	ASTM	B345	1060	A91060		8.5/2.5 [59/17]	Seamless Pipe & Tube	99.60Al
21	22.1	ASTM	B345	3003	A93003		14/5 [97/34]	Seamless Pipe & Tube	Al-Mn-Cu
21	—	ASTM	B345	Alclad 3003	A83003		13/4.5 [90/31]	Seamless Pipe & Tube	Al-Mn-Cu
21	—	ASTM	B361	WP Alclad 3003	A83003		13/4.5 [90/31]	Fittings	Al-Mn-Cu
21	21	ASTM	B361	WP1060	A91060		8.5/2.5 [59/17]	Fittings	99.60Al
21	21	ASTM	B361	WP1100	A91100		11/3 [76/21]	Fittings	99.0Al-Cu
21	22.1	ASTM	B361	WP3003	A93003		14/5 [97/34]	Fittings	Al-Mn-Cu
21	21	ASTM	B483	1060	A91060		8.5/2.5 [59/17]	Tube	99.60Al
21	21	ASTM	B483	1100	A91100		11/3.5 [76/24]	Tube	99.0Al-Cu
21	21	ASTM	B483	1435	A91435		9.5/3 [66/21]	Tube	99.35Al-Fe
21	22.1	ASTM	B483	3003	A93003		14/5 [97/34]	Tube	Al-Mn-Cu
21	22.1	ASTM	B483	3102	A93102		11/3.5 [76/24]	Tube	Al-0.3Mg
21	22.2	ASTM	B483	5050	A95050		18/6 [125/41]	Tube	Al-1.5Mg

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Specification	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
21	21	ASTM	B491	1050	A91050		8/2.5 [55/17]	Extruded Tube	99.5Al-Fe
21	21	ASTM	B491	1100	A91100		11/3 [76/21]	Extruded Tube	99.0Al-Cu
21	21	ASTM	B491	1200	A91200		11/9.5 [76/66]	Extruded Tube	99.0Al-Si-Fe
21	21	ASTM	B491	1235	A91235		9/3 [62/21]	Extruded Tube	99.5Al-Fe
21	22.1	ASTM	B491	3003	A93003		14/5 [97/34]	Extruded Tube	Al-Mn-Cu
21	22.1	ASTM	B491	3102	A93102		11/3.5 [76/24]	Extruded Tube	Al-0.3Mg
21	21	ASTM	B547	1100	A91100		11/3.5 [76/24]	Welded Tube	99.0Al-Cu
21	22.1	ASTM	B547	3003	A93003		14/5 [97/34]	Welded Tube	Al-Mn-Cu
21	22.2	ASTM	B547	5050	A95050		18/6 [125/41]	Welded Tube	Al-1.5Mg
21	—	ASTM	B547	Alclad 3003	A83003		13/4.5 [90/31]	Welded Tube	Al-Mn-Cu
21	21	ASTM	B609	1350	A91350		8.5/— [59/—]	Wire	99.50Al
22	22.2	ASTM/ASME	B/SB-209	3004	A93004		22/8.5 [150/59]	Plate & Sheet	Al-Mn-Mg
22	22.2	ASTM/ASME	B/SB-209	3005	A93005		17/6.5 [115/45]	Plate & Sheet	Al-Mn-Mg
22	22.2	ASTM/ASME	B/SB-209	3105	A93105		14/5 [97/34]	Plate & Sheet	Al-Mn-Mg
22	22.2	ASTM/ASME	B/SB-209	5005	A95005		15/5 [105/34]	Plate & Sheet	Al-1.5Mg
22	22.2	ASTM/ASME	B/SB-209	5010	A95010		15/5 [105/34]	Plate & Sheet	Al-0.4Mg-0.2Mn
22	22.3	ASTM/ASME	B/SB-209	5052	A95052		25/9.5 [170/66]	Plate & Sheet	Al-2.5Mg
22	22.4	ASTM/ASME	B/SB-209	5154	A95154		30/11 [205/76]	Plate & Sheet	Al-3.5Mg
22	22.3	ASTM/ASME	B/SB-209	5252	A95252		25/9.5 [170/66]	Plate & Sheet	Al-2.5Mg
22	22.4	ASTM/ASME	B/SB-209	5254	A95254		30/11 [205/76]	Plate & Sheet	Al-3.5Mg
22	22.3	ASTM/ASME	B/SB-209	5454	A95454		31/12 [215/83]	Plate & Sheet	Al-2.7Mg-Mn
22	22.2	ASTM/ASME	B/SB-209	5457	A95457		16/— [110/—]	Plate & Sheet	Al-1Mg-0.3Mn
22	22.3	ASTM/ASME	B/SB-209	5652	A95652		25/9.5 [170/66]	Plate & Sheet	Al-2.5Mg
22	—	ASTM/ASME	B/SB-209	Alclad 3004	—		≥0.5 [≥13]	Plate & Sheet	Al-Mn-Mg
22	—	ASTM/ASME	B/SB-209	Alclad 3004	—		<0.5 [<13]	Plate & Sheet	Al-Mn-Mg
22	—	ASTM/ASME	B/SB-209	Alclad 3004	—		>0.05 and <0.5 [≥1.3 and <13]	Plate & Sheet	Al-Mn-Mg
22	—	ASTM/ASME	B/SB-209	Alclad 3004	—		≥0.5 and ≤3 [≥13 and ≤76]	Plate & Sheet	Al-Mn-Mg

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Specification	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
22	22.2	ASTM	B210	5005	A95005		15/5 [105/34]	Seamless Tube	Al-1.5Mg
22	22.3	ASTM/ASME	B/SB-210	5052	A95052		25/10 [170/69]	Seamless Tube	Al-2.5Mg
22	22.4	ASTM/ASME	B/SB-210	5154	A95154		30/11 [205/76]	Seamless Tube	Al-3.5Mg
22	22.3	ASTM/ASME	B/SB-211	5052	A95052		25/9.5 [170/66]	Bar, Rod, & Wire	Al-2.5Mg
22	22.4	ASTM/ASME	B/SB-211	5154	A95154		30/11 [205/76]	Bar, Rod, & Wire	Al-3.5Mg
22	22.2	ASTM/ASME	B/SB-221	3004	A93004		23/8.5 [160/59]	Bar, Rod, & Shapes	Al-Mn-Mg
22	22.3	ASTM/ASME	B/SB-221	5052	A95052		25/10 [170/69]	Bar, Rod, & Shapes	Al-2.5Mg
22	22.4	ASTM/ASME	B/SB-221	5154	A95154		30/11 [205/76]	Bar, Rod, & Shapes	Al-3.5Mg
22	22.3	ASTM/ASME	B/SB-221	5454	A95454		31/12 [215/83]	Bar, Rod, & Shapes	Al-2.7Mg-Mn
22	22.3	ASTM/ASME	B/SB-234	5052	A95052		25/10 [170/69]	Seamless Tube	Al-2.5Mg
22	22.3	ASTM/ASME	B/SB-234	5454	A95454		31/12 [215/83]	Seamless Tube	Al-2.7Mg-Mn
22	22.3	ASTM/ASME	B/SB-241	5052	A95052		25/10 [170/69]	Seamless Pipe & Tube	Al-2.5Mg
22	22.3	ASTM/ASME	B/SB-241	5454	A95454		31/12 [215/83]	Seamless Pipe & Tube	Al-2.7Mg-Mn
22	22.2	ASTM	B313	3004	A93004		22/8.5 [150/59]	Welded Tube	Al-Mn-Mg
22	22.2	ASTM	B313	3005	A93005		17/6.5 [115/45]	Welded Tube	Al-Mn-Mg
22	22.3	ASTM	B313	5052	A95052		25/9.5 [170/66]	Welded Tube	Al-2.5Mg
22	22.4	ASTM	B313	5154	A95154		30/11 [205/76]	Welded Tube	Al-3.5Mg
22	—	ASTM	B313	Alclad 3004	—		21/8 [145/55]	Welded Tube	Al-Mn-Mg
22	22.3	ASTM	B361	5154	A95154		30/11 [205/76]	Fittings	Al-3.5Mg
22	22.2	ASTM	B396	5005	A95005		15/5 [105/34]	Wire	Al-1.5Mg
22	22.2	ASTM	B483	5005	A95005		15/5 [105/34]	Tube	Al-1.5Mg
22	22.3	ASTM	B483	5052	A95052		25/9.5 [170/66]	Tube	Al-2.5Mg
22	22.2	ASTM	B547	3004	A93004		22/8.5 [150/59]	Welded Tube	Al-Mn-Mg
22	22.3	ASTM	B547	5052	A95052		25/9.5 [170/66]	Welded Tube	Al-2.5Mg
22	22.4	ASTM	B547	5154	A95154		30/11 [205/76]	Welded Tube	Al-3.5Mg
22	22.3	ASTM	B547	5454	A95454		31/12 [215/83]	Welded Tube	Al-2.7Mg-Mn
22	—	ASTM	B547	Alclad 3004	—		21/8 [145/55]	Welded Tube	Al-Mn-Mg
23	23.1	ASTM/ASME	B/SB-209	6061	A96061		24/- [165/-]	Plate & Sheet	Al-Mg-Si-Cu
23	—	ASTM/ASME	B/SB-209	Alclad 6061	—		24/- [165/-]	Plate & Sheet	Al-Mg-Si-Cu

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Specification	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Aluminum and Aluminum Base Alloys									
23	—	ASTM/ASME	B/SB-209	Alclad 6061	A86061	<0.5 [<13]	23/– [160/–]	Plate & Sheet	Al-Mg-Si-Cu
23	—	ASTM/ASME	B/SB-209	Alclad 6061	A86061	≥ 0.5 [≥ 13]	24/– [165/–]	Plate & Sheet	Al-Mg-Si-Cu
23	23.1	ASTM/ASME	B/SB-210	6061	A96061		24/– [165/–]	Seamless Tube	Al-Mg-Si-Cu
23	23.1	ASTM/ASME	B/SB-210	6063	A96063		17/– [115/–]	Seamless Tube	Al-Mg-Si
23	23.1	ASTM/ASME	B/SB-211	6061	A96061		24/– [165/–]	Bar, Rod, & Wire	Al-Mg-Si-Cu
23	23.1	ASTM/ASME	B/SB-221	6005	A96005		24/– [165/–]	Bar, Rod, & Shapes	Al-Si-Mg
23	23.1	ASTM/ASME	B/SB-221	6005A	A96005		24/– [165/–]	Bar, Rod, & Shapes	Al-Si-Mg
23	23.1	ASTM/ASME	B/SB-221	6061	A96061		24/– [165/–]	Bar, Rod, & Shapes	Al-Mg-Si-Cu
23	23.1	ASTM/ASME	B/SB-221	6063	A96063		17/– [115/–]	Bar, Rod, & Shapes	Al-Mg-Si
23	23.1	ASTM/ASME	B/SB-221	6105	A96105		24/– [165/–]	Bar, Rod, & Shapes	Al-Si-Mg
23	23.1	ASTM/ASME	B/SB-221	6162	A96162		24/– [165/–]	Bar, Rod, & Shapes	Al-Si-Mg
23	23.1	ASTM/ASME	B/SB-221	6351	A96351		24/– [165/–]	Bar, Rod, & Shapes	Al-Si-Mg-Mn
23	23.1	ASTM/ASME	B/SB-221	6463	A96463		17/– [115/–]	Bar, Rod, & Shapes	Al-Si-Mg
23	23.1	ASTM/ASME	B/SB-234	6061	A96061		24/– [165/–]	Seamless Tube	Al-Mg-Si-Cu
23	23.1	ASTM/ASME	B/SB-241	6061	A96061		24/– [165/–]	Seamless Pipe & Tube	Al-Mg-Si-Cu
23	23.1	ASTM/ASME	B/SB-241	6063	A96063		17/– [115/–]	Seamless Pipe & Tube	Al-Mg-Si
23	23.1	ASTM/ASME	B/SB-241	6162	A96162		24/– [165/–]	Seamless Pipe & Tube	Al-Si-Mg
23	23.1	ASTM/ASME	B/SB-241	6351	A96351		24/– [165/–]	Seamless Pipe & Tube	Al-Si-Mg-Mn
23	23.1	ASTM/ASME	B/SB-247	6061	A96061		24/– [165/–]	Forgings	Al-Mg-Si-Cu
23	23.1	ASTM/ASME	B/SB-247	6151	A96151		24/– [165/–]	Forgings	Al-Mg-Si-Cr
23	23.1	ASTM/ASME	B/SB-308	6061	A96061		24/– [165/–]	Shapes	Al-Mg-Si-Cu
23	23.1	ASTM	B313	6061	A96061		24/– [165/–]	Welded Tube	Al-Mg-Si-Cu
23	23.1	ASTM	B317	6101	A96101		11/– [76/–]	Bar, Rod, Shapes, & Tube	Al-Mg-Si
23	23.1	ASTM	B345	6061	A96061		24/– [165/–]	Seamless Pipe & Tube	Al-Mg-Si-Cu
23	23.1	ASTM	B345	6063	A96063		17/– [115/–]	Seamless Pipe & Tube	Al-Mg-Si
23	23.1	ASTM	B345	6351	A96351		24/– [165/–]	Seamless Pipe & Tube	Al-Si-Mg-Mn
23	23.1	ASTM	B361	WP6061	A96061		24/– [165/–]	Fittings	Al-Mg-Si-Cu
23	23.1	ASTM	B361	WP6063	A96063		17/– [115/–]	Fittings	Al-Mg-Si
23	23.1	ASTM	B429	6061	A96061		24/– [165/–]	Pipe & Tube	Al-Mg-Si-Cu

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Specification	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Aluminum and Aluminum Base Alloys									
23	23.1	ASTM	B429	6063	A96063		17/- [115/-]	Pipe & Tube	Al-Mg-Si
23	23.1	ASTM	B483	6061	A96061		24/- [165/-]	Tube	Al-Mg-Si-Cu
23	23.1	ASTM	B483	6063	A96063		17/- [115/-]	Tube	Al-Mg-Si
23	23.1	ASTM	B491	6063	A96063		17/- [115/-]	Extruded Tube	Al-Mg-Si
23	23.1	ASTM	B547	6061	A96061		24/- [165/-]	Welded Tube	Al-Mg-Si-Cu
23	23.1	ISO	209	6082, T4, T6	A96082		24/- [165/-]	Bar, Rod, Shapes, & Tube	Al-1Si-Mg-Mn
24	26	ASTM/ASME	B/SB-209	2014	A92014		35/- [240/-]	Plate & Sheet	Al-4.5Cu-1Si-0.8Mn-0.6Mg
24	26	ASTM/ASME	B/SB-209	2219	A92219		35/- [240/-]	Plate & Sheet	Al-6Cu-0.3Mn-Ti-Zr
24	—	ASTM/ASME	B/SB-209	Alclad 2014	A82014		35/- [240/-]	Plate & Sheet	Al-4.5Cu-1Si-0.8Mn-0.6Mg
24	—	ASTM/ASME	B/SB-209	Alclad 2219	A82219		35/- [240/-]	Plate & Sheet	Al-6Cu-0.3Mn-Ti-Zr
24	26	ASTM	B210	2014	A92014		35/- [240/-]	Seamless Tube	Al-4.5Cu-1Si-0.8Mn-0.6Mg
24	26	ASTM/ASME	B/SB-211	2014	A92014		35/- [240/-]	Bar, Rod, & Wire	Al-4.5Cu-1Si-0.8Mn-0.6Mg
24	26	ASTM/ASME	B/SB-211	2219	A92219		35/- [240/-]	Bar, Rod, & Wire	Al-6Cu-0.3Mn-Ti-Zr
24	26	ASTM/ASME	B/SB-221	2014	A92014		35/- [240/-]	Bar, Rod, & Shapes	Al-4.5Cu-1Si-0.8Mn-0.6Mg
24	26	ASTM/ASME	B/SB-221	2219	A92219		35/- [240/-]	Bar, Rod, & Shapes	Al-6Cu-0.3Mn-Ti-Zr
24	26	ASTM/ASME	B/SB-241	2014	A92014		35/- [240/-]	Seamless Pipe & Tube	Al-4.5Cu-1Si-0.8Mn-0.6Mg
24	26	ASTM/ASME	B/SB-241	2219	A92219		35/- [240/-]	Seamless Pipe & Tube	Al-6Cu-0.3Mn-Ti-Zr
24	26	ASTM/ASME	B/SB-247	2014	A92014		35/- [240/-]	Forgings	Al-4.5Cu-1Si-0.8Mn-0.6Mg
24	26	ASTM/ASME	B/SB-247	2219	A92219		35/- [240/-]	Forgings	Al-6Cu-0.3Mn-Ti-Zr
25	22.4	ASTM/ASME	B/SB-209	5083	A95083	>0.05 and ≤1.5 [>1.3 and ≤38]	40/18 [275/125]	Plate & Sheet	Al-4.4Mg-Mn
25	22.4	ASTM/ASME	B/SB-209	5083	A95083	>7 and ≤8 [>178 and ≤203]	36/14 [250/97]	Plate & Sheet	Al-4.4Mg-Mn
25	22.4	ASTM/ASME	B/SB-209	5083	A95083	>5 and ≤7 [>127 and ≤178]	37/15 [255/105]	Plate & Sheet	Al-4.4Mg-Mn
25	22.4	ASTM/ASME	B/SB-209	5083	A95083	>1.5 and ≤3 [>38 and ≤76]	39/17 [270/115]	Plate & Sheet	Al-4.4Mg-Mn
25	22.4	ASTM/ASME	B/SB-209	5083	A95083	>3 and ≤5 [>76 and ≤127]	38/16 [260/110]	Plate & Sheet	Al-4.4Mg-Mn
25	22.4	ASTM/ASME	B/SB-209	5086	A95086		35/14 [240/97]	Plate & Sheet	Al-4.0Mg-Mn

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Specification	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Aluminum and Aluminum Base Alloys									
25	22.4	ASTM/ASME	B/SB-209	5456	A95456	>5 and ≤7 >127 and ≤178]	39/16 [270/110]	Plate & Sheet	Al-5.1Mg-Mn
25	22.4	ASTM/ASME	B/SB-209	5456	A95456	>7 and ≤8 >178 and ≤203]	38/15 [260/105]	Plate & Sheet	Al-5.1Mg-Mn
25	22.4	ASTM/ASME	B/SB-209	5456	A95456	>0.05 and ≤1.5 >1.3 and ≤38]	42/19 [290/130]	Plate & Sheet	Al-5.1Mg-Mn
25	22.4	ASTM/ASME	B/SB-209	5456	A95456	>3 and ≤5 >76 and ≤127]	40/17 [275/115]	Plate & Sheet	Al-5.1Mg-Mn
25	22.4	ASTM/ASME	B/SB-209	5456	A95456	>1.5 and ≤3 >38 and ≤76]	41/18 [285/125]	Plate & Sheet	Al-5.1Mg-Mn
25	22.4	ASTM	B210	5083	A95083		39/16 [270/110]	Seamless Tube	Al-4.4Mg-Mn
25	22.4	ASTM	B210	5086	A95086		35/14 [240/97]	Seamless Tube	Al-4.0Mg-Mn
25	22.4	ASTM	B210	5456	A95456		41/19 [285/130]	Seamless Tube	Al-5.1Mg-Mn
25	22.4	ASTM/ASME	B/SB-211	5056	A95056		38/— [260/—]	Bar, Rod, & Wire	Al-5Mg-Mn-Cr
25	—	ASTM/ASME	B/SB-211	Alclad 5056	—		37/— [255/—]	Bar, Rod, & Wire	Al-5Mg-Mn-Cr
25	22.4	ASTM/ASME	B/SB-221	5083	A95083		39/16 [270/110]	Bar, Rod, & Shapes	Al-4.4Mg-Mn
25	22.4	ASTM/ASME	B/SB-221	5086	A95086		35/14 [240/97]	Bar, Rod, & Shapes	Al-4.0Mg-Mn
25	22.4	ASTM/ASME	B/SB-221	5456	A95456		41/19 [285/130]	Bar, Rod, & Shapes	Al-5.1Mg-Mn
25	22.4	ASTM/ASME	B/SB-241	5083	A95083		39/16 [270/110]	Seamless Pipe & Tube	Al-4.4Mg-Mn
25	22.4	ASTM/ASME	B/SB-241	5086	A95086		35/14 [240/97]	Seamless Pipe & Tube	Al-4.0Mg-Mn
25	22.4	ASTM/ASME	B/SB-241	5456	A95456		41/19 [285/130]	Seamless Pipe & Tube	Al-5.1Mg-Mn
25	22.4	ASTM/ASME	B/SB-247	5083	A95083		38/16 [260/110]	Forgings	Al-4.4Mg-Mn
25	22.4	ASTM	B313	5086	A95086		35/14 [240/97]	Welded Tube	Al-4.0Mg-Mn
25	22.4	ASTM	B345	5083	A95083		39/16 [270/110]	Seamless Pipe & Tube	Al-4.4Mg-Mn
25	22.4	ASTM	B345	5086	A95086		35/14 [240/97]	Seamless Pipe & Tube	Al-4.0Mg-Mn
25	22.4	ASTM	B361	5083	A95083		39/16 [270/110]	Fittings	Al-4.4Mg-Mn
25	22.4	ASTM	B547	5083	A95083		40/18 [275/125]	Welded Tube	Al-4.4Mg-Mn
25	22.4	ASTM	B547	5086	A95086		35/14 [240/97]	Welded Tube	Al-4.0Mg-Mn
25	22.4	ASTM/ASME	B/SB-928	5083	A95083	>1.5 and ≤3 >38 and ≤76]	39/16 [270/110]	Plate & Sheet	Al-4.4Mg-Mn

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Specification	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Aluminum and Aluminum Base Alloys									
25	22.4	ASTM/ASME	B/SB-928	5086	A95086	>0.05 and ≤2 >1.3 and ≤51]	35/14 [240/97]	Plate & Sheet	Al-4.0Mg-Mn
25	22.4	ASTM/ASME	B/SB-928	5456	A95456	>1.5 and ≤3 >38 and ≤76]	41/19 [285/130]	Plate & Sheet	Al-5.1Mg-Mn
26	25	ASTM/ASME	B/SB-26	208.0	A02080		19/12 [130/83]	Castings	Al-3Si-4Cu
26	—	ASTM/ASME	B/SB-26	222.0, O	A02220		23/— [160/—]	Castings	Al-Cu-Mg
26	—	ASTM/ASME	B/SB-26	222.0, T61	A02220		30/— [205/—]	Castings	Al-Cu-Mg
26	25	ASTM/ASME	B/SB-26	319.0, F	A03190		23/13 [160/90]	Castings	Al-6Si-3Cu
26	25	ASTM/ASME	B/SB-26	319.0, T5	A03190		23/13 [160/90]	Castings	Al-6Si-3Cu
26	25	ASTM/ASME	B/SB-26	319.0, T6	A03190		31/20 [215/140]	Castings	Al-6Si-3Cu
26	25	ASTM/ASME	B/SB-26	328.0, F	A03280		25/14 [170/97]	Castings	Al-8Si-1Cu-Mn-Mg
26	25	ASTM/ASME	B/SB-26	328.0, T6	A03280		34/21 [235/145]	Castings	Al-8Si-1Cu-Mn-Mg
26	24.2	ASTM/ASME	B/SB-26	356.0, F	A03560		19/9.5 [130/66]	Castings	Al-Si-Mg
26	24.2	ASTM/ASME	B/SB-26	356.0, T51	A03560		23/16 [160/110]	Castings	Al-Si-Mg
26	24.2	ASTM/ASME	B/SB-26	356.0, T6	A03560		30/20 [205/140]	Castings	Al-Si-Mg
26	24.2	ASTM/ASME	B/SB-26	356.0, T7	A03560		31/— [215/—]	Castings	Al-Si-Mg
26	24.2	ASTM/ASME	B/SB-26	356.0, T71	A03560		25/18 [170/125]	Castings	Al-Si-Mg
26	24.1	ASTM/ASME	B/SB-26	443.0	A04430		17/7 [115/48]	Castings	Al-Si
26	23.1	ASTM/ASME	B/SB-26	512.0	A05120		17/10 [115/69]	Castings	Al-4Mg-2Si
26	23.1	ASTM/ASME	B/SB-26	514.0	A05140		22/9 [150/62]	Castings	Al-4Mg-Si
26	—	ASTM/ASME	B/SB-26	535.0	A05350		35/18 [240/125]	Castings	Al-7Mg-Mn
26	23.2	ASTM/ASME	B/SB-26	705.0, T5	A07050		30/17 [205/115]	Castings	Al-3Zn-Mg-Mn-Cr
26	23.2	ASTM/ASME	B/SB-26	710.0, T5	A07100		32/20 [220/140]	Castings	Al-6Zn-Mg
26	24.2	ASTM/ASME	B/SB-26	A356.0, T6	A13560		34/24 [235/165]	Castings	Al-Si-Mg
26	24.2	ASTM/ASME	B/SB-26	A356.0, T61	A13560		35/26 [240/180]	Castings	Al-Si-Mg
26	24.1	ASTM/ASME	B/SB-26	B443.0	A24430		17/6 [115/41]	Castings	Al-Si
26	25	ASTM/ASME	B/SB-108	308.0	A03080		24/— [165/—]	Castings	Al-5.5Si-4.5Cu
26	25	ASTM/ASME	B/SB-108	319.0	A03190		27/14 [185/97]	Castings	Al-6Si-3Cu
26	25	ASTM/ASME	B/SB-108	333.0, F	A03330		28/— [195/—]	Castings	Al-9Si-3.5Cu-Mg

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Specification	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Aluminum and Aluminum Base Alloys									
26	25	ASTM/ASME	B/SB-108	333.0, T5	A03330		28/- [195/-]	Castings	Al-9Si-3.5Cu-Mg
26	25	ASTM/ASME	B/SB-108	333.0, T6	A03330		28/- [195/-]	Castings	Al-9Si-3.5Cu-Mg
26	25	ASTM/ASME	B/SB-108	333.0, T7	A03330		28/- [195/-]	Castings	Al-9Si-3.5Cu-Mg
26	24.2	ASTM/ASME	B/SB-108	356.0, F	A03560		21/10 [145/69]	Castings	Al-Si-Mg
26	24.2	ASTM/ASME	B/SB-108	356.0, T6	A03560		33/22 [230/150]	Castings	Al-Si-Mg
26	24.2	ASTM/ASME	B/SB-108	356.0, T71	A03560		23/- [160/-]	Castings	Al-Si-Mg
26	24.1	ASTM/ASME	B/SB-108	443.0	A04430		21/7 [145/48]	Castings	Al-Si
26	23.2	ASTM/ASME	B/SB-108	513.0	A05130		22/12 [150/83]	Castings	Al-4Mg-Zn
26	—	ASTM/ASME	B/SB-108	535.0	A05350		35/18 [240/125]	Castings	Al-7Mg-Mn
26	24.2	ASTM/ASME	B/SB-108	A356.0	A13560		28/26 [195/180]	Castings	Al-Si-Mg
26	24.1	ASTM/ASME	B/SB-108	A444.0	A14440		17/- [115/-]	Castings	Al-7Si
26	24.1	ASTM/ASME	B/SB-108	B443.0	A24430		21/6 [145/41]	Castings	Al-Si
26	25	ASTM	B618	208.0	A02080		19/12 [130/83]	Castings	Al-3Si-4Cu
26	25	ASTM	B618	319.0	A03190		23/13 [160/90]	Castings	Al-6Si-3Cu
26	25	ASTM	B618	328.0	A03280		25/14 [170/97]	Castings	Al-8Si-1Cu-Mn-Mg
26	24.2	ASTM	B618	356.0	A03560		19/- [130/-]	Castings	Al-Si-Mg
26	24.1	ASTM	B618	443.0	A04430		17/7 [115/48]	Castings	Al-Si
26	23.1	ASTM	B618	514.0	A05140		22/9 [150/62]	Castings	Al-4Mg-Si
26	—	ASTM	B618	535.0	A05350		35/18 [240/125]	Castings	Al-7Mg-Mn
26	24.2	ASTM	B618	A356.0	A13560		34/24 [235/165]	Castings	Al-Si-Mg
26	24.1	ASTM	B618	B443.0	A24430		17/6 [115/41]	Castings	Al-Si
26	24.2	ASTM	B686	A356.0	A13560		23/- [160/-]	Castings	Al-Si-Mg
27	23.2	ASTM/ASME	B/SB-221	7005	A97005		-/- [-/-]	Bar, Rod, & Shapes	Al-Zn-Mg-Mn-Cr-Ti
27	23.2	ISO	209	7020, T5	A97020		40/- [275/-]	Bar, Rod, Shapes, & Tube	Al-4.5Zn-1.2Mg-Mn-Cr-Zr

Table C.2
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I.2.2.1, and I.3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
31	31	ASTM/ASME	B/SB-42	—	C10200	30/9 [205/62]	Seamless Pipe	99.95Cu-P	
31	31	ASTM/ASME	B/SB-42	—	C10300	30/9 [205/62]	Seamless Pipe	99.95Cu-P	
31	31	ASTM/ASME	B/SB-42	—	C10800	30/9 [205/62]	Seamless Pipe	99.95Cu-P	
31	31	ASTM/ASME	B/SB-42	—	C12000	30/9 [205/62]	Seamless Pipe	99.9Cu-P	
31	31	ASTM/ASME	B/SB-42	—	C12200	30/9 [205/62]	Seamless Pipe	99.9Cu-P	
31	31	ASTM	B68	—	C10200	30/9 [205/62]	Tube	99.95Cu-P	
31	31	ASTM	B68	—	C10300	30/9 [205/62]	Tube	99.95Cu-P	
31	31	ASTM	B68	—	C10800	30/9 [205/62]	Tube	99.95Cu-P	
31	31	ASTM	B68	—	C12000	30/9 [205/62]	Tube	99.9Cu-P	
31	31	ASTM	B68	—	C12200	30/9 [205/62]	Tube	99.9Cu-P	
31	31	ASTM/ASME	B/SB-75	—	C10100	30/9 [205/62]	Seamless Tube	99.99Cu-P	
31	31	ASTM/ASME	B/SB-75	—	C10200	30/9 [205/62]	Seamless Tube	99.95Cu-P	
31	31	ASTM/ASME	B/SB-75	—	C10300	30/9 [205/62]	Seamless Tube	99.95Cu-P	
31	31	ASTM/ASME	B/SB-75	—	C10800	30/9 [205/62]	Seamless Tube	99.95Cu-P	
31	31	ASTM/ASME	B/SB-75	—	C12000	30/9 [205/62]	Seamless Tube	99.9Cu-P	
31	31	ASTM/ASME	B/SB-75	—	C12200	30/9 [205/62]	Seamless Tube	99.9Cu-P	
31	31	ASTM/ASME	B/SB-75	—	C14200	30/9 [205/62]	Seamless Tube	99.40Cu-P	
31	31	ASTM	B88	—	C10200	30/- [205/-]	Tube	99.95Cu-P	
31	31	ASTM	B88	—	C12000	30/- [205/-]	Tube	99.9Cu-P	
31	31	ASTM	B88	—	C12200	30/- [205/-]	Tube	99.9Cu-P	
31	31	ASTM/ASME	B/SB-111	—	C10100	30/9 [205/62]	Seamless Tube	99.99Cu-P	
31	31	ASTM/ASME	B/SB-111	—	C10200	30/9 [205/62]	Seamless Tube	99.95Cu-P	
31	31	ASTM/ASME	B/SB-111	—	C10300	30/9 [205/62]	Seamless Tube	99.95Cu-P	
31	31	ASTM/ASME	B/SB-111	—	C10800	30/9 [205/62]	Seamless Tube	99.95Cu-P	
31	31	ASTM/ASME	B/SB-111	—	C12000	30/9 [205/62]	Seamless Tube	99.9Cu-P	
31	31	ASTM/ASME	B/SB-111	—	C12200	30/9 [205/62]	Seamless Tube	99.9Cu-P	
31	31	ASTM/ASME	B/SB-111	—	C14200	30/9 [205/62]	Seamless Tube	99.4Cu-As-P	
31	31	ASTM/ASME	B/SB-111	—	C19200	38/12 [260/83]	Seamless Tube	99.7Cu-Fe-P	
31	31	ASTM/ASME	B/SB-152	—	C10100	30/9 [205/62]	Plate, Sheet, Strip, & Bar	99.99Cu-P	

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Copper and Copper Base Alloys									
31	31	ASTM/ASME	B/SB-152	—	C10200	30/9	[205/62]	Plate, Sheet, Strip, & Bar	99.95Cu-P
31	31	ASTM/ASME	B/SB-152	—	C10300	30/9	[205/62]	Plate, Sheet, Strip, & Bar	99.95Cu-P
31	31	ASTM/ASME	B/SB-152	—	C10400	30/9	[205/62]	Plate, Sheet, Strip, & Bar	99.95Cu + Ag
31	31	ASTM/ASME	B/SB-152	—	C10500	30/9	[205/62]	Plate, Sheet, Strip, & Bar	99.95Cu + Ag
31	31	ASTM/ASME	B/SB-152	—	C10700	30/9	[205/62]	Plate, Sheet, Strip, & Bar	99.95Cu + Ag
31	31	ASTM/ASME	B/SB-152	—	C10800	30/9	[205/62]	Plate, Sheet, Strip, & Bar	99.95Cu-P
31	31	ASTM/ASME	B/SB-152	—	C11000	30/9	[205/62]	Plate, Sheet, Strip, & Bar	99.90Cu
31	31	ASTM/ASME	B/SB-152	—	C12000	30/9	[205/62]	Plate, Sheet, Strip, & Bar	99.9Cu-P
31	31	ASTM/ASME	B/SB-152	—	C12200	30/9	[205/62]	Plate, Sheet, Strip, & Bar	99.9Cu-P
31	31	ASTM/ASME	B/SB-152	—	C12300	30/9	[205/62]	Plate, Sheet, Strip, & Bar	99.9Cu-P
31	31	ASTM/ASME	B/SB-152	—	C14200	30/9	[205/62]	Plate, Sheet, Strip, & Bar	99.4Cu-As-P
31	31	ASTM/ASME	B/SB-152	—	C14420	30/9	[205/62]	Plate, Sheet, Strip, & Bar	99.99Cu-Sn-Te
31	31	ASTM	B170	1	C10100	30/9	[205/62]	Shapes	99.99Cu-P
31	31	ASTM	B170	2	C10200	30/9	[205/62]	Shapes	99.95Cu-P
31	31	ASTM/ASME	B/SB-187	—	C10100	28/8	[195/55]	Rod & Bar	99.99Cu-P
31	31	ASTM/ASME	B/SB-187	—	C10200	28/8	[195/55]	Rod & Bar	99.95Cu-P
31	31	ASTM/ASME	B/SB-187	—	C10300	28/8	[195/55]	Rod & Bar	99.95Cu-P
31	31	ASTM/ASME	B/SB-187	—	C10400	28/8	[195/55]	Rod & Bar	99.95Cu + Ag
31	31	ASTM/ASME	B/SB-187	—	C10700	28/8	[195/55]	Rod & Bar	99.95Cu + Ag
31	31	ASTM/ASME	B/SB-187	—	C10940	28/8	[195/55]	Rod & Bar	99.90Cu + Ag
31	31	ASTM/ASME	B/SB-187	—	C11000	28/8	[195/55]	Rod & Bar	99.9Cu
31	31	ASTM/ASME	B/SB-187	—	C14420	28/8	[195/55]	Rod & Bar	99.99Cu-Sn-Te
31	31	ASTM	B280	102	C10200	30/-	[205/-]	Seamless Tube	99.95Cu-P
31	31	ASTM	B280	120	C12000	30/-	[205/-]	Seamless Tube	99.9Cu-P
31	31	ASTM	B280	122	C12200	30/-	[205/-]	Seamless Tube	99.9Cu-P
31	31	ASTM	B302	—	C12000	30/9	[205/62]	Pipe	99.9Cu-P
31	31	ASTM	B302	—	C12200	30/9	[205/62]	Pipe	99.9Cu-P
31	31	ASTM	B359	—	C10100	30/9	[205/62]	Seamless Tube	99.99Cu-P
31	31	ASTM	B359	—	C10200	30/9	[205/62]	Seamless Tube	99.95Cu-P

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Copper and Copper Base Alloys									
31	31	ASTM	B359	—	C10300	—	30/9 [205/62]	Seamless Tube	99.95Cu-P
31	31	ASTM	B359	—	C10800	—	30/9 [205/62]	Seamless Tube	99.95Cu-P
31	31	ASTM	B359	—	C12000	—	30/9 [205/62]	Seamless Tube	99.9Cu-P
31	31	ASTM/ASME	B/SB-359	—	C12200	—	30/9 [205/62]	Seamless Tube	99.9Cu-P
31	31	ASTM	B359	—	C14200	—	30/9 [205/62]	Seamless Tube	99.40Cu-P
31	31	ASTM	B359	—	C19200	—	38/12 [260/83]	Seamless Tube	99.7Cu-Fe-P
31	31	ASTM/ASME	B/SB-395	—	C10200	—	30/9 [205/62]	Seamless Tube	99.95Cu-P
31	31	ASTM/ASME	B/SB-395	—	C10300	—	30/9 [205/62]	Seamless Tube	99.95Cu-P
31	31	ASTM/ASME	B/SB-395	—	C10800	—	30/9 [205/62]	Seamless Tube	99.95Cu-P
31	31	ASTM/ASME	B/SB-395	—	C12000	—	30/9 [205/62]	Seamless Tube	99.9Cu-P
31	31	ASTM/ASME	B/SB-395	—	C12200	—	30/9 [205/62]	Seamless Tube	99.9Cu-P
31	31	ASTM/ASME	B/SB-395	—	C14200	—	30/9 [205/62]	Seamless Tube	99.4Cu-As-P
31	31	ASTM/ASME	B/SB-395	—	C19200	—	38/12 [260/83]	Seamless Tube	99.7Cu-Fe-P
31	31	ASTM/ASME	B/SB-543	—	C10800	—	30/9 [205/62]	Welded Tube	99.95Cu-P
31	31	ASTM/ASME	B/SB-543	—	C12200	—	30/9 [205/62]	Welded Tube	99.9Cu-P
31	31	ASTM/ASME	B/SB-543	—	C19400	—	45/15 [310/105]	Welded Tube	97.5Cu-P
32	32.2	ASTM	B21	—	C46400	>1 and ≤2	52/20 [360/140]	Shapes	60Cu-39Zn-Sn
32	32.2	ASTM	B21	—	C46400	>25 and ≤50]	52/20 [360/140]	Rod & Bar	60Cu-39Zn-Sn
32	32.2	ASTM	B21	—	C46400	>2 [>50]	50/20 [345/140]	Rod & Bar	60Cu-39Zn-Sn
32	32.2	ASTM	B21	—	C46400	≤1 [≤25]	54/20 [370/140]	Rod & Bar	60Cu-39Zn-Sn
32	32.1	ASTM/ASME	B/SB-43	—	C23000	—	40/12 [275/83]	Seamless Pipe	85Cu-15Zn
32	32.1	ASTM/ASME	B/SB-111	—	C23000	—	40/12 [275/83]	Seamless Tube	85Cu-15Zn
32	32.1	ASTM/ASME	B/SB-111	—	C28000	—	50/20 [345/140]	Seamless Tube	60Cu-40Zn
32	32.2	ASTM/ASME	B/SB-111	—	C44300	—	45/15 [310/105]	Seamless Tube	71Cu-28Zn-1Sn-0.06As
32	32.2	ASTM/ASME	B/SB-111	—	C44400	—	45/15 [310/105]	Seamless Tube	71Cu-28Zn-1Sn-0.06Sb
32	32.2	ASTM/ASME	B/SB-111	—	C44500	—	45/15 [310/105]	Seamless Tube	71Cu-28Zn-1Sn-0.06P
32	32.2	ASTM/ASME	B/SB-111	—	C68700	—	50/18 [345/125]	Seamless Tube	78Cu-20Zn-2Al
32	32.1	ASTM/ASME	B/SB-135	—	C22000	—	38/12 [260/83]	Seamless Tube	90Cu-10Zn

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Copper and Copper Base Alloys									
32	32.1	ASTM/ASME	B/SB-135	—	C23000	40/12 [275/83]	40/12 [275/83]	Seamless Tube	85Cu-15Zn
32	32.2	ASTM/ASME	B/SB-171	—	C44300	45/15 [310/105]	45/15 [310/105]	Plate & Sheet	71Cu-28Zn-1Sn-0.06As
32	32.2	ASTM/ASME	B/SB-171	—	C44400	45/15 [310/105]	45/15 [310/105]	Plate & Sheet	71Cu-28Zn-1Sn-0.06Sb
32	32.2	ASTM/ASME	B/SB-171	—	C44500	45/15 [310/105]	45/15 [310/105]	Plate & Sheet	71Cu-28Zn-1Sn-0.06P
32	32.2	ASTM/ASME	B/SB-171	—	C46400	50/18 [345/125]	50/18 [345/125]	Plate & Sheet	60Cu-39Zn-Sn
32	32.2	ASTM/ASME	B/SB-171	—	C46500	50/18 [345/125]	50/18 [345/125]	Plate & Sheet	60Cu-39Zn-As
32	32.1	ASTM	B359	—	C23000	40/12 [275/83]	40/12 [275/83]	Seamless Tube	85Cu-15Zn
32	32.2	ASTM/ASME	B/SB-359	—	C44300	45/15 [310/105]	45/15 [310/105]	Seamless Tube	71Cu-28Zn-1Sn-0.06As
32	32.2	ASTM/ASME	B/SB-359	—	C44400	45/15 [310/105]	45/15 [310/105]	Seamless Tube	71Cu-28Zn-1Sn-0.06Sb
32	32.2	ASTM/ASME	B/SB-359	—	C44500	45/15 [310/105]	45/15 [310/105]	Seamless Tube	71Cu-28Zn-1Sn-0.06P
32	32.2	ASTM	B359	—	C68700	50/18 [345/125]	50/18 [345/125]	Seamless Tube	78Cu-20Zn-2Al
32	32.1	ASTM/ASME	B/SB-395	—	C23000	40/12 [275/83]	40/12 [275/83]	Seamless Tube	85Cu-15Zn
32	32.2	ASTM/ASME	B/SB-395	—	C44300	45/15 [310/105]	45/15 [310/105]	Seamless Tube	71Cu-28Zn-1Sn-0.06As
32	32.2	ASTM/ASME	B/SB-395	—	C44400	45/15 [310/105]	45/15 [310/105]	Seamless Tube	71Cu-28Zn-1Sn-0.06Sb
32	32.2	ASTM/ASME	B/SB-395	—	C44500	45/15 [310/105]	45/15 [310/105]	Seamless Tube	71Cu-28Zn-1Sn-0.06P
32	32.2	ASTM/ASME	B/SB-395	—	C68700	50/18 [345/125]	50/18 [345/125]	Seamless Tube	78Cu-20Zn-2Al
32	32.1	ASTM/ASME	B/SB-543	—	C23000	40/12 [275/83]	40/12 [275/83]	Welded Tube	85Cu-15Zn
32	32.2	ASTM/ASME	B/SB-543	—	C44300	45/15 [310/105]	45/15 [310/105]	Welded Tube	71Cu-28Zn-1Sn-0.06As
32	32.2	ASTM/ASME	B/SB-543	—	C44400	45/15 [310/105]	45/15 [310/105]	Welded Tube	71Cu-28Zn-1Sn-0.06Sb
32	32.2	ASTM/ASME	B/SB-543	—	C44500	45/15 [310/105]	45/15 [310/105]	Welded Tube	71Cu-28Zn-1Sn-0.06P
32	32.2	ASTM/ASME	B/SB-543	—	C68700	50/18 [345/125]	50/18 [345/125]	Welded Tube	78Cu-20Zn-2Al
33	37	ASTM/ASME	B/SB-96	—	C65100	38/- [260/-]	38/- [260/-]	Plate, Sheet, Strip, & Bar	98.5Cu-1.5Si
33	37	ASTM/ASME	B/SB-96	—	C65400	65/- [450/-]	65/- [450/-]	Plate, Sheet, Strip, & Bar	98.5Cu-3Si-1.5Sn-Cr
33	37	ASTM/ASME	B/SB-96	—	C65500	50/18 [345/125]	50/18 [345/125]	Plate, Sheet, Strip, & Bar	97Cu-3Si
33	37	ASTM/ASME	B/SB-98	—	C65100	40/12 [275/83]	40/12 [275/83]	Rod, Bar, & Shapes	98.5Cu-1.5Si
33	37	ASTM/ASME	B/SB-98	—	C65500	52/15 [360/105]	52/15 [360/105]	Rod, Bar, & Shapes	97Cu-3Si
33	37	ASTM/ASME	B/SB-98	—	C66100	52/15 [360/105]	52/15 [360/105]	Rod, Bar, & Shapes	94Cu-3Si
33	31	ASTM/ASME	B/SB-283	—	C65500	50/15 [345/105]	50/15 [345/105]	Forgings	97Cu-3Si
33	37	ASTM/ASME	B/SB-315	—	C65100	40/10 [275/69]	40/10 [275/69]	Seamless Pipe & Tube	98.5Cu-1.5Si

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Copper and Copper Base Alloys									
33	34	ASTM/ASME	B/SB-315	—	C65500	50/15 [345/105]	Seamless Pipe & Tube	Seamless Pipe & Tube	97Cu-3Si
34	34	ASTM/ASME	B/SB-111	—	C70400	38/12 [260/83]	Seamless Tube	Seamless Tube	95Cu-5Ni
34	34	ASTM/ASME	B/SB-111	—	C70600	40/15 [275/105]	Seamless Tube	Seamless Tube	90Cu-10Ni
34	34	ASTM/ASME	B/SB-111	—	C71000	45/16 [310/110]	Seamless Tube	Seamless Tube	80Cu-20Ni
34	34	ASTM/ASME	B/SB-111	—	C71500	52/18 [360/125]	Seamless Tube	Seamless Tube	70Cu-30Ni
34	34	ASTM/ASME	B/SB-111	—	C71640	63/25 [435/170]	Seamless Tube	Seamless Tube	66Cu-30Ni-2Fe-2Mn
34	34	ASTM/ASME	B/SB-111	—	C72200	45/16 [310/110]	Seamless Tube	Seamless Tube	80Cu-16Ni-0.75Fe-0.5Cr
34	34	ASTM/ASME	B/SB-151	—	C70600	38/15 [260/105]	Rod & Bar	Rod & Bar	90Cu-10Ni
34	34	ASTM/ASME	B/SB-151	—	C71500	45/15 [310/105]	Bar (Rect.) & Shapes	Bar (Rect.) & Shapes	70Cu-30Ni
34	34	ASTM/ASME	B/SB-151	—	C71500	52/18 [360/125]	Sq Bar & Rod (Rnd, Hex, Oct)	Sq Bar & Rod (Rnd, Hex, Oct)	70Cu-30Ni
34	34	ASTM/ASME	B/SB-151	—	C71500	45/18 [310/125]	Sq Bar & Rod (Rnd, Hex, Oct)	Sq Bar & Rod (Rnd, Hex, Oct)	70Cu-30Ni
34	34	ASTM/ASME	B/SB-151	—	C71500	48/18 [330/125]	Sq Bar & Rod (Rnd, Hex, Oct)	Sq Bar & Rod (Rnd, Hex, Oct)	70Cu-30Ni
34	34	ASTM/ASME	B/SB-171	—	C70600	40/15 [275/105]	Plate & Sheet	Plate & Sheet	90Cu-10Ni
34	34	ASTM/ASME	B/SB-171	—	C71500	50/20 [345/140]	Plate & Sheet	Plate & Sheet	70Cu-30Ni
34	34	ASTM/ASME	B/SB-171	—	C71500	45/18 [310/125]	Plate & Sheet	Plate & Sheet	70Cu-30Ni
34	34	ASTM/ASME	B/SB-171	—	C72200	42/16 [290/110]	Plate & Sheet	Plate & Sheet	80Cu-16Ni-0.75Fe-0.5Cr
34	34	ASTM	B359	—	C70400	38/12 [260/83]	Seamless Tube	Seamless Tube	95Cu-5Ni
34	34	ASTM/ASME	B/SB-359	—	C70600	40/15 [275/105]	Seamless Tube	Seamless Tube	90Cu-10Ni
34	34	ASTM/ASME	B/SB-359	—	C71000	45/16 [310/110]	Seamless Tube	Seamless Tube	80Cu-20Ni
34	34	ASTM/ASME	B/SB-359	—	C71500	52/18 [360/125]	Seamless Tube	Seamless Tube	70Cu-30Ni
34	34	ASTM	B359	—	C72200	45/16 [310/110]	Seamless Tube	Seamless Tube	80Cu-16Ni-0.75Fe-0.5Cr
34	34	ASTM/ASME	B/SB-369	—	C96200	45/25 [310/170]	Castings	Castings	87.5Cu-10Ni-Fe-Mn
34	34	ASTM/ASME	B/SB-395	—	C70400	38/12 [260/83]	Seamless Tube	Seamless Tube	95Cu-5Ni
34	34	ASTM/ASME	B/SB-395	—	C70600	40/15 [275/105]	Seamless Tube	Seamless Tube	90Cu-10Ni
34	34	ASTM/ASME	B/SB-395	—	C71000	45/16 [310/110]	Seamless Tube	Seamless Tube	80Cu-20Ni
34	34	ASTM/ASME	B/SB-395	—	C71500	52/18 [360/125]	Seamless Tube	Seamless Tube	70Cu-30Ni
34	34	ASTM/ASME	B/SB-395	—	C72200	45/16 [310/110]	Seamless Tube	Seamless Tube	80Cu-16Ni-0.75Fe-0.5Cr

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Copper and Copper Base Alloys									
34	34	ASTM/ASME	B/SB-466	—	C70400		37/12 [255/83]	Seamless Pipe & Tube	95Cu-5Ni
34	34	ASTM/ASME	B/SB-466	—	C70600		38/13 [260/90]	Seamless Pipe & Tube	90Cu-10Ni
34	34	ASTM/ASME	B/SB-466	—	C71000		45/16 [310/110]	Seamless Pipe & Tube	80Cu-20Ni
34	34	ASTM/ASME	B/SB-466	—	C71500		52/18 [360/125]	Seamless Pipe & Tube	70Cu-30Ni
34	34	ASTM/ASME	B/SB-466	—	C72200		40/14 [275/97]	Seamless Pipe & Tube	80Cu-16Ni-0.75Fe-0.5Cr
34	34	ASTM/ASME	B/SB-467	—	C70600	>4.5 [>114]	38/13 [260/90]	Welded Pipe	90Cu-10Ni
34	34	ASTM/ASME	B/SB-467	—	C70600	≤4.5 [≤114]	40/15 [275/105]	Welded Pipe	90Cu-10Ni
34	34	ASTM/ASME	B/SB-467	—	C71500	>4.5 [>114]	45/15 [310/105]	Welded Pipe	70Cu-30Ni
34	34	ASTM/ASME	B/SB-467	—	C71500	≤4.5 [≤114]	50/20 [345/140]	Welded Pipe	70Cu-30Ni
34	34	ASTM/ASME	B/SB-543	—	C70400		38/12 [260/83]	Welded Tube	95Cu-5Ni
34	34	ASTM/ASME	B/SB-543	—	C70600		40/15 [275/105]	Welded Tube	90Cu-10Ni
34	34	ASTM	B543	—	C71000		45/16 [310/110]	Welded Tube	80Cu-20Ni
34	34	ASTM/ASME	B/SB-543	—	C71500		52/18 [360/125]	Welded Tube	70Cu-30Ni
34	34	ASTM/ASME	B/SB-543	—	C71640		63/25 [435/170]	Welded Tube	66Cu-30Ni-2Fe-2Mn
34	34	ASTM	B543	—	C72200		45/16 [310/110]	Welded Tube	80Cu-16Ni-0.75Fe-0.5Cr
34	34	ASTM	B608	—	C70620		40/— [275/—]	Welded Pipe	87Cu-10Ni-1.4Fe
34	34	ASTM	B608	—	C71520		50/— [345/—]	Welded Pipe	65Cu-31Ni-0.7Fe
34	34	ASTM/ASME	B/SB-956	—	C70600		40/15 [275/105]	Finned Welded Tube	90Cu-10Ni
34	34	ASTM/ASME	B/SB-956	—	C71500		52/18 [360/125]	Finned Welded Tube	70Cu-30Ni
35	35	ASTM/ASME	B/SB-111	—	C60800		50/19 [345/130]	Seamless Tube	95Cu-5Al
35	35	ASTM/ASME	B/SB-111	—	C61300		70/30 [485/205]	Seamless Tube	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-111	—	C61400		70/30 [485/205]	Seamless Tube	90Cu-7Al-3Fe
35	35	ASTM/ASME	B/SB-148	—	C95200		65/25 [450/170]	Castings	88Cu-9Al-3Fe
35	35	ASTM/ASME	B/SB-148	—	C95300		65/25 [450/170]	Castings	89Cu-10Al-1Fe
35	35	ASTM/ASME	B/SB-148	—	C95400		75/30 [515/205]	Castings	85Cu-11Al-4Fe
35	35	ASTM/ASME	B/SB-148	—	C95410		75/30 [515/205]	Castings	84Cu-10Al-4Fe-2Ni
35	35	ASTM/ASME	B/SB-148	—	C95500		90/40 [620/275]	Castings	82Cu-11Al-4Fe-3Mn
35	35	ASTM/ASME	B/SB-148	—	C95600		60/28 [415/195]	Castings	90Cu-7Al-3Si
35	35	ASTM/ASME	B/SB-148	—	C95700		90/40 [620/275]	Castings	75Cu-8Al-3Fe-2-Ni-12Mn

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Copper and Copper Base Alloys									
35	35	ASTM/ASME	B/SB-148	—	C95800	—	85/35 [585/240]	Castings	81Cu-9Al-4.5Ni-4Fe-1.2Mn
35	35	ASTM/ASME	B/SB-150	—	C61300	≤0.5 [≤13]	80/40 [550/275]	Bar & Rod (Hex & Oct)	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-150	—	C61300	>2 and ≤3 >50 and ≤75]	70/35 [485/240]	Rod (Round)	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-150	—	C61300	>1 and ≤2 >25 and ≤50]	70/32 [485/220]	Bar & Rod (Hex & Oct)	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-150	—	C61300	>0.5 and ≤1 >13 and ≤25]	75/45 [515/310]	Rod (Round)	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-150	—	C61300	≤0.5 [≤13]	80/50 [550/345]	Rod (Round)	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-150	—	C61300	>0.5 and ≤1 >13 and ≤25]	75/35 [515/240]	Bar & Rod (Hex & Oct)	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-150	—	C61300	>1 and ≤2 >25 and ≤50]	72/40 [495/275]	Rod (Round)	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-150	—	C61400	>0.5 and ≤1 >13 and ≤25]	75/35 [515/240]	Bar & Rod	90Cu-7Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C61400	>2 and ≤3 >50 and ≤75]	70/30 [485/205]	Bar & Rod	90Cu-7Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C61400	>1 and ≤2 >25 and ≤50]	70/32 [485/220]	Bar & Rod	90Cu-7Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C61400	≤0.5 [≤13]	80/40 [550/275]	Bar & Rod	90Cu-7Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C61900	>0.5 and ≤1 >13 and ≤25]	88/44 [605/305]	Rod (Round)	87Cu-9Al-4Fe
35	35	ASTM/ASME	B/SB-150	—	C61900	≤0.5 [≤13]	90/50 [620/345]	Rod (Round)	87Cu-9Al-4Fe
35	35	ASTM/ASME	B/SB-150	—	C61900	>1 and ≤2 >25 and ≤50]	85/40 [585/275]	Rod (Round)	87Cu-9Al-4Fe
35	35	ASTM/ASME	B/SB-150	—	C61900	>3 [>75]	75/30 [515/205]	Rod (Round)	87Cu-9Al-4Fe
35	35	ASTM/ASME	B/SB-150	—	C61900	≤0.5 [≤13]	75/30 [515/205]	Shapes	87Cu-9Al-4Fe
35	35	ASTM/ASME	B/SB-150	—	C61900	>2 and ≤3 >50 and ≤75]	78/37 [540/255]	Rod (Round)	87Cu-9Al-4Fe
35	35	ASTM/ASME	B/SB-150	—	C62300	>0.5 and ≤1 >13 and ≤25]	88/44 [605/305]	Rod (Round)	88Cu-9Al-3Fe

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Copper and Copper Base Alloys									
35	35	ASTM/ASME	B/SB-150	—	C62300	>2 [>50]	75/30 [515/205]	Bar & Rod (Hex & Oct)	88Cu-9Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C62300		75/30 [515/205]	Shapes	88Cu-9Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C62300	≤ 1 [≤ 25]	80/35 [550/240]	Bar & Rod (Hex & Oct)	88Cu-9Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C62300	>2 and ≤ 3 [>50 and ≤ 75]	76/37 [525/255]	Rod (Round)	88Cu-9Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C62300	>3 [>75]	75/30 [515/205]	Rod (Round)	88Cu-9Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C62300	>1 and ≤ 2 [>25 and ≤ 50]	84/40 [580/275]	Rod (Round)	88Cu-9Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C62300	>1 and ≤ 2 [>25 and ≤ 50]	78/32 [540/220]	Bar & Rod (Hex & Oct)	88Cu-9Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C62300	≤ 0.5 [≤ 13]	90/50 [620/345]	Rod (Round)	88Cu-9Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C62400		90/35 [620/240]	Shapes	87Cu-10Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C62400	>3 and ≤ 5 [>75 and ≤ 125]	90/35 [620/240]	Rod (Round)	87Cu-10Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C62400	>2 and ≤ 3 [>50 and ≤ 75]	90/40 [620/275]	Rod (Round)	87Cu-10Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C62400	>1 and ≤ 2 [>25 and ≤ 50]	90/43 [620/295]	Rod (Round)	87Cu-10Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C62400	>0.5 and ≤ 5 [>13 and ≤ 125]	90/35 [620/240]	Bar, & Rod (Hex & Oct)	87Cu-10Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C62400	≤ 1 [≤ 25]	95/45 [655/310]	Rod (Round)	87Cu-10Al-3Fe
35	35	ASTM/ASME	B/SB-150	—	C63000		85/42.5 [585/295]	Shapes	81Cu-10Al-5Ni-3Fe
35	35	ASTM/ASME	B/SB-150	—	C63000	≥ 0.5 and ≤ 1 [≥ 13 and ≤ 25]	100/50 [690/345]	Bar & Rod	81Cu-10Al-5Ni-3Fe
35	35	ASTM/ASME	B/SB-150	—	C63000	>1 and ≤ 2 [>25 and ≤ 50]	90/45 [620/310]	Bar & Rod	81Cu-10Al-5Ni-3Fe
35	35	ASTM/ASME	B/SB-150	—	C63000	>2 and ≤ 4 [>50 and ≤ 100]	85/42.5 [585/295]	Bar & Rod	81Cu-10Al-5Ni-3Fe
35	35	ASTM/ASME	B/SB-150	—	C63000	>4 [>100]	80/40 [550/275]	Bar & Rod	81Cu-10Al-5Ni-3Fe
35	35	ASTM/ASME	B/SB-150	—	C63020	>1 and ≤ 2 [>25 and ≤ 50]	130/95 [895/655]	Bar & Rod	80Cu-10Al-5Ni-5Fe

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Copper and Copper Base Alloys									
35	35	ASTM/ASME	B/SB-150	—	C63020	>2 and ≤4 [>50 and ≤100]	130/90 [895/620]	Bar & Rod	80Cu-10Al-5Ni-5Fe
35	35	ASTM/ASME	B/SB-150	—	C63020	≤1 [≤25]	135/100 [930/690]	Bar & Rod	80Cu-10Al-5Ni-5Fe
35	35	ASTM/ASME	B/SB-150	—	C63200		90/40 [620/275]	Bar, Rod, & Shapes	83Cu-9Al-4Ni-4Fe
35	35	ASTM/ASME	B/SB-150	—	C64200	>0.5 and ≤1 [>13 and ≤25]	85/45 [585/310]	Bar & Rod	91Cu-7Al-2Si
35	35	ASTM/ASME	B/SB-150	—	C64200	>4 [>100]	70/25 [485/170]	Bar & Rod	91Cu-7Al-2Si
35	35	ASTM/ASME	B/SB-150	—	C64200	>3 and ≤4 [>75 and ≤100]	70/30 [485/205]	Bar & Rod	91Cu-7Al-2Si
35	35	ASTM/ASME	B/SB-150	—	C64200	>2 and ≤3 [>50 and ≤75]	75/35 [515/240]	Bar & Rod	91Cu-7Al-2Si
35	35	ASTM/ASME	B/SB-150	—	C64200	>1 and ≤2 [>25 and ≤50]	80/42 [550/290]	Bar & Rod	91Cu-7Al-2Si
35	35	ASTM/ASME	B/SB-150	—	C64200		70/30 [485/205]	Shapes	91Cu-7Al-2Si
35	35	ASTM/ASME	B/SB-150	—	C64200	≤0.5 [≤13]	90/45 [620/310]	Bar & Rod	91Cu-7Al-2Si
35	35	ASTM/ASME	B/SB-169	—	C61300	>2 and ≤5 [>51 and ≤127]	65/28 [450/195]	Plate, Sheet, Strip, & Bar	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-169	—	C61300	>0.5 and ≤2 [>13 and ≤51]	72/32 [485/220]	Plate, Sheet, Strip, & Bar	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-169	—	C61300	≤0.5 [≤13]	75/36 [515/250]	Plate, Sheet, Strip, & Bar	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-169	—	C61400	>2 and ≤5 [>51 and ≤127]	65/28 [450/195]	Plate, Sheet, Strip, & Bar	90Cu-7Al-3Fe
35	35	ASTM/ASME	B/SB-169	—	C61400	>0.5 and ≤2 [>13 and ≤51]	70/30 [485/205]	Plate, Sheet, Strip, & Bar	90Cu-7Al-3Fe
35	35	ASTM/ASME	B/SB-169	—	C61400	≤0.5 [≤13]	72/32 [495/220]	Plate, Sheet, Strip, & Bar	90Cu-7Al-3Fe
35	35	ASTM/ASME	B/SB-171	—	C61300	>2 and ≤3 [>50 and ≤80]	70/30 [485/205]	Plate & Sheet	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-171	—	C61300	≤2 [≤50]	75/37 [515/255]	Plate & Sheet	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-171	—	C61300	>3 and ≤5 [>80 and ≤130]	65/28 [450/195]	Plate & Sheet	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-171	—	C61400	≤2 [≤51]	70/28 [485/195]	Plate & Sheet	90Cu-7Al-3Fe

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Copper and Copper Base Alloys									
35	35	ASTM/ASME	B/SB-171	—	C61400	>2 and ≤5 [>51 and ≤127]	65/26 [450/180]	Plate & Sheet	90Cu-7Al-3Fe
35	35	ASTM/ASME	B/SB-171	—	C63000	≤2 [≤51]	90/36 [620/250]	Plate & Sheet	81Cu-10Al-5Ni-3Fe
35	35	ASTM/ASME	B/SB-171	—	C63000	>2 and ≤3.5 [>51 and ≤89]	85/33 [585/230]	Plate & Sheet	81Cu-10Al-5Ni-3Fe
35	35	ASTM/ASME	B/SB-171	—	C63000	>3.5 and ≤5 [>89 and ≤127]	80/30 [550/205]	Plate & Sheet	81Cu-10Al-5Ni-3Fe
35	35	ASTM/ASME	B/SB-171	—	C63200	>3.5 and ≤5 [>89 and ≤127]	80/30 [550/205]	Plate & Sheet	83Cu-9Al-4Ni-4Fe
35	35	ASTM/ASME	B/SB-171	—	C63200	≤2 [≤51]	90/36 [620/250]	Plate & Sheet	83Cu-9Al-4Ni-4Fe
35	35	ASTM/ASME	B/SB-171	—	C63200	>2 and ≤3.5 [>51 and ≤89]	85/33 [585/230]	Plate & Sheet	83Cu-9Al-4Ni-4Fe
35	35	ASTM/ASME	B/SB-271	—	C95200		65/25 [450/170]	Castings	88Cu-9Al-3Fe
35	35	ASTM/ASME	B/SB-271	—	C95300		65/25 [450/170]	Castings	89Cu-10Al-1Fe
35	35	ASTM/ASME	B/SB-271	—	C95400		75/30 [515/205]	Castings	85Cu-11Al-4Fe
35	35	ASTM/ASME	B/SB-271	—	C95410		75/30 [515/205]	Castings	84Cu-10Al-4Fe-2Ni
35	35	ASTM/ASME	B/SB-271	—	C95500		90/40 [620/275]	Castings	82Cu-11Al-4Fe-3Mn
35	35	ASTM/ASME	B/SB-283	—	C64200	>1.5 [>40]	68/23 [470/160]	Forgings	91Cu-7Al-2Si
35	35	ASTM/ASME	B/SB-283	—	C64200	≤1.5 [≤40]	70/25 [485/170]	Forgings	91Cu-7Al-2Si
35	35	ASTM/ASME	B/SB-315	—	C61300		65/28 [450/195]	Seamless Pipe & Tube	90Cu-7Al-2.5Fe-Sn
35	35	ASTM/ASME	B/SB-315	—	C61400		65/28 [450/195]	Seamless Pipe & Tube	90Cu-7Al-3Fe
35	35	ASTM	B359	—	C60800		50/19 [345/130]	Seamless Tube	95Cu-5Al
35	35	ASTM/ASME	B/SB-395	—	C60800		50/19 [345/130]	Seamless Tube	95Cu-5Al
35	35	ASTM/ASME	B/SB-505	—	C95200		68/26 [470/180]	Castings	88Cu-9Al-3Fe
35	35	ASTM	B608	—	C61300		70/- [485/-]	Welded Pipe	90Cu-7Al-2.5Fe-Sn
35	35	ASTM	B608	—	C61400		70/- [485/-]	Welded Pipe	90Cu-7Al-3Fe

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I.2.2.1, and I.3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
41	41	ASTM/ASME	B/SB-160	—	N02200	55/15 [380/105]	Rod & Bar	99.0Ni	
41	41	ASTM/ASME	B/SB-160	—	N02201	50/10 [345/69]	Rod & Bar	99.0Ni-Low C	
41	41	ASTM/ASME	B/SB-161	—	N02200	55/12 [380/83]	Seamless Pipe, Tube	99.0Ni	
41	41	ASTM/ASME	B/SB-161	—	N02201	50/10 [345/69]	Seamless Pipe, Tube	99.0Ni-Low C	
41	41	ASTM/ASME	B/SB-162	—	N02200	55/15 [380/105]	Plate, Sheet, & Strip	99.0Ni	
41	41	ASTM/ASME	B/SB-162	—	N02201	50/12 [345/83]	Plate, Sheet, & Strip	99.0Ni-Low C	
41	41	ASTM/ASME	B/SB-163	—	N02200	55/15 [380/105]	Seamless Tube	99.0Ni	
41	41	ASTM/ASME	B/SB-163	—	N02201	50/12 [345/83]	Seamless Tube	99.0Ni-Low C	
41	41	ASTM/ASME	B/SB-366	—	N02200	55/15 [380/105]	Fittings	99.0Ni	
41	41	ASTM/ASME	B/SB-366	—	N02201	50/10 [345/69]	Fittings	99.0Ni-Low C	
41	41	ASTM/ASME	B/SB-564	—	N02200	55/15 [380/105]	Forgings	99.0Ni	
41	41	ASTM	B725	—	N02200	55/12 [380/83]	Welded Pipe	99.0Ni	
42	42	ASTM/ASME	B/SB-127	—	N04400	70/28 [485/195]	Plate, Sheet, & Strip	67Ni-30Cu	
42	42	ASTM/ASME	B/SB-163	—	N04400	70/28 [485/195]	Seamless Tube	67Ni-30Cu	
42	42	ASTM/ASME	B/SB-164	—	N04400	70/25 [485/170]	Rod, Bar, & Wire	67Ni-30Cu	
42	42	ASTM/ASME	B/SB-164	—	N04405	70/25 [485/170]	Rod, Bar, & Wire	67Ni-30Cu	
42	42	ASTM/ASME	B/SB-165	—	N04400	70/25 [485/170]	Seamless Pipe & Tube	67Ni-30Cu	
42	42	ASTM/ASME	B/SB-366	—	N04400	70/25 [485/170]	Fittings	67Ni-30Cu	
42	42	ASTM/ASME	A/SA-494	M30C	N24130	65/32.5 [450/225]	Castings	67Ni-30Cu-2Fe-Cb	
42	42	ASTM/ASME	A/SA-494	M35-1	N24135	65/25 [450/170]	Castings	67Ni-30Cu-2Fe-Cb	
42	42	ASTM/ASME	A/SA-494	M35-2	N04020	65/30 [450/205]	Castings	67Ni-30Cu-Fe-Si	
42	42	ASTM/ASME	B/SB-564	—	N04400	70/25 [485/170]	Forgings	67Ni-30Cu	
43	43	ASTM/ASME	B/SB-163	—	N06025	98/39 [675/270]	Seamless Tube	63Ni-25Cr-10Fe-2Al-Ti-Y-Zr	
43	43	ASTM/ASME	B/SB-163	—	N06600	80/35 [550/240]	Seamless Tube	72Ni-15Cr-8Fe	
43	43	ASTM/ASME	B/SB-163	—	N06601	80/30 [550/205]	Seamless Tube	60Ni-23Cr-12Fe-Al	
43	43	ASTM/ASME	B/SB-163	—	N06690	85/35 [585/240]	Seamless Tube	58Ni-29Cr-9Fe	
43	43	ASTM/ASME	B/SB-166	—	N06025	98/39 [675/270]	Rod, Bar, & Wire	63Ni-25Cr-10Fe-2Al-Ti-Y-Zr	
43	43	ASTM/ASME	B/SB-166	—	N06600	80/35 [550/240]	Rod, Bar, & Wire	72Ni-15Cr-8Fe	
43	43	ASTM/ASME	B/SB-166	—	N06601	80/30 [550/205]	Rod, Bar, & Wire	60Ni-23Cr-12Fe-Al	

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Nickel and Nickel Base Alloys									
43	46	ASTM/ASME	B/SB-166	—	N06617		95/35 [655/240]	Rod, Bar, & Wire	52Ni-22Cr-13Co-9Mo
43	43	ASTM/ASME	B/SB-166	—	N06690		85/35 [585/240]	Rod, Bar, & Wire	58Ni-29Cr-9Fe
43	43	ASTM/ASME	B/SB-167	—	N06025		98/39 [675/270]	Seamless Pipe & Tube	63Ni-25Cr-10Fe-2Al-Ti-Y-Zr
43	43	ASTM/ASME	B/SB-167	—	N06600		75/25 [515/170]	Seamless Pipe & Tube	72Ni-15Cr-8Fe
43	43	ASTM/ASME	B/SB-167	—	N06601		80/30 [550/205]	Seamless Pipe & Tube	60Ni-23Cr-12Fe-Al
43	46	ASTM/ASME	B/SB-167	—	N06617		95/35 [655/240]	Seamless Pipe & Tube	52Ni-22Cr-13Co-9Mo
43	43	ASTM/ASME	B/SB-167	—	N06690		75/25 [515/175]	Seamless Pipe & Tube	58Ni-29Cr-9Fe
43	43	ASTM/ASME	B/SB-168	—	N06025		98/39 [675/270]	Plate, Sheet, & Strip	63Ni-25Cr-10Fe-2Al-Ti-Y-Zr
43	43	ASTM/ASME	B/SB-168	—	N06600		80/35 [550/240]	Plate, Sheet, & Strip	72Ni-15Cr-8Fe
43	43	ASTM/ASME	B/SB-168	—	N06601		80/30 [550/205]	Plate, Sheet, & Strip	60Ni-23Cr-12Fe-Al
43	46	ASTM/ASME	B/SB-168	—	N06617		95/35 [655/240]	Plate, Sheet, & Strip	52Ni-22Cr-13Co-9Mo
43	43	ASTM/ASME	B/SB-168	—	N06690		85/35 [585/240]	Plate, Sheet, & Strip	58Ni-29Cr-9Fe
43	43	ASTM/ASME	B/SB-366	—	N06002		100/40 [690/275]	Fittings	47Ni-22Cr-18Fe-9Mo
43	44	ASTM/ASME	B/SB-366	—	N06022		100/45 [690/310]	Fittings	55Ni-21Cr-13.5Mo
43	43	ASTM/ASME	B/SB-366	—	N06025		98/39 [675/270]	Fittings	63Ni-25Cr-10Fe-2Al-Ti-Y-Zr
43	43	ASTM/ASME	B/SB-366	—	N06035		85/35 [585/240]	Fittings	58Ni-33Cr-8Mo
43	43	ASTM/ASME	B/SB-366	—	N06059		100/45 [690/310]	Fittings	59Ni-23Cr-16Mo
43	43	ASTM/ASME	B/SB-366	—	N06200		100/45 [690/310]	Fittings	59Ni-23Cr-16Mo-1.6Cu
43	43	ASTM/ASME	B/SB-366	—	N06210		100/45 [690/310]	Fittings	60Ni-19Cr-19Mo-1.8Ta
43	43	ASTM/ASME	B/SB-366	—	N06230		110/45 [760/310]	Fittings	53Ni-22Cr-14W-Co-Fe-Mo
43	43	ASTM/ASME	B/SB-366	—	N06455		100/40 [690/275]	Fittings	61Ni-15Mo-16Cr
43	43	ASTM/ASME	B/SB-366	—	N06600		80/35 [550/240]	Fittings	72Ni-15Cr-8Fe
43	43	ASTM/ASME	B/SB-366	—	N06603		94/43 [650/295]	Fittings	62Ni-25Cr-9Fe-3Al-Cu-Ti-Zr
43	43	ASTM/ASME	B/SB-366	—	N06625		110/55 [760/380]	Fittings	60Ni-22Cr-9Mo-3.5Cb
43	43	ASTM/ASME	B/SB-366	—	N10276		100/41 [690/285]	Fittings	54Ni-16Mo-15Cr
43	43	ASTM/ASME	B/SB-435	—	N06002		95/35 [655/240]	Plate, Sheet, & Strip	47Ni-22Cr-9Mo-18Fe
43	43	ASTM/ASME	B/SB-435	—	N06230		110/45 [760/310]	Plate, Sheet, & Strip	53Ni-22Cr-14W-Co-Fe-Mo
43	43	ASTM/ASME	B/SB-443	1	N06625		110/55 [760/380]	Plate, Sheet, & Strip	60Ni-22Cr-9Mo-3.5Cb
43	43	ASTM/ASME	B/SB-443	2	N06625		100/40 [690/275]	Plate, Sheet, & Strip	60Ni-22Cr-9Mo-3.5Cb

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
43	43	ASTM/ASME	B/SB-444	1	N06625		120/60 [825/415]	Seamless Pipe & Tube	60Ni-22Cr-9Mo-3.5Cb
43	43	ASTM/ASME	B/SB-444	2	N06625		100/40 [690/275]	Seamless Pipe & Tube	60Ni-22Cr-9Mo-3.5Cb
43	43	ASTM/ASME	B/SB-446	1	N06625		120/60 [825/415]	Rod & Bar	60Ni-22Cr-9Mo-3.5Cb
43	43	ASTM/ASME	B/SB-446	2	N06625		100/40 [690/275]	Rod & Bar	60Ni-22Cr-9Mo-3.5Cb
43	44	ASTM/ASME	B/SB-462	—	N06022		100/45 [690/310]	Forgings	55Ni-21Cr-13.5Mo
43	43	ASTM/ASME	B/SB-462	—	N06035		85/35 [585/240]	Forgings	58Ni-33Cr-8Mo
43	43	ASTM/ASME	B/SB-462	—	N06059		100/45 [690/310]	Forgings	59Ni-23Cr-16Mo
43	43	ASTM/ASME	B/SB-462	—	N06200		100/45 [690/310]	Forgings	59Ni-23Cr-16Mo-1.6Cu
43	43	ASTM/ASME	B/SB-462	—	N06686		100/45 [690/310]	Forgings	58Ni-21Cr-16Mo-3.5N
43	43	ASTM/ASME	B/SB-462	—	N10276		100/41 [690/285]	Forgings	54Ni-16Mo-15Cr
43	43	ASTM/ASME	A/SA-494	CW2M	N26455		72/40 [495/275]	Castings	66Ni-16Mo-16Cr-Fe-W
43	43	ASTM/ASME	A/SA-494	CW6MC	N26625		70/40 [485/275]	Castings	60Ni-21.5Cr-9Mo-4Cb-Fe
43	44	ASTM/ASME	A/SA-494	CX2MW	N26022		80/45 [550/310]	Castings	59Ni-22Cr-14Mo-4Fe-3W
43	43	ASTM/ASME	A/SA-494	CY40	N06040		70/28 [485/195]	Castings	72Ni-15Cr-8Fe-Si
43	43	ASTM/ASME	B/SB-516	—	N06025		98/39 [675/270]	Welded Tube	63Ni-25Cr-10Fe-2Al-Ti-Y-Zr
43	43	ASTM/ASME	B/SB-516	—	N06600		80/35 [550/240]	Welded Tube	72Ni-15Cr-8Fe
43	43	ASTM/ASME	B/SB-516	—	N06603		94/43 [650/295]	Welded Tube	62Ni-25Cr-9Fe-3Al-Cu-Ti-Zr
43	43	ASTM/ASME	B/SB-517	—	N06025		98/39 [675/270]	Welded Pipe	63Ni-25Cr-10Fe-2Al-Ti-Y-Zr
43	43	ASTM/ASME	B/SB-517	—	N06600		80/35 [550/240]	Welded Pipe	72Ni-15Cr-8Fe
43	43	ASTM/ASME	B/SB-517	—	N06603		94/43 [650/295]	Welded Pipe	62Ni-25Cr-9Fe-3Al-Cu-Ti-Zr
43	44	ASTM/ASME	B/SB-564	—	N06022		100/45 [690/310]	Forgings	55Ni-21Cr-13.5Mo
43	43	ASTM/ASME	B/SB-564	—	N06025		98/39 [675/270]	Forgings	63Ni-25Cr-10Fe-2Al-Ti-Y-Zr
43	43	ASTM/ASME	B/SB-564	—	N06025		84/39 [580/270]	Forgings	63Ni-25Cr-10Fe-2Al-Ti-Y-Zr
							>100 and ≤305]		
43	43	ASTM/ASME	B/SB-564	—	N06035		85/35 [585/240]	Forgings	58Ni-33Cr-8Mo
43	43	ASTM/ASME	B/SB-564	—	N06059		100/45 [690/310]	Forgings	59Ni-23Cr-16Mo
43	43	ASTM/ASME	B/SB-564	—	N06110		90/40 [620/275]	Forgings	51Ni-30Cr-10Mo-W
							>4 and ≤10 >102 and ≤254]		
43	43	ASTM/ASME	B/SB-564	—	N06110		95/45 [655/310]	Forgings	51Ni-30Cr-10Mo-W

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Nickel and Nickel Base Alloys									
43	43	ASTM/ASME	B/SB-564	—	N06200		100/45 [690/310]	Forgings	59Ni-23Cr-16Mo-1.6Cu
43	43	ASTM/ASME	B/SB-564	—	N06210		100/45 [690/310]	Forgings	60Ni-19Cr-19Mo-1.8Ta
43	43	ASTM/ASME	B/SB-564	—	N06230		110/45 [760/310]	Forgings	53Ni-22Cr-14W-Co-Fe-Mo
43	43	ASTM/ASME	B/SB-564	—	N06600		80/35 [550/240]	Forgings	72Ni-15Cr-8Fe
43	43	ASTM/ASME	B/SB-564	—	N06603		94/43 [650/295]	Forgings	62Ni-25Cr-9Fe-3Al-Cu-Ti-Zr
43	46	ASTM/ASME	B/SB-564	—	N06617		95/35 [655/240]	Forgings	52Ni-22Cr-13Co-9Mo
43	43	ASTM/ASME	B/SB-564	—	N06625	>4 and ≤10 >102 and ≤254]	110/50 [760/345]	Forgings	60Ni-22Cr-9Mo-3.5Cb
43	43	ASTM/ASME	B/SB-564	—	N06625	≤4 [≤102]	120/60 [825/415]	Forgings	60Ni-22Cr-9Mo-3.5Cb
43	43	ASTM/ASME	B/SB-564	—	N06686		100/45 [690/310]	Forgings	58Ni-21Cr-16Mo-3.5W
43	43	ASTM/ASME	B/SB-564	—	N06690		85/35 [585/240]	Forgings	58Ni-29Cr-9Fe
43	43	ASTM/ASME	B/SB-564	—	N10276		100/41 [690/285]	Forgings	54Ni-16Mo-15Cr
43	43	ASTM/ASME	B/SB-572	—	N06002		95/35 [655/240]	Rod	47Ni-22Cr-9Mo-18Fe
43	43	ASTM/ASME	B/SB-572	—	N06230		110/45 [760/310]	Rod	53Ni-22Cr-14W-Co-Fe-Mo
43	44	ASTM/ASME	B/SB-574	—	N06022		100/45 [690/310]	Rod	55Ni-21Cr-13.5Mo
43	43	ASTM/ASME	B/SB-574	—	N06035		85/35 [585/240]	Rod	58Ni-33Cr-8Mo
43	43	ASTM/ASME	B/SB-574	—	N06059		100/45 [690/310]	Rod	59Ni-23Cr-16Mo
43	43	ASTM/ASME	B/SB-574	—	N06200		100/45 [690/310]	Rod	59Ni-23Cr-16Mo-1.6Cu
43	43	ASTM/ASME	B/SB-574	—	N06210		100/45 [690/310]	Rod	60Ni-19Cr-19Mo-1.8Ta
43	43	ASTM/ASME	B/SB-574	—	N06455		100/40 [690/275]	Rod	61Ni-16Mo-16Cr
43	43	ASTM/ASME	B/SB-574	—	N06686		100/45 [690/310]	Rod	58Ni-21Cr-16Mo-3.5W
43	43	ASTM/ASME	B/SB-574	—	N10276		100/41 [690/285]	Rod	54Ni-16Mo-15Cr
43	44	ASTM/ASME	B/SB-575	—	N06022		100/45 [690/310]	Plate, Sheet, & Strip	55Ni-21Cr-13.5Mo
43	43	ASTM/ASME	B/SB-575	—	N06035		85/35 [585/240]	Plate, Sheet, & Strip	58Ni-33Cr-8Mo
43	43	ASTM/ASME	B/SB-575	—	N06059		100/45 [690/310]	Plate, Sheet, & Strip	59Ni-23Cr-16Mo
43	43	ASTM/ASME	B/SB-575	—	N06200		100/45 [690/310]	Plate, Sheet, & Strip	59Ni-23Cr-16Mo
43	43	ASTM/ASME	B/SB-575	—	N06200		100/45 [690/310]	Plate, Sheet, & Strip	59Ni-23Cr-16Mo-1.6Cu
43	43	ASTM/ASME	B/SB-575	—	N06210		100/45 [690/310]	Plate, Sheet, & Strip	60Ni-19Cr-19Mo-1.8Ta
43	43	ASTM/ASME	B/SB-575	—	N06455		100/40 [690/275]	Plate, Sheet, & Strip	61Ni-16Mo-16Cr
43	43	ASTM/ASME	B/SB-575	—	N06686		100/45 [690/310]	Plate, Sheet, & Strip	58Ni-21Cr-16Mo-3.5W
43	43	ASTM/ASME	B/SB-575	—	N10276		100/41 [690/285]	Plate, Sheet, & Strip	54Ni-16Mo-15Cr
43	43	ASTM/ASME	B/SB-575	—	N06022		100/45 [690/310]	Plate, Sheet, & Strip	55Ni-21Cr-13.5Mo
43	43	ASTM/ASME	B/SB-575	—	N06035		85/35 [585/240]	Plate, Sheet, & Strip	58Ni-33Cr-8Mo
43	43	ASTM/ASME	B/SB-575	—	N06059		100/45 [690/310]	Plate, Sheet, & Strip	59Ni-23Cr-16Mo
43	43	ASTM/ASME	B/SB-575	—	N06200		100/45 [690/310]	Plate, Sheet, & Strip	59Ni-23Cr-16Mo-1.6Cu
43	43	ASTM/ASME	B/SB-575	—	N06210		100/45 [690/310]	Plate, Sheet, & Strip	60Ni-19Cr-19Mo-1.8Ta
43	43	ASTM/ASME	B/SB-575	—	N06455		100/40 [690/275]	Plate, Sheet, & Strip	61Ni-16Mo-16Cr
43	43	ASTM/ASME	B/SB-575	—	N06686		100/45 [690/310]	Plate, Sheet, & Strip	58Ni-21Cr-16Mo-3.5W

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]		Product Form	Nominal Composition
							Strength, ksi [MPa]	Strength, ksi [MPa]		
Nickel and Nickel Base Alloys										
43	43	ASTM/ASME	B/SB-575	—	N10276	100/41	[690/285]		Plate, Sheet, & Strip	54Ni-16Mo-15Cr
43	43	ASTM/ASME	B/SB-619	—	N06002	100/40	[690/275]		Welded Pipe	47Ni-22Cr-9Mo-18Fe
43	44	ASTM/ASME	B/SB-619	—	N06022	100/45	[690/310]		Welded Pipe	55Ni-21Cr-13.5Mo
43	43	ASTM/ASME	B/SB-619	—	N06035	85/35	[585/240]		Welded Pipe	58Ni-33Cr-8Mo
43	43	ASTM/ASME	B/SB-619	—	N06059	100/45	[690/310]		Welded Pipe	59Ni-23Cr-16Mo
43	43	ASTM/ASME	B/SB-619	—	N06200	100/45	[690/310]		Welded Pipe	59Ni-23Cr-16Mo-1.6Cu
43	43	ASTM/ASME	B/SB-619	—	N06210	100/45	[690/310]		Welded Pipe	60Ni-19Cr-19Mo-1.8Ta
43	43	ASTM/ASME	B/SB-619	—	N06230	110/45	[760/310]		Welded Pipe	53Ni-22Cr-14W-Co-Fe-Mo
43	43	ASTM/ASME	B/SB-619	—	N06455	100/40	[690/275]		Welded Pipe	61Ni-16Mo-16Cr
43	43	ASTM/ASME	B/SB-619	—	N06686	100/45	[690/310]		Welded Pipe	58Ni-21Cr-16Mo-3.5W
43	43	ASTM/ASME	B/SB-619	—	N10276	100/41	[690/285]		Welded Pipe	54Ni-16Mo-15Cr
43	43	ASTM/ASME	B/SB-622	—	N06002	100/40	[690/275]		Seamless Pipe & Tube	47Ni-22Cr-9Mo-18Fe
43	44	ASTM/ASME	B/SB-622	—	N06022	100/45	[690/310]		Seamless Pipe & Tube	55Ni-21Cr-13.5Mo
43	43	ASTM/ASME	B/SB-622	—	N06035	85/35	[585/240]		Seamless Pipe & Tube	58Ni-33Cr-8Mo
43	43	ASTM/ASME	B/SB-622	—	N06059	100/45	[690/310]		Seamless Pipe & Tube	59Ni-23Cr-16Mo
43	43	ASTM/ASME	B/SB-622	—	N06060	90/35	[620/240]		Seamless Pipe & Tube	57Ni-21Cr-13Mo-6Fe-Cu-(Cb+Ta)
43	43	ASTM/ASME	B/SB-622	—	N06200	100/45	[690/310]		Seamless Pipe & Tube	59Ni-23Cr-16Mo-1.6Cu
43	43	ASTM/ASME	B/SB-622	—	N06210	100/45	[690/310]		Seamless Pipe & Tube	60Ni-19Cr-19Mo-1.8Ta
43	43	ASTM/ASME	B/SB-622	—	N06230	110/45	[760/310]		Seamless Pipe & Tube	53Ni-22Cr-14W-Co-Fe-Mo
43	43	ASTM/ASME	B/SB-622	—	N06250	90/35	[620/240]		Seamless Pipe & Tube	52Ni-21Cr-13Fe-11Mo-W-Cu
43	43	ASTM/ASME	B/SB-622	—	N06255	85/32	[585/220]		Seamless Pipe & Tube	50Ni-24Cr-17Fe-7Mo-W
43	43	ASTM/ASME	B/SB-622	—	N06455	100/40	[690/275]		Seamless Pipe & Tube	61Ni-16Mo-16Cr
43	43	ASTM/ASME	B/SB-622	—	N06686	100/45	[690/310]		Seamless Pipe & Tube	58Ni-21Cr-16Mo-3.5W
43	43	ASTM/ASME	B/SB-622	—	N10276	100/41	[690/285]		Seamless Pipe & Tube	54Ni-16Mo-15Cr
43	43	ASTM/ASME	B/SB-626	—	N06002	100/40	[690/275]		Welded Tube	47Ni-22Cr-9Mo-18Fe
43	44	ASTM/ASME	B/SB-626	—	N06022	100/45	[690/310]		Welded Tube	55Ni-21Cr-13.5Mo
43	43	ASTM/ASME	B/SB-626	—	N06035	85/35	[585/240]		Welded Tube	58Ni-33Cr-8Mo
43	43	ASTM/ASME	B/SB-626	—	N06059	100/45	[690/310]		Welded Tube	59Ni-23Cr-16Mo
43	43	ASTM/ASME	B/SB-626	—	N06200	100/45	[690/310]		Welded Tube	59Ni-23Cr-16Mo-1.6Cu

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
43	43	ASTM/ASME	B/SB-626	—	N06210		100/45 [690/310]	Welded Tube	60Ni-19Cr-19Mo-1.8Ta
43	43	ASTM/ASME	B/SB-626	—	N06230		110/45 [760/310]	Welded Tube	53Ni-22Cr-14W-Co-Fe-Mo
43	43	ASTM/ASME	B/SB-626	—	N06455		100/40 [690/275]	Welded Tube	61Ni-16Mo-16Cr
43	43	ASTM/ASME	B/SB-626	—	N06686		100/45 [690/310]	Welded Tube	58Ni-21Cr-16Mo-3.5W
43	43	ASTM/ASME	B/SB-626	—	N10276		100/41 [690/285]	Welded Tube	54Ni-16Mo-15Cr
43	43	ASTM/ASME	B/SB-704	—	N06625		120/60 [825/415]	Welded Tube	60Ni-22Cr-9Mo-3.5Cb
43	43	ASTM/ASME	B/SB-705	—	N06625		120/60 [825/415]	Welded Pipe	60Ni-22Cr-9Mo-3.5Cb
43	43	ASTM	B755	—	N06110		95/45 [655/310]	Plate, Sheet, & Strip	51Ni-30Cr-10Mo-W
43	43	ASTM	B756	—	N06110	>4 and ≤10 >102 and ≤254]	90/40 [620/275]	Rod & Bar	51Ni-30Cr-10Mo-W
43	43	ASTM	B756	—	N06110	≤4 [≤102]	95/45 [655/310]	Rod & Bar	51Ni-30Cr-10Mo-W
43	43	ASTM	B757	—	N06110		95/45 [655/310]	Welded Pipe	51Ni-30Cr-10Mo-W
43	43	ASTM	B758	—	N06110		95/45 [655/310]	Welded Tube	51Ni-30Cr-10Mo-W
43	43	ASTM	B759	—	N06110		95/45 [655/310]	Seamless Pipe & Tube	51Ni-30Cr-10Mo-W
44	44	ASTM/ASME	B/SB-333	—	N10001	<0.1875 [<48]	115/50 [795/345]	Plate, Sheet, & Strip	62Ni-28Mo-5Fe
44	44	ASTM/ASME	B/SB-333	—	N10001	≥0.1875 and ≤2.5 [≥4.8 and ≤64]	100/45 [690/310]	Plate, Sheet, & Strip	62Ni-28Mo-5Fe
44	44	ASTM/ASME	B/SB-333	—	N10624		104/46 [715/315]	Plate, Sheet, & Strip	60Ni-23Mo-8Cr-6.5Fe
44	44	ASTM/ASME	B/SB-333	—	N10629		110/51 [760/350]	Plate, Sheet, & Strip	66Ni-28Mo-3Fe-1.3Cr-0.25Al
44	44	ASTM/ASME	B/SB-333	—	N10665		110/51 [760/350]	Plate, Sheet, & Strip	65Ni-28Mo-2Fe
44	44	ASTM/ASME	B/SB-333	—	N10675		110/51 [760/350]	Plate, Sheet, & Strip	65Ni-29.5Mo-2Fe-2Cr
44	44	ASTM/ASME	B/SB-335	—	N10001	>1.5 and ≤3.5 [>38 and ≤89]	100/46 [690/315]	Rod	62Ni-28Mo-5Fe
44	44	ASTM/ASME	B/SB-335	—	N10001	≥0.3125 and ≤1.5 [≥8 and ≤38]	115/46 [795/315]	Rod	62Ni-28Mo-5Fe
44	44	ASTM/ASME	B/SB-335	—	N10624		104/46 [715/315]	Rod	60Ni-23Mo-8Cr-6.5Fe
44	44	ASTM/ASME	B/SB-335	—	N10629		110/51 [760/350]	Rod	66Ni-28Mo-3Fe-1.3Cr-0.25Al
44	44	ASTM/ASME	B/SB-335	—	N10665		110/51 [760/350]	Rod	65Ni-28Mo-2Fe
44	44	ASTM/ASME	B/SB-335	—	N10675		110/51 [760/350]	Rod	65Ni-29.5Mo-2Fe-2Cr

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]		Product Form	Nominal Composition
							Strength, ksi [MPa]	Strength, ksi [MPa]		
Nickel and Nickel Base Alloys										
44	44	ASTM/ASME	B/SB-366	—	N10001	—	100/45	[690/310]	Fittings	62Ni-28Mo-5Fe
44	44	ASTM/ASME	B/SB-366	—	N10003	—	100/40	[690/275]	Fittings	70Ni-16Mo-7Cr-5Fe
44	44	ASTM/ASME	B/SB-366	—	N10242	—	105/45	[725/310]	Fittings	62Ni-25Mo-8Cr-2Fe
44	44	ASTM/ASME	B/SB-366	—	N10624	—	104/46	[715/315]	Fittings	60Ni-23Mo-8Cr-6.5Fe
44	44	ASTM/ASME	B/SB-366	—	N10629	—	110/51	[760/350]	Fittings	66Ni-28Mo-3Fe-1.3Cr-0.25Al
44	44	ASTM/ASME	B/SB-366	—	N10665	—	110/51	[760/350]	Fittings	65Ni-28Mo-2Fe
44	44	ASTM/ASME	B/SB-366	—	N10675	—	110/51	[760/350]	Fittings	65Ni-29.5Mo-2Fe-2Cr
44	44	ASTM/ASME	B/SB-434	—	N10003	—	100/40	[690/275]	Plate, Sheet, & Strip	70Ni-16Mo-7Cr-5Fe
44	44	ASTM/ASME	B/SB-434	—	N10242	—	105/45	[725/310]	Plate, Sheet, & Strip	62Ni-25Mo-8Cr-2Fe
44	44	ASTM/ASME	B/SB-462	—	N10629	—	110/51	[760/350]	Forgings	66Ni-28Mo-3Fe-1.3Cr-0.25Al
44	44	ASTM/ASME	B/SB-462	—	N10665	—	110/51	[760/350]	Forgings	65Ni-28Mo-2Fe
44	44	ASTM/ASME	B/SB-462	—	N10675	—	110/51	[760/350]	Forgings	65Ni-29.5Mo-2Fe-2Cr
44	44	ASTM/ASME	A/SA-494	CW6M	N30107	—	72/40	[495/275]	Castings	56Ni-19Mo-18Cr-2Fe
44	44	ASTM/ASME	A/SA-494	N7M	N30007	—	76/40	[525/275]	Castings	65Ni-31.5Mo-1.5Fe-Cr
44	44	ASTM/ASME	B/SB-564	—	N10242	—	105/45	[725/310]	Forgings	62Ni-25Mo-8Cr-2Fe
44	44	ASTM/ASME	B/SB-564	—	N10624	—	104/46	[715/315]	Forgings	60Ni-23Mo-8Cr-6.5Fe
44	44	ASTM/ASME	B/SB-564	—	N10629	—	110/51	[760/350]	Forgings	66Ni-28Mo-3Fe-1.3Cr-0.25Al
44	44	ASTM/ASME	B/SB-564	—	N10665	—	110/51	[760/350]	Forgings	65Ni-28Mo-2Fe
44	44	ASTM/ASME	B/SB-564	—	N10675	—	110/51	[760/350]	Forgings	65Ni-29.5Mo-2Fe-2Cr
44	44	ASTM/ASME	B/SB-573	—	N10003	—	100/40	[690/275]	Rod	70Ni-16Mo-7Cr-5Fe
44	44	ASTM/ASME	B/SB-573	—	N10242	—	105/45	[725/310]	Rod	62Ni-25Mo-8Cr-2Fe
44	44	ASTM/ASME	B/SB-619	—	N10001	—	100/45	[690/310]	Welded Pipe	62Ni-28Mo-5Fe
44	44	ASTM/ASME	B/SB-619	—	N10242	—	105/45	[725/310]	Welded Pipe	62Ni-25Mo-8Cr-2Fe
44	44	ASTM/ASME	B/SB-619	—	N10624	—	104/46	[715/315]	Welded Pipe	60Ni-23Mo-8Cr-6.5Fe
44	44	ASTM/ASME	B/SB-619	—	N10629	—	110/51	[760/350]	Welded Pipe	66Ni-28Mo-3Fe-1.3Cr-0.25Al
44	44	ASTM/ASME	B/SB-619	—	N10665	—	110/51	[760/350]	Welded Pipe	65Ni-28Mo-2Fe
44	44	ASTM/ASME	B/SB-619	—	N10675	—	110/51	[760/350]	Welded Pipe	65Ni-29.5Mo-2Fe-2Cr
44	44	ASTM/ASME	B/SB-622	—	N10001	—	100/45	[690/310]	Seamless Pipe & Tube	62Ni-28Mo-5Fe
44	44	ASTM/ASME	B/SB-622	—	N10242	—	105/45	[725/310]	Seamless Pipe & Tube	62Ni-25Mo-8Cr-2Fe

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Nickel and Nickel Base Alloys									
44	44	ASTM/ASME	B/SB-622	—	N10624	104/46 [715/315]	104/46 [715/315]	Seamless Pipe & Tube	60Ni-23Mo-8Cr-7Fe
44	44	ASTM/ASME	B/SB-622	—	N10629	110/51 [760/350]	110/51 [760/350]	Seamless Pipe & Tube	66Ni-28Mo-3Fe-1.3Cr-0.25Al
44	44	ASTM/ASME	B/SB-622	—	N10665	110/51 [760/350]	110/51 [760/350]	Seamless Pipe & Tube	65Ni-28Mo-2Fe
44	44	ASTM/ASME	B/SB-622	—	N10675	110/51 [760/350]	110/51 [760/350]	Seamless Pipe & Tube	65Ni-29.5Mo-2Fe-2Cr
44	44	ASTM/ASME	B/SB-626	—	N10001	100/45 [690/310]	100/45 [690/310]	Welded Tube	62Ni-28Mo-5Fe
44	44	ASTM/ASME	B/SB-626	—	N10242	105/45 [725/310]	105/45 [725/310]	Welded Tube	62Ni-25Mo-8Cr-2Fe
44	44	ASTM/ASME	B/SB-626	—	N10624	104/46 [715/315]	104/46 [715/315]	Welded Tube	60Ni-23Mo-8Cr-6.5Fe
44	44	ASTM/ASME	B/SB-626	—	N10629	110/51 [760/350]	110/51 [760/350]	Welded Tube	66Ni-28Mo-3Fe-1.3Cr-0.25Al
44	44	ASTM/ASME	B/SB-626	—	N10665	110/51 [760/350]	110/51 [760/350]	Welded Tube	65Ni-28Mo-2Fe
44	44	ASTM/ASME	B/SB-626	—	N10675	110/51 [760/350]	110/51 [760/350]	Welded Tube	65Ni-29.5Mo-2Fe-2Cr
44	43	AMS	5711	—	N06635	185/120 [1275/825]	185/120 [1275/825]	Sheet	62Ni-16Cr-15Mo-3Fe-2Co-1W-Mn-Si-Al
45	45	ASTM/ASME	B/SB-163	—	N08120	90/40 [620/275]	90/40 [620/275]	Seamless Tube	37Ni-33Fe-25Cr
45	45	ASTM/ASME	B/SB-163	—	N08800	75/30 [515/205]	75/30 [515/205]	Seamless Tube	33Ni-42Fe-21Cr
45	45	ASTM/ASME	B/SB-163	—	N08801	65/25 [450/170]	65/25 [450/170]	Seamless Tube	32Ni-45Fe-20.5Cr-Ti
45	45	ASTM/ASME	B/SB-163	—	N08810	65/25 [450/170]	65/25 [450/170]	Seamless Tube	33Ni-42Fe-21Cr
45	45	ASTM/ASME	B/SB-163	—	N08811	65/25 [450/170]	65/25 [450/170]	Seamless Tube	33Ni-42Fe-21Cr-Al-Ti
45	45	ASTM/ASME	B/SB-163	—	N08825	85/35 [585/240]	85/35 [585/240]	Seamless Tube	42Ni-21.5Cr-3Mo-2.3Cu
45	8.2	ASTM	A182	F904L	N08904	71/31 [490/215]	71/31 [490/215]	Forgings	44Fe-25Ni-21Cr-Mo
45	8.2	ASTM	A240	—	N08367	<0.1875 [<5]	100/45 [690/310]	Sheet & Strip	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM	A240	—	N08367	≥0.1875 [≥5]	95/45 [655/310]	Plate	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM	A240	904L	N08904	71/31 [490/215]	71/31 [490/215]	Plate, Sheet, & Strip	44Fe-25Ni-21Cr-Mo
45	8.2	ASTM	A249	—	N08367	≤0.1875 [≤5]	100/45 [690/310]	Welded Tube	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM	A249	—	N08367	>0.1875 [>5]	95/45 [655/310]	Welded Tube	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	A/SA-249	—	N08904	71/31 [490/215]	71/31 [490/215]	Welded Tube	44Fe-25Ni-21Cr-Mo
45	8.2	ASTM	A312	—	N08904	71/31 [490/215]	71/31 [490/215]	Seamless & Welded Pipe	44Fe-25Ni-21Cr-Mo
45	8.2	ASTM	A312	N08367	N08367	>0.1875 [>5]	95/45 [655/310]	Seamless & Welded Pipe	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM	A312	N08367	N08367	≤0.1875 [≤5]	100/45 [690/310]	Seamless & Welded Pipe	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	A/SA-351	CN7M	N08007	62/25 [425/170]	62/25 [425/170]	Castings	28Ni-19Cr-Cu-Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
45	45	ASTM/ASME	A/SA-351	CT15C	N08151		63/25 [435/170]	Castings	32Ni-45Fe-20Cr-Cb
45	8.2	ASTM	A358	N08367	N08367	≤0.1875 [≤5]	100/45 [690/310]	Fusion Welded Pipe	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM	A358	N08367	N08367	>0.1875 [>5]	95/45 [655/310]	Fusion Welded Pipe	46Fe-24Ni-21Cr-6Mo-Cu-N
45	43	ASTM/ASME	B/SB-366	—	N06007		90/35 [620/240]	Fittings	47Ni-22Cr-19Fe-6Mo
45	45	ASTM/ASME	B/SB-366	—	N06030		85/35 [585/240]	Fittings	40Ni-29Cr-15Fe-5Mo
45	45	ASTM/ASME	B/SB-366	—	N06985		90/35 [620/240]	Fittings	47Ni-22Cr-20Fe-7Mo
45	45	ASTM/ASME	B/SB-366	—	N08020		80/35 [550/240]	Fittings	35Ni-35Fe-20Cr-Cb
45	45	ASTM/ASME	B/SB-366	—	N08031		94/40 [650/275]	Fittings	31Ni-31Fe-27Cr-7Mo
45	45	ASTM/ASME	B/SB-366	—	N08120		90/40 [620/275]	Fittings	37Ni-33Fe-25Cr
45	8.2	ASTM/ASME	B/SB-366	—	N08367	≤0.1875 [≤4.8]	100/45 [690/310]	Fittings	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-366	—	N08367	>0.1875 [>4.8]	95/45 [655/310]	Fittings	46Fe-24Ni-21Cr-6Mo-Cu-N
45	45	ASTM/ASME	B/SB-366	—	N08800		75/30 [515/205]	Fittings	33Ni-42Fe-21Cr
45	45	ASTM/ASME	B/SB-366	—	N08810		65/25 [450/170]	Fittings	33Ni-42Fe-21Cr
45	45	ASTM/ASME	B/SB-366	—	N08811		65/25 [450/170]	Fittings	33Ni-42Fe-21Cr-Al-Ti
45	45	ASTM/ASME	B/SB-366	—	N08825		85/35 [585/240]	Fittings	42Ni-21.5Cr-3Mo-2.3Cu
45	8.2	ASTM/ASME	B/SB-366	—	N08904		71/31 [490/215]	Fittings	44Fe-25Ni-21Cr-Mo
45	8.2	ASTM/ASME	B/SB-366	—	N08925		87/43 [600/295]	Fittings	25Ni-20Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-366	—	N08926		94/43 [650/295]	Fittings	25Ni-20Cr-6Mo-Cu-N
45	45	ASTM/ASME	B/SB-366	—	R20033		109/55 [750/380]	Fittings	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N
45	45	ASTM/ASME	B/SB-366	—	R30556		100/45 [690/310]	Fittings	21Ni-30Fe-22Cr-18Co-3Mo-3W
45	45	ASTM/ASME	B/SB-407	—	N08120		90/40 [620/275]	Seamless Pipe & Tube	37Ni-33Fe-25Cr
45	45	ASTM/ASME	B/SB-407	—	N08800		75/30 [515/205]	Seamless Pipe & Tube	33Ni-42Fe-21Cr
45	45	ASTM/ASME	B/SB-407	—	N08801		65/25 [450/170]	Seamless Pipe & Tube	32Ni-45Fe-20.5Cr-Ti
45	45	ASTM/ASME	B/SB-407	—	N08810		65/25 [450/170]	Seamless Pipe & Tube	33Ni-42Fe-21Cr
45	45	ASTM/ASME	B/SB-407	—	N08811		65/25 [450/170]	Seamless Pipe & Tube	33Ni-42Fe-21Cr-Al-Ti
45	45	ASTM/ASME	B/SB-408	—	N08120		90/40 [620/275]	Rod & Bar	37Ni-33Fe-25Cr
45	45	ASTM/ASME	B/SB-408	—	N08800		75/30 [515/205]	Rod & Bar	33Ni-42Fe-21Cr

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
45	45	ASTM/ASME	B/SB-408	—	N08810		65/25 [450/170]	Rod & Bar	33Ni-42Fe-21Cr
45	45	ASTM/ASME	B/SB-408	—	N08811		65/25 [450/170]	Rod & Bar	33Ni-42Fe-21Cr-Al-Ti
45	45	ASTM/ASME	B/SB-409	—	N08120		90/40 [620/275]	Plate, Sheet, & Strip	37Ni-33Fe-25Cr
45	45	ASTM/ASME	B/SB-409	—	N08800		75/30 [515/205]	Plate, Sheet, & Strip	33Ni-42Fe-21Cr
45	45	ASTM/ASME	B/SB-409	—	N08810		65/25 [450/170]	Plate, Sheet, & Strip	33Ni-42Fe-21Cr
45	45	ASTM/ASME	B/SB-409	—	N08811		65/25 [450/170]	Plate, Sheet, & Strip	33Ni-42Fe-21Cr-Al-Ti
45	45	ASTM/ASME	B/SB-423	—	N08221		79/34 [545/235]	Seamless Pipe & Tube	42Ni-21Cr-6Mo-2.3Cu
45	45	ASTM/ASME	B/SB-423	—	N08825		75/25 [515/170]	Seamless Pipe & Tube	42Ni-21.5Cr-3Mo-2.3Cu
45	45	ASTM/ASME	B/SB-424	—	N08221		79/34 [545/235]	Plate, Sheet, & Strip	42Ni-21Cr-6Mo-2.3Cu
45	45	ASTM/ASME	B/SB-424	—	N08825		85/35 [585/240]	Plate, Sheet, & Strip	42Ni-21.5Cr-3Mo-2.3Cu
45	45	ASTM/ASME	B/SB-425	—	N08221		79/34 [545/235]	Rod & Bar	42Ni-21Cr-6Mo-2.3Cu
45	45	ASTM/ASME	B/SB-425	—	N08825		85/35 [585/240]	Rod & Bar	42Ni-21.5Cr-3Mo-2.3Cu
45	45	ASTM/ASME	B/SB-435	—	R30556		100/45 [690/310]	Plate, Sheet, & Strip	21Ni-30Fe-22Cr-18Co-3Mo-3W
45	45	ASTM/ASME	B/SB-462	—	N06030		85/35 [585/240]	Forgings	40Ni-29Cr-15Fe-5Mo
45	45	ASTM/ASME	B/SB-462	—	N08020		80/35 [550/240]	Forgings	35Ni-35Fe-20Cr-Cb
45	45	ASTM/ASME	B/SB-462	—	N08024		80/35 [550/240]	Forgings	37Ni-33Fe-23Cr-4Mo
45	45	ASTM/ASME	B/SB-462	—	N08026		80/35 [550/240]	Forgings	35Ni-30Fe-24Cr-6Mo-3Cu
45	45	ASTM/ASME	B/SB-462	—	N08031		94/40 [650/275]	Forgings	31Ni-33Fe-22Cr-6.5Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-462	—	N08367		95/45 [655/310]	Forgings	46Fe-24Ni-21Cr-6Mo-Cu-N
45	45	ASTM/ASME	B/SB-462	—	R20033		109/55 [750/380]	Forgings	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N
45	45	ASTM/ASME	B/SB-463	—	N08020		80/35 [550/240]	Plate, Sheet, & Strip	35Ni-35Fe-20Cr-Cb
45	45	ASTM/ASME	B/SB-463	—	N08024		80/35 [550/240]	Plate, Sheet, & Strip	37Ni-33Fe-23Cr-4Mo
45	45	ASTM/ASME	B/SB-463	—	N08026		80/35 [550/240]	Plate, Sheet, & Strip	35Ni-30Fe-24Cr-6Mo-3Cu
45	45	ASTM/ASME	B/SB-464	—	N08020		80/35 [550/240]	Welded Pipe	35Ni-35Fe-20Cr-Cb
45	45	ASTM/ASME	B/SB-464	—	N08024		80/35 [550/240]	Welded Pipe	37Ni-33Fe-23Cr-4Mo
45	45	ASTM/ASME	B/SB-464	—	N08026		80/35 [550/240]	Welded Pipe	35Ni-30Fe-24Cr-6Mo-3Cu
45	45	ASTM/ASME	B/SB-468	—	N08020		80/35 [550/240]	Welded Tube	35Ni-35Fe-20Cr-Cb

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Nickel and Nickel Base Alloys									
45	45	ASTM/ASME	B/SB-468	—	N08024		80/35 [550/240]	Welded Tube	37Ni-33Fe-23Cr-4Mo
45	45	ASTM/ASME	B/SB-468	—	N08026		80/35 [550/240]	Welded Tube	35Ni-30Fe-24Cr-6Mo-3Cu
45	45	ASTM/ASME	B/SB-473	—	N08020		80/35 [550/240]	Bar	35Ni-35Fe-20Cr-Cb
45	45	ASTM/ASME	B/SB-473	—	N08024		80/35 [550/240]	Bar	37Ni-33Fe-23Cr-4Mo
45	45	ASTM/ASME	B/SB-473	—	N08026		80/35 [550/240]	Bar	35Ni-30Fe-24Cr-6Mo-3Cu
45	8.2	ASTM	A479	904L	N08904		71/31 [490/215]	Bars & Shapes	44Fe-25Ni-21Cr-Mo
45	45	ASTM/ASME	A/SA-494	CU5MCuC	N08826		75/35 [515/240]	Castings	42Ni-21.5Cr-3Mo-2.3Cu
45	45	ASTM/ASME	B/SB-514	—	N08120		90/40 [620/275]	Welded Pipe	37Ni-33Fe-25Cr
45	45	ASTM/ASME	B/SB-514	—	N08800		75/30 [515/205]	Welded Pipe	33Ni-42Fe-21Cr
45	45	ASTM/ASME	B/SB-514	—	N08810		65/25 [450/170]	Welded Pipe	33Ni-42Fe-21Cr
45	45	ASTM/ASME	B/SB-515	—	N08120		90/40 [620/275]	Welded Tube	37Ni-33Fe-25Cr
45	45	ASTM/ASME	B/SB-515	—	N08800		75/30 [515/205]	Welded Tube	33Ni-42Fe-21Cr
45	45	ASTM/ASME	B/SB-515	—	N08810		65/25 [450/170]	Welded Tube	33Ni-42Fe-21Cr
45	45	ASTM/ASME	B/SB-515	—	N08811		65/25 [450/170]	Welded Tube	33Ni-42Fe-21Cr-Al-Ti
45	45	ASTM/ASME	B/SB-564	—	N08031		94/40 [650/275]	Forgings	31Ni-31Fe-27Cr-7Mo
45	45	ASTM/ASME	B/SB-564	—	N08120		90/40 [620/275]	Forgings	37Ni-33Fe-25Cr
45	8.2	ASTM/ASME	B/SB-564	—	N08367		95/45 [655/310]	Forgings	46Fe-24Ni-21Cr-6Mo-Cu-N
45	45	ASTM/ASME	B/SB-564	—	N08800		75/30 [515/205]	Forgings	33Ni-42Fe-21Cr
45	45	ASTM/ASME	B/SB-564	—	N08810		65/25 [450/170]	Forgings	33Ni-42Fe-21Cr
45	44	ASTM/ASME	B/SB-564	—	N08811		65/25 [450/170]	Forgings	33Ni-42Fe-21Cr-Al-Ti
45	45	ASTM/ASME	B/SB-564	—	N08825		85/35 [585/240]	Forgings	42Ni-21.5Cr-3Mo-2.3Cu
45	45	ASTM/ASME	B/SB-564	—	R20033		109/55 [750/380]	Forgings	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N
45	45	ASTM/ASME	B/SB-572	—	R30556		100/45 [690/310]	Rod	21Ni-30Fe-22Cr-18Co-3Mo-3W
45	43	ASTM/ASME	B/SB-581	—	N06007	≥0.3125 and ≤0.75 [≥8 and ≤19]	90/35 [620/240]	Rod	47Ni-22Cr-19Fe-6Mo
45	43	ASTM/ASME	B/SB-581	—	N06007	>0.75 and ≤3.5 [≥19 and ≤89]	85/30 [585/205]	Rod	47Ni-22Cr-19Fe-6Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
45	45	ASTM/ASME	B/SB-581	—	N06030		85/35 [585/240]	Rod	40Ni-29Cr-15Fe-5Mo
45	45	ASTM/ASME	B/SB-581	—	N06975		85/32 [585/220]	Rod	49Ni-25Cr-18Fe-6Mo
45	45	ASTM/ASME	B/SB-581	—	N06985	>0.75 and ≤3.5 >19 and ≤89]	85/30 [585/205]	Rod	47Ni-22Cr-20Fe-7Mo
45	45	ASTM/ASME	B/SB-581	—	N06985	≥0.3125 and ≤0.75 [≥8 and ≤19]	90/35 [620/240]	Rod	47Ni-22Cr-20Fe-7Mo
45	45	ASTM/ASME	B/SB-581	—	N08031		94/40 [650/275]	Rod	31Ni-31Fe-27Cr-7Mo
45	43	ASTM/ASME	B/SB-582	—	N06007	≤0.75 [≤19]	90/35 [620/240]	Plate, Sheet, & Strip	47Ni-22Cr-19Fe-6Mo
45	43	ASTM/ASME	B/SB-582	—	N06007	>0.75 and ≤2.5 [>19 and ≤64]	85/30 [585/205]	Plate, Sheet, & Strip	47Ni-22Cr-19Fe-6Mo
45	45	ASTM/ASME	B/SB-582	—	N06030		85/35 [585/240]	Plate, Sheet, & Strip	40Ni-29Cr-15Fe-5Mo
45	45	ASTM/ASME	B/SB-582	—	N06975		85/32 [585/220]	Plate, Sheet, & Strip	49Ni-25Cr-18Fe-6Mo
45	45	ASTM/ASME	B/SB-582	—	N06985	>0.75 and ≤2.5 [>19 and ≤64]	85/30 [585/205]	Plate, Sheet, & Strip	47Ni-22Cr-20Fe-7Mo
45	45	ASTM/ASME	B/SB-582	—	N06985	≤0.75 [≤19]	90/35 [620/240]	Plate, Sheet, & Strip	47Ni-22Cr-20Fe-7Mo
45	8.2	ASTM/ASME	B/SB-599	—	N08700		80/35 [550/240]	Plate, Sheet, & Strip	25Ni-47Fe-21Cr-5Mo
45	43	ASTM/ASME	B/SB-619	—	N06007		90/35 [620/240]	Welded Pipe	47Ni-22Cr-19Fe-6Mo
45	45	ASTM/ASME	B/SB-619	—	N06030		85/35 [585/240]	Welded Pipe	40Ni-29Cr-15Fe-5Mo
45	45	ASTM/ASME	B/SB-619	—	N06975		85/32 [585/220]	Welded Pipe	49Ni-25Cr-18Fe-6Mo
45	45	ASTM/ASME	B/SB-619	—	N06985		90/35 [620/240]	Welded Pipe	47Ni-22Cr-20Fe-7Mo
45	45	ASTM/ASME	B/SB-619	—	N08031		94/40 [650/275]	Welded Pipe	31Ni-31Fe-27Cr-7Mo
45	8.2	ASTM/ASME	B/SB-619	—	N08320		75/28 [515/195]	Welded Pipe	26Ni-22Cr-5Mo-Ti
45	45	ASTM/ASME	B/SB-619	—	R20033		109/55 [750/380]	Welded Pipe	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N
45	45	ASTM/ASME	B/SB-619	—	R30556		100/45 [690/310]	Welded Pipe	21Ni-30Fe-22Cr-18Co-3Mo-3W
45	8.2	ASTM/ASME	B/SB-620	—	N08320		75/28 [515/195]	Plate, Sheet, & Strip	26Ni-22Cr-5Mo-Ti
45	8.2	ASTM/ASME	B/SB-621	—	N08320		75/28 [515/195]	Rod	26Ni-22Cr-5Mo-Ti
45	43	ASTM/ASME	B/SB-622	—	N06007		90/35 [620/240]	Seamless Pipe & Tube	47Ni-22Cr-19Fe-6Mo
45	45	ASTM/ASME	B/SB-622	—	N06030		85/35 [585/240]	Seamless Pipe & Tube	40Ni-29Cr-15Fe-5Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
45	45	ASTM/ASME	B/SB-622	—	N06975		85/32 [585/220]	Seamless Pipe & Tube	49Ni-25Cr-18Fe-6Mo
45	45	ASTM/ASME	B/SB-622	—	N06985		90/35 [620/240]	Seamless Pipe & Tube	47Ni-22Cr-20Fe-7Mo
45	45	ASTM/ASME	B/SB-622	—	N08031		94/40 [650/275]	Seamless Pipe & Tube	31Ni-31Fe-27Cr-7Mo
45	45	ASTM/ASME	B/SB-622	—	N08135		73/31 [505/215]	Seamless Pipe & Tube	36Ni-35Fe-22Cr-5Mo-W
45	8.2	ASTM/ASME	B/SB-622	—	N08320		75/28 [515/195]	Seamless Pipe & Tube	26Ni-22Cr-5Mo-Ti
45	45	ASTM/ASME	B/SB-622	—	N08535		73/31 [505/215]	Seamless Pipe & Tube	37Fe-33Ni-26Cr-3Mo-Cu
45	45	ASTM/ASME	B/SB-622	—	R20033		109/55 [750/380]	Seamless Pipe & Tube	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N
45	45	ASTM/ASME	B/SB-622	—	R30556		100/45 [690/310]	Seamless Pipe & Tube	21Ni-30Fe-22Cr-18Co-3Mo-3W
45	45	ASTM/ASME	B/SB-625	—	N08031		94/40 [650/275]	Plate, Sheet, & Strip	31Ni-31Fe-27Cr-7Mo
45	8.2	ASTM/ASME	B/SB-625	—	N08904		71/31 [490/215]	Plate, Sheet, & Strip	44Fe-25Ni-21Cr-Mo
45	8.2	ASTM/ASME	B/SB-625	—	N08925		87/43 [600/295]	Plate, Sheet, & Strip	25Ni-20Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-625	—	N08926		94/43 [650/295]	Plate, Sheet, & Strip	25Ni-20Cr-6Mo-Co-N
45	8.2	ASTM/ASME	B/SB-625	—	N08932		87/44 [600/305]	Plate, Sheet, & Strip	41Fe-25Ni-25Cr-5Mo-Cu-N
45	45	ASTM/ASME	B/SB-625	—	R20033		109/55 [750/380]	Plate, Sheet, & Strip	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N
45	43	ASTM/ASME	B/SB-626	—	N06007		90/35 [620/240]	Welded Tube	47Ni-22Cr-19Fe-6Mo
45	45	ASTM/ASME	B/SB-626	—	N06030		85/35 [585/240]	Welded Tube	40Ni-29Cr-15Fe-5Mo
45	45	ASTM/ASME	B/SB-626	—	N06975		85/32 [585/220]	Welded Tube	49Ni-25Cr-18Fe-6Mo
45	45	ASTM/ASME	B/SB-626	—	N06985		90/35 [620/240]	Welded Tube	47Ni-22Cr-20Fe-7Mo
45	45	ASTM/ASME	B/SB-626	—	N08031		94/40 [650/275]	Welded Tube	31Ni-31Fe-27Cr-7Mo
45	8.2	ASTM/ASME	B/SB-626	—	N08320		75/28 [515/195]	Welded Tube	26Ni-22Cr-5Mo-Ti
45	45	ASTM/ASME	B/SB-626	—	R20033		109/55 [750/380]	Welded Tube	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N
45	45	ASTM/ASME	B/SB-626	—	R30556		100/45 [690/310]	Welded Tube	21Ni-30Fe-22Cr-18Co-3Mo-3W
45	45	ASTM/ASME	B/SB-649	—	N08031		94/40 [650/275]	Bar & Wire	31Ni-31Fe-27Cr-7Mo
45	8.2	ASTM/ASME	B/SB-649	—	N08904		71/31 [490/215]	Bar & Wire	44Fe-25Ni-21Cr-Mo
45	8.2	ASTM/ASME	B/SB-649	—	N08925		87/43 [600/295]	Bar & Wire	25Ni-20Cr-6Mo-Cu-N

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
45	8.2	ASTM/ASME	B/SB-649	—	N08926		94/43 [650/295]	Bar & Wire	25Ni-20Cr-6Mo-Cu-N
45	45	ASTM/ASME	B/SB-649	—	R20033		109/55 [750/380]	Bar & Wire	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N
45	45	ASTM/ASME	B/SB-668	—	N08028		73/31 [505/215]	Seamless Tube	31Ni-31Fe-29Cr-Mo
45	8.2	ASTM/ASME	B/SB-672	—	N08700		80/35 [550/240]	Bar & Wire	25Ni-47Fe-21Cr-3Mo
45	8.2	ASTM/ASME	B/SB-673	—	N08904		71/31 [490/215]	Welded Pipe	44Fe-25Ni-21Cr-Mo
45	8.2	ASTM/ASME	B/SB-673	—	N08925		87/43 [600/295]	Welded Pipe	25Ni-20Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-673	—	N08926		94/43 [650/295]	Welded Pipe	25Ni-20Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-674	—	N08904		71/31 [490/215]	Welded Tube	44Fe-25Ni-21Cr-Mo
45	8.2	ASTM/ASME	B/SB-674	—	N08925		87/43 [600/295]	Welded Tube	25Ni-20Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-674	—	N08926		94/43 [650/295]	Welded Tube	25Ni-20Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-675	—	N08367	>0.1875 [>4.8]	95/45 [655/310]	Welded Pipe	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-675	—	N08367	≤ 0.1875 [≤ 4.8]	100/45 [690/310]	Welded Pipe	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-676	—	N08367	≤ 0.1875 [≤ 4.8]	100/45 [690/310]	Welded Tube	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-676	—	N08367	>0.1875 [>4.8]	95/45 [655/310]	Welded Tube	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-677	—	N08904		71/31 [490/215]	Seamless Pipe & Tube	44Fe-25Ni-21Cr-Mo
45	8.2	ASTM/ASME	B/SB-677	—	N08925		87/43 [600/295]	Seamless Pipe & Tube	25Ni-20Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-677	—	N08926		94/43 [650/295]	Seamless Pipe & Tube	25Ni-20Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-688	—	N08366		75/35 [515/240]	Plate, Sheet, & Strip	46Fe-24Ni-21Cr-6Mo
45	8.2	ASTM/ASME	B/SB-688	—	N08367	≤ 0.1875 [≤ 4.8]	100/45 [690/310]	Plate, Sheet, & Strip	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-688	—	N08367	>0.1875 [>4.8]	95/45 [655/310]	Plate, Sheet, & Strip	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-690	—	N08366		75/30 [515/205]	Seamless Pipe & Tube	46Fe-24Ni-21Cr-6Mo
45	8.2	ASTM/ASME	B/SB-690	—	N08367	>0.1875 [>4.8]	95/45 [655/310]	Seamless Pipe & Tube	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-690	—	N08367	≤ 0.1875 [≤ 4.8]	100/45 [690/310]	Seamless Pipe & Tube	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-691	—	N08366		75/30 [515/205]	Rod, Bar, & Wire	46Fe-24Ni-21Cr-6Mo
45	8.2	ASTM/ASME	B/SB-691	—	N08367		95/45 [655/310]	Rod, Bar, & Wire	46Fe-24Ni-21Cr-6Mo-Cu-N
45	45	ASTM/ASME	B/SB-704	—	N08825		85/35 [585/240]	Welded Tube	42Ni-21.5Cr-3Mo-2.3Cu
45	45	ASTM/ASME	B/SB-705	—	N08825		85/35 [585/240]	Welded Pipe	42Ni-21.5Cr-3Mo-2.3Cu
45	45	ASTM/ASME	B/SB-709	—	N08028		73/40 [505/275]	Plate, Sheet, & Strip	31Ni-31Fe-29Cr-Mo

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Nickel and Nickel Base Alloys									
45	43	ASTM	B718	—	N06333	>0.1875 [>5]	80/35 [550/240]	Plate, Sheet, & Strip	46Ni-26Cr-16Fe-3Mo-3W-3Co
45	43	ASTM	B719	—	N06333	≤ 0.1875 [≤ 5]	80/35 [550/240]	Bar	46Ni-26Cr-16Fe-3Mo-3W-3Co
45	—	ASTM	B720	—	N08310	—/— [—/—]	—/— [—/—]	Seamless Tube	Fe-Cr-Ni-Mo
45	43	ASTM	B722	—	N06333	>0.1875 [>5]	80/35 [550/240]	Seamless Pipe & Tube	46Ni-26Cr-16Fe-3Mo-3W-3Co
45	43	ASTM	B723	—	N06333	>0.1875 [>5]	80/35 [550/240]	Welded Pipe	46Ni-26Cr-16Fe-3Mo-3W-3Co
45	43	ASTM	B726	—	N06333	>0.1875 [>5]	80/35 [550/240]	Welded Tube	46Ni-26Cr-16Fe-3Mo-3W-3Co
45	45	ASTM/ASME	B/SB-729	—	N08020	>0.1875 [>5]	80/35 [550/240]	Seamless Pipe & Tube	35Ni-35Fe-20Cr-Cb
45	8.2	ASTM/ASME	B/SB-804	—	N08367	>0.1875 [>5]	95/45 [655/310]	Welded Pipe	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM/ASME	B/SB-804	—	N08367	≤ 0.1875 [≤ 5]	100/45 [690/310]	Welded Pipe	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM	A813	N08367	N08367	>0.1875 [>5]	95/45 [655/310]	Welded Pipe	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM	A813	N08367	N08367	≤ 0.1875 [≤ 5]	100/45 [690/310]	Welded Pipe	46Fe-24Ni-21Cr-6Mo-Cu-N
45	43	ASTM	B814	—	N06920	>0.1875 [>5]	95/35 [655/240]	Plate, Sheet, & Strip	46Ni-22Cr-19Fe-9Mo-2W
45	8.2	ASTM	A814	N08367	N08367	≤ 0.1875 [≤ 5]	100/45 [690/310]	Cold Worked Welded Pipe	46Fe-24Ni-21Cr-6Mo-Cu-N
45	8.2	ASTM	A814	N08367	N08367	>0.1875 [>5]	95/45 [655/310]	Cold Worked Welded Pipe	46Fe-24Ni-21Cr-6Mo-Cu-N
45	43	NACE	MR 01-75	100	N06950	110/102 [760/700]	90/35 [620/240]	Pipe	50Ni-20Cr-18Fe-9Mo
45	43	NACE	MR 01-75	110	N06950	115/110 [795/760]	90/35 [620/240]	Pipe	50Ni-20Cr-18Fe-9Mo
45	43	NACE	MR 01-75	125	N06950	131/125 [900/860]	90/35 [620/240]	Pipe	50Ni-20Cr-18Fe-9Mo
45	43	NACE	MR 01-75	140	N06950	145/140 [1000/965]	90/35 [620/240]	Pipe	50Ni-20Cr-18Fe-9Mo
46	45	ASTM/ASME	B/SB-163	—	N06045	>0.1875 [>5]	90/35 [620/240]	Seamless Tube	46Ni-27Cr-23Fe-2.75Si
46	45	ASTM/ASME	B/SB-166	—	N06045	>0.1875 [>5]	90/35 [620/240]	Rod, Bar, & Wire	46Ni-27Cr-23Fe-2.75Si
46	45	ASTM/ASME	B/SB-167	—	N06045	>0.1875 [>5]	90/35 [620/240]	Seamless Pipe & Tube	46Ni-27Cr-23Fe-2.75Si
46	45	ASTM/ASME	B/SB-168	—	N06045	>0.1875 [>5]	90/35 [620/240]	Plate, Sheet, & Strip	46Ni-27Cr-23Fe-2.75Si
46	45	ASTM/ASME	B/SB-366	—	N06045	>0.1875 [>5]	90/35 [620/240]	Fittings	46Ni-27Cr-23Fe-2.75Si
46	45	ASTM/ASME	B/SB-366	—	N08330	>0.1875 [>5]	70/30 [485/205]	Fittings	35Ni-19Cr-1.25Si
46	46	ASTM/ASME	B/SB-366	—	N12160	>0.1875 [>5]	90/35 [620/240]	Fittings	37Ni-30Co-28Cr-2.7Si
46	46	ASTM/ASME	B/SB-435	—	N12160	>0.1875 [>5]	90/35 [620/240]	Plate, Sheet, & Strip	37Ni-30Co-28Cr-2.7Si
46	45	ASTM/ASME	B/SB-462	—	N06045	>0.1875 [>5]	90/35 [620/240]	Forgings	46Ni-27Cr-23Fe-2.75Si
46	45	ASTM/ASME	B/SB-511	—	N08330	>0.1875 [>5]	70/30 [485/205]	Bars & Shapes	35Ni-19Cr-1.25Si
46	45	ASTM/ASME	B/SB-511	—	N08332	>0.1875 [>5]	67/27 [460/185]	Bars & Shapes	35Ni-19Cr-1.25Si-C

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Nickel and Nickel Base Alloys									
46	45	ASTM	B512	—	N08330	—	70/30 [485/205]	Bars & Billets	35Ni-19Cr-1.25Si
46	45	ASTM/ASME	B/SB-516	—	N06045	—	90/35 [620/240]	Welded Tube	46Ni-27Cr-23Fe-2.75Si
46	45	ASTM/ASME	B/SB-517	—	N06045	—	90/35 [620/240]	Welded Pipe	46Ni-27Cr-23Fe-2.75Si
46	45	ASTM/ASME	B/SB-535	—	N08330	—	70/30 [485/205]	Seamless Pipe & Tube	35Ni-19Cr-1.25Si
46	45	ASTM/ASME	B/SB-535	—	N08332	—	67/27 [460/185]	Seamless Pipe & Tube	35Ni-19Cr-1.25Si-C
46	45	ASTM/ASME	B/SB-536	—	N08330	—	70/30 [485/205]	Plate, Sheet, & Strip	35Ni-19Cr-1.25Si
46	45	ASTM/ASME	B/SB-536	—	N08332	—	67/27 [460/185]	Plate, Sheet, & Strip	35Ni-19Cr-1.25Si-C
46	45	ASTM/ASME	B/SB-564	—	N06045	—	90/35 [620/240]	Forgings	46Ni-27Cr-23Fe-2.75Si
46	46	ASTM/ASME	B/SB-564	—	N12160	—	90/35 [620/240]	Forgings	37Ni-30Co-28Cr-2.7Si
46	46	ASTM/ASME	B/SB-572	—	N12160	—	90/35 [620/240]	Rod	37Ni-30Co-28Cr-2.7Si
46	46	ASTM/ASME	B/SB-619	—	N12160	—	90/35 [620/240]	Welded Pipe	37Ni-30Co-28Cr-2.7Si
46	46	ASTM/ASME	B/SB-622	—	N12160	—	90/35 [620/240]	Seamless Pipe & Tube	37Ni-30Co-28Cr-2.7Si
46	46	ASTM/ASME	B/SB-626	—	N12160	—	90/35 [620/240]	Welded Tube	37Ni-30Co-28Cr-2.7Si
46	45	ASTM/ASME	B/SB-710	—	N08330	—	70/30 [485/205]	Welded Pipe	35Ni-19Cr-1.25Si
46	45	ASTM/ASME	B/SB-710	—	N08332	—	67/27 [460/185]	Welded Pipe	35Ni-19Cr-1.25Si-C
49	—	ASTM/ASME	B/SB-815	—	R31233	—	120/55 [825/380]	Rod	Co-26Cr-9Ni-5Mo-3Fe-2W
49	—	ASTM/ASME	B/SB-818	—	R31233	—	120/55 [825/380]	Plate, Sheet, & Strip	Co-26Cr-9Ni-5Mo-3Fe-2W

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I.2.2.1, and I.3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Titanium and Titanium Base Alloys									
51	51	ASTM/ASME	B/SB-265	1	R50250	35/20 [240/140]		Plate, Sheet, & Strip	Ti
51	51	ASTM/ASME	B/SB-265	11	R52250	35/20 [240/140]		Plate, Sheet, & Strip	Ti-Pd
51	52	ASTM/ASME	B/SB-265	13	R53413	40/25 [275/170]		Plate, Sheet, & Strip	Ti-0.5Ni-Ru
51	51	ASTM/ASME	B/SB-265	16	R52402	50/40 [345/275]		Plate, Sheet, & Strip	Ti-Pd
51	51	ASTM/ASME	B/SB-265	16H	R52402	58/40 [400/275]		Plate, Sheet, & Strip	Ti-Pd
51	51	ASTM/ASME	B/SB-265	17	R52252	35/20 [240/140]		Plate, Sheet, & Strip	Ti-Pd
51	51	ASTM/ASME	B/SB-265	2	R50400	50/40 [345/275]		Plate, Sheet, & Strip	Ti
51	51	ASTM/ASME	B/SB-265	26	R52404	50/40 [345/275]		Plate, Sheet, & Strip	Ti-Ru
51	51	ASTM/ASME	B/SB-265	26H	R52404	58/40 [400/275]		Plate, Sheet, & Strip	Ti-Ru
51	51	ASTM/ASME	B/SB-265	27	R52254	35/20 [240/140]		Plate, Sheet, & Strip	Ti-Ru
51	51	ASTM/ASME	B/SB-265	2H	R50400	58/40 [400/275]		Plate, Sheet, & Strip	Ti
51	52	ASTM/ASME	B/SB-265	30	R53530	50/40 [345/275]		Plate, Sheet, & Strip	Ti-0.3Co-Pd
51	54	ASTM/ASME	B/SB-265	33	R53442	50/40 [345/275]		Plate, Sheet, & Strip	Ti-Ni-Pd-Ru-Cr
51	51	ASTM/ASME	B/SB-265	7	R52400	50/40 [345/275]		Plate, Sheet, & Strip	Ti-Pd
51	51	ASTM/ASME	B/SB-265	7H	R52400	58/40 [400/275]		Plate, Sheet, & Strip	Ti-Pd
51	51	ASTM	B337	1	R50250	35/25 [240/170]		Seamless & Welded Pipe	Ti
51	51	ASTM	B337	11	R52250	35/25 [240/170]		Seamless & Welded Pipe	Ti-Pd
51	51	ASTM	B337	2	R50400	50/40 [345/275]		Seamless & Welded Pipe	Ti
51	51	ASTM	B337	7	R52400	50/40 [345/275]		Seamless & Welded Pipe	Ti-Pd
51	51	ASTM/ASME	B/SB-338	1	R50250	35/20 [240/140]		Seamless & Welded Tube	Ti
51	51	ASTM/ASME	B/SB-338	11	R52250	35/20 [240/140]		Seamless & Welded Tube	Ti-Pd
51	52	ASTM/ASME	B/SB-338	13	R53413	40/25 [275/170]		Seamless & Welded Tube	Ti-0.5Ni-Ru
51	51	ASTM/ASME	B/SB-338	16	R52402	50/40 [345/275]		Seamless & Welded Tube	Ti-Pd
51	51	ASTM/ASME	B/SB-338	16H	R52402	58/40 [400/275]		Seamless & Welded Tube	Ti-Pd
51	51	ASTM/ASME	B/SB-338	17	R52252	35/20 [240/140]		Seamless & Welded Tube	Ti-Pd
51	51	ASTM/ASME	B/SB-338	2	R50400	50/40 [345/275]		Seamless & Welded Tube	Ti
51	51	ASTM/ASME	B/SB-338	26	R52404	50/40 [345/275]		Seamless & Welded Tube	Ti-Ru
51	51	ASTM/ASME	B/SB-338	26H	R52404	58/40 [400/275]		Seamless & Welded Tube	Ti-Ru
51	51	ASTM/ASME	B/SB-338	27	R52254	35/20 [240/140]		Seamless & Welded Tube	Ti-Ru

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Titanium and Titanium Base Alloys									
51	51	ASTM/ASME	B/SB-338	2H	R50400		58/40 [400/275]	Seamless & Welded Tube	Ti
51	52	ASTM/ASME	B/SB-338	30	R53530		50/40 [345/275]	Seamless & Welded Tube	Ti-0.3Co-Pd
51	54	ASTM/ASME	B/SB-338	33	R53442		50/40 [345/275]	Seamless & Welded Tube	Ti-Ni-Pd-Ru-Cr
51	51	ASTM/ASME	B/SB-338	7	R52400		50/40 [345/275]	Seamless & Welded Tube	Ti-Pd
51	51	ASTM/ASME	B/SB-338	7H	R52400		58/40 [400/275]	Seamless & Welded Tube	Ti-Pd
51	51	ASTM/ASME	B/SB-348	1	R50250		35/20 [240/140]	Bars & Billets	Ti
51	51	ASTM/ASME	B/SB-348	11	R52250		35/20 [240/140]	Bars & Billets	Ti-Pd
51	52	ASTM/ASME	B/SB-348	13	R53413		40/25 [275/170]	Bars & Billets	Ti-0.5Ni-Ru
51	51	ASTM/ASME	B/SB-348	16	R52402		50/40 [345/275]	Bars & Billets	Ti-Pd
51	51	ASTM/ASME	B/SB-348	16H	R52402		58/40 [400/275]	Bars & Billets	Ti-Pd
51	51	ASTM/ASME	B/SB-348	17	R52252		35/20 [240/140]	Bars & Billets	Ti-Pd
51	51	ASTM/ASME	B/SB-348	2	R50400		50/40 [345/275]	Bars & Billets	Ti
51	51	ASTM/ASME	B/SB-348	26	R52404		50/40 [345/275]	Bars & Billets	Ti-Ru
51	51	ASTM/ASME	B/SB-348	26H	R52404		58/40 [400/275]	Bars & Billets	Ti-Ru
51	51	ASTM/ASME	B/SB-348	2H	R50400		58/40 [400/275]	Bars & Billets	Ti
51	52	ASTM/ASME	B/SB-348	30	R53530		50/40 [345/275]	Bars & Billets	Ti-0.3Co-Pd
51	54	ASTM/ASME	B/SB-348	33	R53442		50/40 [345/275]	Bars & Billets	Ti-Ni-Pd-Ru-Cr
51	51	ASTM/ASME	B/SB-348	7	R52400		50/40 [345/275]	Bars & Billets	Ti-Pd
51	51	ASTM/ASME	B/SB-348	7H	R52400		58/40 [400/275]	Bars & Billets	Ti-Pd
51	51	ASTM/ASME	B/SB-363	WPT 1	R50250		35/25 [240/170]	Seamless & Welded Fittings	Ti
51	51	ASTM/ASME	B/SB-363	WPT 11	R52250		35/25 [240/170]	Seamless & Welded Fittings	Ti-Pd
51	52	ASTM/ASME	B/SB-363	WPT 13	R53413		40/25 [275/170]	Seamless & Welded Fittings	Ti-0.5Ni-Ru
51	51	ASTM/ASME	B/SB-363	WPT 16	R52402		50/40 [345/275]	Seamless & Welded Fittings	Ti-Pd
51	51	ASTM/ASME	B/SB-363	WPT 16H	R52402		58/40 [400/275]	Seamless & Welded Fittings	Ti-Pd
51	51	ASTM/ASME	B/SB-363	WPT 17	R52252		35/25 [240/170]	Seamless & Welded Fittings	Ti-Pd
51	51	ASTM/ASME	B/SB-363	WPT 2	R50400		50/40 [345/275]	Seamless & Welded Fittings	Ti
51	51	ASTM/ASME	B/SB-363	WPT 26	R52404		50/40 [345/275]	Seamless & Welded Fittings	Ti-Ru
51	51	ASTM/ASME	B/SB-363	WPT 26H	R52404		58/40 [400/275]	Seamless & Welded Fittings	Ti-Ru
51	52	ASTM/ASME	B/SB-363	WPT 30	R53530		50/40 [345/275]	Seamless & Welded Fittings	Ti-0.3Co-Pd

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Titanium and Titanium Base Alloys									
51	51	ASTM/ASME	B/SB-363	WPT 7	R52400		50/40 [345/275]	Seamless & Welded Fittings	Ti-Pd
51	51	ASTM/ASME	B/SB-363	WPT 7H	R52400		58/40 [400/275]	Seamless & Welded Fittings	Ti-Pd
51	51	ASTM/ASME	B/SB-367	C-16	R52402		50/40 [345/275]	Castings	Ti-Pd
51	51	ASTM/ASME	B/SB-367	C-17	R52252		35/25 [240/170]	Castings	Ti-Pd
51	51	ASTM/ASME	B/SB-367	C-2	R50400		50/40 [345/275]	Castings	Ti
51	51	ASTM/ASME	B/SB-367	C-7	—		50/40 [345/275]	Castings	Ti-Pd
51	51	ASTM/ASME	B/SB-381	F-1	R50250		35/20 [240/140]	Forgings	Ti
51	51	ASTM/ASME	B/SB-381	F-11	R52250		35/20 [240/140]	Forgings	Ti-Pd
51	52	ASTM/ASME	B/SB-381	F-13	R53413		40/25 [275/170]	Forgings	Ti-0.5Ni-Ru
51	51	ASTM/ASME	B/SB-381	F-16	R52402		50/40 [345/275]	Forgings	Ti-Pd
51	51	ASTM/ASME	B/SB-381	F-16H	R52402		58/40 [400/275]	Forgings	Ti-Pd
51	51	ASTM/ASME	B/SB-381	F-17	R52252		35/20 [240/140]	Forgings	Ti-Pd
51	51	ASTM/ASME	B/SB-381	F-2	R50400		50/40 [345/275]	Forgings	Ti
51	51	ASTM/ASME	B/SB-381	F-26	R52404		50/40 [345/275]	Forgings	Ti-Ru
51	51	ASTM/ASME	B/SB-381	F-26H	R52404		58/40 [400/275]	Forgings	Ti-Ru
51	51	ASTM/ASME	B/SB-381	F-2H	R50400		58/40 [400/275]	Forgings	Ti
51	52	ASTM/ASME	B/SB-381	F-30	R53530		50/40 [345/275]	Forgings	Ti-0.3Co-Pd
51	51	ASTM/ASME	B/SB-381	F-7	R52400		50/40 [345/275]	Forgings	Ti-Pd
51	51	ASTM/ASME	B/SB-381	F-7H	R52400		58/40 [400/275]	Forgings	Ti-Pd
51	51	ASTM/ASME	B/SB-861	1	R50250		35/20 [240/140]	Seamless Pipe	Ti
51	51	ASTM/ASME	B/SB-861	11	R52250		35/20 [240/140]	Seamless Pipe	Ti-Pd
51	52	ASTM/ASME	B/SB-861	13	R53413		40/25 [275/170]	Seamless Pipe	Ti-0.5Ni-Ru
51	51	ASTM/ASME	B/SB-861	16	R52402		50/40 [345/275]	Seamless Pipe	Ti-Pd
51	51	ASTM/ASME	B/SB-861	16H	R52402		58/40 [400/275]	Seamless Pipe	Ti-Pd
51	51	ASTM/ASME	B/SB-861	17	R52252		35/20 [240/140]	Seamless Pipe	Ti-Pd
51	51	ASTM/ASME	B/SB-861	2	R50400		50/40 [345/275]	Seamless Pipe	Ti
51	51	ASTM/ASME	B/SB-861	26	R52404		50/40 [345/275]	Seamless Pipe	Ti-Ru
51	51	ASTM/ASME	B/SB-861	26H	R52404		58/40 [400/275]	Seamless Pipe	Ti-Ru
51	51	ASTM/ASME	B/SB-861	2H	R50400		58/40 [400/275]	Seamless Pipe	Ti

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Titanium and Titanium Base Alloys									
51	54	ASTM/ASME	B/SB-861	33	R53442		50/40 [345/275]	Seamless Pipe	Ti-Ni-Pd-Ru-Cr
51	51	ASTM/ASME	B/SB-861	7	R52400		50/40 [345/275]	Seamless Pipe	Ti-Pd
51	51	ASTM/ASME	B/SB-861	7H	R52400		58/40 [400/275]	Seamless Pipe	Ti-Pd
51	51	ASTM/ASME	B/SB-862	1	R50250		35/20 [240/140]	Welded Pipe	Ti
51	51	ASTM/ASME	B/SB-862	11	R52250		35/20 [240/140]	Welded Pipe	Ti-Pd
51	52	ASTM/ASME	B/SB-862	13	R53413		40/25 [275/170]	Welded Pipe	Ti-0.5Ni-Ru
51	51	ASTM/ASME	B/SB-862	16	R52402		50/40 [345/275]	Welded Pipe	Ti-Pd
51	51	ASTM/ASME	B/SB-862	16H	R52402		58/40 [400/275]	Welded Pipe	Ti-Pd
51	51	ASTM/ASME	B/SB-862	17	R52252		35/20 [240/140]	Welded Pipe	Ti-Pd
51	51	ASTM/ASME	B/SB-862	2	R50400		50/40 [345/275]	Welded Pipe	Ti
51	51	ASTM/ASME	B/SB-862	26	R52404		50/40 [345/275]	Welded Pipe	Ti-Ru
51	51	ASTM/ASME	B/SB-862	26H	R52404		58/40 [400/275]	Welded Pipe	Ti-Ru
51	51	ASTM/ASME	B/SB-862	27	R52254		35/20 [240/140]	Welded Pipe	Ti-Ru
51	51	ASTM/ASME	B/SB-862	2H	R50400		58/40 [400/275]	Welded Pipe	Ti
51	54	ASTM/ASME	B/SB-862	33	R53442		50/40 [345/275]	Welded Pipe	Ti-Ni-Pd-Ru-Cr
51	51	ASTM/ASME	B/SB-862	7	R52400		50/40 [345/275]	Welded Pipe	Ti-Pd
51	51	ASTM/ASME	B/SB-862	7H	R52400		58/40 [400/275]	Welded Pipe	Ti-Pd
52	52	ASTM/ASME	B/SB-265	12	R53400		70/50 [485/345]	Plate, Sheet, & Strip	Ti-0.3Mo-0.8Ni
52	52	ASTM/ASME	B/SB-265	14	R53414		60/40 [415/275]	Plate, Sheet, & Strip	Ti-0.5Ni-Ru
52	52	ASTM/ASME	B/SB-265	15	R53415		70/55 [485/380]	Plate, Sheet, & Strip	Ti-0.5Ni-Ru
52	52	ASTM/ASME	B/SB-265	3	R50550		65/55 [450/380]	Plate, Sheet, & Strip	Ti
52	52	ASTM/ASME	B/SB-265	31	R53532		65/55 [450/380]	Plate, Sheet, & Strip	Ti-0.3Co-Pd
52	54	ASTM/ASME	B/SB-265	34	R53445		65/55 [450/380]	Plate, Sheet, & Strip	Ti-Ni-Pd-Ru-Cr
52	52	ASTM	B337	12	R53400		70/50 [485/345]	Seamless & Welded Pipe	Ti-0.3Mo-0.8Ni
52	52	ASTM	B337	3	R50550		65/55 [450/380]	Seamless & Welded Pipe	Ti
52	52	ASTM/ASME	B/SB-338	12	R53400		70/50 [485/345]	Seamless & Welded Tube	Ti-0.3Mo-0.8Ni
52	52	ASTM/ASME	B/SB-338	14	R53414		60/40 [415/275]	Seamless & Welded Tube	Ti-0.5Ni-Ru
52	52	ASTM/ASME	B/SB-338	15	R53415		70/55 [485/380]	Seamless & Welded Tube	Ti-0.5Ni-Ru
52	52	ASTM/ASME	B/SB-338	3	R50550		65/55 [450/380]	Seamless & Welded Tube	Ti

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Titanium and Titanium Base Alloys									
52	52	ASTM/ASME	B/SB-338	31	R53532		65/55 [450/380]	Seamless & Welded Tube	Ti-0.3Co-Pd
52	54	ASTM/ASME	B/SB-338	34	R53445		65/55 [450/380]	Seamless & Welded Tube	Ti-Ni-Pd-Ru-Cr
52	52	ASTM/ASME	B/SB-348	12	R53400		70/50 [485/345]	Bars & Billets	Ti-0.3Mo-0.8Ni
52	52	ASTM/ASME	B/SB-348	14	R53414		60/40 [415/275]	Bars & Billets	Ti-0.5Ni-Ru
52	52	ASTM/ASME	B/SB-348	15	R53415		70/55 [485/380]	Bars & Billets	Ti-0.5Ni-Ru
52	52	ASTM/ASME	B/SB-348	3	R50550		65/55 [450/380]	Bars & Billets	Ti
52	52	ASTM/ASME	B/SB-348	31	R53532		65/55 [450/380]	Bars & Billets	Ti-0.3Co-Pd
52	54	ASTM/ASME	B/SB-348	34	R53445		65/55 [450/380]	Bars & Billets	Ti-Ni-Pd-Ru-Cr
52	52	ASTM/ASME	B/SB-363	WPT 12	R53400		70/50 [485/345]	Seamless & Welded Fittings	Ti-0.3Mo-0.8Ni
52	52	ASTM/ASME	B/SB-363	WPT 14	R53414		60/40 [415/275]	Seamless & Welded Fittings	Ti-0.5Ni-Ru
52	52	ASTM/ASME	B/SB-363	WPT 15	R53415		65/55 [450/380]	Seamless & Welded Fittings	Ti-0.5Ni-Ru
52	52	ASTM/ASME	B/SB-363	WPT 3	R50550		65/55 [450/380]	Seamless & Welded Fittings	Ti
52	52	ASTM/ASME	B/SB-367	C-3	R50550		65/55 [450/380]	Castings	Ti
52	52	ASTM/ASME	B/SB-367	C-8	—		65/55 [450/380]	Castings	Ti-Pd
52	52	ASTM/ASME	B/SB-381	F-12	R53400		70/50 [485/345]	Forgings	Ti-0.3Mo-0.8Ni
52	52	ASTM/ASME	B/SB-381	F-14	R53414		60/40 [415/275]	Forgings	Ti-0.5Ni-Ru
52	52	ASTM/ASME	B/SB-381	F-15	R53415		70/55 [485/380]	Forgings	Ti-0.5Ni-Ru
52	52	ASTM/ASME	B/SB-381	F-3	R50550		65/55 [450/380]	Forgings	Ti
52	52	ASTM/ASME	B/SB-381	F-31	R53532		65/55 [450/380]	Forgings	Ti-0.3Co-Pd
52	52	ASTM/ASME	B/SB-861	12	R53400		70/50 [485/345]	Seamless Pipe	Ti-0.3Mo-0.8Ni
52	52	ASTM/ASME	B/SB-861	14	R53414		60/40 [415/275]	Seamless Pipe	Ti-0.5Ni-Ru
52	52	ASTM/ASME	B/SB-861	15	R53415		70/55 [485/380]	Seamless Pipe	Ti-0.5Ni-Ru
52	52	ASTM/ASME	B/SB-861	3	R50550		65/55 [450/380]	Seamless Pipe	Ti
52	54	ASTM/ASME	B/SB-861	34	R53445		65/55 [450/380]	Seamless Pipe	Ti-Ni-Pd-Ru-Cr
52	52	ASTM/ASME	B/SB-862	12	R53400		70/50 [485/345]	Welded Pipe	Ti-0.3Mo-0.8Ni
52	52	ASTM/ASME	B/SB-862	14	R53414		60/40 [415/275]	Welded Pipe	Ti-0.5Ni-Ru
52	52	ASTM/ASME	B/SB-862	15	R53415		70/55 [485/380]	Welded Pipe	Ti-0.5Ni-Ru
52	52	ASTM/ASME	B/SB-862	3	R50550		65/55 [450/380]	Welded Pipe	Ti
52	54	ASTM/ASME	B/SB-862	34	R53445		65/55 [450/380]	Welded Pipe	Ti-Ni-Pd-Ru-Cr

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Titanium and Titanium Base Alloys									
53	53	ASTM/ASME	B/SB-265	18	R56322		90/70 [620/485]	Plate, Sheet, & Strip	Ti-3Al-2.5V-Pd
53	54	ASTM/ASME	B/SB-265	19	R58640		115/110 [795/760]	Plate, Sheet, & Strip	Ti-3Al-8V-6Cr-4Zr-4Mo
53	54	ASTM/ASME	B/SB-265	20	R58645		115/110 [795/760]	Plate, Sheet, & Strip	Ti-3Al-8V-6Cr-4Zr-4Mo-Pd
53	54	ASTM/ASME	B/SB-265	21	R58210		115/110 [795/760]	Plate, Sheet, & Strip	Ti-15Mo-3Al-2.7Nb-Si
53	53	ASTM/ASME	B/SB-265	28	R56323		90/70 [620/485]	Plate, Sheet, & Strip	Ti-3Al-2.5V-0.1Ru
53	52	ASTM/ASME	B/SB-265	32	R55111		100/85 [690/585]	Plate, Sheet, & Strip	Ti-5Al-1Sn-1Zr-1V-Mo
53	51.4	ASTM/ASME	B/SB-265	4	R50700		80/70 [550/485]	Plate, Sheet, & Strip	Ti
53	53	ASTM/ASME	B/SB-265	9	R56320		90/70 [620/485]	Plate, Sheet, & Strip	Ti-3Al-2.5V
53	53	ASTM	B337	9	R56320		90/70 [620/485]	Seamless & Welded Pipe	Ti-3Al-2.5V
53	53	ASTM/ASME	B/SB-338	18	R56322		90/70 [620/485]	Seamless & Welded Tube	Ti-3Al-2.5V-Pd
53	53	ASTM/ASME	B/SB-338	28	R56323		90/70 [620/485]	Seamless & Welded Tube	Ti-3Al-2.5V-0.1Ru
53	53	ASTM/ASME	B/SB-338	9	R56320		90/70 [620/485]	Seamless & Welded Tube	Ti-3Al-2.5V
53	53	ASTM/ASME	B/SB-348	18	R56322		90/70 [620/485]	Bars & Billets	Ti-3Al-2.5V-Pd
53	54	ASTM/ASME	B/SB-348	19	R58640		115/110 [795/760]	Bars & Billets	Ti-3Al-8V-6Cr-4Zr-4Mo
53	54	ASTM/ASME	B/SB-348	20	R58645		115/110 [795/760]	Bars & Billets	Ti-3Al-8V-6Cr-4Zr-4Mo-Pd
53	54	ASTM/ASME	B/SB-348	21	R58210		115/110 [795/760]	Bars & Billets	Ti-15Mo-3Al-2.7Nb-Si
53	53	ASTM/ASME	B/SB-348	28	R56323		90/70 [620/485]	Bars & Billets	Ti-3Al-2.5V-0.1Ru
53	52	ASTM/ASME	B/SB-348	32	R55111		100/85 [690/585]	Bars & Billets	Ti-5Al-1Sn-1Zr-1V-Mo
53	51.4	ASTM/ASME	B/SB-348	4	R50700		80/70 [550/485]	Bars & Billets	Ti
53	53	ASTM/ASME	B/SB-348	9	R56320		90/70 [620/485]	Bars & Billets	Ti-3Al-2.5V
53	53	ASTM/ASME	B/SB-363	WPT 18	R56322		90/70 [620/485]	Seamless & Welded Fittings	Ti-3Al-2.5V-Pd
53	54	ASTM/ASME	B/SB-363	WPT 19	R58640		115/110 [795/760]	Seamless & Welded Fittings	Ti-3Al-8V-6Cr-4Zr-4Mo
53	54	ASTM/ASME	B/SB-363	WPT 20	R58645		115/110 [795/760]	Seamless & Welded Fittings	Ti-3Al-8V-6Cr-4Zr-4Mo-Pd
53	54	ASTM/ASME	B/SB-363	WPT 21	R58210		115/110 [795/760]	Seamless & Welded Fittings	Ti-15Mo-3Al-2.7Nb-Si
53	53	ASTM/ASME	B/SB-363	WPT 28	R56323		90/70 [620/485]	Seamless & Welded Fittings	Ti-3Al-2.5V-0.1Ru
53	53	ASTM/ASME	B/SB-363	WPT 9	R56320		90/70 [620/485]	Seamless & Welded Fittings	Ti-3Al-2.5V
53	53	ASTM/ASME	B/SB-381	F-18	R56322		90/70 [620/485]	Forgings	Ti-3Al-2.5V-Pd
53	54	ASTM/ASME	B/SB-381	F-19	R58640		115/110 [795/760]	Forgings	Ti-3Al-8V-6Cr-4Zr-4Mo
53	54	ASTM/ASME	B/SB-381	F-20	R58645		115/110 [795/760]	Forgings	Ti-3Al-8V-6Cr-4Zr-4Mo-Pd

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Titanium and Titanium Base Alloys									
53	54	ASTM/ASME	B/SB-381	F-21	R58210		115/110 [795/760]	Forgings	Ti-15Mo-3Al-2.7Nb-Si
53	53	ASTM/ASME	B/SB-381	F-28	R56323		90/70 [620/485]	Forgings	Ti-3Al-2.5V-0.1Ru
53	51.4	ASTM/ASME	B/SB-381	F-4	R50700		80/70 [550/485]	Forgings	Ti
53	53	ASTM/ASME	B/SB-381	F-9	R56320		90/70 [620/485]	Forgings	Ti-3Al-2.5V
53	53	ASTM/ASME	B/SB-861	18	R56322		90/70 [620/485]	Seamless Pipe	Ti-3Al-2.5V-Pd
53	54	ASTM/ASME	B/SB-861	19	R58640		115/110 [795/760]	Seamless Pipe	Ti-3Al-8V-6Cr-4Zr-4Mo
53	54	ASTM/ASME	B/SB-861	20	R58645		115/110 [795/760]	Seamless Pipe	Ti-3Al-8V-6Cr-4Zr-4Mo-Pd
53	54	ASTM/ASME	B/SB-861	21	R58210		115/110 [795/760]	Seamless Pipe	Ti-15Mo-3Al-2.7Nb-Si
53	53	ASTM/ASME	B/SB-861	28	R56323		90/70 [620/485]	Seamless Pipe	Ti-3Al-2.5V-0.1Ru
53	53	ASTM/ASME	B/SB-861	9	R56320		90/70 [620/485]	Seamless Pipe	Ti-3Al-2.5V
53	53	ASTM/ASME	B/SB-862	18	R56322		90/70 [620/485]	Welded Pipe	Ti-3Al-2.5V-Pd
53	54	ASTM/ASME	B/SB-862	19	R58640		115/110 [795/760]	Welded Pipe	Ti-3Al-8V-6Cr-4Zr-4Mo
53	54	ASTM/ASME	B/SB-862	20	R58645		115/110 [795/760]	Welded Pipe	Ti-3Al-8V-6Cr-4Zr-4Mo-Pd
53	54	ASTM/ASME	B/SB-862	21	R58210		115/110 [795/760]	Welded Pipe	Ti-15Mo-3Al-2.7Nb-Si
53	53	ASTM/ASME	B/SB-862	28	R56323		90/70 [620/485]	Welded Pipe	Ti-3Al-2.5V-0.1Ru
53	53	ASTM/ASME	B/SB-862	9	R56320		90/70 [620/485]	Welded Pipe	Ti-3Al-2.5V
53	54	AMS	4914	—	R58153		98/96 [675/660]	Sheet	Ti-15V-3Al-3Cr-3Sn
54	53	ASTM/ASME	B/SB-265	24	R56405		130/120 [895/825]	Plate, Sheet, & Strip	Ti-6Al-4V-Pd
54	53	ASTM/ASME	B/SB-265	25	R56403		130/120 [895/825]	Plate, Sheet, & Strip	Ti-6Al-4V-Ni-Pd
54	53	ASTM/ASME	B/SB-265	29	R56404		120/110 [825/760]	Plate, Sheet, & Strip	Ti-6Al-4V-Pd-ELI-Ru
54	53	ASTM/ASME	B/SB-265	35	R56340		130/120 [895/825]	Plate, Sheet, & Strip	Ti-4Al-2.5V-1.5Fe
54	53	ASTM/ASME	B/SB-265	5	R56400		130/120 [895/825]	Plate, Sheet, & Strip	Ti-6Al-4V
54	52	ASTM/ASME	B/SB-265	6	R54520		120/115 [825/795]	Plate, Sheet, & Strip	Ti-5Al-2.5Sn
54	53	ASTM/ASME	B/SB-338	35	R56340		130/120 [895/825]	Seamless & Welded Tube	Ti-4Al-2.5V-1.5Fe
54	53	ASTM/ASME	B/SB-348	23	R56407		120/110 [825/760]	Bars & Billets	Ti-6Al-4V-ELI
54	53	ASTM/ASME	B/SB-348	24	R56405		130/120 [895/825]	Bars & Billets	Ti-6Al-4V-Pd
54	53	ASTM/ASME	B/SB-348	25	R56403		130/120 [895/825]	Bars & Billets	Ti-6Al-4V-Ni-Pd
54	53	ASTM/ASME	B/SB-348	35	R56340		130/120 [895/825]	Bars & Billets	Ti-4Al-2.5V-1.5Fe
54	53	ASTM/ASME	B/SB-348	5	R56400		130/120 [895/825]	Bars & Billets	Ti-6Al-4V

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
Titanium and Titanium Base Alloys									
54	52	ASTM/ASME	B/SB-348	6	R54520		120/115 [825/795]	Bars & Billets	Ti-5Al-2.5Sn
54	53	ASTM/ASME	B/SB-363	WPT 23	R56407		120/110 [825/760]	Seamless & Welded Fittings	Ti-6Al-4V-ELI
54	53	ASTM/ASME	B/SB-363	WPT 24	R56405		130/120 [895/825]	Seamless & Welded Fittings	Ti-6Al-4V-Pd
54	53	ASTM/ASME	B/SB-363	WPT 25	R56403		130/120 [895/825]	Seamless & Welded Fittings	Ti-6Al-4V-Ni-Pd
54	53	ASTM/ASME	B/SB-367	C-5	R56400		130/120 [895/825]	Castings	Ti-6Al-4V
54	52	ASTM/ASME	B/SB-367	C-6	R54520		115/105 [795/725]	Castings	Ti-5Al-2.5Sn
54	53	ASTM/ASME	B/SB-381	F-23	R56407		120/110 [825/760]	Forgings	Ti-6Al-4V-ELI
54	53	ASTM/ASME	B/SB-381	F-24	R56405		130/120 [895/825]	Forgings	Ti-6Al-4V-Pd
54	53	ASTM/ASME	B/SB-381	F-25	R56403		130/120 [895/825]	Forgings	Ti-6Al-4V-Ni-Pd
54	53	ASTM/ASME	B/SB-381	F-5	R56400		130/120 [895/825]	Forgings	Ti-6Al-4V
54	52	ASTM/ASME	B/SB-381	F-6	R54520		120/115 [825/795]	Forgings	Ti-5Al-2.5Sn
54	53	ASTM/ASME	B/SB-861	23	R56407		120/110 [825/760]	Seamless Pipe	Ti-6Al-4V-ELI
54	53	ASTM/ASME	B/SB-861	24	R56405		130/120 [895/825]	Seamless Pipe	Ti-6Al-4V-Pd
54	53	ASTM/ASME	B/SB-861	25	R56403		130/120 [895/825]	Seamless Pipe	Ti-6Al-4V-Ni-Pd
54	53	ASTM/ASME	B/SB-861	29	R56404		120/110 [825/760]	Seamless Pipe	Ti-6Al-4V-Pd-ELI-Ru
54	53	ASTM/ASME	B/SB-861	35	R56340		130/120 [895/825]	Seamless Pipe	Ti-4Al-2.5V-1.5Fe
54	53	ASTM/ASME	B/SB-861	5	R56400		130/120 [895/825]	Seamless Pipe	Ti-6Al-4V
54	53	ASTM/ASME	B/SB-862	23	R56407		120/110 [825/760]	Welded Pipe	Ti-6Al-4V-ELI
54	53	ASTM/ASME	B/SB-862	24	R56405		130/120 [895/825]	Welded Pipe	Ti-6Al-4V-Pd
54	53	ASTM/ASME	B/SB-862	25	R56403		130/120 [895/825]	Welded Pipe	Ti-6Al-4V-Ni-Pd
54	53	ASTM/ASME	B/SB-862	29	R56404		120/110 [825/760]	Welded Pipe	Ti-6Al-4V-Pd-ELI-Ru
54	53	ASTM/ASME	B/SB-862	35	R56340		130/120 [895/825]	Welded Pipe	Ti-4Al-2.5V-1.5Fe
54	53	ASTM/ASME	B/SB-862	5	R56400		130/120 [895/825]	Welded Pipe	Ti-6Al-4V
54	52	AMS	4915	—	R54810	>0.187 and ≤0.5 [>5 and ≤13]	145/135 [1000/930]	Plate	Ti-8Al-1Mo-1V
54	52	AMS	4915	—	R54810	>2.5 and ≤4 [>65 and ≤100]	120/110 [825/760]	Plate	Ti-8Al-1Mo-1V
54	52	AMS	4915	—	R54810	>1 and ≤2.5 [>25 and ≤65]	130/120 [895/825]	Plate	Ti-8Al-1Mo-1V

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
54	52	AMS	4915	—	R54810	>0.5 and ≤1 [>13 and ≤25]	140/130 [965/895]	Plate	Ti-8Al-1Mo-1V
54	52	AMS	4915	—	R54810	≤0.187 [≤5]	145/135 [1000/930]	Sheet & Strip	Ti-8Al-1Mo-1V
54	52	AMS	4919	—	R54620		135/125 [930/860]	Sheet	Ti-6Al-4Zr-2Mo-2Sn
54	52	AMS	4973	—	R54810	>2.5 and ≤4 [>65 and ≤100]	120/110 [825/760]	Forgings	Ti-8Al-1Mo-1V
54	52	AMS	4973	—	R54810	≤2.5 [≤65]	130/120 [895/825]	Forgings	Ti-8Al-1Mo-1V
54	52	AMS	4975	—	R54620		130/120 [895/825]	Bar	Ti-6Al-4Zr-2Mo-2Sn
54	52	AMS	4976	—	R54620		130/120 [895/825]	Forgings	Ti-6Al-4Zr-2Mo-2Sn

Table C-2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
61	61	ASTM	B351	R60001	R60001	42/20 [290/140]		Bar, Rod, & Wire	99.9Zr
61	61	ASTM	B351	R60802	R60802	60/35 [415/240]		Bar, Rod, & Wire	98Zr-1.45Sn-0.28(Fe+Ni+Cr)
61	61	ASTM	B351	R60804	R60804	60/35 [415/240]		Bar, Rod, & Wire	98.2Zr-1.5Sn-0.32(Fe+Cr)
61	61	ASTM	B353	R60001	R60001	42/20 [290/140]		Plate, Sheet, & Strip	99.9Zr
61	61	ASTM	B352	R60802	R60802	58/35 [400/240]		Plate, Sheet, & Strip	98Zr-1.45Sn-0.28(Fe+Ni+Cr)
61	61	ASTM	B352	R60804	R60804	56/35 [385/240]		Sheet & Strip	98.2Zr-1.5Sn-0.32(Fe+Cr)
61	61	ASTM	B352	R60804	R60804	58/35 [400/240]		Plate	98.2Zr-1.5Sn-0.32(Fe+Cr)
61	61	ASTM	B353	R60001	R60001	42/20 [290/140]		Seamless & Welded Tube	99.9Zr
61	61	ASTM	B353	R60802	R60802	60/35 [415/240]		Seamless & Welded Tube	98Zr-1.45Sn-0.28(Fe+Ni+Cr)
61	61	ASTM	B353	R60804	R60804	60/35 [415/240]		Seamless & Welded Tube	98.2Zr-1.5Sn-0.32(Fe+Cr)
61	61	ASTM/ASME	B/SB-493	R60702	R60702	55/30 [380/205]		Forgings	99.2Zr
61	61	ASTM/ASME	B/SB-523	R60702	R60702	55/30 [380/205]		Seamless & Welded Tube	99.2Zr
61	61	ASTM/ASME	B/SB-550	R60702	R60702	55/30 [380/205]		Bar & Wire	99.2Zr
61	61	ASTM/ASME	B/SB-551	R60702	R60702	55/30 [380/205]		Plate, Sheet, & Strip	99.2Zr
61	61	ASTM/ASME	B/SB-653	R60702	R60702	55/30 [380/205]		Seamless & Welded Fittings	99.2Zr
61	61	ASTM/ASME	B/SB-658	R60702	R60702	55/30 [380/205]		Seamless & Welded Pipe	99.2Zr
62	62	ASTM	B351	R60901	R60901	65/45 [450/310]		Bar, Rod, & Wire	97.3Zr-2.6Cb
62	62	ASTM	B352	R60901	R60901	65/45 [450/310]		Plate, Sheet, & Strip	97.3Zr-2.6Cb
62	62	ASTM	B353	R60901	R60901	65/45 [450/310]		Seamless & Welded Tube	97.3Zr-2.6Cb
62	62	ASTM	B353	R60904	R60904	65/45 [450/310]		Seamless & Welded Tube	97.35Zr-2.65Cb
62	62	ASTM/ASME	B/SB-493	R60704	R60704	60/35 [415/240]		Forgings	97.5Zr-1.55Sn-0.3(Fe+Cr)
62	62	ASTM/ASME	B/SB-493	R60705	R60705	70/55 [485/380]		Forgings	95.5Zr+2.5Cb
62	62	ASTM/ASME	B/SB-523	R60704	R60704	60/35 [415/240]		Seamless & Welded Tube	97.5Zr-1.5Sn-0.3(Fe+Cr)
62	62	ASTM/ASME	B/SB-523	R60705	R60705	80/55 [550/380]		Seamless & Welded Tube	95.5Zr+2.5Cb
62	62	ASTM/ASME	B/SB-550	R60704	R60704	60/35 [415/240]		Bar & Wire	97.5Zr-1.5Sn-0.3(Fe+Cr)
62	62	ASTM/ASME	B/SB-550	R60705	R60705	80/55 [550/380]		Bar & Wire	95.5Zr+2.5Cb
62	62	ASTM/ASME	B/SB-551	R60704	R60704	60/35 [415/240]		Plate, Sheet, & Strip	97.5Zr-1.55Sn-0.3(Fe+Cr)
62	62	ASTM/ASME	B/SB-551	R60705	R60705	80/55 [550/380]		Plate, Sheet, & Strip	95.5Zr+2.5Cb
62	62	ASTM/ASME	B/SB-551	R60706	R60706	74/50 [510/345]		Plate, Sheet, & Strip	95.5Zr+2.5Cb

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
62	62	ASTM/ASME	B/SB-658	R60704	R60704		60/35 [415/240]	Seamless & Welded Pipe	97.5Zr-1.5Sn-0.3(Fe+Cr)
62	62	ASTM/ASME	B/SB-658	R60705	R60705		80/55 [550/380]	Seamless & Welded Pipe	95.5Zr+2.5Cb

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I.2.2.1, and I.3)

Material Number	ISO 15608 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
81	—	ASTM	B90	AZ31B	M11311		32/— [220/—]	Plate & Sheet	95.5Mg-3Al-Zn-Mn
81	—	ASTM	B90	AZ31C	M11312	≥0.06 and ≤3 [≥1.5 and ≤80]	32/15 [220/105]	Plate & Sheet	95.5Mg-3Al-Zn
81	—	ASTM	B90	AZ31C	M11312	≥0.016 and ≤0.06 [≥0.4 and ≤1.5]	32/18 [220/125]	Sheet	95.5Mg-3Al-Zn
81	—	ASTM	B90	HK31A	M13310	≥0.016 and ≤0.5 [≥0.4 and ≤13]	30/16 [205/110]	Plate & Sheet	95.5Mg-3Al-Zn
81	—	ASTM	B90	HK31A	M13310	>0.5 and ≤1 [>13 and ≤25]	30/15 [205/105]	Plate	95.5Mg-3Al-Zn
81	—	ASTM	B90	HK31A	M13310	>1 and ≤3 [>25 and ≤80]	29/14 [200/97]	Plate	95.5Mg-3Al-Zn
81	—	ASTM	B90	ZE10A	M16100	≥0.25 and ≤0.5 [≥6 and ≤13]	29/12 [200/83]	Plate	98Mg-1.25Zn-0.17Re
81	—	ASTM	B90	ZE10A	M16100	≥0.016 and ≤0.06 [≥0.4 and ≤1.5]	30/18 [205/125]	Sheet	98Mg-1.25Zn-0.17Re
81	—	ASTM	B90	ZE10A	M16100	>0.06 and ≤0.25 [>1.5 and ≤6]	30/15 [205/105]	Sheet	98Mg-1.25Zn-0.17Re
81	—	ASTM	B91	AZ31B	M11311		32/15 [220/105]	Forgings	95.5Mg-3Al-Zn-Mn
81	—	ASTM	B91	AZ61A	M11610		35/19 [240/130]	Forgings	92.5Mg-6Al-Zn
81	—	ASTM	B107	AZ31B	M11311	≥0.25 and <1.5 [≥6 and <40]	32/19 [220/130]	Bar, Rods, Profiles, & Wire	95.5Mg-3Al-Zn-Mn
81	—	ASTM	B107	AZ31B	M11311	>0.25 and ≤0.75 [>6 and ≤20]	29/13 [200/90]	Tube	95.5Mg-3Al-Zn-Mn
81	—	ASTM	B107	AZ31B	M11311	≥0.028 and ≤0.25 [≥1 and ≤6]	29/17 [200/115]	Tube	95.5Mg-3Al-Zn-Mn
81	—	ASTM	B107	AZ31B	M11311		29/13 [200/90]	Hollow Profiles	95.5Mg-3Al-Zn-Mn
81	—	ASTM	B107	AZ31B	M11311	≥1.5 and <2.5 [≥40 and <60]	31/19 [215/130]	Bar, Rods, Profiles, & Wire	95.5Mg-3Al-Zn-Mn
81	—	ASTM	B107	AZ31B	M11311	<0.25 [<6]	32/18 [220/125]	Bar, Rods, Profiles, & Wire	95.5Mg-3Al-Zn-Mn
81	—	ASTM	B107	AZ31B	M11311	≥2.5 and <5 [≥60 and <130]	29/17 [200/115]	Bar, Rods, Profiles, & Wire	95.5Mg-3Al-Zn-Mn

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
81	—	ASTM	B107	AZ31C	M11312	≥1.5 and <2.5 [≥40 and <60]	31/19 [215/130]	Bar, Rods, Profiles, & Wire	95.5Mg-3Al-Zn
81	—	ASTM	B107	AZ31C	M11312	>0.25 and ≤0.75 [≥6 and ≤20]	29/13 [200/90]	Tube	95.5Mg-3Al-Zn
81	—	ASTM	B107	AZ31C	M11312	<0.25 [≤6]	32/18 [220/125]	Bar, Rods, Profiles, & Wire	95.5Mg-3Al-Zn
81	—	ASTM	B107	AZ31C	M11312	≥0.25 and <1.5 [≥6 and <40]	32/19 [220/130]	Bar, Rods, Profiles, & Wire	95.5Mg-3Al-Zn
81	—	ASTM	B107	AZ31C	M11312	≥2.5 and <5 [≥60 and <130]	29/17 [200/115]	Bar, Rods, Profiles, & Wire	95.5Mg-3Al-Zn
81	—	ASTM	B107	AZ31C	M11312		29/13 [200/90]	Hollow Profiles	95.5Mg-3Al-Zn
81	—	ASTM	B107	AZ31C	M11312	≥0.028 and ≤0.25 [≥1 and ≤6]	29/17 [200/115]	Tube	95.5Mg-3Al-Zn
81	—	ASTM	B107	AZ61A	M11610		33/13 [230/90]	Hollow Profiles	92.5Mg-6Al-Zn
81	—	ASTM	B107	AZ61A	M11610	≥0.028 and ≤0.75 [≥1 and ≤20]	33/13 [230/90]	Tube	92.5Mg-6Al-Zn
81	—	ASTM	B107	AZ61A	M11610	≥0.25 and <2.5 [≥6 and <60]	37/21 [255/145]	Bar, Rods, Profiles, & Wire	92.5Mg-6Al-Zn
81	—	ASTM	B107	AZ61A	M11610	<0.25 [≤6]	35/18 [240/125]	Bar, Rods, Profiles, & Wire	92.5Mg-6Al-Zn
81	—	ASTM	B107	AZ61A	M11610	≥2.5 and <5 [≥60 and <130]	37/19 [255/130]	Bar, Rods, Profiles, & Wire	92.5Mg-6Al-Zn
81	—	ASTM	B107	M1A	M15100		33/13 [230/90]	Hollow Profiles	98Mg-Mn
81	—	ASTM	B107	M1A	M15100	<0.25 [≤6]	35/18 [240/125]	Bar, Rods, Profiles, & Wire	98Mg-Mn
81	—	ASTM	B107	M1A	M15100	≥0.25 and <2.5 [≥6 and <60]	37/21 [255/145]	Bar, Rods, Profiles, & Wire	98Mg-Mn
81	—	ASTM	B107	M1A	M15100	≥2.5 and <5 [≥60 and <130]	37/19 [255/130]	Bar, Rods, Profiles, & Wire	98Mg-Mn
81	—	ASTM	B107	M1A	M15100	≥0.028 and ≤0.75 [≥1 and ≤20]	33/13 [230/90]	Tube	98Mg-Mn
83	—	ASTM	B80	AZ91C, F	M11914		21/10 [145/69]	Castings	90.5Mg-9Al-Zn-Mn
83	—	ASTM	B80	AZ92A, F	M11920		21/10 [145/69]	Castings	88.5Mg-9Al-2Zn-Mn
83	—	ASTM	B80	K1A	M18010		22/5 [150/34]	Castings	99.6Mg-Zr

(Continued)

Table C.2 (Continued)
M-Number Listing of Base Metals—Nonferrous Alloys (see C.1, I2.2.1, and I3)

Material Number	ISO Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Thickness or Diameter Limitations, in [mm]	Minimum Tensile/Yield Strength, ksi [MPa]	Product Form	Nominal Composition
83	—	ASTM	B199	AM100A	M10100		18/9 [125/62]	Castings	89.5Mg-10Al-Mn
83	—	ASTM	B199	AZ91C, F	M11914		21/10 [145/69]	Castings	90.5Mg-9Al-Zn-Mn
83	—	ASTM	B199	AZ92A, F	M11920		21/10 [145/69]	Castings	88.5Mg-9Al-2Zn-Mn
83	—	ASTM	B403	AM100A, F	M10100		18/9 [125/62]	Castings	89.5Mg-10Al-Mn
83	—	ASTM	B403	AZ91C, F	M11914		16/9 [110/62]	Castings	90.5Mg-9Al-Zn-Mn
83	—	ASTM	B403	AZ92A, F	M11920		18/9 [125/62]	Castings	88.5Mg-9Al-2Zn-Mn
83	—	ASTM	B403	K1A	M18010		22/5 [150/34]	Castings	99.6Mg-Zr

Table C.3
Listing of Base Metal Specifications—Iron Castings

AWS D11.2 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Minimum As-Welded Tensile/Yield Strength, ksi [MPa]	Type of Base Metal	Nominal Composition
Iron Castings^{a, b}							
A	ASTM	A48	Class 20	F11401	20/- [138/-]	Gray Cast Iron	Not Specified
A	ASTM	A48	Class 25	F11701	25/- [172/-]	Gray Cast Iron	Not Specified
A	ASTM	A48	Class 30	F12101	30/- [207/-]	Gray Cast Iron	Not Specified
A	ASTM	A48	Class 35	F12401	35/- [241/-]	Gray Cast Iron	Not Specified
A	ASTM	A48	Class 40	F12801	40/- [276/-]	Gray Cast Iron	Not Specified
A	ASTM	A48	Class 45	F13101	45/- [310/-]	Gray Cast Iron	Not Specified
A	ASTM	A48	Class 50	F13501	50/- [345/-]	Gray Cast Iron	Not Specified
A	ASTM	A48	Class 55	F13801	55/- [379/-]	Gray Cast Iron	Not Specified
A	ASTM	A48	Class 60	F14101	60/- [414/-]	Gray Cast Iron	Not Specified
A	ASTM	A74	Class A	—	21/- [145/-]	Gray Cast Iron	0.75 Max.P, 0.15 Max.S
A	ASTM	A126	Class A	F11501	21/- [145/-]	Gray Cast Iron	0.75 Max.P, 0.15 Max.S
A	ASTM	A126	Class B	F12102	31/- [214/-]	Gray Cast Iron	0.75 Max.P, 0.15 Max.S
A	ASTM	A126	Class C	F12103	41/- [283/-]	Gray Cast Iron	0.75 Max.P, 0.15 Max.S
A	ASTM	A159	Grade 1800	F10004	18/- [124/-]	Gray Cast Iron	0.55Si-0.65Mn; 4.35CE
A	ASTM	A159	Grade 2500	F10005	25/- [172/-]	Gray Cast Iron	2.2 Si-0.75Mn; 4.12CE
A	ASTM	A159	Grade 2500a	F10009	25/- [172/-]	Gray Cast Iron	1.85Si-0.75Mn; 4.12 CE
A	ASTM	A159	Grade 3000	F10006	30/- [207/-]	Gray Cast Iron	2.1Si-0.75Mn; 4.02CE
A	ASTM	A159	Grade 3500	F10007	35/- [241/-]	Gray Cast Iron	2.0Si-0.75Mn; 3.8CE
A	ASTM	A159	Grade 3500b	F10010	35/- [241/-]	Gray Cast Iron	1.55Si-0.75Mn; 3.8CE
A	ASTM	A159	Grade 3500c	F10011	35/- [241/-]	Gray Cast Iron	1.55Si-0.75Mn; 3.8CE
A	ASTM	A159	Grade 4000	F10008	40/- [276/-]	Gray Cast Iron	1.95Si-0.85Mn; 3.8CE
A	ASTM	A159	Grade 4000d	F10012	40/- [276/-]	Gray Cast Iron	1.95Si-0.85Mn; 3.8CE
A	ASTM	A319	Class I	F10001	25/- [172/-]	Gray Cast Iron	Not Specified
A	ASTM	A319	Class II	F10002	30/- [207/-]	Gray Cast Iron	Not Specified
A	ASTM	A319	Class III	F10003	40/- [276/-]	Gray Cast Iron	Not Specified
A	SAE	J431	G1800	F10004	18/- [124/-]	Gray Cast Iron	2.3Si-0.65Mn; 4.35CE
A	SAE	J431	G2500	F10005	25 [172]	Gray Cast Iron	2.3Si-0.75Mn; 4.12CE
A	SAE	J431	G3000	F10006	30 [207]	Gray Cast Iron	2.1Si-0.65Mn; 4.02CE
A	SAE	J431	G3500	F10007	35 [241]	Gray Cast Iron	2.0Si-0.75Mn; 3.8CE
A	SAE	J431	G4000	F10008	40 [276]	Gray Cast Iron	1.95Si-0.95Mn; 3.8CE
B	ASTM	A536	100-70-03	F34800	100/70 [689/483]	Ductile	Not Specified
B	ASTM	A536	120-90-02	F36200	120/90 [827/621]	Ductile	Not Specified
B	ASTM	A536	60-40-18	F32800	60/40 [414/276]	Ductile	Not Specified
B	ASTM	A536	65-45-12	F33100	65/42 [448/290]	Ductile	Not Specified
B	ASTM	A536	80-55-06	F33800	80/55 [552/379]	Ductile	Not Specified
B	ASTM	A716	60-42-10	F32900	60/- [414/-]	Ductile	Not Specified
B	ASTM	A746	60-42-10	—	60/- [414/-]	Ductile	Not Specified
B	ASTM	A874	—	—	45/30 [310/207]	Ductile	3.35C-1.75Si
B	ASTM	A897	125-80-10	—	125/80 [862/552]	Ductile	1.0Ni-0.5Cu-0.35Mn-0.015Mo
B	SAE	J434	D4018	F32800	60/- [414/-]	Ductile	Not Specified

Table C.3 (Continued)
Listing of Base Metal Specifications—Iron Castings

AWS D11.2 Group	Standard	Base Metal Specification	Type, Grade, or Alloy Designation	UNS Number	Minimum As-Welded Tensile/Yield Strength, ksi [MPa]	Type of Base Metal	Nominal Composition
Iron Castings^{a, b}							
B	SAE	J434	D4512	F33100	65/- [448/-]	Ductile	Not Specified
B	SAE	J434	D5506	F33800	80/- [552/-]	Ductile	Not Specified
B	SAE	J434	D7003	F34800	100/- [689/-]	Ductile	Not Specified
C	ASTM	A47	32510	F22200	50/- [345/-]	Malleable	Not Specified
C	ASTM	A47	35018	F22400	53/- [365/-]	Malleable	Not Specified
C	ASTM	A197	—	F22200	40/- [276/-]	Malleable	Not Specified
C	ASTM	A220	40010	F22830	60/- [414/-]	Malleable	Not Specified
C	ASTM	A220	45006	F23131	65/- [448/-]	Malleable	Not Specified
C	ASTM	A220	45008	F23130	65/- [448/-]	Malleable	Not Specified
C	ASTM	A220	50005	F23530	70/- [483/-]	Malleable	Not Specified
C	ASTM	A220	60004	F24130	80/- [552/-]	Malleable	Not Specified
C	ASTM	A220	70003	F24830	85/- [586/-]	Malleable	Not Specified
C	ASTM	A220	80002	F25530	95/- [655/-]	Malleable	Not Specified
C	ASTM	A220	90001	F26230	105/- [724/-]	Malleable	Not Specified
C	ASTM	A602	M3210	F20000	50/- [345/-]	Malleable	Not Specified
C	ASTM	A602	M4504	F20000	65/- [448/-]	Malleable	Not Specified
C	ASTM	A602	M5003	F20000	75/- [517/-]	Malleable	Not Specified
C	SAE	J158a	M3210	F20000	50/- [345/-]	Malleable	Not Specified
C	SAE	J158a	M4504	F20001	65/- [448/-]	Malleable	Not Specified

^a In the absence of an M number to group the alloys, a separate procedure qualification is required for each group of the above materials.

^b The groups are based on AWS D11.2.

This page is intentionally blank.

