

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING
OF DIAMOND AND COLORED STONES
EDUCATIONAL PROGRAMS

## **ELECTRONIC COPY**

## DIAMOND REPORT

This report is a statement of the diamond's identity and grade including all relevant information.

NUMBER 171557209

ANTWERP, August 26, 2015

## LABORATORY REPORT (ORIGINAL)

TO WHOM IT MAY CONCERN.

DESCRIPTION
SHAPE AND CUT
CARAT WEIGHT
Measurements
CLARITY GRADE
COLOR GRADE

Fluorescence

**FINISH** 

Proportions

Table Size

Crown Height - Angle

Polish - Symmetry

Pavilion Depth - Angle
Girdle Thickness

Culet


NATURAL DIAMOND
CUSHION BRILLIANT
1.00 CARAT
6.34 x 5.53 x 3.31 mm
SI 2
I
NONE


GOOD
GOOD
65.5%
14.5% - 38.8°
42.5% - 32.4°
MEDIUM TO VERY THICK (FACETED)
POINTED

The symbols do not usually reflect the size of the characteristics.

Red symbols indicate internal characteristics.

Green symbols indicate external characteristics.





insignificant **external** details, visible under high magnification only, are not shown



O-m Security features included in this document are hologram, watermarked paper and additional features not listed, that, as a composite, exceed industry security standards.



CLARITY GRADE: Internally Flawl			Flawle	ess	VVS <sub>1</sub>			vvs <sub>2</sub>		VS <sub>1</sub>		vs <sub>2</sub>		SI	2	I <sub>1</sub>	12	l <sub>3</sub>
COLOR GRADE :	D	E	F	G	Н	ı	J	K	L	М	Ν	0	P	Q	R	S-Z	FANCY C	COLOR

PROPORTIONS - MARGIN: ± 1%
MEASUREMENTS - MARGIN: ± 0.02mm

The gemological analysis of diamonds, precious stones and other minerals must be carried out by gemologists with many years experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomenon.

The identification of the various species and varieties of stones, the distinction between natural and synthetic material, as well as various treatment methods currently encountered are all very sensitive factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemological report is provided upon request of the customer and/or the owner of the gem. By making this report I.G.I. does not agree to purchase or replace the article. Neither I.G.I. nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a guaranty or warranty.

This report is subject to the terms and conditions set forth above and on reverse.

© I.G.I., 2000, edition 2010

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute