

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING OF DIAMOND AND COLORED STONES **EDUCATIONAL PROGRAMS** 

## **ELECTRONIC COPY**

## DIAMOND REPORT

This report is a statement of the diamond's identity and grade including all relevant information.

NUMBER 201632661

ANTWERP, February 25, 2016

LABORATORY REPORT (ORIGINAL)

TO WHOM IT MAY CONCERN.

**DESCRIPTION** SHAPE AND CUT

**CARAT WEIGHT COLOR GRADE CLARITY GRADE CUT GRADE** 

**POLISH SYMMETRY** 

Measurements

Table Size

Crown Height - Angle Pavilion Depth - Angle

Girdle Thickness

Culet

**FLUORESCENCE** 

**LASERSCRIBE** 

NATURAL DIAMOND **ROUND BRILLIANT** 

**1.09 CARAT** 

J

SI<sub>1</sub>

**VERY GOOD** 

GOOD

GOOD

6.43 - 6.48 x 4.15 mm

59.5%

14.5% - 35.7°

44.5% - 41.7°


MEDIUM TO THICK

SMALL NATURAL

STRONG

IGI 201632661

The symbols do not usually reflect the size of the characteristics. Red symbols indicate internal characteristics. Green symbols indicate external characteristics.



insignificant external details, visible under high magnification only, are not shown



O-m Security features included in this document are hologram, watermarked paper and additional features not listed, that, as a composite, exceed industry security standards.



CLARITY GRADE: Internally Flawl			Flawle	ess	VVS <sub>1</sub>			vvs <sub>2</sub>		VS <sub>1</sub>		vs <sub>2</sub>		SI	2	I <sub>1</sub>	12	l <sub>3</sub>
COLOR GRADE :	D	E	F	G	Н	ı	J	K	L	М	Ν	0	P	Q	R	S-Z	FANCY C	COLOR

PROPORTIONS - MARGIN: ± 1% MEASUREMENTS - MARGIN: ± 0.02mm

The gemological analysis of diamonds, precious stones and other minerals must be carried out by gemologists with many years experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomenon.

The identification of the various species and varieties of stones, the distinction between natural and synthetic material, as well as various treatment methods currently encountered are all very sensitive factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemological report is provided upon request of the customer and/or the owner of the gem. By making this report I.G.I. does not agree to purchase or replace the article. Neither I.G.I. nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a guaranty or warranty.

This report is subject to the terms and conditions set forth above and on reverse.

© I.G.I., 2000, edition 2010

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute