



Dow ELVAX™ EVA copolymers are used in many applications including flexible packaging, thermal-lamination film, photovoltaic cells, foams, hose & tube, footwear, toys, wire & cable compounds, concentrates, athletic goods and hot-melt adhesives. Dow ELVAX™ EVA copolymers add toughness and flexibility to industrial, consumer and packaging applications.

Industrial & Consumer Grades

GRADE	VINYL ACETATE (%)	MELT INDEX (dg/min.)	DENSITY (g/cm ³)	MELTING POINT (°C)
750	9	7	0.930	98
760	9.3	2	0.930	100
770	9.5	0.8	0.930	96
650Q	12	8	0.933	95
660	12	2.5	0.933	96
670	12	0.35	0.933	95
550	15	8	0.935	85
440	18	30	0.927	84
460	18	2.5	0.941	88
470	18	0.7	0.941	89
350	25	19	0.948	74
360	25	2	0.948	78
4310	25	500	0.945	66
4320	25	150	0.947	70

GRADE	VINYL ACETATE (%)	MELT INDEX (dg/min.)	DENSITY (g/cm ³)	MELTING POINT (°C)
4355	25	6	0.952	76
240W	28	43	0.951	74
250	28	25	0.950	70
260	28	6	0.955	75
265	28	3	0.951	73
4260	28	6	0.955	72
CM4875	28	5	0.954	70
CM576	28	0.7	0.950	71
150	32	43	0.957	63
150W	32	43	0.957	63
CM3326	33	5	0.955	60
40L-03	40	3	0.967	58
40W	40	52	0.965	47

®™ Trademark of The Dow Chemical Company (“Dow”) or an affiliated company of Dow

Film & Packaging Grades

GRADE	VINYL ACETATE (%)	MELT INDEX (dg/min.)	DENSITY (g/cm ³)	MELTING POINT (°C)
3120	7.5	1.2	0.930	99
3150	15	2.5	0.940	92
3165	18	0.7	0.940	89
3169Z	18	1.5	0.950	89
3170SHB	18	2.5	0.940	87
3174	18	8	0.940	86
3174SHB	18	8	0.940	87
3200-2	22.5	32	0.940	71
3190	25	2	0.950	77
3175	28	6	0.950	73
3180	28	25	0.950	70
3180Z	28	25	0.950	70
3182	28	3	0.950	73
3185	32	43	0.960	61
CE9619-1*	13.1	3.8	1.060	87

* Concentrate containing 7% slip and 20% anti-block

Common Applications

- Flexible Packaging
- Thermal-Lamination Film
- Photovoltaic Cells
- Foams
- Concentrates & Hot-Melt Adhesives
- Hose & Tube
- Footwear
- Toys
- Wire & Cable Compounds
- Athletic Goods

®™ Trademark of The Dow Chemical Company (“Dow”) or an affiliated company of Dow