

TexTesT Report: 1273246 2
Date: 3/24/15
Page: 1CLIENT: **TENTCRAFT**
2322 Cass Road
Taverse City, MI 49684

ATTN: Thomas ShimekSAMPLE IDENTIFICATION: Black Coated Woven Fabric
Order: 1787

FLAMMABILITY


NFPA 701 (2010) TEST 2

FOLDS

		After Flame (Seconds)	Char Length (mm)	Drip Burn (Seconds)	
SPECIMEN *	#1	0.0	230.0	0.0	
	#2	0.0	240.0	0.0	
	#3	0.0	185.0	0.0	
	#4	0.0	230.0	0.0	PASS

* Specimens were conditioned at least 24 hours at 20±5°C before testing.

CRITERIA: PASS/FAIL

REQUIREMENTS: CHAR: 1050 mm Maximum Individual
DRIP BURN: 2 Seconds Maximum Individual
AFTER FLAME: 2 Seconds Maximum IndividualCOMMENTS: The submitted sample passes the requirements of NFPA 701 (2010)
Test 2 Flammability.**TEXTTEST**

signed by